

WisDOT Pit and Quarry Listing for Use in 2024.

Acceptable “**Pit**” sources are those tested in 2020 to 2024.

Acceptable “**Quarry**” sources are those tested in 2022 to 2024.

All source test data (both satisfactory and non-satisfactory) is shown, please check source data to ensure source meets specification requirements for the intended usage.

Certified sources expire at end of allocated calendar years.

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
* 175 WEST 55-20-054-QRY Created On: 07/15/20 Updated On:	Q	NE	SW	10	14N	17E	Fond Du Lac	0-225-214-2020	0.0	4.9	1.4	7.7	32.8	2.724	2.757	1.200	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
* 19TH HOLE (BURGESS) 55-25-001-QRY Created On: 03/23/17 Updated On:	Q	SE	SW	15	5N	3E	Iowa	0-225-88-2017	1.7	6.2	9.7	10.0	36.9	2.536	2.629	3.681	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
* 19TH HOLE (BURGESS) 55-25-001-QRY Created On: 07/15/20 Updated On:	Q	SE	SW	15	5N	3E	Iowa	0-225-217-2020	1.3	4.7	10.0	8.0	32.9	2.543	2.628	3.350	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
* 3M 55-37-001-QRY Created On: 08/14/14 Updated On:	Q	NW	SE	11	29N	7E	Marathon	0-225-242-2014		0.0	2.5	3.7	16.2	2.812	2.833	0.760	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
* 3M 55-37-001-QRY Created On: 09/19/19 Updated On:	Q	NW	SE	11	29N	7E	Marathon	0-225-272-2019	0.6	0.0	0.7	4.7	20.5	2.644	2.679	1.338	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
A TO Z AGGREGATE SOLUTIONS 55-51-001-PIT Created On: 01/23/17 Updated On:	P		SW	3	3N	19E	Racine	0-225-56-2017	1.9	2.4	1.7	7.0	35.6	2.694	2.732	1.394	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
A TO Z AGGREGATE SOLUTIONS 55-51-001-PIT Created On: 01/05/21 Updated On:	P		SW	3	3N	19E	Racine	0-225-80-2021	0.0	8.4	5.3	4.4	23.6	2.680	2.720	1.503	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
A-FRAME 55-43-001-PIT Created On: 05/12/16 Updated On:	P	NE	NE	22	37N	6E	Oneida	0-225-169-2016		0.0	0.3	4.6	20.3	2.681	2.712	1.169		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
A-FRAME 55-43-001-PIT Created On: 01/08/20 Updated On:	P	NE	NE	22	37N	6E	Oneida	0-225-49-2020	1.5	0.0	1.9	4.0	18.6	2.724	2.737	0.483		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
ABNET 27-00-008-QRY Created On: 06/26/14 Updated On:	Q			2	104N	5W	Houston	0-225-204-2014		1.9	2.3	10.4	35.2	2.590	2.649	2.276		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
ABNET 27-00-008-QRY Created On: 05/04/17 Updated On:	Q			2	104N	5W	Houston	0-225-170-2017	0.8	2.2	4.8	8.1	32.9	2.644	2.690	1.769		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
ABNET 27-00-008-QRY Created On: 02/03/20 Updated On:	Q			2	104N	5W	Houston	0-225-108-2020	2.4	1.0	4.1	8.0	33.1	2.617	2.672	2.083		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
ABNET 27-00-008-QRY Created On: 01/03/23 Updated On:	Q			2	104N	5W	Houston	0-225-66-2023	0.9	1.3	3.2	9.8	37.1	2.599	2.658	2.268		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
ADAMETZ 55-22-001-QRY Created On: 05/23/14 Updated On:	Q	SE	SE	11	6N	1W	Grant	0-225-170-2014	1.6	2.1	4.1	8.0	31.3	2.613	2.668	2.133		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
ADAMETZ 55-22-001-QRY Created On: 01/05/17 Updated On:	Q	SE	SE	11	6N	1W	Grant	0-225-29-2017	0.3	5.4	4.1	8.5	34.9	2.631	2.680	1.878		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
ADAMETZ 55-22-001-QRY Created On: 01/04/19 Updated On:	Q	SE	SE	11	6N	1W	Grant	0-225-27-2019	1.2	7.9	7.2	12.6	40.8	2.608	2.665	2.185		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
ADAMETZ 55-22-001-QRY Created On: 01/04/22 Updated On:	Q	SE	SE	11	6N	1W	Grant	0-225-52-2022	1.1	5.0	2.7	8.0	29.5	2.644	2.693	1.825		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
AGGRECON 55-36-001-QRY Created On: 06/03/15 Updated On:	Q		SE	33	17N	21E	Manitowoc	0-225-182-2015	1.5	0.0	1.4	7.6	32.9	2.719	2.751	1.152		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
AGGRECON 55-36-001-QRY Created On: 02/15/18 Updated On:	Q		SE	33	17N	21E	Manitowoc	0-225-99-2018	0.9	3.3	2.7	6.6	32.2	2.745	2.770	0.917		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
AGGRECON 55-36-001-QRY Created On: 01/04/21 Updated On:	Q		SE	33	17N	21E	Manitowoc	0-225-43-2021	0.3	1.2	0.3	5.3	25.5	2.764	2.785	0.755		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
AGGRECON 55-36-001-QRY Created On: 01/29/24 Updated On:	Q		SE	33	17N	21E	Manitowoc	0-225-166-2024	0.0	0.9	1.2	6.4	29.4	2.780	2.799	0.659		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
* AINSWORTH 55-34-001-PIT Created On: 07/31/14 Updated On:	P	SW	SW	1	33N	12E	Langlade	0-225-234-2014		0.0	1.7	3.7	16.9	2.690	2.715	0.919		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
* AINSWORTH 55-34-001-PIT Created On: 01/04/19 Updated On:	P	SW	SW	1	33N	12E	Langlade	0-225-13-2019	0.0	0.0	0.2	5.3	22.9	2.693	2.709	0.613		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
* ALT 55-56-033-QRY Created On: 06/02/20 Updated On:	Q			12	9N	3E	Sauk	0-225-183-2020	1.2	0.0	8.5	10.9	37.6	2.574	2.644	2.715		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
ALVA MILLER 55-52-001-QRY Created On: 06/30/16 Updated On:	Q			17	9N	2W	Richland	0-225-219-2016		0.0	2.2	7.3	30.3	2.692	2.727	1.299		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
ALVA MILLER 55-52-001-QRY Created On: 06/20/22 Updated On:	Q			17	9N	2W	Richland	0-225-232-2022	1.2	1.6	1.1	7.9	32.9	2.680	2.718	1.430		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
AMERICAN MATERIALS #31 55-18-003-PIT Created On: 01/05/17 Updated On:	P	N	NE	2	26N	10W	Eau Claire	0-225-32-2017		0.0	2.9	4.4	20.9	2.635	2.666	1.171		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
AMERICAN MATERIALS #31 55-18-003-PIT Created On: 01/04/21 Updated On:	P	N	NE	2	26N	10W	Eau Claire	0-225-36-2021	1.1	5.4	5.7	4.1	20.2	2.638	2.668	1.166		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
AMON / WILSON 55-64-002-PIT Created On: 06/30/17 Updated On:	P	NE	SE	25	3N	18E	Walworth	0-225-226-2017		0.0	0.9	7.4	37.2	2.669	2.708	1.467		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
AMON / WILSON 55-64-002-PIT Created On: 04/05/22 Updated On:	P	NE	SE	25	3N	18E	Walworth	0-225-169-2022	0.9	0.0	4.5	4.8	26.5	2.680	2.720	1.491		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
ANTIGO 55-34-002-PIT Created On: 01/06/14 Updated On:	P	SE	NE	13	31N	11E	Langlade	0-225-21-2014		0.0	0.5	4.6	22.0	2.679	2.697	0.693		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
ANTIGO 55-34-002-PIT Created On: 01/04/19 Updated On:	P	SE	NE	13	31N	11E	Langlade	0-225-15-2019	0.0	0.7	1.4	7.8	32.6	2.650	2.672	0.802		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
ANTIGO 55-34-002-PIT Created On: 01/02/24 Updated On:	P	SE	NE	13	31N	11E	Langlade	0-225-11-2024	0.2	0.0	0.2	6.6	27.5	2.676	2.695	0.719		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
ANTZCAK TRUCKING POLK LIME QUARRY 55-48-034-QRY Created On: 03/17/21 Updated On:	Q	NW	NE	10	32N	18W	Polk	0-225-153-2021	2.3	0.0	6.4	9.7	36.0	2.552	2.637	3.334		
	Approved Use : Base Aggregate																	
ANTZCAK TRUCKING POLK LIME QUARRY 55-48-034-QRY Created On: 10/14/21 Updated On:	Q	NW	NE	10	32N	18W	Polk	0-225-269-2021	5.3	0.0	15.1	12.3	44.9	2.509	2.604	3.803		
	Approved Use : Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Coarse Sp. Gravity		Coarse Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
ANTZCAK TRUCKING POLK LIME QUARRY 55-48-034-QRY Created On: 01/13/22 Updated On:	Q	NW	NE	10	32N	18W	Polk	0-225-113-2022	2.4	0.0	8.8	9.2	38.0	2.529	2.621	3.641	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
* APPEL 55-33-002-QRY Created On: 04/23/15 Updated On:	Q	NW	SW	11	1N	3E	Lafayette	0-225-132-2015	0.2	0.4	3.5	10.1	38.7	2.635	2.686	1.954	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
* APPEL 55-33-002-QRY Created On: 01/04/18 Updated On:	Q	NW	SW	11	1N	3E	Lafayette	0-225-70-2018	0.5	8.4	4.5	12.6	42.9	2.575	2.643	2.644	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
* APPEL 55-33-002-QRY Created On: 01/05/21 Updated On:	Q	NW	SW	11	1N	3E	Lafayette	0-225-61-2021	0.8	3.1	5.0	11.2	39.6	2.619	2.677	2.213	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
ARCADIA 55-61-003-QRY Created On: 01/16/14 Updated On:	Q	NW	SE	16	20N	9W	Trempealeau	0-225-50-2014		0.0	10.4	11.3	41.6	2.563	2.631	2.648	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
ARCADIA 55-61-003-QRY Created On: 04/25/17 Updated On:	Q	NW	SE	16	20N	9W	Trempealeau	0-225-150-2017		0.0	2.3	12.5	43.4	2.536	2.613	3.068	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
ARCADIA 55-61-003-QRY Created On: 06/02/20 Updated On:	Q	NW	SE	16	20N	9W	Trempealeau	0-225-185-2020	0.8	0.0	4.5	8.6	37.7	2.554	2.635	3.170	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
ARCADIA 55-61-003-QRY Created On: 01/03/23 Updated On:	Q	NW	SE	16	20N	9W	Trempealeau	0-225-64-2023	1.8	0.8	3.6	10.6	42.9	2.548	2.614	2.607	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
ARLINGTON 55-11-002-PIT Created On: 05/04/17 Updated On:	P			23	10N	9E	Columbia	0-225-166-2017	2.4	0.0	4.2	5.7	26.4	2.674	2.724	1.863	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
ARLINGTON 55-11-002-PIT Created On: 06/01/22 Updated On:	P			23	10N	9E	Columbia	0-225-210-2022	1.7	0.0	4.8	5.4	26.5	2.705	2.746	1.502	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
ASHTON 55-22-003-QRY Created On: 06/30/16 Updated On:	Q	SW	SW	26	4N	3W	Grant	0-225-218-2016		3.6	1.1	12.3	42.2	2.588	2.663	2.893	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
ASHTON 55-22-003-QRY Created On: 01/07/19 Updated On:	Q	SW	SW	26	4N	3W	Grant	0-225-52-2019	0.4	9.8	2.8	14.0	45.7	2.570	2.646	2.946	
	Approved Use : CONCRETE, Base Aggregate																
ASHTON 55-22-003-QRY Created On: 04/05/23 Updated On:	Q	SW	SW	26	4N	3W	Grant	0-225-189-2023	0.4	9.2	9.4	12.3	42.9	2.591	2.662	2.716	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
ASPHALT CONTRACTORS JEFFERSON 55-28-019-PIT Created On: 01/08/21 Updated On:	P		NE	3	6N	13E	Jefferson	0-225-117-2021	2.3	3.8	0.8	8.6	35.4	2.634	2.681	1.789	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
ATHENS 55-37-005-QRY Created On: 08/16/16 Updated On:	Q	S	SE	24	30N	4E	Marathon	0-225-243-2016		0.0	0.2	5.1	24.8	2.695	2.710	0.573		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
ATHENS 55-37-005-QRY Created On: 05/10/18 Updated On:	Q	S	SE	24	30N	4E	Marathon	0-225-203-2018		0.0	0.2	3.0	16.1	2.837	2.845	0.255		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
ATHENS 55-37-005-QRY Created On: 01/05/21 Updated On:	Q	S	SE	24	30N	4E	Marathon	0-225-87-2021	0.0	0.0	0.6	4.8	23.1	2.711	2.724	0.492		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
ATHENS 55-37-005-QRY Created On: 01/02/24 Updated On:	Q	S	SE	24	30N	4E	Marathon	0-225-81-2024	0.0	0.0	0.3	5.4	25.3	2.708	2.718	0.397		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
ATKINSON 55-64-005-PIT Created On: 01/18/19 Updated On:	P	NE	SW	6	3N	18E	Walworth	0-225-87-2019	4.6	4.2	0.7	5.1	26.3	2.681	2.717	1.342		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
ATKINSON 55-64-005-PIT Created On: 01/02/24 Updated On:	P	NE	SW	6	3N	18E	Walworth	0-225-15-2024	0.4	4.9	2.9	5.0	25.8	2.668	2.704	1.323		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
BADGERLAND 55-36-031-PIT Created On: 05/01/14 Updated On:	P			33	21N	23E	Manitowoc	0-225-156-2014	3.6	0.0	0.0	7.0	33.1	2.698	2.739	1.504		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
BADGERLAND 55-36-031-PIT Created On: 01/25/19 Updated On:	P			33	21N	23E	Manitowoc	0-225-93-2019	1.8	0.0	3.5	5.9	29.5	2.697	2.738	1.535	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
BADGERLAND 55-36-031-PIT Created On: 02/28/24 Updated On:	P			33	21N	23E	Manitowoc	0-225-170-2024	4.2	0.0	2.5	6.5	30.4	2.719	2.753	1.245	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
BADGERLAND - LARABEE 55-36-033-QRY Created On: 04/24/19 Updated On:	Q			33	21N	23E	Manitowoc	0-225-166-2019	0.0	0.0	3.7	6.5	29.6	2.743	2.764	0.768	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
BADGERLAND - LARABEE 55-36-033-QRY Created On: 01/04/22 Updated On:	Q			33	21N	23E	Manitowoc	0-225-63-2022	3.7	0.0	5.3	8.1	34.8	2.661	2.711	1.890	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
BADGERLAND BISON 55-59-003-PIT Created On: 01/04/16 Updated On:	P	SW	NE	19	15N	20E	Sheboygan	0-225-5-2016	2.0	0.7	0.9	5.9	29.2	2.744	2.770	0.961	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
BADGERLAND BISON 55-59-003-PIT Created On: 03/10/21 Updated On:	P	SW	NE	19	15N	20E	Sheboygan	0-225-132-2021	2.0	2.8	2.8	6.5	31.6	2.735	2.765	1.079	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
BADGERLAND X PIT 55-36-039-PIT Created On: 08/28/18 Updated On:	P		SW	9	17N	22E	Manitowoc	0-225-278-2018	0.1	0.0	1.3	6.0	27.5	2.774	2.799	0.870	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
BADGERLAND X PIT 55-36-039-PIT Created On: 03/21/23 Updated On:	P		SW 9	17N	22E	Manitowoc	0-225-172-2023	0.8	0.0	2.9	6.3	30.2	2.763	2.790	0.948		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
BADGERLAND-SHOTO 55-36-005-QRY Created On: 01/21/16 Updated On:	Q	SE	SW 20	20N	24E	Manitowoc	0-225-67-2016	0.8	1.1	1.2	8.0	32.1	2.798	2.817	0.704		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
BADGERLAND-SHOTO 55-36-005-QRY Created On: 01/25/19 Updated On:	Q	SE	SW 20	20N	24E	Manitowoc	0-225-92-2019		0.0	4.1	8.5	32.5	2.746	2.781	1.284		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
BADGERLAND-SHOTO 55-36-005-QRY Created On: 01/04/22 Updated On:	Q	SE	SW 20	20N	24E	Manitowoc	0-225-67-2022	0.0	0.0	8.5	7.9	32.3	2.785	2.806	0.771		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
BAILEYS HARBOR 55-15-001-QRY Created On: 01/21/16 Updated On:	Q	SW	NW 17	30N	28E	Door	0-225-73-2016	4.5	0.0	4.4	7.7	33.0	2.631	2.687	2.132		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
BAILEYS HARBOR 55-15-001-QRY Created On: 04/13/17 Updated On:	Q	SW	NW 17	30N	28E	Door	0-225-130-2017	1.3	0.0	2.9	7.6	32.6	2.637	2.692	2.074		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
BAILEYS HARBOR 55-15-001-QRY Created On: 01/02/20 Updated On:	Q	SW	NW 17	30N	28E	Door	0-225-6-2020		0.0	1.4	6.6	30.3	2.548	2.605	2.233		
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
BAILEYS HARBOR 55-15-001-QRY Created On: 01/03/23 Updated On:	Q	SW	NW	17	30N	28E	Door	0-225-38-2023	0.2	3.9	1.3	6.0	26.9	2.742	2.773	1.137		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
* BAKER 55-22-065-QRY Created On: 06/17/21 Updated On:	Q	NE	NE	35	4N	2W	Grant	0-225-224-2021	0.5	8.2	11.6	15.3	48.3	2.557	2.638	3.177		
	Approved Use : CONCRETE, OGBC, Base Aggregate																	
BAKKESTUEN / COON VALLEY 55-62-002-PIT Created On: 06/12/17 Updated On:	Q	NW	NW	22	14N	5W	Vernon	0-225-211-2017		0.0	1.7	9.7	36.4	2.646	2.694	1.843		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
BAKKESTUEN / COON VALLEY 55-62-002-PIT Created On: 01/10/22 Updated On:	Q	NW	NW	22	14N	5W	Vernon	0-225-107-2022	0.7	1.3	0.3	11.4	35.8	2.639	2.687	1.788		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
BALFANZ 55-56-001-QRY Created On: 07/16/15 Updated On:	Q	NE	NE	14	10N	5E	Sauk	0-225-211-2015		0.0	3.8	9.0	42.8	2.557	2.628	2.758		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
BALFANZ 55-56-001-QRY Created On: 01/03/18 Updated On:	Q	NE	NE	14	10N	5E	Sauk	0-225-24-2018	0.7	6.7	8.1	12.8	45.6	2.527	2.607	3.151		
	Approved Use : HMA<MT, CONCRETE, Base Aggregate																	
BALFANZ 55-56-001-QRY Created On: 04/06/21 Updated On:	Q	NE	NE	14	10N	5E	Sauk	0-225-171-2021	0.6	1.4	1.3	10.9	41.1	2.597	2.655	2.257		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
BALFANZ 55-56-001-QRY Created On: 01/02/24 Updated On:	Q	NE	NE	14	10N	5E	Sauk	0-225-70-2024	0.3	1.7	2.0	11.6	42.5	2.574	2.635	2.381		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
BALLWEG 55-11-003-QRY Created On: 01/21/16 Updated On:	Q		SE	25	10N	7E	Columbia	0-225-63-2016	0.8	1.1	1.0	7.2	30.7	2.590	2.656	2.547		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
BALLWEG 55-11-003-QRY Created On: 04/01/19 Updated On:	Q		SE	25	10N	7E	Columbia	0-225-119-2019	0.9	3.4	5.8	8.7	33.7	2.615	2.669	2.090		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
BALLWEG 55-11-003-QRY Created On: 01/04/22 Updated On:	Q		SE	25	10N	7E	Columbia	0-225-57-2022	0.8	1.3	3.0	7.7	30.0	2.618	2.672	2.065		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
BARNES 55-04-001-QRY Created On: 05/08/15 Updated On:	Q	NW	NE	21	44N	9W	Bayfield	0-225-157-2015		0.0	7.1	3.9	15.4	2.874	2.891	0.570		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
BARNES 55-04-001-QRY Created On: 01/03/18 Updated On:	Q	NW	NE	21	44N	9W	Bayfield	0-225-18-2018	0.2	0.0	3.9	2.8	12.6	2.854	2.881	0.943		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
BARNES 55-04-001-QRY Created On: 05/06/21 Updated On:	Q	NW	NE	21	44N	9W	Bayfield	0-225-203-2021	0.1	1.2	2.9	2.5	11.1	2.884	2.907	0.802		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
BARNES 55-04-001-QRY Created On: 01/02/24 Updated On:	Q	NW	NE	21	44N	9W	Bayfield	0-225-93-2024	0.1	6.2	11.3	4.6	18.3	2.804	2.844	1.422		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
BATES RD PIT 55-59-024-PIT Created On: 02/17/22 Updated On:	P	E	SE	33	14N	21E	Sheboygan	0-225-129-2022	0.1	2.5	3.2	10.0	38.5	2.715	2.749	1.239		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
BATTERMAN 55-20-050-QRY Created On: 02/03/17 Updated On:	Q	SW	SW	11	14N	17E	Fond Du Lac	0-225-60-2017		0.6	1.4	9.1	40.8	2.696	2.725	1.060		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
BATTERMAN 55-20-050-QRY Created On: 03/02/20 Updated On:	Q	SW	SW	11	14N	17E	Fond Du Lac	0-225-116-2020	0.2	0.5	2.1	8.2	34.7	2.753	2.775	0.821		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
BATTERMAN 55-20-050-QRY Created On: 01/04/23 Updated On:	Q	SW	SW	11	14N	17E	Fond Du Lac	0-225-101-2023	0.0	3.0	1.2	6.5	28.9	2.794	2.808	0.508		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
BAUMEISTER 55-51-005-PIT Created On: 03/24/16 Updated On:	P		NW	19	2N	19E	Racine	0-225-112-2016		0.0	3.2	5.7	25.5	2.632	2.672	1.516		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
BAUMEISTER 55-51-005-PIT Created On: 01/05/21 Updated On:	P		NW	19	2N	19E	Racine	0-225-83-2021	0.0	0.0	5.1	4.8	25.6	2.671	2.712	1.544		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
BAY SETTLEMENT 55-05-012-QRY Created On: 05/17/22 Updated On:	Q		5	24N	22E	Brown		0-225-208-2022	1.8	4.9	1.2	10.5	35.4	2.655	2.711	2.090	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
BEAVER 55-38-003-QRY Created On: 03/07/14 Updated On:	Q	NE	NE	26	31N	20E	Marinette	0-225-94-2014		1.0	3.1	6.3	27.4	2.726	2.758	1.181	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
BEAVER 55-38-003-QRY Created On: 06/13/22 Updated On:	Q	NE	NE	26	31N	20E	Marinette	0-225-223-2022	5.6	10.7	5.8	10.6	37.9	2.627	2.679	1.973	
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																
BECKER 55-11-004-PIT Created On: 01/07/16 Updated On:	P		SW	34	13N	10E	Columbia	0-225-42-2016		0.0	2.0	6.8	29.1	2.658	2.707	1.856	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
BECKER 55-11-004-PIT Created On: 01/05/21 Updated On:	P		SW	34	13N	10E	Columbia	0-225-79-2021	0.0	2.9	2.9	5.6	26.3	2.686	2.732	1.714	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
BEECHER 55-38-004-PIT Created On: 07/26/23 Updated On:	P	NW	NE	20	36N	21E	Marinette	0-225-239-2023		1.1	0.0	6.2	27.3	2.716	2.745	1.072	
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																
BEECHWOOD 26-00-013-PIT Created On: 06/11/20 Updated On:	P	NE	NW	1	43N	36W	Iron	0-225-193-2020	0.0	2.0	0.3	3.0	15.8	2.734	2.752	0.676	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
BEN CARRIE 55-70-001-QRY Created On: 01/06/14 Updated On:	Q	NW	SW	29	20N	17E	Winnebago	0-225-28-2014	0.5	3.3	3.6	5.8	26.3	2.751	2.779	1.003	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
BEN CARRIE 55-70-001-QRY Created On: 01/09/15 Updated On:	Q	NW	SW	29	20N	17E	Winnebago	0-225-49-2015	0.1	2.1	1.4	5.6	24.3	2.768	2.792	0.891	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
BEN CARRIE 55-70-001-QRY Created On: 05/12/16 Updated On:	Q	NW	SW	29	20N	17E	Winnebago	0-225-171-2016		0.9	1.3	4.5	21.5	2.780	2.803	0.825	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
BEN CARRIE 55-70-001-QRY Created On: 03/13/17 Updated On:	Q	NW	SW	29	20N	17E	Winnebago	0-225-79-2017	0.2	1.8	4.6	5.0	23.4	2.768	2.792	0.846	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
BEN CARRIE 55-70-001-QRY Created On: 03/28/18 Updated On:	Q	NW	SW	29	20N	17E	Winnebago	0-225-150-2018	0.1	2.1	1.4	4.3	20.6	2.773	2.799	0.919	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
BEN CARRIE 55-70-001-QRY Created On: 04/10/19 Updated On:	Q	NW	SW	29	20N	17E	Winnebago	0-225-128-2019		5.6	2.9	4.6	22.2	2.761	2.788	0.978	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
BEN CARRIE 55-70-001-QRY Created On: 04/08/20 Updated On:	Q	NW	SW	29	20N	17E	Winnebago	0-225-148-2020	0.0	6.3	3.2	4.9	22.4	2.765	2.794	1.042	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
BEN CARRIE 55-70-001-QRY Created On: 01/03/23 Updated On:	Q	NW	SW	29	20N	17E	Winnebago	0-225-76-2023	0.0	6.0	3.2	6.6	29.7	2.717	2.753	1.322	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
* BENDORF 55-22-006-QRY Created On: 05/23/14 Updated On:	Q	SW	NE	19	4N	2W	Grant	0-225-166-2014	0.0	3.4	3.9	13.5	45.0	2.538	2.621	3.287	
	Approved Use : CONCRETE, OGBC, Base Aggregate																
* BENDORF 55-22-006-QRY Created On: 01/05/17 Updated On:	Q	SW	NE	19	4N	2W	Grant	0-225-28-2017		4.1	6.3	14.9	47.5	2.572	2.644	2.778	
	Approved Use : CONCRETE, Base Aggregate																
* BENDORF 55-22-006-QRY Created On: 01/04/19 Updated On:	Q	SW	NE	19	4N	2W	Grant	0-225-24-2019	1.0	6.4	2.7	13.9	47.1	2.565	2.641	2.934	
	Approved Use : CONCRETE, OGBC, Base Aggregate																
* BENECKER 55-12-002-QRY Created On: 01/02/14 Updated On:	Q			5	6N	6W	Crawford	0-225-1-2014	10.9	3.2	10.3	16.7	49.4	2.511	2.593	3.275	
	Approved Use : OGBC, Base Aggregate																
* BENECKER 55-12-002-QRY Created On: 01/04/21 Updated On:	Q			5	6N	6W	Crawford	0-225-28-2021	11.3	7.8	17.1	18.7	50.3	2.423	2.521	4.012	
	Approved Use : Base Aggregate																
BENES 55-34-004-PIT Created On: 07/18/19 Updated On:	P	SW	NE	8	32N	11E	Langlade	0-225-241-2019	0.1	0.0	0.5	4.6	20.5	2.709	2.735	0.935	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
BENES 55-34-004-PIT Created On: 01/02/24 Updated On:	P	SW	NE	8	32N	11E	Langlade	0-225-63-2024	0.1	0.0	2.0	5.2	22.0	2.719	2.747	1.035	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
BERNING 55-25-005-QRY Created On: 08/08/16 Updated On:	Q	NE	SW	26	5N	3E	Iowa	0-225-237-2016	1.1	6.2	7.1	8.1	35.0	2.582	2.664	3.184	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
BERNING 55-25-005-QRY Created On: 02/11/19 Updated On:	Q	NE	SW	26	5N	3E	Iowa	0-225-103-2019	1.1	10.8	12.5	8.8	35.3	2.560	2.645	3.316	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
BERNING 55-25-005-QRY Created On: 03/17/21 Updated On:	Q	NE	SW	26	5N	3E	Iowa	0-225-143-2021	1.3	14.6	6.1	6.0	30.6	2.642	2.706	2.400	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
BERNING 55-25-005-QRY Created On: 02/28/24 Updated On:	Q	NE	SW	26	5N	3E	Iowa	0-225-184-2024	1.2	13.1	9.3	7.2	32.5	2.616	2.686	2.682	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
* BESCHTA 55-44-003-QRY Created On: 06/26/19 Updated On:	Q	E	SW	26	23N	16E	Outagamie	0-225-229-2019	1.4	6.0	3.0	8.2	34.6	2.698	2.743	1.685	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
BESTWAY 55-54-002-PIT Created On: 01/09/15 Updated On:	P		NW	18	33N	9W	Rusk	0-225-40-2015		0.0	4.8	4.8	20.3	2.724	2.756	1.187	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
BESTWAY 55-54-002-PIT Created On: 01/08/20 Updated On:	P		NW	18	33N	9W	Rusk	0-225-52-2020	0.4	0.0	1.2	4.0	18.8	2.760	2.783	0.837	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
BEVENT 55-37-008-PIT Created On: 09/24/14 Updated On:	P	SW	NW	5	26N	9E	Marathon	0-225-264-2014		0.0	1.0	7.4	30.8	2.639	2.673	1.259	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
BEVENT 55-37-008-PIT Created On: 04/30/21 Updated On:	P	SW	NW	5	26N	9E	Marathon	0-225-196-2021	2.0	0.0	0.6	5.8	26.5	2.654	2.675	0.771	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
BEVERLY MATERIALS 17-00-018-PIT Created On: 01/24/22 Updated On:	P	NE	SE	36	42N	8E	Dundee	0-225-115-2022	2.4	12.9	2.8	5.2	26.5	2.674	2.713	1.458	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
* BEYER 55-35-042-PIT Created On: 01/04/19 Updated On:	P			33	31N	8E	Lincoln	0-225-5-2019	0.7	0.0	4.4	7.3	28.7	2.614	2.656	1.613	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
BIBBY 55-49-028-PIT Created On: 01/02/24 Updated On:	P	NE	NW	8	22N	9E	Portage	0-225-65-2024	0.2	6.0	0.1	6.7	27.7	2.672	2.698	0.982	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
BIEHL 55-38-007-QRY Created On: 01/08/16 Updated On:	Q		SE	4	31N	22E	Marinette	0-225-44-2016		7.6	4.9	7.9	34.4	2.675	2.711	1.343	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
BIEHL 55-38-007-QRY Created On: 05/24/19 Updated On:	Q		SE	4	31N	22E	Marinette	0-225-197-2019	0.0	12.3	2.3	9.0	35.0	2.684	2.720	1.314		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
BIEHL 55-38-007-QRY Created On: 05/17/22 Updated On:	Q		SE	4	31N	22E	Marinette	0-225-206-2022	0.0	8.4	2.3	9.5	37.4	2.654	2.704	1.876		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
BIEHL 11TH ROAD 55-38-008-QRY Created On: 01/06/14 Updated On:	Q	NW	NW	19	30N	21E	Marinette	0-225-18-2014		2.1	0.3	5.9	27.1	2.727	2.757	1.100		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
BIEHL 11TH ROAD 55-38-008-QRY Created On: 01/05/17 Updated On:	Q	NW	NW	19	30N	21E	Marinette	0-225-53-2017		1.0	0.9	5.9	25.9	2.726	2.762	1.322		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
BIEHL 11TH ROAD 55-38-008-QRY Created On: 07/15/20 Updated On:	Q	NW	NW	19	30N	21E	Marinette	0-225-213-2020	0.0	0.9	1.3	4.1	25.9	2.723	2.754	1.157		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
BIEHL 11TH ROAD 55-38-008-QRY Created On: 01/03/23 Updated On:	Q	NW	NW	19	30N	21E	Marinette	0-225-48-2023	0.1	2.3	1.3	7.7	30.3	2.717	2.750	1.219		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
BIEHL 9TH ROAD 55-38-007-PIT Created On: 01/04/18 Updated On:	P	S	NW	18	30N	21E	Marinette	0-225-85-2018	0.9	0.0	3.5	5.1	26.3	2.711	2.741	1.131		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
BIEHL 9TH ROAD 55-38-007-PIT Created On: 01/03/23 Updated On:	P	S	NW	18	30N	21E	Marinette	0-225-34-2023		4.7	1.9	5.9	25.7	2.686	2.720	1.250	
Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																	
BIESE 55-36-006-PIT Created On: 01/04/18 Updated On:	P	SW	NE	34	18N	21E	Manitowoc	0-225-83-2018	0.3	1.3	2.7	6.4	30.5	2.752	2.780	1.013	
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
BIESE 55-36-006-PIT Created On: 01/02/24 Updated On:	P	SW	NE	34	18N	21E	Manitowoc	0-225-131-2024	2.2	4.7	3.6	9.5	34.1	2.730	2.764	1.220	
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
BIG RACK (VENDEN) 55-71-004-QRY Created On: 10/19/17 Updated On:	Q	S	SW	31	24N	3E	Wood	0-225-283-2017		0.0	0.4	4.0	18.2	2.606	2.617	0.389	
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
BIG RACK (VENDEN) 55-71-004-QRY Created On: 01/08/20 Updated On:	Q	S	SW	31	24N	3E	Wood	0-225-73-2020	0.0	0.0	0.3	3.6	16.9	2.603	2.616	0.495	
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
BIG RACK (VENDEN) 55-71-004-QRY Created On: 01/10/23 Updated On:	Q	S	SW	31	24N	3E	Wood	0-225-105-2023	0.2	0.0	0.3	3.2	16.1	2.615	2.625	0.377	
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
BIWERS 55-15-002-QRY Created On: 04/27/15 Updated On:	Q	NW	SE	10	30N	27E	Door	0-225-139-2015		0.0	1.0	6.4	24.1	2.760	2.783	0.829	
Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
BIWERS 55-15-002-QRY Created On: 02/15/18 Updated On:	Q	NW	SE	10	30N	27E	Door	0-225-102-2018	0.1	1.0	1.0	6.3	25.9	2.759	2.783	0.876	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
BIWERS 55-15-002-QRY Created On: 01/06/21 Updated On:	Q	NW	SE	10	30N	27E	Door	0-225-113-2021	0.0	0.5	0.7	5.5	23.3	2.760	2.784	0.886	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
BIWERS 55-15-002-QRY Created On: 01/29/24 Updated On:	Q	NW	SE	10	30N	27E	Door	0-225-157-2024	0.1	0.8	0.4	5.4	22.7	2.760	2.783	0.837	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
BJOIN 55-53-003-QRY Created On: 06/12/14 Updated On:	Q	SW	SW	36	3N	11E	Rock	0-225-195-2014		0.9	1.1	6.0	27.9	2.640	2.703	2.415	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
BJOIN 55-53-003-QRY Created On: 03/22/17 Updated On:	Q	SW	SW	36	3N	11E	Rock	0-225-86-2017	0.6	2.6	8.0	7.2	31.1	2.622	2.690	2.597	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
BJOIN 55-53-003-QRY Created On: 03/02/20 Updated On:	Q	SW	SW	36	3N	11E	Rock	0-225-118-2020	0.6	12.3	10.5	7.3	32.1	2.626	2.689	2.400	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
BJOIN 55-53-003-QRY Created On: 01/30/23 Updated On:	Q	SW	SW	36	3N	11E	Rock	0-225-133-2023	0.6	26.4	10.2	8.1	34.8	2.624	2.696	2.733	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
BJOIN 55-53-003-QRY Created On: 03/21/23 Updated On:	Q	SW	SW	36	3N	11E	Rock	0-225-174-2023	0.4	15.0	4.4	5.4	26.7	2.678	2.735	2.129	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
* BJORNSTAD 55-41-001-QRY Created On: 01/09/15 Updated On:	Q	NE	SW	35	15N	4W	Monroe	0-225-52-2015		0.0	6.3	12.9	41.3	2.562	2.632	2.743	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
* BJORNSTAD 55-41-001-QRY Created On: 01/03/18 Updated On:	Q	NE	SW	35	15N	4W	Monroe	0-225-14-2018	1.2	0.0	1.9	10.4	38.2	2.615	2.671	2.140	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
* BJORNSTAD 55-41-001-QRY Created On: 01/04/21 Updated On:	Q	NE	SW	35	15N	4W	Monroe	0-225-27-2021	1.2	0.0	0.9	9.3	34.7	2.620	2.671	1.962	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
* BLACKBERRY 55-37-015-QRY Created On: 05/11/15 Updated On:	Q	SW	NE	36	28N	2E	Marathon	0-225-169-2015		0.0	0.1	5.6	29.1	2.561	2.586	0.956	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
* BLACKBERRY 55-37-015-QRY Created On: 05/02/19 Updated On:	Q	SW	NE	36	28N	2E	Marathon	0-225-177-2019	0.1	0.0	1.2	6.6	29.1	2.582	2.601	0.725	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
* BLACKHAWK 55-23-003-QRY Created On: 05/11/15 Updated On:	Q	SW	NE	20	1N	6E	Green	0-225-162-2015		11.7	9.3	11.0	32.8	2.622	2.676	2.068	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
* BLACKHAWK 55-23-003-QRY Created On: 03/23/18 Updated On:	Q	SW	NE	20	1N	6E	Green	0-225-142-2018	0.1	13.5	1.6	8.1	29.9	2.601	2.668	2.568		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
* BLACKHAWK 55-23-003-QRY Created On: 03/17/21 Updated On:	Q	SW	NE	20	1N	6E	Green	0-225-151-2021	1.6	7.8	2.3	8.1	26.9	2.578	2.652	2.885		
	Approved Use : Base Aggregate																	
BLACKHAWK QUARRY PRODUCTS 55-33-017-QRY Created On: 02/13/20 Updated On:	Q	NE	NE	15	1N	5E	Lafayette	0-225-112-2020	0.5	4.2	5.6	11.6	42.5	2.538	2.627	3.508		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
BLACKHAWK QUARRY PRODUCTS 55-33-017-QRY Created On: 01/02/24 Updated On:	Q	NE	NE	15	1N	5E	Lafayette	0-225-71-2024	0.1	4.6	2.6	9.9	36.0	2.609	2.676	2.559		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
BLANCHARD PIT 55-99-044-PIT Created On: 04/02/20 Updated On:	P			26	31N	7W		0-225-143-2020	1.0	0.0	3.7	4.6	20.3	2.728	2.754	0.943		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
* BLATZ 55-36-047-QRY Created On: 01/07/20 Updated On:	Q	SW	NE	35	17N	21E	Manitowoc	0-225-37-2020	0.1	0.0	2.4	6.3	28.3	2.769	2.792	0.815		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
* BLATZ-CAPSTONE 55-36-046-QRY Created On: 06/26/19 Updated On:	Q	SW	NE	33	17N	21E	Manitowoc	0-225-230-2019	0.6	1.3	1.4	6.1	27.8	2.761	2.785	0.885		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Coarse Sp. Gravity		Coarse Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
BLAU (LYCON) 55-11-006-PIT Created On: 01/20/17 Updated On:	P	NE	NW	2	11N	8E	Columbia	0-225-54-2017	1.4	0.0	2.6	7.1	30.0	2.674	2.708	1.266	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
BLAU (LYCON) 55-11-006-PIT Created On: 01/04/22 Updated On:	P	NE	NW	2	11N	8E	Columbia	0-225-42-2022	1.2	0.0	2.8	6.3	28.7	2.692	2.725	1.213	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
* BLOOMFIELD 55-64-008-PIT Created On: 01/07/14 Updated On:	P	E	SW	1	1N	19E	Walworth	0-225-41-2014	0.1	0.0	1.0	3.5	17.6	2.690	2.726	1.334	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
* BLOOMFIELD 55-64-008-PIT Created On: 01/18/19 Updated On:	P	E	SW	1	1N	19E	Walworth	0-225-86-2019	1.5	7.4	0.9	4.0	21.5	2.669	2.711	1.566	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
BLUE LAKE 55-43-002-PIT Created On: 05/10/18 Updated On:	P	SW	SE	27	39N	6E	Oneida	0-225-205-2018	0.8	0.0	1.4	4.2	18.7	2.701	2.723	0.811	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
BLUE LAKE 55-43-002-PIT Created On: 01/03/23 Updated On:	P	SW	SE	27	39N	6E	Oneida	0-225-29-2023	2.4	0.0	2.5	4.9	20.8	2.670	2.698	1.026	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
* BODE 55-22-008-QRY Created On: 05/23/14 Updated On:	Q	NW	SE	4	2N	3W	Grant	0-225-175-2014	0.5	1.5	6.0	10.9	38.6	2.567	2.636	2.675	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
* BODE 55-22-008-QRY Created On: 04/25/17 Updated On:	Q	NW	SE	4	2N	3W	Grant	0-225-154-2017	0.5	6.5	7.7	11.6	42.5	2.564	2.638	2.909		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
* BODE 55-22-008-QRY Created On: 04/19/19 Updated On:	Q	NW	SE	4	2N	3W	Grant	0-225-154-2019	0.5	4.9	9.0	9.8	36.9	2.577	2.644	2.593		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
BOHL #720 55-03-006-PIT Created On: 02/13/17 Updated On:	P	NW	SE	10	32N	11W	Barron	0-225-70-2017		0.0	2.2	4.4	18.9	2.687	2.715	1.015		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
BOHL #720 55-03-006-PIT Created On: 03/01/22 Updated On:	P	NW	SE	10	32N	11W	Barron	0-225-135-2022	2.5	2.3	2.3	4.0	18.5	2.685	2.715	1.106		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
BOHLMON 55-37-009-PIT Created On: 05/01/18 Updated On:	P		SE	36	28N	10E	Marathon	0-225-187-2018		0.6	2.1	7.5	30.8	2.653	2.682	1.105		
	Approved Use : HMA<MT, HMA>=MT, Base Aggregate																	
BOHLMON 55-37-009-PIT Created On: 01/03/23 Updated On:	P		SE	36	28N	10E	Marathon	0-225-16-2023		0.0	0.4	8.6	33.4	2.646	2.673	1.028		
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																	
BONDE 55-36-008-PIT Created On: 01/05/17 Updated On:	P		NE	5	17N	22E	Manitowoc	0-225-18-2017	0.9	1.9	2.2	8.0	33.1	2.768	2.790	0.797		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
BONDE 55-36-008-PIT Created On: 04/28/22 Updated On:	P		NE	5	17N	22E	Manitowoc	0-225-184-2022	2.1	0.0	0.4	7.8	34.3	2.766	2.790	0.873	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
BONDLEI 55-61-004-QRY Created On: 03/13/17 Updated On:	Q	NE	SW	20	20N	8W	Trempealeau	0-225-81-2017	0.5	0.0	4.5	8.8	34.8	2.612	2.668	2.142	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
BONDLEI 55-61-004-QRY Created On: 03/12/20 Updated On:	Q	NE	SW	20	20N	8W	Trempealeau	0-225-129-2020	0.0	0.0	9.4	12.7	40.5	2.544	2.623	3.084	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
BONDLEI 55-61-004-QRY Created On: 04/04/23 Updated On:	Q	NE	SW	20	20N	8W	Trempealeau	0-225-178-2023	0.0	0.0	5.5	8.4	34.2	2.595	2.658	2.396	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
BONDUEL 55-58-002-QRY Created On: 01/20/16 Updated On:	Q		NE	29	25N	17E	Shawano	0-225-60-2016		1.1	0.9	7.2	30.9	2.719	2.749	1.102	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
BONDUEL 55-58-002-QRY Created On: 01/04/19 Updated On:	Q		NE	29	25N	17E	Shawano	0-225-14-2019		4.3	0.7	6.3	31.0	2.721	2.752	1.162	
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																
BONDUEL 55-58-002-QRY Created On: 01/04/22 Updated On:	Q		NE	29	25N	17E	Shawano	0-225-35-2022	0.0	2.9	1.8	6.3	28.3	2.717	2.747	1.083	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
BONG 55-13-004-QRY Created On: 05/11/18 Updated On:	Q	SW	SE	11	8N	9E	Dane	0-225-210-2018	4.1	1.9	3.7	11.9	39.2	2.537	2.611	2.930		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
BONG 55-13-004-QRY Created On: 02/15/21 Updated On:	Q	SW	SE	11	8N	9E	Dane	0-225-127-2021	5.2	3.4	3.4	9.2	36.4	2.570	2.638	2.624		
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																	
BONG 55-13-004-QRY Created On: 01/04/24 Updated On:	Q	SW	SE	11	8N	9E	Dane	0-225-148-2024	3.2	5.5	2.5	9.8	40.1	2.560	2.625	2.530		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
BONG (YAHARA) 55-13-004-QRY Created On: 04/18/24 Updated On:	Q	SW	SE	11	8N	9E	Dane	0-225-235-2024	0.6	7.4	5.3	12.0	46.5	2.489	2.579	3.606		
	Approved Use : HMA<MT, CONCRETE, OGBC, Base Aggregate																	
BORK 55-06-005-QRY Created On: 09/09/16 Updated On:	Q	NW	NE	30	19N	10W	Buffalo	0-225-253-2016		0.0	5.3	8.8	32.6	2.627	2.678	1.932		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
BORK 55-06-005-QRY Created On: 01/08/19 Updated On:	Q	NW	NE	30	19N	10W	Buffalo	0-225-78-2019	0.8	0.0	2.9	10.1	35.8	2.610	2.667	2.156		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
BORK 55-06-005-QRY Created On: 01/04/22 Updated On:	Q	NW	NE	30	19N	10W	Buffalo	0-225-11-2022	0.3	2.4	4.8	9.1	35.3	2.648	2.694	1.717		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
BOSCOBEL 55-22-060-QRY Created On: 01/05/17 Updated On:	Q	NE	SE	14	7N	3W	Grant	0-225-25-2017	0.7	5.6	2.2	7.5	29.9	2.611	2.674	2.416		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
BOSCOBEL 55-22-060-QRY Created On: 08/03/18 Updated On:	Q	NE	SE	14	7N	3W	Grant	0-225-263-2018	0.8	4.1	6.1	7.5	30.8	2.625	2.678	2.014		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
BOSCOBEL 55-22-060-QRY Created On: 04/07/21 Updated On:	Q	NE	SE	14	7N	3W	Grant	0-225-172-2021	0.0	1.9	6.8	8.1	31.0	2.621	2.680	2.252		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
BOSCOBEL 55-22-060-QRY Created On: 01/02/24 Updated On:	Q	NE	SE	14	7N	3W	Grant	0-225-3-2024	0.2	1.9	1.1	5.8	25.7	2.662	2.707	1.683		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
* BOSS 55-64-009-PIT Created On: 06/07/19 Updated On:	P		NW	33	3N	15E	Walworth	0-225-209-2019	1.2	0.0	1.3	5.4	25.4	2.700	2.735	1.304		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
* BOULANGER 55-31-002-QRY Created On: 07/31/18 Updated On:	Q	NE	SE	15	22N	23E	Kewaunee	0-225-261-2018	1.9	0.0	2.1	6.7	31.1	2.769	2.794	0.885		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
* BOULANGER 55-31-002-QRY Created On: 01/06/21 Updated On:	Q	NE	SE	15	22N	23E	Kewaunee	0-225-112-2021	1.2	0.0	0.6	7.2	31.5	2.781	2.800	0.657		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
BOULDER HILL 55-49-003-PIT Created On: 01/04/18 Updated On:	P	SW	NE	22	22N	9E	Portage	0-225-86-2018	0.9	0.0	4.2	8.7	31.8	2.678	2.707	1.106		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
BOULDER HILL 55-49-003-PIT Created On: 01/03/23 Updated On:	P	SW	NE	22	22N	9E	Portage	0-225-12-2023	0.4	3.5	3.3	7.9	31.2	2.667	2.700	1.234		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
BRACKETT QUARRY 55-26-002-QRY Created On: 07/21/17 Updated On:	Q	NE	NW	31	46N	2E	Iron	0-225-239-2017	0.1	0.0	0.5	2.6	11.9	2.697	2.710	0.487		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
BRACKETT QUARRY 55-26-002-QRY Created On: 01/06/20 Updated On:	Q	NE	NW	31	46N	2E	Iron	0-225-31-2020	0.0	0.0	9.1	3.8	16.2	2.683	2.705	0.816		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
BRACKETT QUARRY 55-26-002-QRY Created On: 01/04/23 Updated On:	Q	NE	NW	31	46N	2E	Iron	0-225-95-2023	0.1	2.9	1.6	3.0	13.4	2.662	2.682	0.759		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
* BRAGGER 55-06-006-QRY Created On: 06/11/14 Updated On:	Q	W	NW	13	22N	10W	Buffalo	0-225-188-2014	1.5	0.0	3.8	9.9	40.0	2.564	2.639	2.901		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
* BRAGGER 55-06-006-QRY Created On: 04/21/17 Updated On:	Q	W	NW	13	22N	10W	Buffalo	0-225-141-2017	0.4	0.0	7.5	10.3	41.1	2.571	2.646	2.915		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
* BRAGGER 55-06-006-QRY Created On: 06/18/20 Updated On:	Q	W	NW	13	22N	10W	Buffalo	0-225-196-2020	0.0	0.0	5.6	10.2	39.6	2.566	2.641	2.936	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
BRATTSET 55-28-020-PIT Created On: 01/04/22 Updated On:	P	NW	NW	5	5N	16E	Jefferson	0-225-41-2022	1.6	5.2	1.1	4.3	22.8	2.694	2.732	1.401	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
BRAUKHOFF 55-53-004-QRY Created On: 05/17/22 Updated On:	Q	S	SW	26	2N	14E	Rock	0-225-203-2022	0.4	6.5	2.7	7.7	34.7	2.652	2.707	2.091	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
BREAKNECK ROAD 55-20-055-QRY Created On: 01/14/21 Updated On:	Q	NE	NW	34	14N	16E	Fond Du Lac	0-225-121-2021	0.0	0.7	0.6	5.8	25.8	2.773	2.792	0.676	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
BREAKNECK ROAD 55-20-055-QRY Created On: 01/02/24 Updated On:	Q	NE	NW	34	14N	16E	Fond Du Lac	0-225-50-2024	0.1	1.3	1.0	5.9	26.7	2.772	2.790	0.646	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
BREUNIG 55-13-006-PIT Created On: 01/20/17 Updated On:	P	NE	NW	7	9N	7E	Dane	0-225-55-2017	1.5	0.0	5.2	7.6	30.6	2.677	2.724	1.745	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
BREUNIG 55-13-006-PIT Created On: 01/04/22 Updated On:	P	NE	NW	7	9N	7E	Dane	0-225-43-2022	2.1	0.0	6.8	7.2	31.4	2.671	2.720	1.819	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
BRIGGS PIT 55-34-008-PIT Created On: 08/20/19 Updated On:	P	SW	NE	1	34N	10E	Langlade	0-225-263-2019	0.6	0.0	1.1	4.3	19.0	2.680	2.703	0.860		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
BRIGGS PIT 55-34-008-PIT Created On: 04/24/23 Updated On:	P	SW	NE	1	34N	10E	Langlade	0-225-207-2023	0.2	0.0	0.7	4.8	22.0	2.691	2.711	0.762		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
BROCK 55-35-003-PIT Created On: 03/09/15 Updated On:	P		NE	29	31N	7E	Lincoln	0-225-93-2015		0.0	3.2	4.1	19.0	2.685	2.714	1.094		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
BROCK 55-35-003-PIT Created On: 01/08/20 Updated On:	P		NE	29	31N	7E	Lincoln	0-225-47-2020	0.0	2.0	0.5	6.0	24.4	2.690	2.715	0.948		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
BROCKER 55-36-009-PIT Created On: 08/28/14 Updated On:	P	NW	SW	20	18N	21E	Manitowoc	0-225-248-2014	0.0	0.0	1.0	6.0	27.5	2.758	2.782	0.866		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
BROCKER 55-36-009-PIT Created On: 04/19/19 Updated On:	P	NW	SW	20	18N	21E	Manitowoc	0-225-147-2019	0.8	0.0	1.3	6.5	29.2	2.764	2.789	0.902		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
BROCKER 55-36-009-PIT Created On: 01/02/24 Updated On:	P	NW	SW	20	18N	21E	Manitowoc	0-225-51-2024	1.1	0.0	2.2	7.9	33.4	2.749	2.777	1.001		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
* BROMMER 55-06-008-QRY Created On: 06/13/16 Updated On:	Q	SW	NE	30	23N	12W	Buffalo	0-225-203-2016		0.0	4.8	8.8	34.7	2.568	2.637	2.681		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
* BROMMER 55-06-008-QRY Created On: 01/05/21 Updated On:	Q	SW	NE	30	23N	12W	Buffalo	0-225-71-2021	2.4	0.0	0.9	8.5	34.4	2.592	2.656	2.470		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
BROOKS 55-60-003-PIT Created On: 08/08/17 Updated On:	P	SW	SE	7	33N	3W	Taylor	0-225-247-2017		0.0	2.2	5.3	21.5	2.734	2.765	1.125		
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																	
BROOKS 55-60-003-PIT Created On: 01/04/22 Updated On:	P	SW	SE	7	33N	3W	Taylor	0-225-81-2022	1.1	0.0	3.8	3.9	19.8	2.697	2.731	1.242		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
BROOKVILLE 55-62-004-QRY Created On: 05/19/16 Updated On:	Q			22	12N	4W	Vernon	0-225-184-2016		0.0	4.0	11.0	38.1	2.637	2.689	1.954		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
BROOKVILLE 55-62-004-QRY Created On: 01/04/18 Updated On:	Q			22	12N	4W	Vernon	0-225-44-2018	0.4	0.0	2.1	9.8	37.3	2.636	2.685	1.861		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
BROOKVILLE 55-62-004-QRY Created On: 01/05/21 Updated On:	Q			22	12N	4W	Vernon	0-225-63-2021	0.4	0.0	0.4	8.1	33.7	2.634	2.687	1.993		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description						Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range					County	100	500	OD	SSD	Crse
BROOKVILLE 55-62-004-QRY Created On: 01/02/24 Updated On:	Q		22	12N	4W	Vernon	0-225-35-2024	1.7	0.8	5.1	11.6	42.3	2.617	2.677	2.278	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate															
BROWN 55-11-010-PIT Created On: 01/03/18 Updated On:	P	NW	SW	18	12N	10E	Columbia	0-225-25-2018	0.3	5.0	1.3	9.8	31.8	2.666	2.718	1.932
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate															
* BROWN 55-52-027-QRY Created On: 06/02/20 Updated On:	Q		4	11N	1W	Richland	0-225-184-2020	1.3	0.0	0.5	10.0	34.5	2.603	2.661	2.216	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate															
BROWN 55-11-010-PIT Created On: 01/04/23 Updated On:	P	NW	SW	18	12N	10E	Columbia	0-225-93-2023	0.4	0.0	1.8	6.9	30.3	2.691	2.732	1.523
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate															
* BROWNS BOTTOM 19-00-002-QRY Created On: 04/23/15 Updated On:	Q		NE	24	88N	3E	Dubuque	0-225-131-2015		0.2	0.8	7.0	28.0	2.670	2.706	1.367
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate															
* BROWNS BOTTOM 19-00-002-QRY Created On: 01/04/18 Updated On:	Q		NE	24	88N	3E	Dubuque	0-225-72-2018	0.2	1.3	1.1	6.4	27.3	2.661	2.701	1.506
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate															
* BROWNS BOTTOM 19-00-002-QRY Created On: 01/05/21 Updated On:	Q		NE	24	88N	3E	Dubuque	0-225-57-2021	0.2	0.5	0.6	7.3	29.1	2.676	2.715	1.430
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate															

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Coarse Sp. Gravity		Coarse Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
* BROWNS BOTTOM 19-00-002-QRY Created On: 01/02/24 Updated On:	Q	NE	24	88N	3E	Dubuque	0-225-34-2024	0.3	3.1	1.0	8.4	32.0	2.620	2.673	2.026			
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
BRUEGGEMAN 55-41-003-QRY Created On: 01/07/14 Updated On:	Q	NE	NW	29	15N	2W	Monroe	0-225-46-2014	0.4	0.0	5.0	9.6	39.4	2.587	2.655	2.639		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
BRUEGGEMAN 55-41-003-QRY Created On: 04/06/17 Updated On:	Q	NE	NW	29	15N	2W	Monroe	0-225-115-2017	0.3	0.0	1.5	9.8	37.6	2.618	2.673	2.081		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
BRUEGGEMAN 55-41-003-QRY Created On: 04/02/20 Updated On:	Q	NE	NW	29	15N	2W	Monroe	0-225-139-2020	0.0	0.0	2.6	10.7	38.1	2.610	2.671	2.342		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
BRUEGGEMAN 55-41-003-QRY Created On: 01/04/24 Updated On:	Q	NE	NW	29	15N	2W	Monroe	0-225-134-2024	1.0	2.7	3.6	8.8	35.6	2.631	2.682	1.936		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
BRUHA 55-03-008-PIT Created On: 01/09/15 Updated On:	P	SW	NE	13	36N	12W	Barron	0-225-44-2015		0.0	2.8	3.5	15.8	2.755	2.789	1.234		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
BRUHA 55-03-008-PIT Created On: 01/08/20 Updated On:	P	SW	NE	13	36N	12W	Barron	0-225-55-2020	0.7	0.0	2.4	3.6	16.5	2.767	2.794	0.973		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
BUCHDA 55-14-004-QRY Created On: 01/04/16 Updated On:	Q	NE	NW	5	12N	14E	Dodge	0-225-3-2016	0.5	2.2	1.4	6.8	27.7	2.745	2.779	1.209		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
BUCHDA 55-14-004-QRY Created On: 06/06/19 Updated On:	Q	NE	NW	5	12N	14E	Dodge	0-225-204-2019		2.1	1.0	7.6	29.5	2.752	2.779	0.973		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
BUCHDA 55-14-004-QRY Created On: 01/04/22 Updated On:	Q	NE	NW	5	12N	14E	Dodge	0-225-95-2022	0.0	2.4	2.5	8.0	27.1	2.738	2.772	1.252		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
BUCKEYE 55-13-008-QRY Created On: 01/21/15 Updated On:	Q	SW	NE	14	7N	10E	Dane	0-225-74-2015		6.1	4.4	9.7	38.9	2.563	2.636	2.824		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
BUCKEYE 55-13-008-QRY Created On: 01/05/17 Updated On:	Q	SW	NE	14	7N	10E	Dane	0-225-35-2017	1.1	3.7	2.1	6.2	27.2	2.603	2.667	2.481		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
BUCKEYE 55-13-008-QRY Created On: 05/13/19 Updated On:	Q	SW	NE	14	7N	10E	Dane	0-225-186-2019	0.3	1.1	0.9	6.9	28.7	2.619	2.678	2.260		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
BUCKEYE 55-13-008-QRY Created On: 03/09/20 Updated On:	Q	SW	NE	14	7N	10E	Dane	0-225-121-2020	0.1	1.6	4.7	6.3	25.1	2.644	2.695	1.895		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
BUCKEYE 55-13-008-QRY Created On: 03/16/21 Updated On:	Q	SW	NE	14	7N	10E	Dane	0-225-136-2021	0.8	1.6	3.4	6.4	26.8	2.634	2.689	2.079	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
BUCKEYE 55-13-008-QRY Created On: 01/02/24 Updated On:	Q	SW	NE	14	7N	10E	Dane	0-225-88-2024	0.2	3.0	2.4	10.1	35.4	2.583	2.646	2.430	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
* BUECHEL STONE OAKFIELD 55-20-056-QRY Created On: 03/24/21 Updated On:	Q	NE	NE	34	14N	16E	Fond Du Lac	0-225-158-2021	0.0	1.0	2.7	5.5	26.0	2.738	2.766	1.007	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
BUGBEE QUARRY 55-62-035-QRY Created On: 02/28/24 Updated On:	Q	SE	SW	21	14N	1W	Vernon	0-225-191-2024	1.2	3.7	6.4	8.5	36.8	2.608	2.667	2.226	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
BURIC 55-03-009-PIT Created On: 06/13/16 Updated On:	P	NW	NW	14	33N	10W	Barron	0-225-204-2016		0.0	1.2	5.6	22.0	2.730	2.754	0.876	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
BURIC 55-03-009-PIT Created On: 01/04/22 Updated On:	P	NW	NW	14	33N	10W	Barron	0-225-85-2022	2.7	0.0	1.9	4.6	21.2	2.667	2.689	0.853	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
BURLINGTON SPRING VALLEY 55-51-006-PIT Created On: 03/24/16 Updated On:	P			6	2N	19E	Racine	0-225-114-2016	2.0	8.5	3.3	7.2	31.9	2.646	2.696	1.913	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
BURLINGTON SPRING VALLEY 55-51-006-PIT Created On: 01/05/21 Updated On:	P		6	2N	19E	Racine		0-225-81-2021	0.0	0.0	5.4	4.9	26.3	2.655	2.702	1.768	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
* BURMEISTER 55-54-029-QRY Created On: 08/20/20 Updated On:	Q	NE	SW	33	33N	5W	Rusk	0-225-234-2020	0.3	0.0	0.4	3.3	14.9	2.814	2.830	0.569	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
BURMEISTER 55-54-030-PIT Created On: 01/04/22 Updated On:	P	NE	SW	33	33N	5W	Rusk	0-225-84-2022	0.4	0.0	1.5	3.6	17.6	2.708	2.736	1.037	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
BURMEISTER 55-54-030-PIT Created On: 01/10/23 Updated On:	P	NE	SW	33	33N	5W	Rusk	0-225-108-2023	0.0	0.0	0.2	2.1	9.6	2.878	2.887	0.328	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
BURT(MUELLER) 55-62-005-QRY Created On: 05/18/17 Updated On:	Q	NW	SW	33	13N	2W	Vernon	0-225-190-2017		0.0	2.1	8.7	33.2	2.626	2.681	2.133	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
BURT(MUELLER) 55-62-005-QRY Created On: 01/08/20 Updated On:	Q	NW	SW	33	13N	2W	Vernon	0-225-65-2020	0.5	0.0	5.6	8.2	32.2	2.650	2.696	1.760	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
BURT(MUELLER) 55-62-005-QRY Created On: 01/30/23 Updated On:	Q	NW	SW	33	13N	2W	Vernon	0-225-134-2023	1.5	1.6	1.7	8.5	33.4	2.654	2.703	1.858	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Coarse Sp. Gravity		Coarse Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
* BYRON 55-20-012-QRY Created On: 01/08/15 Updated On:	Q	N	SE	10	14N	17E	Fond Du Lac	0-225-29-2015		0.5	1.5	5.5	26.4	2.735	2.765	1.106		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
* BYRON 55-20-012-QRY Created On: 03/16/18 Updated On:	Q	N	SE	10	14N	17E	Fond Du Lac	0-225-122-2018		0.6	0.7	5.5	27.8	2.725	2.758	1.203		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
* BYRON 55-20-012-QRY Created On: 01/05/21 Updated On:	Q	N	SE	10	14N	17E	Fond Du Lac	0-225-49-2021	0.0	1.2	0.9	5.8	28.1	2.738	2.767	1.045		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
C6 QUARRY 55-13-126-QRY Created On: 09/05/23 Updated On:	Q	NE	NW	17	6N	8E	Dane	0-225-250-2023	0.7	2.8	0.5	5.4	23.9	2.680	2.720	1.486		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
CAELWAERTS 55-42-002-QRY Created On: 08/16/16 Updated On:	Q	NE	SE	31	29N	22E	Oconto	0-225-241-2016		7.7	2.6	4.6	25.7	2.721	2.753	1.160		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
CAELWAERTS 55-42-002-QRY Created On: 04/24/19 Updated On:	Q	NE	SE	31	29N	22E	Oconto	0-225-165-2019		7.7	1.3	5.5	25.2	2.707	2.741	1.245		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
CAELWAERTS 55-42-002-QRY Created On: 01/04/22 Updated On:	Q	NE	SE	31	29N	22E	Oconto	0-225-92-2022	0.0	4.5	4.7	6.2	28.2	2.709	2.739	1.115		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description						Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range					County	100	500	OD	SSD	Crse	Fine
* CAMEL HILL 55-13-009-QRY Created On: 01/09/15 Updated On:	Q		W	24	7N	7E	Dane	0-225-55-2015		26.6	18.4	8.0	35.2	2.550	2.635	3.338	
* CAMEL HILL 55-13-009-QRY Created On: 02/16/16 Updated On:	Q		W	24	7N	7E	Dane	0-225-83-2016		10.7	13.2	8.4	37.9	2.579	2.652	2.834	
* CAMEL HILL 55-13-009-QRY Created On: 01/04/19 Updated On:	Q		W	24	7N	7E	Dane	0-225-31-2019		1.9	1.7	6.3	7.5	2.632	2.683	1.935	
CAMPIA PIT 55-03-010-PIT Created On: 01/02/24 Updated On:	P	NE	NE	8	35N	10W	Barron	0-225-87-2024		1.3	0.0	0.9	4.2	19.6	2.708	2.734	0.959
CAPITOL SAND & GRAVEL 55-13-010-PIT Created On: 09/26/18 Updated On:	P			11	7N	7E	Dane	0-225-283-2018		9.2	5.8	3.1	8.1	32.1	2.587	2.639	1.997
CAPITOL SAND & GRAVEL 55-13-010-PIT Created On: 01/09/20 Updated On:	P			11	7N	7E	Dane	0-225-92-2020		4.2	9.1	0.9	11.0	38.5	2.635	2.681	1.729
CAPITOL SAND & GRAVEL 55-13-010-PIT Created On: 01/02/24 Updated On:	P			11	7N	7E	Dane	0-225-41-2024		1.7	2.8	5.7	11.0	38.2	2.649	2.691	1.584

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
CAREW - BRUSSELS 55-15-004-QRY Created On: 01/16/15 Updated On:	Q	NW	NW	21	26N	24E	Door	0-225-69-2015		0.0	3.3	7.2	27.5	2.749	2.778	1.052		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
CAREW - BRUSSELS 55-15-004-QRY Created On: 03/01/18 Updated On:	Q	NW	NW	21	26N	24E	Door	0-225-111-2018		0.0	5.2	6.0	26.6	2.773	2.793	0.717		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
CAREW - BRUSSELS 55-15-004-QRY Created On: 01/14/21 Updated On:	Q	NW	NW	21	26N	24E	Door	0-225-120-2021	0.0	0.0	0.9	5.4	24.8	2.780	2.798	0.655		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
CAREW - BRUSSELS 55-15-004-QRY Created On: 02/28/24 Updated On:	Q	NW	NW	21	26N	24E	Door	0-225-177-2024	0.0	0.0	1.7	6.4	27.4	2.772	2.790	0.650		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
CAREW - EDEN 55-20-058-PIT Created On: 01/25/16 Updated On:	P	W	SE	23	14N	18E	Fond Du Lac	0-225-81-2016	0.3	0.0	2.9	8.0	33.0	2.742	2.772	1.093		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
CAREW - EDEN 55-20-058-PIT Created On: 02/08/21 Updated On:	P	W	SE	23	14N	18E	Fond Du Lac	0-225-123-2021	0.5	2.9	3.6	7.6	33.2	2.752	2.783	1.128		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
CAREW - FREEDOM 55-44-006-QRY Created On: 06/05/14 Updated On:	Q	SW	NE	10	22N	18E	Outagamie	0-225-187-2014	0.1	0.5	0.1	3.8	17.0	2.805	2.818	0.463		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
CAREW - FREEDOM 55-44-006-QRY Created On: 01/16/15 Updated On:	Q	SW	NE	10	22N	18E	Outagamie	0-225-68-2015	0.8	0.8	1.0	4.6	20.6	2.791	2.808	0.616		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
CAREW - FREEDOM 55-44-006-QRY Created On: 03/06/17 Updated On:	Q	SW	NE	10	22N	18E	Outagamie	0-225-75-2017		2.8	1.5	4.6	21.2	2.774	2.796	0.794		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
CAREW - FREEDOM 55-44-006-QRY Created On: 01/30/20 Updated On:	Q	SW	NE	10	22N	18E	Outagamie	0-225-100-2020	0.0	2.4	1.2	4.0	18.3	2.796	2.812	0.572		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
CAREW - FREEDOM 55-44-006-QRY Created On: 01/04/23 Updated On:	Q	SW	NE	10	22N	18E	Outagamie	0-225-103-2023	0.0	1.2	1.2	4.4	19.9	2.788	2.804	0.572		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
CAREW - FREEDOM 55-44-006-QRY Created On: 02/28/24 Updated On:	Q	SW	NE	10	22N	18E	Outagamie	0-225-178-2024	0.0	1.2	1.3	4.8	21.3	2.771	2.791	0.732		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
CAREW - ROCK RD 55-44-007-QRY Created On: 01/25/16 Updated On:	Q	NE	NW	20	22N	17E	Outagamie	0-225-82-2016		0.7	3.7	5.6	27.6	2.701	2.738	1.363		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
CAREW - ROCK RD 55-44-007-QRY Created On: 01/10/19 Updated On:	Q	NE	NW	20	22N	17E	Outagamie	0-225-84-2019	0.1	4.1	3.0	6.1	27.9	2.746	2.775	1.045		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
CAREW - ROCK RD 55-44-007-QRY Created On: 03/17/22 Updated On:	Q	NE	NW	20	22N	17E	Outagamie	0-225-152-2022	0.2	2.7	3.6	5.9	27.4	2.725	2.756	1.124	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
CAREW ALTO/WAUPUN 55-20-008-QRY Created On: 01/06/14 Updated On:	Q	S	NE	36	14N	14E	Fond Du Lac	0-225-8-2014		1.0	1.9	6.2	28.2	2.770	2.794	0.879	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
CAREW ALTO/WAUPUN 55-20-008-QRY Created On: 03/08/17 Updated On:	Q	S	NE	36	14N	14E	Fond Du Lac	0-225-78-2017		6.0	4.4	6.3	27.9	2.767	2.790	0.826	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
CAREW ALTO/WAUPUN 55-20-008-QRY Created On: 01/30/20 Updated On:	Q	S	NE	36	14N	14E	Fond Du Lac	0-225-99-2020	0.0	4.0	3.5	6.2	27.1	2.764	2.791	0.974	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
CAREW ALTO/WAUPUN 55-20-008-QRY Created On: 01/04/23 Updated On:	Q	S	NE	36	14N	14E	Fond Du Lac	0-225-100-2023	0.0	3.9	1.6	6.3	28.2	2.771	2.794	0.821	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
CAREW-MARIBEL 55-36-013-PIT Created On: 08/09/18 Updated On:	P	NE	NW	19	21N	22E	Manitowoc	0-225-267-2018	1.2	0.0	2.9	7.6	34.2	2.707	2.748	1.491	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
CAREW-MARIBEL 55-36-013-PIT Created On: 01/04/23 Updated On:	P	NE	NW	19	21N	22E	Manitowoc	0-225-102-2023	0.8	0.0	3.7	8.2	34.9	2.691	2.731	1.486	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
CASSVILLE 55-22-009-QRY Created On: 06/30/16 Updated On:	Q	NW	SW	27	3N	5W	Grant	0-225-214-2016	1.2	1.9	0.8	8.8	36.7	2.592	2.659	2.573		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
CASSVILLE 55-22-009-QRY Created On: 01/07/19 Updated On:	Q	NW	SW	27	3N	5W	Grant	0-225-47-2019	0.4	5.2	3.1	8.3	34.7	2.590	2.656	2.564		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
CASSVILLE 55-22-009-QRY Created On: 01/10/22 Updated On:	Q	NW	SW	27	3N	5W	Grant	0-225-104-2022	2.3	5.0	8.0	8.4	36.4	2.594	2.658	2.469		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
* CCI BELOIT QUARRY 55-53-42-QRY Created On: 08/08/17 Updated On:	Q		NW	22	1N	13E	Rock	0-225-246-2017	1.8	1.8	1.3	7.8	35.1	2.480	2.584	4.225		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
* CCI BELOIT QUARRY 55-53-42-QRY Created On: 07/09/20 Updated On:	Q		NW	22	1N	13E	Rock	0-225-211-2020	2.1	9.2	14.6	9.2	36.6	2.571	2.653	3.188		
	Approved Use : Base Aggregate																	
CEDAR LAKE 55-66-004-PIT Created On: 01/04/16 Updated On:	P	N	SW	35	11N	18E	Washington	0-225-15-2016	1.9	1.3	2.1	5.7	26.4	2.712	2.743	1.165		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
CEDAR LAKE 55-66-004-PIT Created On: 01/08/21 Updated On:	P	N	SW	35	11N	18E	Washington	0-225-116-2021	0.8	8.7	1.1	5.9	32.1	2.749	2.772	0.830		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
CEMSTONE CUMBERLAND PIT 55-03-037-PIT Created On: 01/25/16 Updated On:	P	S	SE	35	36N	13W	Barron	0-225-80-2016		0.0	3.2	3.9	18.3	2.726	2.758	1.181		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
CEMSTONE CUMBERLAND PIT 55-03-037-PIT Created On: 01/05/21 Updated On:	P	S	SE	35	36N	13W	Barron	0-225-86-2021	4.1	0.0	2.5	4.0	18.0	2.698	2.731	1.198		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
CEPRESS 55-71-010-QRY Created On: 03/21/18 Updated On:	Q	SE	NE	2	23N	2E	Wood	0-225-132-2018		0.0	1.3	2.4	12.3	2.723	2.734	0.403		
	Approved Use : HMA<MT, HMA>=MT, Base Aggregate																	
CEPRESS 55-71-010-QRY Created On: 06/28/22 Updated On:	Q	SE	NE	2	23N	2E	Wood	0-225-243-2022		0.0	1.0	3.5	14.4	2.706	2.722	0.602		
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																	
CHARLIE MILLER 55-56-005-QRY Created On: 01/09/15 Updated On:	Q			17	13N	2E	Sauk	0-225-53-2015		0.0	4.6	10.2	36.6	2.615	2.668	2.057		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
CHARLIE MILLER 55-56-005-QRY Created On: 01/03/18 Updated On:	Q			17	13N	2E	Sauk	0-225-13-2018	1.0	0.0	1.9	8.5	34.8	2.626	2.676	1.939		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
CHARLIE MILLER 55-56-005-QRY Created On: 01/04/21 Updated On:	Q			17	13N	2E	Sauk	0-225-24-2021	1.2	0.0	1.7	7.6	32.3	2.626	2.681	2.083		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
CHARLIE MILLER 55-56-005-QRY Created On: 01/02/24 Updated On:	Q		17	13N	2E	Sauk		0-225-123-2024	2.4	6.3	1.5	10.7	38.5	2.599	2.656	2.198	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
CHASE (NEA) 55-42-003-QRY Created On: 01/12/16 Updated On:	Q	NW	NE	17	26N	19E	Oconto	0-225-48-2016		0.2	1.2	3.9	20.7	2.759	2.782	0.821	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
CHASE (NEA) 55-42-003-QRY Created On: 05/12/21 Updated On:	Q	NW	NE	17	26N	19E	Oconto	0-225-205-2021	0.0	0.9	0.2	4.7	20.7	2.776	2.795	0.714	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
CHASE (NEA) 55-42-003-QRY Created On: 01/02/24 Updated On:	Q	NW	NE	17	26N	19E	Oconto	0-225-10-2024	0.6	3.6	0.2	6.2	25.9	2.765	2.788	0.815	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
CHELSEA 55-60-036-PIT Created On: 01/02/24 Updated On:	P	N	SE	10	32N	1E	Taylor	0-225-114-2024	0.5	0.0	3.4	3.1	17.2	2.688	2.716	1.029	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
CHRISTIAN - GADE 55-14-006-PIT Created On: 01/07/16 Updated On:	P	W	SW	33	12N	15E	Dodge	0-225-41-2016		11.7	2.6	5.4	25.5	2.743	2.779	1.332	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
CHRISTIAN - GADE 55-14-006-PIT Created On: 01/04/21 Updated On:	P	W	SW	33	12N	15E	Dodge	0-225-5-2021	0.0	14.4	2.5	5.7	25.9	2.728	2.772	1.598	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
CISLER 55-37-016-QRY Created On: 01/06/16 Updated On:	Q	NW	NW	5	26N	7E	Marathon	0-225-29-2016		0.0	0.5	3.9	17.2	2.680	2.691	0.411		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
CISLER 55-37-016-QRY Created On: 01/04/19 Updated On:	Q	NW	NW	5	26N	7E	Marathon	0-225-32-2019		0.0	0.2	2.6	13.6	2.683	2.691	0.319		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
CISLER 55-37-016-QRY Created On: 04/01/19 Updated On:	Q	NW	NW	5	26N	7E	Marathon	0-225-121-2019	0.0	0.0	0.4	4.3	18.4	2.678	2.688	0.350		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
CISLER 55-37-016-QRY Created On: 01/04/22 Updated On:	Q	NW	NW	5	26N	7E	Marathon	0-225-37-2022	0.0	1.3	1.9	4.2	18.7	2.660	2.677	0.650		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
CLARK 27-00-013-PIT Created On: 05/09/16 Updated On:	P	NW	SW	26	41N	17W	Pine	0-225-166-2016		3.9	3.1	3.1	15.9	2.781	2.820	1.402		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
CLARK 55-62-006-QRY Created On: 05/19/16 Updated On:	Q	SE	SW	28	13N	1E	Vernon	0-225-181-2016	1.0	5.4	6.6	8.5	37.3	2.615	2.673	2.211		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
CLARK 55-62-006-QRY Created On: 07/25/19 Updated On:	Q	SE	SW	28	13N	1E	Vernon	0-225-251-2019	0.8	5.4	4.8	8.2	37.1	2.639	2.693	2.033		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
CLARK 27-00-013-PIT Created On: 06/10/21 Updated On:	P	NW	SW	26	41N	17W	Pine	0-225-219-2021	2.0	2.9	1.6	4.2	19.2	2.797	2.820	0.837	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
CLARK 55-62-006-QRY Created On: 04/05/22 Updated On:	Q	SE	SW	28	13N	1E	Vernon	0-225-167-2022	0.7	9.7	6.6	8.3	36.1	2.625	2.683	2.213	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
CLEARWATER ACRES LLP 55-51-056-PIT Created On: 01/09/20 Updated On:	P		NE	17	4N	19E	Racine	0-225-94-2020		0.0	4.6	5.6	28.7	2.625	2.673	1.797	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
* CLEEREMAN 55-42-044-PIT Created On: 05/24/19 Updated On:	P	SE	SE	32	33N	16E	Oconto	0-225-199-2019	0.0	0.0	0.5	4.6	22.0	2.681	2.703	0.812	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
CLOCKMAKER 55-62-007-QRY Created On: 01/07/14 Updated On:	Q	SE	NW	26	14N	4W	Vernon	0-225-34-2014		0.0	6.6	9.6	36.0	2.613	2.669	2.139	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
CLOCKMAKER 55-62-007-QRY Created On: 01/05/17 Updated On:	Q	SE	NW	26	14N	4W	Vernon	0-225-31-2017		0.0	5.1	10.0	38.3	2.585	2.650	2.489	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
CLOCKMAKER 55-62-007-QRY Created On: 01/08/20 Updated On:	Q	SE	NW	26	14N	4W	Vernon	0-225-63-2020	0.6	0.0	1.5	7.6	33.1	2.644	2.692	1.815	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
CLOCKMAKER 55-62-007-QRY Created On: 01/03/23 Updated On:	Q	SE	NW	26	14N	4W	Vernon	0-225-68-2023	0.7	3.0	1.6	9.8	31.8	2.646	2.694	1.833		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
CLOVERLEAF QUARRY 55-15-032-QRY Created On: 03/13/24 Updated On:	Q	NW	SE	19	27N	25E	Door	0-225-202-2024	0.0	0.0	0.7	6.5	30.6	2.754	2.775	0.759		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
COLBY 55-16-005-QRY Created On: 02/05/14 Updated On:	Q	NE	SW	25	48N	11W	Douglas	0-225-81-2014		0.0	15.2	5.5	20.9	2.787	2.818	1.120		
	Approved Use : Base Aggregate																	
COLBY 55-16-005-QRY Created On: 02/13/17 Updated On:	Q	NE	SW	25	48N	11W	Douglas	0-225-66-2017		0.0	14.4	4.5	20.3	2.798	2.834	1.297		
	Approved Use : Base Aggregate																	
COLBY 55-16-005-QRY Created On: 01/08/20 Updated On:	Q	NE	SW	25	48N	11W	Douglas	0-225-59-2020	0.4	0.0	15.5	5.4	21.6	2.818	2.857	1.368		
	Approved Use : Base Aggregate																	
COLBY 55-16-005-QRY Created On: 01/04/23 Updated On:	Q	NE	SW	25	48N	11W	Douglas	0-225-90-2023	0.0	7.7	13.7	4.7	19.0	2.801	2.841	1.421		
	Approved Use : Base Aggregate																	
COLDSPRING QUARRY 55-37-099-QRY Created On: 01/29/24 Updated On:	Q	SW	SE	34	30N	8E	Marathon	0-225-154-2024	0.2	0.0	1.2	7.1	32.9	2.597	2.612	0.590		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
COLRUE 55-68-033-PIT Created On: 03/01/18 Updated On:	P	SW	NE	31	23N	12E	Waupaca	0-225-110-2018	0.3	0.0	1.3	6.0	27.0	2.680	2.705	0.935		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
COLRUE 55-68-033-PIT Created On: 04/17/23 Updated On:	P	SW	NE	31	23N	12E	Waupaca	0-225-198-2023	1.1	1.6	2.6	5.9	26.9	2.612	2.646	1.298		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
COOMBS 55-35-004-PIT Created On: 01/03/18 Updated On:	P			16	34N	7E	Lincoln	0-225-4-2018	0.2	0.0	1.2	4.3	21.1	2.724	2.745	0.766		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
COOMBS 55-35-004-PIT Created On: 05/22/23 Updated On:	P			16	34N	7E	Lincoln	0-225-224-2023	0.3	0.0	2.8	4.5	20.3	2.749	2.773	0.858		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
COOMBS SOUTH 55-35-005-PIT Created On: 05/10/18 Updated On:	P		NW	21	34N	7E	Lincoln	0-225-204-2018	1.3	0.0	1.4	4.7	22.9	2.709	2.732	0.819		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
COOMBS SOUTH 55-35-005-PIT Created On: 01/02/24 Updated On:	P		NW	21	34N	7E	Lincoln	0-225-67-2024	0.3	2.9	3.2	4.2	20.5	2.683	2.714	1.138		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
COUNTRY SIDE WOODS 55-64-054-PIT Created On: 05/13/19 Updated On:	P		SW	20	3N	16E	Walworth	0-225-187-2019	1.7	2.8	0.8	6.3	26.9	2.649	2.689	1.508		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
COUNTRY SIDE WOODS 55-64-054-PIT Created On: 02/10/22 Updated On:	P		SW	20	3N	16E	Walworth	0-225-120-2022	3.3	6.8	1.6	5.1	26.1	2.676	2.714	1.430	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
CRETEX-MAIN 55-51-015-PIT Created On: 05/21/18 Updated On:	P		NW	6	2N	19E	Racine	0-225-214-2018	1.8	13.1	7.1	5.5	26.6	2.667	2.708	1.560	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
CRETEX-MAIN 55-51-015-PIT Created On: 04/05/23 Updated On:	P		NW	6	2N	19E	Racine	0-225-186-2023	1.4	16.2	11.6	7.4	36.9	2.557	2.612	2.148	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
* CRETEX-WARREN 55-51-007-QRY Created On: 03/24/16 Updated On:	Q		NE	4	2N	19E	Racine	0-225-108-2016		0.0	11.1	7.6	27.3	2.615	2.668	2.026	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
* CRETEX-WARREN 55-51-007-QRY Created On: 06/18/21 Updated On:	Q		NE	4	2N	19E	Racine	0-225-229-2021	0.0	18.0	10.3	6.1	26.3	2.549	2.630	3.176	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
* CRIVITZ 55-38-043-PIT Created On: 03/05/19 Updated On:	P		SE	15	32N	20E	Marinette	0-225-108-2019	1.1	0.0	3.3	6.1	28.2	2.705	2.745	1.444	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
CROFT 55-22-010-QRY Created On: 04/07/16 Updated On:	Q	NW	SE	24	6N	3W	Grant	0-225-132-2016	0.8	24.3	17.5	12.0	41.8	2.577	2.651	2.876	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
CROFT 55-22-010-QRY Created On: 01/05/17 Updated On:	Q	NW	SE	24	6N	3W	Grant	0-225-23-2017	0.4	16.9	9.9	16.7	49.6	2.554	2.632	3.042		
	Approved Use : CONCRETE, Base Aggregate																	
CROFT 55-22-010-QRY Created On: 04/25/17 Updated On:	Q	NW	SE	24	6N	3W	Grant	0-225-153-2017	0.2	17.2	12.9	11.8	41.4	2.579	2.651	2.777		
	Approved Use : Base Aggregate																	
CROFT 55-22-010-QRY Created On: 05/21/18 Updated On:	Q	NW	SE	24	6N	3W	Grant	0-225-216-2018	0.3	14.9	10.3	13.4	44.3	2.561	2.639	3.057		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
CROFT 55-22-010-QRY Created On: 01/05/21 Updated On:	Q	NW	SE	24	6N	3W	Grant	0-225-56-2021	2.7	15.3	17.5	15.9	48.0	2.515	2.606	3.633		
	Approved Use : Base Aggregate																	
CROFT 55-22-010-QRY Created On: 01/02/24 Updated On:	Q	NW	SE	24	6N	3W	Grant	0-225-39-2024	1.4	11.8	5.2	12.8	39.8	2.530	2.617	3.433		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
CRONIN 55-53-006-PIT Created On: 05/18/18 Updated On:	P	S	SE	5	2N	13E	Rock	0-225-212-2018	1.1	0.0	4.2	5.6	27.8	2.663	2.702	1.458		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
CRONIN 55-53-006-PIT Created On: 01/03/23 Updated On:	P	S	SE	5	2N	13E	Rock	0-225-13-2023		0.0	1.4	4.8	25.3	2.637	2.679	1.577		
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
CROOKED LAKE 55-04-003-PIT Created On: 02/05/14 Updated On:	P	SW	NW	36	47N	8W	Bayfield	0-225-82-2014		0.0	1.4	3.5	16.7	2.771	2.796	0.895	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
CROOKED LAKE 55-04-003-PIT Created On: 01/07/19 Updated On:	P	SW	NW	36	47N	8W	Bayfield	0-225-58-2019	1.7	0.0	1.9	5.9	22.7	2.814	2.844	1.078	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
CROOKED LAKE 55-04-003-PIT Created On: 01/02/24 Updated On:	P	SW	NW	36	47N	8W	Bayfield	0-225-91-2024	1.4	2.1	2.7	3.4	16.6	2.817	2.843	0.926	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
CTH "N" / MILESTONE 345 55-37-021-QRY Created On: 01/06/16 Updated On:	Q	NW	NE	19	28N	7E	Marathon	0-225-30-2016		0.0	0.5	11.3	45.4	2.579	2.600	0.795	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
CTH "N" / MILESTONE 345 55-37-021-QRY Created On: 01/04/19 Updated On:	Q	NW	NE	19	28N	7E	Marathon	0-225-34-2019	0.0	0.0	0.7	9.8	42.2	2.276	2.286	0.431	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
CTH "N" / MILESTONE 345 55-37-021-QRY Created On: 01/04/22 Updated On:	Q	NW	NE	19	28N	7E	Marathon	0-225-25-2022	0.0	0.2	0.6	7.6	36.6	2.603	2.617	0.563	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
CTH R 55-35-009-PIT Created On: 07/07/14 Updated On:	P	SE	NE	7	32N	7E	Lincoln	0-225-209-2014		0.0	1.5	4.3	20.3	2.744	2.773	1.068	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
CTH R 55-35-009-PIT Created On: 07/26/21 Updated On:	P	SE	NE	7	32N	7E	Lincoln	0-225-251-2021	0.4	0.0	5.1	4.7	21.3	2.715	2.748	1.217	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
CUSTER 55-49-004-PIT Created On: 01/06/16 Updated On:	P		E	4	23N	9E	Portage	0-225-31-2016		0.0	1.9	7.1	27.6	2.680	2.703	0.868	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
CUSTER 55-49-004-PIT Created On: 01/04/21 Updated On:	P		E	4	23N	9E	Portage	0-225-20-2021	0.0	0.0	0.7	7.3	29.0	2.650	2.683	1.214	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
CZAPIGA 55-26-005-PIT Created On: 06/11/20 Updated On:	P	NE	SE	26	42N	35W	Iron	0-225-194-2020		1.6	0.9	3.2	16.6	2.736	2.754	0.681	
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																
D AND J 55-05-003-QRY Created On: 04/05/16 Updated On:	Q	S	NW	5	22N	21E	Brown	0-225-122-2016	3.0	1.4	1.2	6.3	28.9	2.703	2.749	1.717	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
D AND J 55-05-003-QRY Created On: 04/19/19 Updated On:	Q	S	NW	5	22N	21E	Brown	0-225-149-2019	2.0	1.1	2.9	6.2	27.4	2.709	2.748	1.437	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
D AND J 55-05-003-QRY Created On: 01/04/22 Updated On:	Q	S	NW	5	22N	21E	Brown	0-225-72-2022	6.3	10.3	3.4	7.5	29.1	2.656	2.704	1.797	
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
* D AND J SCRAYS HILL 55-05-004-QRY Created On: 04/05/16 Updated On:	Q		NW 6	22N	21E	Brown		0-225-120-2016	0.1	2.9	1.3	9.1	36.3	2.702	2.748	1.721		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
* D AND J SCRAYS HILL 55-05-004-QRY Created On: 02/24/21 Updated On:	Q		NW 6	22N	21E	Brown		0-225-129-2021		2.4	2.4	9.3	37.7	2.681	2.727	1.712		
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																	
D and J CHASE 55-42-006-QRY Created On: 04/01/16 Updated On:	Q	E	NE 17	26N	19E	Oconto		0-225-118-2016	0.4	8.3	1.3	6.2	26.8	2.718	2.753	1.279		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
D and J CHASE 55-42-006-QRY Created On: 04/24/19 Updated On:	Q	E	NE 17	26N	19E	Oconto		0-225-163-2019	0.0	0.8	1.2	5.1	22.9	2.858	2.879	0.705		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
D and J CHASE 55-42-006-QRY Created On: 01/04/22 Updated On:	Q	E	NE 17	26N	19E	Oconto		0-225-70-2022	1.1	3.7	3.0	5.2	24.6	2.749	2.770	0.762		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
DALKA 55-35-043-PIT Created On: 04/24/19 Updated On:	P	SW	SW 3	35N	8E	Lincoln		0-225-170-2019	0.6	0.0	0.3	4.6	21.5	2.671	2.694	0.868		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
DALKA 55-35-043-PIT Created On: 01/02/24 Updated On:	P	SW	SW 3	35N	8E	Lincoln		0-225-66-2024	0.0	0.0	1.3	4.3	18.7	2.699	2.724	0.917		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
DARIEN 55-64-055-PIT Created On: 06/25/21 Updated On:	P	W	NW	7	2N	15E	Walworth	0-225-234-2021	0.1	5.3	6.7	6.2	25.6	2.662	2.706	1.648	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
DB 55-49-007-QRY Created On: 08/28/14 Updated On:	Q	SW	SW	1	25N	7E	Portage	0-225-250-2014		0.0	1.3	4.7	20.5	2.634	2.651	0.643	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
DB 55-49-007-QRY Created On: 03/21/18 Updated On:	Q	SW	SW	1	25N	7E	Portage	0-225-133-2018		0.0	2.1	5.7	22.6	2.647	2.666	0.741	
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																
DB 55-49-007-QRY Created On: 06/28/22 Updated On:	Q	SW	SW	1	25N	7E	Portage	0-225-240-2022		0.0	1.3	5.2	21.1	2.680	2.699	0.713	
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																
DE LAET 55-38-012-PIT Created On: 06/13/22 Updated On:	P	SE	SE	14	34N	20E	Marinette	0-225-222-2022	3.0	0.0	1.8	6.6	31.8	2.718	2.745	0.977	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
DEITER 55-22-013-QRY Created On: 04/24/14 Updated On:	Q	NW	NW	29	2N	1W	Grant	0-225-140-2014		1.1	5.5	10.9	37.5	2.617	2.684	2.567	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
DEITER 55-22-013-QRY Created On: 04/06/17 Updated On:	Q	NW	NW	29	2N	1W	Grant	0-225-112-2017	0.7	1.4	1.4	10.0	38.1	2.573	2.644	2.760	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
DEITER 55-22-013-QRY Created On: 07/28/17 Updated On:	Q	NW	NW	29	2N	1W	Grant	0-225-242-2017	0.4	2.1	2.1	12.5	43.6	2.554	2.630	2.995	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
DEITER 55-22-013-QRY Created On: 04/28/20 Updated On:	Q	NW	NW	29	2N	1W	Grant	0-225-158-2020	2.1	1.7	2.6	12.9	42.2	2.548	2.627	3.105	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
DEITER 55-22-013-QRY Created On: 01/03/23 Updated On:	Q	NW	NW	29	2N	1W	Grant	0-225-6-2023	0.1	2.0	3.6	11.7	42.0	2.536	2.625	3.500	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
DELARULLE 55-19-003-PIT Created On: 06/19/14 Updated On:	P	SE	SW	12	39N	17E	Florence	0-225-200-2014			2.3	8.0	28.2				
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
DELARULLE 55-19-003-PIT Created On: 01/04/19 Updated On:	P	SE	SW	12	39N	17E	Florence	0-225-12-2019	0.0	0.0	3.2	6.2	29.1	2.619	2.664	1.744	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
DELARULLE 55-19-003-PIT Created On: 01/02/24 Updated On:	P	SE	SW	12	39N	17E	Florence	0-225-12-2024	1.1	0.0	0.5	5.9	26.0	2.641	2.682	1.551	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
DENMARK 55-05-005-QRY Created On: 01/06/14 Updated On:	Q		E	36	22N	22E	Brown	0-225-10-2014		0.6	0.3	5.2	25.2	2.793	2.809	0.585	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
DENMARK 55-05-005-QRY Created On: 01/05/17 Updated On:	Q		E	36	22N	22E	Brown	0-225-41-2017		2.0	0.4	4.5	21.6	2.792	2.809	0.627		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
DENMARK 55-05-005-QRY Created On: 01/02/20 Updated On:	Q		E	36	22N	22E	Brown	0-225-8-2020		14.4	0.4	6.0	25.9	2.791	2.821	1.089		
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																	
DENMARK 55-05-005-QRY Created On: 01/03/23 Updated On:	Q		E	36	22N	22E	Brown	0-225-44-2023	0.0	1.8	0.4	5.5	25.1	2.792	2.809	0.618		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
* DEWEY 55-49-029-QRY Created On: 07/18/19 Updated On:	Q	NE	SW	25	25N	7E	Portage	0-225-240-2019	0.0	0.0	1.2	6.8	25.7	2.981	3.009	0.950		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
DIPPEL 55-59-005-PIT Created On: 02/15/18 Updated On:	P	NE	SE	32	15N	20E	Sheboygan	0-225-100-2018		1.8	1.3	6.6	30.2	2.728	2.760	1.155		
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																	
DIPPEL 55-59-005-PIT Created On: 01/03/23 Updated On:	P	NE	SE	32	15N	20E	Sheboygan	0-225-47-2023	1.4	0.0	0.7	7.2	32.5	2.720	2.754	1.254		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
DON MILLER 55-47-006-QRY Created On: 06/08/15 Updated On:	Q	N	NE	10	27N	15W	Pierce	0-225-191-2015		0.0	6.3	10.3	36.1	2.555	2.625	2.717		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
DON MILLER 55-47-006-QRY Created On: 01/03/18 Updated On:	Q	N	NE	10	27N	15W	Pierce	0-225-34-2018	3.2	0.0	1.1	9.4	34.4	2.559	2.628	2.668		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
DON MILLER 55-47-006-QRY Created On: 01/05/21 Updated On:	Q	N	NE	10	27N	15W	Pierce	0-225-73-2021	2.2	0.0	0.1	8.3	31.8	2.603	2.659	2.146		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
DON MILLER 55-47-006-QRY Created On: 01/02/24 Updated On:	Q	N	NE	10	27N	15W	Pierce	0-225-77-2024	4.1	0.0	5.8	11.0	39.4	2.550	2.624	2.893		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
DONSKEY 55-41-004-QRY Created On: 04/08/15 Updated On:	Q	NW	SE	11	16N	3W	Monroe	0-225-112-2015		0.0	2.4	9.2	37.6	2.625	2.677	1.979		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
DONSKEY 55-41-004-QRY Created On: 05/04/17 Updated On:	Q	NW	SE	11	16N	3W	Monroe	0-225-169-2017	1.6	0.0	3.3	10.0	38.4	2.622	2.674	1.956		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
DONSKEY 55-41-004-QRY Created On: 03/23/18 Updated On:	Q	NW	SE	11	16N	3W	Monroe	0-225-146-2018	0.5	0.0	7.9	11.2	41.2	2.589	2.653	2.482		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
DONSKEY 55-41-004-QRY Created On: 01/03/20 Updated On:	Q	NW	SE	11	16N	3W	Monroe	0-225-18-2020	1.2	0.0	3.7	9.7	38.3	2.608	2.670	2.375		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
DONSKEY 55-41-004-QRY Created On: 01/03/23 Updated On:	Q	NW	SE	11	16N	3W	Monroe	0-225-65-2023	2.3	1.8	6.3	11.9	44.4	2.567	2.635	2.661	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
DOOLEY 55-52-008-QRY Created On: 06/05/15 Updated On:	Q			9	12N	2E	Richland	0-225-187-2015		0.0	1.7	9.2	35.8	2.637	2.685	1.851	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
DOOLEY 55-52-008-QRY Created On: 01/04/18 Updated On:	Q			9	12N	2E	Richland	0-225-50-2018	0.5	0.0	3.1	9.1	36.1	2.628	2.683	2.076	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
DOOLEY 55-52-008-QRY Created On: 01/04/21 Updated On:	Q			9	12N	2E	Richland	0-225-31-2021	0.4	0.0	2.2	9.2	35.8	2.615	2.673	2.222	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
DOOLEY 55-52-008-QRY Created On: 01/02/24 Updated On:	Q			9	12N	2E	Richland	0-225-122-2024	0.8	4.6	1.2	9.5	35.6	2.631	2.691	2.285	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
DOSKOCIL QUARRY 55-12-007-QRY Created On: 06/12/14 Updated On:	Q	S	SE	2	9N	5W	Crawford	0-225-194-2014		0.7	4.3	11.1	39.6	2.577	2.642	2.513	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
DOSKOCIL QUARRY 55-12-007-QRY Created On: 05/19/17 Updated On:	Q	S	SE	2	9N	5W	Crawford	0-225-191-2017		1.4	5.9	10.4	39.6	2.566	2.637	2.788	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
DOSKOCIL QUARRY 55-12-007-QRY Created On: 01/09/20 Updated On:	Q	S	SE	2	9N	5W	Crawford	0-225-83-2020	0.4	3.5	2.0	13.1	46.3	2.502	2.569	2.645	
DOSKOCIL QUARRY 55-12-007-QRY Created On: 01/02/24 Updated On:	Q	S	SE	2	9N	5W	Crawford	0-225-37-2024	1.2	3.5	0.5	9.3	39.2	2.606	2.664	2.235	
DOWNING (RIEMANN) 55-55-004-QRY Created On: 06/20/22 Updated On:	Q	E	SE	1	29N	15W	St. Croix	0-225-231-2022	2.2	1.2	5.8	11.2	46.6	2.542	2.623	3.188	
DREPHALS 55-44-011-QRY Created On: 04/17/14 Updated On:	Q		E	17	24N	17E	Outagamie	0-225-131-2014		0.3	2.1	6.9	30.6	2.721	2.758	1.348	
DREPHALS 55-44-011-QRY Created On: 05/11/17 Updated On:	Q		E	17	24N	17E	Outagamie	0-225-181-2017		3.9	2.5	7.1	30.0	2.717	2.753	1.342	
DREPHALS 55-44-011-QRY Created On: 03/17/22 Updated On:	Q		E	17	24N	17E	Outagamie	0-225-144-2022	0.5	1.0	1.2	10.2	36.8	2.727	2.762	1.293	
DRESSER TRAP 55-48-007-QRY Created On: 01/05/16 Updated On:	Q			5	33N	18W	Polk	0-225-25-2016		0.0	3.6	4.6	16.8	2.880	2.903	0.792	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
DRESSER TRAP 55-48-007-QRY Created On: 01/10/22 Updated On:	Q		5	33N	18W	Polk		0-225-108-2022	0.0	1.4	1.2	2.1	9.2	2.933	2.948	0.522	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
* DUAME #1 55-42-001-QRY Created On: 04/27/17 Updated On:	Q	SE	SE	31	29N	21E	Oconto	0-225-160-2017	0.7	5.9	8.7	10.1	36.8	2.683	2.722	1.456	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
* DUAME #1 55-42-001-QRY Created On: 02/24/21 Updated On:	Q	SE	SE	31	29N	21E	Oconto	0-225-130-2021	0.1	1.8	4.3	8.8	36.6	2.705	2.746	1.532	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
DUESSING 55-60-007-PIT Created On: 06/26/17 Updated On:	P	N	SW	33	32N	1E	Taylor	0-225-221-2017		0.0	0.6	3.5	17.4	2.743	2.769	0.947	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
DUESSING 55-60-007-PIT Created On: 06/28/22 Updated On:	P	N	SW	33	32N	1E	Taylor	0-225-238-2022	0.7	0.0	2.0	4.1	18.4	2.742	2.768	0.948	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
DUNN 55-33-008-QRY Created On: 03/23/17 Updated On:	Q		SW	22	2N	3E	Lafayette	0-225-89-2017	1.8	5.3	7.4	10.5	38.9	2.584	2.654	2.710	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
DUNN 55-33-008-QRY Created On: 02/09/18 Updated On:	Q		SW	22	2N	3E	Lafayette	0-225-92-2018	1.1	3.0	9.0	7.5	33.8	2.563	2.639	2.964	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
DUNN 55-33-008-QRY Created On: 03/17/21 Updated On:	Q		SW	22	2N	3E	Lafayette	0-225-138-2021	0.7	14.2	2.4	9.1	36.3	2.581	2.650	2.678	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
DUNN 55-33-008-QRY Created On: 02/28/24 Updated On:	Q		SW	22	2N	3E	Lafayette	0-225-182-2024	1.6	12.4	8.3	9.5	38.3	2.578	2.649	2.754	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
DURAND 55-46-002-QRY Created On: 06/08/15 Updated On:	Q	SW	SW	33	25N	13W	Pepin	0-225-190-2015		0.0	3.0	10.4	37.9	2.586	2.654	2.632	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
DURAND 55-46-002-QRY Created On: 01/03/18 Updated On:	Q	SW	SW	33	25N	13W	Pepin	0-225-28-2018	1.0	0.0	1.8	9.1	34.5	2.588	2.656	2.604	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
DURAND 55-46-002-QRY Created On: 01/05/21 Updated On:	Q	SW	SW	33	25N	13W	Pepin	0-225-69-2021	1.3	0.0	0.5	8.2	33.0	2.596	2.666	2.675	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
DURAND 55-46-002-QRY Created On: 01/02/24 Updated On:	Q	SW	SW	33	25N	13W	Pepin	0-225-76-2024	0.8	1.4	4.9	9.8	37.9	2.592	2.660	2.613	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
DUSICK 55-09-024-PIT Created On: 05/17/22 Updated On:	P	SE	NW	17	29N	5W	Chippewa	0-225-205-2022	0.3	0.0	1.0	3.5	17.6	2.763	2.782	0.682	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %			
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine		
DW 55-53-043-PIT Created On: 05/02/19 Updated On:	P	SW	7	3N	13E	Rock	0-225-174-2019	2.7	0.0	6.2	7.5	33.2	2.608	2.677	2.644				
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																		
DW 55-53-043-PIT Created On: 02/10/22 Updated On:	P	SW	7	3N	13E	Rock	0-225-122-2022	5.5	4.3	1.6	8.1	29.0	2.651	2.692	1.551				
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																		
EARL'S 55-10-005-QRY Created On: 03/24/16 Updated On:	Q	NE	NE	10	28N	4W	Clark	0-225-116-2016		0.0	2.3	5.4	22.3	2.819	2.833	0.495			
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																		
EARL'S 55-10-005-QRY Created On: 01/08/19 Updated On:	Q	NE	NE	10	28N	4W	Clark	0-225-76-2019		0.0	1.5	4.7	21.8	2.824	2.835	0.380			
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																		
EARL'S 55-10-005-QRY Created On: 05/17/22 Updated On:	Q	NE	NE	10	28N	4W	Clark	0-225-204-2022	0.0	0.0	0.3	3.7	18.2	2.777	2.786	0.322			
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
EGSTAD 55-03-014-PIT Created On: 05/18/17 Updated On:	P	S	SW	34	35N	14W	Barron	0-225-188-2017		0.0	4.0	5.3	20.3	2.727	2.766	1.421			
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																		
EGSTAD 55-03-014-PIT Created On: 04/05/22 Updated On:	P	S	SW	34	35N	14W	Barron	0-225-159-2022	1.9	4.8	7.2	5.2	20.0	2.741	2.773	1.151			
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
EHLER-COBB 55-25-008-QRY Created On: 04/24/14 Updated On:	Q	SE	SE	14	6N	1E	Iowa	0-225-145-2014	0.8	8.1	8.6	13.5	40.5	2.593	2.662	2.637	
EHLER-COBB 55-25-008-QRY Created On: 04/06/17 Updated On:	Q	SE	SE	14	6N	1E	Iowa	0-225-114-2017	1.1	6.2	4.5	14.4	40.1	2.531	2.607	3.013	
EHLER-COBB 55-25-008-QRY Created On: 04/28/20 Updated On:	Q	SE	SE	14	6N	1E	Iowa	0-225-162-2020	0.7	5.4	5.1	15.0	46.7	2.554	2.633	3.079	
EHLER-COBB 55-25-008-QRY Created On: 01/03/23 Updated On:	Q	SE	SE	14	6N	1E	Iowa	0-225-10-2023	0.7	7.0	9.0	12.5	44.2	2.551	2.631	3.167	
ELMWOOD 55-47-008-QRY Created On: 05/09/16 Updated On:	Q	SE	SE	36	27N	15W	Pierce	0-225-164-2016		0.0	3.9	8.3	30.5	2.666	2.708	1.573	
ELMWOOD 55-47-008-QRY Created On: 01/07/19 Updated On:	Q	SE	SE	36	27N	15W	Pierce	0-225-64-2019	2.5	0.0	7.8	14.1	45.8	2.493	2.588	3.836	
ELMWOOD 55-47-008-QRY Created On: 04/05/22 Updated On:	Q	SE	SE	36	27N	15W	Pierce	0-225-160-2022	0.5	0.0	8.2	12.4	44.9	2.555	2.627	2.821	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
ELMWOOD CTH G QUARRY 55-47-036-QRY Created On: 03/27/24 Updated On:	Q	SE	SE	34	27N	15W	Pierce	0-225-208-2024	4.1	0.0	6.1	12.9	41.6	2.562	2.631	2.703	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
ELMWOOD CTH S QUARRY 55-47-037-QRY Created On: 03/27/24 Updated On:	Q	SE	SW	15	26N	15W	Pierce	0-225-209-2024	7.2	0.0	5.8	7.7	32.7	2.618	2.668	1.893	
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																
EMPIRE LIME 55-53-010-QRY Created On: 08/08/16 Updated On:	Q	SW	NE	21	1N	12E	Rock	0-225-239-2016	1.5	6.3	12.6	11.8	41.4	2.564	2.649	3.333	
	Approved Use : Base Aggregate																
EMPIRE LIME 55-53-010-QRY Created On: 03/21/23 Updated On:	Q	SW	NE	21	1N	12E	Rock	0-225-175-2023	0.4	12.2	12.9	11.9	42.0	2.566	2.650	3.286	
	Approved Use : Base Aggregate																
ENDRES 55-41-006-QRY Created On: 07/26/16 Updated On:	Q	NE	SW	22	18N	4W	Monroe	0-225-229-2016	3.2	0.0	5.0	17.2	56.1	2.548	2.623	2.945	
ENDRES 55-41-006-QRY Created On: 08/03/16 Updated On:	Q	NE	SW	22	18N	4W	Monroe	0-225-235-2016	0.4	0.0	4.0	11.4	41.7	2.637	2.687	1.913	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
ENDRES 55-41-006-QRY Created On: 05/13/20 Updated On:	Q	NE	SW	22	18N	4W	Monroe	0-225-178-2020	0.8	0.0	4.6	10.7	39.7	2.629	2.684	2.110	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
ENDRES 55-41-006-QRY Created On: 01/03/23 Updated On:	Q	NE	SW	22	18N	4W	Monroe	0-225-70-2023	0.5	3.9	1.6	11.3	42.2	2.589	2.658	2.665		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
* ERICKSON 55-03-016-PIT Created On: 07/25/19 Updated On:	P	NW	NW	9	35N	13W	Barron	0-225-247-2019	0.6	0.0	1.3	4.3	19.5	2.785	2.807	0.783		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
ERVIN STIEMKE 55-11-013-QRY Created On: 07/03/14 Updated On:	Q	NW	SW	18	10N	10E	Columbia	0-225-207-2014	1.0	0.6	0.8	7.5	32.8	2.562	2.627	2.563		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
ERVIN STIEMKE 55-11-013-QRY Created On: 01/05/17 Updated On:	Q	NW	SW	18	10N	10E	Columbia	0-225-49-2017	1.3	2.5	2.5	11.3	35.5	2.549	2.614	2.559		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
ERVIN STIEMKE 55-11-013-QRY Created On: 01/08/20 Updated On:	Q	NW	SW	18	10N	10E	Columbia	0-225-68-2020	0.1	1.3	3.2	7.9	31.2	2.598	2.658	2.286		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
ERVIN STIEMKE 55-11-013-QRY Created On: 04/04/23 Updated On:	Q	NW	SW	18	10N	10E	Columbia	0-225-177-2023	0.6	1.2	2.2	7.3	29.8	2.556	2.631	2.952		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
ERVIN STIEMKE 55-11-013-QRY Created On: 04/18/24 Updated On:	Q	NW	SW	18	10N	10E	Columbia	0-225-234-2024	0.3	1.1	2.4	7.8	32.9	2.564	2.634	2.741		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
EVANS 55-13-017-QRY Created On: 01/06/20 Updated On:	Q	NW	SW	24	9N	9E	Dane	0-225-29-2020	0.8	1.4	1.9	7.6	31.7	2.614	2.660	1.742		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
EVANS 55-13-017-QRY Created On: 01/04/23 Updated On:	Q	NW	SW	24	9N	9E	Dane	0-225-92-2023	0.7	1.1	1.4	8.8	34.9	2.602	2.661	2.297		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
EVENSON - BERTRAM 55-20-011-QRY Created On: 01/08/15 Updated On:	Q	NE	NW	15	16N	18E	Fond Du Lac	0-225-26-2015		0.2	3.1	11.2	41.8	2.715	2.748	1.245		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
EVENSON - BERTRAM 55-20-011-QRY Created On: 04/13/17 Updated On:	Q	NE	NW	15	16N	18E	Fond Du Lac	0-225-128-2017		1.0	1.2	12.9	44.2	2.714	2.750	1.348		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
EVENSON - BERTRAM 55-20-011-QRY Created On: 01/30/20 Updated On:	Q	NE	NW	15	16N	18E	Fond Du Lac	0-225-106-2020	0.0	0.6	1.1	11.0	42.5	2.720	2.758	1.424		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
EVENSON - BERTRAM 55-20-011-QRY Created On: 01/04/24 Updated On:	Q	NE	NW	15	16N	18E	Fond Du Lac	0-225-149-2024	0.3	0.6	1.0	8.7	36.6	2.759	2.783	0.870		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
EVERSON PIT 55-35-044-PIT Created On: 01/02/24 Updated On:	P	SE	SW	2	35N	8E	Lincoln	0-225-58-2024	0.3	0.0	0.2	3.4	16.1	2.735	2.753	0.641		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
FA 26-00-014-PIT Created On: 04/19/21 Updated On:	P		8	43N	35W	Iron, Mi	0-225-183-2021	0.0	1.0	0.8	4.4	19.1	2.694	2.716	0.810		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
FAIRVIEW QUARRY 55-12-008-QRY Created On: 04/10/14 Updated On:	Q	SW	NE	2	10N	5W	Crawford	0-225-120-2014		1.0	3.5	9.2	33.7	2.646	2.692	1.746	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
FAIRVIEW QUARRY 55-12-008-QRY Created On: 01/05/17 Updated On:	Q	SW	NE	2	10N	5W	Crawford	0-225-30-2017		2.3	5.1	12.0	41.0	2.557	2.625	2.668	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
FAIRVIEW QUARRY 55-12-008-QRY Created On: 01/03/20 Updated On:	Q	SW	NE	2	10N	5W	Crawford	0-225-19-2020	2.6	2.1	1.3	11.1	38.1	2.593	2.653	2.326	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
FAIRVIEW QUARRY 55-12-008-QRY Created On: 01/03/23 Updated On:	Q	SW	NE	2	10N	5W	Crawford	0-225-67-2023	2.3	3.8	1.5	11.6	38.1	2.593	2.658	2.498	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
FARMERSVILLE 55-14-007-QRY Created On: 04/18/22 Updated On:	Q	S	SW	30	13N	17E	Dodge	0-225-176-2022	0.0	0.8	1.5	9.1	37.5	2.690	2.725	1.322	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
FELTES 55-06-010-QRY Created On: 04/23/15 Updated On:	Q	NE	SE	6	20N	10W	Buffalo	0-225-135-2015		0.0	2.3	10.9	38.7	2.613	2.670	2.180	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Coarse Sp. Gravity		Coarse Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
FELTES 55-06-010-QRY Created On: 01/04/18 Updated On:	Q	NE	SE	6	20N	10W	Buffalo	0-225-46-2018	0.7	0.0	1.7	9.2	34.6	2.612	2.672	2.320	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
FELTES 55-06-010-QRY Created On: 04/17/23 Updated On:	Q	NE	SE	6	20N	10W	Buffalo	0-225-197-2023		0.0	5.2	11.3	41.9	2.613	2.672	2.283	
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																
FELTES 55-06-010-QRY Created On: 05/22/23 Updated On:	Q	NE	SE	6	20N	10W	Buffalo	0-225-219-2023	0.2	0.0	2.9	7.4	33.6	2.647	2.697	1.875	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
FINK 55-13-020-QRY Created On: 01/04/22 Updated On:	Q	NW	NW	14	6N	6E	Dane	0-225-44-2022	0.8	7.7	11.0	11.7	43.2	2.552	2.628	2.944	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
FINK (YAHARA) 55-13-021-QRY Created On: 03/19/15 Updated On:	Q	SE	NW	14	6N	6E	Dane	0-225-98-2015		8.2	4.0	10.4	38.4	2.563	2.635	2.807	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
FINK (YAHARA) 55-13-021-QRY Created On: 01/03/18 Updated On:	Q	SE	NW	14	6N	6E	Dane	0-225-27-2018	1.0	10.3	8.2	10.5	40.7	2.506	2.599	3.703	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
FINK (YAHARA) 55-13-021-QRY Created On: 06/20/22 Updated On:	Q	SE	NW	14	6N	6E	Dane	0-225-234-2022	0.6	0.8	2.1	7.7	33.0	2.679	2.719	1.507	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
FITCHBURG HILLS QUARRY 55-13-127-QRY Created On: 03/27/24 Updated On:	Q	NE	NE	18	6N	9E	Dane	0-225-217-2024	0.2	9.2	4.7	8.9	37.8	2.602	2.672	2.669	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
FLANNERY 55-33-009-QRY Created On: 04/16/15 Updated On:	Q	NW	SW	6	2N	5E	Lafayette	0-225-125-2015	1.3	8.1	2.4	7.7	31.6	2.643	2.692	1.852	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
FLANNERY 55-21-004-PIT Created On: 05/11/15 Updated On:	P	SW	SE	33	36N	13E	Forest	0-225-165-2015		0.0	0.5	5.4	23.3	2.701	2.729	1.042	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
FLANNERY 55-33-009-QRY Created On: 03/23/18 Updated On:	Q	NW	SW	6	2N	5E	Lafayette	0-225-141-2018	2.4	17.0	4.0	7.4	28.8	2.597	2.658	2.340	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
FLANNERY 55-33-009-QRY Created On: 01/07/19 Updated On:	Q	NW	SW	6	2N	5E	Lafayette	0-225-53-2019	1.5	9.5	5.4	7.5	29.9	2.603	2.660	2.196	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
FLANNERY 55-33-009-QRY Created On: 04/28/20 Updated On:	Q	NW	SW	6	2N	5E	Lafayette	0-225-163-2020	0.9	6.5	3.5	9.8	34.6	2.599	2.662	2.392	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
FLANNERY 55-21-004-PIT Created On: 07/16/20 Updated On:	P	SW	SE	33	36N	13E	Forest	0-225-221-2020	0.0	0.0	0.4	5.2	23.5	2.743	2.762	0.685	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
FLANNERY 55-33-009-QRY Created On: 03/17/21 Updated On:	Q	NW	SW	6	2N	5E	Lafayette	0-225-148-2021	3.0	8.3	3.4	9.8	35.3	2.560	2.634	2.864	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
FLANNERY 55-33-009-QRY Created On: 03/15/22 Updated On:	Q	NW	SW	6	2N	5E	Lafayette	0-225-143-2022	1.3	5.4	7.0	10.0	35.1	2.635	2.688	1.987	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
FLANNERY 55-33-009-QRY Created On: 01/03/23 Updated On:	Q	NW	SW	6	2N	5E	Lafayette	0-225-5-2023	1.2	4.1	3.8	6.9	29.0	2.609	2.669	2.290	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
FLANNERY 55-33-009-QRY Created On: 01/04/24 Updated On:	Q	NW	SW	6	2N	5E	Lafayette	0-225-139-2024	0.8	6.9	8.1	8.8	36.9	2.610	2.671	2.312	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
* FOOTVILLE ROCK & LIME 55-53-011-QRY Created On: 03/22/19 Updated On:	Q	SE	NW	2	2N	10E	Rock	0-225-115-2019	0.1	5.8	10.5	6.0	28.3	2.648	2.703	2.051	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
* FOOTVILLE ROCK & LIME 55-53-011-QRY Created On: 01/03/23 Updated On:	Q	SE	NW	2	2N	10E	Rock	0-225-61-2023	1.0	16.2	17.4	11.1	40.6	2.570	2.654	3.255	
	Approved Use : Base Aggregate																
FORDE 55-12-009-QRY Created On: 01/04/24 Updated On:	Q	SE	NE	5	10N	6W	Crawford	0-225-137-2024	0.2	16.0	4.6	9.5	34.9	2.606	2.672	2.521	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
FOSTER 55-38-015-QRY Created On: 01/04/22 Updated On:	Q	SE	SE	19	31N	22E	Marinette	0-225-91-2022	0.0	7.3	6.6	6.9	32.0	2.696	2.731	1.314	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
FOSTERS 55-60-008-PIT Created On: 07/07/22 Updated On:	P	NW	SE	20	33N	3W	Taylor	0-225-244-2022	1.9	0.0	3.3	4.5	21.1	2.711	2.739	1.036	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
FRAATZ 55-65-006-PIT Created On: 06/08/17 Updated On:	P		SW	18	41N	12W	Washburn	0-225-207-2017		0.0	3.8	6.0	24.3	2.629	2.682	2.020	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
FRAATZ 55-65-006-PIT Created On: 03/01/23 Updated On:	P		SW	18	41N	12W	Washburn	0-225-162-2023	4.4	0.0	6.9	5.0	22.5	2.661	2.707	1.738	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
FRANKLIN 55-40-008-QRY Created On: 01/21/16 Updated On:	Q		NE	10	5N	21E	Milwaukee	0-225-70-2016	3.5	15.1	2.8	4.4	21.7	2.636	2.695	2.235	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
FRANKLIN 55-40-008-QRY Created On: 05/26/16 Updated On:	Q		NE	10	5N	21E	Milwaukee	0-225-188-2016	0.3	1.3	1.1	5.6	26.0	2.639	2.677	1.453	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
FRANKLIN 55-40-008-QRY Created On: 08/25/17 Updated On:	Q		NE	10	5N	21E	Milwaukee	0-225-266-2017		0.0	1.0	7.9	29.7	2.649	2.704	2.074	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description						Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range					County	100	500	OD	SSD	Crse
FRANKLIN 55-40-008-QRY Created On: 01/09/20 Updated On:	Q		NE	10	5N	21E	Milwaukee	0-225-95-2020	1.5	0.0	3.0	4.5	21.8	2.730	2.760	1.098
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate															
FRANKLIN 55-40-008-QRY Created On: 01/03/23 Updated On:	Q		NE	10	5N	21E	Milwaukee	0-225-82-2023	1.0	3.3	0.3	6.2	29.0	2.578	2.634	2.163
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate															
* FRAWLEY 55-52-010-QRY Created On: 06/21/18 Updated On:	Q			9	10N	2W	Richland	0-225-237-2018	0.8	6.3	9.4	10.2	30.6	2.669	2.716	1.752
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate															
* FRAWLEY 55-52-010-QRY Created On: 03/17/21 Updated On:	Q			9	10N	2W	Richland	0-225-149-2021	1.2	11.2	8.6	12.0	38.9	2.593	2.664	2.737
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate															
FREEDOM - N.E.A. 55-44-012-QRY Created On: 01/06/14 Updated On:	Q	NE	NW	10	22N	18E	Outagamie	0-225-14-2014		0.5	0.4	4.6	20.5	2.790	2.809	0.671
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate															
FREEDOM - N.E.A. 55-44-012-QRY Created On: 01/04/22 Updated On:	Q	NE	NW	10	22N	18E	Outagamie	0-225-13-2022	0.0	2.5	0.3	4.6	21.2	2.757	2.783	0.941
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate															
FRENCHTOWN 19-00-008-QRY Created On: 05/22/19 Updated On:	Q			18	93N	2W	Clayton	0-225-191-2019	0.4	1.4	0.2	5.9	26.6	2.647	2.685	1.444
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate															

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
FRENCHTOWN 19-00-008-QRY Created On: 05/22/19 Updated On:	Q		18	93N	2W	Clayton	0-225-192-2019	0.1	4.3	0.7	6.2	27.7	2.661	2.703	1.558		
FRENCHTOWN 19-00-008-QRY Created On: 01/13/22 Updated On:	Q		18	93N	2W	Clayton	0-225-112-2022	1.8	3.6	2.8	7.5	32.1	2.606	2.660	2.069		
FRENCHTOWN 19-00-008-QRY Created On: 03/27/24 Updated On:	Q		18	93N	2W	Clayton	0-225-207-2024	1.4	14.4	3.9	9.5	36.7	2.580	2.650	2.724		
* FRENS 55-14-038-QRY Created On: 04/05/21 Updated On:	Q	NW	3	13N	14E	Dodge	0-225-169-2021	0.6	3.0	2.9	5.9	25.8	2.770	2.795	0.906		
FREY 55-22-017-QRY Created On: 06/30/16 Updated On:	Q	NW	SE	15	7N	3W	Grant	0-225-216-2016		3.9	4.5	12.0	39.2	2.605	2.668	2.431	
FREY 55-22-017-QRY Created On: 05/12/20 Updated On:	Q	NW	SE	15	7N	3W	Grant	0-225-175-2020	0.7	4.6	3.7	10.5	37.5	2.577	2.646	2.654	
FREY 55-22-017-QRY Created On: 01/10/23 Updated On:	Q	NW	SE	15	7N	3W	Grant	0-225-117-2023	0.4	5.1	4.0	11.0	38.6	2.544	2.631	3.430	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
* FROSTMAN 55-04-004-PIT Created On: 02/28/14 Updated On:	P		NW 26	47N	8W	Bayfield	0-225-87-2014		0.0	2.1	4.2	18.5	2.688	2.711	0.882		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
* FROSTMAN 55-04-004-PIT Created On: 01/07/19 Updated On:	P		NW 26	47N	8W	Bayfield	0-225-57-2019	2.3	0.0	2.6	8.8	20.9	2.684	2.715	1.154		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
GATES #238 55-17-011-QRY Created On: 01/08/15 Updated On:	Q	S	NW 17	28N	14W	Dunn	0-225-36-2015	0.7	0.0	4.5	7.3	32.3	2.629	2.688	2.238		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
GATES #238 55-17-011-QRY Created On: 07/17/15 Updated On:	Q	S	NW 17	28N	14W	Dunn	0-225-215-2015		0.0	1.9	7.5	31.3	2.608	2.669	2.323		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
GATES #238 55-17-011-QRY Created On: 04/21/17 Updated On:	Q	S	NW 17	28N	14W	Dunn	0-225-142-2017	1.3	0.0	2.0	7.7	31.1	2.610	2.672	2.371		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
GATES #238 55-17-011-QRY Created On: 08/09/19 Updated On:	Q	S	NW 17	28N	14W	Dunn	0-225-259-2019	2.9	0.0	5.3	11.3	39.7	2.558	2.641	3.218		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
GATES #238 55-17-011-QRY Created On: 04/05/22 Updated On:	Q	S	NW 17	28N	14W	Dunn	0-225-157-2022	6.5	1.8	10.6	11.6	43.4	2.537	2.614	3.053		
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Sp. Gravity		Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
GATEWAY 55-63-023-PIT Created On: 07/18/19 Updated On:	P	SE	NE	11	42N	10E	Vilas	0-225-236-2019	0.3	0.0	0.6	3.5	16.4	2.744	2.763	0.689		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
GATEWAY 55-63-023-PIT Created On: 01/02/24 Updated On:	P	SE	NE	11	42N	10E	Vilas	0-225-59-2024	0.7	0.0	0.5	3.9	18.0	2.727	2.749	0.824		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
GAY 55-10-007-PIT Created On: 04/23/15 Updated On:	P	SE	SE	5	28N	2W	Clark	0-225-136-2015		0.0	1.4	4.1	19.4	2.670	2.698	1.050		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
GAY 55-10-007-PIT Created On: 01/04/23 Updated On:	P	SE	SE	5	28N	2W	Clark	0-225-96-2023	4.3	0.0	6.2	5.1	22.3	2.597	2.645	1.837		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
GEIER ROAD 55-29-009-QRY Created On: 05/18/18 Updated On:	Q			27	14N	3E	Juneau	0-225-213-2018	0.6	0.0	4.4	12.3	45.7	2.608	2.672	2.457		
	Approved Use : HMA<MT, CONCRETE, OGBC, Base Aggregate																	
GEIER ROAD 55-29-009-QRY Created On: 01/05/21 Updated On:	Q			27	14N	3E	Juneau	0-225-64-2021	0.8	6.2	8.4	10.9	42.9	2.645	2.697	1.973		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
GEIER ROAD 55-29-009-QRY Created On: 01/02/24 Updated On:	Q			27	14N	3E	Juneau	0-225-116-2024	1.8	4.2	1.6	8.4	34.6	2.577	2.634	2.197		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
GENESEEE 55-67-007-PIT Created On: 01/05/16 Updated On:	P	NE	SE	29	6N	18E	Waukesha	0-225-21-2016	0.2	1.9	2.4	8.0	34.9	2.708	2.745	1.346		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
GENESEEE 55-67-007-PIT Created On: 01/05/21 Updated On:	P	NE	SE	29	6N	18E	Waukesha	0-225-95-2021	0.0	6.1	2.8	6.1	27.5	2.727	2.759	1.189		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
GENESEEE / HILLVIEW 55-67-005-PIT Created On: 01/08/15 Updated On:	P		SE	8	8N	19E	Waukesha	0-225-30-2015	0.5	4.6	3.9	5.9	28.1	2.686	2.725	1.439		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
GENESEEE / HILLVIEW 55-67-005-PIT Created On: 02/16/16 Updated On:	P		SE	8	8N	19E	Waukesha	0-225-90-2016		1.6	1.6	7.6	34.6	2.711	2.743	1.180		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
GENESEEE / HILLVIEW 55-67-005-PIT Created On: 01/05/21 Updated On:	P		SE	8	8N	19E	Waukesha	0-225-97-2021	0.4	6.1	3.8	7.4	31.0	2.578	2.643	2.498		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
GENESEEE/OTTAWA PIT 55-67-006-PIT Created On: 01/05/16 Updated On:	P		SW	1	6N	17E	Waukesha	0-225-19-2016	0.0	3.0	4.9	8.4	37.1	2.688	2.723	1.324		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
GENESEEE/OTTAWA PIT 55-67-006-PIT Created On: 01/05/21 Updated On:	P		SW	1	6N	17E	Waukesha	0-225-94-2021	0.0	5.2	6.8	5.5	26.7	2.677	2.716	1.452		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
GERKE 55-41-009-QRY Created On: 04/25/17 Updated On:	Q	NE	SE	36	17N	1W	Monroe	0-225-157-2017	0.2	0.0	11.8	13.1	48.9	2.523	2.606	3.298	
	Approved Use : HMA<E-3, CONCRETE, Base Aggregate																
GERKE 55-41-009-QRY Created On: 01/24/22 Updated On:	Q	NE	SE	36	17N	1W	Monroe	0-225-116-2022	0.0	0.0	4.8	12.8	45.8	2.541	2.619	3.035	
	Approved Use : HMA<MT, CONCRETE, OGBC, Base Aggregate																
GILLEN 55-55-006-QRY Created On: 06/26/14 Updated On:	Q	E	NW	10	30N	17W	St. Croix	0-225-205-2014		0.0	4.9	9.9	35.8	2.637	2.691	2.011	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
GILLEN 55-55-006-QRY Created On: 04/06/17 Updated On:	Q	E	NW	10	30N	17W	St. Croix	0-225-117-2017		0.0	1.1	10.9	39.7	2.605	2.666	2.322	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
GILLEN 55-55-006-QRY Created On: 01/08/20 Updated On:	Q	E	NW	10	30N	17W	St. Croix	0-225-54-2020	1.6	0.0	17.0	12.5	42.2	2.599	2.663	2.479	
	Approved Use : Base Aggregate																
GILLEN 55-55-006-QRY Created On: 01/03/23 Updated On:	Q	E	NW	10	30N	17W	St. Croix	0-225-54-2023	0.5	0.0	10.4	11.7	39.3	2.579	2.656	2.966	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
GILLES (DANE) 55-13-024-QRY Created On: 01/24/22 Updated On:	Q	NW	NW	4	9N	9E	Dane	0-225-117-2022	0.7	1.2	1.1	9.5	34.9	2.602	2.658	2.140	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
GILLES (DANE) 55-13-024-QRY Created On: 01/23/23 Updated On:	Q	NW	NW	4	9N	9E	Dane	0-225-131-2023	0.3	1.2	1.0	8.6	35.3	2.560	2.628	2.681	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
GILLES (DANE) 55-13-024-QRY Created On: 04/15/24 Updated On:	Q	NW	NW	4	9N	9E	Dane	0-225-225-2024	0.7	0.9	1.7	9.5	37.8	2.602	2.665	2.409	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
GLEN FLORA PETERSON 55-54-020-PIT Created On: 06/24/21 Updated On:	P		NE	30	35N	4W	Rusk	0-225-232-2021	1.3	0.0	1.2	4.7	20.5	2.751	2.777	0.939	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
* GLENMORE 55-05-013-QRY Created On: 01/05/15 Updated On:	Q		NE	6	22N	21E	Brown	0-225-5-2015	0.1	0.4	1.2	6.5	30.3	2.730	2.765	1.294	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
* GLENMORE 55-05-013-QRY Created On: 01/04/18 Updated On:	Q		NE	6	22N	21E	Brown	0-225-53-2018		1.1	1.8	6.4	30.0	2.725	2.755	1.090	
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																
* GLENMORE 55-05-013-QRY Created On: 01/04/21 Updated On:	Q		NE	6	22N	21E	Brown	0-225-6-2021	1.6	1.6	2.9	6.0	38.7	2.672	2.721	1.807	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
* GLENMORE 55-05-013-QRY Created On: 01/02/24 Updated On:	Q		NE	6	22N	21E	Brown	0-225-49-2024	20.7	16.5	6.0	13.7	43.6	2.513	2.597	3.370	
	Approved Use : OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
GO GREEN 55-68-019-QRY Created On: 09/02/15 Updated On:	Q		NW	13	21N	14E	Waupaca	0-225-236-2015		0.0	11.3	8.4	34.6	2.701	2.745	1.654		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
GO GREEN 55-68-019-QRY Created On: 02/15/18 Updated On:	Q		NW	13	21N	14E	Waupaca	0-225-101-2018		0.0	2.6	5.9	27.4	2.698	2.738	1.490		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
GO GREEN 55-68-019-QRY Created On: 02/28/23 Updated On:	Q		NW	13	21N	14E	Waupaca	0-225-159-2023	1.3	5.4	2.3	8.5	32.7	2.699	2.739	1.476		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
GOETZ 55-10-039-QRY Created On: 05/17/22 Updated On:	Q	NW	NE	26	24N	2W	Clark	0-225-200-2022	0.5	0.0	0.6	4.0	19.1	2.684	2.694	0.384		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
GOHR 55-42-011-QRY Created On: 05/30/17 Updated On:	Q	SW	NE	4	26N	19E	Oconto	0-225-196-2017		1.2	1.2	5.7	26.2	2.772	2.793	0.751		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
GOHR 55-42-011-QRY Created On: 01/02/20 Updated On:	Q	SW	NE	4	26N	19E	Oconto	0-225-3-2020	0.0	2.9	2.4	5.7	25.5	2.748	2.771	0.823		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
GOHR 55-42-011-QRY Created On: 01/12/23 Updated On:	Q	SW	NE	4	26N	19E	Oconto	0-225-121-2023	0.0	2.1	1.9	6.8	23.7	2.755	2.780	0.884		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
GOLD THORPE 55-25-032-QRY Created On: 06/13/19 Updated On:	Q	SE	SW	15	5N	3E	Iowa	0-225-214-2019	0.1	1.6	3.4	7.6	30.1	2.601	2.669	2.626		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
GOLD THORPE 55-25-032-QRY Created On: 01/10/22 Updated On:	Q	SE	SW	15	5N	3E	Iowa	0-225-100-2022	0.8	3.4	6.9	7.4	35.1	2.573	2.643	2.721		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
GOSBEE 55-60-009-PIT Created On: 06/26/17 Updated On:	P	SE	NE	28	32N	1E	Taylor	0-225-219-2017		0.0	0.6	4.2	19.4	2.697	2.733	1.354		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
GOSBEE 55-60-009-PIT Created On: 06/28/22 Updated On:	P	SE	NE	28	32N	1E	Taylor	0-225-242-2022	0.6	0.0	2.7	4.1	18.0	2.728	2.753	0.921		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
GRAHL-EMPIRE 55-20-014-PIT Created On: 05/12/16 Updated On:	P	S	SE	36	15N	18E	Fond Du Lac	0-225-173-2016	0.1	0.0	2.2	6.5	29.8	2.740	2.768	1.052		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
GRAHL-EMPIRE 55-20-014-PIT Created On: 04/13/21 Updated On:	P	S	SE	36	15N	18E	Fond Du Lac	0-225-178-2021	1.0	4.9	3.2	5.7	28.7	2.734	2.765	1.105		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
GREY CLOUD NELSON 27-00-010-PIT Created On: 04/07/16 Updated On:	P	S	NW	31	27N	21W	Lakeland	0-225-127-2016	0.1	1.9	3.9	4.2	24.0	2.674	2.712	1.422		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
GREY CLOUD NELSON 27-00-010-PIT Created On: 08/12/21 Updated On:	P	S	NW	31	27N	21W	Lakeland	0-225-262-2021	1.5	4.4	1.6	5.2	24.1	2.694	2.722	1.023	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
GRIMMS 55-36-015-QRY Created On: 01/04/16 Updated On:	Q	NE	SE	6	19N	22E	Manitowoc	0-225-6-2016		0.2	1.4	7.8	30.5	2.690	2.727	1.362	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
GRIMMS 55-36-015-QRY Created On: 05/09/19 Updated On:	Q	NE	SE	6	19N	22E	Manitowoc	0-225-182-2019	0.0	0.0	0.7	8.0	32.0	2.693	2.731	1.426	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
GRIMMS 55-36-015-QRY Created On: 01/04/22 Updated On:	Q	NE	SE	6	19N	22E	Manitowoc	0-225-33-2022	0.0	0.0	1.6	9.6	38.6	2.727	2.758	1.133	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
GRIMMS 55-36-015-QRY Created On: 01/02/24 Updated On:	Q	NE	SE	6	19N	22E	Manitowoc	0-225-102-2024	0.0	0.5	1.2	8.9	36.6	2.712	2.744	1.200	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
GRUNEWALD 55-58-009-QRY Created On: 05/10/18 Updated On:	Q			33	27N	17E	Shawano	0-225-206-2018	0.0	6.2	3.4	7.8	32.4	2.715	2.753	1.389	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
GRUNEWALD 55-58-009-QRY Created On: 04/30/21 Updated On:	Q			33	27N	17E	Shawano	0-225-198-2021	0.9	2.3	6.4	8.1	34.6	2.687	2.733	1.703	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Coarse Sp. Gravity		Coarse Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
GRUNEWALD 55-58-009-QRY Created On: 01/02/24 Updated On:	Q		33	27N	17E	Shawano		0-225-68-2024	0.0	3.9	3.7	8.2	35.1	2.676	2.719	1.606	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
GUDGEON 55-62-012-QRY Created On: 01/06/14 Updated On:	Q	NW	NE	27	13N	4E	Vernon		0-225-12-2014		10.0	2.8	13.6	33.1	2.577	2.635	2.231
	Approved Use : CONCRETE, OGBC, Base Aggregate																
GUDGEON 55-62-012-QRY Created On: 01/09/20 Updated On:	Q	NW	NE	27	13N	4E	Vernon		0-225-84-2020	0.0	1.9	3.3	10.5	41.7	2.589	2.655	2.518
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
GUDGEON 55-62-012-QRY Created On: 01/10/23 Updated On:	Q	NW	NE	27	13N	4E	Vernon		0-225-107-2023	0.5	3.6	3.0	11.2	40.6	2.580	2.653	2.842
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
GUEBIG 55-20-015-PIT Created On: 01/21/16 Updated On:	P	NW	SE	9	16N	19E	Fond Du Lac		0-225-66-2016	0.0	3.3	4.7	7.4	31.7	2.739	2.774	1.295
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
GUEBIG 55-20-015-PIT Created On: 01/05/21 Updated On:	P	NW	SE	9	16N	19E	Fond Du Lac		0-225-102-2021	0.0	3.6	1.1	7.5	31.4	2.738	2.771	1.206
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
GUEBIG NORTH 55-20-059-PIT Created On: 10/21/21 Updated On:	P	NW	NE	9	16N	19E	Fond Du Lac		0-225-270-2021	0.3	0.0	4.6	7.5	32.3	2.761	2.789	1.047
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
GULICH 55-09-079-PIT Created On: 01/30/20 Updated On:	P	NW	SE	10	32N	6W	Chippewa	0-225-101-2020	1.2	0.0	2.4	3.5	17.9	2.675	2.710	1.315	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
H&H 55-37-096-QRY Created On: 01/19/23 Updated On:	Q	NW	SW	5	28N	6E	Marathon	0-225-124-2023	0.2	2.6	1.0	4.7	19.0	2.627	2.670	1.619	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
HAAS 0-M PIT 55-54-032-PIT Created On: 07/27/23 Updated On:	P	NW	SE	19	33N	9W	Rusk	0-225-240-2023	1.9	0.0	1.0	5.1	22.5	2.685	2.712	1.002	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
HAAS 124 55-09-025-PIT Created On: 01/17/14 Updated On:	P	SE	SE	6	30N	8W	Chippewa	0-225-55-2014		0.0	3.0	3.9	17.8	2.712	2.745	1.208	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
HAAS 124 55-09-025-PIT Created On: 06/06/19 Updated On:	P	SE	SE	6	30N	8W	Chippewa	0-225-207-2019	7.8	0.0	3.5	5.3	21.6	2.659	2.687	1.060	
	Approved Use : HMA<MT, HMA>=MT, Base Aggregate																
HAAS 124 55-09-025-PIT Created On: 06/04/20 Updated On:	P	SE	SE	6	30N	8W	Chippewa	0-225-186-2020	1.1	0.0	0.9	3.7	19.7	2.712	2.745	1.204	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
HAAS EMSTROM PIT 55-60-035-PIT Created On: 07/27/23 Updated On:	P	NE	NW	3	31N	2W	Taylor	0-225-243-2023	1.8	0.0	1.5	4.5	21.2	2.742	2.762	0.718	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
HAAS LEHMAN PIT 55-54-033-PIT Created On: 07/27/23 Updated On:	P	SE	NE	3	33N	7W	Rusk	0-225-244-2023	0.5	0.0	0.5	3.7	18.1	2.688	2.715	1.000		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
HAAS RW PIT 55-50-029-PIT Created On: 07/27/23 Updated On:	P	NE	SW	36	35N	1E	Price	0-225-242-2023	1.1	0.0	0.7	4.0	18.8	2.717	2.737	0.754		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
HAAS SPORTS PIT 55-09-081-PIT Created On: 07/27/23 Updated On:	P	NE	NW	25	31N	7W	Chippewa	0-225-241-2023	2.0	0.0	1.0	4.4	20.1	2.723	2.748	0.897		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
HACKL 55-25-010-QRY Created On: 05/23/14 Updated On:	Q	SW	SW	21	8N	1E	Iowa	0-225-172-2014	1.1	2.0	1.9	8.9	35.1	2.603	2.662	2.248		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
HACKL 55-25-010-QRY Created On: 01/05/17 Updated On:	Q	SW	SW	21	8N	1E	Iowa	0-225-24-2017	6.9	4.5	4.6	8.9	34.3	2.645	2.696	1.917		
	Approved Use : HMA<E-3, HMA>=E-3, Base Aggregate																	
HACKL 55-25-010-QRY Created On: 01/04/19 Updated On:	Q	SW	SW	21	8N	1E	Iowa	0-225-23-2019	0.9	7.7	2.9	8.3	32.4	2.662	2.707	1.711		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
HACKL 55-25-010-QRY Created On: 01/04/22 Updated On:	Q	SW	SW	21	8N	1E	Iowa	0-225-49-2022	0.2	6.2	0.4	10.3	34.8	2.648	2.698	1.890		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Sp. Gravity		Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
HAEF 55-61-007-PIT Created On: 03/28/17 Updated On:	P	SW	NE	19	18N	8W	Trempealeau	0-225-90-2017		0.0	0.3	4.3	19.1	2.630	2.664	1.291		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
HAEF 55-61-007-PIT Created On: 01/04/22 Updated On:	P	SW	NE	19	18N	8W	Trempealeau	0-225-50-2022	0.0	0.3	0.5	3.2	14.5	2.635	2.674	1.478		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
HAFELDER 55-17-013-QRY Created On: 06/08/15 Updated On:	Q	NE	NE	23	28N	14W	Dunn	0-225-189-2015		0.0	4.4	7.5	39.1	2.571	2.641	2.714		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
HAFELDER 55-17-013-QRY Created On: 01/03/18 Updated On:	Q	NE	NE	23	28N	14W	Dunn	0-225-32-2018	2.0	0.0	6.3	10.5	36.9	2.531	2.616	3.356		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
HAFELDER 55-17-013-QRY Created On: 01/05/21 Updated On:	Q	NE	NE	23	28N	14W	Dunn	0-225-75-2021	1.4	0.0	0.8	9.7	35.3	2.559	2.641	3.186		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
HAFELDER 55-17-013-QRY Created On: 01/02/24 Updated On:	Q	NE	NE	23	28N	14W	Dunn	0-225-75-2024	1.7	6.7	6.7	12.2	43.3	2.548	2.629	3.169		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
* HAGGERTY 55-12-010-QRY Created On: 07/17/15 Updated On:	Q	SW	SW	10	9N	3W	Crawford	0-225-212-2015		2.6	3.4	8.2	33.6	2.625	2.678	2.011		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
* HAGGERTY 55-12-010-QRY Created On: 07/09/20 Updated On:	Q	SW	SW	10	9N	3W	Crawford	0-225-210-2020	0.9	1.5	3.6	9.1	32.3	2.629	2.684	2.072	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
HAHN 55-11-014-QRY Created On: 06/17/14 Updated On:	Q	NW	SE	11	12N	11E	Columbia	0-225-197-2014		6.7	7.2	13.0	38.8	2.527	2.611	3.317	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
HAHN 55-11-014-QRY Created On: 01/05/17 Updated On:	Q	NW	SE	11	12N	11E	Columbia	0-225-48-2017	0.9	2.6	1.6	13.7	38.3	2.548	2.625	3.010	
	Approved Use : CONCRETE, OGBC, Base Aggregate																
HAHN 55-11-014-QRY Created On: 01/08/20 Updated On:	Q	NW	SE	11	12N	11E	Columbia	0-225-69-2020	0.7	4.8	8.0	10.0	41.1	2.549	2.625	2.962	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
HAHN 55-11-014-QRY Created On: 01/04/23 Updated On:	Q	NW	SE	11	12N	11E	Columbia	0-225-94-2023	0.9	4.9	5.5	11.3	43.4	2.531	2.614	3.289	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
HALQUIST NORTH LAKE 55-67-032-PIT Created On: 06/27/18 Updated On:	P		SE	9	8N	18E	Waukesha	0-225-239-2018	1.1	0.8	1.0	5.6	27.3	2.721	2.749	1.042	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
HALQUIST NORTH LAKE 55-67-032-PIT Created On: 03/21/23 Updated On:	P		SE	9	8N	18E	Waukesha	0-225-171-2023	0.6	17.3	0.0	5.3	25.1	2.720	2.744	0.900	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
HAMPTON 55-22-021-QRY Created On: 04/07/16 Updated On:	Q		21	4N	5W	Grant	0-225-136-2016	1.2	8.5	6.9	9.4	36.5	2.576	2.646	2.698		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
HAMPTON 55-22-021-QRY Created On: 04/19/19 Updated On:	Q		21	4N	5W	Grant	0-225-156-2019	1.5	7.6	5.4	10.0	38.0	2.594	2.656	2.424		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
HAMPTON 55-22-021-QRY Created On: 01/04/22 Updated On:	Q		21	4N	5W	Grant	0-225-46-2022	0.9	14.6	1.1	10.6	36.4	2.569	2.638	2.693		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
HARRY'S 55-63-006-PIT Created On: 05/08/15 Updated On:	P	SE	SE	14	40N	6E	Vilas	0-225-153-2015		0.0	0.5	4.4	20.0	2.692	2.717	0.937	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
HARRY'S 55-63-006-PIT Created On: 01/08/20 Updated On:	P	SE	SE	14	40N	6E	Vilas	0-225-72-2020	0.8	0.0	0.9	3.4	16.6	2.702	2.728	0.958	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
* HARTMAN SPRING LAKE 55-45-004-PIT Created On: 06/12/14 Updated On:	P	SE	NE	3	12N	21E	Ozaukee	0-225-193-2014	0.5	0.0	2.6	8.8	42.1	2.713	2.739	0.943	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
* HARTMAN SPRING LAKE 55-45-004-PIT Created On: 04/26/19 Updated On:	P	SE	NE	3	12N	21E	Ozaukee	0-225-171-2019	0.4	1.5	0.6	8.4	35.2	2.717	2.746	1.084	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
HARTMANN QUARRY 55-11-041-QRY Created On: 01/02/24 Updated On:	Q	NE	NE	36	10N	7E	Columbia	0-225-43-2024	1.6	2.9	9.7	9.0	34.8	2.566	2.633	2.631	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
* HARTNETT 55-22-022-QRY Created On: 08/16/16 Updated On:	Q	NW	SW	27	4N	2W	Grant	0-225-244-2016	4.9	9.5	12.7	9.2	38.0	2.577	2.645	2.658	
	Approved Use : Base Aggregate																
* HARTNETT 55-22-022-QRY Created On: 04/19/19 Updated On:	Q	NW	SW	27	4N	2W	Grant	0-225-155-2019	3.1	14.9	12.9	11.3	42.3	2.589	2.663	2.849	
	Approved Use : Base Aggregate																
HARVEST HAVEN / O'BRIAN 55-13-030-QRY Created On: 01/07/15 Updated On:	Q		SE	7	6N	9E	Dane	0-225-8-2015		21.1	10.1	6.0	28.1	2.614	2.680	2.509	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
HARVEST HAVEN / O'BRIAN 55-13-030-QRY Created On: 06/03/15 Updated On:	Q		SE	7	6N	9E	Dane	0-225-181-2015		16.0	7.4	6.4	30.3	2.608	2.683	2.892	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
HARVEST HAVEN / O'BRIAN 55-13-030-QRY Created On: 09/15/16 Updated On:	Q		SE	7	6N	9E	Dane	0-225-256-2016	0.5	15.9	9.8	7.2	32.5	2.596	2.666	2.711	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
HARVEST HAVEN / O'BRIAN 55-13-030-QRY Created On: 01/02/18 Updated On:	Q		SE	7	6N	9E	Dane	0-225-1-2018	0.8	8.7	13.9	6.1	30.7	2.597	2.665	2.601	
	Approved Use : Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
HARVEST HAVEN / O'BRIAN 55-13-030-QRY Created On: 03/18/21 Updated On:	Q		SE	7	6N	9E	Dane	0-225-154-2021	0.4	4.0	7.1	8.1	34.2	2.597	2.657	2.288	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
HARVEST HAVEN / O'BRIAN 55-13-030-QRY Created On: 01/04/24 Updated On:	Q		SE	7	6N	9E	Dane	0-225-146-2024	0.7	7.4	6.2	9.8	40.1	2.580	2.649	2.667	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
* HASKE 55-71-017-QRY Created On: 01/07/15 Updated On:	Q	SW	SE	24	24N	2E	Wood	0-225-17-2015		0.0	0.5	5.0	20.6	2.619	2.629	0.374	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
* HASKE 55-71-017-QRY Created On: 01/02/18 Updated On:	Q	SW	SE	24	24N	2E	Wood	0-225-2-2018		0.0	0.3	3.6	17.7	2.620	2.628	0.308	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
* HASKE 55-71-017-QRY Created On: 01/04/21 Updated On:	Q	SW	SE	24	24N	2E	Wood	0-225-18-2021	0.0	0.1	0.1	5.2	22.0	2.622	2.633	0.416	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
HAUSZ BROS. 55-28-021-QRY Created On: 04/05/22 Updated On:	Q	S	SW	11	5N	14E	Jefferson	0-225-154-2022	1.0	7.1	16.6	17.7	43.4	2.523	2.614	3.645	
	Approved Use : Base Aggregate																
* HAVERLAND 55-22-023-QRY Created On: 04/24/14 Updated On:	Q		NE	NW	26	2N	2W	Grant	0-225-146-2014	0.3	8.8	10.8	11.4	39.1	2.576	2.654	3.001
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
* HAVERLAND 55-22-023-QRY Created On: 04/06/17 Updated On:	Q	NE	NW	26	2N	2W	Grant	0-225-106-2017	1.0	2.4	2.5	12.7	39.1	2.528	2.616	3.516		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
* HAVERLAND 55-22-023-QRY Created On: 03/23/18 Updated On:	Q	NE	NW	26	2N	2W	Grant	0-225-137-2018	1.0	2.9	2.5	13.4	41.0	2.552	2.627	2.962		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
* HAVERLAND 55-22-023-QRY Created On: 03/17/21 Updated On:	Q	NE	NW	26	2N	2W	Grant	0-225-150-2021	0.1	3.9	4.1	18.0	49.1	2.507	2.598	3.604		
	Approved Use : Base Aggregate																	
HAWKINS 286 55-54-008-PIT Created On: 01/05/16 Updated On:	P	S	NW	15	35N	3W	Rusk	0-225-24-2016		0.0	1.4	4.3	19.4	2.731	2.751	0.758		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
HAWKINS 286 55-54-008-PIT Created On: 10/12/21 Updated On:	P	S	NW	15	35N	3W	Rusk	0-225-268-2021	0.4	1.2	1.5	3.5	17.4	2.755	2.770	0.579		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
HAWKINS 286 55-54-008-PIT Created On: 01/10/23 Updated On:	P	S	NW	15	35N	3W	Rusk	0-225-115-2023	0.5	0.0	1.3	3.9	20.0	2.718	2.741	0.826		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
HAWKINSON 55-13-123-PIT Created On: 01/09/20 Updated On:	P	SE	SE	34	6N	10E	Dane	0-225-90-2020	3.9	0.0	4.1	5.7	31.2	2.634	2.687	1.999		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
HAY CREEK (PRICE) 55-50-008-PIT Created On: 07/17/14 Updated On:	P	SE	4	35N	1E	Price	0-225-224-2014		0.0	1.9	4.9	19.9	2.674	2.706	1.183			
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
HAY CREEK (PRICE) 55-50-008-PIT Created On: 04/23/20 Updated On:	P	SE	4	35N	1E	Price	0-225-156-2020	1.1	0.0	3.9	4.8	20.3	2.707	2.740	1.226			
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
HAYTON 55-08-006-QRY Created On: 06/21/16 Updated On:	Q	SW	28	18N	20E	Calumet	0-225-206-2016		0.0	1.7	9.5	39.8	2.727	2.757	1.092			
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
HAYTON 55-08-006-QRY Created On: 01/08/19 Updated On:	Q	SW	28	18N	20E	Calumet	0-225-72-2019		0.7	0.8	7.8	33.5	2.764	2.787	0.817			
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
HAYTON 55-08-006-QRY Created On: 01/04/22 Updated On:	Q	SW	28	18N	20E	Calumet	0-225-29-2022	0.0	0.0	0.5	8.7	36.7	2.758	2.783	0.903			
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
HAYTON 55-08-006-QRY Created On: 01/29/24 Updated On:	Q	SW	28	18N	20E	Calumet	0-225-165-2024	0.0	0.6	1.3	8.7	36.9	2.772	2.792	0.713			
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
* HAYWARD SAND AND GRAVEL 55-57-016-PIT Created On: 03/05/19 Updated On:	P	E	SE	10	41N	9W	Sawyer	0-225-109-2019	2.7	0.0	6.0	4.6	18.8	2.780	2.813	1.178		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Coarse Sp. Gravity		Coarse Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
HAZELHURST 55-43-005-PIT Created On: 06/01/18 Updated On:	P	NE	SE	15	37N	6E	Oneida	0-225-218-2018	0.0	0.5	4.3	20.6	2.689	2.713	0.896			
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																	
HAZELHURST 55-43-005-PIT Created On: 01/03/23 Updated On:	P	NE	SE	15	37N	6E	Oneida	0-225-17-2023	0.0	0.3	3.1	16.4	2.713	2.734	0.773			
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																	
HEATH 55-54-009-PIT Created On: 04/11/18 Updated On:	P	NW	NW	30	35N	4W	Rusk	0-225-163-2018	0.5	0.0	2.4	3.8	17.9	2.760	2.785	0.898		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
HEATH 55-54-009-PIT Created On: 01/10/23 Updated On:	P	NW	NW	30	35N	4W	Rusk	0-225-113-2023	0.7	0.0	1.6	3.5	17.4	2.763	2.782	0.705		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
HELLICKSON 55-13-031-PIT Created On: 04/12/17 Updated On:	P	SE	NW	34	7N	11E	Dane	0-225-123-2017	2.7	0.0	3.9	7.1	31.6	2.635	2.687	1.966		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
HELLICKSON 55-13-031-PIT Created On: 04/18/22 Updated On:	P	SE	NW	34	7N	11E	Dane	0-225-175-2022	3.4	4.5	6.2	7.0	31.4	2.642	2.692	1.910		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
* HENSEN 55-13-032-QRY Created On: 08/22/19 Updated On:	Q	NE	SW	16	8N	12E	Dane	0-225-266-2019	5.6	8.4	8.1	12.0	40.6	2.521	2.608	3.465		
	Approved Use : HMA<MT, HMA>=MT, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
HERMAN 55-14-011-QRY Created On: 04/24/14 Updated On:	Q	SW	NW	6	11N	17E	Dodge	0-225-149-2014	0.5	1.1	3.2	5.7	26.2	2.771	2.787	0.588		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
HERMAN 55-14-011-QRY Created On: 04/06/17 Updated On:	Q	SW	NW	6	11N	17E	Dodge	0-225-105-2017		1.1	1.3	6.9	29.6	2.733	2.764	1.114		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
HERMAN 55-14-011-QRY Created On: 06/04/20 Updated On:	Q	SW	NW	6	11N	17E	Dodge	0-225-187-2020		4.5	0.1	5.0	26.7	2.773	2.789	0.577		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
HERMAN 55-14-011-QRY Created On: 02/27/23 Updated On:	Q	SW	NW	6	11N	17E	Dodge	0-225-147-2023	0.4	6.2	3.1	10.4	33.0	2.734	2.764	1.085		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
HESS 55-34-014-PIT Created On: 01/08/16 Updated On:	P	SW	SW	2	30N	11E	Langlade	0-225-45-2016		0.0	1.8	5.8	27.2	2.677	2.695	0.664		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
HESS 55-34-014-PIT Created On: 01/04/21 Updated On:	P	SW	SW	2	30N	11E	Langlade	0-225-15-2021	0.0	0.6	0.8	5.6	25.3	2.680	2.711	1.180		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
HEYN 55-69-006-PIT Created On: 04/13/17 Updated On:	P	W	NE	22	19N	8E	Waushara	0-225-131-2017		0.0	2.8	6.7	25.8	2.737	2.775	1.388		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
HEYN 55-69-006-PIT Created On: 04/30/21 Updated On:	P	W	NE	22	19N	8E	Waushara	0-225-191-2021	3.3	2.5	4.9	7.6	31.0	2.705	2.741	1.330	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
* HIGH POINT 55-43-010-PIT Created On: 04/18/19 Updated On:	P	SW	NW	36	39N	7E	Oneida	0-225-139-2019	0.3	0.0	0.1	5.5	26.2	2.655	2.673	0.680	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
HIGH ROAD QUARRY 55-15-015-QRY Created On: 01/03/23 Updated On:	Q		NW	4	26N	24E	Door	0-225-42-2023	0.0	2.3	5.4	6.7	29.6	2.705	2.747	1.553	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
HIGHBRIDGE 55-02-005-QRY Created On: 01/04/23 Updated On:	Q	S	SW	16	45N	3W	Ashland	0-225-91-2023	0.1	0.4	0.3	4.5	21.9	2.588	2.612	0.926	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
* HIGHBRIDGE NORTH 55-02-005-QRY Created On: 02/28/14 Updated On:	Q	S	SW	16	45N	3W	Ashland	0-225-90-2014		0.0	3.1	5.6	24.0	2.604	2.624	0.774	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
* HIGHBRIDGE NORTH 55-02-005-QRY Created On: 05/19/17 Updated On:	Q	S	SW	16	45N	3W	Ashland	0-225-192-2017		0.0	0.7	4.5	21.0	2.615	2.633	0.685	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
* HIGHBRIDGE NORTH 55-02-005-QRY Created On: 01/06/20 Updated On:	Q	S	SW	16	45N	3W	Ashland	0-225-33-2020	0.1	0.0	1.2	5.2	24.3	2.623	2.637	0.549	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Coarse Sp. Gravity		Coarse Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
HILGER 55-09-031-PIT Created On: 02/03/14 Updated On:	P		8	30N	8W	Chippewa	0-225-70-2014		0.0	2.2	4.2	19.7	2.724	2.754	1.100			
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
HILGER 55-09-031-PIT Created On: 01/08/19 Updated On:	P		8	30N	8W	Chippewa	0-225-75-2019	0.9	0.0	1.5	3.6	17.4	2.702	2.733	1.123			
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
HILGER 55-09-031-PIT Created On: 01/02/24 Updated On:	P		8	30N	8W	Chippewa	0-225-84-2024	0.7	0.0	1.6	3.5	17.7	2.708	2.736	1.029			
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
HILLPOINT 55-56-010-QRY Created On: 05/14/15 Updated On:	Q	SW	22	11N	3E	Sauk	0-225-175-2015	0.3	1.2	2.5	10.5	41.7	2.629	2.682	2.011			
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
HILLPOINT 55-56-010-QRY Created On: 04/10/18 Updated On:	Q	SW	22	11N	3E	Sauk	0-225-158-2018	0.3	0.0	7.6	12.1	44.8	2.609	2.670	2.362			
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
HILLPOINT 55-56-010-QRY Created On: 01/29/24 Updated On:	Q	SW	22	11N	3E	Sauk	0-225-152-2024	0.9	7.9	10.9	13.2	45.9	2.575	2.644	2.665			
	Approved Use : HMA<MT, CONCRETE, OGBC, Base Aggregate																	
HILLSIDE 55-51-010-PIT Created On: 04/02/14 Updated On:	P	SE	7	2N	19E	Racine	0-225-108-2014	0.5	0.0	1.0	5.1	24.4	2.696	2.729	1.239			
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
HILLSIDE 55-51-010-PIT Created On: 02/20/19 Updated On:	P		SE	7	2N	19E	Racine	0-225-107-2019	0.7	7.1	1.8	5.4	26.0	2.663	2.712	1.877	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
HILLSIDE 55-51-010-PIT Created On: 02/28/24 Updated On:	P		SE	7	2N	19E	Racine	0-225-188-2024	2.0	11.7	7.6	5.6	25.7	2.670	2.712	1.603	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
HOBART QUARRY 55-05-008-QRY Created On: 04/01/16 Updated On:	Q	NE	NE	27	23N	19E	Brown	0-225-119-2016	0.5	5.0	11.3	6.1	26.0	2.739	2.772	1.181	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
HOBART QUARRY 55-05-008-QRY Created On: 04/13/17 Updated On:	Q	NE	NE	27	23N	19E	Brown	0-225-129-2017		7.9	11.1	5.6	24.0	2.759	2.790	1.100	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
HOBART QUARRY 55-05-008-QRY Created On: 03/18/20 Updated On:	Q	NE	NE	27	23N	19E	Brown	0-225-130-2020		20.2	15.7	9.6	27.0	2.733	2.767	1.247	
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																
HOBART QUARRY 55-05-008-QRY Created On: 06/09/20 Updated On:	Q	NE	NE	27	23N	19E	Brown	0-225-190-2020		11.0	4.2	5.4	24.5	2.750	2.779	1.040	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
HOBART QUARRY 55-05-008-QRY Created On: 03/10/21 Updated On:	Q	NE	NE	27	23N	19E	Brown	0-225-134-2021	0.0	1.1	1.0	4.9	22.5	2.791	2.805	0.492	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
HOBART QUARRY 55-05-008-QRY Created On: 01/04/22 Updated On:	Q	NE	NE	27	23N	19E	Brown	0-225-69-2022	0.0	29.3	16.4	5.9	26.6	2.732	2.766	1.248	
HOBART QUARRY 55-05-008-QRY Created On: 02/17/22 Updated On:	Q	NE	NE	27	23N	19E	Brown	0-225-128-2022	0.1	2.1	5.3	4.7	22.5	2.770	2.792	0.811	
HOBART QUARRY 55-05-008-QRY Created On: 03/21/23 Updated On:	Q	NE	NE	27	23N	19E	Brown	0-225-173-2023	0.0	1.1	0.4	5.3	22.7	2.769	2.789	0.707	
HOBART QUARRY 55-05-008-QRY Created On: 01/02/24 Updated On:	Q	NE	NE	27	23N	19E	Brown	0-225-14-2024	0.0	2.7	0.4	6.2	27.0	2.765	2.788	0.836	
HODGE PIT 55-42-046-PIT Created On: 01/02/24 Updated On:	P	SE	SE	8	29N	20E	Oconto	0-225-96-2024	0.1	0.0	4.0	5.8	27.9	2.709	2.741	1.198	
* HOHFELD 55-62-015-QRY Created On: 02/03/20 Updated On:	Q	NE	NE	8	14N	6W	Vernon	0-225-109-2020	2.7	0.0	8.2	12.8	46.2	2.550	2.627	3.035	
HOLCIM-COLGATE 55-67-021-PIT Created On: 01/08/15 Updated On:	P	S	NW	3	8N	19E	Waukesha	0-225-35-2015	0.9	2.5	2.4	4.5	23.9	2.736	2.759	0.827	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
HOLCIM-COLGATE 55-67-021-PIT Created On: 03/16/18 Updated On:	P	S	NW	3	8N	19E	Waukesha	0-225-129-2018		3.7	3.6	5.6	25.7	2.742	2.765	0.840		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
HOLCIM-COLGATE 55-67-021-PIT Created On: 01/03/23 Updated On:	P	S	NW	3	8N	19E	Waukesha	0-225-26-2023	0.0	5.6	1.0	6.0	27.6	2.691	2.728	1.408		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
HOLCIM-DYER LAKE 55-30-004-PIT Created On: 05/11/18 Updated On:	P		W	29	2N	19E	Kenosha	0-225-209-2018	2.4	10.7	6.7	5.2	25.1	2.673	2.713	1.500		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
HOLCIM-DYER LAKE 55-30-004-PIT Created On: 01/03/23 Updated On:	P		W	29	2N	19E	Kenosha	0-225-31-2023	0.0	12.3	1.3	6.6	28.2	2.628	2.683	2.079		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
HOLCIM-MCHENRY 17-00-011-PIT Created On: 04/24/23 Updated On:	P	NE	NE	29	45N	8E	Mchenry	0-225-205-2023	0.5	7.9	5.2	4.6	24.9	2.631	2.678	1.807		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
HOLDER PIT 55-11-017-PIT Created On: 01/03/17 Updated On:	P	NW	SE	30	12N	11E	Columbia	0-225-7-2017	6.6	0.0	7.8	11.5	37.8	2.625	2.680	2.079		
	Approved Use : HMA<E-3, HMA>=E-3, OGBC, Base Aggregate																	
HOLDER PIT 55-11-017-PIT Created On: 01/04/22 Updated On:	P	NW	SE	30	12N	11E	Columbia	0-225-5-2022	6.6	0.0	9.7	11.0	37.6	2.638	2.687	1.882		
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
* HOLLAND 55-05-028-PIT Created On: 08/20/19 Updated On:	P	SW	33	21N	20E	Brown		0-225-264-2019	0.0	11.4	4.0	6.0	27.5	2.724	2.763	1.431		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
HOLLATZ 55-20-017-PIT Created On: 01/12/16 Updated On:	P	NE	NW	17	16N	14E	Fond Du Lac	0-225-51-2016		0.0	1.4	5.0	24.2	2.729	2.760	1.132		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
HOLLATZ 55-20-017-PIT Created On: 01/04/21 Updated On:	P	NE	NW	17	16N	14E	Fond Du Lac	0-225-45-2021	0.0	3.7	2.4	4.7	23.3	2.718	2.754	1.341		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
HOLST 55-47-010-PIT Created On: 01/03/18 Updated On:	P		W	33	25N	18W	Pierce	0-225-40-2018	1.5	0.0	1.9	5.5	24.5	2.660	2.699	1.455		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
HOLST 55-47-010-PIT Created On: 08/22/23 Updated On:	P		W	33	25N	18W	Pierce	0-225-247-2023	1.5	0.0	0.6	6.2	25.1	2.645	2.675	1.167		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
HOLTAN 55-63-007-PIT Created On: 06/13/19 Updated On:	P	NW	NW	33	43N	8E	Vilas	0-225-220-2019	0.3	0.0	1.8	3.9	19.2	2.742	2.767	0.888		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
HOLTAN 55-63-007-PIT Created On: 01/03/23 Updated On:	P	NW	NW	33	43N	8E	Vilas	0-225-27-2023	1.5	0.0	1.0	4.6	20.4	2.720	2.756	1.307		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
HOME RUN 55-16-008-QRY Created On: 05/19/17 Updated On:	Q	NE	SE	21	48N	10W	Douglas	0-225-193-2017		18.3	7.3	4.0	32.4	2.753	2.789	1.311		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
HOME RUN 55-16-008-QRY Created On: 04/16/20 Updated On:	Q	NE	SE	21	48N	10W	Douglas	0-225-153-2020		0.0	2.4	2.5	10.8	2.852	2.886	1.191		
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																	
HOME RUN 55-16-008-QRY Created On: 01/04/23 Updated On:	Q	NE	SE	21	48N	10W	Douglas	0-225-88-2023	0.0	0.0	2.1	2.7	13.4	2.837	2.869	1.105		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
HOUSEHOLDER 55-52-014-QRY Created On: 01/07/14 Updated On:	Q	NW	SE	15	10N	1E	Richland	0-225-37-2014		0.0	8.6	12.7	41.0	2.556	2.624	2.657		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
HOUSEHOLDER 55-52-014-QRY Created On: 05/09/17 Updated On:	Q	NW	SE	15	10N	1E	Richland	0-225-178-2017		0.0	7.0	9.9	37.3	2.569	2.649	3.125		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
HOUSEHOLDER 55-52-014-QRY Created On: 03/12/20 Updated On:	Q	NW	SE	15	10N	1E	Richland	0-225-128-2020	1.9	0.0	2.8	10.6	36.4	2.517	2.600	3.306		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
HOUSEHOLDER 55-52-014-QRY Created On: 01/03/23 Updated On:	Q	NW	SE	15	10N	1E	Richland	0-225-21-2023	0.3	8.4	0.7	9.4	36.8	2.596	2.660	2.456		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
* HUBER 55-06-011-QRY Created On: 05/09/16 Updated On:	Q	SE	SE	4	22N	12W	Buffalo	0-225-165-2016		0.0	11.6	13.0	41.2	2.562	2.635	2.833		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
* HUBER 55-06-011-QRY Created On: 08/25/17 Updated On:	Q	SE	SE	4	22N	12W	Buffalo	0-225-263-2017		0.0	3.7	11.2	41.8	2.561	2.640	3.067		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
* HUBER 55-06-011-QRY Created On: 01/06/20 Updated On:	Q	SE	SE	4	22N	12W	Buffalo	0-225-26-2020	0.5	0.0	6.6	11.2	42.0	2.567	2.641	2.888		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
HUGHES 55-17-015-QRY Created On: 02/05/14 Updated On:	Q		SW	15	28N	14W	Dunn	0-225-78-2014		0.0	3.0	9.3	34.6	2.582	2.655	2.826		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
HUGHES 55-17-015-QRY Created On: 01/05/17 Updated On:	Q		SW	15	28N	14W	Dunn	0-225-47-2017		0.0	5.4	9.0	35.8	2.594	2.661	2.585		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
HUGHES 55-17-015-QRY Created On: 08/15/19 Updated On:	Q		SW	15	28N	14W	Dunn	0-225-261-2019	0.9	0.0	5.5	7.9	33.5	2.601	2.668	2.584		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
HUGHES 55-17-015-QRY Created On: 04/05/22 Updated On:	Q		SW	15	28N	14W	Dunn	0-225-161-2022	2.3	1.4	5.0	11.4	41.0	2.586	2.650	2.464		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
HUNZICKER 55-10-010-QRY Created On: 07/19/21 Updated On:	Q	SE	NE	16	26N	2W	Clark	0-225-245-2021	0.0	0.0	1.1	7.2	31.3	2.597	2.617	0.772		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
HUNZICKER 55-10-010-QRY Created On: 01/29/24 Updated On:	Q	SE	NE	16	26N	2W	Clark	0-225-162-2024	0.0	1.8	1.2	5.4	25.6	2.594	2.614	0.800		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
HURD PIT 55-53-017-PIT Created On: 03/30/15 Updated On:	P	NW	SW	15	4N	12E	Rock	0-225-108-2015	4.2	0.0	2.2	5.7	27.5	2.645	2.691	1.736		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
HURD PIT 55-53-017-PIT Created On: 04/20/23 Updated On:	P	NW	SW	15	4N	12E	Rock	0-225-202-2023	4.9	8.0	2.3	5.9	27.1	2.673	2.721	1.814		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
* HURD QUARRY 55-53-044-QRY Created On: 07/02/19 Updated On:	Q	NW	SW	15	4N	12E	Rock	0-225-233-2019		5.1	9.9	7.3	35.1	2.630	2.691	2.326		
	Approved Use : HMA<MT, HMA>=MT, Base Aggregate																	
* HURD QUARRY 55-53-044-QRY Created On: 01/05/21 Updated On:	Q	NW	SW	15	4N	12E	Rock	0-225-78-2021		9.1	6.0	4.8	30.0	2.659	2.712	1.997		
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																	
HUSTISFORD 55-14-012-QRY Created On: 01/21/16 Updated On:	Q	SE	SW	33	10N	16E	Dodge	0-225-69-2016		4.4	5.3	5.1	24.4	2.669	2.718	1.859		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
HUSTISFORD 55-14-012-QRY Created On: 02/05/19 Updated On:	Q	SE	SW	33	10N	16E	Dodge	0-225-97-2019		3.7	1.2	5.5	25.9	2.697	2.737	1.487		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
HUSTISFORD 55-14-012-QRY Created On: 01/04/22 Updated On:	Q	SE	SW	33	10N	16E	Dodge	0-225-87-2022	0.0	3.5	1.2	5.5	28.1	2.680	2.723	1.620		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
* HWY 154 QUARRY 55-56-034-QRY Created On: 05/04/21 Updated On:	Q	SW	SW	30	11N	3E	Sauk	0-225-200-2021	3.1	9.8	4.1	11.7	41.4	2.606	2.657	1.943		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
HWY 51 55-13-042-QRY Created On: 01/21/15 Updated On:	Q	SW	NE	17	8N	10E	Dane	0-225-73-2015	0.8	1.6	2.7	7.9	32.6	2.609	2.666	2.187		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
HWY 51 55-13-042-QRY Created On: 05/08/17 Updated On:	Q	SW	NE	17	8N	10E	Dane	0-225-176-2017	1.1	0.7	2.6	7.3	31.9	2.610	2.669	2.267		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
HWY 51 55-13-042-QRY Created On: 04/10/18 Updated On:	Q	SW	NE	17	8N	10E	Dane	0-225-162-2018	1.9	3.5	2.9	7.6	32.3	2.586	2.647	2.375		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
HWY 51 55-13-042-QRY Created On: 03/27/19 Updated On:	Q	SW	NE	17	8N	10E	Dane	0-225-117-2019	0.8	2.2	3.0	7.4	31.4	2.647	2.687	1.511		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
HWY 51 55-13-042-QRY Created On: 03/09/20 Updated On:	Q	SW	NE	17	8N	10E	Dane	0-225-120-2020	0.2	1.5	2.8	7.3	30.8	2.613	2.664	1.961	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
HWY 51 55-13-042-QRY Created On: 03/29/21 Updated On:	Q	SW	NE	17	8N	10E	Dane	0-225-159-2021	0.4	1.9	1.6	7.8	30.5	2.607	2.662	2.141	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
HWY 51 55-13-042-QRY Created On: 01/04/22 Updated On:	Q	SW	NE	17	8N	10E	Dane	0-225-6-2022	1.8	5.3	2.3	6.9	30.3	2.579	2.644	2.541	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
HWY 51 55-13-042-QRY Created On: 01/23/23 Updated On:	Q	SW	NE	17	8N	10E	Dane	0-225-130-2023	0.5	2.1	1.3	7.0	30.9	2.588	2.650	2.406	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
HWY 51 55-13-042-QRY Created On: 01/02/24 Updated On:	Q	SW	NE	17	8N	10E	Dane	0-225-74-2024	0.4	2.3	3.0	6.7	30.2	2.567	2.635	2.653	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
* HWY-11 55-22-025-QRY Created On: 05/23/14 Updated On:	Q	SE	NW	26	1N	2W	Grant	0-225-171-2014	0.3	1.1	2.2	10.5	38.0	2.591	2.660	2.646	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
* HWY-11 55-22-025-QRY Created On: 06/01/21 Updated On:	Q	SE	NW	26	1N	2W	Grant	0-225-217-2021	0.8	2.9	3.4	9.4	37.2	2.608	2.667	2.256	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
* HWY-11 55-22-025-QRY Created On: 01/02/24 Updated On:	Q	SE	NW	26	1N	2W	Grant	0-225-32-2024	0.7	3.4	4.9	10.7	36.8	2.561	2.636	2.904	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
INDERGAND 55-23-007-QRY Created On: 07/16/15 Updated On:	Q	SE	SE	20	2N	7E	Green	0-225-210-2015		10.9	6.6	5.5	27.0	2.637	2.698	2.309	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
INDERGAND 55-23-007-QRY Created On: 04/12/16 Updated On:	Q	SE	SE	20	2N	7E	Green	0-225-140-2016		9.3	7.7	5.0	28.1	2.632	2.689	2.175	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
INDERGAND 55-23-007-QRY Created On: 05/16/19 Updated On:	Q	SE	SE	20	2N	7E	Green	0-225-190-2019	0.0	7.5	10.2	5.6	25.2	2.637	2.697	2.259	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
INDERGAND 55-23-007-QRY Created On: 04/05/22 Updated On:	Q	SE	SE	20	2N	7E	Green	0-225-155-2022	0.5	8.6	7.6	5.3	26.5	2.607	2.676	2.659	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
INDIAN LAKE 55-43-006-PIT Created On: 07/16/20 Updated On:	P	E	NE	6	38N	10E	Oneida	0-225-222-2020	0.1	0.0	1.2	4.5	20.1	2.688	2.711	0.856	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
* IRENE 17-01-010-QRY Created On: 05/01/18 Updated On:	Q		NW	9	43N	3E	Statewide	0-225-188-2018	0.2	4.8	4.8	7.6	37.9	2.599	2.662	2.393	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
* IRENE 17-01-010-QRY Created On: 08/10/20 Updated On:	Q		NW	9	43N	3E	Statewide	0-225-230-2020	0.2	10.2	3.9	8.5	35.5	2.603	2.665	2.378	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
IRON RIVER 26-00-008-PIT Created On: 01/05/17 Updated On:	P	SW	NW	22	43N	35W	Iron	0-225-40-2017	0.8	0.5	0.5	3.6	14.8	2.712	2.740	1.030	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
IRON RIVER 26-00-008-PIT Created On: 01/04/22 Updated On:	P	SW	NW	22	43N	35W	Iron	0-225-27-2022	0.0	0.5	0.6	3.4	15.1	2.715	2.736	0.752	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
IRVINE 55-61-009-QRY Created On: 07/02/15 Updated On:	Q	SW	NE	18	19N	7W	Trempealeau	0-225-205-2015		0.0	2.5	10.4	38.3	2.591	2.648	2.208	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
IRVINE 55-61-009-QRY Created On: 01/04/18 Updated On:	Q	SW	NE	18	19N	7W	Trempealeau	0-225-48-2018	0.7	0.0	5.8	9.3	36.2	2.603	2.667	2.483	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
IRVINE 55-61-009-QRY Created On: 01/04/21 Updated On:	Q	SW	NE	18	19N	7W	Trempealeau	0-225-4-2021	1.3	0.0	2.8	9.6	35.9	2.610	2.666	2.135	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
IRVINE 55-61-009-QRY Created On: 01/02/24 Updated On:	Q	SW	NE	18	19N	7W	Trempealeau	0-225-24-2024	0.6	7.8	10.6	13.5	46.5	2.572	2.645	2.820	
	Approved Use : CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
ISENBERGER 55-10-011-QRY Created On: 09/28/16 Updated On:	Q	SW	NW	6	28N	4W	Clark	0-225-265-2016		0.0	1.0	4.3	18.6	3.015	3.026	0.342	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
ISENBERGER 55-10-011-QRY Created On: 01/08/19 Updated On:	Q	SW	NW	6	28N	4W	Clark	0-225-79-2019		0.0	0.6	3.1	14.9	3.038	3.046	0.289	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
ISENBERGER 55-10-011-QRY Created On: 01/04/22 Updated On:	Q	SW	NW	6	28N	4W	Clark	0-225-82-2022	0.0	0.0	2.0	3.9	17.7	2.785	2.797	0.442	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
ISLAND STONE 55-15-030-QRY Created On: 06/28/22 Updated On:	Q	SW	SW	32	34N	30E	Door	0-225-237-2022	1.4	0.0	7.7	5.6	26.8	2.658	2.705	1.777	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
ISON 55-21-011-PIT Created On: 08/16/16 Updated On:	P	SE	NW	19	37N	13E	Forest	0-225-240-2016		0.0	0.6	6.5	26.2	2.696	2.713	0.646	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
ISON 55-21-011-PIT Created On: 01/04/21 Updated On:	P	SE	NW	19	37N	13E	Forest	0-225-12-2021	0.0	1.6	0.8	4.8	21.3	2.673	2.695	0.795	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
JACKSON 55-56-011-QRY Created On: 01/09/15 Updated On:	Q	SW	SW	6	10N	4E	Sauk	0-225-54-2015		0.0	4.0	11.9	40.5	2.561	2.632	2.764	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
JACKSON 55-56-011-QRY Created On: 01/03/18 Updated On:	Q	SW	SW	6	10N	4E	Sauk	0-225-9-2018	1.0	0.0	2.1	8.8	33.8	2.610	2.668	2.230		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
JACKSON 55-56-011-QRY Created On: 01/04/21 Updated On:	Q	SW	SW	6	10N	4E	Sauk	0-225-34-2021	0.5	0.0	0.4	7.9	32.5	2.635	2.685	1.882		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
JACKSON 55-56-011-QRY Created On: 01/29/24 Updated On:	Q	SW	SW	6	10N	4E	Sauk	0-225-153-2024	1.5	5.1	7.7	11.8	42.9	2.577	2.643	2.571		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
JACKSON COUNTY IRON MINE 55-27-004-QRY Created On: 01/06/14 Updated On:	Q			22	21N	3W	Jackson	0-225-11-2014		0.0	13.2	8.7	29.4	2.732	2.793	2.215		
	Approved Use : Base Aggregate																	
JACKSON COUNTY IRON MINE 55-27-004-QRY Created On: 04/10/17 Updated On:	Q			22	21N	3W	Jackson	0-225-120-2017		0.0	0.7	6.2	24.1	2.812	2.850	1.356		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
JACKSON COUNTY IRON MINE 55-27-004-QRY Created On: 01/08/20 Updated On:	Q			22	21N	3W	Jackson	0-225-62-2020		0.0	1.5	6.1	23.6	2.871	2.897	0.882		
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																	
JACKSON COUNTY IRON MINE 55-27-004-QRY Created On: 01/03/23 Updated On:	Q			22	21N	3W	Jackson	0-225-60-2023	0.5	5.5	5.7	6.6	25.0	2.785	2.832	1.679		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
JACKSON COUNTY IRON MINE 55-27-004-QRY Created On: 11/29/23 Updated On:	Q		22	21N	3W	Jackson		0-225-251-2023	1.2	2.9	2.5	6.7	24.3	2.805	2.837	1.125	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
JADIN 55-31-006-PIT Created On: 07/31/18 Updated On:	P	NE	SE	31	25N	25E	Kewaunee		0-225-260-2018	4.5	0.0	3.0	7.2	30.8	2.667	2.697	1.107
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
JADIN 55-31-006-PIT Created On: 05/09/23 Updated On:	P	NE	SE	31	25N	25E	Kewaunee		0-225-217-2023	1.4	0.0	3.1	5.8	28.8	2.691	2.733	1.554
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
* JADIN #2 55-15-009-QRY Created On: 06/27/18 Updated On:	Q	SW	NE	33	26N	24E	Door		0-225-242-2018		0.0	1.4	7.2	30.8	2.740	2.769	1.054
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
* JADIN #2 55-15-009-QRY Created On: 01/14/21 Updated On:	Q	SW	NE	33	26N	24E	Door		0-225-122-2021	0.0	0.0	0.3	6.9	31.1	2.709	2.742	1.219
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
JAECKS 55-35-027-PIT Created On: 06/25/20 Updated On:	P	SE	SW	1	34N	6E	Lincoln		0-225-208-2020	0.3	0.0	0.5	4.6	21.3	2.689	2.718	1.096
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
JANESVILLE SAND & GRAVEL 55-53-018-PIT Created On: 03/02/15 Updated On:	P	SE	SW	24	3N	12E	Rock		0-225-84-2015	2.0	6.2	2.1	6.7	30.0	2.628	2.679	1.925
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
JANESVILLE SAND & GRAVEL 55-53-018-PIT Created On: 01/08/20 Updated On:	P	SE	SW	24	3N	12E	Rock	0-225-50-2020	2.8	0.0	2.7	6.3	29.9	2.624	2.676	1.986	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
JANNETTE CHILTON QUARRY 55-08-019-QRY Created On: 01/04/24 Updated On:	Q	SW	SW	20	18N	20E	Calumet	0-225-136-2024	0.1	0.0	0.4	5.4	25.3	2.791	2.806	0.552	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
JAT ADAMS 55-03-044-PIT Created On: 01/08/20 Updated On:	P	NW	NE	12	33N	10W	Barron	0-225-51-2020	0.8	0.0	1.4	4.8	20.9	2.708	2.736	1.032	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
JENKINS 55-11-018-QRY Created On: 07/17/14 Updated On:	Q			11	13N	10E	Columbia	0-225-225-2014		0.8	3.0	10.5	39.5	2.578	2.643	2.502	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
JENKINS 55-11-018-QRY Created On: 05/11/17 Updated On:	Q			11	13N	10E	Columbia	0-225-184-2017		0.9	2.5	11.1	39.9	2.599	2.663	2.473	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
JENKINS 55-11-018-QRY Created On: 01/06/20 Updated On:	Q			11	13N	10E	Columbia	0-225-34-2020	0.2	0.9	2.7	9.9	38.8	2.602	2.663	2.366	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
JENKINS 55-11-018-QRY Created On: 01/03/23 Updated On:	Q			11	13N	10E	Columbia	0-225-69-2023	0.2	1.3	1.8	10.3	38.1	2.607	2.662	2.126	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
JENNEMAN 55-09-032-PIT Created On: 02/03/14 Updated On:	P		NE	6	30N	8W	Chippewa	0-225-75-2014		0.0	1.2	4.5	19.7	2.722	2.748	0.935	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
JENNEMAN 55-09-032-PIT Created On: 01/08/19 Updated On:	P		NE	6	30N	8W	Chippewa	0-225-77-2019	0.3	0.0	0.9	3.6	17.3	2.726	2.754	1.035	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
JENNEMAN 55-09-032-PIT Created On: 01/02/24 Updated On:	P		NE	6	30N	8W	Chippewa	0-225-85-2024	0.7	0.0	2.0	4.2	20.1	2.708	2.733	0.929	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
* JESSE 55-56-012-PIT Created On: 07/10/14 Updated On:	P		SE	SW	17	11N	7E	Sauk	0-225-219-2014		0.0	2.0	16.6		2.641	2.653	0.481
	Approved Use : CONCRETE, OGBC, Base Aggregate																
* JESSE 55-56-012-PIT Created On: 01/04/19 Updated On:	P		SE	SW	17	11N	7E	Sauk	0-225-30-2019	0.7	0.0	0.2	5.7	22.8	2.651	2.658	0.260
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
JET BLACK QUARRY 55-49-031-QRY Created On: 03/13/24 Updated On:	Q		NE	SW	25	25N	7E	Portage	0-225-200-2024	0.0	0.0	0.7	4.5	18.3	2.971	2.993	0.733
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
JOHNSON 55-03-024-PIT Created On: 05/23/23 Updated On:	P		NE	NW	5	35N	10W	Barron	0-225-227-2023	3.4	0.0	1.0	4.2	18.8	2.744	2.768	0.869
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description						Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range					County	100	500	OD	SSD	Crse
JOHNSON S&G BOWERS ROAD 55-64-015-PIT Created On: 04/03/14 Updated On:	P		NE 2	3N	17E	Walworth	0-225-114-2014	2.6	0.0	5.3	5.6	27.2	2.687	2.722	1.309	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate															
JOHNSON S&G BOWERS ROAD 55-64-015-PIT Created On: 04/24/19 Updated On:	P		NE 2	3N	17E	Walworth	0-225-159-2019	2.1	0.0	3.8	4.0	26.4	2.678	2.713	1.293	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate															
JOHNSON S&G BOWERS ROAD 55-64-015-PIT Created On: 03/27/24 Updated On:	P		NE 2	3N	17E	Walworth	0-225-214-2024	0.8	9.2	0.8	4.2	25.8	2.711	2.748	1.365	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate															
* JONES 55-25-016-QRY Created On: 05/08/15 Updated On:	Q	SE	NE 22	5N	1E	Iowa	0-225-158-2015	0.6	3.4	6.9	14.6	48.5	2.522	2.616	3.719	
	Approved Use : CONCRETE, Base Aggregate															
* JONES 55-25-016-QRY Created On: 03/23/18 Updated On:	Q	SE	NE 22	5N	1E	Iowa	0-225-140-2018	2.0	5.7	1.9	13.5	45.8	2.529	2.615	3.401	
	Approved Use : CONCRETE, Base Aggregate															
* JONES 55-25-016-QRY Created On: 03/17/21 Updated On:	Q	SE	NE 22	5N	1E	Iowa	0-225-145-2021	1.0	7.6	2.1	15.8	48.7	2.489	2.591	4.117	
	Approved Use : CONCRETE, OGBC, Base Aggregate															
* JORGENSON 55-70-004-QRY Created On: 01/09/15 Updated On:	Q		NE 5	20N	17E	Winnebago	0-225-48-2015	0.1	9.2	4.4	6.2	28.8	2.729	2.761	1.149	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate															

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Coarse Sp. Gravity		Coarse Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
* JORGENSON 55-70-004-QRY Created On: 01/04/18 Updated On:	Q	NE	5	20N	17E	Winnebago	0-225-55-2018		13.2	6.0	5.8	28.4	2.749	2.778	1.060			
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
* JORGENSON 55-70-004-QRY Created On: 01/05/21 Updated On:	Q	NE	5	20N	17E	Winnebago	0-225-51-2021	0.0	10.5	2.0	6.4	30.2	2.729	2.761	1.202			
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
JULIUS WIEST 55-22-028-QRY Created On: 05/23/14 Updated On:	Q	NE	NW	26	3N	5W	Grant	0-225-173-2014		2.5	2.7	9.0	35.6	2.621	2.677	2.149		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
JULIUS WIEST 55-22-028-QRY Created On: 04/25/17 Updated On:	Q	NE	NW	26	3N	5W	Grant	0-225-152-2017	0.2	15.9	7.0	10.9	41.3	2.562	2.639	2.987		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
JULIUS WIEST 55-22-028-QRY Created On: 04/19/19 Updated On:	Q	NE	NW	26	3N	5W	Grant	0-225-158-2019	0.8	11.1	10.9	12.4	42.9	2.584	2.652	2.647		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
JULIUS WIEST 55-22-028-QRY Created On: 01/04/22 Updated On:	Q	NE	NW	26	3N	5W	Grant	0-225-48-2022	0.9	15.9	0.8	9.7	36.0	2.578	2.651	2.840		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
JUMP RIVER 55-60-015-QRY Created On: 07/07/22 Updated On:	Q	NE	SE	14	33N	4W	Taylor	0-225-247-2022	0.0	0.0	0.5	4.7	21.6	2.662	2.676	0.519		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
JUMP RIVER PIT 55-60-037-PIT Created On: 01/02/24 Updated On:	P	SW	NE	13	33N	4W	Taylor	0-225-115-2024	0.2	0.0	5.5	4.3	19.9	2.732	2.770	1.387	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
K & N 55-67-019-PIT Created On: 02/05/19 Updated On:	P		S	9	8N	19E	Waukesha	0-225-96-2019		4.0	1.1	4.5	23.4	2.733	2.758	0.908	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
K & N 55-67-019-PIT Created On: 01/02/24 Updated On:	P		S	9	8N	19E	Waukesha	0-225-16-2024	0.1	2.3	1.8	5.2	23.9	2.730	2.756	0.960	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
K QUARRY 55-71-018-QRY Created On: 04/14/16 Updated On:	Q	SW	SW	13	24N	4E	Wood	0-225-147-2016		0.0	0.7	4.0	17.1	2.701	2.728	1.012	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
K QUARRY 55-71-018-QRY Created On: 01/04/21 Updated On:	Q	SW	SW	13	24N	4E	Wood	0-225-1-2021	0.5	0.0	2.9	3.4	15.5	2.699	2.718	0.710	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
K QUARRY 55-71-018-QRY Created On: 02/28/24 Updated On:	Q	SW	SW	13	24N	4E	Wood	0-225-172-2024	0.2	0.0	1.9	2.9	17.0	2.755	2.775	0.739	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
K-PIT ONEIDA 55-43-011-PIT Created On: 06/13/18 Updated On:	P	NW	NW	6	36N	8E	Oneida	0-225-228-2018	1.8	0.0	1.8	7.3	28.2	2.690	2.715	0.914	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
K-PIT ONEIDA 55-43-011-PIT Created On: 01/19/23 Updated On:	P	NW	NW	6	36N	8E	Oneida	0-225-129-2023	1.0	0.0	3.5	5.7	24.7	2.664	2.698	1.299	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
* KAASA 55-47-015-QRY Created On: 01/12/15 Updated On:	Q			15	24N	16W	Pierce	0-225-61-2015		0.0	5.4	11.6	42.0	2.551	2.623	2.801	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
* KAASA 55-47-015-QRY Created On: 01/03/18 Updated On:	Q			15	24N	16W	Pierce	0-225-35-2018	1.4	0.0	5.1	8.3	30.5	2.637	2.683	1.757	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
* KAASA 55-47-015-QRY Created On: 01/05/21 Updated On:	Q			15	24N	16W	Pierce	0-225-72-2021	1.8	0.0	0.6	9.0	32.3	2.660	2.701	1.557	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
KAFKA QUARRY 55-37-039-QRY Created On: 01/03/17 Updated On:	Q	NE	NW	3	27N	3E	Marathon	0-225-6-2017		0.0	0.5	2.0	10.6	2.776	2.785	0.325	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
KAFKA QUARRY 55-37-039-QRY Created On: 01/07/20 Updated On:	Q	NE	NW	3	27N	3E	Marathon	0-225-42-2020	0.0	0.0	0.1	2.5	10.8	2.800	2.805	0.201	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
KAFKA QUARRY 55-37-039-QRY Created On: 01/03/23 Updated On:	Q	NE	NW	3	27N	3E	Marathon	0-225-37-2023	0.0	0.8	0.6	3.5	14.6	2.749	2.766	0.638	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
KAFKA ROAD MATERIALS 55-37-097-QRY Created On: 05/09/23 Updated On:	Q	NE	SW	20	27N	6E	Marathon	0-225-216-2023	0.3	0.0	1.8	8.8	37.4	2.554	2.582	1.083	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
KAFKA ROAD MATERIALS 55-37-097-QRY Created On: 03/13/24 Updated On:	Q	NE	SW	20	27N	6E	Marathon	0-225-201-2024	0.0	0.0	1.1	7.3	28.7	2.571	2.596	0.979	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
KALATA 55-70-005-QRY Created On: 01/12/16 Updated On:	Q	NE	NE	27	19N	14E	Winnebago	0-225-52-2016	0.2	1.7	3.3	9.1	36.0	2.692	2.731	1.436	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
KALATA 55-70-005-QRY Created On: 05/24/19 Updated On:	Q	NE	NE	27	19N	14E	Winnebago	0-225-198-2019	0.9	0.8	1.9	8.0	33.5	2.701	2.739	1.422	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
KALATA 55-70-005-QRY Created On: 01/04/22 Updated On:	Q	NE	NE	27	19N	14E	Winnebago	0-225-17-2022	1.8	2.0	4.5	9.9	37.6	2.656	2.703	1.751	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
KALATA 55-70-005-QRY Created On: 01/02/24 Updated On:	Q	NE	NE	27	19N	14E	Winnebago	0-225-107-2024	0.3	1.2	3.9	8.0	35.0	2.679	2.720	1.510	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
KAMPMEIER 55-13-045-QRY Created On: 04/09/15 Updated On:	Q	SW	SW	26	7N	10E	Dane	0-225-119-2015	7.0	16.1	17.1	12.4	44.0	2.493	2.591	3.926	
	Approved Use : Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
KAMPMEIER 55-13-045-QRY Created On: 01/04/22 Updated On:	Q	SW	SW	26	7N	10E	Dane	0-225-58-2022	3.1	6.8	5.2	10.1	37.7	2.574	2.641	2.610		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
KAZMIERKOWSKI PIT 55-54-011-PIT Created On: 07/12/23 Updated On:	P	SW	SE	9	34N	8W	Rusk	0-225-237-2023	1.3	0.0	0.7	5.4	23.8	2.677	2.697	0.724		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
KELLEY 55-69-018-PIT Created On: 11/12/18 Updated On:	P	NE	NE	22	19N	3E	Waushara	0-225-291-2018	1.5	0.0	1.7	6.9	27.9	2.730	2.756	0.975		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
KELLEY 55-69-018-PIT Created On: 06/26/23 Updated On:	P	NE	NE	22	19N	3E	Waushara	0-225-236-2023		0.0	0.1	5.6	25.5	2.739	2.766	0.991		
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																	
KELLEY 55-04-019-PIT Created On: 10/04/21 Updated On:	P	SW	NW	25	43N	8W	Bayfield	0-225-266-2021	0.9	0.0	1.6	3.8	17.5	2.811	2.837	0.950		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
KELLY 55-13-047-QRY Created On: 04/06/16 Updated On:	Q	SW	SW	14	6N	7E	Dane	0-225-125-2016	0.2	15.7	7.7	9.7	36.0	2.582	2.655	2.854		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
KELLY 55-43-007-PIT Created On: 04/19/19 Updated On:	P	NE	SE	32	38N	11E	Oneida	0-225-151-2019	1.1	0.0	0.4	5.3	22.9	2.689	2.714	0.954		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
KELLY 55-13-047-QRY Created On: 06/03/19 Updated On:	Q	SW	SW	14	6N	7E	Dane	0-225-203-2019	0.7	5.3	0.5	8.1	33.6	2.583	2.656	2.826		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
KELLY 55-43-007-PIT Created On: 07/30/20 Updated On:	P	NE	SE	32	38N	11E	Oneida	0-225-227-2020	0.0	0.0	0.2	4.1	22.0	2.751	2.767	0.581		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
KELLY 55-13-047-QRY Created On: 01/04/22 Updated On:	Q	SW	SW	14	6N	7E	Dane	0-225-56-2022	0.7	5.0	2.4	6.7	28.9	2.581	2.648	2.573		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
KELLY QUARRY 55-43-034-QRY Created On: 01/03/23 Updated On:	Q	NE	SE	32	38N	11E	Oneida	0-225-25-2023	0.0	0.0	0.5	7.6	30.4	2.751	2.767	0.581		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
KESSLER 55-99-068-PIT Created On: 01/04/22 Updated On:	P	SE	SE	6	41N	4E		0-225-26-2022	0.0	0.6	2.1	3.0	15.6	2.775	2.802	0.979		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
KETTLESON 55-11-041-PIT Created On: 05/02/17 Updated On:	P	NW	NE	6	13N	7E	Columbia	0-225-163-2017		0.0	3.7	9.4	33.1	2.770	2.803	1.191		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
KETTLESON 55-11-041-PIT Created On: 01/04/22 Updated On:	P	NW	NE	6	13N	7E	Columbia	0-225-12-2022	0.5	0.0	1.5	6.4	27.6	2.773	2.803	1.093		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
* KIMBALL 55-26-013-QRY Created On: 04/23/15 Updated On:	Q	S	1	46N	1E	Iron	0-225-129-2015		0.0	1.6	2.6	12.0	2.733	2.764	1.142			
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
* KIMBALL 55-26-013-QRY Created On: 01/04/18 Updated On:	Q	S	1	46N	1E	Iron	0-225-60-2018	0.3	0.0	2.3	2.6	12.2	2.685	2.719	1.274			
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
* KIMBALL 55-26-013-QRY Created On: 04/30/21 Updated On:	Q	S	1	46N	1E	Iron	0-225-194-2021	0.3	0.0	2.4	2.6	12.3	2.700	2.736	1.344			
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
KIMMES 55-16-011-QRY Created On: 02/06/14 Updated On:	Q	SW	NW	14	47N	14W	Douglas	0-225-83-2014		0.0	7.1	4.1	16.3	2.703	2.734	1.161		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
KIMMES 55-16-011-QRY Created On: 02/13/17 Updated On:	Q	SW	NW	14	47N	14W	Douglas	0-225-67-2017		0.0	10.0	4.9	20.6	2.692	2.731	1.468		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
KIMMES 55-16-011-QRY Created On: 01/08/20 Updated On:	Q	SW	NW	14	47N	14W	Douglas	0-225-56-2020	0.0	0.0	4.2	2.8	13.6	2.756	2.786	1.086		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
KIMMES 55-16-011-QRY Created On: 01/03/23 Updated On:	Q	SW	NW	14	47N	14W	Douglas	0-225-56-2023	0.0	4.8	1.6	3.3	13.3	2.771	2.800	1.051		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
KING 55-43-008-QRY Created On: 04/05/16 Updated On:	Q	NW	NW	19	38N	10E	Oneida	0-225-121-2016		0.0	0.3	9.5	40.2	2.608	2.623	0.586		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
KING 55-41-011-QRY Created On: 04/07/16 Updated On:	Q	SE	SE	1	16N	1W	Monroe	0-225-130-2016		0.0	3.0	8.1	34.4	2.637	2.690	1.999		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
KING 55-41-011-QRY Created On: 05/04/17 Updated On:	Q	SE	SE	1	16N	1W	Monroe	0-225-172-2017		0.0	11.7	8.3	36.6	2.621	2.680	2.244		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
KING 55-43-008-QRY Created On: 01/07/19 Updated On:	Q	NW	NW	19	38N	10E	Oneida	0-225-69-2019		0.0	0.2	6.3	29.5	2.616	2.628	0.479		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
KING 55-41-011-QRY Created On: 04/02/20 Updated On:	Q	SE	SE	1	16N	1W	Monroe	0-225-140-2020	0.0	0.0	4.4	8.6	34.7	2.616	2.675	2.257		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
KING 55-43-008-QRY Created On: 07/16/20 Updated On:	Q	NW	NW	19	38N	10E	Oneida	0-225-219-2020	0.0	0.0	0.2	7.6	36.4	2.608	2.622	0.563		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
KING 55-43-008-QRY Created On: 01/03/23 Updated On:	Q	NW	NW	19	38N	10E	Oneida	0-225-20-2023	0.7	0.0	0.7	5.8	28.8	2.622	2.639	0.652		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
KING 55-41-011-QRY Created On: 05/22/23 Updated On:	Q	SE	SE	1	16N	1W	Monroe	0-225-221-2023	0.8	10.5	6.1	10.3	39.6	2.593	2.661	2.622		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
KINGS BLUFF 55-32-010-QRY Created On: 09/02/15 Updated On:	Q	W	NE	25	18N	8W	La Crosse	0-225-235-2015	1.6	0.0	3.6	10.9	40.9	2.580	2.649	2.670		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
KINGS BLUFF 55-32-010-QRY Created On: 04/25/17 Updated On:	Q	W	NE	25	18N	8W	La Crosse	0-225-156-2017		0.0	3.0	12.0	44.3	2.584	2.650	2.532		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
KINGS BLUFF 55-32-010-QRY Created On: 03/23/18 Updated On:	Q	W	NE	25	18N	8W	La Crosse	0-225-145-2018	0.9	0.0	9.9	13.7	45.3	2.572	2.644	2.793		
	Approved Use : CONCRETE, Base Aggregate																	
KINGS BLUFF 55-32-010-QRY Created On: 01/07/19 Updated On:	Q	W	NE	25	18N	8W	La Crosse	0-225-48-2019	1.9	0.0	3.2	11.0	42.9	2.593	2.654	2.373		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
KINGS BLUFF 55-32-010-QRY Created On: 01/04/22 Updated On:	Q	W	NE	25	18N	8W	La Crosse	0-225-10-2022	1.1	3.0	6.6	11.0	42.6	2.589	2.655	2.544		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
KIPPLEY 55-13-048-QRY Created On: 05/26/16 Updated On:	Q	NW	NE	11	8N	9E	Dane	0-225-186-2016	1.0	2.8	1.4	10.0	37.1	2.548	2.619	2.798		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
KIPPLEY 55-13-048-QRY Created On: 01/04/23 Updated On:	Q	NW	NE	11	8N	9E	Dane	0-225-99-2023	1.9	2.5	3.0	12.0	41.6	2.510	2.590	3.200	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
* KIRSCHBAUM 55-22-030-QRY Created On: 04/07/16 Updated On:	Q	NE	SW	26	5N	5W	Grant	0-225-135-2016	1.6	7.0	5.7	15.1	47.0	2.596	2.665	2.643	
	Approved Use : CONCRETE, Base Aggregate																
* KIRSCHBAUM 55-22-030-QRY Created On: 04/19/19 Updated On:	Q	NE	SW	26	5N	5W	Grant	0-225-157-2019	2.3	3.1	7.1	14.4	46.8	2.588	2.656	2.648	
	Approved Use : CONCRETE, Base Aggregate																
KISSER 55-15-013-QRY Created On: 01/04/16 Updated On:	Q	NW	NW	20	27N	25E	Door	0-225-9-2016		3.0	2.5	6.4	26.3	2.762	2.788	0.957	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
KISSER 55-15-013-QRY Created On: 01/08/19 Updated On:	Q	NW	NW	20	27N	25E	Door	0-225-73-2019		0.0	3.0	7.8	32.2	2.790	2.817	0.997	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
KISSER 55-15-013-QRY Created On: 01/10/22 Updated On:	Q	NW	NW	20	27N	25E	Door	0-225-97-2022	0.0	1.7	1.7	6.5	29.2	2.750	2.778	0.995	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
KLAR 55-22-031-QRY Created On: 06/30/16 Updated On:	Q	NW	NW	33	3N	2W	Grant	0-225-217-2016		5.4	4.3	11.7	40.9	2.580	2.653	2.810	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
KLAR 55-22-031-QRY Created On: 07/28/17 Updated On:	Q	NW	NW	33	3N	2W	Grant	0-225-244-2017	2.3	6.0	2.2	11.1	40.3	2.575	2.649	2.872	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
KLAR 55-22-031-QRY Created On: 04/28/20 Updated On:	Q	NW	NW	33	3N	2W	Grant	0-225-157-2020	0.7	3.3	1.8	9.8	36.6	2.604	2.667	2.432	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
KLAR 55-22-031-QRY Created On: 01/03/23 Updated On:	Q	NW	NW	33	3N	2W	Grant	0-225-11-2023	1.0	2.8	4.2	9.3	35.6	2.575	2.646	2.751	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
KLAVER 55-43-009-PIT Created On: 08/28/14 Updated On:	P	NW	SE	4	36N	8E	Oneida	0-225-251-2014		0.0	1.0	4.8	22.5	2.715	2.747	1.157	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
KLAVER 55-43-009-PIT Created On: 06/25/20 Updated On:	P	NW	SE	4	36N	8E	Oneida	0-225-209-2020	0.1	0.0	0.6	5.1	23.4	2.737	2.759	0.791	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
KLINGAMEYER-LARUE 55-56-015-QRY Created On: 08/16/16 Updated On:	Q		NW	22	11N	5E	Sauk	0-225-245-2016		0.0	0.2	5.5	24.1	2.619	2.632	0.495	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
KLINGAMEYER-LARUE 55-56-015-QRY Created On: 04/06/21 Updated On:	Q		NW	22	11N	5E	Sauk	0-225-170-2021	1.3	0.4	0.5	6.5	26.6	2.599	2.621	0.843	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
KLINGAMEYER-LARUE 55-56-015-QRY Created On: 01/02/24 Updated On:	Q		NW	22	11N	5E	Sauk	0-225-69-2024	0.5	0.2	0.4	6.0	23.8	2.603	2.627	0.914	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
* KLITZKE 55-23-009-QRY Created On: 03/19/15 Updated On:	Q			16	4N	7E	Green	0-225-97-2015		5.6	6.7	14.1	46.7	2.510	2.611	4.014	
	Approved Use : CONCRETE, Base Aggregate																
* KLITZKE 55-23-009-QRY Created On: 05/11/18 Updated On:	Q			16	4N	7E	Green	0-225-211-2018	1.7	6.8	7.7	12.3	41.5	2.546	2.634	3.485	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
* KLITZKE 55-23-009-QRY Created On: 04/30/21 Updated On:	Q			16	4N	7E	Green	0-225-195-2021	0.1	22.4	3.8	10.4	38.2	2.582	2.655	2.836	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
* KLITZKE 55-23-009-QRY Created On: 08/11/21 Updated On:	Q			16	4N	7E	Green	0-225-258-2021	0.1	5.0	7.4	10.8	37.5	2.595	2.654	2.282	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
KNUTSON 55-03-026-PIT Created On: 04/07/16 Updated On:	P	SW	SE	22	32N	11W	Barron	0-225-128-2016		0.0	1.7	4.6	20.3	2.698	2.729	1.168	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
KNUTSON 55-03-026-PIT Created On: 07/19/21 Updated On:	P	SW	SE	22	32N	11W	Barron	0-225-247-2021	3.5	0.0	1.3	4.3	20.2	2.677	2.709	1.178	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Coarse Sp. Gravity		Coarse Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
KOCH QUARRY 55-52-028-QRY Created On: 05/03/22 Updated On:	Q	SE	NE	18	11N	2E	Richland	0-225-198-2022	0.7	7.5	9.3	11.3	42.4	2.588	2.661	2.816		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
KOEPEL 55-34-015-PIT Created On: 06/13/22 Updated On:	P		NW	12	30N	12E	Langlade	0-225-228-2022	0.0	0.5	0.3	6.6	29.3	2.671	2.691	0.743		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
KOHN 55-11-019-PIT Created On: 05/03/22 Updated On:	P			30	12N	11E	Columbia	0-225-193-2022	2.7	4.5	3.6	5.9	27.9	2.717	2.754	1.376		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
KORDUS AGGREGATES 55-51-057-PIT Created On: 06/25/21 Updated On:	P	S	SW	7	2N	19E	Racine	0-225-235-2021	1.2	10.9	5.3	7.4	31.0	2.656	2.708	1.942		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
KOSSUTH QUARRY 55-36-048-QRY Created On: 03/28/18 Updated On:	Q	W	SE	36	20N	23E	Manitowoc	0-225-151-2018	0.0	0.8	0.4	7.4	33.2	2.794	2.811	0.633		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
KOSSUTH QUARRY 55-36-048-QRY Created On: 01/05/21 Updated On:	Q	W	SE	36	20N	23E	Manitowoc	0-225-106-2021	0.0	1.0	2.2	8.1	33.3	2.752	2.780	1.045		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
KOSSUTH QUARRY 55-36-048-QRY Created On: 01/04/24 Updated On:	Q	W	SE	36	20N	23E	Manitowoc	0-225-135-2024	0.0	0.0	0.8	10.1	37.8	2.766	2.790	0.852		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
KRAEMER 55-59-008-PIT Created On: 01/21/16 Updated On:	P	SW	NE	13	14N	20E	Sheboygan	0-225-64-2016	0.5	0.0	0.8	6.0	28.8	2.752	2.778	0.927		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
KRAEMER 55-59-008-PIT Created On: 01/05/21 Updated On:	P	SW	NE	13	14N	20E	Sheboygan	0-225-108-2021	0.5	2.2	0.7	5.6	26.9	2.740	2.767	0.981		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
KRAUS 55-50-011-PIT Created On: 07/17/14 Updated On:	P	E	NE	7	34N	3E	Price	0-225-226-2014		0.0	4.3	3.8	18.3	2.709	2.740	1.125		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
KRAUS 55-50-011-PIT Created On: 06/26/19 Updated On:	P	E	NE	7	34N	3E	Price	0-225-231-2019	2.0	0.0	2.0	4.6	20.0	2.691	2.725	1.263		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
KRAUS 55-50-011-PIT Created On: 01/02/24 Updated On:	P	E	NE	7	34N	3E	Price	0-225-113-2024	7.1	0.0	5.9	6.4	24.0	2.674	2.714	1.513		
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																	
* KREPLINE 55-08-012-QRY Created On: 05/26/16 Updated On:	Q	NE	NE	34	19N	19E	Calumet	0-225-191-2016		0.0	2.8	8.3	35.1	2.689	2.727	1.415		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
* KREPLINE 55-08-012-QRY Created On: 04/24/19 Updated On:	Q	NE	NE	34	19N	19E	Calumet	0-225-167-2019	0.1	0.0	0.5	13.1	49.1	2.671	2.706	1.319		
	Approved Use : HMA<MT, CONCRETE, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
KREUGER 55-13-050-QRY Created On: 06/10/15 Updated On:	Q	SW	SW	3	6N	11E	Dane	0-225-194-2015		24.6	6.9	6.0	30.0	2.641	2.699	2.220	
KREUGER 55-13-050-QRY Created On: 08/05/15 Updated On:	Q	SW	SW	3	6N	11E	Dane	0-225-224-2015		9.1	11.1	7.1	31.7	2.641	2.701	2.300	
KREUGER 55-13-050-QRY Created On: 01/04/18 Updated On:	Q	SW	SW	3	6N	11E	Dane	0-225-65-2018		0.3	1.7	8.1	5.6	27.7	2.657	2.707	1.912
KREUGER 55-13-050-QRY Created On: 06/14/21 Updated On:	Q	SW	SW	3	6N	11E	Dane	0-225-223-2021		0.6	7.9	7.2	5.4	26.7	2.679	2.730	1.906
KREUGER 55-13-050-QRY Created On: 04/04/23 Updated On:	Q	SW	SW	3	6N	11E	Dane	0-225-180-2023		0.6	14.7	10.1	10.1	39.8	2.523	2.614	3.604
KROENING 55-58-014-QRY Created On: 01/07/15 Updated On:	Q			24	26N	17E	Shawano	0-225-16-2015		11.1	12.8	7.5	28.7	2.674	2.721	1.762	
KROENING 55-58-014-QRY Created On: 01/04/18 Updated On:	Q			24	26N	17E	Shawano	0-225-58-2018		0.6	11.6	15.2	8.8	32.3	2.640	2.696	2.126

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
KROENING 55-58-014-QRY Created On: 01/04/19 Updated On:	Q			24	26N	17E	Shawano	0-225-38-2019	1.4	20.7	15.4	7.2	28.0	2.638	2.698	2.278	
KROENING 55-58-014-QRY Created On: 01/02/20 Updated On:	Q			24	26N	17E	Shawano	0-225-10-2020 Approved Use : Base Aggregate	1.6	14.3	13.1	7.0	28.2	2.662	2.713	1.937	
KROENING 55-58-014-QRY Created On: 01/03/23 Updated On:	Q			24	26N	17E	Shawano	0-225-78-2023 Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate	1.8	8.0	7.0	6.0	25.7	2.715	2.748	1.198	
KROPP AB 55-31-020-QRY Created On: 02/11/19 Updated On:	Q	NE	SE	15	22N	23E	Kewaunee	0-225-105-2019 Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate		0.0	1.7	7.9	34.6	2.810	2.823	0.456	
KROPP AB 55-31-020-QRY Created On: 04/28/22 Updated On:	Q	NE	SE	15	22N	23E	Kewaunee	0-225-187-2022 Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate	0.2	0.0	3.4	8.1	35.0	2.780	2.801	0.737	
KRUEGER 55-42-017-QRY Created On: 01/07/16 Updated On:	Q	SE	SE	6	27N	21E	Oconto	0-225-35-2016 Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate	0.0	1.2	2.5	6.3	29.1	2.693	2.728	1.313	
KRUEGER 55-42-017-QRY Created On: 01/25/19 Updated On:	Q	SE	SE	6	27N	21E	Oconto	0-225-91-2019 Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate	0.3	13.2	4.0	6.4	29.0	2.668	2.708	1.509	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
KRUEGER 55-42-017-QRY Created On: 01/04/22 Updated On:	Q	SE	SE	6	27N	21E	Oconto	0-225-93-2022	0.1	2.4	3.4	5.7	27.8	2.710	2.740	1.084	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
KRUG 55-60-012-PIT Created On: 08/07/14 Updated On:	P			28	32N	1E	Taylor	0-225-241-2014		0.0	0.2	4.4	20.5	2.703	2.737	1.245	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
KRUG 55-60-012-PIT Created On: 05/24/19 Updated On:	P			28	32N	1E	Taylor	0-225-201-2019	0.1	0.0	1.7	3.9	17.5	2.723	2.750	0.972	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
KRUG 55-60-012-PIT Created On: 01/02/24 Updated On:	P			28	32N	1E	Taylor	0-225-112-2024	0.1	0.0	4.2	3.8	17.9	2.717	2.751	1.222	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
KUCZMARSKI 55-43-037-PIT Created On: 01/02/24 Updated On:	P	W	SE	26	37N	10E	Oneida	0-225-64-2024	0.2	0.0	1.1	4.3	20.6	2.716	2.736	0.722	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
KUNKEL QUARRY 55-22-066-QRY Created On: 05/22/23 Updated On:	Q	SE	NE	15	1N	2W	Grant	0-225-220-2023	2.0	2.8	2.7	13.2	42.6	2.529	2.615	3.406	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
* KUSSMAUL 55-22-036-QRY Created On: 04/07/16 Updated On:	Q	NW	SE	34	6N	4W	Grant	0-225-137-2016	0.5	3.1	3.8	10.4	37.8	2.598	2.657	2.284	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
* KUSSMAUL 55-22-036-QRY Created On: 01/04/19 Updated On:	Q	NW	SE	34	6N	4W	Grant	0-225-26-2019	0.9	3.8	3.7	10.8	39.0	2.631	2.682	1.954		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
LABINE 55-21-21-PIT Created On: 08/22/17 Updated On:	P	S	SW	12	37N	16E	Forest	0-225-258-2017	0.8	0.0	0.5	5.1	19.9	2.741	2.762	0.732		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
LABINE 55-21-21-PIT Created On: 06/13/22 Updated On:	P	S	SW	12	37N	16E	Forest	0-225-227-2022	0.0	0.6	0.8	4.0	18.0	2.724	2.743	0.691		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
LADYSMITH EAST 55-54-012-PIT Created On: 01/03/18 Updated On:	P	S	NW	15	35N	6W	Rusk	0-225-30-2018	1.0	0.0	1.3	4.2	19.1	2.727	2.752	0.906		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
LADYSMITH EAST 55-54-012-PIT Created On: 01/10/23 Updated On:	P	S	NW	15	35N	6W	Rusk	0-225-109-2023	1.1	0.0	2.6	3.8	19.1	2.687	2.718	1.173		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
LADYSMITH WEST 55-54-022-PIT Created On: 03/08/18 Updated On:	P	SE	NW	16	35N	6W	Rusk	0-225-117-2018	1.8	0.0	2.4	4.0	18.9	2.688	2.721	1.225		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
LADYSMITH WEST 55-54-022-PIT Created On: 03/06/23 Updated On:	P	SE	NW	16	35N	6W	Rusk	0-225-163-2023	0.0	0.0	1.0	4.4	19.1	2.733	2.761	1.051		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
* LAFARGE KENDALL 17-00-017-QRY Created On: 04/30/21 Updated On:	Q	W	29	35N	7E	Kendall, Il	0-225-199-2021	0.6	1.9	0.4	6.8	29.0	2.695	2.727	1.213			
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
LAGESSE 55-09-036-PIT Created On: 08/19/15 Updated On:	P	SE	SE	7	30N	8W	Chippewa	0-225-228-2015		0.0	0.7	4.5	20.3	2.739	2.761	0.799		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
LAGESSE 55-09-036-PIT Created On: 01/09/20 Updated On:	P	SE	SE	7	30N	8W	Chippewa	0-225-86-2020	0.7	0.0	0.9	3.7	17.9	2.717	2.745	1.050		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
LAGRANGE 55-64-024-PIT Created On: 01/07/14 Updated On:	P	W	SE	20	4N	16E	Walworth	0-225-42-2014		0.0	2.3	6.5	27.3	2.704	2.738	1.237		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
LAGRANGE 55-64-024-PIT Created On: 02/05/19 Updated On:	P	W	SE	20	4N	16E	Walworth	0-225-94-2019	0.9	7.0	0.5	4.3	22.4	2.695	2.731	1.337		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
LAGRANGE 55-64-024-PIT Created On: 01/02/24 Updated On:	P	W	SE	20	4N	16E	Walworth	0-225-17-2024	0.0	4.5	2.9	4.8	23.2	2.705	2.738	1.224		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
LAKETOWN 55-48-015-QRY Created On: 05/07/15 Updated On:	Q	SW	SE	12	36N	18W	Polk	0-225-149-2015		0.0	0.5	0.9	9.3	2.993	3.000	0.243		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
LAKETOWN 55-48-015-QRY Created On: 05/21/18 Updated On:	Q	SW	SE	12	36N	18W	Polk	0-225-215-2018	0.0	0.0	1.4	2.5	11.3	2.967	2.979	0.405		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
LAKETOWN 55-48-015-QRY Created On: 01/04/21 Updated On:	Q	SW	SE	12	36N	18W	Polk	0-225-38-2021	0.0	0.3	0.2	1.7	8.0	2.998	3.009	0.384		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
LAKETOWN 55-48-015-QRY Created On: 01/04/24 Updated On:	Q	SW	SE	12	36N	18W	Polk	0-225-142-2024	0.0	0.1	0.2	1.9	9.2	2.989	3.001	0.384		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
LANGE (CAREY) 55-33-013-QRY Created On: 10/10/16 Updated On:	Q	NE	SE	6	2N	3E	Lafayette	0-225-266-2016	3.3	2.6	1.6	8.3	33.3	2.545	2.620	2.968		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
LANGE (CAREY) 55-33-013-QRY Created On: 01/07/19 Updated On:	Q	NE	SE	6	2N	3E	Lafayette	0-225-56-2019	3.2	6.2	3.8	10.9	38.1	2.530	2.609	3.125		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
LANGE (CAREY) 55-33-013-QRY Created On: 01/10/22 Updated On:	Q	NE	SE	6	2N	3E	Lafayette	0-225-106-2022	2.2	8.1	8.8	10.4	39.6	2.502	2.594	3.681		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
LANNON LISBON PIT 55-67-024-PIT Created On: 01/08/15 Updated On:	P		SW	24	8N	19E	Waukesha	0-225-31-2015	0.8	2.9	4.9	6.4	29.2	2.729	2.758	1.039		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
LANNON LISBON PIT 55-67-024-PIT Created On: 01/09/20 Updated On:	P		SW 24	8N	19E	Waukesha	0-225-93-2020	0.0	2.7	1.1	4.3	22.9	2.736	2.764	1.041		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
LANNON STONE - JACKSON 55-66-012-QRY Created On: 01/22/16 Updated On:	Q		NE 12	10N	20E	Washington	0-225-75-2016		0.3	0.2	9.4	34.0	2.705	2.734	1.068		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
LANNON STONE - JACKSON 55-66-012-QRY Created On: 01/18/19 Updated On:	Q		NE 12	10N	20E	Washington	0-225-88-2019		0.9	0.2	8.9	34.4	2.658	2.697	1.478		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
LANNON STONE - JACKSON 55-66-012-QRY Created On: 01/13/22 Updated On:	Q		NE 12	10N	20E	Washington	0-225-111-2022	0.0	0.7	0.6	8.1	36.5	2.608	2.648	1.554		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
LANNON STONE - JACKSON 55-66-012-QRY Created On: 01/03/23 Updated On:	Q		NE 12	10N	20E	Washington	0-225-80-2023	1.6	1.6	0.6	7.4	31.6	2.620	2.670	1.914		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
* LANNON STONE - LANNON 55-67-026-QRY Created On: 01/08/15 Updated On:	Q		E 20	8N	20E	Waukesha	0-225-34-2015		0.9	4.6	6.1	28.5	2.720	2.748	1.026		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
* LANNON STONE - LANNON 55-67-026-QRY Created On: 02/09/18 Updated On:	Q		E 20	8N	20E	Waukesha	0-225-91-2018		3.8	2.3	5.5	24.0	2.729	2.759	1.110		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description						Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range					County	100	500	OD	SSD	Crse
* LANNON STONE - LANNON 55-67-026-QRY Created On: 01/08/21 Updated On:	Q	E	20	8N	20E	Waukesha	0-225-115-2021	0.0	2.7	4.1	4.8	21.8	2.746	2.772	0.936	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate															
LANNON STONE - RICHFIELD 55-66-013-PIT Created On: 02/16/16 Updated On:	P	SE	24	9N	19E	Washington	0-225-89-2016		2.6	1.1	8.2	35.1				
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate															
LANNON STONE - RICHFIELD 55-66-013-PIT Created On: 01/08/21 Updated On:	P	SE	24	9N	19E	Washington	0-225-114-2021	0.0	2.2	2.3	6.9	28.6	2.710	2.740	1.116	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate															
LANNON STONE - SUSSEX 55-67-025-QRY Created On: 02/28/14 Updated On:	Q	NE	35	8N	19E	Waukesha	0-225-92-2014	0.2	0.4	0.7	4.7	22.7	2.692	2.730	1.403	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate															
LANNON STONE - SUSSEX 55-67-025-QRY Created On: 04/04/17 Updated On:	Q	NE	35	8N	19E	Waukesha	0-225-103-2017		1.5	1.2	5.7	25.8	2.721	2.748	0.980	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate															
LANNON STONE - SUSSEX 55-67-025-QRY Created On: 01/08/20 Updated On:	Q	NE	35	8N	19E	Waukesha	0-225-80-2020	0.0	0.9	0.6	5.0	24.9	2.715	2.747	1.167	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate															
LANNON STONE - SUSSEX 55-67-025-QRY Created On: 02/27/23 Updated On:	Q	NE	35	8N	19E	Waukesha	0-225-145-2023	3.7	3.1	0.9	5.3	24.7	2.735	2.767	1.176	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate															

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description						Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range					County	100	500	OD	SSD	Crse
LANNON STONE - WEST QUARRY 55-67-008-QRY Created On: 01/08/15 Updated On:	Q		NW	35	8N	19E	Waukesha	0-225-33-2015	0.8	1.3	5.8	26.1	2.738	2.766	1.027	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate															
LANNON STONE - WEST QUARRY 55-67-008-QRY Created On: 01/12/16 Updated On:	Q		NW	35	8N	19E	Waukesha	0-225-57-2016	0.6	0.4	8.2	39.7	2.716	2.743	0.974	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate															
LANNON STONE - WEST QUARRY 55-67-008-QRY Created On: 02/11/19 Updated On:	Q		NW	35	8N	19E	Waukesha	0-225-101-2019	6.2	5.1	1.2	4.1	22.4	2.715	2.750	1.282
	Approved Use : HMA<MT, HMA>=MT, Base Aggregate															
LANNON STONE - WEST QUARRY 55-67-008-QRY Created On: 01/13/22 Updated On:	Q		NW	35	8N	19E	Waukesha	0-225-110-2022	0.0	11.1	4.1	5.3	25.5	2.684	2.725	1.512
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate															
LANNON STONE - WEST QUARRY 55-67-008-QRY Created On: 01/03/23 Updated On:	Q		NW	35	8N	19E	Waukesha	0-225-81-2023	2.7	12.1	0.5	5.5	25.4	2.718	2.748	1.109
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate															
LARSEN 55-70-007-QRY Created On: 01/05/15 Updated On:	Q	N	NE	19	20N	16E	Winnebago	0-225-2-2015	1.6	0.7	1.9	5.0	23.1	2.725	2.755	1.102
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate															
LARSEN 55-70-007-QRY Created On: 01/04/18 Updated On:	Q	N	NE	19	20N	16E	Winnebago	0-225-54-2018	0.7	0.7	4.8	22.8	2.716	2.749	1.211	
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate															

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
LARSEN 55-70-007-QRY Created On: 01/05/21 Updated On:	Q	N	NE	19	20N	16E	Winnebago	0-225-47-2021	0.0	1.6	2.1	6.8	27.4	2.713	2.750	1.340		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
LARSEN 55-70-007-QRY Created On: 01/02/24 Updated On:	Q	N	NE	19	20N	16E	Winnebago	0-225-97-2024	0.5	0.7	0.2	4.8	21.3	2.756	2.779	0.800		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
LASSIG PIT 55-43-036-PIT Created On: 09/05/23 Updated On:	P	NW	NE	29	36N	9E	Oneida	0-225-249-2023	0.1	0.0	3.5	6.8	27.4	2.726	2.748	0.838		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
LATHER 55-53-022-PIT Created On: 04/12/16 Updated On:	P	NW	NW	16	1N	13E	Rock	0-225-141-2016	0.9	3.6	4.1	4.7	25.0	2.638	2.679	1.560		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
LATHER 55-53-022-PIT Created On: 02/06/18 Updated On:	P	NW	NW	16	1N	13E	Rock	0-225-88-2018	3.0	0.0	2.2	4.7	23.8	2.640	2.683	1.638		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
LATHER 55-53-022-PIT Created On: 01/07/19 Updated On:	P	NW	NW	16	1N	13E	Rock	0-225-67-2019	3.8	0.0	5.1	5.1	26.9	2.632	2.676	1.690		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
LATHER 55-53-022-PIT Created On: 03/13/24 Updated On:	P	NW	NW	16	1N	13E	Rock	0-225-197-2024	4.9	6.0	1.8	4.4	23.9	2.637	2.677	1.504		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Coarse Sp. Gravity		Coarse Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
* LATZIG 55-35-024-PIT Created On: 07/07/14 Updated On:	P	SW	NW	31	33N	8E	Lincoln	0-225-214-2014		0.0	0.9	3.2	17.7	2.685	2.714	1.085		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
* LATZIG 55-35-024-PIT Created On: 01/04/19 Updated On:	P	SW	NW	31	33N	8E	Lincoln	0-225-4-2019	0.7	0.0	2.7	4.2	19.4	2.673	2.708	1.311		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
LAUERSDORF 55-42-019-QRY Created On: 03/17/16 Updated On:	Q	NE	SW	35	29N	18E	Oconto	0-225-99-2016	0.9	1.4	0.7	8.5	35.6	2.700	2.738	1.396		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
LAUERSDORF 55-42-019-QRY Created On: 01/08/20 Updated On:	Q	NE	SW	35	29N	18E	Oconto	0-225-71-2020	0.1	0.9	3.0	8.7	35.9	2.728	2.756	1.027		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
LAUERSDORF 55-42-019-QRY Created On: 01/12/23 Updated On:	Q	NE	SW	35	29N	18E	Oconto	0-225-120-2023	0.0	4.8	4.8	10.1	41.3	2.648	2.700	1.964		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
LAWRENCE 55-05-015-QRY Created On: 01/08/16 Updated On:	Q	SW	SW	30	23N	20E	Brown	0-225-46-2016	0.1	12.6	5.1	6.2	26.6	2.725	2.762	1.360		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
LAWRENCE 55-05-015-QRY Created On: 01/05/17 Updated On:	Q	SW	SW	30	23N	20E	Brown	0-225-36-2017	0.2	22.6	18.9	8.3	29.1	2.740	2.774	1.237		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
LAWRENCE 55-05-015-QRY Created On: 03/22/17 Updated On:	Q	SW	SW	30	23N	20E	Brown	0-225-84-2017		5.0	15.9	6.8	24.4	2.745	2.776	1.122	
LAWRENCE 55-05-015-QRY Created On: 04/11/18 Updated On:	Q	SW	SW	30	23N	20E	Brown	0-225-167-2018	0.3	16.7	11.1	5.1	23.5	2.747	2.776	1.066	
LAWRENCE 55-05-015-QRY Created On: 07/18/19 Updated On:	Q	SW	SW	30	23N	20E	Brown	0-225-239-2019	0.2	15.6	20.0	5.2	24.1	2.751	2.779	1.028	
LAWRENCE 55-05-015-QRY Created On: 06/09/20 Updated On:	Q	SW	SW	30	23N	20E	Brown	0-225-192-2020	0.2	8.2	4.0	5.0	21.8	2.778	2.801	0.853	
LAWRENCE 55-05-015-QRY Created On: 01/10/22 Updated On:	Q	SW	SW	30	23N	20E	Brown	0-225-99-2022	0.6	3.4	4.6	5.0	22.0	2.752	2.779	0.979	
LAWRENCE 55-05-015-QRY Created On: 01/03/23 Updated On:	Q	SW	SW	30	23N	20E	Brown	0-225-45-2023	0.4	6.2	3.8	6.4	25.9	2.723	2.759	1.313	
* LDV 55-51-055-PIT Created On: 05/13/19 Updated On:	P	SE	NW	5	2N	19E	Racine	0-225-189-2019		0.0	5.6	5.7	27.0	2.681	2.723	1.543	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
LEATHERBERRY 55-56-017-PIT Created On: 06/12/14 Updated On:	P	E	NW	26	12N	6E	Sauk	0-225-191-2014		0.0	1.6	7.0	26.8	2.630	2.666	1.370		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
LEATHERBERRY 55-56-017-PIT Created On: 01/08/20 Updated On:	P	E	NW	26	12N	6E	Sauk	0-225-66-2020		0.0	2.1	8.8	29.4	2.649	2.681	1.198		
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																	
* LEIGHTY 55-25-017-QRY Created On: 02/09/18 Updated On:	Q	N	NE	4	4N	1E	Iowa	0-225-93-2018	0.9	1.6	6.7	10.6	39.6	2.556	2.628	2.822		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
* LEIGHTY 55-25-017-QRY Created On: 03/17/21 Updated On:	Q	N	NE	4	4N	1E	Iowa	0-225-140-2021	1.6	12.7	4.0	8.2	34.8	2.539	2.621	3.259		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
LEMBERGER QUARRY 55-36-049-QRY Created On: 01/29/24 Updated On:	Q	SE	NE	34	20N	22E	Manitowoc	0-225-164-2024	0.2	0.0	0.6	9.6	34.6	2.716	2.747	1.116		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
* LEMKE STONE 55-67-046-QRY Created On: 05/07/20 Updated On:	Q	NE	NW	19	8N	20E	Waukesha	0-225-174-2020	0.0	2.1	3.1	5.3	25.3	2.755	2.792	1.319		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
LEWIN 55-09-039-PIT Created On: 01/07/15 Updated On:	P		NE	18	30N	8W	Chippewa	0-225-12-2015		0.0	2.1	3.9	19.0	2.690	2.715	0.956		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
LEWIN 55-09-039-PIT Created On: 01/08/19 Updated On:	P		NE	18	30N	8W	Chippewa	0-225-74-2019	2.8	0.0	1.9	3.8	19.9	2.706	2.734	1.029		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
LEWIN 55-09-039-PIT Created On: 01/02/24 Updated On:	P		NE	18	30N	8W	Chippewa	0-225-83-2024	1.6	0.0	1.7	4.5	19.7	2.711	2.737	0.970		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
LIGHTS 55-09-080-PIT Created On: 04/02/20 Updated On:	P	SE	NW	23	29N	6W	Chippewa	0-225-144-2020	2.2	0.0	2.2	4.8	20.7	2.708	2.735	0.984		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
LINCK #22 55-14-019-QRY Created On: 01/29/15 Updated On:	Q	SW	SW	9	12N	14E	Dodge	0-225-79-2015		2.4	0.9	6.3	29.1	2.764	2.786	0.794		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
LINCK #22 55-14-019-QRY Created On: 03/01/18 Updated On:	Q	SW	SW	9	12N	14E	Dodge	0-225-107-2018	0.3	3.8	2.2	6.9	28.9	2.743	2.777	1.239		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
LINCK #22 55-14-019-QRY Created On: 03/29/21 Updated On:	Q	SW	SW	9	12N	14E	Dodge	0-225-162-2021	0.0	10.4	0.5	6.8	27.2	2.768	2.794	0.938		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
LINCK #22 55-14-019-QRY Created On: 02/28/24 Updated On:	Q	SW	SW	9	12N	14E	Dodge	0-225-189-2024	0.0	5.0	0.3	5.3	24.0	2.778	2.799	0.762		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
LINCK #26 55-20-028-QRY Created On: 05/09/19 Updated On:	Q	NW	SE	36	14N	14E	Fond Du Lac	0-225-183-2019	0.0	0.9	0.9	6.3	26.4	2.778	2.800	0.809		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
LINCK #26 55-20-028-QRY Created On: 06/28/22 Updated On:	Q	NW	SE	36	14N	14E	Fond Du Lac	0-225-236-2022	0.0	4.4	0.5	6.4	25.6	2.780	2.802	0.798		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
* LINCK #27 55-11-026-QRY Created On: 01/29/15 Updated On:	Q	SW	SW	24	10N	12E	Columbia	0-225-77-2015	0.3	1.4	3.6	5.6	22.9	2.622	2.673	1.954		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
* LINCK #27 55-11-026-QRY Created On: 03/01/18 Updated On:	Q	SW	SW	24	10N	12E	Columbia	0-225-108-2018	0.3	3.2	2.5	8.3	35.0	2.577	2.657	3.087		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
* LINCK #27 55-11-026-QRY Created On: 03/29/21 Updated On:	Q	SW	SW	24	10N	12E	Columbia	0-225-164-2021	5.0	14.3	1.2	10.5	38.5	2.587	2.654	2.563		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
LINCOLN CTH W 55-35-041-PIT Created On: 01/02/20 Updated On:	P	E	SW	33	31N	7E	Lincoln	0-225-11-2020	3.2	0.0	6.2	5.1	22.7	2.613	2.655	1.617		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
LINDBERG AND SONS 26-99-001-PIT Created On: 01/04/19 Updated On:	P	NW	SW	5	40N	30W	Dickerson	0-225-37-2019	1.0	2.1	2.1	5.3	24.7	2.651	2.675	0.909		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
LINDBERG AND SONS 26-99-001-PIT Created On: 01/02/24 Updated On:	P	NW	SW	5	40N	30W	Dickerson	0-225-13-2024	1.6	0.0	1.6	5.6	27.6	2.661	2.683	0.805	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
LINDEN 55-25-018-QRY Created On: 06/30/16 Updated On:	Q	SW	SW	14	5N	2E	Iowa	0-225-215-2016		0.8	0.5	10.7	39.8	2.676	2.720	1.661	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
LINDEN 55-25-018-QRY Created On: 01/07/19 Updated On:	Q	SW	SW	14	5N	2E	Iowa	0-225-54-2019	0.2	1.8	4.1	10.8	35.9	2.603	2.669	2.522	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
LINDEN 55-25-018-QRY Created On: 01/10/22 Updated On:	Q	SW	SW	14	5N	2E	Iowa	0-225-103-2022	0.4	3.0	4.2	11.0	37.1	2.602	2.670	2.617	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
LINS 55-56-019-QRY Created On: 09/21/15 Updated On:	Q	NW	NE	22	9N	3E	Sauk	0-225-238-2015	3.5	2.7	5.9	10.6	40.5	2.568	2.643	2.897	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
LINS 55-56-019-QRY Created On: 07/24/18 Updated On:	Q	NW	NE	22	9N	3E	Sauk	0-225-257-2018	2.7	3.8	6.5	9.9	38.5	2.587	2.656	2.656	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
LINS 55-56-019-QRY Created On: 04/07/21 Updated On:	Q	NW	NE	22	9N	3E	Sauk	0-225-173-2021	2.6	8.3	7.1	8.5	35.6	2.600	2.665	2.493	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
LINS 55-56-019-QRY Created On: 03/27/24 Updated On:	Q	NW	NE	22	9N	3E	Sauk	0-225-210-2024	1.3	5.8	5.6	8.1	30.0	2.601	2.660	2.259		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
LISSNER 55-60-014-PIT Created On: 01/09/15 Updated On:	P		SW	27	32N	1E	Taylor	0-225-46-2015		0.0	2.7	3.7	17.7	2.718	2.749	1.133		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
LISSNER 55-60-014-PIT Created On: 01/08/20 Updated On:	P		SW	27	32N	1E	Taylor	0-225-48-2020	1.0	0.0	2.6	4.2	18.8	2.760	2.781	0.771		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
LITTLE LIMESTONE 55-53-023-QRY Created On: 07/14/14 Updated On:	Q	SW	NE	6	1N	14E	Rock	0-225-220-2014	6.3	2.9	14.7	10.7	39.4	2.500	2.608	4.326		
	Approved Use : Base Aggregate																	
LITTLE LIMESTONE 55-53-023-QRY Created On: 03/29/17 Updated On:	Q	SW	NE	6	1N	14E	Rock	0-225-92-2017	2.2	3.4	14.9	10.8	39.0	2.547	2.634	3.414		
	Approved Use : Base Aggregate																	
LITTLE LIMESTONE 55-53-023-QRY Created On: 03/19/20 Updated On:	Q	SW	NE	6	1N	14E	Rock	0-225-132-2020	3.1	10.1	16.8	10.4	39.8	2.536	2.624	3.457		
	Approved Use : Base Aggregate																	
LITTLE LIMESTONE 55-53-023-QRY Created On: 01/03/23 Updated On:	Q	SW	NE	6	1N	14E	Rock	0-225-2-2023	3.1	13.3	18.0	99.7	46.6	2.484	2.585	4.090		
	Approved Use : Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
LITTLE LIMESTONE 55-53-023-QRY Created On: 04/05/23 Updated On:	Q	SW	NE	6	1N	14E	Rock	0-225-190-2023	4.0	9.2	8.8	10.5	39.3	2.640	2.702	2.352		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
* LOEFFELHOLZ 55-22-037-QRY Created On: 05/09/16 Updated On:	Q	SE	SE	5	2N	1W	Grant	0-225-168-2016	1.3	6.9	9.1	12.5	43.7	2.560	2.639	3.061		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
* LOEFFELHOLZ 55-22-037-QRY Created On: 06/13/19 Updated On:	Q	SE	SE	5	2N	1W	Grant	0-225-213-2019	1.7	6.1	11.6	15.0	46.0	2.536	2.630	3.696		
	Approved Use : CONCRETE, Base Aggregate																	
LONGBRANCH 55-10-015-QRY Created On: 01/29/15 Updated On:	Q	N	SW	34	29N	4W	Clark	0-225-75-2015		0.0	0.9	3.2	14.3	2.720	2.740	0.731		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
LONGBRANCH 55-10-015-QRY Created On: 03/08/18 Updated On:	Q	N	SW	34	29N	4W	Clark	0-225-112-2018		0.0	0.5	2.6	13.4	2.751	2.764	0.489		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
LONGBRANCH 55-10-015-QRY Created On: 01/05/21 Updated On:	Q	N	SW	34	29N	4W	Clark	0-225-89-2021	0.3	0.0	0.8	3.4	16.0	2.742	2.755	0.472		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
LONGBRANCH 55-10-015-QRY Created On: 01/02/24 Updated On:	Q	N	SW	34	29N	4W	Clark	0-225-86-2024	0.1	0.0	1.1	3.3	16.2	2.756	2.769	0.465		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
LUND / RIOPEL 55-43-013-PIT Created On: 01/04/18 Updated On:	P	SW	SW	6	36N	8E	Oneida	0-225-59-2018		0.0	1.5	4.2	20.2	2.674	2.702	1.027		
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																	
LUND / RIOPEL 55-43-013-PIT Created On: 01/03/23 Updated On:	P	SW	SW	6	36N	8E	Oneida	0-225-15-2023		0.0	0.6	3.3	17.6	2.696	2.721	0.933		
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																	
LUPPINO KIMBALL 55-26-030-QRY Created On: 06/13/18 Updated On:	Q		NW	4	46N	2E	Iron	0-225-230-2018		0.0	9.2	5.0	27.1	2.826	2.890	2.262		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
LUPPINO KIMBALL 55-26-030-QRY Created On: 04/01/21 Updated On:	Q		NW	4	46N	2E	Iron	0-225-165-2021		0.0	1.7	2.9	12.4	2.796	2.832	1.285		
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																	
LUPPINO KIMBALL 55-26-030-QRY Created On: 01/02/24 Updated On:	Q		NW	4	46N	2E	Iron	0-225-62-2024	0.1	0.0	9.4	3.5	15.9	2.608	2.671	2.430		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
LUPPINO MERCER 55-26-029-PIT Created On: 01/05/17 Updated On:	P	NW	NE	1	42N	3E	Iron	0-225-37-2017		0.0	2.8	3.9	18.8	2.710	2.740	1.085		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
LUPPINO MERCER 55-26-029-PIT Created On: 04/04/23 Updated On:	P	NW	NE	1	42N	3E	Iron	0-225-182-2023		0.0	2.7	4.3	18.7	2.721	2.753	1.167		
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
LUTZKE 55-36-022-PIT Created On: 04/17/14 Updated On:	P	SE	SE	20	18N	22E	Manitowoc	0-225-132-2014	0.6	0.0	1.1	5.9	28.8	2.769	2.791	0.794		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
LUTZKE 55-36-022-PIT Created On: 10/05/18 Updated On:	P	SE	SE	20	18N	22E	Manitowoc	0-225-288-2018	1.2	0.0	1.0	6.7	31.6	2.766	2.789	0.835		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
LUTZKE 55-36-022-PIT Created On: 04/28/22 Updated On:	P	SE	SE	20	18N	22E	Manitowoc	0-225-189-2022	1.5	0.0	0.4	6.9	32.4	2.769	2.792	0.819		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MACKVILLE 55-44-019-QRY Created On: 09/11/14 Updated On:	Q	SW	NE	33	22N	17E	Outagamie	0-225-261-2014	0.1	0.8	0.2	4.0	18.9	2.755	2.782	0.997		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
MACKVILLE 55-44-019-QRY Created On: 03/30/15 Updated On:	Q	SW	NE	33	22N	17E	Outagamie	0-225-105-2015	0.1	0.5	2.4	4.3	18.8	2.767	2.789	0.789		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
MACKVILLE 55-44-019-QRY Created On: 02/16/16 Updated On:	Q	SW	NE	33	22N	17E	Outagamie	0-225-84-2016	0.4	2.7	0.8	4.7	21.5	2.751	2.777	0.940		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
MACKVILLE 55-44-019-QRY Created On: 02/03/17 Updated On:	Q	SW	NE	33	22N	17E	Outagamie	0-225-58-2017	0.2	3.7	1.5	6.1	24.5	2.724	2.759	1.284		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
MACKVILLE 55-44-019-QRY Created On: 03/16/18 Updated On:	Q	SW	NE	33	22N	17E	Outagamie	0-225-123-2018	0.5	3.0	1.0	4.2	19.6	2.765	2.788	0.856		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
MACKVILLE 55-44-019-QRY Created On: 04/24/19 Updated On:	Q	SW	NE	33	22N	17E	Outagamie	0-225-168-2019	0.6	2.5	0.4	5.2	21.5	2.771	2.795	0.870		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MACKVILLE 55-44-019-QRY Created On: 06/24/20 Updated On:	Q	SW	NE	33	22N	17E	Outagamie	0-225-205-2020	0.2	8.5	1.7	4.4	22.2	2.773	2.795	0.800		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MACKVILLE 55-44-019-QRY Created On: 01/17/23 Updated On:	Q	SW	NE	33	22N	17E	Outagamie	0-225-122-2023	0.1	4.7	1.2	4.6	20.4	2.762	2.788	0.923		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MACKVILLE 55-44-019-QRY Created On: 01/02/24 Updated On:	Q	SW	NE	33	22N	17E	Outagamie	0-225-105-2024	0.3	6.4	1.0	5.0	21.7	2.764	2.788	0.882		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MAHR 55-09-041-PIT Created On: 01/12/15 Updated On:	P	SW	SW	26	29N	5W	Chippewa	0-225-56-2015		0.0	3.2	3.8	18.3	2.733	2.758	0.923		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
MAHR 55-09-041-PIT Created On: 01/09/20 Updated On:	P	SW	SW	26	29N	5W	Chippewa	0-225-87-2020	1.0	0.0	4.8	5.0	21.7	2.704	2.736	1.183		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
MAHR 55-09-041-PIT Created On: 01/09/20 Updated On:	P	SW	SW	26	29N	5W	Chippewa	0-225-89-2020	1.7	0.0	3.0	3.9	18.6	2.684	2.719	1.297	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
MAIER 55-13-124-QRY Created On: 01/05/21 Updated On:	Q		NW	21	9N	9E	Dane	0-225-99-2021	3.4	4.0	10.0	10.2	37.4	2.553	2.623	2.714	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
MAIER 55-13-124-QRY Created On: 02/28/24 Updated On:	Q		NW	21	9N	9E	Dane	0-225-190-2024	2.5	4.5	4.3	7.5	32.2	2.602	2.665	2.428	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
MAIN PIT 55-60-016-PIT Created On: 01/10/23 Updated On:	P	NE	SE	14	33N	4W	Taylor	0-225-114-2023	0.4	0.0	1.9	4.2	20.3	2.727	2.751	0.902	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
MANITOWOC CO. STH 310 55-36-023-QRY Created On: 01/12/16 Updated On:	Q	E	SW	36	20N	23E	Manitowoc	0-225-49-2016		0.0	0.7	6.8	30.0	2.779	2.799	0.741	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
MANITOWOC CO. STH 310 55-36-023-QRY Created On: 01/04/19 Updated On:	Q	E	SW	36	20N	23E	Manitowoc	0-225-16-2019		1.3	9.6	8.1	34.3	2.764	2.790	0.950	
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																
MANITOWOC CO. STH 310 55-36-023-QRY Created On: 01/10/22 Updated On:	Q	E	SW	36	20N	23E	Manitowoc	0-225-98-2022	0.2	2.8	2.8	10.0	37.7	2.738	2.766	1.014	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Coarse Sp. Gravity		Coarse Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
MANTHEY EAST 55-01-004-PIT Created On: 04/07/16 Updated On:	P		26	17N	7E	Adams		0-225-133-2016		0.0	1.9	8.8	32.4	2.697	2.737	1.494		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
MANTHEY EAST 55-01-004-PIT Created On: 01/04/21 Updated On:	P		26	17N	7E	Adams		0-225-23-2021	4.5	2.6	4.3	8.4	34.5	2.702	2.741	1.411		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MAPLE RIDGE #2 55-71-020-QRY Created On: 05/11/17 Updated On:	Q	NW	NW	17	22N	3E	Wood	0-225-182-2017		0.0	1.3	6.8	25.7	2.707	2.728	0.774		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
MAPLE RIDGE #2 55-71-020-QRY Created On: 01/07/20 Updated On:	Q	NW	NW	17	22N	3E	Wood	0-225-44-2020	0.4	0.0	0.5	4.0	17.2	2.734	2.744	0.353		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MAPLE RIDGE #2 55-71-020-QRY Created On: 05/22/23 Updated On:	Q	NW	NW	17	22N	3E	Wood	0-225-225-2023	0.4	0.0	1.0	4.0	17.5	2.759	2.772	0.473		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MARHAR - MICHIGAN 26-00-003-PIT Created On: 01/04/22 Updated On:	P	S	NW	34	45N	35E	Gogebic	0-225-28-2022	0.0	1.4	1.4	3.0	14.2	2.769	2.783	0.519		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MARION AGGREGATES 55-68-022-PIT Created On: 06/30/17 Updated On:	P	SW	NW	5	25N	13E	Waupaca	0-225-223-2017		0.0	0.3	4.8	24.9	2.701	2.722	0.801		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
MARION AGGREGATES 55-68-022-PIT Created On: 01/04/22 Updated On:	P	SW	NW	5	25N	13E	Waupaca	0-225-71-2022	0.0	0.9	0.6	5.0	23.6	2.700	2.724	0.904	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
MARKESAN 55-24-007-QRY Created On: 01/16/15 Updated On:	Q		NE	3	14N	13E	Green Lake	0-225-70-2015	0.1	0.9	7.9	6.3	28.2	2.693	2.741	1.785	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
MARKESAN 55-24-007-QRY Created On: 04/11/18 Updated On:	Q		NE	3	14N	13E	Green Lake	0-225-166-2018	0.3	15.1	10.2	7.5	31.5	2.671	2.722	1.926	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
MARKESAN 55-24-007-QRY Created On: 01/10/19 Updated On:	Q		NE	3	14N	13E	Green Lake	0-225-83-2019		12.5	8.9	7.6	31.8	2.681	2.733	1.931	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
MARKESAN 55-24-007-QRY Created On: 03/07/22 Updated On:	Q		NE	3	14N	13E	Green Lake	0-225-139-2022	0.0	10.9	6.7	6.2	28.0	2.703	2.744	1.507	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
MARSHFIELD 55-71-021-QRY Created On: 01/06/14 Updated On:	Q	SE	NW	2	25N	3E	Wood	0-225-19-2014		0.0	1.9	6.7	25.6	2.676	2.696	0.733	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
MARSHFIELD 55-71-021-QRY Created On: 01/03/17 Updated On:	Q	SE	NW	2	25N	3E	Wood	0-225-1-2017		0.0	0.3	5.1	23.8	2.676	2.690	0.520	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
MARSHFIELD 55-71-021-QRY Created On: 01/03/20 Updated On:	Q	SE	NW	2	25N	3E	Wood	0-225-12-2020	0.0	0.0	0.3	5.0	22.6	2.719	2.731	0.460		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MARSHFIELD 55-71-021-QRY Created On: 01/03/23 Updated On:	Q	SE	NW	2	25N	3E	Wood	0-225-36-2023	0.0	1.2	3.0	5.5	24.2	2.763	2.783	0.708		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MARSOLEK 55-06-014-QRY Created On: 01/17/14 Updated On:	Q	NW	SE	36	23N	10W	Buffalo	0-225-51-2014		0.0	12.3	10.4	39.6	2.574	2.645	2.766		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
MARSOLEK 55-06-014-QRY Created On: 04/25/14 Updated On:	Q	NW	SE	36	23N	10W	Buffalo	0-225-151-2014		0.0	8.3	10.4	39.6	2.574	2.645	2.766		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
MARSOLEK 55-06-014-QRY Created On: 06/30/16 Updated On:	Q	NW	SE	36	23N	10W	Buffalo	0-225-213-2016		0.0	3.5	8.1	33.4	2.572	2.641	2.694		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
MARSOLEK 55-06-014-QRY Created On: 01/04/19 Updated On:	Q	NW	SE	36	23N	10W	Buffalo	0-225-29-2019	0.9	0.0	7.6	11.5	40.5	2.541	2.623	3.258		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
MARSOLEK 55-06-014-QRY Created On: 01/04/22 Updated On:	Q	NW	SE	36	23N	10W	Buffalo	0-225-76-2022	4.6	0.0	11.6	12.2	44.5	2.540	2.623	3.280		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
MARTIN ROAD 55-37-091-QRY Created On: 06/26/19 Updated On:	Q	SE	SE	6	27N	9E	Marathon	0-225-232-2019	1.3	0.0	1.3	9.6	38.3	2.591	2.609	0.713		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
MARTIN ROAD 55-37-091-QRY Created On: 02/17/22 Updated On:	Q	SE	SE	6	27N	9E	Marathon	0-225-132-2022	0.0	0.0	0.5	6.8	33.7	2.610	2.623	0.500		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MASHUDA UPPER 55-24-008-QRY Created On: 03/20/14 Updated On:	Q	NE	NW	28	16N	12E	Green Lake	0-225-100-2014	0.0	0.3	1.1	6.3	30.2	2.689	2.728	1.472		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
MASHUDA UPPER 55-24-008-QRY Created On: 03/31/17 Updated On:	Q	NE	NW	28	16N	12E	Green Lake	0-225-95-2017	0.4	1.7	2.6	10.7	38.6	2.640	2.701	2.315		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
MASHUDA UPPER 55-24-008-QRY Created On: 05/07/20 Updated On:	Q	NE	NW	28	16N	12E	Green Lake	0-225-172-2020	0.6	1.8	2.2	8.5	37.7					
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MASHUDA UPPER 55-24-008-QRY Created On: 04/04/23 Updated On:	Q	NE	NW	28	16N	12E	Green Lake	0-225-176-2023	0.5	1.6	1.8	10.9	37.5	2.665	2.718	1.975		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MATHEY 55-15-014-QRY Created On: 07/08/15 Updated On:	Q	E	SE	22	28N	26E	Door	0-225-208-2015	0.1	0.0	0.6	5.7	25.8	2.793	2.811	0.616		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
MATHEY 55-15-014-QRY Created On: 01/04/18 Updated On:	Q	E	SE	22	28N	26E	Door	0-225-84-2018	1.0	3.3	1.7	8.0	30.8	2.748	2.780	1.144		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MATHEY 55-15-014-QRY Created On: 01/05/21 Updated On:	Q	E	SE	22	28N	26E	Door	0-225-107-2021	0.0	1.5	0.7	5.7	24.7	2.778	2.802	0.831		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MATHEY 55-15-014-QRY Created On: 01/02/24 Updated On:	Q	E	SE	22	28N	26E	Door	0-225-48-2024	0.1	0.0	0.6	0.9	29.5	2.778	2.797	0.705		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
* MATOUSHEK 55-56-021-QRY Created On: 07/14/14 Updated On:	Q			28	10N	6E	Sauk	0-225-221-2014		0.0	3.5	9.4	35.7	2.628	2.684	2.136		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
* MATOUSHEK 55-56-021-QRY Created On: 05/11/17 Updated On:	Q			28	10N	6E	Sauk	0-225-185-2017		0.0	4.1	10.7	37.6	2.598	2.661	2.459		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
* MATOUSHEK 55-56-021-QRY Created On: 01/06/20 Updated On:	Q			28	10N	6E	Sauk	0-225-25-2020	0.9	0.0	0.2	8.5	33.6	2.619	2.677	2.204		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MATTHIAE 55-37-047-PIT Created On: 03/13/23 Updated On:	P	SE	SE	35	29N	5E	Marathon	0-225-167-2023	0.3	0.0	1.8	3.3	15.5	2.764	2.786	0.796		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Coarse Sp. Gravity		Coarse Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
MAYER 55-60-017-PIT Created On: 06/26/17 Updated On:	P	SE	SW	2	32N	1E	Taylor	0-225-218-2017		0.0	2.5	4.9	21.9	2.739	2.766	1.004	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
MAYER 55-60-017-PIT Created On: 01/10/23 Updated On:	P	SE	SW	2	32N	1E	Taylor	0-225-112-2023	0.2	0.0	4.0	5.2	23.7	2.762	2.792	1.080	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
MAYVILLE WHITELIME 55-14-023-QRY Created On: 05/02/14 Updated On:	Q			1	11N	16E	Dodge	0-225-159-2014		2.3	3.2	6.8	30.5	2.720	2.759	1.416	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
MAYVILLE WHITELIME 55-14-023-QRY Created On: 08/08/17 Updated On:	Q			1	11N	16E	Dodge	0-225-248-2017	2.3	1.5	0.2	6.6	29.0	2.704	2.748	1.628	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
MAYVILLE WHITELIME 55-14-023-QRY Created On: 08/24/20 Updated On:	Q			1	11N	16E	Dodge	0-225-235-2020	1.8	3.3	0.2	6.8	30.1	2.725	2.764	1.419	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
MAYVILLE WHITELIME 55-14-023-QRY Created On: 02/27/23 Updated On:	Q			1	11N	16E	Dodge	0-225-151-2023	2.1	7.5	5.1	6.0	29.7	2.712	2.754	1.530	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
MCC - LARSEN 55-70-010-QRY Created On: 05/26/16 Updated On:	Q	NE	NW	19	20N	16E	Winnebago	0-225-193-2016	2.8	1.4	1.2	5.3	24.4	2.737	2.761	0.873	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
MCC - LARSEN 55-70-010-QRY Created On: 03/16/18 Updated On:	Q	NE	NW	19	20N	16E	Winnebago	0-225-125-2018	0.3	3.3	1.4	5.6	24.2	2.729	2.756	1.003		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
MCC - LARSEN 55-70-010-QRY Created On: 01/05/21 Updated On:	Q	NE	NW	19	20N	16E	Winnebago	0-225-103-2021	0.2	10.0	11.3	6.8	28.9	2.708	2.750	1.553		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MCC - LARSEN 55-70-010-QRY Created On: 01/02/24 Updated On:	Q	NE	NW	19	20N	16E	Winnebago	0-225-7-2024	0.0	13.8	3.9	7.5	32.3	2.723	2.757	1.260		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MCC ROCK ROAD 55-44-031-QRY Created On: 01/05/21 Updated On:	Q	SE	SW	17	22N	17E	Outagamie	0-225-100-2021	0.2	0.8	3.2	6.7	30.2	2.716	2.756	1.469		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MCC ROCK ROAD 55-44-031-QRY Created On: 01/02/24 Updated On:	Q	SE	SW	17	22N	17E	Outagamie	0-225-6-2024	0.6	1.5	0.4	7.3	31.6	2.712	2.743	1.120		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MCC- FREEDOM WEST 55-44-020-QRY Created On: 05/02/16 Updated On:	Q	NE	SE	17	22N	18E	Outagamie	0-225-160-2016	0.4	12.0	0.2	5.6	23.7	2.768	2.790	0.823		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
MCC- FREEDOM WEST 55-44-020-QRY Created On: 04/19/19 Updated On:	Q	NE	SE	17	22N	18E	Outagamie	0-225-150-2019	0.3	3.8	2.5	4.8	21.6	2.768	2.793	0.907		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
MCC- FREEDOM WEST 55-44-020-QRY Created On: 06/24/20 Updated On:	Q	NE	SE	17	22N	18E	Outagamie	0-225-206-2020	0.6	7.9	2.2	5.2	21.5	2.769	2.792	0.841	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
MCC- FREEDOM WEST 55-44-020-QRY Created On: 01/05/21 Updated On:	Q	NE	SE	17	22N	18E	Outagamie	0-225-101-2021	0.1	2.2	2.4	5.2	22.4	2.762	2.787	0.909	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
MCC- FREEDOM WEST 55-44-020-QRY Created On: 01/02/24 Updated On:	Q	NE	SE	17	22N	18E	Outagamie	0-225-5-2024	0.0	5.9	1.7	5.0	22.2	2.763	2.789	0.919	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
MCCLAIN 55-03-027-PIT Created On: 05/08/15 Updated On:	P	SW	NE	9	35N	13W	Barron	0-225-159-2015		0.0	2.9	2.8	14.0	2.795	2.817	0.788	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
MCCLAIN 55-03-027-PIT Created On: 04/18/22 Updated On:	P	SW	NE	9	35N	13W	Barron	0-225-177-2022		0.0	2.4	3.4	14.9	2.785	2.811	0.911	
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																
MCKEEFRY 55-58-021-QRY Created On: 01/27/14 Updated On:	Q		NW	23	25N	18E	Shawano	0-225-60-2014		0.2	1.7	4.5	19.3	2.781	2.799	0.657	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
MCKEEFRY 55-58-021-QRY Created On: 03/30/15 Updated On:	Q		NW	23	25N	18E	Shawano	0-225-106-2015	0.9	2.2	2.2	4.9	21.5	2.776	2.796	0.723	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
MCKEEFRY 55-58-021-QRY Created On: 02/16/16 Updated On:	Q		NW	23	25N	18E	Shawano	0-225-85-2016	0.1	2.4	0.4	5.2	22.6	2.765	2.786	0.749		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
MCKEEFRY 55-58-021-QRY Created On: 05/24/19 Updated On:	Q		NW	23	25N	18E	Shawano	0-225-196-2019	0.7	9.6	3.1	5.7	25.1	2.746	2.773	1.014		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
MCKEEFRY 55-58-021-QRY Created On: 05/17/22 Updated On:	Q		NW	23	25N	18E	Shawano	0-225-207-2022	0.3	7.7	0.6	6.2	30.0	2.747	2.772	0.921		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MCKEEFRY #3 55-58-049-QRY Created On: 10/19/17 Updated On:	Q	N	SW	14	25N	18E	Shawano	0-225-282-2017	0.2	5.2	2.7	6.1	25.7	2.748	2.779	1.112		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MCKEEFRY #3 55-58-049-QRY Created On: 04/08/20 Updated On:	Q	N	SW	14	25N	18E	Shawano	0-225-145-2020	0.5	2.2	3.4	5.5	23.9	2.767	2.790	0.861		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MCKEEFRY #3 55-58-049-QRY Created On: 06/12/23 Updated On:	Q	N	SW	14	25N	18E	Shawano	0-225-228-2023	0.0	17.0	10.1	4.8	30.4	2.703	2.743	1.501		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MCKEEFRY - CHASE 55-42-023-PIT Created On: 08/16/16 Updated On:	P		NW	SE	3	26N	19E	Oconto	0-225-242-2016	0.8	1.3	0.4	6.5	29.0	2.743	2.769	0.970	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Coarse Sp. Gravity		Coarse Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
MCKEEFRY - CHASE 55-42-023-PIT Created On: 04/13/21 Updated On:	P	NW	SE	3	26N	19E	Oconto	0-225-179-2021	0.4	3.3	5.2	8.5	36.8	2.710	2.745	1.303		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MCNAMARA 55-55-007-QRY Created On: 04/21/17 Updated On:	Q	SE	NW	25	31N	15W	St. Croix	0-225-145-2017		0.0	5.2	10.4	38.0	2.558	2.633	2.956		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
MCNAMARA 55-55-007-QRY Created On: 01/06/20 Updated On:	Q	SE	NW	25	31N	15W	St. Croix	0-225-27-2020	1.8	0.0	7.5	10.2	34.7	2.533	2.620	3.440		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MCNAMARA 55-55-007-QRY Created On: 04/05/23 Updated On:	Q	SE	NW	25	31N	15W	St. Croix	0-225-187-2023	6.2	0.0	10.0	11.8	40.8	2.511	2.598	3.462		
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																	
* MEADOW LANE 55-37-089-PIT Created On: 01/04/19 Updated On:	P		NE	8	25N	10E	Marathon	0-225-36-2019	0.1	0.0	1.8	9.8	35.1	2.674	2.698	0.885		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
MEDINA 55-44-016-PIT Created On: 03/17/22 Updated On:	P		SW	19	21N	16E	Outagamie	0-225-146-2022	0.5	0.0	0.3	5.2	25.2	2.754	2.780	0.924		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MEINHOLZ 55-13-064-QRY Created On: 01/20/16 Updated On:	Q			35	8N	8E	Dane	0-225-62-2016	1.0	1.4	0.8	7.6	33.0	2.563	2.627	2.493		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
MEINHOLZ 55-13-064-QRY Created On: 04/01/19 Updated On:	Q			35	8N	8E	Dane	0-225-120-2019	0.8	1.5	2.8	9.3	35.2	2.565	2.636	2.748	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
MEINHOLZ 55-13-064-QRY Created On: 03/29/21 Updated On:	Q			35	8N	8E	Dane	0-225-160-2021	0.8	2.4	2.5	7.7	30.4	2.593	2.656	2.426	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
MEINHOLZ 55-13-064-QRY Created On: 01/04/22 Updated On:	Q			35	8N	8E	Dane	0-225-40-2022	1.3	4.5	5.1	9.4	31.3	2.578	2.643	2.515	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
MEINHOLZ 55-13-064-QRY Created On: 01/23/23 Updated On:	Q			35	8N	8E	Dane	0-225-132-2023	0.6	2.3	2.3	9.4	37.8	2.533	2.602	2.715	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
MEINHOLZ 55-13-064-QRY Created On: 01/02/24 Updated On:	Q			35	8N	8E	Dane	0-225-72-2024	0.8	1.7	1.3	7.2	30.4	2.540	2.619	3.106	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
MENN 55-41-013-QRY Created On: 03/07/16 Updated On:	Q	SW	NW	2	15N	2W	Monroe	0-225-92-2016	0.4	0.0	3.4	19.1	45.9	2.532	2.614	3.242	
	Approved Use : CONCRETE, Base Aggregate																
MENN 55-41-013-QRY Created On: 04/19/18 Updated On:	Q	SW	NW	2	15N	2W	Monroe	0-225-176-2018	0.3	0.0	1.7	10.1	37.5	2.598	2.659	2.360	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
MENN 55-41-013-QRY Created On: 03/12/20 Updated On:	Q	SW	NW	2	15N	2W	Monroe	0-225-127-2020	0.0	0.0	3.7	11.8	40.5	2.551	2.626	2.945		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MENN 55-41-013-QRY Created On: 04/10/23 Updated On:	Q	SW	NW	2	15N	2W	Monroe	0-225-192-2023	1.3	3.6	5.5	10.8	40.1	2.608	2.663	2.102		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MERRILLAN-734 55-10-018-QRY Created On: 07/02/15 Updated On:	Q	NW	SW	13	23N	3W	Clark	0-225-203-2015		0.0	0.5	2.5	15.8	2.635	2.646	0.435		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
MERRILLAN-734 55-10-018-QRY Created On: 01/03/18 Updated On:	Q	NW	SW	13	23N	3W	Clark	0-225-37-2018		0.0	0.4	3.7	20.1	2.622	2.634	0.432		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MERRILLAN-734 55-10-018-QRY Created On: 01/04/21 Updated On:	Q	NW	SW	13	23N	3W	Clark	0-225-19-2021	0.0	0.3	0.4	3.3	16.5	2.694	2.705	0.424		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MERRILLAN-734 55-10-018-QRY Created On: 01/02/24 Updated On:	Q	NW	SW	13	23N	3W	Clark	0-225-110-2024	1.0	3.2	2.2	3.9	19.8	2.658	2.692	1.268		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MERRILLAN-734 55-10-018-QRY Created On: 01/02/24 Updated On:	Q	NW	SW	13	23N	3W	Clark	0-225-111-2024	0.0	0.6	0.6	4.2	19.1	2.705	2.725	0.754		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
* MEVERDAN MATERIALS HWY T 55-34-026-PIT Created On: 07/18/19 Updated On:	P	SW	SW	2	33N	9E	Langlade	0-225-238-2019	0.7	0.0	1.3	5.2	21.1	2.666	2.693	1.031		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
* MEVERDEN MATERIALS 55-37-048-QRY Created On: 01/22/16 Updated On:	Q	NE	SW	19	28N	7E	Marathon	0-225-76-2016		0.0	0.5	8.1	36.7	2.594	2.622	1.074		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
* MEVERDEN MATERIALS 55-37-048-QRY Created On: 05/09/19 Updated On:	Q	NE	SW	19	28N	7E	Marathon	0-225-185-2019	0.0	0.0	0.6	9.4	40.9	2.616	2.635	0.702		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
MEYER 55-69-012-PIT Created On: 01/04/22 Updated On:	P	NW	NW	36	20N	9E	Waushara	0-225-39-2022	1.0	0.0	6.4	6.9	29.2	2.699	2.733	1.256		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MICHELS - MISHICOT 55-36-025-PIT Created On: 01/08/15 Updated On:	P	SE	SE	27	21N	23E	Manitowoc	0-225-27-2015	0.5	0.0	3.7	7.1	32.4	2.679	2.720	1.537		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
MICHELS - MISHICOT 55-36-025-PIT Created On: 01/05/21 Updated On:	P	SE	SE	27	21N	23E	Manitowoc	0-225-46-2021	0.8	0.0	3.6	6.0	29.8	2.698	2.741	1.612		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
* MICHELS - BRILLION 55-08-014-QRY Created On: 01/07/15 Updated On:	Q		SW	24	20N	20E	Calumet	0-225-22-2015	0.4	0.0	2.6	9.8	39.9	2.627	2.680	2.009		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
* MICHEL'S - BRILLION 55-08-014-QRY Created On: 03/16/18 Updated On:	Q		SW	24	20N	20E	Calumet	0-225-124-2018		0.0	2.0	9.0	35.7	2.687	2.727	1.498		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
* MICHEL'S - BRILLION 55-08-014-QRY Created On: 01/05/21 Updated On:	Q		SW	24	20N	20E	Calumet	0-225-48-2021	0.8	0.0	1.2	8.0	34.5	2.661	2.711	1.903		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MICHEL'S - TAYCHEEDAH 55-20-021-QRY Created On: 01/06/14 Updated On:	Q	SW	NE	16	16N	18E	Fond Du Lac	0-225-13-2014		0.3	1.9	8.4	37.6	2.718	2.750	1.170		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
MICHEL'S - TAYCHEEDAH 55-20-021-QRY Created On: 01/04/17 Updated On:	Q	SW	NE	16	16N	18E	Fond Du Lac	0-225-11-2017	1.3	0.6	1.4	7.6	33.4	2.749	2.777	1.027		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
MICHEL'S - TAYCHEEDAH 55-20-021-QRY Created On: 01/08/20 Updated On:	Q	SW	NE	16	16N	18E	Fond Du Lac	0-225-70-2020	0.2	0.9	1.4	9.2	38.3	2.740	2.770	1.088		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MICHEL'S - TAYCHEEDAH 55-20-021-QRY Created On: 01/03/23 Updated On:	Q	SW	NE	16	16N	18E	Fond Du Lac	0-225-43-2023	0.2	0.7	2.1	7.3	33.5	2.742	2.774	1.175		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MICHEL'S ALLEN 55-70-011-QRY Created On: 01/21/16 Updated On:	Q	NE	SW	9	18N	14E	Winnebago	0-225-68-2016	0.5	1.4	6.8	11.6	39.5	2.645	2.700	2.056		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
MICHELS ALLEN 55-70-011-QRY Created On: 01/07/19 Updated On:	Q	NE	SW	9	18N	14E	Winnebago	0-225-70-2019	0.0	1.7	2.3	7.2	32.0	2.753	2.785	1.180		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
MICHELS ALLEN 55-70-011-QRY Created On: 01/04/22 Updated On:	Q	NE	SW	9	18N	14E	Winnebago	0-225-18-2022	0.0	1.1	1.2	7.9	33.9	2.738	2.769	1.142		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MICHELS ALLEN 55-70-011-QRY Created On: 01/02/24 Updated On:	Q	NE	SW	9	18N	14E	Winnebago	0-225-104-2024	0.8	2.2	2.8	9.3	36.2	2.693	2.734	1.512		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MICHELS BECKER 55-66-016-PIT Created On: 01/08/15 Updated On:	P	SW	SW	27	11N	18E	Washington	0-225-32-2015	0.2	3.6	3.7	6.6	29.1	2.704	2.738	1.262		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
MICHELS BECKER 55-66-016-PIT Created On: 01/08/20 Updated On:	P	SW	SW	27	11N	18E	Washington	0-225-77-2020	2.2	10.5	2.7	6.1	28.8	2.678	2.718	1.499		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MICHELS BEECHWOOD 55-59-023-PIT Created On: 01/05/21 Updated On:	P	W	NE	4	13N	20E	Sheboygan	0-225-85-2021	0.6	0.0	3.7	9.5	35.9	2.715	2.753	1.391		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MICHELS BROWN 55-08-015-QRY Created On: 01/04/16 Updated On:	Q	S	SW	32	20N	19E	Calumet	0-225-7-2016	0.1	0.0	1.4	6.0	26.8	2.767	2.789	0.787		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
MICHELSON BROWN 55-08-015-QRY Created On: 01/04/19 Updated On:	Q	S	SW	32	20N	19E	Calumet	0-225-39-2019	0.7	0.0	3.6	8.1	32.6	2.743	2.774	1.131		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
MICHELSON BROWN 55-08-015-QRY Created On: 01/04/22 Updated On:	Q	S	SW	32	20N	19E	Calumet	0-225-32-2022	1.2	0.0	3.2	9.6	37.0	2.713	2.752	1.440		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MICHELSON CHASE 55-42-024-QRY Created On: 01/07/15 Updated On:	Q	NE	SW	17	26N	19E	Oconto	0-225-21-2015		2.0	2.4	4.8	22.1	2.733	2.759	0.924		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
MICHELSON CHASE 55-42-024-QRY Created On: 01/04/19 Updated On:	Q	NE	SW	17	26N	19E	Oconto	0-225-40-2019		5.7	3.2	5.9	25.8	2.738	2.764	0.975		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MICHELSON CHASE 55-42-024-QRY Created On: 04/11/22 Updated On:	Q	NE	SW	17	26N	19E	Oconto	0-225-174-2022	0.1	3.4	3.4	5.8	24.7	2.730	2.760	1.129		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MICHELSON COLUMBUS 55-11-028-QRY Created On: 04/11/14 Updated On:	Q			11	10N	12E	Columbia	0-225-125-2014		7.0	10.1	9.3	37.0	2.566	2.635	2.675		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
MICHELSON COLUMBUS 55-11-028-QRY Created On: 01/03/17 Updated On:	Q			11	10N	12E	Columbia	0-225-9-2017	1.9	7.8	7.5	9.8	38.7	2.584	2.647	2.440		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
MICHEL'S COLUMBUS 55-11-028-QRY Created On: 03/09/20 Updated On:	Q			11	10N	12E	Columbia	0-225-124-2020	2.9	15.0	7.8	10.1	41.5	2.598	2.664	2.568	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
MICHEL'S COLUMBUS 55-11-028-QRY Created On: 01/04/22 Updated On:	Q			11	10N	12E	Columbia	0-225-4-2022	2.7	6.5	9.5	10.0	40.5	2.542	2.616	2.925	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
MICHEL'S DEVENS 55-70-013-QRY Created On: 01/07/16 Updated On:	Q	NW	NW	21	19N	16E	Winnebago	0-225-40-2016		2.8	2.3	4.5	20.4	2.767	2.791	0.876	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
MICHEL'S DEVENS 55-70-013-QRY Created On: 01/07/20 Updated On:	Q	NW	NW	21	19N	16E	Winnebago	0-225-36-2020	0.2	9.9	2.0	6.1	26.0	2.736	2.772	1.323	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
MICHEL'S DEVENS 55-70-013-QRY Created On: 01/02/24 Updated On:	Q	NW	NW	21	19N	16E	Winnebago	0-225-47-2024	0.1	5.1	3.8	6.1	26.0	2.763	2.791	0.999	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
MICHEL'S DIETZ 55-70-014-QRY Created On: 01/06/14 Updated On:	Q			8	20N	17E	Winnebago	0-225-25-2014		7.5	3.3	6.5	29.7	2.734	2.765	1.119	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
MICHEL'S DIETZ 55-70-014-QRY Created On: 03/31/17 Updated On:	Q			8	20N	17E	Winnebago	0-225-96-2017	0.1	3.8	5.4	6.9	30.5	2.741	2.770	1.060	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
MICHELS DIETZ 55-70-014-QRY Created On: 01/07/20 Updated On:	Q		8	20N	17E	Winnebago		0-225-39-2020	0.1	12.5	2.1	5.5	26.0	2.742	2.777	1.297	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
MICHELS DIETZ 55-70-014-QRY Created On: 01/03/23 Updated On:	Q		8	20N	17E	Winnebago		0-225-79-2023	0.1	13.6	10.6	6.6	28.8	2.717	2.760	1.576	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
MICHELS GARVEY 55-44-021-QRY Created On: 01/07/16 Updated On:	Q	SE	SE	17	22N	17E	Outagamie	0-225-36-2016		0.6	1.9	7.0	31.4	2.682	2.720	1.428	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
MICHELS GARVEY 55-44-021-QRY Created On: 01/07/19 Updated On:	Q	SE	SE	17	22N	17E	Outagamie	0-225-42-2019	0.2	3.9	5.1	6.9	31.6	2.741	2.769	1.022	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
MICHELS GARVEY 55-44-021-QRY Created On: 01/04/22 Updated On:	Q	SE	SE	17	22N	17E	Outagamie	0-225-34-2022	0.2	0.8	1.7	5.8	27.9	2.720	2.753	1.221	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
MICHELS GARVEY 55-44-021-QRY Created On: 01/02/24 Updated On:	Q	SE	SE	17	22N	17E	Outagamie	0-225-106-2024	1.2	3.9	4.1	7.8	32.4	2.688	2.728	1.509	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
MICHELS GRUNSKA 55-70-016-QRY Created On: 05/10/18 Updated On:	Q	SE	SE	8	20N	16E	Winnebago	0-225-201-2018	1.4	10.5	3.9	6.9	30.0	2.695	2.730	1.298	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
MICHELS GRUNSKA 55-70-016-QRY Created On: 01/05/21 Updated On:	Q	SE	SE	8	20N	16E	Winnebago	0-225-50-2021	1.5	5.7	4.8	7.0	30.6	2.705	2.743	1.392	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
MICHELS GRUNSKA 55-70-016-QRY Created On: 01/02/24 Updated On:	Q	SE	SE	8	20N	16E	Winnebago	0-225-46-2024	1.3	7.9	5.8	6.8	28.5	2.705	2.740	1.265	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
* MICHELS HAMILTON HILL 55-20-024-QRY Created On: 07/07/21 Updated On:	Q		NW	10	14N	17E	Fond Du Lac	0-225-243-2021	1.6	7.4	7.9	12.7	41.3	2.697	2.742	1.665	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
MICHELS KETTER 55-20-025-PIT Created On: 11/06/14 Updated On:	P		SW	4	13N	19E	Fond Du Lac	0-225-269-2014	1.1	0.0	4.1	7.9	32.8	2.725	2.757	1.176	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
MICHELS KETTER 55-20-025-PIT Created On: 03/19/15 Updated On:	P		SW	4	13N	19E	Fond Du Lac	0-225-100-2015	1.1	0.0	4.1	7.9	32.8	2.725	2.758	1.180	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
MICHELS KETTER 55-20-025-PIT Created On: 01/08/20 Updated On:	P		SW	4	13N	19E	Fond Du Lac	0-225-74-2020	2.0	8.5	4.0	8.5	34.3	2.715	2.755	1.466	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
MICHELS KOCH 55-70-017-QRY Created On: 01/04/22 Updated On:	Q	NW	NE	29	20N	17E	Winnebago	0-225-20-2022	0.2	1.7	2.0	5.2	23.9	2.758	2.787	1.050	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
MICHELS KOCH 55-70-017-QRY Created On: 01/04/24 Updated On:	Q	NW	NE	29	20N	17E	Winnebago	0-225-147-2024	0.0	2.9	2.4	5.4	25.6	2.759	2.788	1.039	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
MICHELS MANCHESTER 55-24-010-PIT Created On: 07/08/15 Updated On:	P	SW	SE	16	14N	12E	Green Lake	0-225-207-2015	7.7	0.0	7.3	7.3	33.6	2.573	2.632	2.258	
	Approved Use : HMA<E-3, HMA>=E-3, Base Aggregate																
MICHELS MANCHESTER 55-24-010-PIT Created On: 01/07/20 Updated On:	P	SW	SE	16	14N	12E	Green Lake	0-225-40-2020	1.7	14.5	9.5	6.5	32.3	2.570	2.630	2.356	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
MICHELS MARBLEHEAD 55-20-026-QRY Created On: 01/04/16 Updated On:	Q	NE	NE	7	14N	18E	Fond Du Lac	0-225-13-2016		2.3	1.1	8.4	34.6	2.760	2.782	0.806	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
MICHELS MARBLEHEAD 55-20-026-QRY Created On: 01/04/19 Updated On:	Q	NE	NE	7	14N	18E	Fond Du Lac	0-225-19-2019		5.0	2.7	9.3	36.0	2.739	2.766	0.981	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
MICHELS MARBLEHEAD 55-20-026-QRY Created On: 01/04/22 Updated On:	Q	NE	NE	7	14N	18E	Fond Du Lac	0-225-23-2022	0.0	2.6	1.6	8.8	35.3	2.739	2.770	1.140	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
MICHELS MARKESAN 55-24-011-QRY Created On: 01/04/16 Updated On:	Q	SW	SW	9	14N	13E	Green Lake	0-225-14-2016		13.7	6.0	6.1	27.0	2.678	2.724	1.714	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
MICHELS MARKESAN 55-24-011-QRY Created On: 01/03/23 Updated On:	Q	SW	SW	9	14N	13E	Green Lake	0-225-41-2023	0.0	14.9	9.3	6.6	29.0	2.673	2.724	1.902	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
MICHELS NASBRO 55-14-025-QRY Created On: 01/04/16 Updated On:	Q	W	SE	18	13N	17E	Dodge	0-225-1-2016		0.4	1.3	7.5	32.2	2.714	2.746	1.179	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
MICHELS NASBRO 55-14-025-QRY Created On: 01/04/19 Updated On:	Q	W	SE	18	13N	17E	Dodge	0-225-1-2019	0.1	0.9	1.4	9.1	35.7	2.710	2.744	1.269	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
MICHELS NASBRO 55-14-025-QRY Created On: 01/04/22 Updated On:	Q	W	SE	18	13N	17E	Dodge	0-225-2-2022	0.0	0.5	1.0	7.2	30.8	2.731	2.763	1.155	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
MICHELS OSHKOSH 55-70-018-QRY Created On: 01/04/16 Updated On:	Q		NE	27	18N	16E	Winnebago	0-225-11-2016		3.1	2.8	5.0	22.1	2.755	2.782	0.992	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
MICHELS OSHKOSH 55-70-018-QRY Created On: 01/04/19 Updated On:	Q		NE	27	18N	16E	Winnebago	0-225-6-2019		8.9	2.1	4.1	19.8	2.766	2.792	0.929	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
MICHELS OSHKOSH 55-70-018-QRY Created On: 01/04/22 Updated On:	Q		NE	27	18N	16E	Winnebago	0-225-22-2022	0.1	7.3	5.0	4.9	22.8	2.730	2.766	1.321	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
MICHELS OSHKOSH 55-70-018-QRY Created On: 01/02/24 Updated On:	Q		NE	27	18N	16E	Winnebago	0-225-103-2024	0.0	6.3	2.3	4.8	22.8	2.753	2.781	1.035	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
MICHELS-HUGHES 55-70-019-QRY Created On: 01/06/14 Updated On:	Q	SW	NW	32	17N	16E	Winnebago	0-225-26-2014		11.3	9.7	6.7	28.5	2.734	2.768	1.253	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
MICHELS-HUGHES 55-70-019-QRY Created On: 01/05/17 Updated On:	Q	SW	NW	32	17N	16E	Winnebago	0-225-13-2017	0.3	11.7	9.9	6.6	28.9	2.731	2.765	1.269	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
MICHELS-HUGHES 55-70-019-QRY Created On: 01/04/19 Updated On:	Q	SW	NW	32	17N	16E	Winnebago	0-225-7-2019	0.5	22.5	8.7	7.3	30.2	2.708	2.752	1.629	
MICHELS-HUGHES 55-70-019-QRY Created On: 05/09/19 Updated On:	Q	SW	NW	32	17N	16E	Winnebago	0-225-181-2019	0.5	10.8	10.4	6.9	30.8	2.735	2.770	1.282	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
MICHELS-HUGHES 55-70-019-QRY Created On: 01/04/22 Updated On:	Q	SW	NW	32	17N	16E	Winnebago	0-225-31-2022	0.3	9.9	9.2	6.9	30.2	2.720	2.756	1.340	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
MICHELS-RIB 55-37-093-QRY Created On: 01/04/22 Updated On:	Q	SW	SE	9	30N	7E	Marathon	0-225-16-2022	0.0	0.0	0.8	7.7	32.4	2.579	2.597	0.687	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
MICHELS-WATERLOO 55-14-028-QRY Created On: 01/04/16 Updated On:	Q	NW	NW	34	9N	13E	Dodge	0-225-2-2016		0.4	0.5	4.1	21.8	2.655	2.667	0.461		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
MICHELS-WATERLOO 55-14-028-QRY Created On: 01/04/19 Updated On:	Q	NW	NW	34	9N	13E	Dodge	0-225-2-2019		0.8	0.3	4.1	22.0	2.651	2.667	0.604		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MICHELS-WATERLOO 55-14-028-QRY Created On: 01/04/22 Updated On:	Q	NW	NW	34	9N	13E	Dodge	0-225-1-2022	0.0	0.1	0.2	5.2	26.1	2.662	2.673	0.397		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MICHELS-WAUPUN 55-20-031-QRY Created On: 01/04/16 Updated On:	Q	S	NW	36	14N	14E	Fond Du Lac	0-225-8-2016		4.5	4.2	6.5	27.5	2.778	2.801	0.828		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
MICHELS-WAUPUN 55-20-031-QRY Created On: 01/08/19 Updated On:	Q	S	NW	36	14N	14E	Fond Du Lac	0-225-71-2019	0.0	9.5	6.0	6.7	30.9	2.798	2.822	0.865		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MICHELS-WAUPUN 55-20-031-QRY Created On: 01/04/22 Updated On:	Q	S	NW	36	14N	14E	Fond Du Lac	0-225-19-2022	0.0	5.6	2.8	6.0	28.6	2.764	2.791	0.973		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MICHELS/BERRES 55-20-004-PIT Created On: 09/11/14 Updated On:	P	SW	SE	32	14N	19E	Fond Du Lac	0-225-259-2014	1.4	0.0	2.8	7.0	28.7	2.721	2.754	1.231		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
MICHELS/BERRES 55-20-004-PIT Created On: 01/04/19 Updated On:	P	SW	SE	32	14N	19E	Fond Du Lac	0-225-17-2019	0.8	0.0	2.2	8.9	34.6	2.728	2.764	1.316	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
MICHELS/BERRES 55-20-004-PIT Created On: 01/02/24 Updated On:	P	SW	SE	32	14N	19E	Fond Du Lac	0-225-52-2024	1.0	0.0	2.9	8.6	34.2	2.735	2.764	1.025	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
MIKKOLA QUARRY 55-16-014-QRY Created On: 08/15/17 Updated On:	Q	NE	NE	35	48N	11W	Douglas	0-225-254-2017		0.0	0.9	3.1	13.9	2.620	2.643	0.891	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
MIKKOLA QUARRY 55-16-014-QRY Created On: 01/06/20 Updated On:	Q	NE	NE	35	48N	11W	Douglas	0-225-30-2020	0.1	0.0	4.9	3.1	13.9	2.582	2.615	1.247	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
MIKKOLA QUARRY 55-16-014-QRY Created On: 01/04/23 Updated On:	Q	NE	NE	35	48N	11W	Douglas	0-225-89-2023	0.6	2.4	2.9	3.4	15.0	2.645	2.682	1.392	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
MILAS 55-10-020-PIT Created On: 03/08/18 Updated On:	P	SE	NW	3	29N	3W	Clark	0-225-116-2018	1.4	0.0	2.5	4.3	19.4	2.686	2.713	1.011	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
MILAS 55-10-020-PIT Created On: 01/04/23 Updated On:	P	SE	NW	3	29N	3W	Clark	0-225-98-2023	1.2	0.0	2.8	3.6	18.0	2.733	2.759	0.969	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
MILE ROAD 55-13-007-QRY Created On: 03/07/16 Updated On:	Q	NE	NE	13	9N	10E	Dane	0-225-97-2016	1.1	2.6	8.9	6.5	29.4	2.640	2.693	2.030		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
MILE ROAD 55-13-007-QRY Created On: 01/04/19 Updated On:	Q	NE	NE	13	9N	10E	Dane	0-225-9-2019	1.7	7.0	7.4	10.1	28.7	2.536	2.616	3.134		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
MILE ROAD 55-13-007-QRY Created On: 01/02/24 Updated On:	Q	NE	NE	13	9N	10E	Dane	0-225-42-2024	0.7	14.1	12.6	9.8	43.1	2.545	2.623	3.066		
	Approved Use : Base Aggregate																	
MILESTONE #43 27-00-024-QRY Created On: 01/07/19 Updated On:	Q			16	106N	7W	Winona	0-225-49-2019	0.6	2.0	2.5	8.7	34.9	2.619	2.676	2.192		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
MILESTONE #43 27-00-024-QRY Created On: 01/03/23 Updated On:	Q			16	106N	7W	Winona	0-225-72-2023	0.8	1.1	3.8	10.1	39.4	2.614	2.672	2.223		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MILESTONE RIEKEMANN PIT #222 55-18-011-PIT Created On: 01/03/18 Updated On:	P	SE	SW	4	26N	10W	Eau Claire	0-225-41-2018	1.7	0.0	2.0	3.8	19.4	2.641	2.670	1.078		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
MILESTONE RIEKEMANN PIT #222 55-18-011-PIT Created On: 01/03/23 Updated On:	P	SE	SW	4	26N	10W	Eau Claire	0-225-52-2023	0.7	4.4	3.1	4.2	20.9	2.632	2.665	1.261		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
MILESTONE SOMERS 55-49-015-PIT Created On: 01/07/15 Updated On:	P	NE	NE	29	23N	9E	Portage	0-225-18-2015		0.0	2.5	6.9	28.8	2.685	2.718	1.206		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
MILESTONE SOMERS 55-49-015-PIT Created On: 01/07/20 Updated On:	P	NE	NE	29	23N	9E	Portage	0-225-43-2020	2.6	0.0	3.9	9.4	33.4	2.663	2.698	1.321		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MILESTONE-ANDERSON EE 55-32-001-QRY Created On: 07/15/20 Updated On:	Q	SE	NW	33	18N	5W	La Crosse	0-225-216-2020	0.8	0.0	2.6	8.9	38.5	2.606	2.666	2.278		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MILESTONE-ANDERSON EE 55-32-001-QRY Created On: 01/04/23 Updated On:	Q	SE	NW	33	18N	5W	La Crosse	0-225-85-2023	0.2	1.0	0.9	8.1	35.4	2.628	2.678	1.910		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MILESTONE-ANSEL JOHNSON 55-48-013-PIT Created On: 01/05/16 Updated On:	P	NW	SW	35	34N	16W	Polk	0-225-22-2016		0.0	1.6	2.9	14.7	2.744	2.773	1.035		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
MILESTONE-ANSEL JOHNSON 55-48-013-PIT Created On: 01/04/21 Updated On:	P	NW	SW	35	34N	16W	Polk	0-225-37-2021	0.7	1.2	2.3	2.7	14.1	2.747	2.779	1.159		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MILESTONE-ARNOLD ANDERSON 55-22-002-QRY Created On: 04/07/16 Updated On:	Q	SW	SE	34	3N	1W	Grant	0-225-131-2016	1.5	6.1	7.6	12.8	44.0	2.549	2.631	3.202		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
MILESTONE-ARNOLD ANDERSON 55-22-002-QRY Created On: 01/04/19 Updated On:	Q	SW	SE	34	3N	1W	Grant	0-225-25-2019	3.4	9.9	9.4	15.0	48.1	2.537	2.618	3.195	
	Approved Use : CONCRETE, Base Aggregate																
MILESTONE-ARNOLD ANDERSON 55-22-002-QRY Created On: 05/01/23 Updated On:	Q	SW	SE	34	3N	1W	Grant	0-225-214-2023	1.9	7.0	12.0	12.8	44.9	2.546	2.628	3.224	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
MILESTONE-BUCKLEY 55-16-002-QRY Created On: 02/05/14 Updated On:	Q	NW	NW	32	48N	12W	Douglas	0-225-80-2014		0.0	7.2	5.0	22.5	2.783	2.813	1.084	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
MILESTONE-BUCKLEY 55-16-002-QRY Created On: 02/13/17 Updated On:	Q	NW	NW	32	48N	12W	Douglas	0-225-69-2017		0.0	9.5	4.8	21.2	2.880	2.910	1.027	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
MILESTONE-BUCKLEY 55-16-002-QRY Created On: 08/15/17 Updated On:	Q	NW	NW	32	48N	12W	Douglas	0-225-253-2017	0.1	0.0	6.7	5.6	22.4	2.870	2.887	0.584	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
MILESTONE-BUCKLEY 55-16-002-QRY Created On: 01/08/20 Updated On:	Q	NW	NW	32	48N	12W	Douglas	0-225-58-2020	0.0	0.0	5.6	5.3	22.3	2.816	2.841	0.882	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
MILESTONE-BUCKLEY 55-16-002-QRY Created On: 01/03/23 Updated On:	Q	NW	NW	32	48N	12W	Douglas	0-225-59-2023	0.0	1.5	2.3	3.5	17.3	2.817	2.845	1.009	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
MILESTONE-CHARLES OLSEN 55-09-047-PIT Created On: 01/08/15 Updated On:	P	SW	NW	35	30N	8W	Chippewa	0-225-37-2015		0.0	3.3	3.9	17.9	2.704	2.735	1.139		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
MILESTONE-CHARLES OLSEN 55-09-047-PIT Created On: 01/08/20 Updated On:	P	SW	NW	35	30N	8W	Chippewa	0-225-53-2020	1.4	0.0	0.0	4.6	19.6	2.727	2.756	1.068		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MILESTONE-CLEMENTS 33 55-32-003-QRY Created On: 05/08/14 Updated On:	Q	NW	NE	7	15N	5W	La Crosse	0-225-160-2014		0.0	2.6	8.9	34.4	2.631	2.681	1.905		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
MILESTONE-CLEMENTS 33 55-32-003-QRY Created On: 04/06/17 Updated On:	Q	NW	NE	7	15N	5W	La Crosse	0-225-109-2017	1.3	0.0	1.6	10.0	41.0	2.529	2.607	3.051		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
MILESTONE-CLEMENTS 33 55-32-003-QRY Created On: 01/03/20 Updated On:	Q	NW	NE	7	15N	5W	La Crosse	0-225-17-2020	1.8	0.0	5.1	11.2	41.6	2.539	2.618	3.141		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MILESTONE-CLEMENTS 33 55-32-003-QRY Created On: 01/04/23 Updated On:	Q	NW	NE	7	15N	5W	La Crosse	0-225-86-2023	2.1	3.4	3.8	11.4	41.8	2.544	2.621	3.050		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MILESTONE-CLEMENTS YY 55-32-004-QRY Created On: 06/05/15 Updated On:	Q	SW	NE	3	15N	6W	La Crosse	0-225-186-2015		0.0	2.3	10.4	36.9	2.597	2.656	2.237		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
MILESTONE-CLEMENTS YY 55-32-004-QRY Created On: 01/03/18 Updated On:	Q	SW	NE	3	15N	6W	La Crosse	0-225-11-2018	3.0	0.0	2.6	12.2	41.9	2.551	2.620	2.700		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
MILESTONE-CLEMENTS YY 55-32-004-QRY Created On: 01/04/21 Updated On:	Q	SW	NE	3	15N	6W	La Crosse	0-225-30-2021	2.9	0.0	0.0	10.7	38.2	2.536	2.612	3.006		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MILESTONE-CLEMENTS YY 55-32-004-QRY Created On: 01/02/24 Updated On:	Q	SW	NE	3	15N	6W	La Crosse	0-225-25-2024	2.5	6.8	2.3	10.4	39.4	2.568	2.636	2.657		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MILESTONE-DON JOHNSON 55-07-006-PIT Created On: 01/05/16 Updated On:	P	E	SW	21	39N	17W	Burnett	0-225-26-2016		0.0	6.6	3.8	16.9	2.739	2.771	1.148		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
MILESTONE-DON JOHNSON 55-07-006-PIT Created On: 10/12/21 Updated On:	P	E	SW	21	39N	17W	Burnett	0-225-267-2021	0.8	3.0	3.7	3.8	16.9	2.778	2.804	0.927		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MILESTONE-DON JOHNSON 55-07-006-PIT Created On: 01/04/24 Updated On:	P	E	SW	21	39N	17W	Burnett	0-225-144-2024	1.0	4.8	6.4	3.5	16.6	2.747	2.794	1.701		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MILESTONE-DONALD NELSON 55-11-029-PIT Created On: 06/12/14 Updated On:	P	SW	NW	12	13N	6E	Columbia	0-225-192-2014		0.0	2.7	7.4	30.4	2.761	2.791	1.097		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
MILESTONE-DONALD NELSON 55-11-029-PIT Created On: 01/04/19 Updated On:	P	SW	NW	12	13N	6E	Columbia	0-225-21-2019	0.5	0.0	4.1	8.0	31.3	2.693	2.735	1.561		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
MILESTONE-DONALD NELSON 55-11-029-PIT Created On: 01/02/24 Updated On:	P	SW	NW	12	13N	6E	Columbia	0-225-20-2024	1.0	4.2	3.0	7.4	29.3	2.702	2.739	1.355		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MILESTONE-MONDOVI-BUCK RIDGE 55-06-016-QRY Created On: 02/03/14 Updated On:	Q	N	SE	28	24N	11W	Buffalo	0-225-74-2014		0.0	2.4	10.5	42.2	2.591	2.657	2.547		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
MILESTONE-MONDOVI-BUCK RIDGE 55-06-016-QRY Created On: 01/05/17 Updated On:	Q	N	SE	28	24N	11W	Buffalo	0-225-46-2017	0.6	0.0	3.3	8.7	38.7	2.580	2.643	2.445		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
MILESTONE-MONDOVI-BUCK RIDGE 55-06-016-QRY Created On: 06/18/20 Updated On:	Q	N	SE	28	24N	11W	Buffalo	0-225-197-2020	0.6	0.0	6.6	13.3	48.2	2.533	2.615	3.220		
	Approved Use : HMA<MT, CONCRETE, OGBC, Base Aggregate																	
MILESTONE-MONDOVI-BUCK RIDGE 55-06-016-QRY Created On: 01/04/22 Updated On:	Q	N	SE	28	24N	11W	Buffalo	0-225-74-2022	0.6	0.0	40.6	14.7	50.3	2.537	2.622	3.360		
	Approved Use : HMA<MT, CONCRETE, OGBC, Base Aggregate																	
MILESTONE-MONDOVI-BUCK RIDGE 55-06-016-QRY Created On: 08/17/22 Updated On:	Q	N	SE	28	24N	11W	Buffalo	0-225-251-2022	0.1	7.8	12.6	15.3	49.4	2.594	2.660	2.567		
	Approved Use : Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
MILESTONE-THOMPSON F 55-62-030-QRY Created On: 01/07/14 Updated On:	Q	SE	SW	8	14N	1E	Vernon	0-225-35-2014		0.0	9.8	15.3	43.9	2.493	2.575	3.312	
	Approved Use : CONCRETE, OGBC, Base Aggregate																
MILESTONE-THOMPSON F 55-62-030-QRY Created On: 05/04/17 Updated On:	Q	SE	SW	8	14N	1E	Vernon	0-225-171-2017		0.0	3.2	8.8	36.4	2.615	2.669	2.066	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
MILESTONE-THOMPSON F 55-62-030-QRY Created On: 01/03/20 Updated On:	Q	SE	SW	8	14N	1E	Vernon	0-225-24-2020	1.2	0.0	5.1	9.7	34.7	2.597	2.661	2.461	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
MILESTONE-THOMPSON F 55-62-030-QRY Created On: 01/03/23 Updated On:	Q	SE	SW	8	14N	1E	Vernon	0-225-30-2023	1.0	3.6	0.6	9.7	35.5	2.623	2.674	1.940	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
MILESTONE-WALKER 8 55-48-030-PIT Created On: 06/21/18 Updated On:	P	SE	SE	23	34N	17W	Polk	0-225-238-2018	0.3	0.0	1.6	4.8	17.4	2.823	2.853	1.051	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
MILESTONE-WALKER 8 55-48-030-PIT Created On: 05/01/23 Updated On:	P	SE	SE	23	34N	17W	Polk	0-225-209-2023	0.1	0.0	1.1	2.6	13.1	2.854	2.880	0.911	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
* MILESTONE-WAYNE ANDERSON 55-47-030-QRY Created On: 01/03/18 Updated On:	Q	NW	NE	9	25N	18W	Pierce	0-225-39-2018	2.1	0.0	4.2	8.7	33.4	2.615	2.674	2.258	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
* MILESTONE-WAYNE ANDERSON 55-47-030-QRY Created On: 01/05/21 Updated On:	Q	NW	NE	9	25N	18W	Pierce	0-225-76-2021	1.9	0.0	0.4	7.7	31.3	2.605	2.667	2.360	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
MILITARY 55-43-015-PIT Created On: 01/05/21 Updated On:	P	NE	SE	2	39N	11E	Oneida	0-225-53-2021	0.9	0.0	0.6	3.0	15.7	2.702	2.725	0.847	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
MILLER 55-25-019-QRY Created On: 04/16/15 Updated On:	Q	NW	NW	31	6N	3E	Iowa	0-225-124-2015		4.7	7.2	6.9	30.0	2.588	2.661	2.840	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
MILLER 55-25-019-QRY Created On: 03/28/17 Updated On:	Q	NW	NW	31	6N	3E	Iowa	0-225-91-2017	0.0	4.6	9.2	6.9	30.1	2.594	2.666	2.762	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
MILLER 55-50-014-PIT Created On: 05/11/17 Updated On:	P		NE	4	35N	1E	Price	0-225-179-2017		0.0	1.5	4.0	18.7	2.717	2.742	0.913	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
MILLER 55-25-019-QRY Created On: 02/09/18 Updated On:	Q	NW	NW	31	6N	3E	Iowa	0-225-96-2018	3.0	4.0	6.8	10.8	42.3	2.580	2.650	2.707	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
MILLER 55-25-019-QRY Created On: 03/17/21 Updated On:	Q	NW	NW	31	6N	3E	Iowa	0-225-142-2021	0.1	5.9	3.6	7.7	33.2	2.579	2.651	2.796	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
MILLER 55-50-014-PIT Created On: 05/17/22 Updated On:	P	NE	4	35N	1E	Price	0-225-201-2022	0.0	0.0	4.2	4.1	19.2	2.724	2.752	1.063			
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MILLER 55-25-019-QRY Created On: 02/28/24 Updated On:	Q	NW	NW	31	6N	3E Iowa	0-225-179-2024	0.8	8.1	10.1	10.2	38.4	2.537	2.627	3.577			
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MIMBACH 55-55-008-QRY Created On: 01/08/15 Updated On:	Q	SW	NW	5	28N	19W St. Croix	0-225-38-2015		0.0	6.4	7.6	29.5	2.694	2.735	1.497			
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
MIMBACH 55-55-008-QRY Created On: 04/21/17 Updated On:	Q	SW	NW	5	28N	19W St. Croix	0-225-140-2017	0.1	0.0	2.7	6.7	28.5	2.675	2.720	1.702			
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
MIMBACH 55-55-008-QRY Created On: 01/08/20 Updated On:	Q	SW	NW	5	28N	19W St. Croix	0-225-60-2020	2.2	0.0	8.1	10.0	37.8	2.562	2.639	2.990			
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MIMBACH 55-55-008-QRY Created On: 01/03/23 Updated On:	Q	SW	NW	5	28N	19W St. Croix	0-225-55-2023	0.7	7.7	12.4	13.9	44.8	2.559	2.642	3.214			
	Approved Use : CONCRETE, OGBC, Base Aggregate																	
MIMBACH 55-55-008-QRY Created On: 03/01/23 Updated On:	Q	SW	NW	5	28N	19W St. Croix	0-225-161-2023	0.3	2.6	2.3	8.2	32.7	2.643	2.700	2.160			
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
MINDORO 55-32-012-QRY Created On: 01/07/14 Updated On:	Q	SW	SW	33	18N	6W	La Crosse	0-225-45-2014		0.0	4.5	8.1	32.4	2.625	2.675	1.919		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
MINDORO 55-32-012-QRY Created On: 05/04/17 Updated On:	Q	SW	SW	33	18N	6W	La Crosse	0-225-174-2017		0.0	2.7	10.2	32.7	2.611	2.669	2.187		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
MINDORO 55-32-012-QRY Created On: 01/08/20 Updated On:	Q	SW	SW	33	18N	6W	La Crosse	0-225-67-2020	0.7	0.0	7.4	10.3	38.6	2.584	2.650	2.549		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MINDORO 55-32-012-QRY Created On: 01/04/23 Updated On:	Q	SW	SW	33	18N	6W	La Crosse	0-225-87-2023	0.6	3.5	1.5	9.7	38.3	2.596	2.659	2.442		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MINONG 55-65-009-QRY Created On: 10/08/15 Updated On:	Q	NE	NW	27	42N	11W	Washburn	0-225-241-2015		0.0	0.4	2.9	11.8	2.903	2.915	0.400		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
MINONG 55-65-009-QRY Created On: 06/07/18 Updated On:	Q	NE	NW	27	42N	11W	Washburn	0-225-219-2018		0.0	0.5	2.3	10.1	2.930	2.940	0.320		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
MINONG 55-65-009-QRY Created On: 07/07/22 Updated On:	Q	NE	NW	27	42N	11W	Washburn	0-225-246-2022	0.0	0.5	0.3	2.0	10.7	2.914	2.924	0.339		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
MISHICOT 55-36-027-PIT Created On: 01/12/16 Updated On:	P	NE	SE	27	21N	23E	Manitowoc	0-225-55-2016		0.0	1.3	6.1	28.9	2.727	2.757	1.109		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
MISHICOT 55-36-027-PIT Created On: 01/05/21 Updated On:	P	NE	SE	27	21N	23E	Manitowoc	0-225-105-2021	0.0	3.7	0.9	5.7	27.3	2.675	2.721	1.710		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MITCH KING 55-37-051-PIT Created On: 01/07/14 Updated On:	P	SW	NE	6	26N	9E	Marathon	0-225-38-2014		0.0	3.4	9.5	35.0	2.596	2.630	1.277		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
MITCH KING 55-37-051-PIT Created On: 01/03/17 Updated On:	P	SW	NE	6	26N	9E	Marathon	0-225-3-2017		0.0	2.2	8.2	33.4	2.619	2.650	1.173		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
MITCH KING 55-37-051-PIT Created On: 02/17/22 Updated On:	P	SW	NE	6	26N	9E	Marathon	0-225-133-2022	1.3	0.0	2.5	9.0	34.2	2.628	2.655	1.035		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MOATS 55-09-044-PIT Created On: 03/08/18 Updated On:	P	SW	NE	15	29N	7W	Chippewa	0-225-114-2018	8.1	0.0	6.5	5.9	20.5	2.630	2.674	1.682		
	Approved Use : HMA<MT, HMA>=MT, Base Aggregate																	
MOATS 55-09-044-PIT Created On: 01/05/21 Updated On:	P	SW	NE	15	29N	7W	Chippewa	0-225-90-2021	2.6	0.0	2.3	5.0	21.7	2.677	2.712	1.298		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
MOLLETT 55-62-022-QRY Created On: 05/19/16 Updated On:	Q	NE	SE	4	12N	4W	Vernon	0-225-180-2016		0.0	4.6	9.4	35.5	2.636	2.686	1.903		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
MOLLETT 55-62-022-QRY Created On: 01/07/19 Updated On:	Q	NE	SE	4	12N	4W	Vernon	0-225-51-2019	0.5	0.0	2.0	8.1	33.7	2.632	2.683	1.931		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MOLLETT 55-62-022-QRY Created On: 01/10/22 Updated On:	Q	NE	SE	4	12N	4W	Vernon	0-225-101-2022	0.2	6.0	0.5	9.4	35.2	2.635	2.690	2.091		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MONICO (MICHEL'S) 55-43-016-PIT Created On: 05/15/14 Updated On:	P	NW	SE	26	36N	11E	Oneida	0-225-164-2014		0.0	0.5	2.3	10.5	2.709	2.729	0.715		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
MONICO (MICHEL'S) 55-43-016-PIT Created On: 07/16/20 Updated On:	P	NW	SE	26	36N	11E	Oneida	0-225-220-2020	0.0	1.3	0.4	3.2	13.4	2.699	2.715	0.615		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MONROE CONSTRUCTION 55-23-014-QRY Created On: 07/17/14 Updated On:	Q	SE	NE	32	2N	7E	Green	0-225-222-2014		14.1	1.9	10.0	39.2	2.597	2.669	2.741		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
MONROE CONSTRUCTION 55-23-014-QRY Created On: 03/08/17 Updated On:	Q	SE	NE	32	2N	7E	Green	0-225-76-2017	0.2	11.2	2.6	11.5	40.7	2.573	2.650	2.974		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
MONROE CONSTRUCTION 55-23-014-QRY Created On: 04/17/23 Updated On:	Q	SE	NE	32	2N	7E	Green	0-225-196-2023	0.9	4.2	6.3	12.0	43.5	2.514	2.611	3.860		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
* MONTEVIDEO QUARRY 55-42-025-QRY Created On: 07/07/14 Updated On:	Q	NW	SE	3	26N	20E	Oconto	0-225-212-2014	0.2	5.8	2.3	5.9	25.6	2.734	2.762	0.989		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
* MONTEVIDEO QUARRY 55-42-025-QRY Created On: 07/23/19 Updated On:	Q	NW	SE	3	26N	20E	Oconto	0-225-245-2019	0.5	7.0	4.1	5.8	25.6	2.738	2.768	1.114		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
MORGAN 55-37-052-PIT Created On: 07/31/14 Updated On:	P	SE	SW	35	29N	5E	Marathon	0-225-237-2014		0.0	2.7	4.7	21.9	2.644	2.681	1.409		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
MORGAN 55-37-052-PIT Created On: 04/05/19 Updated On:	P	SE	SW	35	29N	5E	Marathon	0-225-123-2019	0.6	0.0	0.8	5.1	21.5	2.642	2.673	1.161		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
MORGAN 55-37-052-PIT Created On: 01/02/24 Updated On:	P	SE	SW	35	29N	5E	Marathon	0-225-57-2024	0.6	0.0	1.6	3.8	20.9	2.615	2.650	1.356		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
* MORRIS 55-24-012-QRY Created On: 03/20/14 Updated On:	Q	SE	SW	3	16N	13E	Green Lake	0-225-99-2014	0.9	1.8	1.9	6.6	28.8	2.692	2.728	1.332		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
MORRIS 55-22-040-QRY Created On: 04/09/15 Updated On:	Q	NW	NW	3	5N	3W	Grant	0-225-116-2015	1.3	2.4	3.9	11.4	39.8	2.671	2.733	2.297		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
* MORRIS 55-24-012-QRY Created On: 04/03/17 Updated On:	Q	SE	SW	3	16N	13E	Green Lake	0-225-99-2017	0.7	6.4	5.3	12.7	37.1	2.648	2.698	1.874		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
* MORRIS 55-24-012-QRY Created On: 05/07/20 Updated On:	Q	SE	SW	3	16N	13E	Green Lake	0-225-171-2020	3.2	22.9	3.8	10.4	38.1	2.648	2.703	2.072		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
* MORRIS 55-24-012-QRY Created On: 05/27/21 Updated On:	Q	SE	SW	3	16N	13E	Green Lake	0-225-216-2021	2.1	5.7	3.6	7.7	29.8	2.682	2.722	1.487		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MORRIS 55-22-040-QRY Created On: 04/05/23 Updated On:	Q	NW	NW	3	5N	3W	Grant	0-225-188-2023		17.6	2.7	9.5	37.8	2.657	2.685	1.057		
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																	
MORRISON 55-47-018-QRY Created On: 06/10/16 Updated On:	Q	SE	NW	35	25N	18W	Pierce	0-225-196-2016	2.1	0.0	2.1	7.3	31.2	2.665	2.709	1.622		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
MORRISON 55-47-018-QRY Created On: 01/07/19 Updated On:	Q	SE	NW	35	25N	18W	Pierce	0-225-62-2019	2.2	0.0	5.7	9.5	38.5	2.614	2.669	2.125		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
MORRISON 55-47-018-QRY Created On: 03/07/22 Updated On:	Q	SE	NW	35	25N	18W	Pierce	0-225-141-2022		3.2	5.1	8.5	34.9	2.640	2.690	1.900		
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																	
MOUNDS BRANCH 55-33-018-QRY Created On: 01/29/24 Updated On:	Q	NW	NE	33	4N	1E	Lafayette	0-225-150-2024	1.0	5.8	3.2	9.2	34.9	2.574	2.645	2.755		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MROCZINSKI 55-37-054-PIT Created On: 04/24/19 Updated On:	P	SW	NW	16	29N	5E	Marathon	0-225-169-2019	0.0	0.0	0.2	3.5	17.8	2.638	2.656	0.675		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
MROCZINSKI 55-37-054-PIT Created On: 01/02/24 Updated On:	P	SW	NW	16	29N	5E	Marathon	0-225-60-2024	0.0	0.0	6.9	6.3	25.7	2.637	2.673	1.372		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MROTEK 55-57-013-PIT Created On: 01/03/18 Updated On:	P		SW	1	41N	8W	Sawyer	0-225-16-2018	0.8	0.0	2.2	3.6	15.8	2.810	2.837	0.969		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MROTEK 55-57-013-PIT Created On: 01/03/23 Updated On:	P		SW	1	41N	8W	Sawyer	0-225-57-2023	1.9	1.5	1.1	3.8	16.1	2.769	2.800	1.122		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MURRAY 55-15-017-PIT Created On: 07/30/15 Updated On:	P	NE	SE	26	26N	23E	Door	0-225-220-2015	0.1	0.0	9.3	8.2	36.1	2.638	2.697	2.256		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
MURRAY 55-15-017-PIT Created On: 08/25/20 Updated On:	P	NE	SE	26	26N	23E	Door	0-225-236-2020	1.5	0.0	3.4	6.5	30.2	2.693	2.736	1.598	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
MUSKEGO 55-67-029-PIT Created On: 01/04/18 Updated On:	P	SW	SW	18	5N	20E	Waukesha	0-225-76-2018	0.3	2.9	1.8	3.8	24.9	2.676	2.723	1.774	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
MUSKEGO 55-67-029-PIT Created On: 01/03/23 Updated On:	P	SW	SW	18	5N	20E	Waukesha	0-225-73-2023	0.1	3.6	0.9	4.7	22.7	2.700	2.735	1.314	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
MYKLEBUST 55-56-023-PIT Created On: 01/03/18 Updated On:	P		NE	26	13N	6E	Sauk	0-225-7-2018	1.5	0.0	1.5	6.5	26.3	2.720	2.753	1.219	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
MYKLEBUST 55-56-023-PIT Created On: 04/17/23 Updated On:	P		NE	26	13N	6E	Sauk	0-225-199-2023	0.4	0.0	2.6	5.4	24.8	2.697	2.720	0.856	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
NABER 55-28-009-PIT Created On: 03/20/20 Updated On:	P	NE	NW	31	5N	14E	Jefferson	0-225-133-2020	0.7	0.0	1.7	6.3	30.2	2.654	2.697	1.606	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
NABER QUARRY 55-28-022-QRY Created On: 09/06/22 Updated On:	Q	NE	NW	31	5N	14E	Jefferson	0-225-255-2022	2.2	15.6	10.6	9.7	39.0	2.633	2.694	2.328	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
NABER QUARRY 55-28-022-QRY Created On: 11/07/22 Updated On:	Q	NE	NW	31	5N	14E	Jefferson	0-225-261-2022	0.2	10.9	6.1	4.9	26.5	2.693	2.736	1.614	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
NAEDLER 55-10-021-QRY Created On: 01/17/14 Updated On:	Q	SE	NE	35	25N	1W	Clark	0-225-53-2014		0.0	2.0	6.6	26.8	2.611	2.634	0.887	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
NAEDLER 55-10-021-QRY Created On: 06/12/17 Updated On:	Q	SE	NE	35	25N	1W	Clark	0-225-210-2017		0.0	2.2	4.9	23.9	2.632	2.647	0.562	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
NAEDLER 55-10-021-QRY Created On: 01/08/20 Updated On:	Q	SE	NE	35	25N	1W	Clark	0-225-57-2020	0.2	0.0	0.8	5.5	25.2	2.632	2.648	0.598	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
NAEDLER 55-10-021-QRY Created On: 01/03/23 Updated On:	Q	SE	NE	35	25N	1W	Clark	0-225-39-2023	0.3	2.9	3.1	6.4	27.9	2.614	2.634	0.783	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
NANKEY 55-25-020-QRY Created On: 05/23/14 Updated On:	Q	SE	NE	14	7N	1E	Iowa	0-225-167-2014		1.3	2.4	7.9	31.0	2.604	2.670	2.519	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
NANKEY 55-25-020-QRY Created On: 01/05/17 Updated On:	Q	SE	NE	14	7N	1E	Iowa	0-225-26-2017	0.9	3.4	5.2	7.2	30.2	2.634	2.685	1.932	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
NANKEY 55-25-020-QRY Created On: 01/04/19 Updated On:	Q	SE	NE	14	7N	1E	Iowa	0-225-28-2019	0.6	6.4	4.8	6.7	28.9	2.645	2.692	1.786		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
NANKEY 55-25-020-QRY Created On: 01/02/24 Updated On:	Q	SE	NE	14	7N	1E	Iowa	0-225-40-2024	0.2	5.1	2.3	9.2	32.6	2.621	2.677	2.131		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
NEA MENASHA 55-70-024-QRY Created On: 01/05/15 Updated On:	Q		NW	4	20N	17E	Winnebago	0-225-3-2015		4.8	2.8	3.9	19.1	2.733	2.765	1.159		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
NEA MENASHA 55-70-024-QRY Created On: 01/04/18 Updated On:	Q		NW	4	20N	17E	Winnebago	0-225-56-2018		11.5	3.0	4.7	25.5	2.717	2.751	1.240		
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																	
NEA MENASHA 55-70-024-QRY Created On: 01/04/21 Updated On:	Q		NW	4	20N	17E	Winnebago	0-225-44-2021	0.0	10.6	3.6	5.5	26.9	2.722	2.757	1.272		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
NEA MENASHA 55-70-024-QRY Created On: 01/02/24 Updated On:	Q		NW	4	20N	17E	Winnebago	0-225-98-2024	0.1	12.7	0.3	5.0	25.1	2.747	2.771	0.846		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
NEECK READY MIX 55-50-016-PIT Created On: 03/20/14 Updated On:	P	NW	NW	31	39N	1E	Price	0-225-98-2014		0.0	0.9	3.8	18.1	2.745	2.765	0.739		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
NEECK READY MIX 55-50-016-PIT Created On: 01/04/19 Updated On:	P	NW	NW	31	39N	1E	Price	0-225-3-2019	1.0	0.0	2.0	4.1	19.0	2.738	2.764	0.924		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
NEECK READY MIX 55-50-016-PIT Created On: 01/02/24 Updated On:	P	NW	NW	31	39N	1E	Price	0-225-90-2024	0.3	2.6	2.8	3.6	17.5	2.722	2.750	1.034		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
NEILLSVILLE 55-10-035-QRY Created On: 06/12/17 Updated On:	Q	SE	SW	10	24N	2W	Clark	0-225-208-2017		0.0	0.4	4.7	22.5	2.598	2.611	0.494		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
NEILLSVILLE 55-10-035-QRY Created On: 01/08/20 Updated On:	Q	SE	SW	10	24N	2W	Clark	0-225-61-2020	0.4	0.0	1.5	5.0	23.1	2.609	2.624	0.537		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
NEILLSVILLE 55-10-035-QRY Created On: 01/02/24 Updated On:	Q	SE	SW	10	24N	2W	Clark	0-225-109-2024	1.2	0.4	1.4	5.2	22.9	2.585	2.605	0.767		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
NELSON MINE 55-09-046-PIT Created On: 01/12/15 Updated On:	P	NW	NW	13	28N	9W	Chippewa	0-225-57-2015		0.0	3.7	5.0	21.5	2.627	2.657	1.113		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
NELSON MINE 55-09-046-PIT Created On: 04/02/20 Updated On:	P	NW	NW	13	28N	9W	Chippewa	0-225-141-2020	1.5	0.0	1.2	5.1	20.8	2.721	2.739	0.692		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
NERDRUM 55-10-038-PIT Created On: 10/05/20 Updated On:	P	SE	NW	15	29N	2W	Clark	0-225-243-2020	1.5	0.0	1.2	4.9	21.9	2.684	2.717	1.228	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
NEUMAN 55-60-018-PIT Created On: 06/26/17 Updated On:	P	NE	SE	28	32N	1E	Taylor	0-225-222-2017		0.0	0.6	3.5	17.8	2.729	2.758	1.052	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
NEUMAN 55-60-018-PIT Created On: 06/28/22 Updated On:	P	NE	SE	28	32N	1E	Taylor	0-225-239-2022	1.1	0.0	2.4	3.6	17.3	2.751	2.778	0.995	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
NEW LONDON 55-44-025-QRY Created On: 05/26/16 Updated On:	Q			30	22N	15E	Outagamie	0-225-192-2016		8.3	8.8	7.4	31.7	2.691	2.731	1.467	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
NEW LONDON 55-44-025-QRY Created On: 01/25/19 Updated On:	Q			30	22N	15E	Outagamie	0-225-89-2019	0.4	2.6	1.1	8.0	31.3	2.731	2.759	1.005	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
NEW LONDON 55-44-025-QRY Created On: 04/28/22 Updated On:	Q			30	22N	15E	Outagamie	0-225-186-2022	0.4	7.3	2.1	6.3	29.8	2.722	2.754	1.193	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
NLC MERCER 55-26-024-PIT Created On: 05/02/16 Updated On:	P	S	NW	6	42N	4E	Iron	0-225-159-2016		0.0	0.5	3.7	18.2	2.734	2.760	0.963	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
NLC MERCER 55-26-024-PIT Created On: 01/05/21 Updated On:	P	S	NW	6	42N	4E	Iron	0-225-55-2021	1.1	0.0	1.7	3.4	17.9	2.731	2.756	0.924	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
NLC WOODRUFF 55-63-013-PIT Created On: 04/11/18 Updated On:	P	NW	SE	14	40N	6E	Vilas	0-225-169-2018	0.6	0.0	0.6	3.6	18.2	2.691	2.713	0.818	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
NLC WOODRUFF 55-63-013-PIT Created On: 01/03/23 Updated On:	P	NW	SE	14	40N	6E	Vilas	0-225-23-2023	1.2	0.0	1.0	4.5	20.2	2.701	2.722	0.812	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
NOLL 55-38-022-PIT Created On: 03/02/15 Updated On:	P	NW	SW	8	30N	21E	Marinette	0-225-85-2015	0.5	0.0	3.4	5.0	29.2	2.716	2.746	1.104	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
NOLL 55-38-022-PIT Created On: 01/02/20 Updated On:	P	NW	SW	8	30N	21E	Marinette	0-225-2-2020	0.5	0.0	5.7	5.5	27.2	2.713	2.745	1.177	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
NORWAY GROVE 55-13-068-PIT Created On: 10/27/22 Updated On:	P	NW	SW	14	9N	9E	Dane	0-225-260-2022	6.8	0.0	3.8	8.4	32.9	2.656	2.698	1.587	
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																
NOVAK 55-54-016-PIT Created On: 08/24/17 Updated On:	P	SE	NE	32	34N	9W	Rusk	0-225-261-2017		0.0	2.9	5.1	21.4	2.734	2.764	1.081	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
NOVAK 55-54-016-PIT Created On: 07/19/21 Updated On:	P	SE	NE	32	34N	9W	Rusk	0-225-246-2021	1.1	0.0	0.7	4.0	20.2	2.754	2.774	0.726		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
* O'CONNELL 55-12-013-QRY Created On: 06/20/19 Updated On:	Q			8	8N	6W	Crawford	0-225-223-2019	3.6	4.2	8.6	13.0	42.6	2.528	2.607	3.108		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
* O'NEIL 55-06-017-QRY Created On: 01/16/14 Updated On:	Q	SE	NW	36	24N	11W	Buffalo	0-225-49-2014		0.0	13.6	12.3	42.6	2.584	2.653	2.695		
	Approved Use : Base Aggregate																	
* O'NEIL 55-06-017-QRY Created On: 06/17/14 Updated On:	Q	SE	NW	36	24N	11W	Buffalo	0-225-196-2014		0.0	8.6	11.5	43.4	2.598	2.661	2.403		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
* O'NEIL 55-06-017-QRY Created On: 05/04/17 Updated On:	Q	SE	NW	36	24N	11W	Buffalo	0-225-167-2017		0.0	14.3	14.1	47.8	2.548	2.639	3.583		
	Approved Use : Base Aggregate																	
* O'NEIL 55-06-017-QRY Created On: 01/06/20 Updated On:	Q	SE	NW	36	24N	11W	Buffalo	0-225-28-2020	0.2	0.0	12.8	14.9	46.1	2.553	2.637	3.312		
	Approved Use : Base Aggregate																	
OAK PARK 55-13-069-QRY Created On: 03/28/14 Updated On:	Q	NE	SW	29	7N	12E	Dane	0-225-105-2014		15.7	12.7	9.4	31.9	2.639	2.707	2.582		
	Approved Use : Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
OAK PARK 55-13-069-QRY Created On: 01/02/24 Updated On:	Q	NE	SW	29	7N	12E	Dane	0-225-89-2024	0.1	16.0	8.1	6.6	28.8	2.578	2.656	3.038		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
* OAKFIELD STONE FOND DU LAC 55-20-033-QRY Created On: 04/22/20 Updated On:	Q	SE	SE	10	14N	17E	Fond Du Lac	0-225-154-2020	0.0	2.2	1.7	5.7	26.5	2.771	2.796	0.879		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
ODLING 55-64-013-PIT Created On: 01/19/23 Updated On:	P	NW	SE	36	2N	16E	Walworth	0-225-123-2023	1.9	2.6	2.4	4.7	30.5	2.664	2.704	1.503		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
* OLM 55-36-030-PIT Created On: 04/18/19 Updated On:	P	E	NE	9	18N	21E	Manitowoc	0-225-137-2019	0.8	2.7	0.4	8.5	31.1	2.763	2.788	0.920		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
* OLSON 55-16-017-QRY Created On: 06/13/16 Updated On:	Q	NW	NW	24	48N	10W	Douglas	0-225-198-2016		1.7	0.2	2.4	11.9	2.853	2.885	1.121		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
OLSON 55-57-017-PIT Created On: 02/13/17 Updated On:	P	NW	SW	14	41N	9W	Sawyer	0-225-71-2017		0.0	4.6	3.1	15.6	2.815	2.840	0.882		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
* OLSON 55-16-017-QRY Created On: 06/03/21 Updated On:	Q	NW	NW	24	48N	10W	Douglas	0-225-218-2021	0.7	0.0	4.0	4.4	18.7	2.844	2.872	1.016		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Coarse Sp. Gravity		Coarse Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
OLSON 55-57-017-PIT Created On: 01/10/22 Updated On:	P	NW	SW	14	41N	9W	Sawyer	0-225-105-2022	1.7	3.7	4.9	3.6	16.3	2.778	2.808	1.089	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
OLYNICK - BOHLS 55-09-049-PIT Created On: 06/08/15 Updated On:	P			16	29N	5W	Chippewa	0-225-192-2015		0.0	2.4	5.1	20.3	2.716	2.752	1.321	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
OLYNICK - BOHLS 55-09-049-PIT Created On: 04/02/20 Updated On:	P			16	29N	5W	Chippewa	0-225-142-2020	0.0	0.0	1.3	4.8	21.7	2.738	2.768	1.106	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
OPELT PIT 55-10-023-PIT Created On: 04/25/17 Updated On:	P	NE	NW	8	23N	2W	Clark	0-225-149-2017		0.0	1.1	3.9	18.9	2.709	2.734	0.920	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
OPELT PIT 55-10-023-PIT Created On: 04/05/22 Updated On:	P	NE	NW	8	23N	2W	Clark	0-225-158-2022	2.0	0.0	0.9	3.9	19.6	2.674	2.703	1.085	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
OPELT QUARRY 55-10-024-QRY Created On: 04/25/17 Updated On:	Q	NE	NW	8	23N	2W	Clark	0-225-148-2017		0.0	0.2	4.2	18.0	2.829	2.839	0.354	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
OPELT QUARRY 55-10-024-QRY Created On: 05/04/20 Updated On:	Q	NE	NW	8	23N	2W	Clark	0-225-164-2020	0.0	0.0	0.4	4.4	21.7	2.745	2.753	0.314	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Coarse Sp. Gravity		Coarse Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
OPELT QUARRY 55-10-024-QRY Created On: 01/03/23 Updated On:	Q	NE	NW	8	23N	2W	Clark	0-225-35-2023	0.0	0.2	0.3	3.7	17.6	2.851	2.865	0.492	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
OREGON 55-13-112-PIT Created On: 01/05/17 Updated On:	P	NW	SE	36	5N	9E	Dane	0-225-50-2017	2.5	4.1	1.4	11.2	39.0	2.561	2.630	2.668	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
OREGON 55-13-112-PIT Created On: 01/04/22 Updated On:	P	NW	SE	36	5N	9E	Dane	0-225-59-2022	5.2	5.2	2.9	7.0	30.4	2.591	2.645	2.068	
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																
OSCEOLA 55-48-018-PIT Created On: 01/09/15 Updated On:	P	NW	SE	16	33N	18W	Polk	0-225-42-2015		0.0	3.4	5.8	18.3	2.780	2.809	1.068	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
OSCEOLA 55-48-018-PIT Created On: 01/02/24 Updated On:	P	NW	SE	16	33N	18W	Polk	0-225-80-2024	4.0	0.0	2.4	5.3	19.9	2.737	2.772	1.263	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
OVYN 55-60-020-QRY Created On: 02/14/17 Updated On:	Q	NE	SW	28	30N	2W	Taylor	0-225-72-2017		0.0	0.2	3.2	15.2	3.004	3.024	0.683	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
OVYN 55-60-030-PIT Created On: 02/14/17 Updated On:	P	NE	SW	28	30N	2W	Taylor	0-225-73-2017		0.0	1.4	4.2	20.3	2.659	2.700	1.526	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
OVYN 55-60-030-PIT Created On: 04/22/21 Updated On:	P	NE	SW	28	30N	2W	Taylor	0-225-187-2021	2.3	0.0	2.8	5.0	20.9	2.671	2.704	1.199	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
OVYN 55-60-020-QRY Created On: 04/22/21 Updated On:	Q	NE	SW	28	30N	2W	Taylor	0-225-188-2021	0.0	0.0	0.3	3.8	16.9	2.865	2.878	0.436	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
OVYN 55-60-020-QRY Created On: 04/15/24 Updated On:	Q	NE	SW	28	30N	2W	Taylor	0-225-219-2024	0.0	0.0	0.3	3.8	17.2	2.825	2.842	0.615	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
P&D HONEY CREEK 55-51-020-PIT Created On: 01/04/18 Updated On:	P		NW	6	3N	19E	Racine	0-225-78-2018	0.5	5.8	1.8	4.1	26.4	2.675	2.720	1.666	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
P&D HONEY CREEK 55-51-020-PIT Created On: 01/03/23 Updated On:	P		NW	6	3N	19E	Racine	0-225-74-2023	0.2	11.5	1.3	5.3	24.4	2.673	2.719	1.722	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
PADDOCK 55-64-028-PIT Created On: 04/10/18 Updated On:	P	E	SE	1	3N	16E	Walworth	0-225-161-2018	1.4	0.0	1.3	5.3	25.7	2.670	2.709	1.457	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
PADDOCK 55-64-028-PIT Created On: 05/14/21 Updated On:	P	E	SE	1	3N	16E	Walworth	0-225-208-2021	4.9	7.2	3.0	4.6	29.8	2.696	2.732	1.316	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
PAFFEL 55-65-010-PIT Created On: 01/24/14 Updated On:	P	NE	NE	21	39N	12W	Washburn	0-225-59-2014		0.0	2.9	3.6	16.4	2.715	2.740	0.932	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
PAFFEL 55-65-010-PIT Created On: 01/07/19 Updated On:	P	NE	NE	21	39N	12W	Washburn	0-225-59-2019	0.3	0.0	2.3	3.8	17.3	2.708	2.743	1.323	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
PAFFEL 55-65-010-PIT Created On: 01/02/24 Updated On:	P	NE	NE	21	39N	12W	Washburn	0-225-94-2024	0.9	3.3	2.0	3.9	18.6	2.706	2.742	1.313	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
PALECEK 55-02-012-PIT Created On: 06/16/22 Updated On:	P	NW	SW	24	47N	1W	Ashland	0-225-230-2022	0.6	2.1	2.4	4.2	18.9	2.753	2.780	1.004	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
PAUL BUGAR "B" 55-10-026-QRY Created On: 05/21/15 Updated On:	Q	SE	NE	26	25N	1W	Clark	0-225-178-2015		0.0	0.3	6.9	30.5	2.620	2.642	0.831	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
PAUL BUGAR "B" 55-10-026-QRY Created On: 04/25/18 Updated On:	Q	SE	NE	26	25N	1W	Clark	0-225-185-2018	0.4	0.0	0.3	5.3	26.4	2.641	2.656	0.597	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
PAUL BUGAR "B" 55-10-026-QRY Created On: 06/17/21 Updated On:	Q	SE	NE	26	25N	1W	Clark	0-225-226-2021	0.1	0.0	2.1	7.2	30.6	2.605	2.626	0.803	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
PAUL BUGAR "B" 55-10-026-QRY Created On: 02/28/24 Updated On:	Q	SE	NE	26	25N	1W	Clark	0-225-192-2024	0.5	0.0	0.5	7.2	32.6	2.615	2.628	0.490	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
PAUL BUGAR "N" 55-37-057-QRY Created On: 05/21/15 Updated On:	Q	N	NE	2	27N	2E	Marathon	0-225-176-2015		0.0	1.2	4.5	22.0	2.573	2.603	1.159	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
PAUL BUGAR "N" 55-37-057-QRY Created On: 04/25/18 Updated On:	Q	N	NE	2	27N	2E	Marathon	0-225-184-2018		0.0	0.2	5.0	23.3	2.617	2.631	0.534	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
PAUL BUGAR "N" 55-37-057-QRY Created On: 06/17/21 Updated On:	Q	N	NE	2	27N	2E	Marathon	0-225-228-2021	0.3	0.0	0.7	6.7	30.4	2.597	2.616	0.747	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
PAUL BUGAR "N" 55-37-057-QRY Created On: 02/28/24 Updated On:	Q	N	NE	2	27N	2E	Marathon	0-225-193-2024	0.1	0.0	0.6	5.3	24.7	2.607	2.621	0.550	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
PAUL BUGAR "R" 55-37-058-QRY Created On: 05/21/15 Updated On:	Q	NE	NW	1	27N	2E	Marathon	0-225-177-2015		0.0	0.9	4.7	23.1	2.626	2.654	1.037	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
PAUL BUGAR "R" 55-37-058-QRY Created On: 04/25/18 Updated On:	Q	NE	NW	1	27N	2E	Marathon	0-225-183-2018	0.1	0.0	0.6	5.2	25.9	2.593	2.610	0.655	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
PAUL BUGAR "R" 55-37-058-QRY Created On: 06/17/21 Updated On:	Q	NE	NW	1	27N	2E	Marathon	0-225-227-2021	0.0	0.0	0.3	5.5	26.8	2.607	2.618	0.450	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
PAUL BUGAR "R" 55-37-058-QRY Created On: 02/28/24 Updated On:	Q	NE	NW	1	27N	2E	Marathon	0-225-194-2024	0.0	0.0	0.3	7.3	32.2	2.601	2.618	0.644	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
PAYNE AND DOLAN / RACINE 55-51-022-QRY Created On: 01/07/14 Updated On:	Q		S	29	4N	23E	Racine	0-225-43-2014	0.1	0.0	0.9	4.7	20.5	2.758	2.785	0.999	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
PAYNE AND DOLAN / RACINE 55-51-022-QRY Created On: 02/03/17 Updated On:	Q		S	29	4N	23E	Racine	0-225-57-2017	1.2	0.0	0.9	6.4	27.3	2.633	2.685	1.970	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
PAYNE AND DOLAN / RACINE 55-51-022-QRY Created On: 01/08/20 Updated On:	Q		S	29	4N	23E	Racine	0-225-78-2020	3.2	0.0	4.1	6.3	27.8	2.638	2.693	2.102	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
PAYNE AND DOLAN / RACINE 55-51-022-QRY Created On: 01/03/23 Updated On:	Q		S	29	4N	23E	Racine	0-225-50-2023	0.0	0.4	0.1	5.9	26.0	2.665	2.691	0.999	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
PEDRETTI 55-62-028-QRY Created On: 01/09/15 Updated On:	Q	SW	NW	27	13N	7W	Vernon	0-225-51-2015		0.0	9.2	10.8	40.0	2.575	2.641	2.576	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
PEDRETTI 55-62-028-QRY Created On: 01/03/18 Updated On:	Q	SW	NW	27	13N	7W	Vernon	0-225-15-2018	0.5	0.0	2.1	8.5	32.3	2.594	2.659	2.520		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
PEDRETTI 55-62-028-QRY Created On: 01/04/21 Updated On:	Q	SW	NW	27	13N	7W	Vernon	0-225-25-2021	0.4	0.0	0.9	10.0	34.8	2.573	2.646	2.835		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
PEDRETTI 55-62-028-QRY Created On: 01/02/24 Updated On:	Q	SW	NW	27	13N	7W	Vernon	0-225-29-2024	2.1	9.0	11.7	13.4	45.6	2.538	2.619	3.220		
	Approved Use : HMA<MT, CONCRETE, OGBC, Base Aggregate																	
PERZINSKI 55-49-018-PIT Created On: 01/07/14 Updated On:	P	SE	SE	20	23N	9E	Portage	0-225-32-2014		0.0	1.5	6.7	27.3	2.681	2.712	1.145		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
PERZINSKI 55-49-018-PIT Created On: 04/15/24 Updated On:	P	SE	SE	20	23N	9E	Portage	0-225-218-2024	1.9	2.2	2.3	6.1	29.3	2.659	2.693	1.263		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
PETERS - PESHTIGO QUARRY 55-38-026-QRY Created On: 07/07/14 Updated On:	Q	SE	NW	33	30N	22E	Marinette	0-225-213-2014	1.3	1.1	1.2	5.3	26.6	2.725	2.765	1.462		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
PETERS - PESHTIGO QUARRY 55-38-026-QRY Created On: 01/05/17 Updated On:	Q	SE	NW	33	30N	22E	Marinette	0-225-52-2017	1.8	4.4	3.7	8.9	33.7	2.663	2.715	1.953		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
PETERS - PESHTIGO QUARRY 55-38-026-QRY Created On: 01/02/20 Updated On:	Q	SE	NW	33	30N	22E	Marinette	0-225-5-2020	0.1	3.7	4.0	5.3	24.7	2.737	2.766	1.056	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
PETERS - PESHTIGO QUARRY 55-38-026-QRY Created On: 01/12/23 Updated On:	Q	SE	NW	33	30N	22E	Marinette	0-225-119-2023	0.1	3.8	4.0	7.0	31.0	2.676	2.730	2.000	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
PETERS CHASE #5 55-42-030-QRY Created On: 01/27/14 Updated On:	Q		NW	17	26N	19E	Oconto	0-225-61-2014		2.5	2.8	5.2	23.3	2.750	2.774	0.857	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
PETERS CHASE #5 55-42-030-QRY Created On: 01/30/15 Updated On:	Q		NW	17	26N	19E	Oconto	0-225-81-2015	0.7	4.2	3.9	5.6	24.9	2.731	2.759	0.995	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
PETERS CHASE #5 55-42-030-QRY Created On: 01/07/16 Updated On:	Q		NW	17	26N	19E	Oconto	0-225-39-2016		1.8	2.6	5.3	24.4	2.720	2.748	1.033	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
PETERS CHASE #5 55-42-030-QRY Created On: 01/25/19 Updated On:	Q		NW	17	26N	19E	Oconto	0-225-90-2019	0.1	6.5	1.7	5.2	23.6	2.756	2.780	0.879	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
PETERS CHASE #5 55-42-030-QRY Created On: 01/04/22 Updated On:	Q		NW	17	26N	19E	Oconto	0-225-90-2022	0.0	2.7	1.9	5.0	23.5	2.736	2.760	0.876	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
PETERS-BONDUEL 55-58-050-PIT Created On: 01/06/21 Updated On:	P	NW	NE	30	26N	17E	Shawano	0-225-110-2021	3.4	4.9	4.9	9.7	35.2	2.645	2.694	1.844	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
PETERS-BRUSSELS 55-15-003-PIT Created On: 04/14/16 Updated On:	P	SE	NW	26	26N	23E	Door	0-225-148-2016	0.4	0.0	9.4	8.0	25.5	2.691	2.736	1.676	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
PETERS-BRUSSELS 55-15-003-PIT Created On: 05/30/17 Updated On:	P	SE	NW	26	26N	23E	Door	0-225-195-2017	0.4	0.0	6.3	8.2	33.5	2.714	2.763	1.795	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
PETERS-BRUSSELS 55-15-003-PIT Created On: 04/20/23 Updated On:	P	SE	NW	26	26N	23E	Door	0-225-203-2023	0.2	0.0	6.9	6.1	28.5	2.719	2.757	1.393	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
PETERSON 55-09-052-PIT Created On: 10/03/17 Updated On:	P	NE	SW	32	29N	5W	Chippewa	0-225-278-2017		0.0	0.9	4.0	19.1	2.685	2.720	1.273	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
PETERSON 55-35-029-PIT Created On: 07/16/20 Updated On:	P	NW	SE	30	32N	6E	Lincoln	0-225-218-2020	1.4	0.0	0.8	4.2	20.6	2.688	2.717	1.087	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
PETERSON 55-09-052-PIT Created On: 01/04/22 Updated On:	P	NE	SW	32	29N	5W	Chippewa	0-225-83-2022	0.8	0.0	1.8	3.3	16.8	2.713	2.744	1.135	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
PETERSON "CC" 55-42-032-PIT Created On: 03/30/15 Updated On:	P	S	NW	32	28N	19E	Oconto	0-225-102-2015	0.2	0.0	3.3	6.8	30.5	2.734	2.765	1.134		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
PETERSON "CC" 55-42-032-PIT Created On: 01/08/20 Updated On:	P	S	NW	32	28N	19E	Oconto	0-225-75-2020	0.2	0.0	2.8	6.1	29.9	2.732	2.759	0.996		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
PETERSON MARENGO 55-02-013-PIT Created On: 05/19/16 Updated On:	P	N	SW	18	45N	4W	Ashland	0-225-182-2016		0.0	2.6	5.4	23.1	2.639	2.693	2.050		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
PETERSON MARENGO 55-02-013-PIT Created On: 05/10/21 Updated On:	P	N	SW	18	45N	4W	Ashland	0-225-204-2021	2.5	0.0	14.2	5.8	23.7	2.686	2.741	2.034		
	Approved Use : Base Aggregate																	
PHILLIPS 55-50-019-PIT Created On: 01/05/21 Updated On:	P	SW	SW	5	37N	1E	Price	0-225-54-2021	0.8	0.0	1.5	4.0	19.3	2.691	2.720	1.042		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
* PICKWICK 27-00-030-QRY Created On: 06/14/18 Updated On:	Q			1	105N	6W	Winona, Mn	0-225-233-2018	1.6	1.1	2.3	7.8	34.8	2.618	2.674	2.145		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
* PICKWICK 27-00-030-QRY Created On: 01/07/19 Updated On:	Q			1	105N	6W	Winona, Mn	0-225-50-2019	1.5	4.0	4.0	9.4	39.4	2.586	2.650	2.471		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
PINE BROOK 55-65-012-PIT Created On: 05/14/15 Updated On:	P	N	21	38N	11W	Washburn	0-225-174-2015		0.0	3.1	4.1	18.5	2.788	2.815	0.978			
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
PINE BROOK 55-65-012-PIT Created On: 01/08/21 Updated On:	P	N	21	38N	11W	Washburn	0-225-118-2021	0.3	0.0	4.3	4.9	20.4	2.736	2.776	1.464			
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
PINE LAKE MATERIALS 55-51-025-PIT Created On: 03/24/16 Updated On:	P	NE	35	3N	19E	Racine	0-225-117-2016	0.6	7.3	2.3	5.7	29.6	2.676	2.724	1.793			
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
PINE LAKE MATERIALS 55-51-025-PIT Created On: 01/05/21 Updated On:	P	NE	35	3N	19E	Racine	0-225-82-2021	0.0	14.4	4.8	5.0	25.0	2.654	2.703	1.880			
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
PINE RIDGE 55-35-030-PIT Created On: 05/11/15 Updated On:	P	NW	SW	8	31N	7E	Lincoln	0-225-168-2015		0.0	0.9	4.5	19.8	2.675	2.708	1.256		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
PINE RIDGE 55-35-030-PIT Created On: 05/12/20 Updated On:	P	NW	SW	8	31N	7E	Lincoln	0-225-176-2020	1.9	0.0	2.3	4.4	20.6	2.679	2.708	1.085		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
PINE VALLEY 55-10-027-QRY Created On: 05/07/15 Updated On:	Q	NW	21	24N	2W	Clark	0-225-152-2015		0.0	0.8	5.9	25.6	2.608	2.621	0.498			
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description						Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range					County	100	500	OD	SSD	Crse	Fine
PINE VALLEY 55-10-027-QRY Created On: 04/19/18 Updated On:	Q		NW	21	24N	2W	Clark	0-225-174-2018	0.8	0.0	1.5	6.7	28.0	2.571	2.596	0.973	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
PINE VALLEY 55-10-027-QRY Created On: 04/08/21 Updated On:	Q		NW	21	24N	2W	Clark	0-225-174-2021	2.4	1.1	3.3	8.8	32.2	2.548	2.579	1.207	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
PINE VALLEY 55-10-027-QRY Created On: 01/29/24 Updated On:	Q		NW	21	24N	2W	Clark	0-225-163-2024	1.0	1.4	0.8	4.1	21.0	2.598	2.613	0.582	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
PLENTY 55-11-030-QRY Created On: 05/08/19 Updated On:	Q			16	10N	9E	Columbia	0-225-179-2019	2.8	4.3	3.2	11.0	43.0	2.494	2.596	4.114	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
PLENTY 55-11-030-QRY Created On: 08/02/22 Updated On:	Q			16	10N	9E	Columbia	0-225-250-2022	3.3	5.4	4.1	9.7	38.5	2.564	2.623	2.291	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
PLOVER 55-49-019-PIT Created On: 03/06/17 Updated On:	P	SW	SW	5	22N	9E	Portage	0-225-74-2017	0.2	0.0	1.8	7.1	29.0	2.661	2.691	1.110	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
PLOVER 55-49-019-PIT Created On: 02/17/22 Updated On:	P	SW	SW	5	22N	9E	Portage	0-225-131-2022	0.9	0.0	3.2	6.3	27.2	2.652	2.681	1.107	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description						Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range					County	100	500	OD	SSD	Crse
POINT SPORT 55-57-020-PIT Created On: 01/03/18 Updated On:	P		NE	2	41N	7W	Sawyer	0-225-19-2018	0.9	0.0	1.5	4.1	18.3	2.763	2.788	0.877
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate															
POINT SPORT 55-57-020-PIT Created On: 01/03/23 Updated On:	P		NE	2	41N	7W	Sawyer	0-225-58-2023	0.2	0.9	1.5	3.5	16.4	2.756	2.787	1.133
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate															
POPPLE RIVER 55-21-016-PIT Created On: 07/01/21 Updated On:	P	SW	NW	12	38N	14E	Forest	0-225-240-2021	0.0	0.2	0.2	3.6	17.1	2.734	2.749	0.556
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate															
POTAPENKO 55-09-053-PIT Created On: 03/08/18 Updated On:	P	SE	SW	25	31N	5W	Chippewa	0-225-113-2018	3.3	0.0	1.4	3.9	21.1	2.655	2.691	1.380
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate															
POTAPENKO 55-09-053-PIT Created On: 01/10/23 Updated On:	P	SE	SW	25	31N	5W	Chippewa	0-225-118-2023	2.3	0.0	2.1	3.7	19.3	2.643	2.685	1.610
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate															
* PRAGER 55-51-026-PIT Created On: 01/07/14 Updated On:	P	N	SW	7	4N	19E	Racine	0-225-40-2014	0.4	0.0	1.0	4.6	21.3	2.724	2.754	1.120
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate															
* PRAGER 55-51-026-PIT Created On: 02/05/19 Updated On:	P	N	SW	7	4N	19E	Racine	0-225-95-2019	1.1	6.6	0.4	4.7	22.8	2.706	2.741	1.305
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate															

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description						Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range					County	100	500	OD	SSD	Crse	Fine
PRAIRIE AVE S&G 55-53-030-PIT Created On: 02/16/16 Updated On:	P	SW	6	1N	13E	Rock	0-225-87-2016	0.4	2.2	0.8	8.1	39.5	2.669	2.708	1.481		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
PRAIRIE AVE S&G 55-53-030-PIT Created On: 02/06/18 Updated On:	P	SW	6	1N	13E	Rock	0-225-87-2018	4.5	0.0	2.4	5.5	26.7	2.672	2.709	1.399		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
PRAIRIE AVE S&G 55-53-030-PIT Created On: 01/07/19 Updated On:	P	SW	6	1N	13E	Rock	0-225-68-2019	4.6	0.0	4.7	5.3	26.2	2.654	2.694	1.490		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
PRAIRIE AVE S&G 55-53-030-PIT Created On: 01/02/24 Updated On:	P	SW	6	1N	13E	Rock	0-225-1-2024	4.5	0.0	4.1	5.0	25.8	2.662	2.701	1.464		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
PRESCOTT 55-47-020-QRY Created On: 09/02/16 Updated On:	Q	NW	NW	12	26N	20W	Pierce	0-225-252-2016		0.0	3.5	8.6	34.8	2.604	2.664	2.321	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
PRESCOTT 55-47-020-QRY Created On: 01/07/19 Updated On:	Q	NW	NW	12	26N	20W	Pierce	0-225-61-2019	1.2	0.0	7.4	8.4	34.6	2.622	2.679	2.160	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
PRESCOTT 55-47-020-QRY Created On: 01/04/22 Updated On:	Q	NW	NW	12	26N	20W	Pierce	0-225-75-2022	4.6	7.0	5.2	7.8	33.1	2.635	2.685	1.901	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
* PRIBBERNOW 55-10-032-QRY Created On: 01/30/14 Updated On:	Q	E	E	13	28N	2W	Clark	0-225-64-2014		0.0	0.9	4.2	18.1	2.647	2.667	0.766		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
* PRIBBERNOW 55-10-032-QRY Created On: 01/03/17 Updated On:	Q	E	E	13	28N	2W	Clark	0-225-5-2017		0.0	0.8	4.6	21.0	2.626	2.647	0.784		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
* PRIBBERNOW 55-10-032-QRY Created On: 01/07/20 Updated On:	Q	E	E	13	28N	2W	Clark	0-225-41-2020	0.0	0.0	0.6	4.4	19.9	2.707	2.716	0.361		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
PROHASKA 55-50-024-PIT Created On: 06/26/17 Updated On:	P	SW	SW	10	36N	1W	Price	0-225-220-2017		0.0	1.9	4.7	21.5	2.736	2.758	0.829		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
PROHASKA 55-50-024-PIT Created On: 01/04/22 Updated On:	P	SW	SW	10	36N	1W	Price	0-225-86-2022	1.5	0.0	1.7	4.9	22.5	2.742	2.768	0.933		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
* PROJECT SITE 55-99-026-PIT Created On: 07/24/19 Updated On:	P							0-225-246-2019	0.2	2.1	0.3	5.6	28.0	2.714	2.745	1.136		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
* R & R WASH 55-20-035-PIT Created On: 03/07/14 Updated On:	P	E	SW	7	16N	14E	Fond Du Lac	0-225-93-2014	0.2	0.0	4.3	8.4	32.8	2.689	2.731	1.582		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
* R & R WASH 55-20-035-PIT Created On: 04/24/19 Updated On:	P	E	SW	7	16N	14E	Fond Du Lac	0-225-164-2019	1.9	4.4	4.0	7.8	31.5	2.704	2.743	1.446	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
RADEMANN STONE 55-20-036-QRY Created On: 05/08/15 Updated On:	Q	NE	SW	11	14N	17E	Fond Du Lac	0-225-156-2015		1.2	0.4	6.9	29.4	2.778	2.795	0.615	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
RADEMANN STONE 55-20-036-QRY Created On: 06/27/18 Updated On:	Q	NE	SW	11	14N	17E	Fond Du Lac	0-225-241-2018		1.0	1.0	6.3	30.2	2.759	2.781	0.797	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
RADEMANN STONE 55-20-036-QRY Created On: 04/30/21 Updated On:	Q	NE	SW	11	14N	17E	Fond Du Lac	0-225-197-2021	0.7	1.1	0.5	7.7	31.5	2.739	2.763	0.867	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
RADEMANN STONE 55-20-036-QRY Created On: 01/02/24 Updated On:	Q	NE	SW	11	14N	17E	Fond Du Lac	0-225-108-2024	0.0	0.7	0.7	6.2	28.4	2.770	2.790	0.719	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
RANDY MAHR 55-09-055-PIT Created On: 01/07/15 Updated On:	P	NE	SW	23	29N	5W	Chippewa	0-225-10-2015		0.0	1.8	3.7	18.0	2.749	2.774	0.907	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
RANDY MAHR 55-09-055-PIT Created On: 01/05/21 Updated On:	P	NE	SW	23	29N	5W	Chippewa	0-225-92-2021	1.5	0.0	3.4	4.3	20.6	2.714	2.745	1.143	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
RATZ 55-06-020-QRY Created On: 04/23/15 Updated On:	Q	SW	SW	12	20N	11W	Buffalo	0-225-134-2015		0.0	3.2	11.9	41.4	2.595	2.659	2.438		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
RATZ 55-06-020-QRY Created On: 01/04/18 Updated On:	Q	SW	SW	12	20N	11W	Buffalo	0-225-47-2018	0.3	0.0	0.9	9.0	35.1	2.609	2.668	2.269		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
RATZ 55-06-020-QRY Created On: 01/04/21 Updated On:	Q	SW	SW	12	20N	11W	Buffalo	0-225-39-2021	0.9	0.0	0.4	7.8	33.7	2.590	2.650	2.320		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
RATZ 55-06-020-QRY Created On: 01/02/24 Updated On:	Q	SW	SW	12	20N	11W	Buffalo	0-225-117-2024	0.3	3.5	4.3	10.1	39.3	2.607	2.667	2.313		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
RC HOGARTY 55-37-092-QRY Created On: 07/01/21 Updated On:	Q	SW	SE	32	30N	10E	Marathon	0-225-241-2021	0.1	0.0	1.0	6.7	34.0	2.656	2.673	0.648		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
RC HOGARTY 55-37-092-QRY Created On: 01/29/24 Updated On:	Q	SW	SE	32	30N	10E	Marathon	0-225-155-2024	0.0	0.0	0.6	11.8	38.5	2.676	2.685	0.360		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
READFIELD 55-68-025-QRY Created On: 08/03/16 Updated On:	Q	NE	SW	26	21N	14E	Waupaca	0-225-231-2016		0.0	2.0	7.2	31.5	2.645	2.702	2.155		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
READFIELD 55-68-025-QRY Created On: 01/10/19 Updated On:	Q	NE	SW	26	21N	14E	Waupaca	0-225-85-2019	0.3	0.0	2.4	6.1	29.8	2.712	2.752	1.453		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
READFIELD 55-68-025-QRY Created On: 03/17/22 Updated On:	Q	NE	SW	26	21N	14E	Waupaca	0-225-147-2022	0.9	0.0	1.2	9.2	39.7	2.635	2.686	1.905		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
RECYCLED PCC 55-99-031-QRY Created On: 01/07/14 Updated On:	Q							0-225-33-2014				0.0	10.0	35.9				
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
RECYCLED PCC 55-99-031-QRY Created On: 02/07/14 Updated On:	Q							0-225-86-2014		0.0	0.0	6.9	30.2					
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
RECYCLED PCC 55-99-031-QRY Created On: 03/17/14 Updated On:	Q							0-225-96-2014		0.0	0.0	10.1	38.1					
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
RECYCLED PCC 55-99-031-QRY Created On: 03/31/14 Updated On:	Q							0-225-107-2014		0.0	0.0	9.2	34.3					
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
RECYCLED PCC 55-99-031-QRY Created On: 04/03/14 Updated On:	Q							0-225-110-2014		0.0	0.0	9.2	34.3					
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Coarse Sp. Gravity		Coarse Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
RECYCLED PCC 55-99-031-QRY Created On: 04/03/14 Updated On:	Q							0-225-112-2014	0.0	0.0	5.8	28.9						
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
RECYCLED PCC 55-99-031-QRY Created On: 04/03/14 Updated On:	Q							0-225-113-2014	0.0	0.0	8.0	30.3						
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
RECYCLED PCC 55-99-031-QRY Created On: 04/11/14 Updated On:	Q							0-225-126-2014		0.0	8.3	34.7						
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
RECYCLED PCC 55-99-031-QRY Created On: 04/17/14 Updated On:	Q							0-225-134-2014	0.0	0.0	13.0	37.3						
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
RECYCLED PCC 55-99-031-QRY Created On: 04/22/14 Updated On:	Q							0-225-136-2014		0.0	10.5	38.6						
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
RECYCLED PCC 55-99-031-QRY Created On: 04/22/14 Updated On:	Q							0-225-137-2014		0.0	11.5	34.1						
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
RECYCLED PCC 55-99-031-QRY Created On: 04/24/14 Updated On:	Q							0-225-142-2014	0.0	0.0	12.4	41.2						
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Coarse Sp. Gravity		Coarse Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
RECYCLED PCC 55-99-031-QRY Created On: 04/24/14 Updated On:	Q							0-225-147-2014	0.0	0.0	10.2	36.5						
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
RECYCLED PCC 55-99-031-QRY Created On: 04/24/14 Updated On:	Q							0-225-148-2014	0.0	0.0	9.2	30.7						
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
RECYCLED PCC 55-99-031-QRY Created On: 05/23/14 Updated On:	Q							0-225-169-2014		0.0	13.2	42.9						
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
RECYCLED PCC 55-99-031-QRY Created On: 05/23/14 Updated On:	Q							0-225-174-2014		0.0	14.5	42.6						
	Approved Use : CONCRETE, OGBC, Base Aggregate																	
RECYCLED PCC 55-99-031-QRY Created On: 06/05/14 Updated On:	Q							0-225-184-2014	0.0	0.0	8.4	38.9						
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
RECYCLED PCC 55-99-031-QRY Created On: 06/05/14 Updated On:	Q							0-225-185-2014	0.0	0.0	8.7	34.1						
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
RECYCLED PCC 55-99-031-QRY Created On: 06/05/14 Updated On:	Q							0-225-186-2014	0.0	10.2	14.0	42.8						
	Approved Use : CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Coarse Sp. Gravity		Coarse Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
RECYCLED PCC 55-99-031-QRY Created On: 06/26/14 Updated On:	Q							0-225-203-2014		0.0	0.0	10.1	31.0					
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
RECYCLED PCC 55-99-031-QRY Created On: 07/17/14 Updated On:	Q							0-225-227-2014		0.0	0.0	10.3	42.5					
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
RECYCLED PCC 55-99-031-QRY Created On: 07/30/14 Updated On:	Q							0-225-231-2014		0.0	0.0	13.8	37.7					
	Approved Use : CONCRETE, OGBC, Base Aggregate																	
RECYCLED PCC 55-99-031-QRY Created On: 08/01/14 Updated On:	Q							0-225-238-2014		0.0	0.0	8.6	30.5					
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
RECYCLED PCC 55-99-031-QRY Created On: 08/14/14 Updated On:	Q							0-225-243-2014			0.0	9.9	36.1					
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
RECYCLED PCC 55-99-031-QRY Created On: 08/14/14 Updated On:	Q							0-225-244-2014		0.0	0.0	7.0	35.2					
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
RECYCLED PCC 55-99-031-QRY Created On: 08/14/14 Updated On:	Q							0-225-245-2014		0.0	0.0	7.6	31.2					
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
RECYCLED PCC 55-99-031-QRY Created On: 08/14/14 Updated On:	Q							0-225-246-2014		0.0	0.0	6.9	28.0					
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
RECYCLED PCC 55-99-031-QRY Created On: 09/02/14 Updated On:	Q							0-225-253-2014		0.0	0.0	7.1	37.8					
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
RECYCLED PCC 55-99-031-QRY Created On: 09/04/14 Updated On:	Q							0-225-254-2014		0.0	0.0	7.9	30.1					
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
RECYCLED PCC 55-99-031-QRY Created On: 09/11/14 Updated On:	Q							0-225-255-2014		0.0	0.0	7.4	33.5					
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
RECYCLED PCC 55-99-031-QRY Created On: 09/11/14 Updated On:	Q							0-225-257-2014			0.0	9.5	31.4					
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
RECYCLED PCC 55-99-031-QRY Created On: 09/11/14 Updated On:	Q							0-225-258-2014		0.0	0.0	-780.2	37.4					
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
RECYCLED PCC 55-99-031-QRY Created On: 11/13/14 Updated On:	Q							0-225-270-2014		0.0	0.0	7.7	39.0					
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Coarse Sp. Gravity		Coarse Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
RECYCLED PCC 55-99-031-QRY Created On: 01/07/15 Updated On:	Q							0-225-9-2015			0.0							
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
RECYCLED PCC 55-99-031-QRY Created On: 01/08/15 Updated On:	Q							0-225-24-2015		0.0	0.0	6.6	28.2					
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
RECYCLED PCC 55-99-031-QRY Created On: 01/21/15 Updated On:	Q							0-225-72-2015			0.0	9.0	34.7					
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
RECYCLED PCC 55-99-031-QRY Created On: 03/02/15 Updated On:	Q							0-225-86-2015		0.0	0.0	8.3	32.6					
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
RECYCLED PCC 55-99-031-QRY Created On: 03/09/15 Updated On:	Q							0-225-90-2015		0.0	0.0	12.6	40.9					
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
RECYCLED PCC 55-99-031-QRY Created On: 03/09/15 Updated On:	Q							0-225-91-2015			0.0	8.2	40.1					
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
RECYCLED PCC 55-99-031-QRY Created On: 03/19/15 Updated On:	Q							0-225-96-2015			0.0	6.7	33.9					
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Coarse Sp. Gravity		Coarse Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
RECYCLED PCC 55-99-031-QRY Created On: 03/30/15 Updated On:	Q							0-225-110-2015			0.0	7.2	34.0					
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
RECYCLED PCC 55-99-031-QRY Created On: 04/08/15 Updated On:	Q							0-225-113-2015		0.0	0.0	10.4	40.2					
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
RECYCLED PCC 55-99-031-QRY Created On: 04/08/15 Updated On:	Q							0-225-114-2015		0.0	0.0	7.6	30.0					
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
RECYCLED PCC 55-99-031-QRY Created On: 04/08/15 Updated On:	Q							0-225-115-2015		0.0	0.0	7.3	30.0					
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
RECYCLED PCC 55-99-031-QRY Created On: 04/23/15 Updated On:	Q							0-225-133-2015		0.0	0.0	8.9	28.8					
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
RECYCLED PCC 55-99-031-QRY Created On: 04/23/15 Updated On:	Q							0-225-137-2015		0.0	0.0	8.9	31.9					
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
RECYCLED PCC 55-99-031-QRY Created On: 04/23/15 Updated On:	Q							0-225-138-2015		0.0	0.0	6.8	34.0					
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Coarse Sp. Gravity		Coarse Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
RECYCLED PCC 55-99-031-QRY Created On: 04/28/15 Updated On:	Q							0-225-140-2015	0.0	0.0		11.4	34.2					
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
RECYCLED PCC 55-99-031-QRY Created On: 05/06/15 Updated On:	Q							0-225-143-2015	0.0	0.0		8.3	33.1					
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
RECYCLED PCC 55-99-031-QRY Created On: 05/06/15 Updated On:	Q							0-225-144-2015			0.0	9.1	34.9					
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
RECYCLED PCC 55-99-031-QRY Created On: 05/06/15 Updated On:	Q							0-225-145-2015	0.0	0.0		8.2	35.8					
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
RECYCLED PCC 55-99-031-QRY Created On: 05/07/15 Updated On:	Q							0-225-150-2015	0.0	0.0		8.1	29.8					
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
RECYCLED PCC 55-99-031-QRY Created On: 05/11/15 Updated On:	Q							0-225-161-2015			0.0	8.9	34.2					
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
RECYCLED PCC 55-99-031-QRY Created On: 05/11/15 Updated On:	Q							0-225-166-2015			0.0	7.8	27.4					
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Coarse Sp. Gravity		Coarse Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
RECYCLED PCC 55-99-031-QRY Created On: 05/14/15 Updated On:	Q							0-225-173-2015		0.0	0.0	9.6	38.5					
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
RECYCLED PCC 55-99-031-QRY Created On: 06/17/15 Updated On:	Q							0-225-195-2015			0.0	12.0	35.0					
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
RECYCLED PCC 55-99-031-QRY Created On: 06/17/15 Updated On:	Q							0-225-196-2015			0.0	10.7	36.0					
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
RECYCLED PCC 55-99-031-QRY Created On: 06/23/15 Updated On:	Q							0-225-198-2015		0.0	0.0	9.3	34.0					
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
RECYCLED PCC 55-99-031-QRY Created On: 06/25/15 Updated On:	Q							0-225-201-2015		0.0	0.0	10.2	36.0					
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
RECYCLED PCC 55-99-031-QRY Created On: 07/23/15 Updated On:	Q							0-225-217-2015		0.0	0.0	7.5	29.2					
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
RECYCLED PCC 55-99-031-QRY Created On: 08/05/15 Updated On:	Q							0-225-225-2015		0.0	0.0	9.9	35.2					
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
RECYCLED PCC 55-99-031-QRY Created On: 08/05/15 Updated On:	Q							0-225-226-2015		0.0	0.0	7.0	28.7					
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
RECYCLED PCC 55-99-031-QRY Created On: 09/24/15 Updated On:	Q							0-225-239-2015			0.0	9.9	38.4					
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
RECYCLED PCC 55-99-031-QRY Created On: 10/08/15 Updated On:	Q							0-225-243-2015			0.0	7.5	28.0					
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
RECYCLED PCC 55-99-031-QRY Created On: 10/08/15 Updated On:	Q							0-225-244-2015			0.0	6.7	28.4					
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
RECYCLED PCC 55-99-031-QRY Created On: 11/04/15 Updated On:	Q							0-225-246-2015		0.0	0.0	7.7	26.1					
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
RECYCLED PCC 55-99-031-QRY Created On: 11/04/15 Updated On:	Q							0-225-247-2015		0.0	0.0	7.9	33.4					
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
RECYCLED PCC 55-99-031-QRY Created On: 01/20/16 Updated On:	Q							0-225-59-2016			0.0	10.6	36.1					
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Coarse Sp. Gravity		Coarse Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
RECYCLED PCC 55-99-031-QRY Created On: 01/21/16 Updated On:	Q							0-225-72-2016		0.0	0.0	10.7	41.6					
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
RECYCLED PCC 55-99-031-QRY Created On: 03/18/16 Updated On:	Q							0-225-100-2016			0.0	9.1	33.9					
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
RECYCLED PCC 55-99-031-QRY Created On: 03/18/16 Updated On:	Q							0-225-101-2016			0.0	8.6	33.5					
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
RECYCLED PCC 55-99-031-QRY Created On: 03/24/16 Updated On:	Q							0-225-105-2016			0.0	7.6	31.8					
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
RECYCLED PCC 55-99-031-QRY Created On: 03/24/16 Updated On:	Q							0-225-106-2016		0.0	0.0	15.3	44.2					
	Approved Use : CONCRETE, Base Aggregate																	
RECYCLED PCC 55-99-031-QRY Created On: 03/24/16 Updated On:	Q							0-225-107-2016		0.0	0.0	14.4	43.0					
	Approved Use : CONCRETE, Base Aggregate																	
RECYCLED PCC 55-99-031-QRY Created On: 03/24/16 Updated On:	Q							0-225-111-2016		0.0	0.0	8.5	29.8					
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Coarse Sp. Gravity		Coarse Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
RECYCLED PCC 55-99-031-QRY Created On: 04/05/16 Updated On:	Q							0-225-123-2016			0.0	11.2	35.8					
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
RECYCLED PCC 55-99-031-QRY Created On: 04/05/16 Updated On:	Q							0-225-124-2016		0.0	0.0	9.9	35.0					
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
RECYCLED PCC 55-99-031-QRY Created On: 04/13/16 Updated On:	Q							0-225-144-2016		0.0	0.0	9.2	33.2					
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
RECYCLED PCC 55-99-031-QRY Created On: 04/13/16 Updated On:	Q							0-225-145-2016		0.0	0.0	10.6	33.4					
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
RECYCLED PCC 55-99-031-QRY Created On: 04/14/16 Updated On:	Q							0-225-149-2016		0.0	0.0	7.5	29.6					
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
RECYCLED PCC 55-99-031-QRY Created On: 04/14/16 Updated On:	Q							0-225-150-2016		0.0	0.0	8.0	32.4					
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
RECYCLED PCC 55-99-031-QRY Created On: 04/14/16 Updated On:	Q							0-225-151-2016		0.0	0.0	7.5	29.3					
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Coarse Sp. Gravity		Coarse Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
RECYCLED PCC 55-99-031-QRY Created On: 04/14/16 Updated On:	Q							0-225-152-2016		0.0	0.0	6.3	26.7					
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
RECYCLED PCC 55-99-031-QRY Created On: 04/14/16 Updated On:	Q							0-225-153-2016			0.0	8.7	34.0					
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
RECYCLED PCC 55-99-031-QRY Created On: 04/22/16 Updated On:	Q							0-225-158-2016		0.0	0.0	11.9	41.0					
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
RECYCLED PCC 55-99-031-QRY Created On: 05/02/16 Updated On:	Q							0-225-161-2016			0.0	8.8	35.5					
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
RECYCLED PCC 55-99-031-QRY Created On: 05/12/16 Updated On:	Q							0-225-174-2016		0.0	0.0	8.0	29.8					
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
RECYCLED PCC 55-99-031-QRY Created On: 05/12/16 Updated On:	Q							0-225-175-2016			0.0	8.5	35.2					
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
RECYCLED PCC 55-99-031-QRY Created On: 05/12/16 Updated On:	Q							0-225-176-2016		0.0	0.0	8.5	29.9					
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Coarse Sp. Gravity		Coarse Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
RECYCLED PCC 55-99-031-QRY Created On: 05/19/16 Updated On:	Q							0-225-177-2016			0.0	8.9	37.9					
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
RECYCLED PCC 55-99-031-QRY Created On: 05/19/16 Updated On:	Q							0-225-178-2016			0.0	10.3	34.2					
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
RECYCLED PCC 55-99-031-QRY Created On: 05/26/16 Updated On:	Q							0-225-187-2016			0.0	11.7	38.1					
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
RECYCLED PCC 55-99-031-QRY Created On: 06/13/16 Updated On:	Q							0-225-199-2016		0.0	0.0	9.7	31.6					
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
RECYCLED PCC 55-99-031-QRY Created On: 06/13/16 Updated On:	Q							0-225-200-2016		0.0	0.0	11.3	36.7					
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
RECYCLED PCC 55-99-031-QRY Created On: 06/13/16 Updated On:	Q							0-225-201-2016		0.0	0.0	12.4	36.4					
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
RECYCLED PCC 55-99-031-QRY Created On: 06/13/16 Updated On:	Q							0-225-202-2016		0.0	0.0	9.5	32.2					
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Coarse Sp. Gravity		Coarse Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
RECYCLED PCC 55-99-031-QRY Created On: 06/16/16 Updated On:	Q							0-225-205-2016		0.0	0.0	9.1	29.4					
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
RECYCLED PCC 55-99-031-QRY Created On: 06/30/16 Updated On:	Q							0-225-220-2016			0.0	7.5	29.1					
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
RECYCLED PCC 55-99-031-QRY Created On: 06/30/16 Updated On:	Q							0-225-221-2016		0.0	0.0	11.1	34.2					
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
RECYCLED PCC 55-99-031-QRY Created On: 06/30/16 Updated On:	Q							0-225-222-2016			0.0	10.5	37.5					
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
RECYCLED PCC 55-99-031-QRY Created On: 06/30/16 Updated On:	Q							0-225-223-2016			0.0	8.7	36.0					
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
RECYCLED PCC 55-99-031-QRY Created On: 08/08/16 Updated On:	Q							0-225-236-2016		0.0	0.0	5.7	26.2					
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
RECYCLED PCC 55-99-031-QRY Created On: 08/23/16 Updated On:	Q							0-225-246-2016			0.0	11.9	36.3					
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Coarse Sp. Gravity		Coarse Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
RECYCLED PCC 55-99-031-QRY Created On: 08/25/16 Updated On:	Q							0-225-247-2016			0.0	36.7						
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
RECYCLED PCC 55-99-031-QRY Created On: 08/30/16 Updated On:	Q							0-225-250-2016		0.0	0.0	7.3	31.5					
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
RECYCLED PCC 55-99-031-QRY Created On: 09/09/16 Updated On:	Q							0-225-254-2016			0.0	9.9	37.8					
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
RECYCLED PCC 55-99-031-QRY Created On: 09/15/16 Updated On:	Q							0-225-255-2016			0.0	7.9	32.0					
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
RECYCLED PCC 55-99-031-QRY Created On: 09/16/16 Updated On:	Q							0-225-258-2016			0.0		34.7					
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
RECYCLED PCC 55-99-031-QRY Created On: 09/20/16 Updated On:	Q							0-225-259-2016		0.0	0.0	8.6	29.0					
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
RECYCLED PCC 55-99-031-QRY Created On: 09/22/16 Updated On:	Q							0-225-262-2016		0.0	0.0	11.7	35.4					
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Coarse Sp. Gravity		Coarse Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
RECYCLED PCC 55-99-031-QRY Created On: 09/22/16 Updated On:	Q							0-225-263-2016			0.0	9.8	33.9					
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
RECYCLED PCC 55-99-031-QRY Created On: 10/11/16 Updated On:	Q							0-225-269-2016			0.0		35.3					
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
RECYCLED PCC 55-99-031-QRY Created On: 10/14/16 Updated On:	Q							0-225-271-2016		0.0	0.0	6.9	28.1					
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
RECYCLED PCC 55-99-031-QRY Created On: 11/11/16 Updated On:	Q							0-225-273-2016			0.0	7.6	31.7					
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
RECYCLED PCC 55-99-031-QRY Created On: 11/17/16 Updated On:	Q							0-225-274-2016			0.0	8.9	37.6					
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
RECYCLED PCC 55-99-031-QRY Created On: 12/31/16 Updated On:	Q							0-225-275-2016		0.0	0.0	10.1	36.1					
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
RECYCLED PCC 55-99-031-QRY Created On: 01/05/17 Updated On:	Q							0-225-27-2017		0.0	0.0	10.1	36.1					
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Coarse Sp. Gravity		Coarse Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
RECYCLED PCC 55-99-031-QRY Created On: 02/13/17 Updated On:	Q							0-225-63-2017			0.0	8.4	34.0					
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
RECYCLED PCC 55-99-031-QRY Created On: 02/13/17 Updated On:	Q							0-225-64-2017			0.0	8.9	36.6					
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
RECYCLED PCC 55-99-031-QRY Created On: 02/13/17 Updated On:	Q							0-225-65-2017			0.0	7.9	33.4					
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
RECYCLED PCC 55-99-031-QRY Created On: 02/13/17 Updated On:	Q							0-225-68-2017			0.0	7.5	35.0					
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
RECYCLED PCC 55-99-031-QRY Created On: 03/13/17 Updated On:	Q							0-225-82-2017			0.0	8.2	34.8					
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
RECYCLED PCC 55-99-031-QRY Created On: 03/13/17 Updated On:	Q							0-225-83-2017		0.0	0.0	8.5	32.9					
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
RECYCLED PCC 55-99-031-QRY Created On: 03/22/17 Updated On:	Q							0-225-85-2017			0.0	9.9	35.7					
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Coarse Sp. Gravity		Coarse Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
RECYCLED PCC 55-99-031-QRY Created On: 04/03/17 Updated On:	Q							0-225-98-2017		0.0	0.0	7.3	31.1					
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
RECYCLED PCC 55-99-031-QRY Created On: 04/03/17 Updated On:	Q							0-225-100-2017		0.0	0.0	8.1	32.3					
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
RECYCLED PCC 55-99-031-QRY Created On: 04/04/17 Updated On:	Q							0-225-104-2017			0.0	7.6	30.5					
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
RECYCLED PCC 55-99-031-QRY Created On: 04/06/17 Updated On:	Q							0-225-107-2017		0.0	0.0	11.3	42.5					
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
RECYCLED PCC 55-99-031-QRY Created On: 04/06/17 Updated On:	Q							0-225-108-2017		0.0	0.0	10.1	39.6					
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
RECYCLED PCC 55-99-031-QRY Created On: 04/10/17 Updated On:	Q							0-225-118-2017			0.0	10.9	32.2					
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
RECYCLED PCC 55-99-031-QRY Created On: 04/10/17 Updated On:	Q							0-225-119-2017			0.0	9.1	29.6					
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Coarse Sp. Gravity		Coarse Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
RECYCLED PCC 55-99-031-QRY Created On: 04/12/17 Updated On:	Q							0-225-126-2017		0.0	0.0	12.4	37.9					
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
RECYCLED PCC 55-99-031-QRY Created On: 04/13/17 Updated On:	Q							0-225-132-2017			0.0	8.7	30.5					
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
RECYCLED PCC 55-99-031-QRY Created On: 04/13/17 Updated On:	Q							0-225-133-2017		0.0	0.0	12.1	40.2					
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
RECYCLED PCC 55-99-031-QRY Created On: 04/13/17 Updated On:	Q							0-225-136-2017		0.0	0.0	7.9	31.7					
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
RECYCLED PCC 55-99-031-QRY Created On: 04/17/17 Updated On:	Q							0-225-137-2017			0.0	9.1	32.1					
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
RECYCLED PCC 55-99-031-QRY Created On: 04/21/17 Updated On:	Q							0-225-146-2017		0.0	0.0	10.3	36.8					
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
RECYCLED PCC 55-99-031-QRY Created On: 05/04/17 Updated On:	Q							0-225-173-2017			0.0	11.6	44.1					
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Coarse Sp. Gravity		Coarse Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
RECYCLED PCC 55-99-031-QRY Created On: 05/05/17 Updated On:	Q							0-225-175-2017			0.0	10.9	36.5					
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
RECYCLED PCC 55-99-031-QRY Created On: 05/18/17 Updated On:	Q							0-225-187-2017		0.0	0.0	10.5	37.3					
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
RECYCLED PCC 55-99-031-QRY Created On: 05/30/17 Updated On:	Q							0-225-194-2017			0.0	8.9	35.7					
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
RECYCLED PCC 55-99-031-QRY Created On: 05/30/17 Updated On:	Q							0-225-198-2017		0.0	0.0	6.2	28.8					
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
RECYCLED PCC 55-99-031-QRY Created On: 06/16/17 Updated On:	Q							0-225-213-2017		0.0	0.0	8.5	31.2					
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
RECYCLED PCC 55-99-031-QRY Created On: 06/16/17 Updated On:	Q							0-225-214-2017		0.0	0.0	8.9	26.0					
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
RECYCLED PCC 55-99-031-QRY Created On: 06/26/17 Updated On:	Q							0-225-217-2017			0.0	6.9	29.6					
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Coarse Sp. Gravity		Coarse Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
RECYCLED PCC 55-99-031-QRY Created On: 07/14/17 Updated On:	Q							0-225-231-2017			0.0	8.8	34.2					
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
RECYCLED PCC 55-99-031-QRY Created On: 07/14/17 Updated On:	Q							0-225-232-2017			0.0	6.6	29.2					
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
RECYCLED PCC 55-99-031-QRY Created On: 07/14/17 Updated On:	Q							0-225-233-2017		0.0	0.0	9.0	30.9					
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
RECYCLED PCC 55-99-031-QRY Created On: 07/14/17 Updated On:	Q							0-225-234-2017			0.0	6.7	30.2					
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
RECYCLED PCC 55-99-031-QRY Created On: 07/28/17 Updated On:	Q							0-225-245-2017		0.0	0.0	8.1	29.5					
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
RECYCLED PCC 55-99-031-QRY Created On: 08/14/17 Updated On:	Q							0-225-251-2017			0.0	12.7	37.8					
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
RECYCLED PCC 55-99-031-QRY Created On: 08/14/17 Updated On:	Q							0-225-252-2017			0.0	10.7	34.4					
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Coarse Sp. Gravity		Coarse Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
RECYCLED PCC 55-99-031-QRY Created On: 08/15/17 Updated On:	Q							0-225-257-2017		0.0	0.0	9.3	33.1					
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
RECYCLED PCC 55-99-031-QRY Created On: 08/22/17 Updated On:	Q							0-225-259-2017			0.0	7.6	30.7					
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
RECYCLED PCC 55-99-031-QRY Created On: 08/22/17 Updated On:	Q							0-225-260-2017			0.0	8.1	32.4					
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
RECYCLED PCC 55-99-031-QRY Created On: 08/31/17 Updated On:	Q							0-225-270-2017		0.0	0.0	11.8	38.2					
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
RECYCLED PCC 55-99-031-QRY Created On: 09/25/17 Updated On:	Q							0-225-276-2017		0.0	0.0	7.6	30.5					
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
RECYCLED PCC 55-99-031-QRY Created On: 10/16/17 Updated On:	Q							0-225-281-2017		0.0	0.0	8.1	32.0					
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
RECYCLED PCC 55-99-031-QRY Created On: 11/03/17 Updated On:	Q							0-225-286-2017		0.0	0.0	8.6	29.9					
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Coarse Sp. Gravity		Coarse Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
RECYCLED PCC 55-99-031-QRY Created On: 11/03/17 Updated On:	Q							0-225-287-2017		0.0	0.0	7.7	29.4					
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
RECYCLED PCC 55-99-031-QRY Created On: 01/03/18 Updated On:	Q							0-225-38-2018		0.0	0.0	13.6	40.3					
	Approved Use : CONCRETE, OGBC, Base Aggregate																	
RECYCLED PCC 55-99-031-QRY Created On: 01/04/18 Updated On:	Q							0-225-62-2018		0.0	0.0	10.0	38.1					
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
RECYCLED PCC 55-99-031-QRY Created On: 01/04/18 Updated On:	Q							0-225-63-2018			0.0	7.3	29.7					
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
RECYCLED PCC 55-99-031-QRY Created On: 01/04/18 Updated On:	Q							0-225-79-2018			0.0	8.1	38.7					
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
RECYCLED PCC 55-99-031-QRY Created On: 02/16/18 Updated On:	Q							0-225-103-2018			0.0	13.8	37.2					
	Approved Use : CONCRETE, Base Aggregate																	
RECYCLED PCC 55-99-031-QRY Created On: 03/08/18 Updated On:	Q							0-225-118-2018		0.0	0.0	13.3	38.0					
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
RECYCLED PCC 55-99-031-QRY Created On: 03/16/18 Updated On:	Q							0-225-126-2018			0.0	8.5	33.2				
RECYCLED PCC 55-99-031-QRY Created On: 03/16/18 Updated On:	Q							0-225-127-2018			0.0	6.5	27.4				
RECYCLED PCC 55-99-031-QRY Created On: 03/16/18 Updated On:	Q							0-225-128-2018			0.0	6.9	28.6				
RECYCLED PCC 55-99-031-QRY Created On: 03/23/18 Updated On:	Q							0-225-138-2018		0.0	0.0	11.8	40.0				
RECYCLED PCC 55-99-031-QRY Created On: 03/23/18 Updated On:	Q							0-225-143-2018		0.0	0.0	10.3	39.3				
RECYCLED PCC 55-99-031-QRY Created On: 03/28/18 Updated On:	Q							0-225-147-2018		0.0	0.0	6.8	26.2				
RECYCLED PCC 55-99-031-QRY Created On: 03/28/18 Updated On:	Q							0-225-148-2018		0.0	0.0	7.2	27.9				

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
RECYCLED PCC 55-99-031-QRY Created On: 03/28/18 Updated On:	Q							0-225-149-2018		0.0	0.0	8.2	37.7				
RECYCLED PCC 55-99-031-QRY Created On: 03/29/18 Updated On:	Q							0-225-153-2018			0.0	5.3	25.6				
RECYCLED PCC 55-99-031-QRY Created On: 03/29/18 Updated On:	Q							0-225-154-2018			0.0	7.0	28.6				
RECYCLED PCC 55-99-031-QRY Created On: 04/10/18 Updated On:	Q							0-225-160-2018		0.0	0.0	7.9	30.2				
RECYCLED PCC 55-99-031-QRY Created On: 04/13/18 Updated On:	Q							0-225-170-2018			0.0	10.5	36.9				
RECYCLED PCC 55-99-031-QRY Created On: 04/13/18 Updated On:	Q							0-225-171-2018			0.0	10.1	35.9				
RECYCLED PCC 55-99-031-QRY Created On: 04/13/18 Updated On:	Q							0-225-172-2018			0.0	5.2	25.8				

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
RECYCLED PCC 55-99-031-QRY Created On: 04/19/18 Updated On:	Q							0-225-173-2018	0.0	0.0	9.2	34.0					
RECYCLED PCC 55-99-031-QRY Created On: 04/19/18 Updated On:	Q							0-225-175-2018	0.0	0.0	12.3	37.4					
RECYCLED PCC 55-99-031-QRY Created On: 04/19/18 Updated On:	Q							0-225-178-2018	0.0	0.0	11.8	34.9					
RECYCLED PCC 55-99-031-QRY Created On: 04/20/18 Updated On:	Q							0-225-179-2018		0.0	6.1	27.2					
RECYCLED PCC 55-99-031-QRY Created On: 04/20/18 Updated On:	Q							0-225-181-2018		0.0	6.2	30.2					
RECYCLED PCC 55-99-031-QRY Created On: 04/25/18 Updated On:	Q							0-225-182-2018	0.0	0.0	8.3	32.1					
RECYCLED PCC 55-99-031-QRY Created On: 05/01/18 Updated On:	Q							0-225-186-2018	0.0	0.0	10.2	31.4					

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
RECYCLED PCC 55-99-031-QRY Created On: 05/01/18 Updated On:	Q							0-225-189-2018			0.0	10.4	37.6				
RECYCLED PCC 55-99-031-QRY Created On: 05/07/18 Updated On:	Q							0-225-193-2018			0.0	9.7	32.0				
RECYCLED PCC 55-99-031-QRY Created On: 05/07/18 Updated On:	Q							0-225-194-2018		0.0	0.0	10.3	35.1				
RECYCLED PCC 55-99-031-QRY Created On: 05/10/18 Updated On:	Q							0-225-200-2018		0.0	0.0	9.4	33.5				
RECYCLED PCC 55-99-031-QRY Created On: 05/11/18 Updated On:	Q							0-225-207-2018			0.0	8.6	31.3				
RECYCLED PCC 55-99-031-QRY Created On: 05/11/18 Updated On:	Q							0-225-208-2018			0.0	6.8	24.8				
RECYCLED PCC 55-99-031-QRY Created On: 06/07/18 Updated On:	Q							0-225-221-2018		0.0	0.0	11.6	34.9				

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
RECYCLED PCC 55-99-031-QRY Created On: 06/27/18 Updated On:	Q							0-225-240-2018		0.0	0.0	8.6	31.4				
RECYCLED PCC 55-99-031-QRY Created On: 07/11/18 Updated On:	Q							0-225-248-2018		0.0	0.0	6.8	28.5				
RECYCLED PCC 55-99-031-QRY Created On: 07/11/18 Updated On:	Q							0-225-249-2018		0.0	0.0	12.4	36.8				
RECYCLED PCC 55-99-031-QRY Created On: 07/23/18 Updated On:	Q							0-225-254-2018			0.0	5.6	25.6				
RECYCLED PCC 55-99-031-QRY Created On: 07/23/18 Updated On:	Q							0-225-256-2018		0.0	0.0	6.3	29.8				
RECYCLED PCC 55-99-031-QRY Created On: 07/31/18 Updated On:	Q							0-225-258-2018		0.0	0.0	9.4	31.9				
RECYCLED PCC 55-99-031-QRY Created On: 07/31/18 Updated On:	Q							0-225-259-2018		0.0	0.0	8.3	30.0				

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
RECYCLED PCC 55-99-031-QRY Created On: 08/20/18 Updated On:	Q							0-225-269-2018		0.0	0.0	9.2	29.2				
RECYCLED PCC 55-99-031-QRY Created On: 08/20/18 Updated On:	Q							0-225-272-2018		0.0	0.0	11.0	40.0				
RECYCLED PCC 55-99-031-QRY Created On: 08/24/18 Updated On:	Q							0-225-274-2018		0.0	0.0	6.1	27.5				
RECYCLED PCC 55-99-031-QRY Created On: 08/28/18 Updated On:	Q							0-225-275-2018		0.0	0.0	8.1	31.7				
RECYCLED PCC 55-99-031-QRY Created On: 08/28/18 Updated On:	Q							0-225-276-2018		0.0	0.0	7.9	30.4				
RECYCLED PCC 55-99-031-QRY Created On: 08/28/18 Updated On:	Q							0-225-277-2018		0.0	0.0	90.7	93.1				
RECYCLED PCC 55-99-031-QRY Created On: 09/06/18 Updated On:	Q							0-225-279-2018		0.0	0.0	10.7	35.7				

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
RECYCLED PCC 55-99-031-QRY Created On: 09/26/18 Updated On:	Q							0-225-281-2018		0.0	0.0	11.6	41.4				
RECYCLED PCC 55-99-031-QRY Created On: 09/26/18 Updated On:	Q							0-225-284-2018		0.0	0.0	7.1	29.7				
RECYCLED PCC 55-99-031-QRY Created On: 09/26/18 Updated On:	Q							0-225-285-2018		0.0	0.0	10.0	33.2				
RECYCLED PCC 55-99-031-QRY Created On: 10/01/18 Updated On:	Q							0-225-287-2018		0.0	0.0	10.6	37.6				
RECYCLED PCC 55-99-031-QRY Created On: 10/09/18 Updated On:	Q							0-225-289-2018		0.0	0.0	8.0	31.0				
RECYCLED PCC 55-99-031-QRY Created On: 01/07/19 Updated On:	Q							0-225-44-2019		0.0	0.0	7.8	30.7				
RECYCLED PCC 55-99-031-QRY Created On: 02/05/19 Updated On:	Q							0-225-99-2019			0.0	9.7	30.9				

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
RECYCLED PCC 55-99-031-QRY Created On: 02/05/19 Updated On:	Q							0-225-100-2019			0.0	8.0	30.8					
	Approved Use : HMA<MT, HMA>=MT, Base Aggregate																	
RECYCLED PCC 55-99-031-QRY Created On: 03/21/19 Updated On:	Q							0-225-111-2019			0.0	10.5	30.8					
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																	
RECYCLED PCC 55-99-031-QRY Created On: 03/22/19 Updated On:	Q							0-225-114-2019		0.0	0.0	8.0	32.1					
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																	
RECYCLED PCC 55-99-031-QRY Created On: 04/05/19 Updated On:	Q							0-225-127-2019			0.0	9.2	31.8					
	Approved Use : HMA<MT, HMA>=MT, Base Aggregate																	
RECYCLED PCC 55-99-031-QRY Created On: 04/10/19 Updated On:	Q							0-225-130-2019		0.0	0.0	9.9	39.2					
	Approved Use : HMA<MT, HMA>=MT, Base Aggregate																	
RECYCLED PCC 55-99-031-QRY Created On: 04/10/19 Updated On:	Q							0-225-131-2019		0.0	0.0	10.6	35.1					
	Approved Use : HMA<MT, HMA>=MT, Base Aggregate																	
RECYCLED PCC 55-99-031-QRY Created On: 04/10/19 Updated On:	Q							0-225-134-2019		0.0	0.0	7.3	30.0					
	Approved Use : HMA<MT, HMA>=MT, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
RECYCLED PCC 55-99-031-QRY Created On: 04/10/19 Updated On:	Q							0-225-135-2019		0.0	0.0	7.1	29.0				
RECYCLED PCC 55-99-031-QRY Created On: 04/10/19 Updated On:	Q							0-225-136-2019		0.0	0.0	7.0	29.7				
RECYCLED PCC 55-99-031-QRY Created On: 04/18/19 Updated On:	Q							0-225-138-2019		0.0	0.0	8.6	26.5				
RECYCLED PCC 55-99-031-QRY Created On: 04/18/19 Updated On:	Q							0-225-140-2019		0.0	0.0	5.6	26.2				
RECYCLED PCC 55-99-031-QRY Created On: 04/18/19 Updated On:	Q							0-225-141-2019		0.0	0.0	10.0	33.0				
RECYCLED PCC 55-99-031-QRY Created On: 04/18/19 Updated On:	Q							0-225-142-2019			0.0	6.9	27.1				
RECYCLED PCC 55-99-031-QRY Created On: 04/19/19 Updated On:	Q							0-225-143-2019			0.0	8.4	30.4				

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
RECYCLED PCC 55-99-031-QRY Created On: 04/19/19 Updated On:	Q							0-225-144-2019	0.0	0.0	5.3	25.7						
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																	
RECYCLED PCC 55-99-031-QRY Created On: 04/19/19 Updated On:	Q							0-225-145-2019	0.0	0.0	5.9	27.8						
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																	
RECYCLED PCC 55-99-031-QRY Created On: 04/24/19 Updated On:	Q							0-225-160-2019	0.0	0.0	6.9	28.9						
	Approved Use : HMA<MT, HMA>=MT, Base Aggregate																	
RECYCLED PCC 55-99-031-QRY Created On: 04/24/19 Updated On:	Q							0-225-161-2019	0.0	0.0	8.3	30.7						
	Approved Use : HMA<MT, HMA>=MT, Base Aggregate																	
RECYCLED PCC 55-99-031-QRY Created On: 04/24/19 Updated On:	Q							0-225-162-2019	0.0	0.0	8.9	32.6						
	Approved Use : HMA<MT, HMA>=MT, Base Aggregate																	
RECYCLED PCC 55-99-031-QRY Created On: 04/26/19 Updated On:	Q							0-225-172-2019		0.0	5.4	26.4						
	Approved Use : HMA<MT, HMA>=MT, Base Aggregate																	
RECYCLED PCC 55-99-031-QRY Created On: 04/26/19 Updated On:	Q							0-225-173-2019		0.0	5.7	25.2						
	Approved Use : HMA<MT, HMA>=MT, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Coarse Sp. Gravity		Coarse Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
RECYCLED PCC 55-99-031-QRY Created On: 05/02/19 Updated On:	Q							0-225-178-2019			0.0	8.0	34.5				
RECYCLED PCC 55-99-031-QRY Created On: 05/09/19 Updated On:	Q							0-225-184-2019		0.0	0.0	6.9	27.7				
RECYCLED PCC 55-99-031-QRY Created On: 05/13/19 Updated On:	Q							0-225-188-2019		0.0	0.0	5.6	26.8				
RECYCLED PCC 55-99-031-QRY Created On: 05/24/19 Updated On:	Q							0-225-193-2019		0.0	0.0	10.5	37.8				
RECYCLED PCC 55-99-031-QRY Created On: 05/24/19 Updated On:	Q							0-225-195-2019		0.0	0.0	9.0	33.0				
RECYCLED PCC 55-99-031-QRY Created On: 06/06/19 Updated On:	Q							0-225-208-2019		0.0	0.0	9.4	34.4				
RECYCLED PCC 55-99-031-QRY Created On: 06/07/19 Updated On:	Q							0-225-210-2019		0.0	0.0	7.1	30.3				

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
RECYCLED PCC 55-99-031-QRY Created On: 06/07/19 Updated On:	Q							0-225-211-2019		0.0	0.0	7.7	30.4				
RECYCLED PCC 55-99-031-QRY Created On: 06/07/19 Updated On:	Q							0-225-212-2019		0.0	0.0	5.9	27.9				
RECYCLED PCC 55-99-031-QRY Created On: 06/13/19 Updated On:	Q							0-225-215-2019		0.0	0.0	7.6	29.7				
RECYCLED PCC 55-99-031-QRY Created On: 06/13/19 Updated On:	Q							0-225-216-2019		0.0	0.0	9.1	35.0				
RECYCLED PCC 55-99-031-QRY Created On: 06/24/19 Updated On:	Q							0-225-226-2019		0.0	0.0		40.4				
RECYCLED PCC 55-99-031-QRY Created On: 07/16/19 Updated On:	Q							0-225-234-2019		0.0	0.0	9.6	32.3				
RECYCLED PCC 55-99-031-QRY Created On: 07/23/19 Updated On:	Q							0-225-242-2019		0.0	0.0	12.0	36.0				

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
RECYCLED PCC 55-99-031-QRY Created On: 07/23/19 Updated On:	Q							0-225-243-2019		0.0	0.0	9.6	29.6				
RECYCLED PCC 55-99-031-QRY Created On: 07/23/19 Updated On:	Q							0-225-244-2019		0.0	0.0	8.7	30.3				
RECYCLED PCC 55-99-031-QRY Created On: 07/25/19 Updated On:	Q							0-225-248-2019			0.0	10.1	32.6				
RECYCLED PCC 55-99-031-QRY Created On: 07/25/19 Updated On:	Q							0-225-253-2019		0.0	0.0	5.9	28.1				
RECYCLED PCC 55-99-031-QRY Created On: 07/31/19 Updated On:	Q							0-225-254-2019		0.0	0.0	7.6	30.6				
RECYCLED PCC 55-99-031-QRY Created On: 08/05/19 Updated On:	Q							0-225-255-2019			0.0	10.6	38.7				
RECYCLED PCC 55-99-031-QRY Created On: 08/09/19 Updated On:	Q							0-225-256-2019		0.0	0.0		43.1				

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Coarse Sp. Gravity		Coarse Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
RECYCLED PCC 55-99-031-QRY Created On: 08/09/19 Updated On:	Q							0-225-257-2019	0.0	0.0		32.6					
RECYCLED PCC 55-99-031-QRY Created On: 09/16/19 Updated On:	Q							0-225-270-2019	0.0	0.0	9.0	32.9					
RECYCLED PCC 55-99-031-QRY Created On: 09/18/19 Updated On:	Q							0-225-271-2019	0.0	0.0	6.9	29.7					
RECYCLED PCC 55-99-031-QRY Created On: 09/19/19 Updated On:	Q							0-225-273-2019	0.0	0.0	6.9	27.3					
RECYCLED PCC 55-99-031-QRY Created On: 10/10/19 Updated On:	Q							0-225-275-2019	0.0	0.0	7.8	30.8					
RECYCLED PCC 55-99-031-QRY Created On: 10/22/19 Updated On:	Q							0-225-276-2019	0.0	0.0	8.6	31.1					
RECYCLED PCC 55-99-031-QRY Created On: 10/22/19 Updated On:	Q							0-225-277-2019		0.0	4.8	25.8					

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
RECYCLED PCC 55-99-031-QRY Created On: 01/08/20 Updated On:	Q							0-225-81-2020		22.7	0.0	7.4	29.1				
RECYCLED PCC 55-99-031-QRY Created On: 01/09/20 Updated On:	Q							0-225-96-2020		39.2	0.0	13.1	36.8				
RECYCLED PCC 55-99-031-QRY Created On: 01/09/20 Updated On:	Q							0-225-97-2020		55.8	0.0	12.2	37.7				
RECYCLED PCC 55-99-031-QRY Created On: 01/30/20 Updated On:	Q							0-225-103-2020		14.6	0.0	5.6	28.1				
								Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate									
RECYCLED PCC 55-99-031-QRY Created On: 01/30/20 Updated On:	Q							0-225-105-2020		36.5	0.0	8.3	32.6				
RECYCLED PCC 55-99-031-QRY Created On: 03/09/20 Updated On:	Q							0-225-125-2020		50.0	0.0	7.5	33.6				
RECYCLED PCC 55-99-031-QRY Created On: 03/30/20 Updated On:	Q							0-225-135-2020		53.3	0.0	10.7	37.2				

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Coarse Sp. Gravity		Coarse Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
RECYCLED PCC 55-99-031-QRY Created On: 04/01/20 Updated On:	Q							0-225-138-2020		49.5	0.0	7.8	33.5				
RECYCLED PCC 55-99-031-QRY Created On: 04/08/20 Updated On:	Q						Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate	0-225-147-2020		4.7	0.0	6.9	29.6				
RECYCLED PCC 55-99-031-QRY Created On: 04/09/20 Updated On:	Q							0-225-150-2020		31.0	0.0	6.2	29.4				
RECYCLED PCC 55-99-031-QRY Created On: 04/09/20 Updated On:	Q							0-225-151-2020		24.4	0.0	6.0	26.9				
RECYCLED PCC 55-99-031-QRY Created On: 05/06/20 Updated On:	Q						Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate	0-225-168-2020		16.8	0.0	6.1	27.5				
RECYCLED PCC 55-99-031-QRY Created On: 05/19/20 Updated On:	Q							0-225-180-2020		22.5	0.0	7.7	31.5				
RECYCLED PCC 55-99-031-QRY Created On: 07/17/20 Updated On:	Q							0-225-223-2020		40.9	0.0	7.3	30.3				

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
RECYCLED PCC 55-99-031-QRY Created On: 08/12/20 Updated On:	Q							0-225-232-2020		44.1	0.0	8.4	29.7				
RECYCLED PCC 55-99-031-QRY Created On: 01/06/21 Updated On:	Q							0-225-111-2021		10.7	0.0	8.1	31.3	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate			
RECYCLED PCC 55-99-031-QRY Created On: 01/08/21 Updated On:	Q							0-225-119-2021		31.5	0.0	7.5	30.5				
RECYCLED PCC 55-99-031-QRY Created On: 04/13/21 Updated On:	Q							0-225-180-2021		41.0	0.0	10.2	35.4				
RECYCLED PCC 55-99-031-QRY Created On: 04/13/21 Updated On:	Q							0-225-181-2021		25.3	0.0	8.2	35.4				
RECYCLED PCC 55-99-031-QRY Created On: 04/30/21 Updated On:	Q							0-225-192-2021		21.1	0.0	9.3	32.5				
RECYCLED PCC 55-99-031-QRY Created On: 07/07/21 Updated On:	Q							0-225-242-2021		30.7	0.0	10.0	35.7				

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Coarse Sp. Gravity		Coarse Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
RECYCLED PCC 55-99-031-QRY Created On: 07/19/21 Updated On:	Q							0-225-248-2021		16.2	0.0	9.1	34.5					
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																	
RECYCLED PCC 55-99-031-QRY Created On: 01/04/22 Updated On:	Q							0-225-61-2022		16.5	0.0	7.5	29.3					
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																	
RECYCLED PCC 55-99-031-QRY Created On: 01/04/22 Updated On:	Q							0-225-62-2022		24.7	0.0	9.9	35.6					
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																	
RECYCLED PCC 55-99-031-QRY Created On: 01/04/22 Updated On:	Q							0-225-94-2022	16.7	11.8	0.0	7.0	29.9					
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																	
RECYCLED PCC 55-99-031-QRY Created On: 03/17/22 Updated On:	Q							0-225-145-2022		25.6	0.0	11.0	33.8					
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																	
RECYCLED PCC 55-99-031-QRY Created On: 03/17/22 Updated On:	Q							0-225-151-2022		25.1	0.0	10.7	35.8					
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																	
RECYCLED PCC 55-99-031-QRY Created On: 04/19/22 Updated On:	Q							0-225-178-2022		30.1	0.0	10.2	34.7					
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
RECYCLED PCC 55-99-031-QRY Created On: 04/19/22 Updated On:	Q							0-225-179-2022	44.3	0.0	12.7	37.7					
RECYCLED PCC 55-99-031-QRY Created On: 05/03/22 Updated On:	Q							0-225-199-2022	55.3	0.0	11.6	41.7					
RECYCLED PCC 55-99-031-QRY Created On: 02/06/23 Updated On:	Q							0-225-139-2023	35.3	0.0	7.7	31.0					
RECYCLED PCC 55-99-031-QRY Created On: 02/14/23 Updated On:	Q							0-225-143-2023	35.1	0.0	11.6	38.1					
RECYCLED PCC 55-99-031-QRY Created On: 02/14/23 Updated On:	Q							0-225-144-2023	0.0	61.6	12.9	40.9					
RECYCLED PCC 55-99-031-QRY Created On: 02/27/23 Updated On:	Q							0-225-146-2023	41.2	0.0	8.4	28.1					
RECYCLED PCC 55-99-031-QRY Created On: 02/27/23 Updated On:	Q							0-225-149-2023	40.0	0.0	9.0	30.5					

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
RECYCLED PCC 55-99-031-QRY Created On: 02/28/23 Updated On:	Q							0-225-152-2023		36.3	0.0	9.0	32.8				
RECYCLED PCC 55-99-031-QRY Created On: 03/13/23 Updated On:	Q						Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate	0-225-168-2023		18.2	0.0	9.5	32.9				
RECYCLED PCC 55-99-031-QRY Created On: 03/20/23 Updated On:	Q							0-225-169-2023		34.0	0.0	8.0	32.2				
RECYCLED PCC 55-99-031-QRY Created On: 04/04/23 Updated On:	Q							0-225-183-2023		30.5	0.0	10.3	32.7				
RECYCLED PCC 55-99-031-QRY Created On: 04/10/23 Updated On:	Q							0-225-191-2023		49.1	0.0	10.7	37.9				
RECYCLED PCC 55-99-031-QRY Created On: 04/20/23 Updated On:	Q						Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate	0-225-201-2023		11.8	0.0	8.1	31.5				
RECYCLED PCC 55-99-031-QRY Created On: 05/01/23 Updated On:	Q							0-225-210-2023	23.3	39.0	0.0	7.7	32.6	2.380	2.464	3.526	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Coarse Sp. Gravity		Coarse Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
RECYCLED PCC 55-99-031-QRY Created On: 05/01/23 Updated On:	Q							0-225-212-2023		55.7	0.0	8.4	31.2	2.404	2.487	3.462	
RECYCLED PCC 55-99-031-QRY Created On: 05/09/23 Updated On:	Q							0-225-215-2023		33.6	0.0	9.3	35.7				
RECYCLED PCC 55-99-031-QRY Created On: 05/22/23 Updated On:	Q							0-225-222-2023		40.0	0.0	8.8	34.3				
RECYCLED PCC 55-99-031-QRY Created On: 05/22/23 Updated On:	Q							0-225-223-2023		43.6	0.0	9.3	33.5				
RECYCLED PCC 55-99-031-QRY Created On: 06/14/23 Updated On:	Q							0-225-232-2023		21.6	0.0	8.5	30.0				
RECYCLED PCC 55-99-031-QRY Created On: 01/02/24 Updated On:	Q							0-225-95-2024		16.0	0.0	6.9	30.2				
RECYCLED PCC 55-99-031-QRY Created On: 01/02/24 Updated On:	Q							0-225-125-2024		19.0	0.0	8.7	33.1				

Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
RECYCLED PCC 55-99-031-QRY Created On: 02/28/24 Updated On:	Q							0-225-171-2024		36.6	0.0	10.7	34.0				
RECYCLED PCC 55-99-031-QRY Created On: 03/13/24 Updated On:	Q							0-225-199-2024		19.7	0.0	8.9	30.3				
RECYCLED PCC 55-99-031-QRY Created On: 03/27/24 Updated On:	Q						Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate	0-225-216-2024		0.7	0.0	4.5	21.9				
RECYCLED PCC 55-99-031-QRY Created On: 04/15/24 Updated On:	Q							0-225-224-2024		27.0	0.0	9.6	32.5				
RECYCLED PCC 55-99-031-QRY Created On: 04/15/24 Updated On:	Q						Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate	0-225-226-2024		9.5	0.0	6.7	28.5				
* RED ROCK GRANITE 55-37-063-QRY Created On: 07/01/21 Updated On:	Q	N	NW	19	27N	6E	Marathon	0-225-238-2021	0.0	0.0	2.2	10.7	44.0	2.594	2.613	0.722	
REEDS CORNER 55-20-039-PIT Created On: 01/16/15 Updated On:	P	E	NW	12	15N	14E	Fond Du Lac	0-225-67-2015		0.0	3.0	7.0	30.3	2.751	2.785	1.215	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
REEDS CORNER 55-20-039-PIT Created On: 05/19/20 Updated On:	P	E	NW	12	15N	14E	Fond Du Lac	0-225-181-2020	0.0	0.0	4.3	5.5	25.8	2.774	2.801	0.973	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
* REESE 55-36-034-PIT Created On: 06/26/19 Updated On:	P	SW	SW	22	17N	21E	Manitowoc	0-225-228-2019	1.1	2.2	0.8	5.4	29.4	2.753	2.776	0.833	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
REESMAN CO. - BOLTON 55-64-020-PIT Created On: 02/16/18 Updated On:	P		SW	4	3N	18E	Walworth	0-225-106-2018	1.0	0.0	0.2	5.1	27.2	2.678	2.714	1.341	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
REESMAN CO. - BOLTON 55-64-020-PIT Created On: 01/19/23 Updated On:	P		SW	4	3N	18E	Walworth	0-225-126-2023	0.7	0.0	4.4	5.1	24.9	2.682	2.719	1.366	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
REESMAN-HUGHES PIT 55-51-059-PIT Created On: 06/26/23 Updated On:	P	NW	SW	5	2N	19E	Racine	0-225-235-2023	0.7	17.6	3.0	6.4	23.6	2.629	2.689	2.274	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
REPROCESSED MATERIAL 55-99-033-PIT Created On: 01/08/20 Updated On:	P							0-225-76-2020		0.0	0.0	6.4	26.1				
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																
REPROCESSED MATERIAL 55-99-033-PIT Created On: 01/08/20 Updated On:	P							0-225-79-2020		0.0	0.0	5.9	24.1				
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
REPROCESSED MATERIAL 55-99-033-PIT Created On: 01/09/20 Updated On:	P							0-225-82-2020		0.0	0.0	8.0	30.2					
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																	
REPROCESSED MATERIAL 55-99-033-PIT Created On: 01/30/20 Updated On:	P							0-225-104-2020		0.0	0.0	5.9	26.5					
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																	
REPROCESSED MATERIAL 55-99-033-PIT Created On: 04/01/20 Updated On:	P							0-225-137-2020		0.0	0.0	8.2	34.0					
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																	
REPROCESSED MATERIAL 55-99-033-PIT Created On: 04/09/20 Updated On:	P							0-225-149-2020			0.0	8.9	32.1					
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																	
REPROCESSED MATERIAL 55-99-033-PIT Created On: 04/22/20 Updated On:	P							0-225-155-2020		0.0	0.0	7.5	27.8					
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																	
REPROCESSED MATERIAL 55-99-033-PIT Created On: 05/04/20 Updated On:	P							0-225-166-2020		0.0	0.0	5.8	25.1					
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																	
REPROCESSED MATERIAL 55-99-033-PIT Created On: 05/06/20 Updated On:	P							0-225-167-2020		18.8	0.0	8.0	30.3					

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
REPROCESSED MATERIAL 55-99-033-PIT Created On: 05/06/20 Updated On:	P							0-225-169-2020		21.7	0.0	8.6	31.1				
REPROCESSED MATERIAL 55-99-033-PIT Created On: 05/06/20 Updated On:	P							0-225-170-2020		11.4	0.0	8.0	31.9				
REPROCESSED MATERIAL 55-99-033-PIT Created On: 05/07/20 Updated On:	P							0-225-173-2020		0.0	0.0	7.3	29.5				
REPROCESSED MATERIAL 55-99-033-PIT Created On: 05/12/20 Updated On:	P							0-225-177-2020		0.0	0.0	9.2	27.8				
REPROCESSED MATERIAL 55-99-033-PIT Created On: 05/21/20 Updated On:	P							0-225-182-2020			0.0	5.5	24.9				
REPROCESSED MATERIAL 55-99-033-PIT Created On: 06/09/20 Updated On:	P							0-225-191-2020		0.0	0.0	6.8	29.2				
REPROCESSED MATERIAL 55-99-033-PIT Created On: 06/22/20 Updated On:	P							0-225-199-2020		0.0	0.0	5.9	27.7				

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
REPROCESSED MATERIAL 55-99-033-PIT Created On: 07/15/20 Updated On:	P							0-225-215-2020		0.0	0.0	5.2	23.4					
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																	
REPROCESSED MATERIAL 55-99-033-PIT Created On: 07/23/20 Updated On:	P							0-225-226-2020		0.0	0.0	7.8	30.3					
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																	
REPROCESSED MATERIAL 55-99-033-PIT Created On: 07/31/20 Updated On:	P							0-225-228-2020		34.7	0.0	7.9	29.3					
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																	
REPROCESSED MATERIAL 55-99-033-PIT Created On: 08/04/20 Updated On:	P							0-225-229-2020		0.0	0.0		30.4					
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																	
REPROCESSED MATERIAL 55-99-033-PIT Created On: 08/12/20 Updated On:	P							0-225-233-2020			0.0	6.8	27.1					
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																	
REPROCESSED MATERIAL 55-99-033-PIT Created On: 08/27/20 Updated On:	P							0-225-237-2020		0.0	0.0	5.7	25.7					
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																	
REPROCESSED MATERIAL 55-99-033-PIT Created On: 08/31/20 Updated On:	P							0-225-238-2020		0.0	0.0	6.0	27.1					
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
REPROCESSED MATERIAL 55-99-033-PIT Created On: 08/31/20 Updated On:	P							0-225-239-2020		26.6	8.5	7.2	27.4				
REPROCESSED MATERIAL 55-99-033-PIT Created On: 01/04/21 Updated On:	P							0-225-7-2021		0.0	0.0	7.4	30.7				
REPROCESSED MATERIAL 55-99-033-PIT Created On: 01/05/21 Updated On:	P							0-225-88-2021		17.8	0.0	11.0	35.2				
REPROCESSED MATERIAL 55-99-033-PIT Created On: 02/08/21 Updated On:	P							0-225-124-2021		15.5	0.0	7.0	27.5				
REPROCESSED MATERIAL 55-99-033-PIT Created On: 02/08/21 Updated On:	P							0-225-125-2021		19.6	0.0	7.4	28.3				
REPROCESSED MATERIAL 55-99-033-PIT Created On: 03/24/21 Updated On:	P							0-225-156-2021			0.0	7.1	29.8				
REPROCESSED MATERIAL 55-99-033-PIT Created On: 04/01/21 Updated On:	P							0-225-168-2021		29.5	0.0	7.5	31.2				

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
REPROCESSED MATERIAL 55-99-033-PIT Created On: 04/19/21 Updated On:	P							0-225-185-2021		34.5	0.0	7.4	29.4				
REPROCESSED MATERIAL 55-99-033-PIT Created On: 04/19/21 Updated On:	P							0-225-186-2021		32.3	0.0	8.3	30.5				
REPROCESSED MATERIAL 55-99-033-PIT Created On: 06/14/21 Updated On:	P						Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate	0-225-220-2021		11.1	0.0	6.9	28.7				
REPROCESSED MATERIAL 55-99-033-PIT Created On: 06/14/21 Updated On:	P						Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate	0-225-221-2021		15.7	0.0	7.3	27.9				
REPROCESSED MATERIAL 55-99-033-PIT Created On: 06/17/21 Updated On:	P						Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate	0-225-225-2021		11.8	0.0	6.9	30.6				
REPROCESSED MATERIAL 55-99-033-PIT Created On: 06/25/21 Updated On:	P							0-225-236-2021		31.9	0.0	6.2	27.2				
REPROCESSED MATERIAL 55-99-033-PIT Created On: 07/01/21 Updated On:	P						Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate	0-225-239-2021		9.8	0.0	6.5	29.2				

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
REPROCESSED MATERIAL 55-99-033-PIT Created On: 07/29/21 Updated On:	P							0-225-255-2021		5.6	0.0	7.1	28.6					
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																	
REPROCESSED MATERIAL 55-99-033-PIT Created On: 08/11/21 Updated On:	P							0-225-259-2021		10.8	0.0	7.2	28.6					
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																	
REPROCESSED MATERIAL 55-99-033-PIT Created On: 01/04/22 Updated On:	P							0-225-53-2022		33.4	0.0	6.6	28.1					
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																	
REPROCESSED MATERIAL 55-99-033-PIT Created On: 01/04/22 Updated On:	P							0-225-65-2022		7.5	0.0	6.7	28.3					
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																	
REPROCESSED MATERIAL 55-99-033-PIT Created On: 01/04/22 Updated On:	P							0-225-66-2022	18.5	9.2	0.0	7.3	29.7					
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																	
REPROCESSED MATERIAL 55-99-033-PIT Created On: 01/10/22 Updated On:	P							0-225-96-2022		26.6	0.0	6.0	25.7					
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																	
REPROCESSED MATERIAL 55-99-033-PIT Created On: 02/16/22 Updated On:	P							0-225-124-2022		36.1	3.0	5.2	24.8					
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
REPROCESSED MATERIAL 55-99-033-PIT Created On: 02/16/22 Updated On:	P							0-225-125-2022		37.5	0.0	7.6	27.6				
REPROCESSED MATERIAL 55-99-033-PIT Created On: 02/16/22 Updated On:	P							0-225-127-2022		24.7	0.0	7.8	28.9				
REPROCESSED MATERIAL 55-99-033-PIT Created On: 03/01/22 Updated On:	P							0-225-134-2022		21.3	0.0	10.3	31.0				
REPROCESSED MATERIAL 55-99-033-PIT Created On: 03/17/22 Updated On:	P							0-225-148-2022		37.0	0.0	9.1	33.5				
REPROCESSED MATERIAL 55-99-033-PIT Created On: 03/17/22 Updated On:	P							0-225-149-2022		30.8	0.0	9.1	33.9				
REPROCESSED MATERIAL 55-99-033-PIT Created On: 04/05/22 Updated On:	P							0-225-168-2022		26.0	0.0	6.4	26.7				
REPROCESSED MATERIAL 55-99-033-PIT Created On: 04/05/22 Updated On:	P							0-225-171-2022		36.2	0.0	8.9	32.3				

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
REPROCESSED MATERIAL 55-99-033-PIT Created On: 04/28/22 Updated On:	P							0-225-188-2022		24.8	0.0	5.7	26.1				
REPROCESSED MATERIAL 55-99-033-PIT Created On: 04/28/22 Updated On:	P							0-225-190-2022	7.2	20.1	0.0	6.9	29.9				
REPROCESSED MATERIAL 55-99-033-PIT Created On: 05/03/22 Updated On:	P							0-225-195-2022		32.8	0.0	7.1	27.0				
REPROCESSED MATERIAL 55-99-033-PIT Created On: 05/03/22 Updated On:	P							0-225-196-2022		41.5	0.0	7.3	28.0				
REPROCESSED MATERIAL 55-99-033-PIT Created On: 05/03/22 Updated On:	P							0-225-197-2022		18.0	0.0	7.0	27.8				
REPROCESSED MATERIAL 55-99-033-PIT Created On: 05/17/22 Updated On:	P							0-225-209-2022		15.4	0.0	99.7	99.4				
REPROCESSED MATERIAL 55-99-033-PIT Created On: 06/01/22 Updated On:	P							0-225-212-2022		40.6	0.0	8.6	31.3				

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
REPROCESSED MATERIAL 55-99-033-PIT Created On: 06/06/22 Updated On:	P							0-225-215-2022		0.0	0.0	6.9	29.5					
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																	
REPROCESSED MATERIAL 55-99-033-PIT Created On: 06/16/22 Updated On:	P							0-225-229-2022		27.7	0.0	7.9	30.9					
REPROCESSED MATERIAL 55-99-033-PIT Created On: 07/26/22 Updated On:	P							0-225-249-2022		27.9	0.0	8.0	31.5					
REPROCESSED MATERIAL 55-99-033-PIT Created On: 08/17/22 Updated On:	P							0-225-252-2022		40.8	0.0	9.2	32.5					
REPROCESSED MATERIAL 55-99-033-PIT Created On: 10/24/22 Updated On:	P							0-225-259-2022		33.3	0.0	13.4	33.0					
REPROCESSED MATERIAL 55-99-033-PIT Created On: 01/03/23 Updated On:	P							0-225-40-2023		15.8	0.0	7.2	29.4					
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																	
REPROCESSED MATERIAL 55-99-033-PIT Created On: 01/03/23 Updated On:	P							0-225-77-2023	14.7	8.1	0.0	6.2	29.4					
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
REPROCESSED MATERIAL 55-99-033-PIT Created On: 02/06/23 Updated On:	P							0-225-136-2023		26.8	0.0	6.6	27.2				
REPROCESSED MATERIAL 55-99-033-PIT Created On: 02/06/23 Updated On:	P							0-225-137-2023		30.1	0.0	6.9	28.4				
REPROCESSED MATERIAL 55-99-033-PIT Created On: 02/28/23 Updated On:	P							0-225-153-2023		24.4	0.0	9.6	32.5				
REPROCESSED MATERIAL 55-99-033-PIT Created On: 02/28/23 Updated On:	P							0-225-154-2023		39.7	0.0	8.4	32.0				
REPROCESSED MATERIAL 55-99-033-PIT Created On: 02/28/23 Updated On:	P							0-225-155-2023		38.9	0.0	6.9	30.5				
REPROCESSED MATERIAL 55-99-033-PIT Created On: 02/28/23 Updated On:	P							0-225-156-2023		28.5	0.0	9.0	30.2				
REPROCESSED MATERIAL 55-99-033-PIT Created On: 02/28/23 Updated On:	P							0-225-158-2023		38.3	0.0	7.9	31.8				

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
REPROCESSED MATERIAL 55-99-033-PIT Created On: 03/06/23 Updated On:	P							0-225-164-2023		37.1	0.0	8.5	33.0				
REPROCESSED MATERIAL 55-99-033-PIT Created On: 03/06/23 Updated On:	P							0-225-165-2023		28.7	0.0	6.2	27.4				
REPROCESSED MATERIAL 55-99-033-PIT Created On: 03/06/23 Updated On:	P							0-225-166-2023		29.9	0.0	6.7	26.9				
REPROCESSED MATERIAL 55-99-033-PIT Created On: 04/04/23 Updated On:	P							0-225-179-2023		10.5	0.0	6.9	27.2				
								Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate									
REPROCESSED MATERIAL 55-99-033-PIT Created On: 04/05/23 Updated On:	P							0-225-184-2023		40.5	0.0	6.4	28.0				
REPROCESSED MATERIAL 55-99-033-PIT Created On: 04/05/23 Updated On:	P							0-225-185-2023		51.3	0.0	6.6	28.9				
REPROCESSED MATERIAL 55-99-033-PIT Created On: 04/10/23 Updated On:	P							0-225-194-2023		29.8	0.0	5.5	27.0				

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
REPROCESSED MATERIAL 55-99-033-PIT Created On: 04/20/23 Updated On:	P							0-225-200-2023		24.7	0.0	7.1	31.5				
REPROCESSED MATERIAL 55-99-033-PIT Created On: 04/24/23 Updated On:	P							0-225-204-2023		35.5	0.0	8.7	30.0				
REPROCESSED MATERIAL 55-99-033-PIT Created On: 05/01/23 Updated On:	P							0-225-211-2023		24.3	0.0	6.1	28.2				
REPROCESSED MATERIAL 55-99-033-PIT Created On: 05/01/23 Updated On:	P							0-225-213-2023	9.2	33.5	0.0	8.6	33.5	2.401	2.487	3.588	
REPROCESSED MATERIAL 55-99-033-PIT Created On: 06/12/23 Updated On:	P							0-225-229-2023		38.3	0.5	8.5	32.2				
REPROCESSED MATERIAL 55-99-033-PIT Created On: 06/12/23 Updated On:	P							0-225-230-2023		33.5	0.0	6.1	27.1				
REPROCESSED MATERIAL 55-99-033-PIT Created On: 06/14/23 Updated On:	P							0-225-231-2023		16.3	0.0	7.6	28.6				

Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
REPROCESSED MATERIAL 55-99-033-PIT Created On: 06/26/23 Updated On:	P							0-225-233-2023	14.4	28.9	0.0	10.1	30.9	2.442	2.499	2.354	
REPROCESSED MATERIAL 55-99-033-PIT Created On: 06/26/23 Updated On:	P							0-225-234-2023		24.1	2.1	6.5	26.8				
REPROCESSED MATERIAL 55-99-033-PIT Created On: 08/22/23 Updated On:	P							0-225-245-2023	4.5	17.0	0.5	6.8	15.3	2.411	2.476	2.706	
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
REPROCESSED MATERIAL 55-99-033-PIT Created On: 08/22/23 Updated On:	P							0-225-246-2023	9.1	21.2	0.6	7.1	40.2	2.382	2.457	3.134	
REPROCESSED MATERIAL 55-99-033-PIT Created On: 01/02/24 Updated On:	P							0-225-4-2024		22.3	0.0	6.4	29.4				
REPROCESSED MATERIAL 55-99-033-PIT Created On: 01/02/24 Updated On:	P							0-225-126-2024		19.0	0.0	10.1	30.2				
REPROCESSED MATERIAL 55-99-033-PIT Created On: 01/02/24 Updated On:	P							0-225-127-2024		38.3	0.0	6.2	30.2				

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
REPROCESSED MATERIAL 55-99-033-PIT Created On: 01/02/24 Updated On:	P							0-225-128-2024		26.5	0.0	5.8	26.8				
REPROCESSED MATERIAL 55-99-033-PIT Created On: 01/04/24 Updated On:	P							0-225-138-2024		21.3	0.0	8.5	33.4				
REPROCESSED MATERIAL 55-99-033-PIT Created On: 01/29/24 Updated On:	P							0-225-159-2024		31.0	0.0	10.3	33.9				
REPROCESSED MATERIAL 55-99-033-PIT Created On: 01/29/24 Updated On:	P							0-225-161-2024		24.4	0.0	6.2	26.7				
REPROCESSED MATERIAL 55-99-033-PIT Created On: 01/29/24 Updated On:	P							0-225-167-2024		17.1	0.0	9.8	31.4				
REPROCESSED MATERIAL 55-99-033-PIT Created On: 02/28/24 Updated On:	P							0-225-168-2024		31.0	0.0	9.2	31.8				
REPROCESSED MATERIAL 55-99-033-PIT Created On: 02/28/24 Updated On:	P							0-225-169-2024		22.2	0.0	7.5	31.6				

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
REPROCESSED MATERIAL 55-99-033-PIT Created On: 02/28/24 Updated On:	P							0-225-173-2024		34.4	0.0	10.1	35.4				
REPROCESSED MATERIAL 55-99-033-PIT Created On: 02/28/24 Updated On:	P							0-225-174-2024		47.0	0.0	12.0	34.6				
REPROCESSED MATERIAL 55-99-033-PIT Created On: 02/28/24 Updated On:	P							0-225-175-2024		31.3	0.0	8.2	30.8				
REPROCESSED MATERIAL 55-99-033-PIT Created On: 02/28/24 Updated On:	P							0-225-176-2024		17.7	0.0	8.2	29.5				
								Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate									
REPROCESSED MATERIAL 55-99-033-PIT Created On: 02/28/24 Updated On:	P							0-225-186-2024		33.9	0.0	6.4	28.1				
REPROCESSED MATERIAL 55-99-033-PIT Created On: 02/28/24 Updated On:	P							0-225-187-2024		28.4	0.0	6.0	25.5				
REPROCESSED MATERIAL 55-99-033-PIT Created On: 03/13/24 Updated On:	P							0-225-203-2024		16.3	0.0	4.9	26.1				
								Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate									

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
REPROCESSED MATERIAL 55-99-033-PIT Created On: 03/13/24 Updated On:	P							0-225-204-2024		17.9	0.0	5.5	26.2					
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																	
REPROCESSED MATERIAL 55-99-033-PIT Created On: 03/13/24 Updated On:	P							0-225-205-2024		30.0	0.0	6.5	27.1					
REPROCESSED MATERIAL 55-99-033-PIT Created On: 03/13/24 Updated On:	P							0-225-206-2024		33.7	0.0	8.9	33.0					
REPROCESSED MATERIAL 55-99-033-PIT Created On: 03/27/24 Updated On:	P							0-225-213-2024		33.7	0.0	6.0	26.6					
REPROCESSED MATERIAL 55-99-033-PIT Created On: 03/27/24 Updated On:	P							0-225-215-2024		0.6	0.0	4.4	20.8					
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																	
REPROCESSED MATERIAL 55-99-033-PIT Created On: 04/15/24 Updated On:	P							0-225-227-2024		8.4	0.0	5.5	23.8					
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																	
RESCH 55-37-066-PIT Created On: 01/05/17 Updated On:	P	NW	NW	1	29N	10E	Marathon	0-225-16-2017		0.0	2.8	8.3	32.8	2.651	2.672	0.760		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Coarse Sp. Gravity		Coarse Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
RESCH 55-37-066-PIT Created On: 05/17/22 Updated On:	P	NW	NW	1	29N	10E	Marathon	0-225-202-2022	0.0	0.0	2.8	8.7	33.5	2.636	2.663	1.047	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
REVELS QUARRY 55-41-018-QRY Created On: 04/10/14 Updated On:	Q	NW	SE	1	16N	3W	Monroe	0-225-121-2014	0.2	0.0	9.2	13.9	44.2	2.523	2.604	3.227	
	Approved Use : CONCRETE, OGBC, Base Aggregate																
REVELS QUARRY 55-41-018-QRY Created On: 04/25/17 Updated On:	Q	NW	SE	1	16N	3W	Monroe	0-225-155-2017	0.6	0.0	7.0	12.0	42.7	2.547	2.624	3.030	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
REVELS QUARRY 55-41-018-QRY Created On: 02/13/20 Updated On:	Q	NW	SE	1	16N	3W	Monroe	0-225-115-2020	0.0	0.0	3.2	12.9	44.7	2.558	2.631	2.866	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
REVELS QUARRY 55-41-018-QRY Created On: 04/10/23 Updated On:	Q	NW	SE	1	16N	3W	Monroe	0-225-193-2023	2.9	3.5	8.3	11.2	41.9	2.580	2.645	2.540	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
RICHMOND 55-64-035-PIT Created On: 01/12/16 Updated On:	P	NW	NW	15	3N	15E	Walworth	0-225-58-2016	2.4	0.0	1.6	5.2	25.2	2.697	2.736	1.466	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
RICHMOND 55-64-035-PIT Created On: 01/04/21 Updated On:	P	NW	NW	15	3N	15E	Walworth	0-225-10-2021	0.4	3.4	2.3	5.3	26.2	2.696	2.731	1.293	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
* RIDGESTONE 55-24-015-QRY Created On: 10/14/16 Updated On:	Q	SW	SE	15	17N	13E	Green Lake	0-225-270-2016	0.9	2.9	1.3	9.5	37.8	2.672	2.719	1.778	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
* RIDGESTONE 55-24-015-QRY Created On: 05/24/19 Updated On:	Q	SW	SE	15	17N	13E	Green Lake	0-225-200-2019	0.1	9.3	2.1	10.1	38.9	2.686	2.730	1.634	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
RIGGENBERG 55-13-016-QRY Created On: 10/03/22 Updated On:	Q		NW	23	6N	7E	Dane	0-225-256-2022	0.5	11.6	4.4	7.1	32.4	2.653	2.708	2.068	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
RILEY 55-01-007-PIT Created On: 07/10/14 Updated On:	P	NW	SW	19	14N	7E	Adams	0-225-215-2014		0.0	1.1	5.9	25.5	2.777	2.808	1.092	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
RILEY 55-01-007-PIT Created On: 05/01/15 Updated On:	P	NW	SW	19	14N	7E	Adams	0-225-141-2015		0.0	2.8	7.5	28.9	2.819	2.846	0.969	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
RILEY 55-01-007-PIT Created On: 04/28/22 Updated On:	P	NW	SW	19	14N	7E	Adams	0-225-192-2022	0.1	0.0	0.6	6.2	25.7	2.770	2.803	1.188	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
RIO AGGREGATE PRODUCTS 55-11-020-QRY Created On: 02/09/22 Updated On:	Q	NW	SE	32	12N	11E	Columbia	0-225-118-2022	0.8	2.4	3.1	8.1	35.2	2.617	2.675	2.203	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
* RIPP 55-13-076-QRY Created On: 03/19/15 Updated On:	Q	NW	NW	16	9N	9E	Dane	0-225-99-2015	2.8	3.7	3.2	10.3	36.5	2.555	2.629	2.921		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
* RIPP 55-13-076-QRY Created On: 01/03/18 Updated On:	Q	NW	NW	16	9N	9E	Dane	0-225-23-2018	2.8	2.3	3.1	7.9	31.9	2.575	2.647	2.813		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
* RIPP 55-13-076-QRY Created On: 01/05/21 Updated On:	Q	NW	NW	16	9N	9E	Dane	0-225-98-2021	2.7	3.4	3.7	9.3	36.5	2.543	2.609	2.630		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
RISNER 55-38-029-PIT Created On: 06/13/22 Updated On:	P	S	SW	16	30N	20E	Marinette	0-225-225-2022	1.2	0.0	0.6	6.0	26.4	2.711	2.741	1.083		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
RIVARD 55-55-012-QRY Created On: 01/12/15 Updated On:	Q	SE	NE	12	30N	20W	St. Croix	0-225-63-2015		0.0	10.9	12.2	39.7	2.522	2.611	3.564		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
RIVARD 55-55-012-QRY Created On: 01/03/18 Updated On:	Q	SE	NE	12	30N	20W	St. Croix	0-225-33-2018	1.2	0.0	4.1	9.9	35.4	2.562	2.639	3.018		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
RIVARD 55-55-012-QRY Created On: 01/05/21 Updated On:	Q	SE	NE	12	30N	20W	St. Croix	0-225-74-2021	1.4	0.0	0.8	7.8	33.9	2.535	2.605	2.738		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
RIVARD 55-55-012-QRY Created On: 01/02/24 Updated On:	Q	SE	NE	12	30N	20W	St. Croix	0-225-78-2024	2.2	5.6	5.1	8.7	29.9	2.607	2.665	2.246		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
* RIVER 55-37-069-PIT Created On: 06/19/14 Updated On:	P	NW	SE	9	27N	7E	Marathon	0-225-201-2014		0.0	1.1	3.8	18.9	2.634	2.661	1.031		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
* RIVER 55-37-069-PIT Created On: 04/19/19 Updated On:	P	NW	SE	9	27N	7E	Marathon	0-225-152-2019	0.6	0.0	1.0	4.0	19.0	2.634	2.662	1.062		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
RIVER BEND 55-43-020-PIT Created On: 06/13/18 Updated On:	P			22	36N	9E	Oneida	0-225-229-2018	0.0	0.0	1.1	5.1	22.6	2.730	2.749	0.698		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
RIVER BEND 55-43-020-PIT Created On: 01/19/23 Updated On:	P			22	36N	9E	Oneida	0-225-125-2023	0.0	0.0	1.7	4.6	21.4	2.705	2.726	0.774		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
RIVERVIEW 55-38-046-PIT Created On: 06/13/22 Updated On:	P	SW	SW	18	31N	21E	Marinette	0-225-224-2022	0.5	0.0	2.5	4.6	24.8	2.719	2.743	0.897		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
RLAM (RIPON LIME & 55-20-035-QRY Created On: 06/05/14 Updated On:	Q	SW	NW	20	16N	14E	Fond Du Lac	0-225-182-2014		6.6	1.4	9.1	34.4	2.685	2.735	1.871		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
RLAM (RIPON LIME & 55-20-035-QRY Created On: 02/06/23 Updated On:	Q	SW	NW	20	16N	14E	Fond Du Lac	0-225-135-2023	0.2	13.7	5.9	7.7	32.3	2.702	2.744	1.525	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
ROBERTSON 27-00-014-PIT Created On: 03/16/16 Updated On:	P	NW	SW	11	52N	17W	St Louis	0-225-98-2016		0.6	0.4	2.3	13.4	2.753	2.781	1.035	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
ROBERTSON 27-00-014-PIT Created On: 04/19/21 Updated On:	P	NW	SW	11	52N	17W	St Louis	0-225-184-2021	2.0	1.3	1.6	4.2	19.2	2.797	2.820	0.837	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
ROCK SPRINGS 55-56-024-QRY Created On: 04/17/15 Updated On:	Q		SW	28	12N	5E	Sauk	0-225-127-2015		0.0	0.1	4.0	19.4	2.641	2.649	0.302	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
ROCK SPRINGS 55-56-024-QRY Created On: 02/09/18 Updated On:	Q		SW	28	12N	5E	Sauk	0-225-95-2018	0.2	0.0	0.4	5.6	23.8	2.650	2.658	0.313	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
ROCK SPRINGS 55-56-024-QRY Created On: 01/05/21 Updated On:	Q		SW	28	12N	5E	Sauk	0-225-62-2021	0.1	0.2	0.4	5.1	22.2	2.656	2.666	0.351	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
ROCK SPRINGS 55-56-024-QRY Created On: 01/02/24 Updated On:	Q		SW	28	12N	5E	Sauk	0-225-124-2024	0.0	0.5	0.3	5.2	22.5	2.657	2.664	0.273	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
ROCKLAND QUARRY 55-05-023-QRY Created On: 04/03/14 Updated On:	Q	SE	NE	12	22N	20E	Brown	0-225-116-2014	3.3	1.9	2.0	6.1	27.0	2.707	2.749	1.541		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
ROCKLAND QUARRY 55-05-023-QRY Created On: 02/03/17 Updated On:	Q	SE	NE	12	22N	20E	Brown	0-225-61-2017	1.8	5.0	5.6	9.1	33.6	2.680	2.731	1.897		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
ROCKLAND QUARRY 55-05-023-QRY Created On: 01/02/20 Updated On:	Q	SE	NE	12	22N	20E	Brown	0-225-4-2020	0.5	1.9	0.7	5.6	26.9	2.735	2.767	1.163		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
ROCKLAND QUARRY 55-05-023-QRY Created On: 01/03/23 Updated On:	Q	SE	NE	12	22N	20E	Brown	0-225-75-2023	1.5	1.5	1.5	6.3	28.1	2.709	2.747	1.416		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
ROCKWELL LIMESTONE 55-36-035-QRY Created On: 04/13/16 Updated On:	Q			36	20N	23E	Manitowoc	0-225-146-2016		0.0	2.0	12.6	41.7	2.693	2.735	1.577		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
ROCKWELL LIMESTONE 55-36-035-QRY Created On: 04/19/19 Updated On:	Q			36	20N	23E	Manitowoc	0-225-148-2019		0.0	2.9	12.7	42.1	2.692	2.739	1.722		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
ROCKWELL LIMESTONE 55-36-035-QRY Created On: 03/07/22 Updated On:	Q			36	20N	23E	Manitowoc	0-225-137-2022	0.0	0.0	3.0	9.6	32.0	2.728	2.759	1.126		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description						Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range					County	100	500	OD	SSD	Crse	Fine
ROCKY RUN 55-43-024-PIT Created On: 04/11/18 Updated On:	P	SW	14	37N	6E	Oneida	0-225-168-2018	0.5	0.0	0.3	4.3	19.2	2.705	2.727	0.801		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
ROCKY RUN 55-43-024-PIT Created On: 01/03/23 Updated On:	P	SW	14	37N	6E	Oneida	0-225-28-2023	0.5	0.0	1.4	3.9	18.3	2.715	2.740	0.915		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
* ROGERS 17-00-013-PIT Created On: 06/14/18 Updated On:	P	SW	9	46N	2E	Winnebago II	0-225-235-2018		1.1	1.8	4.8	23.9	2.663	2.702	1.461		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
* ROGERS 17-00-013-PIT Created On: 06/03/19 Updated On:	P	SW	9	46N	2E	Winnebago II	0-225-202-2019	5.0	4.7	0.7	4.3	26.0	2.672	2.706	1.270		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
ROMANOWSKI 55-09-058-PIT Created On: 04/21/17 Updated On:	P	NW	NE	36	31N	5W	Chippewa	0-225-147-2017		0.0	2.1	4.9	21.8	2.667	2.704	1.391	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
ROMANOWSKI 55-09-058-PIT Created On: 01/10/23 Updated On:	P	NW	NE	36	31N	5W	Chippewa	0-225-106-2023	4.1	0.0	2.3	3.8	19.4	2.662	2.693	1.166	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
ROMSKOG 55-32-014-QRY Created On: 01/07/14 Updated On:	Q	NE	SE	18	17N	6W	La Crosse	0-225-47-2014		0.0	6.2	9.0	34.7	2.621	2.672	1.938	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
ROMSKOG 55-32-014-QRY Created On: 04/28/17 Updated On:	Q	NE	SE	18	17N	6W	La Crosse	0-225-162-2017		0.0	5.4	9.8	38.9	2.552	2.636	3.288		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
ROMSKOG 55-32-014-QRY Created On: 01/08/20 Updated On:	Q	NE	SE	18	17N	6W	La Crosse	0-225-64-2020	0.2	0.0	6.3	10.2	37.2	2.567	2.639	2.815		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
ROMSKOG 55-32-014-QRY Created On: 01/03/23 Updated On:	Q	NE	SE	18	17N	6W	La Crosse	0-225-24-2023	0.5	3.8	3.4	12.4	43.5	2.567	2.636	2.683		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
ROSE 55-37-071-QRY Created On: 01/06/14 Updated On:	Q	NE	NW	36	30N	8E	Marathon	0-225-31-2014		0.1	0.3	6.4	27.3	2.601	2.615	0.539		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
ROSE 55-37-071-QRY Created On: 01/05/17 Updated On:	Q	NE	NW	36	30N	8E	Marathon	0-225-39-2017		0.0	0.2	6.0	26.7	2.615	2.625	0.399		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
ROSE 55-37-071-QRY Created On: 01/03/20 Updated On:	Q	NE	NW	36	30N	8E	Marathon	0-225-14-2020	0.0	0.0	0.5	6.9	32.0	2.598	2.614	0.622		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
ROSE 55-37-071-QRY Created On: 01/03/23 Updated On:	Q	NE	NW	36	30N	8E	Marathon	0-225-19-2023	0.0	0.0	0.3	6.6	29.7	2.605	2.621	0.603		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
* ROSE SPUR 19-00-005-QRY Created On: 07/30/15 Updated On:	Q	NE	SE	27	90N	2E	Dubuque	0-225-221-2015	1.9	3.5	3.4	10.5	38.6	2.585	2.651	2.533		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
* ROSE SPUR 19-00-005-QRY Created On: 01/04/18 Updated On:	Q	NE	SE	27	90N	2E	Dubuque	0-225-69-2018	2.5	11.3	4.1	9.7	36.4	2.582	2.646	2.493		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
* ROSE SPUR 19-00-005-QRY Created On: 01/05/21 Updated On:	Q	NE	SE	27	90N	2E	Dubuque	0-225-58-2021	1.2	5.2	10.0	9.3	35.3	2.567	2.638	2.764		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
* ROSE SPUR 19-00-005-QRY Created On: 01/02/24 Updated On:	Q	NE	SE	27	90N	2E	Dubuque	0-225-28-2024	2.0	9.4	3.5	9.8	35.8	2.584	2.652	2.603		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
ROSE STONE 55-03-032-QRY Created On: 01/09/15 Updated On:	Q	SE	SE	30	35N	10W	Barron	0-225-45-2015		0.0	0.7	9.1	41.7	2.553	2.577	0.961		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
ROSE STONE 55-03-032-QRY Created On: 03/23/18 Updated On:	Q	SE	SE	30	35N	10W	Barron	0-225-135-2018		0.0	1.4	7.7	33.7	2.559	2.582	0.885		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
ROSE STONE 55-03-032-QRY Created On: 03/17/21 Updated On:	Q	SE	SE	30	35N	10W	Barron	0-225-152-2021	0.0	0.1	0.3	9.2	38.7	2.565	2.583	0.705		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Coarse Sp. Gravity		Coarse Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
ROSE STONE 55-03-032-QRY Created On: 01/04/24 Updated On:	Q	SE	SE	30	35N	10W	Barron	0-225-143-2024	0.0	0.7	1.2	12.6	45.4	2.536	2.567	1.189	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
ROSEMEYER 55-22-045-QRY Created On: 04/07/16 Updated On:	Q	SW	NW	14	3N	1W	Grant	0-225-134-2016	0.7	13.0	8.1	10.9	38.2	2.603	2.672	2.635	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
ROSEMEYER 55-22-045-QRY Created On: 01/04/19 Updated On:	Q	SW	NW	14	3N	1W	Grant	0-225-22-2019	1.8	13.7	4.9	12.2	41.3	2.601	2.667	2.505	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
ROSEMEYER 55-22-045-QRY Created On: 01/04/22 Updated On:	Q	SW	NW	14	3N	1W	Grant	0-225-47-2022	1.3	9.9	0.1	8.5	32.6	2.581	2.651	2.706	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
ROSENBAUM 55-13-078-PIT Created On: 02/17/16 Updated On:	P	SW	NE	18	5N	11E	Dane	0-225-91-2016	7.4	0.0	5.0	8.3	34.0	2.600	2.658	2.249	
	Approved Use : HMA<E-3, HMA>=E-3, Base Aggregate																
ROSENBAUM 55-13-078-PIT Created On: 06/01/22 Updated On:	P	SW	NE	18	5N	11E	Dane	0-225-211-2022	0.3	4.9	6.6	10.0	34.0	2.607	2.661	2.064	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
ROSS 55-63-017-PIT Created On: 01/02/24 Updated On:	P	NE	SW	28	41N	10E	Vilas	0-225-61-2024	1.6	0.0	2.1	4.7	20.5	2.670	2.702	1.179	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
ROUER 55-42-033-QRY Created On: 01/04/22 Updated On:	Q	NW	NE	28	29N	21E	Oconto	0-225-89-2022	0.1	6.3	5.2	6.7	31.5	2.682	2.719	1.359	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
RUBIE 19-00-007-QRY Created On: 01/04/18 Updated On:	Q		SE	6	88N	3E	Dubuque	0-225-66-2018	0.6	4.6	2.5	8.5	35.4	2.578	2.639	2.392	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
RUBIE 19-00-007-QRY Created On: 03/17/21 Updated On:	Q		SE	6	88N	3E	Dubuque	0-225-144-2021	1.1	3.5	3.7	7.6	33.0	2.614	2.670	2.141	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
RUBIE 19-00-007-QRY Created On: 01/02/24 Updated On:	Q		SE	6	88N	3E	Dubuque	0-225-30-2024	0.4	2.9	0.7	8.4	31.8	2.625	2.678	1.997	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
RUBY 55-37-072-QRY Created On: 01/06/14 Updated On:	Q	SE	NW	22	30N	7E	Marathon	0-225-30-2014		0.2	0.5	7.5	32.5	2.577	2.596	0.732	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
RUBY 55-37-072-QRY Created On: 01/05/17 Updated On:	Q	SE	NW	22	30N	7E	Marathon	0-225-38-2017		0.0	0.8	5.7	26.7	2.598	2.611	0.485	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
RUBY 55-37-072-QRY Created On: 01/03/20 Updated On:	Q	SE	NW	22	30N	7E	Marathon	0-225-13-2020		0.0	1.1	8.0	37.1	2.581	2.602	0.827	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
RUBY 55-37-072-QRY Created On: 01/03/23 Updated On:	Q	SE	NW	22	30N	7E	Marathon	0-225-18-2023	0.0	0.0	0.6	5.8	28.0	2.596	2.613	0.650	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
RUDINGER 55-20-041-QRY Created On: 01/08/15 Updated On:	Q		NW	11	14N	17E	Fond Du Lac	0-225-28-2015		0.4	1.9	8.0	34.1	2.730	2.758	1.030	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
RUDINGER 55-20-041-QRY Created On: 03/07/16 Updated On:	Q		NW	11	14N	17E	Fond Du Lac	0-225-95-2016		1.0	1.3	5.2	25.1	2.762	2.785	0.866	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
RUDINGER 55-20-041-QRY Created On: 01/04/19 Updated On:	Q		NW	11	14N	17E	Fond Du Lac	0-225-20-2019	0.7	1.5	0.9	5.7	27.2	2.760	2.786	0.950	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
RUDINGER 55-20-041-QRY Created On: 01/04/22 Updated On:	Q		NW	11	14N	17E	Fond Du Lac	0-225-21-2022	0.0	0.7	1.5	6.2	28.8	2.727	2.761	1.255	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
RUDINGER 55-20-041-QRY Created On: 01/02/24 Updated On:	Q		NW	11	14N	17E	Fond Du Lac	0-225-101-2024	0.0	0.7	0.8	5.6	27.1	2.775	2.794	0.692	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
RUEF 55-33-024-QRY Created On: 04/24/14 Updated On:	Q	SW	SE	11	2N	3E	Lafayette	0-225-143-2014	1.9	3.2	2.8	9.5	34.1	2.531	2.586	2.175	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
RUEF 55-33-024-QRY Created On: 04/06/17 Updated On:	Q	SW	SE	11	2N	3E	Lafayette	0-225-111-2017	1.9	2.4	1.5	10.1	35.5	2.591	2.657	2.532		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
RUEF 55-33-024-QRY Created On: 04/28/20 Updated On:	Q	SW	SE	11	2N	3E	Lafayette	0-225-159-2020	1.1	4.1	1.6	9.3	35.1	2.586	2.665	3.055		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
RUEF 55-33-024-QRY Created On: 01/03/23 Updated On:	Q	SW	SE	11	2N	3E	Lafayette	0-225-8-2023	0.4	4.9	4.3	10.8	38.2	2.551	2.632	3.191		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
RUFERS 55-23-020-QRY Created On: 03/08/17 Updated On:	Q			30	2N	8E	Green	0-225-77-2017	0.4	16.0	5.1	10.6	38.0	2.554	2.639	3.342		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
RUFERS 55-23-020-QRY Created On: 04/17/23 Updated On:	Q			30	2N	8E	Green	0-225-195-2023	0.6	18.1	4.6	6.4	28.8	2.582	2.658	2.934		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
* RUMPCA CTH MM 55-47-014-PIT Created On: 01/04/19 Updated On:	P	NE	SE	29	27N	19W	Pierce	0-225-8-2019	1.1	13.3	5.9	6.8	26.3	2.652	2.678	0.962		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
SAFFERT 795 55-03-034-PIT Created On: 01/06/16 Updated On:	P	SW	SW	1	34N	11W	Barron	0-225-27-2016		0.0	5.3	5.7	24.0	2.662	2.703	1.554		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Coarse Sp. Gravity		Coarse Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
SAFFERT 795 55-03-034-PIT Created On: 01/05/21 Updated On:	P	SW	SW	1	34N	11W	Barron	0-225-77-2021	0.9	3.8	5.1	4.9	20.8	2.711	2.743	1.184	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
SALZGERBER 55-22-046-QRY Created On: 01/02/14 Updated On:	Q	NE	SW	2	7N	3W	Grant	0-225-2-2014	2.6	1.8	7.3	8.3	34.6	2.612	2.673	2.320	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
SALZGERBER 55-22-046-QRY Created On: 01/05/17 Updated On:	Q	NE	SW	2	7N	3W	Grant	0-225-34-2017	3.1	4.8	5.6	9.1	37.2	2.619	2.670	1.925	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
SALZGERBER 55-22-046-QRY Created On: 01/09/20 Updated On:	Q	NE	SW	2	7N	3W	Grant	0-225-85-2020	2.8	3.8	7.1	10.2	40.5	2.603	2.659	2.124	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
SALZGERBER 55-22-046-QRY Created On: 01/03/23 Updated On:	Q	NE	SW	2	7N	3W	Grant	0-225-63-2023	1.4	5.6	1.3	11.5	39.5	2.592	2.657	2.498	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
SAMBS STONE 55-34-022-PIT Created On: 03/09/15 Updated On:	P	NW	NW	11	30N	11E	Langlade	0-225-94-2015		0.0	1.6	6.2	26.7	2.675	2.698	0.884	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
SAMBS STONE 55-34-022-PIT Created On: 01/07/20 Updated On:	P	NW	NW	11	30N	11E	Langlade	0-225-46-2020	0.0	1.6	0.5	6.9	29.4	2.687	2.706	0.724	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
SAND LAKE 55-57-023-PIT Created On: 01/25/16 Updated On:	P	NW	NW	15	38N	9W	Sawyer	0-225-78-2016		0.0	1.6	4.2	17.0	2.787	2.816	1.030		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
SAND LAKE 55-57-023-PIT Created On: 05/23/23 Updated On:	P	NW	NW	15	38N	9W	Sawyer	0-225-226-2023	1.4	0.0	0.8	4.5	19.6	2.750	2.773	0.843		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
SANICKI 55-19-012-PIT Created On: 05/13/21 Updated On:	P		SE	31	38N	17E	Florence	0-225-207-2021	0.2	0.4	0.7	4.9	21.1	2.725	2.747	0.805		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
SAXON 55-26-019-PIT Created On: 06/13/18 Updated On:	P	SW	SW	18	46N	1E	Iron	0-225-231-2018		1.0	7.5	5.5	27.2	2.617	2.680	2.440		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
SAXON 55-26-019-PIT Created On: 04/04/23 Updated On:	P	SW	SW	18	46N	1E	Iron	0-225-181-2023		0.0	14.3	5.2	21.7	2.615	2.681	2.528		
	Approved Use : Base Aggregate																	
SCHADLER 55-13-081-PIT Created On: 01/03/18 Updated On:	P	NE	SE	10	8N	6E	Dane	0-225-26-2018	2.9	3.7	3.1	8.8	34.0	2.444	2.512	2.786		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
SCHADLER 55-13-081-PIT Created On: 01/04/23 Updated On:	P	NE	SE	10	8N	6E	Dane	0-225-97-2023	6.9	0.0	3.3	8.8	34.0	2.580	2.629	1.886		
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
SCHALLOCK 55-21-018-PIT Created On: 08/03/16 Updated On:	P	SE	NE	36	36N	12E	Forest	0-225-234-2016	0.4	0.0	1.5	5.0	21.9	2.695	2.721	0.939		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
SCHALLOCK 55-21-018-PIT Created On: 01/04/21 Updated On:	P	SE	NE	36	36N	12E	Forest	0-225-13-2021	0.0	1.4	0.3	4.8	20.7	2.675	2.707	1.208		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
SCHICK 55-09-060-PIT Created On: 04/21/17 Updated On:	P	SW	NW	2	29N	8W	Chippewa	0-225-143-2017		0.0	2.4	4.9	20.6	2.688	2.720	1.163		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
SCHICK 55-09-060-PIT Created On: 01/04/22 Updated On:	P	SW	NW	2	29N	8W	Chippewa	0-225-80-2022	1.2	0.0	3.2	4.3	20.8	2.688	2.715	1.025		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
SCHILL 55-71-025-QRY Created On: 01/06/14 Updated On:	Q	NW	SW	1	23N	4E	Wood	0-225-22-2014		0.0	0.8	5.4	22.4	2.598	2.614	0.606		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
SCHILL 55-71-025-QRY Created On: 01/03/17 Updated On:	Q	NW	SW	1	23N	4E	Wood	0-225-4-2017		0.0	0.2	4.9	22.8	2.605	2.617	0.487		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
SCHILL 55-71-025-QRY Created On: 01/02/20 Updated On:	Q	NW	SW	1	23N	4E	Wood	0-225-9-2020	0.9	0.0	0.9	5.1	21.6	2.617	2.629	0.464		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
SCHILL 55-71-025-QRY Created On: 01/03/23 Updated On:	Q	NW	SW	1	23N	4E	Wood	0-225-32-2023	0.2	1.3	1.0	5.7	24.1	2.606	2.619	0.509	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
SCHMITZ 55-41-020-QRY Created On: 01/07/14 Updated On:	Q		SW	18	15N	2W	Monroe	0-225-44-2014		0.0	3.3	9.7	35.3	2.630	2.679	1.862	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
SCHMITZ 55-41-020-QRY Created On: 08/03/18 Updated On:	Q		SW	18	15N	2W	Monroe	0-225-262-2018	0.7	0.0	5.4	12.4	41.2	2.594	2.657	2.406	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
SCHMITZ 55-41-020-QRY Created On: 01/05/21 Updated On:	Q		SW	18	15N	2W	Monroe	0-225-65-2021	0.7	0.0	0.3	7.3	30.7	2.634	2.685	1.921	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
SCHMITZ 55-41-020-QRY Created On: 01/02/24 Updated On:	Q		SW	18	15N	2W	Monroe	0-225-26-2024	0.9	2.2	4.2	10.5	39.3	2.599	2.663	2.464	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
SCHMOKER 55-70-029-QRY Created On: 01/06/14 Updated On:	Q		NE	20	19N	16E	Winnebago	0-225-24-2014		5.3	7.0	5.6	25.0	2.755	2.784	1.061	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
SCHMOKER 55-70-029-QRY Created On: 01/09/15 Updated On:	Q		NE	20	19N	16E	Winnebago	0-225-47-2015		3.1	2.0	4.5	20.9	2.773	2.795	0.803	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
SCHMOKER 55-70-029-QRY Created On: 01/04/18 Updated On:	Q		NE	20	19N	16E	Winnebago	0-225-57-2018		4.0	2.1	4.7	21.5	2.771	2.796	0.877		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
SCHMOKER 55-70-029-QRY Created On: 01/05/21 Updated On:	Q		NE	20	19N	16E	Winnebago	0-225-52-2021	0.0	2.9	6.3	6.4	29.9	2.787	2.811	0.841		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
SCHMOKER 55-70-029-QRY Created On: 01/02/24 Updated On:	Q		NE	20	19N	16E	Winnebago	0-225-55-2024	0.2	5.9	7.4	6.1	25.9	2.768	2.793	0.921		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
SCHNEIDER 55-22-048-QRY Created On: 04/16/15 Updated On:	Q	NW	SE	18	4N	3W	Grant	0-225-122-2015	2.2	10.4	6.7	12.8	43.4	2.598	2.665	2.571		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
SCHNEIDER 55-22-048-QRY Created On: 07/28/17 Updated On:	Q	NW	SE	18	4N	3W	Grant	0-225-243-2017	0.3	4.2	8.3	14.4	44.3	2.599	2.667	2.610		
	Approved Use : CONCRETE, OGBC, Base Aggregate																	
SCHNEIDER 55-22-048-QRY Created On: 04/28/20 Updated On:	Q	NW	SE	18	4N	3W	Grant	0-225-161-2020	0.1	3.5	2.1	10.8	39.6	2.547	2.631	3.309		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
SCHNEIDER 55-22-048-QRY Created On: 01/03/23 Updated On:	Q	NW	SE	18	4N	3W	Grant	0-225-7-2023	0.4	4.4	7.9	13.0	42.6	2.567	2.640	2.852		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
SCHOEPP 55-13-082-QRY Created On: 03/30/18 Updated On:	Q	NE	9	7N	7E	Dane	0-225-156-2018	1.3	3.5	2.0	9.9	36.8	2.595	2.654	2.262			
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
SCHOEPP 55-13-082-QRY Created On: 06/24/19 Updated On:	Q	NE	9	7N	7E	Dane	0-225-225-2019	0.3	2.2	1.8	8.4	35.7	2.592	2.652	2.289			
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
SCHOEPP 55-13-082-QRY Created On: 03/21/23 Updated On:	Q	NE	9	7N	7E	Dane	0-225-170-2023	0.3	1.9	3.9	10.2	41.9	2.610	2.664	2.034			
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
SCHOOL HILL 55-36-036-PIT Created On: 04/17/14 Updated On:	P	NE	NW	16	17N	22E	Manitowoc	0-225-130-2014	0.5	0.0	1.3	6.4	27.3	2.761	2.783	0.812		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
SCHOOL HILL 55-36-036-PIT Created On: 04/19/19 Updated On:	P	NE	NW	16	17N	22E	Manitowoc	0-225-146-2019	0.6	2.1	0.5	7.2	29.7	2.786	2.807	0.767		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
SCHOOL HILL 55-36-036-PIT Created On: 01/02/24 Updated On:	P	NE	NW	16	17N	22E	Manitowoc	0-225-130-2024	0.0	2.0	0.7	6.4	30.1	2.785	2.806	0.764		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
SCHREINER 55-60-022-PIT Created On: 01/03/18 Updated On:	P	SE	1	32N	2E	Taylor	0-225-29-2018	0.5	0.0	1.5	4.1	18.3	2.710	2.733	0.825			
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
SCHREINER 55-60-022-PIT Created On: 01/10/23 Updated On:	P		SE	1	32N	2E	Taylor	0-225-111-2023	2.1	0.0	2.1	4.1	19.8	2.659	2.688	1.086	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
* SCHRICKER 55-65-013-PIT Created On: 02/28/14 Updated On:	P	NE	SW	4	38N	12W	Washburn	0-225-88-2014		0.0	5.7	4.1	18.9	2.680	2.721	1.527	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
* SCHRICKER 55-65-013-PIT Created On: 04/05/19 Updated On:	P	NE	SW	4	38N	12W	Washburn	0-225-126-2019	1.5	0.0	4.1	4.3	19.6	2.739	2.768	1.077	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
SCHUCKNECHT 55-56-026-QRY Created On: 09/11/14 Updated On:	Q	SW	SW	25	9N	4E	Sauk	0-225-262-2014		0.0	4.9	8.3	32.9	2.643	2.693	1.901	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
SCHUCKNECHT 55-56-026-QRY Created On: 01/03/18 Updated On:	Q	SW	SW	25	9N	4E	Sauk	0-225-10-2018	0.1	0.0	1.2	8.1	31.4	2.644	2.696	1.973	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
SCHUCKNECHT 55-56-026-QRY Created On: 01/04/21 Updated On:	Q	SW	SW	25	9N	4E	Sauk	0-225-32-2021	0.5	0.0	0.4	8.9	33.1	2.635	2.690	2.091	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
SCHUCKNECHT 55-56-026-QRY Created On: 01/02/24 Updated On:	Q	SW	SW	25	9N	4E	Sauk	0-225-21-2024	0.4	7.3	1.5	8.8	33.0	2.653	2.703	1.892	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
SCHUETZ 55-13-083-QRY Created On: 08/01/14 Updated On:	Q	SE	SW	26	6N	10E	Dane	0-225-239-2014	3.6	0.3	2.4	7.0	31.6	2.636	2.684	1.816		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
SCHUETZ 55-13-083-QRY Created On: 04/11/18 Updated On:	Q	SE	SW	26	6N	10E	Dane	0-225-164-2018	4.6	3.8	7.5	10.4	39.4	2.554	2.620	2.605		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
SCHUETZ 55-13-083-QRY Created On: 01/03/23 Updated On:	Q	SE	SW	26	6N	10E	Dane	0-225-1-2023	1.1	1.6	1.9	5.5	27.4	2.651	2.692	1.521		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
SCHWARZENBERGER 55-23-023-QRY Created On: 05/06/15 Updated On:	Q	NW	NW	5	1N	8E	Green	0-225-146-2015	2.4	7.6	13.7	12.8	44.9	2.541	2.634	3.654		
	Approved Use : Base Aggregate																	
SCHWARZENBERGER 55-23-023-QRY Created On: 04/25/17 Updated On:	Q	NW	NW	5	1N	8E	Green	0-225-158-2017	0.4	6.7	10.1	10.7	39.9	2.598	2.674	2.921		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
SCHWARZENBERGER 55-23-023-QRY Created On: 02/12/20 Updated On:	Q	NW	NW	5	1N	8E	Green	0-225-111-2020	0.4	17.9	21.9	9.3	37.7	2.628	2.691	2.410		
SCHWARZENBERGER 55-23-023-QRY Created On: 03/13/24 Updated On:	Q	NW	NW	5	1N	8E	Green	0-225-196-2024	1.1	2.9	5.2	11.6	42.8	2.559	2.645	3.354		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
SCOTT 55-05-027-QRY Created On: 01/02/24 Updated On:	Q	NW	NE	18	24N	22E	Brown	0-225-9-2024	0.2	1.2	0.3	5.4	23.1	2.713	2.751	1.408	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
SCOTT CONSTRUCTION - COOPERSTOWN 55-36-044-QRY Created On: 05/30/17 Updated On:	Q	W	NW	19	21N	22E	Manitowoc	0-225-200-2017	11.6	0.0	6.4	6.1	26.7	2.673	2.722	1.843	
	Approved Use : HMA<MT, HMA>=MT, Base Aggregate																
SCOTT CONSTRUCTION - COOPERSTOWN 55-36-044-QRY Created On: 02/28/23 Updated On:	Q	W	NW	19	21N	22E	Manitowoc	0-225-157-2023	9.6	5.6	5.2	5.8	27.5	2.665	2.712	1.737	
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																
SEAS BRANCH 55-62-029-QRY Created On: 08/21/14 Updated On:	Q	NE	NW	15	13N	4W	Vernon	0-225-247-2014		0.0	1.6	8.2	33.9	2.624	2.675	1.938	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
SEAS BRANCH 55-62-029-QRY Created On: 01/04/23 Updated On:	Q	NE	NW	15	13N	4W	Vernon	0-225-84-2023	0.5	1.5	2.4	9.6	33.9	2.681	2.720	1.471	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
SEVEN SISTERS 55-01-008-QRY Created On: 08/25/16 Updated On:	Q			36	20N	7E	Adams	0-225-248-2016		0.9	0.7	4.6	20.7	2.631	2.646	0.591	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
SEVEN SISTERS 55-01-008-QRY Created On: 01/04/19 Updated On:	Q			36	20N	7E	Adams	0-225-33-2019	0.2	0.0	0.9	4.7	19.6	2.625	2.642	0.666	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
SEVEN SISTERS 55-01-008-QRY Created On: 01/04/22 Updated On:	Q			36	20N	7E	Adams	0-225-36-2022	4.2	12.0	7.8	6.1	22.9	2.543	2.598	2.169	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
SEYMOUR 55-44-027-QRY Created On: 05/15/14 Updated On:	Q	SW	SE	31	24N	18E	Outagamie	0-225-162-2014		3.4	1.8	6.1	24.2	2.749	2.779	1.062	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
SEYMOUR 55-44-027-QRY Created On: 05/11/17 Updated On:	Q	SW	SE	31	24N	18E	Outagamie	0-225-180-2017		3.9	1.1	7.5	30.5	2.724	2.761	1.330	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
SEYMOUR 55-44-027-QRY Created On: 04/08/20 Updated On:	Q	SW	SE	31	24N	18E	Outagamie	0-225-146-2020	0.2	12.6	2.4	8.0	30.9	2.758	2.784	0.918	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
SEYMOUR 55-44-027-QRY Created On: 02/28/23 Updated On:	Q	SW	SE	31	24N	18E	Outagamie	0-225-160-2023	1.0	8.8	1.4	6.9	27.6	2.741	2.772	1.124	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
* SHADY NOOK 55-60-032-QRY Created On: 01/05/17 Updated On:	Q	NW	SW	23	30N	2W	Taylor	0-225-17-2017		0.0	0.2	4.7	23.0	2.740	2.754	0.503	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
* SHADY NOOK 55-60-032-QRY Created On: 05/21/21 Updated On:	Q	NW	SW	23	30N	2W	Taylor	0-225-211-2021	0.0	0.0	0.3	4.8	21.9	2.735	2.747	0.467	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
SHAKAL VALLEY 55-09-063-PIT Created On: 02/05/14 Updated On:	P	NW	SW	23	29N	6W	Chippewa	0-225-79-2014		0.0	5.5	10.5	23.2	2.597	2.652	2.117	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
SHAKAL VALLEY 55-09-063-PIT Created On: 03/21/19 Updated On:	P	NW	SW	23	29N	6W	Chippewa	0-225-110-2019	5.5	0.0	6.1	6.3	22.7	2.649	2.686	1.392	
	Approved Use : HMA<MT, HMA>=MT, Base Aggregate																
SHAKAL VALLEY 55-09-063-PIT Created On: 01/02/24 Updated On:	P	NW	SW	23	29N	6W	Chippewa	0-225-118-2024	2.6	0.0	2.6	4.7	19.4	2.674	2.704	1.127	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
SHANNON 55-52-021-QRY Created On: 05/19/16 Updated On:	Q	NW	SW	32	10N	1W	Richland	0-225-179-2016	1.0	4.2	4.9	8.4	35.3	2.625	2.677	1.988	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
SHANNON 55-52-021-QRY Created On: 07/25/19 Updated On:	Q	NW	SW	32	10N	1W	Richland	0-225-249-2019	0.6	3.2	2.5	7.3	33.2	2.662	2.705	1.623	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
SHANNON 55-52-021-QRY Created On: 04/05/22 Updated On:	Q	NW	SW	32	10N	1W	Richland	0-225-165-2022	0.5	4.5	5.7	8.0	34.4	2.648	2.695	1.803	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
SHAWANO 55-58-036-QRY Created On: 05/11/15 Updated On:	Q	NE	NW	2	26N	16E	Shawano	0-225-164-2015	0.4	3.1	2.5	8.8	33.8	2.684	2.727	1.613	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
SHAWANO 55-58-036-QRY Created On: 01/04/18 Updated On:	Q	NE	NW	2	26N	16E	Shawano	0-225-61-2018		2.4	2.3	6.7	30.8	2.700	2.734	1.259		
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																	
SHAWANO 55-58-036-QRY Created On: 01/04/21 Updated On:	Q	NE	NW	2	26N	16E	Shawano	0-225-11-2021	0.2	4.1	3.1	5.3	26.5	2.699	2.737	1.410		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
SHAWANO 55-58-036-QRY Created On: 01/02/24 Updated On:	Q	NE	NW	2	26N	16E	Shawano	0-225-8-2024	0.0	2.3	0.3	5.7	26.9	2.722	2.754	1.151		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
* SHOCKLEY HILL 55-12-020-QRY Created On: 01/07/14 Updated On:	Q	SW	NE	21	8N	3W	Crawford	0-225-36-2014		1.0	3.4	6.9	27.8	2.630	2.679	1.870		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
* SHOCKLEY HILL 55-12-020-QRY Created On: 05/18/17 Updated On:	Q	SW	NE	21	8N	3W	Crawford	0-225-189-2017		2.8	6.6	8.7	33.7	2.632	2.687	2.097		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
* SHOCKLEY HILL 55-12-020-QRY Created On: 01/03/20 Updated On:	Q	SW	NE	21	8N	3W	Crawford	0-225-20-2020	0.5	1.1	0.5	7.2	28.3	2.618	2.675	2.193		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
* SHOCKLEY HILL 55-12-020-QRY Created On: 01/02/24 Updated On:	Q	SW	NE	21	8N	3W	Crawford	0-225-33-2024	0.8	4.5	2.8	9.2	34.2	2.599	2.662	2.416		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
SIEKIERZYNSKI 55-37-094-PIT Created On: 06/13/22 Updated On:	P	SW	NE	29	27N	9E	Marathon	0-225-216-2022	0.5	0.0	1.0	7.9	32.2	2.614	2.645	1.188	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
SIEKIERZYNSKI 55-37-095-QRY Created On: 06/13/22 Updated On:	Q	SW	NE	29	27N	9E	Marathon	0-225-217-2022	0.1	0.0	0.9	7.6	34.2	2.643	2.659	0.630	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
SILHA MH 55-53-014-QRY Created On: 04/09/14 Updated On:	Q	SW	NE	2	3N	13E	Rock	0-225-117-2014	5.7	1.8	12.3	10.3	41.9	2.481	2.590	4.392	
	Approved Use : HMA<E-3, HMA>=E-3, OGBC, Base Aggregate																
SILHA MH 55-53-012-PIT Created On: 04/16/15 Updated On:	P	SW	NE	2	3N	13E	Rock	0-225-121-2015	0.9	0.0	5.1	6.5	30.2	2.650	2.703	2.026	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
SILHA MH 55-53-014-QRY Created On: 04/12/16 Updated On:	Q	SW	NE	2	3N	13E	Rock	0-225-143-2016	0.2	4.0	8.7	8.5	35.5	2.626	2.687	2.347	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
SILHA MH 55-53-014-QRY Created On: 06/02/17 Updated On:	Q	SW	NE	2	3N	13E	Rock	0-225-203-2017	1.1	2.1	7.9	8.1	34.2	2.603	2.669	2.559	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
SILHA MH 55-53-014-QRY Created On: 09/11/19 Updated On:	Q	SW	NE	2	3N	13E	Rock	0-225-269-2019	1.4	2.6	7.2	8.7	37.7	2.587	2.660	2.819	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
SILHA MH 55-53-014-QRY Created On: 06/23/20 Updated On:	Q	SW	NE	2	3N	13E	Rock	0-225-202-2020	1.8	12.3	13.2	9.8	39.3	2.621	2.672	1.928	
	Approved Use : Base Aggregate																
SILHA MH 55-53-012-PIT Created On: 06/23/20 Updated On:	P	SW	NE	2	3N	13E	Rock	0-225-203-2020	4.3	0.0	5.3	5.4	28.6	2.621	2.672	1.928	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
SILHA MH 55-53-014-QRY Created On: 01/03/23 Updated On:	Q	SW	NE	2	3N	13E	Rock	0-225-14-2023	2.1	6.9	8.7	10.0	39.4	2.553	2.632	3.119	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
SIMMON 55-22-049-QRY Created On: 05/23/14 Updated On:	Q	SW	NW	21	4N	4W	Grant	0-225-165-2014	0.1	1.6	6.0	11.3	41.3	2.553	2.628	2.904	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
SIMMON 55-22-049-QRY Created On: 01/04/18 Updated On:	Q	SW	NW	21	4N	4W	Grant	0-225-71-2018	0.8	10.7	10.0	11.2	40.4	2.575	2.642	2.590	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
SIMMON 55-22-049-QRY Created On: 01/04/22 Updated On:	Q	SW	NW	21	4N	4W	Grant	0-225-45-2022	1.1	10.1	0.7	10.9	39.0	2.559	2.629	2.746	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
SIREN 55-07-018-PIT Created On: 04/17/15 Updated On:	P	NE	SW	32	38N	16W	Burnett	0-225-128-2015		0.0	-7.4	5.1	20.2	2.703	2.740	1.347	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Coarse Sp. Gravity		Coarse Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
SIREN 55-07-018-PIT Created On: 04/05/22 Updated On:	P	NE	SW	32	38N	16W	Burnett	0-225-164-2022	6.7	0.0	6.2	4.9	20.0	2.697	2.731	1.272		
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																	
SITTE 55-15-028-QRY Created On: 03/22/19 Updated On:	Q	S	NE	2	31N	28E	Door	0-225-113-2019	5.5	0.0	5.0	6.1	27.5	2.618	2.674	2.165		
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																	
SITTE 55-15-028-QRY Created On: 03/07/22 Updated On:	Q	S	NE	2	31N	28E	Door	0-225-138-2022	2.1	0.0	12.0	6.4	29.4	2.620	2.674	2.073		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
SKILLE V 55-57-025-PIT Created On: 01/23/14 Updated On:	P	NW	NE	33	40N	9W	Sawyer	0-225-56-2014		0.0	3.4	6.2	21.8	2.779	2.811	1.130		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
SKILLE V 55-57-025-PIT Created On: 05/02/19 Updated On:	P	NW	NE	33	40N	9W	Sawyer	0-225-175-2019	1.1	0.0	1.8	3.4	15.3	2.836	2.858	0.787		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
SKILLE V 55-57-025-PIT Created On: 01/04/24 Updated On:	P	NW	NE	33	40N	9W	Sawyer	0-225-140-2024	1.9	4.4	2.5	4.2	18.1	2.776	2.811	1.259		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
SLAMA 55-12-021-QRY Created On: 07/30/15 Updated On:	Q			18	7N	6W	Crawford	0-225-222-2015	1.1	1.8	2.1	8.7	33.9	2.614	2.675	2.350		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
SLAMA 55-12-021-QRY Created On: 01/04/18 Updated On:	Q		18	7N	6W	Crawford	0-225-73-2018	0.7	1.0	3.2	7.5	37.9	2.636	2.685	1.845		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
SLAMA 55-12-021-QRY Created On: 01/04/21 Updated On:	Q		18	7N	6W	Crawford	0-225-26-2021	1.0	6.6	5.0	7.5	31.7	2.612	2.668	2.167		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
SLAMA 55-12-021-QRY Created On: 01/02/24 Updated On:	Q		18	7N	6W	Crawford	0-225-27-2024	2.0	4.1	1.2	7.0	28.1	2.650	2.696	1.710		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
SMASAL 55-50-028-PIT Created On: 01/09/15 Updated On:	P	SE	25	39N	1W	Price	0-225-50-2015		0.0	1.7	15.5	16.6	2.724	2.751	0.993		
	Approved Use : CONCRETE, OGBC, Base Aggregate																
SMASAL 55-50-028-PIT Created On: 01/07/20 Updated On:	P	SE	25	39N	1W	Price	0-225-45-2020	0.1	0.0	1.8	3.4	16.6	2.733	2.759	0.923		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
* SMITH 55-27-011-PIT Created On: 08/22/19 Updated On:	P	NE	SE	20	22N	3W	Jackson	0-225-265-2019	2.8	1.1	5.2	2.3	19.0	2.661	2.691	1.122	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
SMITH-PIT 55-21-021-PIT Created On: 02/28/24 Updated On:	P	SE	SW	7	34N	15E	Forest	0-225-195-2024	0.9	0.0	0.3	4.4	20.3	2.731	2.746	0.545	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
SOLON SPRINGS 55-16-024-QRY Created On: 05/09/16 Updated On:	Q	NE	NW	18	45N	11W	Douglas	0-225-167-2016		0.0	4.6	3.8	16.7	2.807	2.839	1.155		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
SOLON SPRINGS 55-16-024-QRY Created On: 01/07/19 Updated On:	Q	NE	NW	18	45N	11W	Douglas	0-225-60-2019	0.3	0.0	8.8	4.6	19.4	2.780	2.824	1.552		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
SOLON SPRINGS 55-16-024-QRY Created On: 07/07/22 Updated On:	Q	NE	NW	18	45N	11W	Douglas	0-225-245-2022	1.4	0.0	4.7	4.8	19.0	2.778	2.807	1.041		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
SPILEDE 55-13-085-PIT Created On: 08/11/15 Updated On:	P		N	17	6N	11E	Dane	0-225-227-2015		7.8	7.4	8.5	34.4	2.631	2.689	2.211		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
SPILEDE 55-13-085-PIT Created On: 01/04/21 Updated On:	P		N	17	6N	11E	Dane	0-225-2-2021	9.4	0.0	12.7	10.7	39.0	2.584	2.647	2.438		
	Approved Use : Base Aggregate																	
SPRAGUE 55-42-037-PIT Created On: 01/06/16 Updated On:	P	SE	NE	16	30N	19E	Oconto	0-225-33-2016	1.2	0.0	7.4	8.1	31.2	2.687	2.722	1.305		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
SPRAGUE 55-42-037-PIT Created On: 02/10/21 Updated On:	P	SE	NE	16	30N	19E	Oconto	0-225-126-2021	2.5	0.0	5.9	6.8	29.5	2.683	2.722	1.449		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
SPREAD EAGLE 55-19-009-QRY Created On: 01/12/16 Updated On:	Q	NW	SE	11	39N	19E	Florence	0-225-50-2016		0.0	0.3	2.9	12.4	2.895	2.903	0.294		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
SPREAD EAGLE 55-19-009-QRY Created On: 01/04/19 Updated On:	Q	NW	SE	11	39N	19E	Florence	0-225-11-2019		0.2	0.1	1.9	9.1	2.951	2.964	0.429		
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																	
SPREAD EAGLE 55-19-009-QRY Created On: 01/04/22 Updated On:	Q	NW	SE	11	39N	19E	Florence	0-225-24-2022	0.0	1.0	0.2	6.1	12.4	2.973	2.982	0.291		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
SPRINGVALLEY 55-47-026-QRY Created On: 01/30/14 Updated On:	Q	NE	NE	16	27N	15W	Pierce	0-225-63-2014		0.0	0.7	6.4	30.2	2.596	2.651	2.114		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
SPRINGVALLEY 55-47-026-QRY Created On: 01/05/17 Updated On:	Q	NE	NE	16	27N	15W	Pierce	0-225-44-2017		0.0	0.9	4.4	23.2	2.694	2.725	1.175		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
SPRINGVALLEY 55-47-026-QRY Created On: 03/02/20 Updated On:	Q	NE	NE	16	27N	15W	Pierce	0-225-117-2020	0.1	0.0	0.2	6.3	28.5	2.653	2.698	1.693		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
SPRINGVALLEY 55-47-026-QRY Created On: 01/10/23 Updated On:	Q	NE	NE	16	27N	15W	Pierce	0-225-104-2023	0.9	7.4	0.2	6.0	30.5	2.634	2.686	1.981		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
SPRINGWATER 55-69-019-PIT Created On: 05/13/21 Updated On:	P	NW	NW	6	20N	11E	Waushara	0-225-206-2021	0.2	2.9	1.3	4.7	21.2	2.700	2.730	1.097	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
ST NAZIANZ 55-36-043-PIT Created On: 01/05/17 Updated On:	P		S	30	18N	22E	Manitowoc	0-225-20-2017	0.5	1.6	2.0	7.8	33.3	2.750	2.778	1.033	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
ST NAZIANZ 55-36-043-PIT Created On: 04/28/22 Updated On:	P		S	30	18N	22E	Manitowoc	0-225-185-2022	1.1	0.0	1.3	7.2	33.0	2.761	2.788	0.983	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
* ST. AUBIN 55-09-064-PIT Created On: 02/03/14 Updated On:	P	NE	NE	27	31N	7W	Chippewa	0-225-71-2014		0.0	2.4	4.4	20.4	2.707	2.738	1.146	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
* ST. AUBIN 55-09-064-PIT Created On: 01/08/19 Updated On:	P	NE	NE	27	31N	7W	Chippewa	0-225-81-2019	3.1	0.0	1.6	3.2	17.9	2.674	2.702	1.064	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
STAG LAKE 55-43-033-PIT Created On: 06/13/18 Updated On:	P	NW	NW	34	36N	7E	Oneida	0-225-226-2018	0.2	0.0	1.9	5.5	24.1	2.682	2.703	0.790	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
STAG LAKE 55-43-033-PIT Created On: 01/19/23 Updated On:	P	NW	NW	34	36N	7E	Oneida	0-225-127-2023	0.4	0.0	2.7	5.3	23.5	2.665	2.695	1.134	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
STAUDENMAIER 55-38-032-QRY Created On: 03/31/17 Updated On:	Q	NW	SW	7	29N	22E	Marinette	0-225-97-2017	0.0	1.9	3.7	5.8	26.2	2.717	2.752	1.294		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
STAUDENMAIER 55-38-032-QRY Created On: 06/13/22 Updated On:	Q	NW	SW	7	29N	22E	Marinette	0-225-220-2022	0.0	2.6	1.0	7.2	28.8	2.706	2.741	1.263		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
STEGER 55-20-057-PIT Created On: 01/06/14 Updated On:	P	SW	SW	24	13N	18E	Fond Du Lac	0-225-7-2014		0.0	1.5	6.1	27.0	2.759	2.783	0.846		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
STEGER 55-20-057-PIT Created On: 03/24/21 Updated On:	P	SW	SW	24	13N	18E	Fond Du Lac	0-225-157-2021	0.1	0.0	3.0	6.4	29.3	2.767	2.790	0.822		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
* STELTER 55-09-065-PIT Created On: 04/25/14 Updated On:	P	SW	SW	5	30N	8W	Chippewa	0-225-150-2014		0.0	0.4	4.3	19.5	2.739	2.767	1.031		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
* STELTER 55-09-065-PIT Created On: 05/02/19 Updated On:	P	SW	SW	5	30N	8W	Chippewa	0-225-176-2019	0.0	0.0	2.2	4.5	20.0	2.740	2.765	0.920		
	Approved Use : HMA<MT, HMA>=MT, Base Aggregate																	
STEVENSON 55-11-036-QRY Created On: 03/31/15 Updated On:	Q			8	10N	9E	Columbia	0-225-111-2015		1.2	2.2	13.0	45.0	2.524	2.602	3.118		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
STEVENSON 55-11-036-QRY Created On: 01/03/18 Updated On:	Q		8	10N	9E	Columbia		0-225-6-2018	2.5	0.7	3.9	10.4	36.7	2.529	2.615	3.422		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
STEVENSON 55-11-036-QRY Created On: 01/04/21 Updated On:	Q		8	10N	9E	Columbia		0-225-40-2021	2.3	1.2	0.6	8.9	33.9	2.548	2.620	2.799		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
STEVENSON 55-11-036-QRY Created On: 01/02/24 Updated On:	Q		8	10N	9E	Columbia		0-225-18-2024	4.9	5.1	3.1	15.9	45.9	2.512	2.604	3.663		
	Approved Use : CONCRETE, OGBC, Base Aggregate																	
* STOUGHTON 55-13-001-PIT Created On: 05/02/14 Updated On:	P	E	NW	10	5N	11E	Dane	0-225-158-2014		0.0	5.6	8.7	37.1	2.634	2.688	2.038		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
* STOUGHTON 55-13-001-PIT Created On: 01/04/19 Updated On:	P	E	NW	10	5N	11E	Dane	0-225-10-2019	2.0	9.3	0.9	6.4	30.8	2.664	2.710	1.718		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
* STRAND 55-06-023-QRY Created On: 10/07/20 Updated On:	Q		NE	28	23N	13W	Buffalo	0-225-244-2020	0.3	0.0	12.5	10.3	41.8	2.563	2.655	3.608		
	Approved Use : Base Aggregate																	
STRAUB 55-20-006-PIT Created On: 01/06/14 Updated On:	P		W	23	14N	18E	Fond Du Lac	0-225-16-2014		0.0	0.7	5.4	25.2	2.784	2.805	0.740		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
STRAUB 55-20-006-PIT Created On: 01/04/19 Updated On:	P	W	23	14N	18E	Fond Du Lac	0-225-18-2019		4.9	0.8	7.1	30.0	2.758	2.785	0.984			
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																	
STRAUB 55-20-006-PIT Created On: 01/02/24 Updated On:	P	W	23	14N	18E	Fond Du Lac	0-225-100-2024	0.8	2.9	0.2	6.1	26.3	2.772	2.795	0.806			
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
STROETZ 55-37-075-QRY Created On: 03/21/18 Updated On:	Q	SW	NW	10	26N	3E	Marathon	0-225-131-2018	0.0	2.9	6.2	28.0	2.593	2.616	0.874			
	Approved Use : HMA<MT, HMA>=MT, Base Aggregate																	
STROETZ 55-37-075-QRY Created On: 06/28/22 Updated On:	Q	SW	NW	10	26N	3E	Marathon	0-225-241-2022	0.0	1.7	7.6	29.3	2.592	2.620	1.073			
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																	
STUCZYNSKI (DUFFEK) 55-49-024-PIT Created On: 09/25/14 Updated On:	P	NE	NW	4	23N	9E	Portage	0-225-267-2014	0.0	2.5	7.6	26.9	2.631	2.661	1.153			
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
STUCZYNSKI (DUFFEK) 55-49-024-PIT Created On: 07/26/21 Updated On:	P	NE	NW	4	23N	9E	Portage	0-225-250-2021	0.6	0.0	0.6	9.4	34.9	2.603	2.637	1.303		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
STUPAK 55-16-025-QRY Created On: 05/08/15 Updated On:	Q	NW	NW	29	47N	14W	Douglas	0-225-154-2015	0.0	3.2	2.9	15.0	2.791	2.810	0.680			
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
STUPAK 55-16-025-QRY Created On: 01/03/18 Updated On:	Q	NW	NW	29	47N	14W	Douglas	0-225-17-2018		0.0	9.1	3.5	15.5	2.686	2.719	1.235		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
STUPAK 55-16-025-QRY Created On: 01/05/21 Updated On:	Q	NW	NW	29	47N	14W	Douglas	0-225-68-2021	0.0	16.5	10.9	3.5	15.2	2.715	2.749	1.259		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
STUPAK 55-16-025-QRY Created On: 01/02/24 Updated On:	Q	NW	NW	29	47N	14W	Douglas	0-225-92-2024	0.0	0.0	10.6	3.6	17.2	2.633	2.684	1.930		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
STURGEON BAY - MM 55-15-022-QRY Created On: 01/06/14 Updated On:	Q	SE	NW	21	27N	25E	Door	0-225-6-2014		0.0	0.6	6.2	26.2	2.779	2.797	0.630		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
STURGEON BAY - MM 55-15-022-QRY Created On: 01/05/17 Updated On:	Q	SE	NW	21	27N	25E	Door	0-225-21-2017		0.0	1.9	7.8	27.6	2.769	2.789	0.736		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
STURGEON BAY - MM 55-15-022-QRY Created On: 01/02/20 Updated On:	Q	SE	NW	21	27N	25E	Door	0-225-7-2020	0.0	0.0	0.5	5.4	25.4	2.779	2.796	0.611		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
STURGEON BAY - MM 55-15-022-QRY Created On: 01/03/23 Updated On:	Q	SE	NW	21	27N	25E	Door	0-225-46-2023		7.2	1.8	5.7	24.0	2.773	2.792	0.688		
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
SUGAR BUSH 55-65-020-PIT Created On: 06/18/20 Updated On:	P		NW	23	37N	10W	Washburn	0-225-198-2020	2.0	0.0	2.1	4.6	20.7	2.753	2.778	0.915	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
SUPER AGGREGATE - BURGETT LAKES 17-00-007-PIT Created On: 02/16/16 Updated On:	P		SE	1	46N	7E	Mchenry	0-225-88-2016	1.6	3.2	1.7	6.9	34.8	2.677	2.718	1.525	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
SUPER AGGREGATE - BURGETT LAKES 17-00-007-PIT Created On: 01/04/21 Updated On:	P		SE	1	46N	7E	Mchenry	0-225-9-2021	0.7	4.7	0.3	4.5	23.4	2.676	2.708	1.199	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
* SUPER AGGREGATE / WATERFORD 55-51-028-PIT Created On: 01/06/14 Updated On:	P	SW	SE	28	4N	19E	Racine	0-225-29-2014	0.6	0.0	4.5	6.3	29.5	2.649	2.690	1.544	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
* SUPER AGGREGATE / WATERFORD 55-51-028-PIT Created On: 02/11/19 Updated On:	P	SW	SE	28	4N	19E	Racine	0-225-102-2019	3.1	0.0	7.8	4.6	23.0	2.646	2.692	1.748	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
* SUPER AGGREGATE-SUGAR CREEK 55-64-037-PIT Created On: 07/17/14 Updated On:	P	SE	NW	9	3N	16E	Walworth	0-225-228-2014	4.7	0.0	3.8	9.6	33.9	2.681	2.715	1.274	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
* SUPER AGGREGATE-SUGAR CREEK 55-64-037-PIT Created On: 02/11/19 Updated On:	P	SE	NW	9	3N	16E	Walworth	0-225-106-2019	3.0	0.0	7.0	3.9	24.2	2.651	2.692	1.527	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
SVEC 55-47-027-QRY Created On: 03/24/16 Updated On:	Q	E	NW	17	26N	18W	Pierce	0-225-115-2016		0.0	7.8	9.9	34.2	2.609	2.674	2.499		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
SVEC 55-47-027-QRY Created On: 01/07/19 Updated On:	Q	E	NW	17	26N	18W	Pierce	0-225-63-2019	0.5	0.0	5.8	9.2	33.8	2.611	2.675	2.469		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
SVEC 55-47-027-QRY Created On: 01/04/22 Updated On:	Q	E	NW	17	26N	18W	Pierce	0-225-77-2022	5.5	16.0	16.4	15.0	45.0	2.551	2.630	3.087		
	Approved Use : Base Aggregate																	
SVEC 55-47-027-PIT Created On: 03/15/22 Updated On:	P	E	NW	17	26N	18W	Pierce	0-225-142-2022	2.4	8.7	11.1	10.7	37.6	2.633	2.691	2.177		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
SWAGEL 55-31-017-PIT Created On: 11/03/17 Updated On:	P		N	29	23N	24E	Kewaunee	0-225-285-2017	1.5	0.0	5.6	7.9	32.9	2.710	2.748	1.420		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
SWAGEL 55-31-017-PIT Created On: 03/07/22 Updated On:	P		N	29	23N	24E	Kewaunee	0-225-140-2022	3.1	0.0	4.2	6.2	30.8	2.693	2.730	1.368		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
* SWIGGUM 55-25-025-QRY Created On: 04/16/15 Updated On:	Q	NE	NE	30	6N	3E	Iowa	0-225-120-2015	0.5	2.1	3.3	12.6	44.3	2.494	2.587	3.719		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
SWIGGUM 55-12-022-QRY Created On: 07/17/15 Updated On:	Q	SW	NW	29	11N	3W	Crawford	0-225-213-2015		1.1	1.4	9.1	35.6	2.640	2.687	1.764		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
SWIGGUM 55-12-022-QRY Created On: 05/19/16 Updated On:	Q	SW	NW	29	11N	3W	Crawford	0-225-183-2016		1.4	3.9	8.9	34.4	2.661	2.705	1.650		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
* SWIGGUM 55-25-025-QRY Created On: 03/23/18 Updated On:	Q	NE	NE	30	6N	3E	Iowa	0-225-144-2018		1.8	1.3	0.5	9.8	37.3	2.506	2.596	3.617	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
SWIGGUM 55-12-022-QRY Created On: 01/07/19 Updated On:	Q	SW	NW	29	11N	3W	Crawford	0-225-55-2019		1.0	2.0	3.5	10.1	36.8	2.602	2.662	2.325	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
* SWIGGUM 55-25-025-QRY Created On: 03/17/21 Updated On:	Q	NE	NE	30	6N	3E	Iowa	0-225-146-2021		0.8	1.6	0.9	9.9	38.7	2.491	2.591	4.004	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
SWIGGUM 55-12-022-QRY Created On: 02/16/22 Updated On:	Q	SW	NW	29	11N	3W	Crawford	0-225-123-2022		0.4	5.6	0.3	9.0	35.8	2.642	2.697	2.073	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
SWIGGUM 55-12-022-QRY Created On: 01/02/24 Updated On:	Q	SW	NW	29	11N	3W	Crawford	0-225-2-2024		0.1	1.3	1.5	8.5	36.0	2.537	2.619	3.207	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
SZEWS 55-37-077-PIT Created On: 09/15/16 Updated On:	P	SW	SW	4	28N	10E	Marathon	0-225-257-2016		0.0	0.4	8.2	32.3	2.669	2.689	0.741		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
SZEWS 55-37-077-PIT Created On: 01/04/21 Updated On:	P	SW	SW	4	28N	10E	Marathon	0-225-17-2021	0.0	0.4	0.4	6.9	30.9	2.669	2.691	0.807		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
TAGGE 55-15-023-PIT Created On: 01/05/17 Updated On:	P		NE	31	27N	26E	Door	0-225-22-2017	0.3	0.0	0.3	7.2	30.2	2.726	2.763	1.373		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
TAGGE 55-15-023-PIT Created On: 01/04/22 Updated On:	P		NE	31	27N	26E	Door	0-225-15-2022	0.1	2.2	1.8	6.4	27.5	2.733	2.764	1.151		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
TAMMEC PIT 55-55-016-PIT Created On: 02/03/14 Updated On:	P		SW	16	30N	18W	St. Croix	0-225-73-2014		0.0	3.2	4.6	20.1	2.712	2.748	1.320		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
TAMMEC PIT 55-55-016-PIT Created On: 01/05/17 Updated On:	P		SW	16	30N	18W	St. Croix	0-225-45-2017		0.0	3.0	3.6	19.1	2.702	2.735	1.207		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
TAMMEC PIT 55-55-016-PIT Created On: 01/04/22 Updated On:	P		SW	16	30N	18W	St. Croix	0-225-78-2022	3.0	4.1	5.0	4.5	20.3	2.678	2.716	1.393		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %			
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine		
TAMMEC QUARRY 55-55-017-QRY Created On: 02/03/14 Updated On:	Q	SW	16	30N	18W	St. Croix	0-225-72-2014		0.0	8.3	12.6	43.1	2.523	2.605	3.227				
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																		
TAMMEC QUARRY 55-55-017-QRY Created On: 01/08/15 Updated On:	Q	SW	16	30N	18W	St. Croix	0-225-39-2015	4.9	0.0	10.3	12.2	41.8	2.497	2.579	3.319				
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																		
TAMMEC QUARRY 55-55-017-QRY Created On: 04/21/17 Updated On:	Q	SW	16	30N	18W	St. Croix	0-225-144-2017	2.8	0.0	6.7	9.2	35.1	2.562	2.626	2.475				
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																		
TAMMEC QUARRY 55-55-017-QRY Created On: 05/04/20 Updated On:	Q	SW	16	30N	18W	St. Croix	0-225-165-2020	2.6	0.0	7.1	9.5	37.0	2.572	2.644	2.800				
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
TAMMEC QUARRY 55-55-017-QRY Created On: 01/03/23 Updated On:	Q	SW	16	30N	18W	St. Croix	0-225-53-2023	9.1	14.4	4.2	12.0	43.2	2.481	2.564	3.359				
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																		
TAYLOR #1 55-43-028-PIT Created On: 06/13/18 Updated On:	P	NW	NW	16	36N	9E	Oneida	0-225-227-2018	0.2	0.0	0.9	5.1	23.4	2.637	2.655	0.647			
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
TAYLOR #1 55-43-028-PIT Created On: 04/24/23 Updated On:	P	NW	NW	16	36N	9E	Oneida	0-225-206-2023	0.0	0.0	0.8	5.7	25.0	2.742	2.763	0.751			
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
TENNYSON 55-22-052-QRY Created On: 04/24/14 Updated On:	Q	NW	NE	36	3N	3W	Grant	0-225-141-2014		5.8	4.8	10.0	37.2	2.595	2.661	2.528		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
TENNYSON 55-22-052-QRY Created On: 04/06/17 Updated On:	Q	NW	NE	36	3N	3W	Grant	0-225-116-2017	2.6	7.7	3.2	11.3	35.1	2.562	2.636	2.888		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
TENNYSON 55-22-052-QRY Created On: 07/28/17 Updated On:	Q	NW	NE	36	3N	3W	Grant	0-225-241-2017	0.3	3.3	1.1	7.5	31.0	2.624	2.678	2.073		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
TENNYSON 55-22-052-QRY Created On: 04/28/20 Updated On:	Q	NW	NE	36	3N	3W	Grant	0-225-160-2020	0.0	3.7	2.2	8.8	33.6	2.642	2.693	1.941		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
TENNYSON 55-22-052-QRY Created On: 01/03/23 Updated On:	Q	NW	NE	36	3N	3W	Grant	0-225-9-2023	0.3	7.0	10.6	10.1	36.8	2.543	2.627	3.277		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
THACKRAY 55-20-048-PIT Created On: 09/11/14 Updated On:	P			13	15N	19E	Fond Du Lac	0-225-256-2014		0.0	2.7	8.1	33.5	2.747	2.775	1.000		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
THACKRAY 55-20-048-PIT Created On: 04/10/19 Updated On:	P			13	15N	19E	Fond Du Lac	0-225-129-2019	0.3	0.0	0.9	7.6	33.6	2.748	2.775	0.967		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
THACKRAY 55-20-048-PIT Created On: 01/02/24 Updated On:	P			13	15N	19E	Fond Du Lac	0-225-53-2024	1.1	0.0	1.1	6.0	28.0	2.766	2.787	0.752	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
THACKRAY SOUTH 55-20-053-PIT Created On: 05/15/20 Updated On:	P	SE	NW	13	15N	19E	Fond Du Lac	0-225-179-2020	0.0	0.0	2.3	7.8	36.0	2.725	2.760	1.289	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
THELEN-ANTIOCH 17-00-002-PIT Created On: 06/12/14 Updated On:	P			9	46N	9E	Lake	0-225-189-2014	2.2	0.0	4.8	7.9	33.9	2.695	2.727	1.184	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
THELEN-ANTIOCH 17-00-002-PIT Created On: 05/09/18 Updated On:	P			9	46N	9E	Lake	0-225-196-2018	0.2	11.9	0.9	5.7	26.1	2.695	2.733	1.439	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
THELEN-ANTIOCH 17-00-002-PIT Created On: 01/03/23 Updated On:	P			9	46N	9E	Lake	0-225-51-2023	1.0	16.2	6.6	4.5	25.1	2.662	2.701	1.465	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
THELEN-LANGE ROAD 55-64-025-PIT Created On: 06/12/14 Updated On:	P	SE	SE	32	1N	18E	Walworth	0-225-190-2014	2.1	0.0	3.1	7.6	37.9	2.679	2.716	1.397	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
THELEN-LANGE ROAD 55-64-025-PIT Created On: 06/25/15 Updated On:	P	SE	SE	32	1N	18E	Walworth	0-225-202-2015	1.0	0.0	1.1	5.7	33.5	2.674	2.713	1.439	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Sp. Gravity		Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
THELEN-LANGE ROAD 55-64-025-PIT Created On: 05/09/18 Updated On:	P	SE	SE	32	1N	18E	Walworth	0-225-197-2018	0.3	10.4	0.9	5.5	25.8	2.699	2.737	1.421		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
THELEN-LANGE ROAD 55-64-025-PIT Created On: 01/03/23 Updated On:	P	SE	SE	32	1N	18E	Walworth	0-225-49-2023	0.7	14.4	6.6	5.9	28.4	2.671	2.704	1.241		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
THIEL 55-68-028-PIT Created On: 06/21/16 Updated On:	P	NE	NW	5	22N	13E	Waupaca	0-225-209-2016		0.0	1.1	5.7	27.5	2.691	2.712	0.794		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
THIEL 55-68-028-PIT Created On: 01/04/21 Updated On:	P	NE	NW	5	22N	13E	Waupaca	0-225-21-2021	0.6	3.1	2.0	5.5	26.6	2.703	2.727	0.913		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
THOMAS COBB 55-25-026-QRY Created On: 02/09/18 Updated On:	Q	NE	NE	30	6N	2E	Iowa	0-225-97-2018	2.1	3.9	8.9	10.5	42.6	2.504	2.601	3.891		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
THOMAS COBB 55-25-026-QRY Created On: 03/17/21 Updated On:	Q	NE	NE	30	6N	2E	Iowa	0-225-139-2021	2.6	11.0	9.5	12.7	43.9	2.534	2.625	3.573		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
THOMAS COBB 55-25-026-QRY Created On: 02/28/24 Updated On:	Q	NE	NE	30	6N	2E	Iowa	0-225-181-2024	2.3	12.5	12.4	9.2	38.7	2.526	2.613	3.425		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
THOMAS\RIDGE 55-25-029-QRY Created On: 04/07/16 Updated On:	Q	NW	NE	33	6N	4E	Iowa	0-225-129-2016	5.6	7.4	5.3	12.3	43.2	2.560	2.633	2.859	
	Approved Use : HMA<E-3, HMA>=E-3, Base Aggregate																
THOMAS\RIDGE 55-25-029-QRY Created On: 02/11/19 Updated On:	Q	NW	NE	33	6N	4E	Iowa	0-225-104-2019	1.8	3.0	5.5	10.6	39.8	2.544	2.631	3.408	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
THOMAS\RIDGE 55-25-029-QRY Created On: 03/17/21 Updated On:	Q	NW	NE	33	6N	4E	Iowa	0-225-141-2021	1.5	5.3	2.9	9.2	38.2	2.613	2.676	2.415	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
THOMAS\RIDGE 55-25-029-QRY Created On: 02/28/24 Updated On:	Q	NW	NE	33	6N	4E	Iowa	0-225-183-2024	2.0	5.4	10.5	9.2	37.6	2.542	2.626	3.275	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
THOMSON LIMESTONE 55-42-038-QRY Created On: 01/04/22 Updated On:	Q	SE	SE	20	30N	19E	Oconto	0-225-14-2022	1.4	6.9	6.5	6.0	33.8	2.696	2.736	1.489	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
* THONI 55-25-030-QRY Created On: 03/23/18 Updated On:	Q	SW	SE	3	6N	5E	Iowa	0-225-139-2018	2.7	3.9	1.3	10.9	41.2	2.549	2.632	3.232	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
* THONI 55-25-030-QRY Created On: 03/17/21 Updated On:	Q	SW	SE	3	6N	5E	Iowa	0-225-147-2021	1.9	2.5	0.6	14.9	46.7	2.562	2.632	2.712	
	Approved Use : CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
THURS 55-37-090-QRY Created On: 04/05/19 Updated On:	Q	NE	SW	27	29N	5E	Marathon	0-225-124-2019		0.0	1.4	4.2	18.4	2.715	2.736	0.766		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
THURS 55-37-090-QRY Created On: 04/11/22 Updated On:	Q	NE	SW	27	29N	5E	Marathon	0-225-172-2022	0.0	0.0	0.6	3.2	14.1	2.769	2.780	0.397		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
TIMBERLANE S & G 55-28-015-PIT Created On: 01/04/22 Updated On:	P	NW	SW	19	6N	14E	Jefferson	0-225-88-2022	0.6	6.2	1.8	4.8	25.5	2.677	2.710	1.234		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
TIMM 55-44-029-QRY Created On: 03/17/22 Updated On:	Q	NE	NE	25	22N	16E	Outagamie	0-225-150-2022	0.0	9.0	1.1	5.2	23.6	2.746	2.776	1.083		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
TNT 55-13-094-QRY Created On: 01/30/15 Updated On:	Q		SW	14	6N	12E	Dane	0-225-80-2015		15.5	9.5	8.1	34.5	2.603	2.679	2.917		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
TNT 55-13-094-QRY Created On: 03/22/17 Updated On:	Q		SW	14	6N	12E	Dane	0-225-87-2017	1.6	31.6	19.1	10.5	38.3	2.557	2.644	3.416		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
TNT 55-13-094-QRY Created On: 04/12/17 Updated On:	Q		SW	14	6N	12E	Dane	0-225-122-2017		13.2	8.8	8.0	34.9	2.616	2.687	2.679		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
TNT 55-13-094-QRY Created On: 04/12/17 Updated On:	Q	SW	14	6N	12E	Dane	0-225-124-2017	0.5	12.1	6.9	6.5	29.1	2.630	2.692	2.387			
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
TNT 55-13-094-QRY Created On: 04/12/17 Updated On:	Q	SW	14	6N	12E	Dane	0-225-125-2017	0.3	10.1	9.5	6.1	28.3	2.630	2.691	2.312			
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
TNT 55-13-094-QRY Created On: 02/12/20 Updated On:	Q	SW	14	6N	12E	Dane	0-225-110-2020	0.4	29.8	15.7	7.3	32.8	2.619	2.683	2.461			
TNT 55-13-094-QRY Created On: 04/01/20 Updated On:	Q	SW	14	6N	12E	Dane	0-225-136-2020	0.2	22.0	12.7	6.7	30.8						
TNT 55-13-094-QRY Created On: 08/10/20 Updated On:	Q	SW	14	6N	12E	Dane	0-225-231-2020		17.6	6.7	5.3	26.8	2.662	2.713	1.888			
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																	
TNT 55-13-094-QRY Created On: 04/26/21 Updated On:	Q	SW	14	6N	12E	Dane	0-225-189-2021	0.1	16.8	5.8	5.7	27.6	2.622	2.684	2.377			
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
TNT 55-13-094-QRY Created On: 01/04/22 Updated On:	Q	SW	14	6N	12E	Dane	0-225-79-2022	0.2	14.2	10.4	5.9	29.5	2.651	2.706	2.058			
	Approved Use : Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
* TORDEUR 55-05-024-QRY Created On: 01/05/15 Updated On:	Q		18	24N	22E	Brown		0-225-1-2015	0.3	1.3	2.3	5.8	27.2	2.729	2.764	1.285		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
* TORDEUR 55-05-024-QRY Created On: 01/04/18 Updated On:	Q		18	24N	22E	Brown		0-225-52-2018		2.6	2.8	7.2	33.5	2.708	2.748	1.490		
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																	
* TORDEUR 55-05-024-QRY Created On: 01/04/21 Updated On:	Q		18	24N	22E	Brown		0-225-8-2021	0.3	0.9	1.5	5.2	24.6	2.703	2.742	1.446		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
TORK 55-71-029-QRY Created On: 01/06/14 Updated On:	Q	NE	SW	1	22N	5E	Wood	0-225-20-2014		0.0	1.0	7.0	28.2	2.649	2.666	0.659		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
TORK 55-71-029-QRY Created On: 01/03/17 Updated On:	Q	NE	SW	1	22N	5E	Wood	0-225-2-2017		0.0	0.1	5.8	25.1	2.668	2.682	0.538		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
TORK 55-71-029-QRY Created On: 01/02/20 Updated On:	Q	NE	SW	1	22N	5E	Wood	0-225-1-2020	0.2	0.0	1.6	6.6	27.4	2.664	2.679	0.584		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
TORK 55-71-029-QRY Created On: 01/03/23 Updated On:	Q	NE	SW	1	22N	5E	Wood	0-225-33-2023	0.0	1.0	1.7	6.6	27.6	2.624	2.640	0.608		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
TOWER 55-38-036-PIT Created On: 01/12/16 Updated On:	P	W	NE	34	31N	20E	Marinette	0-225-53-2016		0.0	1.3	4.6	24.4	2.712	2.741	1.081		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
TOWER 55-38-036-PIT Created On: 01/06/21 Updated On:	P	W	NE	34	31N	20E	Marinette	0-225-109-2021	0.3	3.5	1.8	4.6	23.0	2.706	2.737	1.142		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
TOWNLINE 55-53-038-PIT Created On: 04/12/16 Updated On:	P	NE	NE	1	1N	12E	Rock	0-225-142-2016	0.7	3.5	3.1	5.3	24.9	2.646	2.688	1.575		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
TOWNLINE 55-53-038-PIT Created On: 02/06/18 Updated On:	P	NE	NE	1	1N	12E	Rock	0-225-89-2018	2.8	0.0	3.4	5.9	26.5	2.639	2.682	1.629		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
TOWNLINE 55-53-038-PIT Created On: 01/07/19 Updated On:	P	NE	NE	1	1N	12E	Rock	0-225-66-2019	3.1	0.0	3.4	4.5	24.8	2.646	2.689	1.614		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
TOWNLINE 55-53-038-PIT Created On: 03/13/24 Updated On:	P	NE	NE	1	1N	12E	Rock	0-225-198-2024	0.7	8.8	3.0	5.0	24.3	2.689	2.727	1.429		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
TOWNSEND 55-42-039-PIT Created On: 01/05/21 Updated On:	P	SE	SW	15	33N	15E	Oconto	0-225-104-2021	0.0	0.2	0.4	3.9	18.8	2.682	2.697	0.581		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
TRIEMSTRA 55-11-037-QRY Created On: 03/23/16 Updated On:	Q	NE	SW	11	13N	10E	Columbia	0-225-104-2016		0.9	0.5	10.5	39.6	2.599	2.656	2.187		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
TRIEMSTRA 55-11-037-QRY Created On: 04/01/19 Updated On:	Q	NE	SW	11	13N	10E	Columbia	0-225-122-2019	2.6	1.8	1.1	10.4	37.7	2.642	2.689	1.765		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
TRIEMSTRA 55-11-037-QRY Created On: 04/05/22 Updated On:	Q	NE	SW	11	13N	10E	Columbia	0-225-162-2022	4.1	1.5	1.5	10.7	39.1	2.618	2.673	2.086		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
* TRIMBELLE 55-47-029-QRY Created On: 09/24/20 Updated On:	Q		SW	21	26N	18W	Pierce	0-225-242-2020	3.8	0.0	11.3	12.4	44.8	2.574	2.643	2.668		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
TUBBS 55-65-017-PIT Created On: 01/23/14 Updated On:	P	NE	SE	18	41N	12W	Washburn	0-225-57-2014		0.0	7.9	5.7	22.7	2.705	2.745	1.495		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
TUBBS 55-65-017-PIT Created On: 06/09/20 Updated On:	P	NE	SE	18	41N	12W	Washburn	0-225-189-2020	1.7	0.0	2.3	4.0	18.7	2.735	2.771	1.325		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
TWESME 55-61-020-QRY Created On: 01/30/15 Updated On:	Q	SW	SE	34	21N	8W	Trempealeau	0-225-83-2015		0.0	7.1	12.1	41.4	2.590	2.651	2.378		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
TWESME 55-61-020-QRY Created On: 01/04/18 Updated On:	Q	SW	SE	34	21N	8W	Trempealeau	0-225-45-2018	1.4	0.0	6.0	13.1	42.2	2.578	2.646	2.646		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
TWESME 55-61-020-QRY Created On: 01/04/21 Updated On:	Q	SW	SE	34	21N	8W	Trempealeau	0-225-35-2021	1.2	0.0	2.7	10.4	38.7	2.586	2.650	2.496		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
TWESME 55-61-020-QRY Created On: 01/02/24 Updated On:	Q	SW	SE	34	21N	8W	Trempealeau	0-225-120-2024	0.7	6.4	8.8	11.6	40.6	2.584	2.652	2.624		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
UNION 55-15-024-PIT Created On: 07/08/15 Updated On:	P	SW	NW	36	26N	23E	Door	0-225-209-2015	0.1	0.0	7.1	6.0	25.2	2.710	2.748	1.378		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
UNION 55-15-024-PIT Created On: 06/13/22 Updated On:	P	SW	NW	36	26N	23E	Door	0-225-221-2022	0.2	8.9	2.1	5.5	26.8	2.704	2.741	1.368		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
UTECHT 55-55-018-PIT Created On: 01/12/15 Updated On:	P	NE	NE	21	30N	18W	St. Croix	0-225-62-2015		0.0	4.1	5.5	22.4	2.644	2.683	1.496		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
UTECHT 55-55-018-PIT Created On: 01/30/20 Updated On:	P	NE	NE	21	30N	18W	St. Croix	0-225-102-2020	1.1	0.0	5.5	6.0	24.8	2.634	2.678	1.662		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
UTLEY 55-24-019-QRY Created On: 01/04/16 Updated On:	Q	SE	NW	36	15N	13E	Green Lake	0-225-12-2016		0.2	0.1	4.5	18.8	2.632	2.639	0.240		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
UTLEY 55-24-019-QRY Created On: 06/13/19 Updated On:	Q	SE	NW	36	15N	13E	Green Lake	0-225-221-2019	0.0	0.3	0.5	4.9	20.1	2.620	2.632	0.455		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
UTLEY 55-24-019-QRY Created On: 01/04/22 Updated On:	Q	SE	NW	36	15N	13E	Green Lake	0-225-38-2022	0.0	0.4	0.3	4.9	19.9	2.621	2.631	0.372		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
UTLEY 55-24-019-QRY Created On: 01/29/24 Updated On:	Q	SE	NW	36	15N	13E	Green Lake	0-225-156-2024	0.0	1.1	0.9	4.9	20.6	2.620	2.630	0.363		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
V.M.I. 55-38-039-PIT Created On: 08/14/17 Updated On:	P	NE	SW	17	31N	21E	Marinette	0-225-250-2017	0.8	6.4	3.9	5.5	25.8	2.730	2.763	1.216		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
V.M.I. 55-38-039-PIT Created On: 04/28/22 Updated On:	P	NE	SW	17	31N	21E	Marinette	0-225-181-2022	0.5	0.0	2.8	5.5	26.9	2.716	2.745	1.046		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
VALDERS 55-36-026-QRY Created On: 01/05/17 Updated On:	Q	SE	NE	32	19N	22E	Manitowoc	0-225-19-2017		0.0	0.8	9.4	39.7	2.730	2.755	0.932		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
VALDERS 55-36-026-QRY Created On: 03/09/20 Updated On:	Q	SE	NE	32	19N	22E	Manitowoc	0-225-122-2020	0.2	0.2	1.9	7.9	36.2	2.745	2.768	0.810		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
VALDERS 55-36-026-QRY Created On: 02/09/23 Updated On:	Q	SE	NE	32	19N	22E	Manitowoc	0-225-142-2023	0.0	0.0	1.5	7.9	35.3	2.740	2.762	0.806		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
* VAN ALLEN 55-53-040-QRY Created On: 03/30/15 Updated On:	Q	SE	SE	15	2N	13E	Rock	0-225-109-2015	3.8	4.1	15.4	12.1	44.3	2.533	2.623	3.539		
	Approved Use : Base Aggregate																	
* VAN ALLEN 55-53-040-QRY Created On: 06/02/17 Updated On:	Q	SE	SE	15	2N	13E	Rock	0-225-202-2017	0.2	1.4	8.7	9.3	38.7	2.601	2.669	2.632		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
* VAN ALLEN 55-53-040-QRY Created On: 03/09/20 Updated On:	Q	SE	SE	15	2N	13E	Rock	0-225-126-2020	0.1	2.2	8.2	8.9	36.4	2.576	2.653	3.012		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
VERMILLION 55-03-039-PIT Created On: 01/30/14 Updated On:	P	NW	SW	14	35N	13W	Barron	0-225-67-2014		0.0	1.6	4.6	18.5	2.710	2.735	0.942		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
VERMILLION 55-03-039-PIT Created On: 01/09/20 Updated On:	P	NW	SW	14	35N	13W	Barron	0-225-88-2020	4.2	0.0	2.6	4.0	19.5	2.711	2.735	0.881		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
VEUM 55-09-068-PIT Created On: 01/17/14 Updated On:	P	NE	NW	35	28N	10W	Chippewa	0-225-54-2014		0.0	5.5	6.9	26.3	2.606	2.649	1.625		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
VEUM 55-09-068-PIT Created On: 01/08/19 Updated On:	P	NE	NW	35	28N	10W	Chippewa	0-225-82-2019	4.2	0.0	6.7	7.1	26.8	2.593	2.631	1.450		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
VEUM 55-09-068-PIT Created On: 01/02/24 Updated On:	P	NE	NW	35	28N	10W	Chippewa	0-225-79-2024	3.2	0.0	4.6	5.4	22.7	2.677	2.707	1.123		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
VICTORY 55-62-034-QRY Created On: 08/22/22 Updated On:	Q	NE	NE	34	12N	7W	Vernon	0-225-254-2022	1.2	10.4	7.0	14.5	48.1	2.578	2.646	2.654		
	Approved Use : CONCRETE, OGBC, Base Aggregate																	
VIENNA 55-13-099-QRY Created On: 01/05/15 Updated On:	Q	NE	SW	34	9N	9E	Dane	0-225-7-2015	0.7	0.7	2.0	6.8	30.1	2.610	2.670	2.310		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
VIENNA 55-13-099-QRY Created On: 01/03/18 Updated On:	Q	NE	SW	34	9N	9E	Dane	0-225-21-2018	2.1	1.0	3.4	8.3	35.4	2.539	2.619	3.158		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
VIENNA 55-13-099-QRY Created On: 09/17/20 Updated On:	Q	NE	SW	34	9N	9E	Dane	0-225-241-2020	2.0	2.4	3.7	7.8	31.3	2.614	2.667	2.024		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
VIENNA 55-13-099-QRY Created On: 01/03/23 Updated On:	Q	NE	SW	34	9N	9E	Dane	0-225-3-2023	0.6	2.4	8.8	7.2	32.8	2.607	2.662	2.099	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
VINLAND 55-70-032-QRY Created On: 06/05/14 Updated On:	Q	E	NW	21	19N	16E	Winnebago	0-225-180-2014		2.6	3.0	6.0	25.6	2.762	2.791	1.040	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
VINLAND 55-70-032-QRY Created On: 01/02/24 Updated On:	Q	E	NW	21	19N	16E	Winnebago	0-225-99-2024	0.0	2.9	0.5	5.0	22.1	2.785	2.806	0.751	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
* VOEGGLI 55-23-027-QRY Created On: 04/02/14 Updated On:	Q	NE	NE	35	4N	7E	Green	0-225-109-2014	5.1	1.2	3.7	8.9	34.8	2.522	2.619	3.823	
	Approved Use : HMA<E-3, HMA>=E-3, OGBC, Base Aggregate																
* VOEGGLI 55-23-027-QRY Created On: 04/11/18 Updated On:	Q	NE	NE	35	4N	7E	Green	0-225-165-2018	0.7	15.6	14.2	13.5	46.4	2.523	2.640	4.674	
	Approved Use : Base Aggregate																
* VOEGGLI 55-23-027-QRY Created On: 07/28/21 Updated On:	Q	NE	NE	35	4N	7E	Green	0-225-254-2021	0.9	6.7	2.8	6.1	29.7	2.608	2.668	2.301	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
VOLENBERG 55-13-100-PIT Created On: 01/05/16 Updated On:	P		NW	19	6N	12E	Dane	0-225-17-2016	6.9	0.0	6.5	6.6	34.2	2.618	2.678	2.294	
	Approved Use : HMA<E-3, HMA>=E-3, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description						Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range					County	100	500	OD	SSD	Crse
VOLENBERG 55-13-100-PIT Created On: 01/04/21 Updated On:	P		NW	19	6N	12E	Dane	0-225-3-2021	4.0	0.0	8.0	8.4	34.5	2.640	2.693	1.982
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate															
* VOLENBERG QUARRY 55-13-101-QRY Created On: 01/05/16 Updated On:	Q		NW	19	6N	12E	Dane	0-225-16-2016		9.5	12.9	5.5	25.9	2.668	2.715	1.768
	Approved Use : Base Aggregate															
* VOLENBERG QUARRY 55-13-101-QRY Created On: 04/19/19 Updated On:	Q		NW	19	6N	12E	Dane	0-225-153-2019	0.8	16.8	14.6	6.2	28.4	2.649	2.701	1.994
	Approved Use : Base Aggregate															
VOLKMAN 55-63-022-PIT Created On: 07/18/19 Updated On:	P	S	NE	17	41N	12E	Vilas	0-225-237-2019	2.4	0.0	0.6	4.8	19.0	2.682	2.709	1.012
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate															
VOLKMAN 55-63-022-PIT Created On: 01/02/24 Updated On:	P	S	NE	17	41N	12E	Vilas	0-225-56-2024	0.8	0.0	0.3	4.2	18.4	2.701	2.729	1.041
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate															
W.E. ROCK 55-33-029-QRY Created On: 04/13/21 Updated On:	Q	NE	NE	30	1N	1E	Lafayette	0-225-182-2021	0.0	3.6	1.6	16.1	44.6	2.594	2.664	2.668
	Approved Use : CONCRETE, OGBC, Base Aggregate															
W.E. ROCK 55-33-029-QRY Created On: 01/29/24 Updated On:	Q	NE	NE	30	1N	1E	Lafayette	0-225-151-2024	0.2	4.1	4.6	8.7	34.9	2.552	2.640	3.426
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate															

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
WABASHA SAND & GRAVEL 27-00-020-PIT Created On: 08/12/21 Updated On:	P		32	11N	10W	Wabasha		0-225-263-2021	0.5	1.7	1.4	3.3	17.7	2.685	2.706	0.757	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
WAGNER 55-38-041-QRY Created On: 08/28/14 Updated On:	Q	NW	17	33N	22E	Marinette		0-225-252-2014		0.5	1.3	6.8	29.9	2.733	2.771	1.375	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
WAGNER 55-38-041-QRY Created On: 05/10/18 Updated On:	Q	NW	17	33N	22E	Marinette		0-225-202-2018	0.0	1.8	0.9	7.8	31.9	2.726	2.761	1.250	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
WAGNER 55-38-041-QRY Created On: 04/28/22 Updated On:	Q	NW	17	33N	22E	Marinette		0-225-183-2022	0.3	1.0	1.8	6.3	28.1	2.711	2.750	1.442	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
WALDENBERGER 55-32-017-QRY Created On: 04/24/14 Updated On:	Q		23	17N	7W	La Crosse		0-225-138-2014		0.0	5.3	12.0	45.3	2.561	2.633	2.809	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
WALDENBERGER 55-32-017-QRY Created On: 03/29/17 Updated On:	Q		23	17N	7W	La Crosse		0-225-93-2017	0.3	0.0	3.2	11.8	44.2	2.521	2.610	3.526	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
WALDENBERGER 55-32-017-QRY Created On: 01/03/20 Updated On:	Q		23	17N	7W	La Crosse		0-225-22-2020	1.1	0.0	6.3	10.8	40.5	2.557	2.633	2.981	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
WALDENBERGER 55-32-017-QRY Created On: 01/03/23 Updated On:	Q		23	17N	7W	La Crosse	0-225-22-2023	0.4	6.7	7.8	12.7	45.5	2.529	2.611	3.230			
	Approved Use : HMA<MT, CONCRETE, OGBC, Base Aggregate																	
* WALTERS ROAD PIT 55-38-045-PIT Created On: 06/13/19 Updated On:	P	NW	SW 7	31N	22E	Marinette	0-225-219-2019	0.6	0.0	3.5	5.8	27.6	2.712	2.750	1.384			
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
* WALTERS ROAD QUARRY 55-38-044-QRY Created On: 06/13/19 Updated On:	Q	NW	SW 7	31N	22E	Marinette	0-225-218-2019	0.4	7.4	3.6	6.5	26.4	2.691	2.732	1.533			
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
WARMKA 55-14-034-QRY Created On: 04/11/14 Updated On:	Q	NE	NW 9	12N	14E	Dodge	0-225-124-2014		1.2	2.4	5.6	25.1	2.764	2.788	0.894			
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
WARMKA 55-14-034-QRY Created On: 01/03/17 Updated On:	Q	NE	NW 9	12N	14E	Dodge	0-225-8-2017		4.0	2.4	5.8	25.1	2.763	2.788	0.904			
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
WARMKA 55-14-034-QRY Created On: 04/01/19 Updated On:	Q	NE	NW 9	12N	14E	Dodge	0-225-118-2019		4.6	2.5	5.2	24.3	2.757	2.785	1.017			
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
WARMKA 55-14-034-QRY Created On: 01/04/22 Updated On:	Q	NE	NW 9	12N	14E	Dodge	0-225-3-2022	0.0	1.8	1.5	5.1	24.5	2.750	2.780	1.070			
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Coarse Sp. Gravity		Coarse Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
WARTGOW 55-02-019-PIT Created On: 05/23/14 Updated On:	P	NE	NW	4	42N	2W	Ashland	0-225-176-2014		0.0	2.2	4.2	18.5	2.761	2.778	0.606		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
WARTGOW 55-02-019-PIT Created On: 06/11/20 Updated On:	P	NE	NW	4	42N	2W	Ashland	0-225-195-2020		0.0	2.3	4.0	18.4	2.758	2.783	0.913		
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																	
WAUKESHA LIME & STONE 55-67-042-QRY Created On: 01/04/16 Updated On:	Q	SE	SE	26	7N	19E	Waukesha	0-225-4-2016		9.0	3.0	4.3	20.5	2.712	2.751	1.426		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
WAUKESHA LIME & STONE 55-67-041-PIT Created On: 01/21/16 Updated On:	P	SE	SE	26	7N	8E	Waukesha	0-225-71-2016	1.2	4.7	2.3	4.7	23.4	2.713	2.748	1.311		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
WAUKESHA LIME & STONE 55-67-042-QRY Created On: 02/05/19 Updated On:	Q	SE	SE	26	7N	19E	Waukesha	0-225-98-2019	0.3	1.2	0.2	5.7	27.4	2.682	2.718	1.370		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
WAUKESHA LIME & STONE 55-67-041-PIT Created On: 01/05/21 Updated On:	P	SE	SE	26	7N	8E	Waukesha	0-225-96-2021	0.4	2.2	2.1	5.7	29.2	2.693	2.733	1.502		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
WAUKESHA LIME & STONE 55-67-042-QRY Created On: 01/04/22 Updated On:	Q	SE	SE	26	7N	19E	Waukesha	0-225-54-2022	0.3	0.9	0.5	4.1	20.0	2.776	2.793	0.639		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
WEBSTER PIT 55-54-031-PIT Created On: 01/10/23 Updated On:	P	NE	NE	7	34N	4W	Rusk	0-225-116-2023	1.1	0.0	2.2	4.1	18.5	2.768	2.790	0.815	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
WEISENBERGER 55-37-083-QRY Created On: 01/06/16 Updated On:	Q		N	1	28N	5E	Marathon	0-225-32-2016		0.0	0.9	4.5	19.3	2.689	2.720	1.154	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
WEISENBERGER 55-37-083-QRY Created On: 01/04/19 Updated On:	Q		N	1	28N	5E	Marathon	0-225-35-2019		0.0	0.4	4.8	19.6	2.673	2.712	1.471	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
WEISENBERGER 55-37-083-QRY Created On: 01/13/22 Updated On:	Q		N	1	28N	5E	Marathon	0-225-109-2022	0.0	0.3	0.2	4.5	17.7	2.829	2.846	0.615	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
WENDERS 55-06-028-QRY Created On: 05/09/16 Updated On:	Q			10	20N	12W	Buffalo	0-225-163-2016		0.0	11.8	13.7	40.7	2.599	2.660	2.318	
	Approved Use : CONCRETE, Base Aggregate																
WENDERS 55-06-028-QRY Created On: 01/08/19 Updated On:	Q			10	20N	12W	Buffalo	0-225-80-2019	0.7	0.0	2.6	8.8	32.6	2.644	2.691	1.770	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
WENDERS 55-06-028-QRY Created On: 01/04/22 Updated On:	Q			10	20N	12W	Buffalo	0-225-9-2022	0.1	1.7	4.7	9.4	37.1	2.630	2.683	2.015	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
* WEST BEND S & G 55-66-020-PIT Created On: 02/28/14 Updated On:	P	SW	SE	8	11N	19E	Washington	0-225-91-2014	0.2	0.6	1.1	5.3	24.6	2.725	2.752	1.019	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
* WEST BEND S & G 55-66-020-PIT Created On: 03/22/19 Updated On:	P	SW	SE	8	11N	19E	Washington	0-225-116-2019	0.0	1.1	0.3	4.8	27.3	2.757	2.780	0.819	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
WESTPHAL 55-14-035-QRY Created On: 01/03/18 Updated On:	Q	SE	SE	8	10N	14E	Dodge	0-225-20-2018		13.5	8.9	5.4	25.0	2.689	2.733	1.636	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
WESTPHAL 55-14-035-QRY Created On: 05/17/21 Updated On:	Q	SE	SE	8	10N	14E	Dodge	0-225-209-2021	0.0	8.6	8.2	5.7	25.3	2.689	2.732	1.614	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
WESTPHAL 55-14-035-QRY Created On: 02/06/23 Updated On:	Q	SE	SE	8	10N	14E	Dodge	0-225-141-2023	0.0	17.0	10.1	4.8	30.4	2.703	2.743	1.501	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
WESTRES 55-13-066-QRY Created On: 07/03/14 Updated On:	Q	SW	NE	2	7N	6E	Dane	0-225-206-2014	1.0	6.0	4.0	11.3	38.3	2.556	2.631	2.931	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
WESTRES 55-13-066-QRY Created On: 04/06/17 Updated On:	Q	SW	NE	2	7N	6E	Dane	0-225-110-2017	0.7	1.9	2.2	11.0	37.3	2.613	2.672	2.268	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
WESTRES 55-13-066-QRY Created On: 03/29/21 Updated On:	Q	SW	NE	2	7N	6E	Dane	0-225-161-2021	0.3	7.5	3.2	9.1	33.6	2.573	2.646	2.848	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
WESTRES 55-13-066-QRY Created On: 01/02/24 Updated On:	Q	SW	NE	2	7N	6E	Dane	0-225-73-2024	0.7	4.8	2.0	11.6	42.5	2.494	2.576	3.284	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
WETZEL 55-12-024-QRY Created On: 04/10/14 Updated On:	Q	NW	SE	31	7N	6W	Crawford	0-225-119-2014		1.2	4.8	7.8	30.0	2.574	2.632	2.247	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
WETZEL 55-12-024-QRY Created On: 01/05/17 Updated On:	Q	NW	SE	31	7N	6W	Crawford	0-225-33-2017		1.2	3.3	6.7	28.7	2.633	2.685	1.977	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
WETZEL 55-12-024-QRY Created On: 01/03/20 Updated On:	Q	NW	SE	31	7N	6W	Crawford	0-225-23-2020	2.3	3.6	2.9	12.1	40.5	2.558	2.633	2.939	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
WETZEL 55-12-024-QRY Created On: 01/03/23 Updated On:	Q	NW	SE	31	7N	6W	Crawford	0-225-71-2023	1.2	4.7	0.6	11.7	39.2	2.604	2.662	2.251	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
WHELAN 55-64-039-PIT Created On: 03/24/16 Updated On:	P	SE	NE	1	1N	15E	Walworth	0-225-110-2016		0.0	2.7	5.6	26.6	2.693	2.726	1.229	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
WHELAN 55-64-039-PIT Created On: 01/05/21 Updated On:	P	SE	NE	1	1N	15E	Walworth	0-225-84-2021	0.0	5.1	3.6	5.2	29.6	2.689	2.727	1.400	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
WHITEWATER LIMESTONE 55-99-052-QRY Created On: 10/03/17 Updated On:	Q	NW	SW	9	4N	15E	Walworth	0-225-277-2017	1.1	2.6	2.1	8.8	34.3	2.618	2.678	2.309	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
WHITEWATER LIMESTONE 55-99-052-QRY Created On: 04/09/20 Updated On:	Q	NW	SW	9	4N	15E	Walworth	0-225-152-2020	0.2	1.8	6.1	8.1	35.2	2.627	2.683	2.152	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
WHITEWATER LIMESTONE 55-99-052-QRY Created On: 02/10/22 Updated On:	Q	NW	SW	9	4N	15E	Walworth	0-225-121-2022	0.6	4.6	7.9	8.1	33.6	2.612	2.675	2.419	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
WIEDL 55-41-024-QRY Created On: 06/10/16 Updated On:	Q	NW	NW	29	16N	2W	Monroe	0-225-195-2016	2.0	0.0	4.6	11.3	39.7	2.547	2.618	2.814	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
WIEDL 55-41-024-QRY Created On: 05/03/18 Updated On:	Q	NW	NW	29	16N	2W	Monroe	0-225-190-2018	0.7	0.0	3.2	8.4	35.2	2.591	2.650	2.294	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
WIEDL 55-41-024-QRY Created On: 08/12/21 Updated On:	Q	NW	NW	29	16N	2W	Monroe	0-225-261-2021	3.4	0.0	8.4	11.4	41.1	2.566	2.633	2.614	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
WIEDL 55-41-024-QRY Created On: 01/02/24 Updated On:	Q	NW	NW	29	16N	2W	Monroe	0-225-23-2024	2.0	2.6	5.0	11.8	40.5	2.576	2.642	2.565		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
WIEMEIR 26-00-005-PIT Created On: 04/23/15 Updated On:	P	SW	NW	33	48N	47W	Gogebic	0-225-130-2015		6.3	13.9	5.4	23.0	2.717	2.760	1.581		
	Approved Use : Base Aggregate																	
WIEMEIR 26-00-005-PIT Created On: 04/30/21 Updated On:	P	SW	NW	33	48N	47W	Gogebic	0-225-193-2021	1.8	11.1	17.7	5.6	24.9	2.715	2.754	1.456		
	Approved Use : Base Aggregate																	
WIESER 55-47-033-QRY Created On: 06/08/17 Updated On:	Q	E	NE	9	25N	16W	Pierce	0-225-206-2017		0.0	3.9	11.8	40.5	2.581	2.644	2.458		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
WIESER 55-47-033-QRY Created On: 06/06/19 Updated On:	Q	E	NE	9	25N	16W	Pierce	0-225-206-2019	1.9	0.0	7.6	9.7	39.9	2.555	2.626	2.814		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
WIESER 55-47-033-QRY Created On: 04/19/22 Updated On:	Q	E	NE	9	25N	16W	Pierce	0-225-180-2022	2.8	0.0	4.9	12.8	42.9	2.566	2.637	2.779		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
WILLIAMS 55-11-039-QRY Created On: 03/30/15 Updated On:	Q	SE	NE	19	12N	8E	Columbia	0-225-103-2015		0.2	0.2	6.0	24.1	2.633	2.646	0.477		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
WILLIAMS 55-11-039-QRY Created On: 01/03/18 Updated On:	Q	SE	NE	19	12N	8E	Columbia	0-225-8-2018	0.0	0.0	0.0	4.4	19.7	2.634	2.644	0.400		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
WILLIAMS 55-11-039-QRY Created On: 01/04/21 Updated On:	Q	SE	NE	19	12N	8E	Columbia	0-225-41-2021	0.0	0.0	0.4	6.1	25.1	2.627	2.639	0.481		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
WILLIAMS 55-11-039-QRY Created On: 01/02/24 Updated On:	Q	SE	NE	19	12N	8E	Columbia	0-225-19-2024	0.1	0.3	0.4	5.3	23.1	2.653	2.659	0.219		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
WILTON 55-41-027-QRY Created On: 07/25/19 Updated On:	Q		SW	35	16N	1W	Monroe	0-225-250-2019		0.0	4.4	14.1	46.6	2.573	2.637	2.467		
	Approved Use : Base Aggregate																	
WILTON 55-41-027-QRY Created On: 01/04/22 Updated On:	Q		SW	35	16N	1W	Monroe	0-225-73-2022		1.2	5.3	13.9	45.7	2.556	2.627	2.796		
	Approved Use : OGBC, Base Aggregate																	
WIMMIE 55-49-026-PIT Created On: 01/07/16 Updated On:	P		NW	28	23N	9E	Portage	0-225-43-2016	0.2	0.0	0.8	5.1	24.3	2.705	2.729	0.876		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
WIMMIE 55-49-026-PIT Created On: 01/04/21 Updated On:	P		NW	28	23N	9E	Portage	0-225-22-2021	0.4	2.2	0.4	6.2	26.9	2.726	2.747	0.792		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
WIMMIE #2 55-49-030-PIT Created On: 09/05/23 Updated On:	P	SW	21	23N	9E	Portage	0-225-248-2023	1.0	1.6	1.7	6.1	28.2	2.682	2.709	0.997			
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
WISSOTA RUGBY S&G 55-66-021-PIT Created On: 02/07/14 Updated On:	P	SE	NE	34	10N	19E	Washington	0-225-85-2014	1.2	1.2	1.4	5.1	26.4	2.740	2.762	0.789		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
WISSOTA RUGBY S&G 55-66-021-PIT Created On: 01/07/19 Updated On:	P	SE	NE	34	10N	19E	Washington	0-225-43-2019	0.2	4.6	1.1	5.2	27.4	2.731	2.760	1.095		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
WISSOTA RUGBY S&G 55-66-021-PIT Created On: 01/29/24 Updated On:	P	SE	NE	34	10N	19E	Washington	0-225-160-2024	0.4	9.7	1.1	6.8	31.2	2.725	2.755	1.095		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
WITTWER 55-04-016-PIT Created On: 05/11/15 Updated On:	P	NE	SE	30	44N	7W	Bayfield	0-225-160-2015		0.0	3.6	4.8	20.5	2.791	2.816	0.923		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
WITTWER 55-04-016-PIT Created On: 01/06/20 Updated On:	P	NE	SE	30	44N	7W	Bayfield	0-225-32-2020	0.8	0.0	4.0	4.0	17.4	2.766	2.803	1.345		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
* WK 55-13-102-QRY Created On: 03/20/15 Updated On:	Q	SW	SW	8	7N	8E	Dane	0-225-101-2015	1.2	2.3	6.0	7.0	31.3	2.626	2.681	2.081		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
* WK 55-13-102-QRY Created On: 01/03/18 Updated On:	Q	SW	SW	8	7N	8E	Dane	0-225-22-2018	4.6	2.0	11.1	8.7	40.4	2.553	2.633	3.112		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
* WK 55-13-102-QRY Created On: 01/05/21 Updated On:	Q	SW	SW	8	7N	8E	Dane	0-225-93-2021	1.8	3.0	7.4	7.2	31.6	2.612	2.672	2.271		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
WOLF 55-67-043-PIT Created On: 04/03/17 Updated On:	P		E	6	6N	18E	Waukesha	0-225-102-2017		2.8	2.7	5.2	24.9	2.723	2.750	1.000		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
WOLF 55-67-043-PIT Created On: 08/03/21 Updated On:	P		E	6	6N	18E	Waukesha	0-225-257-2021	0.8	1.3	2.4	4.1	23.0	2.736	2.766	1.064		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
WOLF RIVER 55-34-025-PIT Created On: 05/26/16 Updated On:	P	NW	SW	36	31N	14E	Langlade	0-225-189-2016	0.4	0.0	2.1	7.7	26.8	2.635	2.658	0.870		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
WOLF RIVER 55-34-025-PIT Created On: 01/04/21 Updated On:	P	NW	SW	36	31N	14E	Langlade	0-225-14-2021	0.0	0.4	0.3	4.1	23.0	2.664	2.684	0.772		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
WOZNIAK 55-09-074-PIT Created On: 01/07/15 Updated On:	P	SW	NE	1	28N	5W	Chippewa	0-225-11-2015		0.0	1.8	3.6	17.8	2.658	2.689	1.169		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
WOZNIAK 55-09-074-QRY Created On: 07/23/15 Updated On:	Q	NW	SE	1	28N	5W	Chippewa	0-225-216-2015		0.0	5.3	5.2	21.3	2.977	3.001	0.808		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
WOZNIAK 55-09-074-PIT Created On: 03/08/18 Updated On:	P	SW	NE	1	28N	5W	Chippewa	0-225-115-2018	0.5	0.0	3.1	3.9	17.4	2.909	2.935	0.866		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
WOZNIAK 55-09-074-PIT Created On: 01/05/21 Updated On:	P	SW	NE	1	28N	5W	Chippewa	0-225-91-2021	0.1	0.0	1.9	4.4	20.1	2.878	2.889	0.374		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
WOZNIAK 55-09-074-QRY Created On: 01/02/24 Updated On:	Q	NW	SE	1	28N	5W	Chippewa	0-225-82-2024	0.0	0.0	1.1	4.2	18.9	2.936	2.946	0.351		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
WRIGLY 55-13-114-QRY Created On: 06/02/17 Updated On:	Q		NW	29	6N	12E	Dane	0-225-201-2017		3.5	3.8	7.0	28.6					
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
WRIGLY 55-13-114-QRY Created On: 06/07/18 Updated On:	Q		NW	29	6N	12E	Dane	0-225-220-2018	0.5	11.3	17.2	7.9	33.3	2.619	2.683	2.428		
	Approved Use : Base Aggregate																	
WRIGLY 55-13-114-QRY Created On: 01/04/22 Updated On:	Q		NW	29	6N	12E	Dane	0-225-55-2022	0.1	17.9	6.2	7.6	30.4	2.615	2.680	2.483		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
ZANDER 55-13-109-PIT Created On: 03/14/18 Updated On:	P	NW	SW	11	7N	7E	Dane	0-225-119-2018	10.1	5.3	16.3	16.4	46.2	2.542	2.621	3.113	
	Approved Use : Base Aggregate																
ZANDER 55-13-109-PIT Created On: 01/07/19 Updated On:	P	NW	SW	11	7N	7E	Dane	0-225-46-2019	4.1	2.2	6.3	9.7	37.0	2.602	2.663	2.362	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
ZANDER 55-13-122-QRY Created On: 06/20/19 Updated On:	Q	NW	SW	11	7N	7E	Dane	0-225-222-2019	0.9	3.3	8.3	8.3	39.0	2.581	2.647	2.581	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
ZANDER 55-13-122-QRY Created On: 04/26/23 Updated On:	Q	NW	SW	11	7N	7E	Dane	0-225-208-2023	1.8	10.9	9.2	11.6	41.5	2.556	2.631	2.938	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
ZANDER 55-13-109-PIT Created On: 01/02/24 Updated On:	P	NW	SW	11	7N	7E	Dane	0-225-129-2024	3.0	0.0	7.8	8.5	34.7	2.619	2.672	2.043	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
ZART 55-22-061-QRY Created On: 04/17/15 Updated On:	Q	SE	SE	7	6N	3W	Grant	0-225-126-2015	2.2	1.3	6.2	9.9	35.6	2.595	2.655	2.302	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
ZART 55-22-061-QRY Created On: 08/15/17 Updated On:	Q	SE	SE	7	6N	3W	Grant	0-225-255-2017	2.4	6.1	2.1	9.4	34.1	2.606	2.663	2.158	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
ZART 55-22-061-QRY Created On: 01/04/18 Updated On:	Q	SE	SE	7	6N	3W	Grant	0-225-67-2018	1.0	5.6	7.7	10.6	38.6	2.620	2.677	2.196		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
ZART 55-22-061-QRY Created On: 01/05/21 Updated On:	Q	SE	SE	7	6N	3W	Grant	0-225-59-2021	1.3	5.7	9.4	13.7	43.9	2.628	2.684	2.135		
	Approved Use : CONCRETE, OGBC, Base Aggregate																	
ZART 55-22-061-QRY Created On: 01/02/24 Updated On:	Q	SE	SE	7	6N	3W	Grant	0-225-36-2024	0.3	3.3	2.4	9.2	33.7	2.627	2.684	2.189		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
ZEINERT 55-58-045-PIT Created On: 05/12/16 Updated On:	P	SE	SW	3	28N	12E	Shawano	0-225-170-2016	0.4	0.0	0.9	8.8	34.6	2.631	2.662	1.205		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
ZEINERT 55-58-045-PIT Created On: 01/04/21 Updated On:	P	SE	SW	3	28N	12E	Shawano	0-225-16-2021	0.3	1.4	2.1	9.6	34.0	2.641	2.665	0.920		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
ZIOLKOWSKI 55-37-087-PIT Created On: 01/02/18 Updated On:	P	SW	SE	29	27N	9'E	Marathon	0-225-3-2018	0.6	0.0	1.0	7.0	30.2	2.647	2.672	0.940		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
ZIOLKOWSKI 55-37-087-PIT Created On: 01/02/24 Updated On:	P	SW	SE	29	27N	9'E	Marathon	0-225-44-2024	0.7	1.4	4.8	7.5	32.2	2.645	2.670	0.970		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Coarse Sp. Gravity		Coarse Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
ZOBEL 55-56-031-QRY Created On: 06/05/15 Updated On:	Q			21	12N	4E	Sauk	0-225-188-2015		0.0	1.5	10.3	36.7	2.620	2.673	2.006		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
ZOBEL 55-56-031-QRY Created On: 01/04/18 Updated On:	Q			21	12N	4E	Sauk	0-225-51-2018	0.4	0.0	1.7	9.1	35.2	2.631	2.682	1.951		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
ZOBEL 55-56-031-QRY Created On: 01/04/21 Updated On:	Q			21	12N	4E	Sauk	0-225-33-2021	0.6	0.0	0.6	11.4	39.0	2.584	2.644	2.334		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
ZOBEL 55-56-031-QRY Created On: 01/02/24 Updated On:	Q			21	12N	4E	Sauk	0-225-22-2024	0.7	12.9	1.4	8.6	33.4	2.653	2.699	1.758		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
ZOGG 55-62-033-QRY Created On: 07/02/15 Updated On:	Q	SW	SE	27	14N	7W	Vernon	0-225-206-2015		0.0	6.9	11.5	39.7	2.594	2.656	2.412		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
ZOGG 55-62-033-QRY Created On: 01/03/18 Updated On:	Q	SW	SE	27	14N	7W	Vernon	0-225-12-2018	1.0	0.0	3.8	9.9	35.4	2.605	2.667	2.408		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
ZOGG 55-62-033-QRY Created On: 01/04/21 Updated On:	Q	SW	SE	27	14N	7W	Vernon	0-225-29-2021	0.9	0.0	1.2	7.8	32.3	2.600	2.667	2.583		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 05/06/2024

TEST YEARS BETWEEN 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse			Absorp. %			
	P/Q	Qrt	Qrt	Sect	Town	Range	County					LA Wear (%)	Sp. Gravity	Absorp. %	100	500	OD	SSD
ZOGG 55-62-033-QRY Created On: 01/02/24 Updated On:	Q	SW	SE	27	14N	7W	Vernon	0-225-38-2024	0.2	8.9	6.8	9.9	36.6	2.601	2.667	2.529		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

Prepared by:
 Wisconsin Department of Transportation
 Bureau of Highway Construction
 Quality Management Section

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse					
	P/Q	Qrt	Qrt	Sect	Town	Range	County	LA Wear (%)					Sp. Gravity		Absorp. %			
												100	500	OD	SSD	Crse	Fine	
ADAMS -- WI																		
MANTHEY EAST 55-01-004-PIT Created On: 04/07/16 Updated On:	P			26	17N	7E	Adams	0-225-133-2016		0.0	1.9	8.8	32.4	2.697	2.737	1.494		
								Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate										
MANTHEY EAST 55-01-004-PIT Created On: 01/04/21 Updated On:	P			26	17N	7E	Adams	0-225-23-2021	4.5	2.6	4.3	8.4	34.5	2.702	2.741	1.411		
								Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate										
RILEY 55-01-007-PIT Created On: 07/10/14 Updated On:	P	NW	SW	19	14N	7E	Adams	0-225-215-2014		0.0	1.1	5.9	25.5	2.777	2.808	1.092		
								Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate										
RILEY 55-01-007-PIT Created On: 05/01/15 Updated On:	P	NW	SW	19	14N	7E	Adams	0-225-141-2015		0.0	2.8	7.5	28.9	2.819	2.846	0.969		
								Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate										
RILEY 55-01-007-PIT Created On: 04/28/22 Updated On:	P	NW	SW	19	14N	7E	Adams	0-225-192-2022	0.1	0.0	0.6	6.2	25.7	2.770	2.803	1.188		
								Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate										
SEVEN SISTERS 55-01-008-QRY Created On: 08/25/16 Updated On:	Q			36	20N	7E	Adams	0-225-248-2016		0.9	0.7	4.6	20.7	2.631	2.646	0.591		
								Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate										
SEVEN SISTERS 55-01-008-QRY Created On: 01/04/19 Updated On:	Q			36	20N	7E	Adams	0-225-33-2019	0.2	0.0	0.9	4.7	19.6	2.625	2.642	0.666		
								Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate										

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse					
	P/Q	Qrt	Qrt	Sect	Town	Range	County	LA Wear (%) 100 500					Sp. Gravity OD SSD	Absorp. % Crse Fine				
ADAMS -- WI																		
SEVEN SISTERS 55-01-008-QRY Created On: 01/04/22 Updated On:	Q			36	20N	7E	Adams	0-225-36-2022	4.2	12.0	7.8	6.1	22.9	2.543	2.598	2.169		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
ASHLAND -- WI																		
HIGHBRIDGE 55-02-005-QRY Created On: 01/04/23 Updated On:	Q	S	SW	16	45N	3W	Ashland	0-225-91-2023	0.1	0.4	0.3	4.5	21.9	2.588	2.612	0.926		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
*HIGHBRIDGE NORTH 55-02-005-QRY Created On: 02/28/14 Updated On:	Q	S	SW	16	45N	3W	Ashland	0-225-90-2014		0.0	3.1	5.6	24.0	2.604	2.624	0.774		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
*HIGHBRIDGE NORTH 55-02-005-QRY Created On: 05/19/17 Updated On:	Q	S	SW	16	45N	3W	Ashland	0-225-192-2017		0.0	0.7	4.5	21.0	2.615	2.633	0.685		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
*HIGHBRIDGE NORTH 55-02-005-QRY Created On: 01/06/20 Updated On:	Q	S	SW	16	45N	3W	Ashland	0-225-33-2020	0.1	0.0	1.2	5.2	24.3	2.623	2.637	0.549		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
PALECEK 55-02-012-PIT Created On: 06/16/22 Updated On:	P	NW	SW	24	47N	1W	Ashland	0-225-230-2022	0.6	2.1	2.4	4.2	18.9	2.753	2.780	1.004		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
PETERSON MARENGO 55-02-013-PIT Created On: 05/19/16 Updated On:	P	N	SW	18	45N	4W	Ashland	0-225-182-2016		0.0	2.6	5.4	23.1	2.639	2.693	2.050		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
ASHLAND -- WI																		
PETERSON MARENGO 55-02-013-PIT Created On: 05/10/21 Updated On:	P	N	SW	18	45N	4W	Ashland	0-225-204-2021	2.5	0.0	14.2	5.8	23.7	2.686	2.741	2.034		
Approved Use : Base Aggregate																		
WARTGOW 55-02-019-PIT Created On: 05/23/14 Updated On:	P	NE	NW	4	42N	2W	Ashland	0-225-176-2014		0.0	2.2	4.2	18.5	2.761	2.778	0.606		
Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																		
WARTGOW 55-02-019-PIT Created On: 06/11/20 Updated On:	P	NE	NW	4	42N	2W	Ashland	0-225-195-2020		0.0	2.3	4.0	18.4	2.758	2.783	0.913		
Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																		
BARRON -- WI																		
BOHL #720 55-03-006-PIT Created On: 02/13/17 Updated On:	P	NW	SE	10	32N	11W	Barron	0-225-70-2017		0.0	2.2	4.4	18.9	2.687	2.715	1.015		
Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																		
BOHL #720 55-03-006-PIT Created On: 03/01/22 Updated On:	P	NW	SE	10	32N	11W	Barron	0-225-135-2022	2.5	2.3	2.3	4.0	18.5	2.685	2.715	1.106		
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
BRUHA 55-03-008-PIT Created On: 01/09/15 Updated On:	P	SW	NE	13	36N	12W	Barron	0-225-44-2015		0.0	2.8	3.5	15.8	2.755	2.789	1.234		
Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																		
BRUHA 55-03-008-PIT Created On: 01/08/20 Updated On:	P	SW	NE	13	36N	12W	Barron	0-225-55-2020	0.7	0.0	2.4	3.6	16.5	2.767	2.794	0.973		
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse					
	P/Q	Qrt	Qrt	Sect	Town	Range	County	LA Wear (%) 100 500					Sp. Gravity OD SSD		Absorp. % Crse Fine			
BARRON -- WI																		
BURIC 55-03-009-PIT Created On: 06/13/16 Updated On:	P	NW	NW	14	33N	10W	Barron	0-225-204-2016		0.0	1.2	5.6	22.0	2.730	2.754	0.876		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
BURIC 55-03-009-PIT Created On: 01/04/22 Updated On:	P	NW	NW	14	33N	10W	Barron	0-225-85-2022	2.7	0.0	1.9	4.6	21.2	2.667	2.689	0.853		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
CAMPIA PIT 55-03-010-PIT Created On: 01/02/24 Updated On:	P	NE	NE	8	35N	10W	Barron	0-225-87-2024	1.3	0.0	0.9	4.2	19.6	2.708	2.734	0.959		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
CEMSTONE CUMBERLAND PIT 55-03-037-PIT Created On: 01/25/16 Updated On:	P	S	SE	35	36N	13W	Barron	0-225-80-2016		0.0	3.2	3.9	18.3	2.726	2.758	1.181		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
CEMSTONE CUMBERLAND PIT 55-03-037-PIT Created On: 01/05/21 Updated On:	P	S	SE	35	36N	13W	Barron	0-225-86-2021	4.1	0.0	2.5	4.0	18.0	2.698	2.731	1.198		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
EGSTAD 55-03-014-PIT Created On: 05/18/17 Updated On:	P	S	SW	34	35N	14W	Barron	0-225-188-2017		0.0	4.0	5.3	20.3	2.727	2.766	1.421		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
EGSTAD 55-03-014-PIT Created On: 04/05/22 Updated On:	P	S	SW	34	35N	14W	Barron	0-225-159-2022	1.9	4.8	7.2	5.2	20.0	2.741	2.773	1.151		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse					
	P/Q	Qrt	Qrt	Sect	Town	Range	County	LA Wear (%) 100 500					Sp. Gravity OD SSD		Absorp. % Crse Fine			
BARRON -- WI																		
*ERICKSON 55-03-016-PIT Created On: 07/25/19 Updated On:	P	NW	NW	9	35N	13W	Barron	0-225-247-2019	0.6	0.0	1.3	4.3	19.5	2.785	2.807	0.783		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
JAT ADAMS 55-03-044-PIT Created On: 01/08/20 Updated On:	P	NW	NE	12	33N	10W	Barron	0-225-51-2020	0.8	0.0	1.4	4.8	20.9	2.708	2.736	1.032		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
JOHNSON 55-03-024-PIT Created On: 05/23/23 Updated On:	P	NE	NW	5	35N	10W	Barron	0-225-227-2023	3.4	0.0	1.0	4.2	18.8	2.744	2.768	0.869		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
KNUTSON 55-03-026-PIT Created On: 04/07/16 Updated On:	P	SW	SE	22	32N	11W	Barron	0-225-128-2016		0.0	1.7	4.6	20.3	2.698	2.729	1.168		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
KNUTSON 55-03-026-PIT Created On: 07/19/21 Updated On:	P	SW	SE	22	32N	11W	Barron	0-225-247-2021	3.5	0.0	1.3	4.3	20.2	2.677	2.709	1.178		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MCCLAIN 55-03-027-PIT Created On: 05/08/15 Updated On:	P	SW	NE	9	35N	13W	Barron	0-225-159-2015		0.0	2.9	2.8	14.0	2.795	2.817	0.788		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
MCCLAIN 55-03-027-PIT Created On: 04/18/22 Updated On:	P	SW	NE	9	35N	13W	Barron	0-225-177-2022		0.0	2.4	3.4	14.9	2.785	2.811	0.911		
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse					
	P/Q	Qrt	Qrt	Sect	Town	Range	County	LA Wear (%) 100 500					Sp. Gravity OD SSD	Absorp. % Crse Fine				
BARRON -- WI																		
ROSE STONE 55-03-032-QRY Created On: 01/09/15 Updated On:	Q	SE	SE	30	35N	10W	Barron	0-225-45-2015		0.0	0.7	9.1	41.7	2.553	2.577	0.961		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
ROSE STONE 55-03-032-QRY Created On: 03/23/18 Updated On:	Q	SE	SE	30	35N	10W	Barron	0-225-135-2018		0.0	1.4	7.7	33.7	2.559	2.582	0.885		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
ROSE STONE 55-03-032-QRY Created On: 03/17/21 Updated On:	Q	SE	SE	30	35N	10W	Barron	0-225-152-2021	0.0	0.1	0.3	9.2	38.7	2.565	2.583	0.705		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
ROSE STONE 55-03-032-QRY Created On: 01/04/24 Updated On:	Q	SE	SE	30	35N	10W	Barron	0-225-143-2024	0.0	0.7	1.2	12.6	45.4	2.536	2.567	1.189		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
SAFFERT 795 55-03-034-PIT Created On: 01/06/16 Updated On:	P	SW	SW	1	34N	11W	Barron	0-225-27-2016		0.0	5.3	5.7	24.0	2.662	2.703	1.554		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
SAFFERT 795 55-03-034-PIT Created On: 01/05/21 Updated On:	P	SW	SW	1	34N	11W	Barron	0-225-77-2021	0.9	3.8	5.1	4.9	20.8	2.711	2.743	1.184		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
VERMILLION 55-03-039-PIT Created On: 01/30/14 Updated On:	P	NW	SW	14	35N	13W	Barron	0-225-67-2014		0.0	1.6	4.6	18.5	2.710	2.735	0.942		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse					
	P/Q	Qrt	Qrt	Sect	Town	Range	County	LA Wear (%) 100					500	Sp. Gravity OD SSD		Absorp. % Crse Fine		
BARRON -- WI																		
VERMILLION 55-03-039-PIT Created On: 01/09/20 Updated On:	P	NW	SW	14	35N	13W	Barron	0-225-88-2020	4.2	0.0	2.6	4.0	19.5	2.711	2.735	0.881		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
BAYFIELD -- WI																		
BARNES 55-04-001-QRY Created On: 05/08/15 Updated On:	Q	NW	NE	21	44N	9W	Bayfield	0-225-157-2015		0.0	7.1	3.9	15.4	2.874	2.891	0.570		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
BARNES 55-04-001-QRY Created On: 01/03/18 Updated On:	Q	NW	NE	21	44N	9W	Bayfield	0-225-18-2018	0.2	0.0	3.9	2.8	12.6	2.854	2.881	0.943		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
BARNES 55-04-001-QRY Created On: 05/06/21 Updated On:	Q	NW	NE	21	44N	9W	Bayfield	0-225-203-2021	0.1	1.2	2.9	2.5	11.1	2.884	2.907	0.802		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
BARNES 55-04-001-QRY Created On: 01/02/24 Updated On:	Q	NW	NE	21	44N	9W	Bayfield	0-225-93-2024	0.1	6.2	11.3	4.6	18.3	2.804	2.844	1.422		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
CROOKED LAKE 55-04-003-PIT Created On: 02/05/14 Updated On:	P	SW	NW	36	47N	8W	Bayfield	0-225-82-2014		0.0	1.4	3.5	16.7	2.771	2.796	0.895		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
CROOKED LAKE 55-04-003-PIT Created On: 01/07/19 Updated On:	P	SW	NW	36	47N	8W	Bayfield	0-225-58-2019	1.7	0.0	1.9	5.9	22.7	2.814	2.844	1.078		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse					
	P/Q	Qrt	Qrt	Sect	Town	Range	County	LA Wear (%) 100 500					Sp. Gravity OD SSD		Absorp. % Crse Fine			
BAYFIELD -- WI																		
CROOKED LAKE 55-04-003-PIT Created On: 01/02/24 Updated On:	P	SW	NW	36	47N	8W	Bayfield	0-225-91-2024	1.4	2.1	2.7	3.4	16.6	2.817	2.843	0.926		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
*FROSTMAN 55-04-004-PIT Created On: 02/28/14 Updated On:	P		NW	26	47N	8W	Bayfield	0-225-87-2014		0.0	2.1	4.2	18.5	2.688	2.711	0.882		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
*FROSTMAN 55-04-004-PIT Created On: 01/07/19 Updated On:	P		NW	26	47N	8W	Bayfield	0-225-57-2019	2.3	0.0	2.6	8.8	20.9	2.684	2.715	1.154		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
KELLEY 55-04-019-PIT Created On: 10/04/21 Updated On:	P	SW	NW	25	43N	8W	Bayfield	0-225-266-2021	0.9	0.0	1.6	3.8	17.5	2.811	2.837	0.950		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
WITTWER 55-04-016-PIT Created On: 05/11/15 Updated On:	P	NE	SE	30	44N	7W	Bayfield	0-225-160-2015		0.0	3.6	4.8	20.5	2.791	2.816	0.923		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
WITTWER 55-04-016-PIT Created On: 01/06/20 Updated On:	P	NE	SE	30	44N	7W	Bayfield	0-225-32-2020	0.8	0.0	4.0	4.0	17.4	2.766	2.803	1.345		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
BROWN -- WI																		
BAY SETTLEMENT 55-05-012-QRY Created On: 05/17/22 Updated On:	Q			5	24N	22E	Brown	0-225-208-2022	1.8	4.9	1.2	10.5	35.4	2.655	2.711	2.090		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
BROWN -- WI																		
D AND J 55-05-003-QRY Created On: 04/05/16 Updated On:	Q	S	NW	5	22N	21E	Brown	0-225-122-2016	3.0	1.4	1.2	6.3	28.9	2.703	2.749	1.717		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
D AND J 55-05-003-QRY Created On: 04/19/19 Updated On:	Q	S	NW	5	22N	21E	Brown	0-225-149-2019	2.0	1.1	2.9	6.2	27.4	2.709	2.748	1.437		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
D AND J 55-05-003-QRY Created On: 01/04/22 Updated On:	Q	S	NW	5	22N	21E	Brown	0-225-72-2022	6.3	10.3	3.4	7.5	29.1	2.656	2.704	1.797		
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																	
*D AND J SCRAYS HILL 55-05-004-QRY Created On: 04/05/16 Updated On:	Q		NW	6	22N	21E	Brown	0-225-120-2016	0.1	2.9	1.3	9.1	36.3	2.702	2.748	1.721		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
*D AND J SCRAYS HILL 55-05-004-QRY Created On: 02/24/21 Updated On:	Q		NW	6	22N	21E	Brown	0-225-129-2021		2.4	2.4	9.3	37.7	2.681	2.727	1.712		
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																	
DENMARK 55-05-005-QRY Created On: 01/06/14 Updated On:	Q		E	36	22N	22E	Brown	0-225-10-2014		0.6	0.3	5.2	25.2	2.793	2.809	0.585		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
DENMARK 55-05-005-QRY Created On: 01/05/17 Updated On:	Q		E	36	22N	22E	Brown	0-225-41-2017		2.0	0.4	4.5	21.6	2.792	2.809	0.627		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse		Absorp. %							
	P/Q	Qrt	Qrt	Sect	Town	Range	County					LA Wear (%) 100 500	Sp. Gravity OD SSD	Crse Fine	Fine						
BROWN -- WI																					
DENMARK 55-05-005-QRY Created On: 01/02/20 Updated On:	Q		E	36	22N	22E	Brown	0-225-8-2020		14.4	0.4	6.0	25.9	2.791	2.821	1.089					
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																				
DENMARK 55-05-005-QRY Created On: 01/03/23 Updated On:	Q		E	36	22N	22E	Brown	0-225-44-2023		0.0	1.8	0.4	5.5	25.1	2.792	2.809	0.618				
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																				
*GLENMORE 55-05-013-QRY Created On: 01/05/15 Updated On:	Q		NE	6	22N	21E	Brown	0-225-5-2015		0.1	0.4	1.2	6.5	30.3	2.730	2.765	1.294				
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																				
*GLENMORE 55-05-013-QRY Created On: 01/04/18 Updated On:	Q		NE	6	22N	21E	Brown	0-225-53-2018			1.1	1.8	6.4	30.0	2.725	2.755	1.090				
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																				
*GLENMORE 55-05-013-QRY Created On: 01/04/21 Updated On:	Q		NE	6	22N	21E	Brown	0-225-6-2021		1.6	1.6	2.9	6.0	38.7	2.672	2.721	1.807				
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																				
*GLENMORE 55-05-013-QRY Created On: 01/02/24 Updated On:	Q		NE	6	22N	21E	Brown	0-225-49-2024		20.7	16.5	6.0	13.7	43.6	2.513	2.597	3.370				
	Approved Use : OGBC, Base Aggregate																				
HOBART QUARRY 55-05-008-QRY Created On: 04/01/16 Updated On:	Q	NE	NE	27	23N	19E	Brown	0-225-119-2016		0.5	5.0	11.3	6.1	26.0	2.739	2.772	1.181				
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																				

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse							
	P/Q	Qrt	Qrt	Sect	Town	Range	County	LA Wear (%)					Sp. Gravity		Absorp. %					
								100					500	OD	SSD	Crse	Fine			
BROWN -- WI																				
HOBART QUARRY 55-05-008-QRY Created On: 04/13/17 Updated On:	Q	NE	NE	27	23N	19E	Brown	0-225-129-2017		7.9	11.1	5.6	24.0	2.759	2.790	1.100				
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																			
HOBART QUARRY 55-05-008-QRY Created On: 03/18/20 Updated On:	Q	NE	NE	27	23N	19E	Brown	0-225-130-2020		20.2	15.7	9.6	27.0	2.733	2.767	1.247				
HOBART QUARRY 55-05-008-QRY Created On: 06/09/20 Updated On:	Q	NE	NE	27	23N	19E	Brown	0-225-190-2020		11.0	4.2	5.4	24.5	2.750	2.779	1.040				
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																			
HOBART QUARRY 55-05-008-QRY Created On: 03/10/21 Updated On:	Q	NE	NE	27	23N	19E	Brown	0-225-134-2021		0.0	1.1	1.0	4.9	22.5	2.791	2.805	0.492			
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																			
HOBART QUARRY 55-05-008-QRY Created On: 01/04/22 Updated On:	Q	NE	NE	27	23N	19E	Brown	0-225-69-2022		0.0	29.3	16.4	5.9	26.6	2.732	2.766	1.248			
HOBART QUARRY 55-05-008-QRY Created On: 02/17/22 Updated On:	Q	NE	NE	27	23N	19E	Brown	0-225-128-2022		0.1	2.1	5.3	4.7	22.5	2.770	2.792	0.811			
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																			
HOBART QUARRY 55-05-008-QRY Created On: 03/21/23 Updated On:	Q	NE	NE	27	23N	19E	Brown	0-225-173-2023		0.0	1.1	0.4	5.3	22.7	2.769	2.789	0.707			
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																			

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse				
	P/Q	Qrt	Qrt	Sect	Town	Range	County	LA Wear (%) 100 500					Sp. Gravity OD SSD	Absorp. % Crse Fine			
BROWN -- WI HOBART QUARRY 55-05-008-QRY Created On: 01/02/24 Updated On:	Q	NE	NE	27	23N	19E	Brown	0-225-14-2024	0.0	2.7	0.4	6.2	27.0	2.765	2.788	0.836	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
*HOLLAND 55-05-028-PIT Created On: 08/20/19 Updated On:	P		SW	33	21N	20E	Brown	0-225-264-2019	0.0	11.4	4.0	6.0	27.5	2.724	2.763	1.431	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
LAWRENCE 55-05-015-QRY Created On: 01/08/16 Updated On:	Q	SW	SW	30	23N	20E	Brown	0-225-46-2016	0.1	12.6	5.1	6.2	26.6	2.725	2.762	1.360	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
LAWRENCE 55-05-015-QRY Created On: 01/05/17 Updated On:	Q	SW	SW	30	23N	20E	Brown	0-225-36-2017	0.2	22.6	18.9	8.3	29.1	2.740	2.774	1.237	
	Approved Use : Base Aggregate																
LAWRENCE 55-05-015-QRY Created On: 03/22/17 Updated On:	Q	SW	SW	30	23N	20E	Brown	0-225-84-2017		5.0	15.9	6.8	24.4	2.745	2.776	1.122	
	Approved Use : Base Aggregate																
LAWRENCE 55-05-015-QRY Created On: 04/11/18 Updated On:	Q	SW	SW	30	23N	20E	Brown	0-225-167-2018	0.3	16.7	11.1	5.1	23.5	2.747	2.776	1.066	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
LAWRENCE 55-05-015-QRY Created On: 07/18/19 Updated On:	Q	SW	SW	30	23N	20E	Brown	0-225-239-2019	0.2	15.6	20.0	5.2	24.1	2.751	2.779	1.028	
	Approved Use : Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse								
	P/Q	Qrt	Qrt	Sect	Town	Range	County	LA Wear (%) 100					500	Sp. Gravity OD SSD		Absorp. % Crse Fine					
BROWN -- WI																					
LAWRENCE 55-05-015-QRY Created On: 06/09/20 Updated On:	Q	SW	SW	30	23N	20E	Brown	0-225-192-2020	0.2	8.2	4.0	5.0	21.8	2.778	2.801	0.853					
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																				
LAWRENCE 55-05-015-QRY Created On: 01/10/22 Updated On:	Q	SW	SW	30	23N	20E	Brown	0-225-99-2022	0.6	3.4	4.6	5.0	22.0	2.752	2.779	0.979					
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																				
LAWRENCE 55-05-015-QRY Created On: 01/03/23 Updated On:	Q	SW	SW	30	23N	20E	Brown	0-225-45-2023	0.4	6.2	3.8	6.4	25.9	2.723	2.759	1.313					
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																				
ROCKLAND QUARRY 55-05-023-QRY Created On: 04/03/14 Updated On:	Q	SE	NE	12	22N	20E	Brown	0-225-116-2014	3.3	1.9	2.0	6.1	27.0	2.707	2.749	1.541					
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																				
ROCKLAND QUARRY 55-05-023-QRY Created On: 02/03/17 Updated On:	Q	SE	NE	12	22N	20E	Brown	0-225-61-2017	1.8	5.0	5.6	9.1	33.6	2.680	2.731	1.897					
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																				
ROCKLAND QUARRY 55-05-023-QRY Created On: 01/02/20 Updated On:	Q	SE	NE	12	22N	20E	Brown	0-225-4-2020	0.5	1.9	0.7	5.6	26.9	2.735	2.767	1.163					
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																				
ROCKLAND QUARRY 55-05-023-QRY Created On: 01/03/23 Updated On:	Q	SE	NE	12	22N	20E	Brown	0-225-75-2023	1.5	1.5	1.5	6.3	28.1	2.709	2.747	1.416					
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																				

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse					
	P/Q	Qrt	Qrt	Sect	Town	Range	County	LA Wear (%) 100					500	Sp. Gravity OD SSD		Absorp. % Crse Fine		
BROWN -- WI																		
SCOTT 55-05-027-QRY Created On: 01/02/24 Updated On:	Q	NW	NE	18	24N	22E	Brown	0-225-9-2024	0.2	1.2	0.3	5.4	23.1	2.713	2.751	1.408		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
*TORDEUR 55-05-024-QRY Created On: 01/05/15 Updated On:	Q			18	24N	22E	Brown	0-225-1-2015	0.3	1.3	2.3	5.8	27.2	2.729	2.764	1.285		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
*TORDEUR 55-05-024-QRY Created On: 01/04/18 Updated On:	Q			18	24N	22E	Brown	0-225-52-2018				2.6	2.8	7.2	33.5	2.708	2.748	1.490
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																	
*TORDEUR 55-05-024-QRY Created On: 01/04/21 Updated On:	Q			18	24N	22E	Brown	0-225-8-2021	0.3	0.9	1.5	5.2	24.6	2.703	2.742	1.446		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
BUFFALO -- WI																		
BORK 55-06-005-QRY Created On: 09/09/16 Updated On:	Q	NW	NE	30	19N	10W	Buffalo	0-225-253-2016		0.0	5.3	8.8	32.6	2.627	2.678	1.932		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
BORK 55-06-005-QRY Created On: 01/08/19 Updated On:	Q	NW	NE	30	19N	10W	Buffalo	0-225-78-2019	0.8	0.0	2.9	10.1	35.8	2.610	2.667	2.156		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
BORK 55-06-005-QRY Created On: 01/04/22 Updated On:	Q	NW	NE	30	19N	10W	Buffalo	0-225-11-2022	0.3	2.4	4.8	9.1	35.3	2.648	2.694	1.717		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Coarse Sp. Gravity		Coarse Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
BUFFALO -- WI																		
*BRAGGER 55-06-006-QRY Created On: 06/11/14 Updated On:	Q	W	NW	13	22N	10W	Buffalo	0-225-188-2014	1.5	0.0	3.8	9.9	40.0	2.564	2.639	2.901		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
*BRAGGER 55-06-006-QRY Created On: 04/21/17 Updated On:	Q	W	NW	13	22N	10W	Buffalo	0-225-141-2017	0.4	0.0	7.5	10.3	41.1	2.571	2.646	2.915		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
*BRAGGER 55-06-006-QRY Created On: 06/18/20 Updated On:	Q	W	NW	13	22N	10W	Buffalo	0-225-196-2020	0.0	0.0	5.6	10.2	39.6	2.566	2.641	2.936		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
*BROMMER 55-06-008-QRY Created On: 06/13/16 Updated On:	Q	SW	NE	30	23N	12W	Buffalo	0-225-203-2016		0.0	4.8	8.8	34.7	2.568	2.637	2.681		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
*BROMMER 55-06-008-QRY Created On: 01/05/21 Updated On:	Q	SW	NE	30	23N	12W	Buffalo	0-225-71-2021	2.4	0.0	0.9	8.5	34.4	2.592	2.656	2.470		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
FELTES 55-06-010-QRY Created On: 04/23/15 Updated On:	Q	NE	SE	6	20N	10W	Buffalo	0-225-135-2015		0.0	2.3	10.9	38.7	2.613	2.670	2.180		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
FELTES 55-06-010-QRY Created On: 01/04/18 Updated On:	Q	NE	SE	6	20N	10W	Buffalo	0-225-46-2018	0.7	0.0	1.7	9.2	34.6	2.612	2.672	2.320		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Coarse Sp. Gravity		Coarse Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine		
BUFFALO -- WI																			
FELTES 55-06-010-QRY Created On: 04/17/23 Updated On:	Q	NE	SE	6	20N	10W	Buffalo	0-225-197-2023		0.0	5.2	11.3	41.9	2.613	2.672	2.283			
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																		
FELTES 55-06-010-QRY Created On: 05/22/23 Updated On:	Q	NE	SE	6	20N	10W	Buffalo	0-225-219-2023	0.2	0.0	2.9	7.4	33.6	2.647	2.697	1.875			
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
*HUBER 55-06-011-QRY Created On: 05/09/16 Updated On:	Q	SE	SE	4	22N	12W	Buffalo	0-225-165-2016		0.0	11.6	13.0	41.2	2.562	2.635	2.833			
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																		
*HUBER 55-06-011-QRY Created On: 08/25/17 Updated On:	Q	SE	SE	4	22N	12W	Buffalo	0-225-263-2017		0.0	3.7	11.2	41.8	2.561	2.640	3.067			
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
*HUBER 55-06-011-QRY Created On: 01/06/20 Updated On:	Q	SE	SE	4	22N	12W	Buffalo	0-225-26-2020	0.5	0.0	6.6	11.2	42.0	2.567	2.641	2.888			
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																		
MARSOLEK 55-06-014-QRY Created On: 01/17/14 Updated On:	Q	NW	SE	36	23N	10W	Buffalo	0-225-51-2014		0.0	12.3	10.4	39.6	2.574	2.645	2.766			
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																		
MARSOLEK 55-06-014-QRY Created On: 04/25/14 Updated On:	Q	NW	SE	36	23N	10W	Buffalo	0-225-151-2014		0.0	8.3	10.4	39.6	2.574	2.645	2.766			
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																		

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Coarse Sp. Gravity		Coarse Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine		
BUFFALO -- WI																			
MARSOLEK 55-06-014-QRY Created On: 06/30/16 Updated On:	Q	NW	SE	36	23N	10W	Buffalo	0-225-213-2016		0.0	3.5	8.1	33.4	2.572	2.641	2.694			
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																		
MARSOLEK 55-06-014-QRY Created On: 01/04/19 Updated On:	Q	NW	SE	36	23N	10W	Buffalo	0-225-29-2019	0.9	0.0	7.6	11.5	40.5	2.541	2.623	3.258			
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																		
MARSOLEK 55-06-014-QRY Created On: 01/04/22 Updated On:	Q	NW	SE	36	23N	10W	Buffalo	0-225-76-2022	4.6	0.0	11.6	12.2	44.5	2.540	2.623	3.280			
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
MILESTONE-MONDOVI-BUCK RIDGE 55-06-016-QRY Created On: 02/03/14 Updated On:	Q	N	SE	28	24N	11W	Buffalo	0-225-74-2014		0.0	2.4	10.5	42.2	2.591	2.657	2.547			
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																		
MILESTONE-MONDOVI-BUCK RIDGE 55-06-016-QRY Created On: 01/05/17 Updated On:	Q	N	SE	28	24N	11W	Buffalo	0-225-46-2017	0.6	0.0	3.3	8.7	38.7	2.580	2.643	2.445			
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																		
MILESTONE-MONDOVI-BUCK RIDGE 55-06-016-QRY Created On: 06/18/20 Updated On:	Q	N	SE	28	24N	11W	Buffalo	0-225-197-2020	0.6	0.0	6.6	13.3	48.2	2.533	2.615	3.220			
	Approved Use : HMA<MT, CONCRETE, OGBC, Base Aggregate																		
MILESTONE-MONDOVI-BUCK RIDGE 55-06-016-QRY Created On: 01/04/22 Updated On:	Q	N	SE	28	24N	11W	Buffalo	0-225-74-2022	0.6	0.0	40.6	14.7	50.3	2.537	2.622	3.360			

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
BUFFALO -- WI																		
MILESTONE-MONDOVI-BUCK RIDGE 55-06-016-QRY Created On: 08/17/22 Updated On:	Q	N	SE	28	24N	11W	Buffalo	0-225-251-2022	0.1	7.8	12.6	15.3	49.4	2.594	2.660	2.567		
	Approved Use : Base Aggregate																	
*O'NEIL 55-06-017-QRY Created On: 01/16/14 Updated On:	Q	SE	NW	36	24N	11W	Buffalo	0-225-49-2014		0.0	13.6	12.3	42.6	2.584	2.653	2.695		
	Approved Use : Base Aggregate																	
*O'NEIL 55-06-017-QRY Created On: 06/17/14 Updated On:	Q	SE	NW	36	24N	11W	Buffalo	0-225-196-2014		0.0	8.6	11.5	43.4	2.598	2.661	2.403		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
*O'NEIL 55-06-017-QRY Created On: 05/04/17 Updated On:	Q	SE	NW	36	24N	11W	Buffalo	0-225-167-2017		0.0	14.3	14.1	47.8	2.548	2.639	3.583		
	Approved Use : Base Aggregate																	
*O'NEIL 55-06-017-QRY Created On: 01/06/20 Updated On:	Q	SE	NW	36	24N	11W	Buffalo	0-225-28-2020	0.2	0.0	12.8	14.9	46.1	2.553	2.637	3.312		
	Approved Use : Base Aggregate																	
RATZ 55-06-020-QRY Created On: 04/23/15 Updated On:	Q	SW	SW	12	20N	11W	Buffalo	0-225-134-2015		0.0	3.2	11.9	41.4	2.595	2.659	2.438		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
RATZ 55-06-020-QRY Created On: 01/04/18 Updated On:	Q	SW	SW	12	20N	11W	Buffalo	0-225-47-2018	0.3	0.0	0.9	9.0	35.1	2.609	2.668	2.269		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse					
	P/Q	Qrt	Qrt	Sect	Town	Range	County	LA Wear (%) 100 500					Sp. Gravity OD SSD		Absorp. % Crse Fine			
BUFFALO -- WI																		
RATZ 55-06-020-QRY Created On: 01/04/21 Updated On:	Q	SW	SW	12	20N	11W	Buffalo	0-225-39-2021	0.9	0.0	0.4	7.8	33.7	2.590	2.650	2.320		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
RATZ 55-06-020-QRY Created On: 01/02/24 Updated On:	Q	SW	SW	12	20N	11W	Buffalo	0-225-117-2024	0.3	3.5	4.3	10.1	39.3	2.607	2.667	2.313		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
*STRAND 55-06-023-QRY Created On: 10/07/20 Updated On:	Q		NE	28	23N	13W	Buffalo	0-225-244-2020	0.3	0.0	12.5	10.3	41.8	2.563	2.655	3.608		
	Approved Use : Base Aggregate																	
WENDERS 55-06-028-QRY Created On: 05/09/16 Updated On:	Q			10	20N	12W	Buffalo	0-225-163-2016		0.0	11.8	13.7	40.7	2.599	2.660	2.318		
	Approved Use : CONCRETE, Base Aggregate																	
WENDERS 55-06-028-QRY Created On: 01/08/19 Updated On:	Q			10	20N	12W	Buffalo	0-225-80-2019	0.7	0.0	2.6	8.8	32.6	2.644	2.691	1.770		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
WENDERS 55-06-028-QRY Created On: 01/04/22 Updated On:	Q			10	20N	12W	Buffalo	0-225-9-2022	0.1	1.7	4.7	9.4	37.1	2.630	2.683	2.015		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
BURNETT -- WI																		
MILESTONE-DON JOHNSON 55-07-006-PIT Created On: 01/05/16 Updated On:	P	E	SW	21	39N	17W	Burnett	0-225-26-2016		0.0	6.6	3.8	16.9	2.739	2.771	1.148		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse					
	P/Q	Qrt	Qrt	Sect	Town	Range	County	LA Wear (%) 100 500					Sp. Gravity OD SSD		Absorp. % Crse Fine			
BURNETT -- WI																		
MILESTONE-DON JOHNSON 55-07-006-PIT Created On: 10/12/21 Updated On:	P	E	SW	21	39N	17W	Burnett	0-225-267-2021	0.8	3.0	3.7	3.8	16.9	2.778	2.804	0.927		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MILESTONE-DON JOHNSON 55-07-006-PIT Created On: 01/04/24 Updated On:	P	E	SW	21	39N	17W	Burnett	0-225-144-2024	1.0	4.8	6.4	3.5	16.6	2.747	2.794	1.701		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
SIREN 55-07-018-PIT Created On: 04/17/15 Updated On:	P	NE	SW	32	38N	16W	Burnett	0-225-128-2015				5.1	20.2	2.703	2.740	1.347		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
SIREN 55-07-018-PIT Created On: 04/05/22 Updated On:	P	NE	SW	32	38N	16W	Burnett	0-225-164-2022	6.7	0.0	6.2	4.9	20.0	2.697	2.731	1.272		
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																	
CALUMET -- WI																		
HAYTON 55-08-006-QRY Created On: 06/21/16 Updated On:	Q		SW	28	18N	20E	Calumet	0-225-206-2016		0.0	1.7	9.5	39.8	2.727	2.757	1.092		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
HAYTON 55-08-006-QRY Created On: 01/08/19 Updated On:	Q		SW	28	18N	20E	Calumet	0-225-72-2019		0.7	0.8	7.8	33.5	2.764	2.787	0.817		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
HAYTON 55-08-006-QRY Created On: 01/04/22 Updated On:	Q		SW	28	18N	20E	Calumet	0-225-29-2022	0.0	0.0	0.5	8.7	36.7	2.758	2.783	0.903		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Coarse Sp. Gravity		Coarse Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
CALUMET -- WI																		
HAYTON 55-08-006-QRY Created On: 01/29/24 Updated On:	Q		SW	28	18N	20E	Calumet	0-225-165-2024	0.0	0.6	1.3	8.7	36.9	2.772	2.792	0.713		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
JANNETTE CHILTON QUARRY 55-08-019-QRY Created On: 01/04/24 Updated On:	Q	SW	SW	20	18N	20E	Calumet	0-225-136-2024	0.1	0.0	0.4	5.4	25.3	2.791	2.806	0.552		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
*KREPLINE 55-08-012-QRY Created On: 05/26/16 Updated On:	Q	NE	NE	34	19N	19E	Calumet	0-225-191-2016		0.0	2.8	8.3	35.1	2.689	2.727	1.415		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
*KREPLINE 55-08-012-QRY Created On: 04/24/19 Updated On:	Q	NE	NE	34	19N	19E	Calumet	0-225-167-2019	0.1	0.0	0.5	13.1	49.1	2.671	2.706	1.319		
	Approved Use : HMA<MT, CONCRETE, Base Aggregate																	
*MICHELS - BRILLION 55-08-014-QRY Created On: 01/07/15 Updated On:	Q		SW	24	20N	20E	Calumet	0-225-22-2015	0.4	0.0	2.6	9.8	39.9	2.627	2.680	2.009		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
*MICHELS - BRILLION 55-08-014-QRY Created On: 03/16/18 Updated On:	Q		SW	24	20N	20E	Calumet	0-225-124-2018		0.0	2.0	9.0	35.7	2.687	2.727	1.498		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
*MICHELS - BRILLION 55-08-014-QRY Created On: 01/05/21 Updated On:	Q		SW	24	20N	20E	Calumet	0-225-48-2021	0.8	0.0	1.2	8.0	34.5	2.661	2.711	1.903		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
CALUMET -- WI																		
MICHELS BROWN 55-08-015-QRY Created On: 01/04/16 Updated On:	Q	S	SW	32	20N	19E	Calumet	0-225-7-2016	0.1	0.0	1.4	6.0	26.8	2.767	2.789	0.787		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
MICHELS BROWN 55-08-015-QRY Created On: 01/04/19 Updated On:	Q	S	SW	32	20N	19E	Calumet	0-225-39-2019	0.7	0.0	3.6	8.1	32.6	2.743	2.774	1.131		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
MICHELS BROWN 55-08-015-QRY Created On: 01/04/22 Updated On:	Q	S	SW	32	20N	19E	Calumet	0-225-32-2022	1.2	0.0	3.2	9.6	37.0	2.713	2.752	1.440		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
CHIPPEWA -- WI																		
DUSICK 55-09-024-PIT Created On: 05/17/22 Updated On:	P	SE	NW	17	29N	5W	Chippewa	0-225-205-2022	0.3	0.0	1.0	3.5	17.6	2.763	2.782	0.682		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
GULICH 55-09-079-PIT Created On: 01/30/20 Updated On:	P	NW	SE	10	32N	6W	Chippewa	0-225-101-2020	1.2	0.0	2.4	3.5	17.9	2.675	2.710	1.315		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
HAAS 124 55-09-025-PIT Created On: 01/17/14 Updated On:	P	SE	SE	6	30N	8W	Chippewa	0-225-55-2014		0.0	3.0	3.9	17.8	2.712	2.745	1.208		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
HAAS 124 55-09-025-PIT Created On: 06/06/19 Updated On:	P	SE	SE	6	30N	8W	Chippewa	0-225-207-2019	7.8	0.0	3.5	5.3	21.6	2.659	2.687	1.060		
	Approved Use : HMA<MT, HMA>=MT, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Coarse Sp. Gravity		Coarse Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine		
CHIPPEWA -- WI																			
HAAS 124 55-09-025-PIT Created On: 06/04/20 Updated On:	P	SE	SE	6	30N	8W	Chippewa	0-225-186-2020	1.1	0.0	0.9	3.7	19.7	2.712	2.745	1.204			
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
HAAS SPORTS PIT 55-09-081-PIT Created On: 07/27/23 Updated On:	P	NE	NW	25	31N	7W	Chippewa	0-225-241-2023	2.0	0.0	1.0	4.4	20.1	2.723	2.748	0.897			
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
HILGER 55-09-031-PIT Created On: 02/03/14 Updated On:	P			8	30N	8W	Chippewa	0-225-70-2014		0.0	2.2	4.2	19.7	2.724	2.754	1.100			
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																		
HILGER 55-09-031-PIT Created On: 01/08/19 Updated On:	P			8	30N	8W	Chippewa	0-225-75-2019	0.9	0.0	1.5	3.6	17.4	2.702	2.733	1.123			
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																		
HILGER 55-09-031-PIT Created On: 01/02/24 Updated On:	P			8	30N	8W	Chippewa	0-225-84-2024	0.7	0.0	1.6	3.5	17.7	2.708	2.736	1.029			
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
JENNEMAN 55-09-032-PIT Created On: 02/03/14 Updated On:	P		NE	6	30N	8W	Chippewa	0-225-75-2014		0.0	1.2	4.5	19.7	2.722	2.748	0.935			
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																		
JENNEMAN 55-09-032-PIT Created On: 01/08/19 Updated On:	P		NE	6	30N	8W	Chippewa	0-225-77-2019	0.3	0.0	0.9	3.6	17.3	2.726	2.754	1.035			
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Coarse Sp. Gravity		Coarse Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
CHIPPEWA -- WI																		
JENNEMAN 55-09-032-PIT Created On: 01/02/24 Updated On:	P		NE	6	30N	8W	Chippewa	0-225-85-2024	0.7	0.0	2.0	4.2	20.1	2.708	2.733	0.929		
		Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
LAGESSE 55-09-036-PIT Created On: 08/19/15 Updated On:	P	SE	SE	7	30N	8W	Chippewa	0-225-228-2015		0.0	0.7	4.5	20.3	2.739	2.761	0.799		
		Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
LAGESSE 55-09-036-PIT Created On: 01/09/20 Updated On:	P	SE	SE	7	30N	8W	Chippewa	0-225-86-2020	0.7	0.0	0.9	3.7	17.9	2.717	2.745	1.050		
		Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
LEWIN 55-09-039-PIT Created On: 01/07/15 Updated On:	P		NE	18	30N	8W	Chippewa	0-225-12-2015		0.0	2.1	3.9	19.0	2.690	2.715	0.956		
		Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
LEWIN 55-09-039-PIT Created On: 01/08/19 Updated On:	P		NE	18	30N	8W	Chippewa	0-225-74-2019	2.8	0.0	1.9	3.8	19.9	2.706	2.734	1.029		
		Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
LEWIN 55-09-039-PIT Created On: 01/02/24 Updated On:	P		NE	18	30N	8W	Chippewa	0-225-83-2024	1.6	0.0	1.7	4.5	19.7	2.711	2.737	0.970		
		Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
LICHTS 55-09-080-PIT Created On: 04/02/20 Updated On:	P	SE	NW	23	29N	6W	Chippewa	0-225-144-2020	2.2	0.0	2.2	4.8	20.7	2.708	2.735	0.984		
		Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse						
	P/Q	Qrt	Qrt	Sect	Town	Range	County	LA Wear (%) 100					500	Sp. Gravity OD SSD		Absorp. % Crse Fine			
CHIPPEWA -- WI																			
MAHR 55-09-041-PIT Created On: 01/12/15 Updated On:	P	SW	SW	26	29N	5W	Chippewa	0-225-56-2015		0.0	3.2	3.8	18.3	2.733	2.758	0.923			
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																		
MAHR 55-09-041-PIT Created On: 01/09/20 Updated On:	P	SW	SW	26	29N	5W	Chippewa	0-225-87-2020	1.0	0.0	4.8	5.0	21.7	2.704	2.736	1.183			
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
MAHR 55-09-041-PIT Created On: 01/09/20 Updated On:	P	SW	SW	26	29N	5W	Chippewa	0-225-89-2020	1.7	0.0	3.0	3.9	18.6	2.684	2.719	1.297			
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
MILESTONE-CHARLES OLSEN 55-09-047-PIT Created On: 01/08/15 Updated On:	P	SW	NW	35	30N	8W	Chippewa	0-225-37-2015		0.0	3.3	3.9	17.9	2.704	2.735	1.139			
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																		
MILESTONE-CHARLES OLSEN 55-09-047-PIT Created On: 01/08/20 Updated On:	P	SW	NW	35	30N	8W	Chippewa	0-225-53-2020	1.4	0.0	0.0	4.6	19.6	2.727	2.756	1.068			
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
MOATS 55-09-044-PIT Created On: 03/08/18 Updated On:	P	SW	NE	15	29N	7W	Chippewa	0-225-114-2018	8.1	0.0	6.5	5.9	20.5	2.630	2.674	1.682			
	Approved Use : HMA<MT, HMA>=MT, Base Aggregate																		
MOATS 55-09-044-PIT Created On: 01/05/21 Updated On:	P	SW	NE	15	29N	7W	Chippewa	0-225-90-2021	2.6	0.0	2.3	5.0	21.7	2.677	2.712	1.298			
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse					
	P/Q	Qrt	Qrt	Sect	Town	Range	County	LA Wear (%)					Sp. Gravity		Absorp. %			
												100	500	OD	SSD	Crse	Fine	
CHIPPEWA -- WI																		
NELSON MINE 55-09-046-PIT Created On: 01/12/15 Updated On:	P	NW	NW	13	28N	9W	Chippewa	0-225-57-2015		0.0	3.7	5.0	21.5	2.627	2.657	1.113		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
NELSON MINE 55-09-046-PIT Created On: 04/02/20 Updated On:	P	NW	NW	13	28N	9W	Chippewa	0-225-141-2020	1.5	0.0	1.2	5.1	20.8	2.721	2.739	0.692		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
OLYNICK - BOHLS 55-09-049-PIT Created On: 06/08/15 Updated On:	P			16	29N	5W	Chippewa	0-225-192-2015		0.0	2.4	5.1	20.3	2.716	2.752	1.321		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
OLYNICK - BOHLS 55-09-049-PIT Created On: 04/02/20 Updated On:	P			16	29N	5W	Chippewa	0-225-142-2020	0.0	0.0	1.3	4.8	21.7	2.738	2.768	1.106		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
PETERSON 55-09-052-PIT Created On: 10/03/17 Updated On:	P	NE	SW	32	29N	5W	Chippewa	0-225-278-2017		0.0	0.9	4.0	19.1	2.685	2.720	1.273		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
PETERSON 55-09-052-PIT Created On: 01/04/22 Updated On:	P	NE	SW	32	29N	5W	Chippewa	0-225-83-2022	0.8	0.0	1.8	3.3	16.8	2.713	2.744	1.135		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
POTAPENKO 55-09-053-PIT Created On: 03/08/18 Updated On:	P	SE	SW	25	31N	5W	Chippewa	0-225-113-2018	3.3	0.0	1.4	3.9	21.1	2.655	2.691	1.380		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse					
	P/Q	Qrt	Qrt	Sect	Town	Range	County	LA Wear (%) 100 500					Sp. Gravity OD SSD		Absorp. % Crse Fine			
CHIPPEWA -- WI																		
POTAPENKO 55-09-053-PIT Created On: 01/10/23 Updated On:	P	SE	SW	25	31N	5W	Chippewa	0-225-118-2023	2.3	0.0	2.1	3.7	19.3	2.643	2.685	1.610		
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
RANDY MAHR 55-09-055-PIT Created On: 01/07/15 Updated On:	P	NE	SW	23	29N	5W	Chippewa	0-225-10-2015		0.0	1.8	3.7	18.0	2.749	2.774	0.907		
Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																		
RANDY MAHR 55-09-055-PIT Created On: 01/05/21 Updated On:	P	NE	SW	23	29N	5W	Chippewa	0-225-92-2021	1.5	0.0	3.4	4.3	20.6	2.714	2.745	1.143		
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
ROMANOWSKI 55-09-058-PIT Created On: 04/21/17 Updated On:	P	NW	NE	36	31N	5W	Chippewa	0-225-147-2017		0.0	2.1	4.9	21.8	2.667	2.704	1.391		
Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																		
ROMANOWSKI 55-09-058-PIT Created On: 01/10/23 Updated On:	P	NW	NE	36	31N	5W	Chippewa	0-225-106-2023	4.1	0.0	2.3	3.8	19.4	2.662	2.693	1.166		
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
SCHICK 55-09-060-PIT Created On: 04/21/17 Updated On:	P	SW	NW	2	29N	8W	Chippewa	0-225-143-2017		0.0	2.4	4.9	20.6	2.688	2.720	1.163		
Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																		
SCHICK 55-09-060-PIT Created On: 01/04/22 Updated On:	P	SW	NW	2	29N	8W	Chippewa	0-225-80-2022	1.2	0.0	3.2	4.3	20.8	2.688	2.715	1.025		
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Coarse Sp. Gravity		Coarse Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine		
CHIPPEWA -- WI																			
SHAKAL VALLEY 55-09-063-PIT Created On: 02/05/14 Updated On:	P	NW	SW	23	29N	6W	Chippewa	0-225-79-2014		0.0	5.5	10.5	23.2	2.597	2.652	2.117			
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																		
SHAKAL VALLEY 55-09-063-PIT Created On: 03/21/19 Updated On:	P	NW	SW	23	29N	6W	Chippewa	0-225-110-2019		5.5	0.0	6.1	6.3	22.7	2.649	2.686	1.392		
	Approved Use : HMA<MT, HMA>=MT, Base Aggregate																		
SHAKAL VALLEY 55-09-063-PIT Created On: 01/02/24 Updated On:	P	NW	SW	23	29N	6W	Chippewa	0-225-118-2024		2.6	0.0	2.6	4.7	19.4	2.674	2.704	1.127		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
*ST. AUBIN 55-09-064-PIT Created On: 02/03/14 Updated On:	P	NE	NE	27	31N	7W	Chippewa	0-225-71-2014		0.0	2.4	4.4	20.4	2.707	2.738	1.146			
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																		
*ST. AUBIN 55-09-064-PIT Created On: 01/08/19 Updated On:	P	NE	NE	27	31N	7W	Chippewa	0-225-81-2019		3.1	0.0	1.6	3.2	17.9	2.674	2.702	1.064		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																		
*STELTER 55-09-065-PIT Created On: 04/25/14 Updated On:	P	SW	SW	5	30N	8W	Chippewa	0-225-150-2014		0.0	0.4	4.3	19.5	2.739	2.767	1.031			
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																		
*STELTER 55-09-065-PIT Created On: 05/02/19 Updated On:	P	SW	SW	5	30N	8W	Chippewa	0-225-176-2019		0.0	0.0	2.2	4.5	20.0	2.740	2.765	0.920		
	Approved Use : HMA<MT, HMA>=MT, Base Aggregate																		

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse							
	P/Q	Qrt	Qrt	Sect	Town	Range	County	LA Wear (%) 100 500					Sp. Gravity OD SSD		Absorp. % Crse Fine					
CHIPPEWA -- WI																				
VEUM 55-09-068-PIT Created On: 01/17/14 Updated On:	P	NE	NW	35	28N	10W	Chippewa	0-225-54-2014		0.0	5.5	6.9	26.3	2.606	2.649	1.625				
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																			
VEUM 55-09-068-PIT Created On: 01/08/19 Updated On:	P	NE	NW	35	28N	10W	Chippewa	0-225-82-2019	4.2	0.0	6.7	7.1	26.8	2.593	2.631	1.450				
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																			
VEUM 55-09-068-PIT Created On: 01/02/24 Updated On:	P	NE	NW	35	28N	10W	Chippewa	0-225-79-2024	3.2	0.0	4.6	5.4	22.7	2.677	2.707	1.123				
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																			
WOZNIAK 55-09-074-PIT Created On: 01/07/15 Updated On:	P	SW	NE	1	28N	5W	Chippewa	0-225-11-2015		0.0	1.8	3.6	17.8	2.658	2.689	1.169				
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																			
WOZNIAK 55-09-074-QRY Created On: 07/23/15 Updated On:	Q	NW	SE	1	28N	5W	Chippewa	0-225-216-2015		0.0	5.3	5.2	21.3	2.977	3.001	0.808				
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																			
WOZNIAK 55-09-074-PIT Created On: 03/08/18 Updated On:	P	SW	NE	1	28N	5W	Chippewa	0-225-115-2018	0.5	0.0	3.1	3.9	17.4	2.909	2.935	0.866				
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																			
WOZNIAK 55-09-074-PIT Created On: 01/05/21 Updated On:	P	SW	NE	1	28N	5W	Chippewa	0-225-91-2021	0.1	0.0	1.9	4.4	20.1	2.878	2.889	0.374				
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																			

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse					
	P/Q	Qrt	Qrt	Sect	Town	Range	County	LA Wear (%) 100					500	Sp. Gravity OD	SSD	Absorp. % Crse	Fine	
CHIPPEWA -- WI																		
WOZNIAK 55-09-074-QRY Created On: 01/02/24 Updated On:	Q	NW	SE	1	28N	5W	Chippewa	0-225-82-2024	0.0	0.0	1.1	4.2	18.9	2.936	2.946	0.351		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
CLARK -- WI																		
EARL'S 55-10-005-QRY Created On: 03/24/16 Updated On:	Q	NE	NE	10	28N	4W	Clark	0-225-116-2016		0.0	2.3	5.4	22.3	2.819	2.833	0.495		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
EARL'S 55-10-005-QRY Created On: 01/08/19 Updated On:	Q	NE	NE	10	28N	4W	Clark	0-225-76-2019		0.0	1.5	4.7	21.8	2.824	2.835	0.380		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
EARL'S 55-10-005-QRY Created On: 05/17/22 Updated On:	Q	NE	NE	10	28N	4W	Clark	0-225-204-2022	0.0	0.0	0.3	3.7	18.2	2.777	2.786	0.322		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
GAY 55-10-007-PIT Created On: 04/23/15 Updated On:	P	SE	SE	5	28N	2W	Clark	0-225-136-2015		0.0	1.4	4.1	19.4	2.670	2.698	1.050		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
GAY 55-10-007-PIT Created On: 01/04/23 Updated On:	P	SE	SE	5	28N	2W	Clark	0-225-96-2023	4.3	0.0	6.2	5.1	22.3	2.597	2.645	1.837		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
GOETZ 55-10-039-QRY Created On: 05/17/22 Updated On:	Q	NW	NE	26	24N	2W	Clark	0-225-200-2022	0.5	0.0	0.6	4.0	19.1	2.684	2.694	0.384		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	LA Wear (%) 100 500					Sp. Gravity OD SSD	Crse	Fine	
CLARK -- WI HUNZICKER 55-10-010-QRY Created On: 07/19/21 Updated On:	Q	SE	NE	16	26N	2W	Clark	0-225-245-2021	0.0	0.0	1.1	7.2	31.3	2.597	2.617	0.772
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate															
HUNZICKER 55-10-010-QRY Created On: 01/29/24 Updated On:	Q	SE	NE	16	26N	2W	Clark	0-225-162-2024	0.0	1.8	1.2	5.4	25.6	2.594	2.614	0.800
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate															
ISENBERGER 55-10-011-QRY Created On: 09/28/16 Updated On:	Q	SW	NW	6	28N	4W	Clark	0-225-265-2016		0.0	1.0	4.3	18.6	3.015	3.026	0.342
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate															
ISENBERGER 55-10-011-QRY Created On: 01/08/19 Updated On:	Q	SW	NW	6	28N	4W	Clark	0-225-79-2019		0.0	0.6	3.1	14.9	3.038	3.046	0.289
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate															
ISENBERGER 55-10-011-QRY Created On: 01/04/22 Updated On:	Q	SW	NW	6	28N	4W	Clark	0-225-82-2022	0.0	0.0	2.0	3.9	17.7	2.785	2.797	0.442
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate															
LONGBRANCH 55-10-015-QRY Created On: 01/29/15 Updated On:	Q	N	SW	34	29N	4W	Clark	0-225-75-2015		0.0	0.9	3.2	14.3	2.720	2.740	0.731
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate															
LONGBRANCH 55-10-015-QRY Created On: 03/08/18 Updated On:	Q	N	SW	34	29N	4W	Clark	0-225-112-2018		0.0	0.5	2.6	13.4	2.751	2.764	0.489
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate															

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse					
	P/Q	Qrt	Qrt	Sect	Town	Range	County	LA Wear (%) 100 500					Sp. Gravity OD SSD	Absorp. % Crse Fine				
CLARK -- WI																		
LONGBRANCH 55-10-015-QRY Created On: 01/05/21 Updated On:	Q	N	SW	34	29N	4W	Clark	0-225-89-2021	0.3	0.0	0.8	3.4	16.0	2.742	2.755	0.472		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
LONGBRANCH 55-10-015-QRY Created On: 01/02/24 Updated On:	Q	N	SW	34	29N	4W	Clark	0-225-86-2024	0.1	0.0	1.1	3.3	16.2	2.756	2.769	0.465		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MERRILLAN-734 55-10-018-QRY Created On: 07/02/15 Updated On:	Q	NW	SW	13	23N	3W	Clark	0-225-203-2015		0.0	0.5	2.5	15.8	2.635	2.646	0.435		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
MERRILLAN-734 55-10-018-QRY Created On: 01/03/18 Updated On:	Q	NW	SW	13	23N	3W	Clark	0-225-37-2018		0.0	0.4	3.7	20.1	2.622	2.634	0.432		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MERRILLAN-734 55-10-018-QRY Created On: 01/04/21 Updated On:	Q	NW	SW	13	23N	3W	Clark	0-225-19-2021	0.0	0.3	0.4	3.3	16.5	2.694	2.705	0.424		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MERRILLAN-734 55-10-018-QRY Created On: 01/02/24 Updated On:	Q	NW	SW	13	23N	3W	Clark	0-225-110-2024	1.0	3.2	2.2	3.9	19.8	2.658	2.692	1.268		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MERRILLAN-734 55-10-018-QRY Created On: 01/02/24 Updated On:	Q	NW	SW	13	23N	3W	Clark	0-225-111-2024	0.0	0.6	0.6	4.2	19.1	2.705	2.725	0.754		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine		
CLARK -- WI																			
MILAS 55-10-020-PIT Created On: 03/08/18 Updated On:	P	SE	NW	3	29N	3W	Clark	0-225-116-2018	1.4	0.0	2.5	4.3	19.4	2.686	2.713	1.011			
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																		
MILAS 55-10-020-PIT Created On: 01/04/23 Updated On:	P	SE	NW	3	29N	3W	Clark	0-225-98-2023	1.2	0.0	2.8	3.6	18.0	2.733	2.759	0.969			
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
NAEDLER 55-10-021-QRY Created On: 01/17/14 Updated On:	Q	SE	NE	35	25N	1W	Clark	0-225-53-2014		0.0	2.0	6.6	26.8	2.611	2.634	0.887			
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																		
NAEDLER 55-10-021-QRY Created On: 06/12/17 Updated On:	Q	SE	NE	35	25N	1W	Clark	0-225-210-2017		0.0	2.2	4.9	23.9	2.632	2.647	0.562			
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																		
NAEDLER 55-10-021-QRY Created On: 01/08/20 Updated On:	Q	SE	NE	35	25N	1W	Clark	0-225-57-2020	0.2	0.0	0.8	5.5	25.2	2.632	2.648	0.598			
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
NAEDLER 55-10-021-QRY Created On: 01/03/23 Updated On:	Q	SE	NE	35	25N	1W	Clark	0-225-39-2023	0.3	2.9	3.1	6.4	27.9	2.614	2.634	0.783			
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
NEILLSVILLE 55-10-035-QRY Created On: 06/12/17 Updated On:	Q	SE	SW	10	24N	2W	Clark	0-225-208-2017		0.0	0.4	4.7	22.5	2.598	2.611	0.494			
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																		

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
CLARK -- WI																		
NEILLSVILLE 55-10-035-QRY Created On: 01/08/20 Updated On:	Q	SE	SW	10	24N	2W	Clark	0-225-61-2020	0.4	0.0	1.5	5.0	23.1	2.609	2.624	0.537		
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
NEILLSVILLE 55-10-035-QRY Created On: 01/02/24 Updated On:	Q	SE	SW	10	24N	2W	Clark	0-225-109-2024	1.2	0.4	1.4	5.2	22.9	2.585	2.605	0.767		
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
NERDRUM 55-10-038-PIT Created On: 10/05/20 Updated On:	P	SE	NW	15	29N	2W	Clark	0-225-243-2020	1.5	0.0	1.2	4.9	21.9	2.684	2.717	1.228		
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
OPELT PIT 55-10-023-PIT Created On: 04/25/17 Updated On:	P	NE	NW	8	23N	2W	Clark	0-225-149-2017		0.0	1.1	3.9	18.9	2.709	2.734	0.920		
Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																		
OPELT PIT 55-10-023-PIT Created On: 04/05/22 Updated On:	P	NE	NW	8	23N	2W	Clark	0-225-158-2022	2.0	0.0	0.9	3.9	19.6	2.674	2.703	1.085		
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
OPELT QUARRY 55-10-024-QRY Created On: 04/25/17 Updated On:	Q	NE	NW	8	23N	2W	Clark	0-225-148-2017		0.0	0.2	4.2	18.0	2.829	2.839	0.354		
Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																		
OPELT QUARRY 55-10-024-QRY Created On: 05/04/20 Updated On:	Q	NE	NW	8	23N	2W	Clark	0-225-164-2020	0.0	0.0	0.4	4.4	21.7	2.745	2.753	0.314		
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse								
	P/Q	Qrt	Qrt	Sect	Town	Range	County	LA Wear (%) 100 500					Sp. Gravity OD SSD	Absorp. % Crse Fine							
CLARK -- WI																					
OPELT QUARRY 55-10-024-QRY Created On: 01/03/23 Updated On:	Q	NE	NW	8	23N	2W	Clark	0-225-35-2023	0.0	0.2	0.3	3.7	17.6	2.851	2.865	0.492					
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																				
PAUL BUGAR "B" 55-10-026-QRY Created On: 05/21/15 Updated On:	Q	SE	NE	26	25N	1W	Clark	0-225-178-2015		0.0	0.3	6.9	30.5	2.620	2.642	0.831					
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																				
PAUL BUGAR "B" 55-10-026-QRY Created On: 04/25/18 Updated On:	Q	SE	NE	26	25N	1W	Clark	0-225-185-2018	0.4	0.0	0.3	5.3	26.4	2.641	2.656	0.597					
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																				
PAUL BUGAR "B" 55-10-026-QRY Created On: 06/17/21 Updated On:	Q	SE	NE	26	25N	1W	Clark	0-225-226-2021	0.1	0.0	2.1	7.2	30.6	2.605	2.626	0.803					
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																				
PAUL BUGAR "B" 55-10-026-QRY Created On: 02/28/24 Updated On:	Q	SE	NE	26	25N	1W	Clark	0-225-192-2024	0.5	0.0	0.5	7.2	32.6	2.615	2.628	0.490					
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																				
PINE VALLEY 55-10-027-QRY Created On: 05/07/15 Updated On:	Q		NW	21	24N	2W	Clark	0-225-152-2015		0.0	0.8	5.9	25.6	2.608	2.621	0.498					
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																				
PINE VALLEY 55-10-027-QRY Created On: 04/19/18 Updated On:	Q		NW	21	24N	2W	Clark	0-225-174-2018	0.8	0.0	1.5	6.7	28.0	2.571	2.596	0.973					
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																				

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse				
	P/Q	Qrt	Qrt	Sect	Town	Range	County					LA Wear (%)		Sp. Gravity		Absorp. %
											100	500	OD	SSD	Crse	Fine
CLARK -- WI																
PINE VALLEY 55-10-027-QRY Created On: 04/08/21 Updated On:	Q		NW	21	24N	2W	Clark	0-225-174-2021	2.4	1.1	3.3	8.8	32.2	2.548	2.579	1.207
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate															
PINE VALLEY 55-10-027-QRY Created On: 01/29/24 Updated On:	Q		NW	21	24N	2W	Clark	0-225-163-2024	1.0	1.4	0.8	4.1	21.0	2.598	2.613	0.582
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate															
*PRIBBERNOW 55-10-032-QRY Created On: 01/30/14 Updated On:	Q	E	E	13	28N	2W	Clark	0-225-64-2014		0.0	0.9	4.2	18.1	2.647	2.667	0.766
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate															
*PRIBBERNOW 55-10-032-QRY Created On: 01/03/17 Updated On:	Q	E	E	13	28N	2W	Clark	0-225-5-2017		0.0	0.8	4.6	21.0	2.626	2.647	0.784
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate															
*PRIBBERNOW 55-10-032-QRY Created On: 01/07/20 Updated On:	Q	E	E	13	28N	2W	Clark	0-225-41-2020	0.0	0.0	0.6	4.4	19.9	2.707	2.716	0.361
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate															
COLUMBIA -- WI																
ARLINGTON 55-11-002-PIT Created On: 05/04/17 Updated On:	P			23	10N	9E	Columbia	0-225-166-2017	2.4	0.0	4.2	5.7	26.4	2.674	2.724	1.863
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate															
ARLINGTON 55-11-002-PIT Created On: 06/01/22 Updated On:	P			23	10N	9E	Columbia	0-225-210-2022	1.7	0.0	4.8	5.4	26.5	2.705	2.746	1.502
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate															

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Coarse Sp. Gravity		Coarse Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
COLUMBIA -- WI																		
BALLWEG 55-11-003-QRY Created On: 01/21/16 Updated On:	Q		SE	25	10N	7E	Columbia	0-225-63-2016	0.8	1.1	1.0	7.2	30.7	2.590	2.656	2.547		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
BALLWEG 55-11-003-QRY Created On: 04/01/19 Updated On:	Q		SE	25	10N	7E	Columbia	0-225-119-2019	0.9	3.4	5.8	8.7	33.7	2.615	2.669	2.090		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
BALLWEG 55-11-003-QRY Created On: 01/04/22 Updated On:	Q		SE	25	10N	7E	Columbia	0-225-57-2022	0.8	1.3	3.0	7.7	30.0	2.618	2.672	2.065		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
BECKER 55-11-004-PIT Created On: 01/07/16 Updated On:	P		SW	34	13N	10E	Columbia	0-225-42-2016		0.0	2.0	6.8	29.1	2.658	2.707	1.856		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
BECKER 55-11-004-PIT Created On: 01/05/21 Updated On:	P		SW	34	13N	10E	Columbia	0-225-79-2021	0.0	2.9	2.9	5.6	26.3	2.686	2.732	1.714		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
BLAU (LYCON) 55-11-006-PIT Created On: 01/20/17 Updated On:	P	NE	NW	2	11N	8E	Columbia	0-225-54-2017	1.4	0.0	2.6	7.1	30.0	2.674	2.708	1.266		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
BLAU (LYCON) 55-11-006-PIT Created On: 01/04/22 Updated On:	P	NE	NW	2	11N	8E	Columbia	0-225-42-2022	1.2	0.0	2.8	6.3	28.7	2.692	2.725	1.213		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse							
	P/Q	Qrt	Qrt	Sect	Town	Range	County	LA Wear (%) 100					500	Sp. Gravity OD SSD		Absorp. % Crse Fine				
COLUMBIA -- WI																				
BROWN 55-11-010-PIT Created On: 01/03/18 Updated On:	P	NW	SW	18	12N	10E	Columbia	0-225-25-2018	0.3	5.0	1.3	9.8	31.8	2.666	2.718	1.932				
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																			
BROWN 55-11-010-PIT Created On: 01/04/23 Updated On:	P	NW	SW	18	12N	10E	Columbia	0-225-93-2023	0.4	0.0	1.8	6.9	30.3	2.691	2.732	1.523				
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																			
ERVIN STIEMKE 55-11-013-QRY Created On: 07/03/14 Updated On:	Q	NW	SW	18	10N	10E	Columbia	0-225-207-2014	1.0	0.6	0.8	7.5	32.8	2.562	2.627	2.563				
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																			
ERVIN STIEMKE 55-11-013-QRY Created On: 01/05/17 Updated On:	Q	NW	SW	18	10N	10E	Columbia	0-225-49-2017	1.3	2.5	2.5	11.3	35.5	2.549	2.614	2.559				
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																			
ERVIN STIEMKE 55-11-013-QRY Created On: 01/08/20 Updated On:	Q	NW	SW	18	10N	10E	Columbia	0-225-68-2020	0.1	1.3	3.2	7.9	31.2	2.598	2.658	2.286				
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																			
ERVIN STIEMKE 55-11-013-QRY Created On: 04/04/23 Updated On:	Q	NW	SW	18	10N	10E	Columbia	0-225-177-2023	0.6	1.2	2.2	7.3	29.8	2.556	2.631	2.952				
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																			
ERVIN STIEMKE 55-11-013-QRY Created On: 04/18/24 Updated On:	Q	NW	SW	18	10N	10E	Columbia	0-225-234-2024	0.3	1.1	2.4	7.8	32.9	2.564	2.634	2.741				
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																			

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse						
	P/Q	Qrt	Qrt	Sect	Town	Range	County	LA Wear (%) 100 500					Sp. Gravity OD SSD	Absorp. % Crse Fine					
COLUMBIA -- WI																			
HAHN 55-11-014-QRY Created On: 06/17/14 Updated On:	Q	NW	SE	11	12N	11E	Columbia	0-225-197-2014		6.7	7.2	13.0	38.8	2.527	2.611	3.317			
Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																			
HAHN 55-11-014-QRY Created On: 01/05/17 Updated On:	Q	NW	SE	11	12N	11E	Columbia	0-225-48-2017		0.9	2.6	1.6	13.7	38.3	2.548	2.625	3.010		
Approved Use : CONCRETE, OGBC, Base Aggregate																			
HAHN 55-11-014-QRY Created On: 01/08/20 Updated On:	Q	NW	SE	11	12N	11E	Columbia	0-225-69-2020		0.7	4.8	8.0	10.0	41.1	2.549	2.625	2.962		
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																			
HAHN 55-11-014-QRY Created On: 01/04/23 Updated On:	Q	NW	SE	11	12N	11E	Columbia	0-225-94-2023		0.9	4.9	5.5	11.3	43.4	2.531	2.614	3.289		
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																			
HARTMANN QUARRY 55-11-041-QRY Created On: 01/02/24 Updated On:	Q	NE	NE	36	10N	7E	Columbia	0-225-43-2024		1.6	2.9	9.7	9.0	34.8	2.566	2.633	2.631		
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																			
HOLDER PIT 55-11-017-PIT Created On: 01/03/17 Updated On:	P	NW	SE	30	12N	11E	Columbia	0-225-7-2017		6.6	0.0	7.8	11.5	37.8	2.625	2.680	2.079		
Approved Use : HMA<E-3, HMA>=E-3, OGBC, Base Aggregate																			
HOLDER PIT 55-11-017-PIT Created On: 01/04/22 Updated On:	P	NW	SE	30	12N	11E	Columbia	0-225-5-2022		6.6	0.0	9.7	11.0	37.6	2.638	2.687	1.882		
Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																			

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse						
	P/Q	Qrt	Qrt	Sect	Town	Range	County	LA Wear (%) 100					500	Sp. Gravity OD SSD		Absorp. % Crse Fine			
COLUMBIA -- WI																			
JENKINS 55-11-018-QRY Created On: 07/17/14 Updated On:	Q			11	13N	10E	Columbia	0-225-225-2014		0.8	3.0	10.5	39.5	2.578	2.643	2.502			
Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																			
JENKINS 55-11-018-QRY Created On: 05/11/17 Updated On:	Q			11	13N	10E	Columbia	0-225-184-2017		0.9	2.5	11.1	39.9	2.599	2.663	2.473			
Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																			
JENKINS 55-11-018-QRY Created On: 01/06/20 Updated On:	Q			11	13N	10E	Columbia	0-225-34-2020		0.2	0.9	2.7	9.9	38.8	2.602	2.663	2.366		
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																			
JENKINS 55-11-018-QRY Created On: 01/03/23 Updated On:	Q			11	13N	10E	Columbia	0-225-69-2023		0.2	1.3	1.8	10.3	38.1	2.607	2.662	2.126		
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																			
KETTLESON 55-11-041-PIT Created On: 05/02/17 Updated On:	P	NW	NE	6	13N	7E	Columbia	0-225-163-2017		0.0	3.7	9.4	33.1	2.770	2.803	1.191			
Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																			
KETTLESON 55-11-041-PIT Created On: 01/04/22 Updated On:	P	NW	NE	6	13N	7E	Columbia	0-225-12-2022		0.5	0.0	1.5	6.4	27.6	2.773	2.803	1.093		
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																			
KOHN 55-11-019-PIT Created On: 05/03/22 Updated On:	P			30	12N	11E	Columbia	0-225-193-2022		2.7	4.5	3.6	5.9	27.9	2.717	2.754	1.376		
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																			

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse							
	P/Q	Qrt	Qrt	Sect	Town	Range	County	LA Wear (%) 100					500	Sp. Gravity OD SSD		Absorp. % Crse Fine				
COLUMBIA -- WI																				
*LINCK #27 55-11-026-QRY Created On: 01/29/15 Updated On:	Q	SW	SW	24	10N	12E	Columbia	0-225-77-2015	0.3	1.4	3.6	5.6	22.9	2.622	2.673	1.954				
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																			
*LINCK #27 55-11-026-QRY Created On: 03/01/18 Updated On:	Q	SW	SW	24	10N	12E	Columbia	0-225-108-2018	0.3	3.2	2.5	8.3	35.0	2.577	2.657	3.087				
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																			
*LINCK #27 55-11-026-QRY Created On: 03/29/21 Updated On:	Q	SW	SW	24	10N	12E	Columbia	0-225-164-2021	5.0	14.3	1.2	10.5	38.5	2.587	2.654	2.563				
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																			
MICHELS COLUMBUS 55-11-028-QRY Created On: 04/11/14 Updated On:	Q			11	10N	12E	Columbia	0-225-125-2014		7.0	10.1	9.3	37.0	2.566	2.635	2.675				
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																			
MICHELS COLUMBUS 55-11-028-QRY Created On: 01/03/17 Updated On:	Q			11	10N	12E	Columbia	0-225-9-2017	1.9	7.8	7.5	9.8	38.7	2.584	2.647	2.440				
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																			
MICHELS COLUMBUS 55-11-028-QRY Created On: 03/09/20 Updated On:	Q			11	10N	12E	Columbia	0-225-124-2020	2.9	15.0	7.8	10.1	41.5	2.598	2.664	2.568				
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																			
MICHELS COLUMBUS 55-11-028-QRY Created On: 01/04/22 Updated On:	Q			11	10N	12E	Columbia	0-225-4-2022	2.7	6.5	9.5	10.0	40.5	2.542	2.616	2.925				
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																			

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse						
	P/Q	Qrt	Qrt	Sect	Town	Range	County	LA Wear (%) 100 500					Sp. Gravity OD SSD	Absorp. % Crse Fine					
COLUMBIA -- WI																			
MILESTONE-DONALD NELSON 55-11-029-PIT Created On: 06/12/14 Updated On:	P	SW	NW	12	13N	6E	Columbia	0-225-192-2014		0.0	2.7	7.4	30.4	2.761	2.791	1.097			
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																		
MILESTONE-DONALD NELSON 55-11-029-PIT Created On: 01/04/19 Updated On:	P	SW	NW	12	13N	6E	Columbia	0-225-21-2019	0.5	0.0	4.1	8.0	31.3	2.693	2.735	1.561			
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																		
MILESTONE-DONALD NELSON 55-11-029-PIT Created On: 01/02/24 Updated On:	P	SW	NW	12	13N	6E	Columbia	0-225-20-2024	1.0	4.2	3.0	7.4	29.3	2.702	2.739	1.355			
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
PLENTY 55-11-030-QRY Created On: 05/08/19 Updated On:	Q			16	10N	9E	Columbia	0-225-179-2019	2.8	4.3	3.2	11.0	43.0	2.494	2.596	4.114			
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
PLENTY 55-11-030-QRY Created On: 08/02/22 Updated On:	Q			16	10N	9E	Columbia	0-225-250-2022	3.3	5.4	4.1	9.7	38.5	2.564	2.623	2.291			
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
RIO AGGREGATE PRODUCTS 55-11-020-QRY Created On: 02/09/22 Updated On:	Q	NW	SE	32	12N	11E	Columbia	0-225-118-2022	0.8	2.4	3.1	8.1	35.2	2.617	2.675	2.203			
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
STEVENSON 55-11-036-QRY Created On: 03/31/15 Updated On:	Q			8	10N	9E	Columbia	0-225-111-2015		1.2	2.2	13.0	45.0	2.524	2.602	3.118			
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																		

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse							
	P/Q	Qrt	Qrt	Sect	Town	Range	County	LA Wear (%) 100					500	Sp. Gravity OD SSD		Absorp. % Crse Fine				
COLUMBIA -- WI																				
STEVENSON 55-11-036-QRY Created On: 01/03/18 Updated On:	Q			8	10N	9E	Columbia	0-225-6-2018	2.5	0.7	3.9	10.4	36.7	2.529	2.615	3.422				
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																			
STEVENSON 55-11-036-QRY Created On: 01/04/21 Updated On:	Q			8	10N	9E	Columbia	0-225-40-2021	2.3	1.2	0.6	8.9	33.9	2.548	2.620	2.799				
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																			
STEVENSON 55-11-036-QRY Created On: 01/02/24 Updated On:	Q			8	10N	9E	Columbia	0-225-18-2024	4.9	5.1	3.1	15.9	45.9	2.512	2.604	3.663				
	Approved Use : CONCRETE, OGBC, Base Aggregate																			
TRIAMSTRA 55-11-037-QRY Created On: 03/23/16 Updated On:	Q	NE	SW	11	13N	10E	Columbia	0-225-104-2016		0.9	0.5	10.5	39.6	2.599	2.656	2.187				
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																			
TRIAMSTRA 55-11-037-QRY Created On: 04/01/19 Updated On:	Q	NE	SW	11	13N	10E	Columbia	0-225-122-2019	2.6	1.8	1.1	10.4	37.7	2.642	2.689	1.765				
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																			
TRIAMSTRA 55-11-037-QRY Created On: 04/05/22 Updated On:	Q	NE	SW	11	13N	10E	Columbia	0-225-162-2022	4.1	1.5	1.5	10.7	39.1	2.618	2.673	2.086				
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																			
WILLIAMS 55-11-039-QRY Created On: 03/30/15 Updated On:	Q	SE	NE	19	12N	8E	Columbia	0-225-103-2015		0.2	0.2	6.0	24.1	2.633	2.646	0.477				
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																			

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse						
	P/Q	Qrt	Qrt	Sect	Town	Range	County	LA Wear (%) 100 500					Sp. Gravity OD SSD		Absorp. % Crse Fine				
COLUMBIA -- WI																			
WILLIAMS 55-11-039-QRY Created On: 01/03/18 Updated On:	Q	SE	NE	19	12N	8E	Columbia	0-225-8-2018	0.0	0.0	0.0	4.4	19.7	2.634	2.644	0.400			
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																		
WILLIAMS 55-11-039-QRY Created On: 01/04/21 Updated On:	Q	SE	NE	19	12N	8E	Columbia	0-225-41-2021	0.0	0.0	0.4	6.1	25.1	2.627	2.639	0.481			
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
WILLIAMS 55-11-039-QRY Created On: 01/02/24 Updated On:	Q	SE	NE	19	12N	8E	Columbia	0-225-19-2024	0.1	0.3	0.4	5.3	23.1	2.653	2.659	0.219			
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
CRAWFORD -- WI																			
*BENECKER 55-12-002-QRY Created On: 01/02/14 Updated On:	Q			5	6N	6W	Crawford	0-225-1-2014	10.9	3.2	10.3	16.7	49.4	2.511	2.593	3.275			
	Approved Use : OGBC, Base Aggregate																		
*BENECKER 55-12-002-QRY Created On: 01/04/21 Updated On:	Q			5	6N	6W	Crawford	0-225-28-2021	11.3	7.8	17.1	18.7	50.3	2.423	2.521	4.012			
	Approved Use : Base Aggregate																		
DOSKOCIL QUARRY 55-12-007-QRY Created On: 06/12/14 Updated On:	Q	S	SE	2	9N	5W	Crawford	0-225-194-2014		0.7	4.3	11.1	39.6	2.577	2.642	2.513			
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																		
DOSKOCIL QUARRY 55-12-007-QRY Created On: 05/19/17 Updated On:	Q	S	SE	2	9N	5W	Crawford	0-225-191-2017		1.4	5.9	10.4	39.6	2.566	2.637	2.788			
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Coarse Sp. Gravity		Coarse Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
CRAWFORD -- WI																		
DOSKOCIL QUARRY 55-12-007-QRY Created On: 01/09/20 Updated On:	Q	S	SE	2	9N	5W	Crawford	0-225-83-2020	0.4	3.5	2.0	13.1	46.3	2.502	2.569	2.645		
	Approved Use : HMA<MT, CONCRETE, Base Aggregate																	
DOSKOCIL QUARRY 55-12-007-QRY Created On: 01/02/24 Updated On:	Q	S	SE	2	9N	5W	Crawford	0-225-37-2024	1.2	3.5	0.5	9.3	39.2	2.606	2.664	2.235		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
FAIRVIEW QUARRY 55-12-008-QRY Created On: 04/10/14 Updated On:	Q	SW	NE	2	10N	5W	Crawford	0-225-120-2014		1.0	3.5	9.2	33.7	2.646	2.692	1.746		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
FAIRVIEW QUARRY 55-12-008-QRY Created On: 01/05/17 Updated On:	Q	SW	NE	2	10N	5W	Crawford	0-225-30-2017		2.3	5.1	12.0	41.0	2.557	2.625	2.668		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
FAIRVIEW QUARRY 55-12-008-QRY Created On: 01/03/20 Updated On:	Q	SW	NE	2	10N	5W	Crawford	0-225-19-2020	2.6	2.1	1.3	11.1	38.1	2.593	2.653	2.326		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
FAIRVIEW QUARRY 55-12-008-QRY Created On: 01/03/23 Updated On:	Q	SW	NE	2	10N	5W	Crawford	0-225-67-2023	2.3	3.8	1.5	11.6	38.1	2.593	2.658	2.498		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
FORDE 55-12-009-QRY Created On: 01/04/24 Updated On:	Q	SE	NE	5	10N	6W	Crawford	0-225-137-2024	0.2	16.0	4.6	9.5	34.9	2.606	2.672	2.521		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse						
	P/Q	Qrt	Qrt	Sect	Town	Range	County	LA Wear (%) 100 500					Sp. Gravity OD SSD		Absorp. % Crse Fine				
CRAWFORD -- WI																			
*HAGGERTY 55-12-010-QRY Created On: 07/17/15 Updated On:	Q	SW	SW	10	9N	3W	Crawford	0-225-212-2015		2.6	3.4	8.2	33.6	2.625	2.678	2.011			
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																		
*HAGGERTY 55-12-010-QRY Created On: 07/09/20 Updated On:	Q	SW	SW	10	9N	3W	Crawford	0-225-210-2020		0.9	1.5	3.6	9.1	32.3	2.629	2.684	2.072		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
*O'CONNELL 55-12-013-QRY Created On: 06/20/19 Updated On:	Q			8	8N	6W	Crawford	0-225-223-2019		3.6	4.2	8.6	13.0	42.6	2.528	2.607	3.108		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																		
*SHOCKLEY HILL 55-12-020-QRY Created On: 01/07/14 Updated On:	Q	SW	NE	21	8N	3W	Crawford	0-225-36-2014		1.0	3.4	6.9	27.8	2.630	2.679	1.870			
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																		
*SHOCKLEY HILL 55-12-020-QRY Created On: 05/18/17 Updated On:	Q	SW	NE	21	8N	3W	Crawford	0-225-189-2017		2.8	6.6	8.7	33.7	2.632	2.687	2.097			
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
*SHOCKLEY HILL 55-12-020-QRY Created On: 01/03/20 Updated On:	Q	SW	NE	21	8N	3W	Crawford	0-225-20-2020		0.5	1.1	0.5	7.2	28.3	2.618	2.675	2.193		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
*SHOCKLEY HILL 55-12-020-QRY Created On: 01/02/24 Updated On:	Q	SW	NE	21	8N	3W	Crawford	0-225-33-2024		0.8	4.5	2.8	9.2	34.2	2.599	2.662	2.416		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse						
	P/Q	Qrt	Qrt	Sect	Town	Range	County	LA Wear (%) 100 500					Sp. Gravity OD SSD		Absorp. % Crse Fine				
CRAWFORD -- WI																			
SLAMA 55-12-021-QRY Created On: 07/30/15 Updated On:	Q		18	7N	6W	Crawford		0-225-222-2015	1.1	1.8	2.1	8.7	33.9	2.614	2.675	2.350			
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																		
SLAMA 55-12-021-QRY Created On: 01/04/18 Updated On:	Q		18	7N	6W	Crawford		0-225-73-2018	0.7	1.0	3.2	7.5	37.9	2.636	2.685	1.845			
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
SLAMA 55-12-021-QRY Created On: 01/04/21 Updated On:	Q		18	7N	6W	Crawford		0-225-26-2021	1.0	6.6	5.0	7.5	31.7	2.612	2.668	2.167			
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
SLAMA 55-12-021-QRY Created On: 01/02/24 Updated On:	Q		18	7N	6W	Crawford		0-225-27-2024	2.0	4.1	1.2	7.0	28.1	2.650	2.696	1.710			
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
SWIGGUM 55-12-022-QRY Created On: 07/17/15 Updated On:	Q	SW	NW	29	11N	3W	Crawford	0-225-213-2015		1.1	1.4	9.1	35.6	2.640	2.687	1.764			
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																		
SWIGGUM 55-12-022-QRY Created On: 05/19/16 Updated On:	Q	SW	NW	29	11N	3W	Crawford	0-225-183-2016		1.4	3.9	8.9	34.4	2.661	2.705	1.650			
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																		
SWIGGUM 55-12-022-QRY Created On: 01/07/19 Updated On:	Q	SW	NW	29	11N	3W	Crawford	0-225-55-2019		1.0	2.0	3.5	10.1	36.8	2.602	2.662	2.325		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																		

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse				
	P/Q	Qrt	Qrt	Sect	Town	Range	County					LA Wear (%)		Sp. Gravity		Absorp. %
											100	500	OD	SSD	Crse	Fine
CRAWFORD -- WI																
SWIGGUM 55-12-022-QRY Created On: 02/16/22 Updated On:	Q	SW	NW	29	11N	3W	Crawford	0-225-123-2022	0.4	5.6	0.3	9.0	35.8	2.642	2.697	2.073
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate															
SWIGGUM 55-12-022-QRY Created On: 01/02/24 Updated On:	Q	SW	NW	29	11N	3W	Crawford	0-225-2-2024	0.1	1.3	1.5	8.5	36.0	2.537	2.619	3.207
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate															
WETZEL 55-12-024-QRY Created On: 04/10/14 Updated On:	Q	NW	SE	31	7N	6W	Crawford	0-225-119-2014		1.2	4.8	7.8	30.0	2.574	2.632	2.247
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate															
WETZEL 55-12-024-QRY Created On: 01/05/17 Updated On:	Q	NW	SE	31	7N	6W	Crawford	0-225-33-2017		1.2	3.3	6.7	28.7	2.633	2.685	1.977
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate															
WETZEL 55-12-024-QRY Created On: 01/03/20 Updated On:	Q	NW	SE	31	7N	6W	Crawford	0-225-23-2020	2.3	3.6	2.9	12.1	40.5	2.558	2.633	2.939
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate															
WETZEL 55-12-024-QRY Created On: 01/03/23 Updated On:	Q	NW	SE	31	7N	6W	Crawford	0-225-71-2023	1.2	4.7	0.6	11.7	39.2	2.604	2.662	2.251
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate															
DANE -- WI																
BONG 55-13-004-QRY Created On: 05/11/18 Updated On:	Q	SW	SE	11	8N	9E	Dane	0-225-210-2018	4.1	1.9	3.7	11.9	39.2	2.537	2.611	2.930
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate															

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
DANE -- WI																		
BONG 55-13-004-QRY Created On: 02/15/21 Updated On:	Q	SW	SE	11	8N	9E	Dane	0-225-127-2021	5.2	3.4	3.4	9.2	36.4	2.570	2.638	2.624		
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																	
BONG 55-13-004-QRY Created On: 01/04/24 Updated On:	Q	SW	SE	11	8N	9E	Dane	0-225-148-2024	3.2	5.5	2.5	9.8	40.1	2.560	2.625	2.530		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
BONG (YAHARA) 55-13-004-QRY Created On: 04/18/24 Updated On:	Q	SW	SE	11	8N	9E	Dane	0-225-235-2024	0.6	7.4	5.3	12.0	46.5	2.489	2.579	3.606		
	Approved Use : HMA<MT, CONCRETE, OGBC, Base Aggregate																	
BREUNIG 55-13-006-PIT Created On: 01/20/17 Updated On:	P	NE	NW	7	9N	7E	Dane	0-225-55-2017	1.5	0.0	5.2	7.6	30.6	2.677	2.724	1.745		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
BREUNIG 55-13-006-PIT Created On: 01/04/22 Updated On:	P	NE	NW	7	9N	7E	Dane	0-225-43-2022	2.1	0.0	6.8	7.2	31.4	2.671	2.720	1.819		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
BUCKEYE 55-13-008-QRY Created On: 01/21/15 Updated On:	Q	SW	NE	14	7N	10E	Dane	0-225-74-2015		6.1	4.4	9.7	38.9	2.563	2.636	2.824		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
BUCKEYE 55-13-008-QRY Created On: 01/05/17 Updated On:	Q	SW	NE	14	7N	10E	Dane	0-225-35-2017	1.1	3.7	2.1	6.2	27.2	2.603	2.667	2.481		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse					
	P/Q	Qrt	Qrt	Sect	Town	Range	County					LA Wear (%)		Sp. Gravity		Absorp. %	
												100	500	OD	SSD	Crse	Fine
DANE -- WI																	
BUCKEYE 55-13-008-QRY Created On: 05/13/19 Updated On:	Q	SW	NE	14	7N	10E	Dane	0-225-186-2019	0.3	1.1	0.9	6.9	28.7	2.619	2.678	2.260	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
BUCKEYE 55-13-008-QRY Created On: 03/09/20 Updated On:	Q	SW	NE	14	7N	10E	Dane	0-225-121-2020	0.1	1.6	4.7	6.3	25.1	2.644	2.695	1.895	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
BUCKEYE 55-13-008-QRY Created On: 03/16/21 Updated On:	Q	SW	NE	14	7N	10E	Dane	0-225-136-2021	0.8	1.6	3.4	6.4	26.8	2.634	2.689	2.079	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
BUCKEYE 55-13-008-QRY Created On: 01/02/24 Updated On:	Q	SW	NE	14	7N	10E	Dane	0-225-88-2024	0.2	3.0	2.4	10.1	35.4	2.583	2.646	2.430	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
C6 QUARRY 55-13-126-QRY Created On: 09/05/23 Updated On:	Q	NE	NW	17	6N	8E	Dane	0-225-250-2023	0.7	2.8	0.5	5.4	23.9	2.680	2.720	1.486	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
*CAMEL HILL 55-13-009-QRY Created On: 01/09/15 Updated On:	Q		W	24	7N	7E	Dane	0-225-55-2015		26.6	18.4	8.0	35.2	2.550	2.635	3.338	
	Approved Use : Base Aggregate																
*CAMEL HILL 55-13-009-QRY Created On: 02/16/16 Updated On:	Q		W	24	7N	7E	Dane	0-225-83-2016		10.7	13.2	8.4	37.9	2.579	2.652	2.834	
	Approved Use : Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Coarse Sp. Gravity		Coarse Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
DANE -- WI																		
*CAMEL HILL 55-13-009-QRY Created On: 01/04/19 Updated On:	Q		W	24	7N	7E	Dane	0-225-31-2019	1.9	1.7	6.3	7.5	30.9	2.632	2.683	1.935		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
CAPITOL SAND & GRAVEL 55-13-010-PIT Created On: 09/26/18 Updated On:	P			11	7N	7E	Dane	0-225-283-2018	9.2	5.8	3.1	8.1	32.1	2.587	2.639	1.997		
	Approved Use : HMA<MT, HMA>=MT, Base Aggregate																	
CAPITOL SAND & GRAVEL 55-13-010-PIT Created On: 01/09/20 Updated On:	P			11	7N	7E	Dane	0-225-92-2020	4.2	9.1	0.9	11.0	38.5	2.635	2.681	1.729		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
CAPITOL SAND & GRAVEL 55-13-010-PIT Created On: 01/02/24 Updated On:	P			11	7N	7E	Dane	0-225-41-2024	1.7	2.8	5.7	11.0	38.2	2.649	2.691	1.584		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
EVANS 55-13-017-QRY Created On: 01/06/20 Updated On:	Q	NW	SW	24	9N	9E	Dane	0-225-29-2020	0.8	1.4	1.9	7.6	31.7	2.614	2.660	1.742		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
EVANS 55-13-017-QRY Created On: 01/04/23 Updated On:	Q	NW	SW	24	9N	9E	Dane	0-225-92-2023	0.7	1.1	1.4	8.8	34.9	2.602	2.661	2.297		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
FINK 55-13-020-QRY Created On: 01/04/22 Updated On:	Q	NW	NW	14	6N	6E	Dane	0-225-44-2022	0.8	7.7	11.0	11.7	43.2	2.552	2.628	2.944		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse					
	P/Q	Qrt	Qrt	Sect	Town	Range	County					LA Wear (%)		Sp. Gravity		Absorp. %	
											100	500	OD	SSD	Crse	Fine	
DANE -- WI																	
FINK (YAHARA) 55-13-021-QRY Created On: 03/19/15 Updated On:	Q	SE	NW	14	6N	6E	Dane	0-225-98-2015		8.2	4.0	10.4	38.4	2.563	2.635	2.807	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
FINK (YAHARA) 55-13-021-QRY Created On: 01/03/18 Updated On:	Q	SE	NW	14	6N	6E	Dane	0-225-27-2018		1.0	10.3	8.2	10.5	40.7	2.506	2.599	3.703
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
FINK (YAHARA) 55-13-021-QRY Created On: 06/20/22 Updated On:	Q	SE	NW	14	6N	6E	Dane	0-225-234-2022		0.6	0.8	2.1	7.7	33.0	2.679	2.719	1.507
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
FITCHBURG HILLS QUARRY 55-13-127-QRY Created On: 03/27/24 Updated On:	Q	NE	NE	18	6N	9E	Dane	0-225-217-2024		0.2	9.2	4.7	8.9	37.8	2.602	2.672	2.669
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
GILLES (DANE) 55-13-024-QRY Created On: 01/24/22 Updated On:	Q	NW	NW	4	9N	9E	Dane	0-225-117-2022		0.7	1.2	1.1	9.5	34.9	2.602	2.658	2.140
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
GILLES (DANE) 55-13-024-QRY Created On: 01/23/23 Updated On:	Q	NW	NW	4	9N	9E	Dane	0-225-131-2023		0.3	1.2	1.0	8.6	35.3	2.560	2.628	2.681
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
GILLES (DANE) 55-13-024-QRY Created On: 04/15/24 Updated On:	Q	NW	NW	4	9N	9E	Dane	0-225-225-2024		0.7	0.9	1.7	9.5	37.8	2.602	2.665	2.409
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Coarse Sp. Gravity		Coarse Absorp. %			
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine		
DANE -- WI																			
HARVEST HAVEN / O'BRIAN 55-13-030-QRY Created On: 01/07/15 Updated On:	Q		SE	7	6N	9E	Dane	0-225-8-2015		21.1	10.1	6.0	28.1	2.614	2.680	2.509			
HARVEST HAVEN / O'BRIAN 55-13-030-QRY Created On: 06/03/15 Updated On:	Q		SE	7	6N	9E	Dane	0-225-181-2015 Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate		16.0	7.4	6.4	30.3	2.608	2.683	2.892			
HARVEST HAVEN / O'BRIAN 55-13-030-QRY Created On: 09/15/16 Updated On:	Q		SE	7	6N	9E	Dane	0-225-256-2016 Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate		0.5	15.9	9.8	7.2	32.5	2.596	2.666	2.711		
HARVEST HAVEN / O'BRIAN 55-13-030-QRY Created On: 01/02/18 Updated On:	Q		SE	7	6N	9E	Dane	0-225-1-2018 Approved Use : Base Aggregate		0.8	8.7	13.9	6.1	30.7	2.597	2.665	2.601		
HARVEST HAVEN / O'BRIAN 55-13-030-QRY Created On: 03/18/21 Updated On:	Q		SE	7	6N	9E	Dane	0-225-154-2021 Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate		0.4	4.0	7.1	8.1	34.2	2.597	2.657	2.288		
HARVEST HAVEN / O'BRIAN 55-13-030-QRY Created On: 01/04/24 Updated On:	Q		SE	7	6N	9E	Dane	0-225-146-2024 Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate		0.7	7.4	6.2	9.8	40.1	2.580	2.649	2.667		
HAWKINSON 55-13-123-PIT Created On: 01/09/20 Updated On:	P	SE	SE	34	6N	10E	Dane	0-225-90-2020 Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate		3.9	0.0	4.1	5.7	31.2	2.634	2.687	1.999		

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse						
	P/Q	Qrt	Qrt	Sect	Town	Range	County	LA Wear (%) 100 500					Sp. Gravity OD SSD	Absorp. % Crse Fine					
DANE -- WI																			
HELLICKSON 55-13-031-PIT Created On: 04/12/17 Updated On:	P	SE	NW	34	7N	11E	Dane	0-225-123-2017	2.7	0.0	3.9	7.1	31.6	2.635	2.687	1.966			
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																		
HELLICKSON 55-13-031-PIT Created On: 04/18/22 Updated On:	P	SE	NW	34	7N	11E	Dane	0-225-175-2022	3.4	4.5	6.2	7.0	31.4	2.642	2.692	1.910			
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
*HENSEN 55-13-032-QRY Created On: 08/22/19 Updated On:	Q	NE	SW	16	8N	12E	Dane	0-225-266-2019	5.6	8.4	8.1	12.0	40.6	2.521	2.608	3.465			
	Approved Use : HMA<MT, HMA>=MT, Base Aggregate																		
HWY 51 55-13-042-QRY Created On: 01/21/15 Updated On:	Q	SW	NE	17	8N	10E	Dane	0-225-73-2015	0.8	1.6	2.7	7.9	32.6	2.609	2.666	2.187			
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																		
HWY 51 55-13-042-QRY Created On: 05/08/17 Updated On:	Q	SW	NE	17	8N	10E	Dane	0-225-176-2017	1.1	0.7	2.6	7.3	31.9	2.610	2.669	2.267			
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
HWY 51 55-13-042-QRY Created On: 04/10/18 Updated On:	Q	SW	NE	17	8N	10E	Dane	0-225-162-2018	1.9	3.5	2.9	7.6	32.3	2.586	2.647	2.375			
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																		
HWY 51 55-13-042-QRY Created On: 03/27/19 Updated On:	Q	SW	NE	17	8N	10E	Dane	0-225-117-2019	0.8	2.2	3.0	7.4	31.4	2.647	2.687	1.511			
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																		

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse					
	P/Q	Qrt	Qrt	Sect	Town	Range	County					LA Wear (%)		Sp. Gravity		Absorp. %	
												100	500	OD	SSD	Crse	Fine
DANE -- WI																	
HWY 51 55-13-042-QRY Created On: 03/09/20 Updated On:	Q	SW	NE	17	8N	10E	Dane	0-225-120-2020	0.2	1.5	2.8	7.3	30.8	2.613	2.664	1.961	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
HWY 51 55-13-042-QRY Created On: 03/29/21 Updated On:	Q	SW	NE	17	8N	10E	Dane	0-225-159-2021	0.4	1.9	1.6	7.8	30.5	2.607	2.662	2.141	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
HWY 51 55-13-042-QRY Created On: 01/04/22 Updated On:	Q	SW	NE	17	8N	10E	Dane	0-225-6-2022	1.8	5.3	2.3	6.9	30.3	2.579	2.644	2.541	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
HWY 51 55-13-042-QRY Created On: 01/23/23 Updated On:	Q	SW	NE	17	8N	10E	Dane	0-225-130-2023	0.5	2.1	1.3	7.0	30.9	2.588	2.650	2.406	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
HWY 51 55-13-042-QRY Created On: 01/02/24 Updated On:	Q	SW	NE	17	8N	10E	Dane	0-225-74-2024	0.4	2.3	3.0	6.7	30.2	2.567	2.635	2.653	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
KAMPMEIER 55-13-045-QRY Created On: 04/09/15 Updated On:	Q	SW	SW	26	7N	10E	Dane	0-225-119-2015	7.0	16.1	17.1	12.4	44.0	2.493	2.591	3.926	
	Approved Use : Base Aggregate																
KAMPMEIER 55-13-045-QRY Created On: 01/04/22 Updated On:	Q	SW	SW	26	7N	10E	Dane	0-225-58-2022	3.1	6.8	5.2	10.1	37.7	2.574	2.641	2.610	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse					
	P/Q	Qrt	Qrt	Sect	Town	Range	County					LA Wear (%)		Sp. Gravity		Absorp. %	
												100	500	OD	SSD	Crse	Fine
DANE -- WI																	
KELLY 55-13-047-QRY Created On: 04/06/16 Updated On:	Q	SW	SW	14	6N	7E	Dane	0-225-125-2016	0.2	15.7	7.7	9.7	36.0	2.582	2.655	2.854	
Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
KELLY 55-13-047-QRY Created On: 06/03/19 Updated On:	Q	SW	SW	14	6N	7E	Dane	0-225-203-2019	0.7	5.3	0.5	8.1	33.6	2.583	2.656	2.826	
Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
KELLY 55-13-047-QRY Created On: 01/04/22 Updated On:	Q	SW	SW	14	6N	7E	Dane	0-225-56-2022	0.7	5.0	2.4	6.7	28.9	2.581	2.648	2.573	
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
KIPPLEY 55-13-048-QRY Created On: 05/26/16 Updated On:	Q	NW	NE	11	8N	9E	Dane	0-225-186-2016	1.0	2.8	1.4	10.0	37.1	2.548	2.619	2.798	
Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
KIPPLEY 55-13-048-QRY Created On: 01/04/23 Updated On:	Q	NW	NE	11	8N	9E	Dane	0-225-99-2023	1.9	2.5	3.0	12.0	41.6	2.510	2.590	3.200	
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
KREUGER 55-13-050-QRY Created On: 06/10/15 Updated On:	Q	SW	SW	3	6N	11E	Dane	0-225-194-2015		24.6	6.9	6.0	30.0	2.641	2.699	2.220	
KREUGER 55-13-050-QRY Created On: 08/05/15 Updated On:	Q	SW	SW	3	6N	11E	Dane	0-225-224-2015		9.1	11.1	7.1	31.7	2.641	2.701	2.300	
Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse							
	P/Q	Qrt	Qrt	Sect	Town	Range	County	LA Wear (%) 100 500					Sp. Gravity OD SSD	Absorp. % Crse Fine						
DANE -- WI																				
KREUGER 55-13-050-QRY Created On: 01/04/18 Updated On:	Q	SW	SW	3	6N	11E	Dane	0-225-65-2018	0.3	1.7	8.1	5.6	27.7	2.657	2.707	1.912				
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																			
KREUGER 55-13-050-QRY Created On: 06/14/21 Updated On:	Q	SW	SW	3	6N	11E	Dane	0-225-223-2021	0.6	7.9	7.2	5.4	26.7	2.679	2.730	1.906				
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																			
KREUGER 55-13-050-QRY Created On: 04/04/23 Updated On:	Q	SW	SW	3	6N	11E	Dane	0-225-180-2023	0.6	14.7	10.1	10.1	39.8	2.523	2.614	3.604				
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																			
MAIER 55-13-124-QRY Created On: 01/05/21 Updated On:	Q		NW	21	9N	9E	Dane	0-225-99-2021	3.4	4.0	10.0	10.2	37.4	2.553	2.623	2.714				
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																			
MAIER 55-13-124-QRY Created On: 02/28/24 Updated On:	Q		NW	21	9N	9E	Dane	0-225-190-2024	2.5	4.5	4.3	7.5	32.2	2.602	2.665	2.428				
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																			
MEINHOLZ 55-13-064-QRY Created On: 01/20/16 Updated On:	Q			35	8N	8E	Dane	0-225-62-2016	1.0	1.4	0.8	7.6	33.0	2.563	2.627	2.493				
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																			
MEINHOLZ 55-13-064-QRY Created On: 04/01/19 Updated On:	Q			35	8N	8E	Dane	0-225-120-2019	0.8	1.5	2.8	9.3	35.2	2.565	2.636	2.748				
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																			

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse					
	P/Q	Qrt	Qrt	Sect	Town	Range	County					LA Wear (%)		Sp. Gravity		Absorp. %	
											100	500	OD	SSD	Crse	Fine	
DANE -- WI																	
MEINHOLZ 55-13-064-QRY Created On: 03/29/21 Updated On:	Q			35	8N	8E	Dane	0-225-160-2021	0.8	2.4	2.5	7.7	30.4	2.593	2.656	2.426	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
MEINHOLZ 55-13-064-QRY Created On: 01/04/22 Updated On:	Q			35	8N	8E	Dane	0-225-40-2022	1.3	4.5	5.1	9.4	31.3	2.578	2.643	2.515	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
MEINHOLZ 55-13-064-QRY Created On: 01/23/23 Updated On:	Q			35	8N	8E	Dane	0-225-132-2023	0.6	2.3	2.3	9.4	37.8	2.533	2.602	2.715	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
MEINHOLZ 55-13-064-QRY Created On: 01/02/24 Updated On:	Q			35	8N	8E	Dane	0-225-72-2024	0.8	1.7	1.3	7.2	30.4	2.540	2.619	3.106	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
MILE ROAD 55-13-007-QRY Created On: 03/07/16 Updated On:	Q	NE	NE	13	9N	10E	Dane	0-225-97-2016	1.1	2.6	8.9	6.5	29.4	2.640	2.693	2.030	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
MILE ROAD 55-13-007-QRY Created On: 01/04/19 Updated On:	Q	NE	NE	13	9N	10E	Dane	0-225-9-2019	1.7	7.0	7.4	10.1	28.7	2.536	2.616	3.134	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
MILE ROAD 55-13-007-QRY Created On: 01/02/24 Updated On:	Q	NE	NE	13	9N	10E	Dane	0-225-42-2024	0.7	14.1	12.6	9.8	43.1	2.545	2.623	3.066	
	Approved Use : Base Aggregate																

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
DANE -- WI																		
NORWAY GROVE 55-13-068-PIT Created On: 10/27/22 Updated On:	P	NW	SW	14	9N	9E	Dane	0-225-260-2022	6.8	0.0	3.8	8.4	32.9	2.656	2.698	1.587		
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																	
OAK PARK 55-13-069-QRY Created On: 03/28/14 Updated On:	Q	NE	SW	29	7N	12E	Dane	0-225-105-2014		15.7	12.7	9.4	31.9	2.639	2.707	2.582		
	Approved Use : Base Aggregate																	
OAK PARK 55-13-069-QRY Created On: 01/02/24 Updated On:	Q	NE	SW	29	7N	12E	Dane	0-225-89-2024	0.1	16.0	8.1	6.6	28.8	2.578	2.656	3.038		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
OREGON 55-13-112-PIT Created On: 01/05/17 Updated On:	P	NW	SE	36	5N	9E	Dane	0-225-50-2017	2.5	4.1	1.4	11.2	39.0	2.561	2.630	2.668		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
OREGON 55-13-112-PIT Created On: 01/04/22 Updated On:	P	NW	SE	36	5N	9E	Dane	0-225-59-2022	5.2	5.2	2.9	7.0	30.4	2.591	2.645	2.068		
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																	
RIGGENBERG 55-13-016-QRY Created On: 10/03/22 Updated On:	Q		NW	23	6N	7E	Dane	0-225-256-2022	0.5	11.6	4.4	7.1	32.4	2.653	2.708	2.068		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
*RIPP 55-13-076-QRY Created On: 03/19/15 Updated On:	Q	NW	NW	16	9N	9E	Dane	0-225-99-2015	2.8	3.7	3.2	10.3	36.5	2.555	2.629	2.921		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
DANE -- WI																		
*RIPP 55-13-076-QRY Created On: 01/03/18 Updated On:	Q	NW	NW	16	9N	9E	Dane	0-225-23-2018	2.8	2.3	3.1	7.9	31.9	2.575	2.647	2.813		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
*RIPP 55-13-076-QRY Created On: 01/05/21 Updated On:	Q	NW	NW	16	9N	9E	Dane	0-225-98-2021	2.7	3.4	3.7	9.3	36.5	2.543	2.609	2.630		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
ROSENBAUM 55-13-078-PIT Created On: 02/17/16 Updated On:	P	SW	NE	18	5N	11E	Dane	0-225-91-2016	7.4	0.0	5.0	8.3	34.0	2.600	2.658	2.249		
	Approved Use : HMA<E-3, HMA>=E-3, Base Aggregate																	
ROSENBAUM 55-13-078-PIT Created On: 06/01/22 Updated On:	P	SW	NE	18	5N	11E	Dane	0-225-211-2022	0.3	4.9	6.6	10.0	34.0	2.607	2.661	2.064		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
SCHADLER 55-13-081-PIT Created On: 01/03/18 Updated On:	P	NE	SE	10	8N	6E	Dane	0-225-26-2018	2.9	3.7	3.1	8.8	34.0	2.444	2.512	2.786		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
SCHADLER 55-13-081-PIT Created On: 01/04/23 Updated On:	P	NE	SE	10	8N	6E	Dane	0-225-97-2023	6.9	0.0	3.3	8.8	34.0	2.580	2.629	1.886		
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																	
SCHOEPP 55-13-082-QRY Created On: 03/30/18 Updated On:	Q		NE	9	7N	7E	Dane	0-225-156-2018	1.3	3.5	2.0	9.9	36.8	2.595	2.654	2.262		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Coarse Sp. Gravity		Coarse Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
DANE -- WI																		
SCHOEPP 55-13-082-QRY Created On: 06/24/19 Updated On:	Q		NE	9	7N	7E	Dane	0-225-225-2019	0.3	2.2	1.8	8.4	35.7	2.592	2.652	2.289		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
SCHOEPP 55-13-082-QRY Created On: 03/21/23 Updated On:	Q		NE	9	7N	7E	Dane	0-225-170-2023	0.3	1.9	3.9	10.2	41.9	2.610	2.664	2.034		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
SCHUETZ 55-13-083-QRY Created On: 08/01/14 Updated On:	Q	SE	SW	26	6N	10E	Dane	0-225-239-2014	3.6	0.3	2.4	7.0	31.6	2.636	2.684	1.816		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
SCHUETZ 55-13-083-QRY Created On: 04/11/18 Updated On:	Q	SE	SW	26	6N	10E	Dane	0-225-164-2018	4.6	3.8	7.5	10.4	39.4	2.554	2.620	2.605		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
SCHUETZ 55-13-083-QRY Created On: 01/03/23 Updated On:	Q	SE	SW	26	6N	10E	Dane	0-225-1-2023	1.1	1.6	1.9	5.5	27.4	2.651	2.692	1.521		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
SPIILDE 55-13-085-PIT Created On: 08/11/15 Updated On:	P		N	17	6N	11E	Dane	0-225-227-2015		7.8	7.4	8.5	34.4	2.631	2.689	2.211		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
SPIILDE 55-13-085-PIT Created On: 01/04/21 Updated On:	P		N	17	6N	11E	Dane	0-225-2-2021	9.4	0.0	12.7	10.7	39.0	2.584	2.647	2.438		
	Approved Use : Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse						
	P/Q	Qrt	Qrt	Sect	Town	Range	County	LA Wear (%) 100 500					Sp. Gravity OD SSD		Absorp. % Crse Fine				
DANE -- WI																			
*STOUGHTON 55-13-001-PIT Created On: 05/02/14 Updated On:	P	E	NW	10	5N	11E	Dane	0-225-158-2014		0.0	5.6	8.7	37.1	2.634	2.688	2.038			
Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																			
*STOUGHTON 55-13-001-PIT Created On: 01/04/19 Updated On:	P	E	NW	10	5N	11E	Dane	0-225-10-2019	2.0	9.3	0.9	6.4	30.8	2.664	2.710	1.718			
Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																			
TNT 55-13-094-QRY Created On: 01/30/15 Updated On:	Q		SW	14	6N	12E	Dane	0-225-80-2015		15.5	9.5	8.1	34.5	2.603	2.679	2.917			
Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																			
TNT 55-13-094-QRY Created On: 03/22/17 Updated On:	Q		SW	14	6N	12E	Dane	0-225-87-2017	1.6	31.6	19.1	10.5	38.3	2.557	2.644	3.416			
Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																			
TNT 55-13-094-QRY Created On: 04/12/17 Updated On:	Q		SW	14	6N	12E	Dane	0-225-122-2017		13.2	8.8	8.0	34.9	2.616	2.687	2.679			
Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																			
TNT 55-13-094-QRY Created On: 04/12/17 Updated On:	Q		SW	14	6N	12E	Dane	0-225-124-2017	0.5	12.1	6.9	6.5	29.1	2.630	2.692	2.387			
Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																			
TNT 55-13-094-QRY Created On: 04/12/17 Updated On:	Q		SW	14	6N	12E	Dane	0-225-125-2017	0.3	10.1	9.5	6.1	28.3	2.630	2.691	2.312			
Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																			

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
DANE -- WI																		
TNT 55-13-094-QRY Created On: 02/12/20 Updated On:	Q		SW	14	6N	12E	Dane	0-225-110-2020	0.4	29.8	15.7	7.3	32.8	2.619	2.683	2.461		
TNT 55-13-094-QRY Created On: 04/01/20 Updated On:	Q		SW	14	6N	12E	Dane	0-225-136-2020	0.2	22.0	12.7	6.7	30.8					
TNT 55-13-094-QRY Created On: 08/10/20 Updated On:	Q		SW	14	6N	12E	Dane	0-225-231-2020 Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate		17.6	6.7	5.3	26.8	2.662	2.713	1.888		
TNT 55-13-094-QRY Created On: 04/26/21 Updated On:	Q		SW	14	6N	12E	Dane	0-225-189-2021 Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate	0.1	16.8	5.8	5.7	27.6	2.622	2.684	2.377		
TNT 55-13-094-QRY Created On: 01/04/22 Updated On:	Q		SW	14	6N	12E	Dane	0-225-79-2022 Approved Use : Base Aggregate	0.2	14.2	10.4	5.9	29.5	2.651	2.706	2.058		
VIENNA 55-13-099-QRY Created On: 01/05/15 Updated On:	Q	NE	SW	34	9N	9E	Dane	0-225-7-2015 Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate	0.7	0.7	2.0	6.8	30.1	2.610	2.670	2.310		
VIENNA 55-13-099-QRY Created On: 01/03/18 Updated On:	Q	NE	SW	34	9N	9E	Dane	0-225-21-2018 Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate	2.1	1.0	3.4	8.3	35.4	2.539	2.619	3.158		

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse		Absorp. %				
	P/Q	Qrt	Qrt	Sect	Town	Range	County	LA Wear (%) 100 500					Sp. Gravity OD SSD	Crse	Fine				
DANE -- WI																			
VIENNA 55-13-099-QRY Created On: 09/17/20 Updated On:	Q	NE	SW	34	9N	9E	Dane	0-225-241-2020	2.0	2.4	3.7	7.8	31.3	2.614	2.667	2.024			
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
VIENNA 55-13-099-QRY Created On: 01/03/23 Updated On:	Q	NE	SW	34	9N	9E	Dane	0-225-3-2023	0.6	2.4	8.8	7.2	32.8	2.607	2.662	2.099			
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
VOLENBERG 55-13-100-PIT Created On: 01/05/16 Updated On:	P		NW	19	6N	12E	Dane	0-225-17-2016	6.9	0.0	6.5	6.6	34.2	2.618	2.678	2.294			
	Approved Use : HMA<E-3, HMA>=E-3, Base Aggregate																		
VOLENBERG 55-13-100-PIT Created On: 01/04/21 Updated On:	P		NW	19	6N	12E	Dane	0-225-3-2021	4.0	0.0	8.0	8.4	34.5	2.640	2.693	1.982			
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
*VOLENBERG QUARRY 55-13-101-QRY Created On: 01/05/16 Updated On:	Q		NW	19	6N	12E	Dane	0-225-16-2016		9.5	12.9	5.5	25.9	2.668	2.715	1.768			
	Approved Use : Base Aggregate																		
*VOLENBERG QUARRY 55-13-101-QRY Created On: 04/19/19 Updated On:	Q		NW	19	6N	12E	Dane	0-225-153-2019	0.8	16.8	14.6	6.2	28.4	2.649	2.701	1.994			
	Approved Use : Base Aggregate																		
WESTRES 55-13-066-QRY Created On: 07/03/14 Updated On:	Q	SW	NE	2	7N	6E	Dane	0-225-206-2014	1.0	6.0	4.0	11.3	38.3	2.556	2.631	2.931			
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																		

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse				
	P/Q	Qrt	Qrt	Sect	Town	Range	County					LA Wear (%)		Sp. Gravity		Absorp. %
											100	500	OD	SSD	Crse	Fine
DANE -- WI																
WESTRES 55-13-066-QRY Created On: 04/06/17 Updated On:	Q	SW	NE	2	7N	6E	Dane	0-225-110-2017	0.7	1.9	2.2	11.0	37.3	2.613	2.672	2.268
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate															
WESTRES 55-13-066-QRY Created On: 03/29/21 Updated On:	Q	SW	NE	2	7N	6E	Dane	0-225-161-2021	0.3	7.5	3.2	9.1	33.6	2.573	2.646	2.848
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate															
WESTRES 55-13-066-QRY Created On: 01/02/24 Updated On:	Q	SW	NE	2	7N	6E	Dane	0-225-73-2024	0.7	4.8	2.0	11.6	42.5	2.494	2.576	3.284
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate															
*WK 55-13-102-QRY Created On: 03/20/15 Updated On:	Q	SW	SW	8	7N	8E	Dane	0-225-101-2015	1.2	2.3	6.0	7.0	31.3	2.626	2.681	2.081
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate															
*WK 55-13-102-QRY Created On: 01/03/18 Updated On:	Q	SW	SW	8	7N	8E	Dane	0-225-22-2018	4.6	2.0	11.1	8.7	40.4	2.553	2.633	3.112
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate															
*WK 55-13-102-QRY Created On: 01/05/21 Updated On:	Q	SW	SW	8	7N	8E	Dane	0-225-93-2021	1.8	3.0	7.4	7.2	31.6	2.612	2.672	2.271
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate															
WRIGLY 55-13-114-QRY Created On: 06/02/17 Updated On:	Q		NW	29	6N	12E	Dane	0-225-201-2017		3.5	3.8	7.0	28.6			
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate															

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Coarse Sp. Gravity		Coarse Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
DANE -- WI																		
WRIGLY 55-13-114-QRY Created On: 06/07/18 Updated On:	Q		NW	29	6N	12E	Dane	0-225-220-2018	0.5	11.3	17.2	7.9	33.3	2.619	2.683	2.428		
	Approved Use : Base Aggregate																	
WRIGLY 55-13-114-QRY Created On: 01/04/22 Updated On:	Q		NW	29	6N	12E	Dane	0-225-55-2022	0.1	17.9	6.2	7.6	30.4	2.615	2.680	2.483		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
ZANDER 55-13-109-PIT Created On: 03/14/18 Updated On:	P	NW	SW	11	7N	7E	Dane	0-225-119-2018	10.1	5.3	16.3	16.4	46.2	2.542	2.621	3.113		
	Approved Use : Base Aggregate																	
ZANDER 55-13-109-PIT Created On: 01/07/19 Updated On:	P	NW	SW	11	7N	7E	Dane	0-225-46-2019	4.1	2.2	6.3	9.7	37.0	2.602	2.663	2.362		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
ZANDER 55-13-122-QRY Created On: 06/20/19 Updated On:	Q	NW	SW	11	7N	7E	Dane	0-225-222-2019	0.9	3.3	8.3	8.3	39.0	2.581	2.647	2.581		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
ZANDER 55-13-122-QRY Created On: 04/26/23 Updated On:	Q	NW	SW	11	7N	7E	Dane	0-225-208-2023	1.8	10.9	9.2	11.6	41.5	2.556	2.631	2.938		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
ZANDER 55-13-109-PIT Created On: 01/02/24 Updated On:	P	NW	SW	11	7N	7E	Dane	0-225-129-2024	3.0	0.0	7.8	8.5	34.7	2.619	2.672	2.043		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse					
	P/Q	Qrt	Qrt	Sect	Town	Range	County	LA Wear (%) 100 500					Sp. Gravity OD SSD	Absorp. % Crse Fine				
DODGE -- WI																		
BUCHDA 55-14-004-QRY Created On: 01/04/16 Updated On:	Q	NE	NW	5	12N	14E	Dodge	0-225-3-2016	0.5	2.2	1.4	6.8	27.7	2.745	2.779	1.209		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
BUCHDA 55-14-004-QRY Created On: 06/06/19 Updated On:	Q	NE	NW	5	12N	14E	Dodge	0-225-204-2019		2.1	1.0	7.6	29.5	2.752	2.779	0.973		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
BUCHDA 55-14-004-QRY Created On: 01/04/22 Updated On:	Q	NE	NW	5	12N	14E	Dodge	0-225-95-2022	0.0	2.4	2.5	8.0	27.1	2.738	2.772	1.252		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
CHRISTIAN - GADE 55-14-006-PIT Created On: 01/07/16 Updated On:	P	W	SW	33	12N	15E	Dodge	0-225-41-2016		11.7	2.6	5.4	25.5	2.743	2.779	1.332		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
CHRISTIAN - GADE 55-14-006-PIT Created On: 01/04/21 Updated On:	P	W	SW	33	12N	15E	Dodge	0-225-5-2021	0.0	14.4	2.5	5.7	25.9	2.728	2.772	1.598		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
FARMERSVILLE 55-14-007-QRY Created On: 04/18/22 Updated On:	Q	S	SW	30	13N	17E	Dodge	0-225-176-2022	0.0	0.8	1.5	9.1	37.5	2.690	2.725	1.322		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
*FRENS 55-14-038-QRY Created On: 04/05/21 Updated On:	Q		NW	3	13N	14E	Dodge	0-225-169-2021	0.6	3.0	2.9	5.9	25.8	2.770	2.795	0.906		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse					
	P/Q	Qrt	Qrt	Sect	Town	Range	County	LA Wear (%) 100 500					Sp. Gravity OD SSD		Absorp. % Crse Fine			
DODGE -- WI																		
HERMAN 55-14-011-QRY Created On: 04/24/14 Updated On:	Q	SW	NW	6	11N	17E	Dodge	0-225-149-2014	0.5	1.1	3.2	5.7	26.2	2.771	2.787	0.588		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
HERMAN 55-14-011-QRY Created On: 04/06/17 Updated On:	Q	SW	NW	6	11N	17E	Dodge	0-225-105-2017		1.1	1.3	6.9	29.6	2.733	2.764	1.114		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
HERMAN 55-14-011-QRY Created On: 06/04/20 Updated On:	Q	SW	NW	6	11N	17E	Dodge	0-225-187-2020		4.5	0.1	5.0	26.7	2.773	2.789	0.577		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
HERMAN 55-14-011-QRY Created On: 02/27/23 Updated On:	Q	SW	NW	6	11N	17E	Dodge	0-225-147-2023	0.4	6.2	3.1	10.4	33.0	2.734	2.764	1.085		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
HUSTISFORD 55-14-012-QRY Created On: 01/21/16 Updated On:	Q	SE	SW	33	10N	16E	Dodge	0-225-69-2016		4.4	5.3	5.1	24.4	2.669	2.718	1.859		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
HUSTISFORD 55-14-012-QRY Created On: 02/05/19 Updated On:	Q	SE	SW	33	10N	16E	Dodge	0-225-97-2019		3.7	1.2	5.5	25.9	2.697	2.737	1.487		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
HUSTISFORD 55-14-012-QRY Created On: 01/04/22 Updated On:	Q	SE	SW	33	10N	16E	Dodge	0-225-87-2022	0.0	3.5	1.2	5.5	28.1	2.680	2.723	1.620		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine		
DODGE -- WI																			
LINCK #22 55-14-019-QRY Created On: 01/29/15 Updated On:	Q	SW	SW	9	12N	14E	Dodge	0-225-79-2015		2.4	0.9	6.3	29.1	2.764	2.786	0.794			
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																		
LINCK #22 55-14-019-QRY Created On: 03/01/18 Updated On:	Q	SW	SW	9	12N	14E	Dodge	0-225-107-2018		0.3	3.8	2.2	6.9	28.9	2.743	2.777	1.239		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																		
LINCK #22 55-14-019-QRY Created On: 03/29/21 Updated On:	Q	SW	SW	9	12N	14E	Dodge	0-225-162-2021		0.0	10.4	0.5	6.8	27.2	2.768	2.794	0.938		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
LINCK #22 55-14-019-QRY Created On: 02/28/24 Updated On:	Q	SW	SW	9	12N	14E	Dodge	0-225-189-2024		0.0	5.0	0.3	5.3	24.0	2.778	2.799	0.762		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
MAYVILLE WHITELIME 55-14-023-QRY Created On: 05/02/14 Updated On:	Q			1	11N	16E	Dodge	0-225-159-2014		2.3	3.2	6.8	30.5	2.720	2.759	1.416			
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																		
MAYVILLE WHITELIME 55-14-023-QRY Created On: 08/08/17 Updated On:	Q			1	11N	16E	Dodge	0-225-248-2017		2.3	1.5	0.2	6.6	29.0	2.704	2.748	1.628		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
MAYVILLE WHITELIME 55-14-023-QRY Created On: 08/24/20 Updated On:	Q			1	11N	16E	Dodge	0-225-235-2020		1.8	3.3	0.2	6.8	30.1	2.725	2.764	1.419		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse					
	P/Q	Qrt	Qrt	Sect	Town	Range	County	LA Wear (%) 100 500					Sp. Gravity OD SSD		Absorp. % Crse Fine			
DODGE -- WI																		
MAYVILLE WHITELIME 55-14-023-QRY Created On: 02/27/23 Updated On:	Q		1	11N	16E	Dodge		0-225-151-2023	2.1	7.5	5.1	6.0	29.7	2.712	2.754	1.530		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MICHELS NASBRO 55-14-025-QRY Created On: 01/04/16 Updated On:	Q	W	SE	18	13N	17E	Dodge	0-225-1-2016		0.4	1.3	7.5	32.2	2.714	2.746	1.179		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
MICHELS NASBRO 55-14-025-QRY Created On: 01/04/19 Updated On:	Q	W	SE	18	13N	17E	Dodge	0-225-1-2019	0.1	0.9	1.4	9.1	35.7	2.710	2.744	1.269		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
MICHELS NASBRO 55-14-025-QRY Created On: 01/04/22 Updated On:	Q	W	SE	18	13N	17E	Dodge	0-225-2-2022	0.0	0.5	1.0	7.2	30.8	2.731	2.763	1.155		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MICHELS-WATERLOO 55-14-028-QRY Created On: 01/04/16 Updated On:	Q	NW	NW	34	9N	13E	Dodge	0-225-2-2016		0.4	0.5	4.1	21.8	2.655	2.667	0.461		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
MICHELS-WATERLOO 55-14-028-QRY Created On: 01/04/19 Updated On:	Q	NW	NW	34	9N	13E	Dodge	0-225-2-2019		0.8	0.3	4.1	22.0	2.651	2.667	0.604		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MICHELS-WATERLOO 55-14-028-QRY Created On: 01/04/22 Updated On:	Q	NW	NW	34	9N	13E	Dodge	0-225-1-2022	0.0	0.1	0.2	5.2	26.1	2.662	2.673	0.397		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse						
	P/Q	Qrt	Qrt	Sect	Town	Range	County	LA Wear (%) 100 500					Sp. Gravity OD SSD		Absorp. % Crse Fine				
DODGE -- WI																			
WARMKA 55-14-034-QRY Created On: 04/11/14 Updated On:	Q	NE	NW	9	12N	14E	Dodge	0-225-124-2014		1.2	2.4	5.6	25.1	2.764	2.788	0.894			
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																		
WARMKA 55-14-034-QRY Created On: 01/03/17 Updated On:	Q	NE	NW	9	12N	14E	Dodge	0-225-8-2017		4.0	2.4	5.8	25.1	2.763	2.788	0.904			
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																		
WARMKA 55-14-034-QRY Created On: 04/01/19 Updated On:	Q	NE	NW	9	12N	14E	Dodge	0-225-118-2019		4.6	2.5	5.2	24.3	2.757	2.785	1.017			
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																		
WARMKA 55-14-034-QRY Created On: 01/04/22 Updated On:	Q	NE	NW	9	12N	14E	Dodge	0-225-3-2022		0.0	1.8	1.5	5.1	24.5	2.750	2.780	1.070		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
WESTPHAL 55-14-035-QRY Created On: 01/03/18 Updated On:	Q	SE	SE	8	10N	14E	Dodge	0-225-20-2018		13.5	8.9	5.4	25.0	2.689	2.733	1.636			
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
WESTPHAL 55-14-035-QRY Created On: 05/17/21 Updated On:	Q	SE	SE	8	10N	14E	Dodge	0-225-209-2021		0.0	8.6	8.2	5.7	25.3	2.689	2.732	1.614		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
WESTPHAL 55-14-035-QRY Created On: 02/06/23 Updated On:	Q	SE	SE	8	10N	14E	Dodge	0-225-141-2023		0.0	17.0	10.1	4.8	30.4	2.703	2.743	1.501		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse				
	P/Q	Qrt	Qrt	Sect	Town	Range	County	LA Wear (%) 100 500					Sp. Gravity OD SSD	Absorp. % Crse Fine			
DOOR -- WI BAILEYS HARBOR 55-15-001-QRY Created On: 01/21/16 Updated On:	Q	SW	NW	17	30N	28E	Door	0-225-73-2016	4.5	0.0	4.4	7.7	33.0	2.631	2.687	2.132	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
BAILEYS HARBOR 55-15-001-QRY Created On: 04/13/17 Updated On:	Q	SW	NW	17	30N	28E	Door	0-225-130-2017	1.3	0.0	2.9	7.6	32.6	2.637	2.692	2.074	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
BAILEYS HARBOR 55-15-001-QRY Created On: 01/02/20 Updated On:	Q	SW	NW	17	30N	28E	Door	0-225-6-2020		0.0	1.4	6.6	30.3	2.548	2.605	2.233	
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																
BAILEYS HARBOR 55-15-001-QRY Created On: 01/03/23 Updated On:	Q	SW	NW	17	30N	28E	Door	0-225-38-2023	0.2	3.9	1.3	6.0	26.9	2.742	2.773	1.137	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
BIWERS 55-15-002-QRY Created On: 04/27/15 Updated On:	Q	NW	SE	10	30N	27E	Door	0-225-139-2015		0.0	1.0	6.4	24.1	2.760	2.783	0.829	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
BIWERS 55-15-002-QRY Created On: 02/15/18 Updated On:	Q	NW	SE	10	30N	27E	Door	0-225-102-2018	0.1	1.0	1.0	6.3	25.9	2.759	2.783	0.876	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
BIWERS 55-15-002-QRY Created On: 01/06/21 Updated On:	Q	NW	SE	10	30N	27E	Door	0-225-113-2021	0.0	0.5	0.7	5.5	23.3	2.760	2.784	0.886	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse							
	P/Q	Qrt	Qrt	Sect	Town	Range	County	LA Wear (%) 100					500	Sp. Gravity OD SSD		Absorp. % Crse Fine				
DOOR -- WI																				
BIWERS 55-15-002-QRY Created On: 01/29/24 Updated On:	Q	NW	SE	10	30N	27E	Door	0-225-157-2024	0.1	0.8	0.4	5.4	22.7	2.760	2.783	0.837				
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																			
CAREW - BRUSSELS 55-15-004-QRY Created On: 01/16/15 Updated On:	Q	NW	NW	21	26N	24E	Door	0-225-69-2015		0.0	3.3	7.2	27.5	2.749	2.778	1.052				
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																			
CAREW - BRUSSELS 55-15-004-QRY Created On: 03/01/18 Updated On:	Q	NW	NW	21	26N	24E	Door	0-225-111-2018		0.0	5.2	6.0	26.6	2.773	2.793	0.717				
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																			
CAREW - BRUSSELS 55-15-004-QRY Created On: 01/14/21 Updated On:	Q	NW	NW	21	26N	24E	Door	0-225-120-2021	0.0	0.0	0.9	5.4	24.8	2.780	2.798	0.655				
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																			
CAREW - BRUSSELS 55-15-004-QRY Created On: 02/28/24 Updated On:	Q	NW	NW	21	26N	24E	Door	0-225-177-2024	0.0	0.0	1.7	6.4	27.4	2.772	2.790	0.650				
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																			
CLOVERLEAF QUARRY 55-15-032-QRY Created On: 03/13/24 Updated On:	Q	NW	SE	19	27N	25E	Door	0-225-202-2024	0.0	0.0	0.7	6.5	30.6	2.754	2.775	0.759				
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																			
HIGH ROAD QUARRY 55-15-015-QRY Created On: 01/03/23 Updated On:	Q		NW	4	26N	24E	Door	0-225-42-2023	0.0	2.3	5.4	6.7	29.6	2.705	2.747	1.553				
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																			

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Coarse Sp. Gravity		Coarse Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
DOOR -- WI																		
ISLAND STONE 55-15-030-QRY Created On: 06/28/22 Updated On:	Q	SW	SW	32	34N	30E	Door	0-225-237-2022	1.4	0.0	7.7	5.6	26.8	2.658	2.705	1.777		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
*JADIN #2 55-15-009-QRY Created On: 06/27/18 Updated On:	Q	SW	NE	33	26N	24E	Door	0-225-242-2018		0.0	1.4	7.2	30.8	2.740	2.769	1.054		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
*JADIN #2 55-15-009-QRY Created On: 01/14/21 Updated On:	Q	SW	NE	33	26N	24E	Door	0-225-122-2021	0.0	0.0	0.3	6.9	31.1	2.709	2.742	1.219		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
KISSER 55-15-013-QRY Created On: 01/04/16 Updated On:	Q	NW	NW	20	27N	25E	Door	0-225-9-2016		3.0	2.5	6.4	26.3	2.762	2.788	0.957		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
KISSER 55-15-013-QRY Created On: 01/08/19 Updated On:	Q	NW	NW	20	27N	25E	Door	0-225-73-2019		0.0	3.0	7.8	32.2	2.790	2.817	0.997		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
KISSER 55-15-013-QRY Created On: 01/10/22 Updated On:	Q	NW	NW	20	27N	25E	Door	0-225-97-2022	0.0	1.7	1.7	6.5	29.2	2.750	2.778	0.995		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MATHEY 55-15-014-QRY Created On: 07/08/15 Updated On:	Q	E	SE	22	28N	26E	Door	0-225-208-2015	0.1	0.0	0.6	5.7	25.8	2.793	2.811	0.616		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %			
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine		
DOOR -- WI																			
MATHEY 55-15-014-QRY Created On: 01/04/18 Updated On:	Q	E	SE	22	28N	26E	Door	0-225-84-2018	1.0	3.3	1.7	8.0	30.8	2.748	2.780	1.144			
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
MATHEY 55-15-014-QRY Created On: 01/05/21 Updated On:	Q	E	SE	22	28N	26E	Door	0-225-107-2021	0.0	1.5	0.7	5.7	24.7	2.778	2.802	0.831			
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
MATHEY 55-15-014-QRY Created On: 01/02/24 Updated On:	Q	E	SE	22	28N	26E	Door	0-225-48-2024	0.1	0.0	0.6	0.9	29.5	2.778	2.797	0.705			
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
MURRAY 55-15-017-PIT Created On: 07/30/15 Updated On:	P	NE	SE	26	26N	23E	Door	0-225-220-2015	0.1	0.0	9.3	8.2	36.1	2.638	2.697	2.256			
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																		
MURRAY 55-15-017-PIT Created On: 08/25/20 Updated On:	P	NE	SE	26	26N	23E	Door	0-225-236-2020	1.5	0.0	3.4	6.5	30.2	2.693	2.736	1.598			
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
PETERS-BRUSSELS 55-15-003-PIT Created On: 04/14/16 Updated On:	P	SE	NW	26	26N	23E	Door	0-225-148-2016	0.4	0.0	9.4	8.0	25.5	2.691	2.736	1.676			
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																		
PETERS-BRUSSELS 55-15-003-PIT Created On: 05/30/17 Updated On:	P	SE	NW	26	26N	23E	Door	0-225-195-2017	0.4	0.0	6.3	8.2	33.5	2.714	2.763	1.795			
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																		

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse					
	P/Q	Qrt	Qrt	Sect	Town	Range	County	LA Wear (%) 100 500					Sp. Gravity OD SSD	Absorp. % Crse Fine				
DOOR -- WI PETERS-BRUSSELS 55-15-003-PIT Created On: 04/20/23 Updated On:	P	SE	NW	26	26N	23E	Door	0-225-203-2023	0.2	0.0	6.9	6.1	28.5	2.719	2.757	1.393		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
SITTE 55-15-028-QRY Created On: 03/22/19 Updated On:	Q	S	NE	2	31N	28E	Door	0-225-113-2019	5.5	0.0	5.0	6.1	27.5	2.618	2.674	2.165		
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																	
SITTE 55-15-028-QRY Created On: 03/07/22 Updated On:	Q	S	NE	2	31N	28E	Door	0-225-138-2022	2.1	0.0	12.0	6.4	29.4	2.620	2.674	2.073		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
STURGEON BAY - MM 55-15-022-QRY Created On: 01/06/14 Updated On:	Q	SE	NW	21	27N	25E	Door	0-225-6-2014		0.0	0.6	6.2	26.2	2.779	2.797	0.630		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
STURGEON BAY - MM 55-15-022-QRY Created On: 01/05/17 Updated On:	Q	SE	NW	21	27N	25E	Door	0-225-21-2017		0.0	1.9	7.8	27.6	2.769	2.789	0.736		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
STURGEON BAY - MM 55-15-022-QRY Created On: 01/02/20 Updated On:	Q	SE	NW	21	27N	25E	Door	0-225-7-2020	0.0	0.0	0.5	5.4	25.4	2.779	2.796	0.611		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
STURGEON BAY - MM 55-15-022-QRY Created On: 01/03/23 Updated On:	Q	SE	NW	21	27N	25E	Door	0-225-46-2023		7.2	1.8	5.7	24.0	2.773	2.792	0.688		
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse				
	P/Q	Qrt	Qrt	Sect	Town	Range	County					LA Wear (%)		Sp. Gravity		Absorp. %
											100	500	OD	SSD	Crse	Fine
DOOR -- WI																
TAGGE 55-15-023-PIT Created On: 01/05/17 Updated On:	P		NE	31	27N	26E	Door	0-225-22-2017	0.3	0.0	0.3	7.2	30.2	2.726	2.763	1.373
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate															
TAGGE 55-15-023-PIT Created On: 01/04/22 Updated On:	P		NE	31	27N	26E	Door	0-225-15-2022	0.1	2.2	1.8	6.4	27.5	2.733	2.764	1.151
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate															
UNION 55-15-024-PIT Created On: 07/08/15 Updated On:	P	SW	NW	36	26N	23E	Door	0-225-209-2015	0.1	0.0	7.1	6.0	25.2	2.710	2.748	1.378
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate															
UNION 55-15-024-PIT Created On: 06/13/22 Updated On:	P	SW	NW	36	26N	23E	Door	0-225-221-2022	0.2	8.9	2.1	5.5	26.8	2.704	2.741	1.368
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate															
DOUGLAS -- WI																
COLBY 55-16-005-QRY Created On: 02/05/14 Updated On:	Q	NE	SW	25	48N	11W	Douglas	0-225-81-2014		0.0	15.2	5.5	20.9	2.787	2.818	1.120
	Approved Use : Base Aggregate															
COLBY 55-16-005-QRY Created On: 02/13/17 Updated On:	Q	NE	SW	25	48N	11W	Douglas	0-225-66-2017		0.0	14.4	4.5	20.3	2.798	2.834	1.297
	Approved Use : Base Aggregate															
COLBY 55-16-005-QRY Created On: 01/08/20 Updated On:	Q	NE	SW	25	48N	11W	Douglas	0-225-59-2020	0.4	0.0	15.5	5.4	21.6	2.818	2.857	1.368
	Approved Use : Base Aggregate															

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse					
	P/Q	Qrt	Qrt	Sect	Town	Range	County	LA Wear (%)					Sp. Gravity		Absorp. %			
												100	500	OD	SSD	Crse	Fine	
DOUGLAS -- WI																		
COLBY 55-16-005-QRY Created On: 01/04/23 Updated On:	Q	NE	SW	25	48N	11W	Douglas	0-225-90-2023	0.0	7.7	13.7	4.7	19.0	2.801	2.841	1.421		
	Approved Use : Base Aggregate																	
HOME RUN 55-16-008-QRY Created On: 05/19/17 Updated On:	Q	NE	SE	21	48N	10W	Douglas	0-225-193-2017		18.3	7.3	4.0	32.4	2.753	2.789	1.311		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
HOME RUN 55-16-008-QRY Created On: 04/16/20 Updated On:	Q	NE	SE	21	48N	10W	Douglas	0-225-153-2020		0.0	2.4	2.5	10.8	2.852	2.886	1.191		
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																	
HOME RUN 55-16-008-QRY Created On: 01/04/23 Updated On:	Q	NE	SE	21	48N	10W	Douglas	0-225-88-2023	0.0	0.0	2.1	2.7	13.4	2.837	2.869	1.105		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
KIMMES 55-16-011-QRY Created On: 02/06/14 Updated On:	Q	SW	NW	14	47N	14W	Douglas	0-225-83-2014		0.0	7.1	4.1	16.3	2.703	2.734	1.161		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
KIMMES 55-16-011-QRY Created On: 02/13/17 Updated On:	Q	SW	NW	14	47N	14W	Douglas	0-225-67-2017		0.0	10.0	4.9	20.6	2.692	2.731	1.468		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
KIMMES 55-16-011-QRY Created On: 01/08/20 Updated On:	Q	SW	NW	14	47N	14W	Douglas	0-225-56-2020	0.0	0.0	4.2	2.8	13.6	2.756	2.786	1.086		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Coarse Sp. Gravity		Coarse Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
DOUGLAS -- WI																		
KIMMES 55-16-011-QRY Created On: 01/03/23 Updated On:	Q	SW	NW	14	47N	14W	Douglas	0-225-56-2023	0.0	4.8	1.6	3.3	13.3	2.771	2.800	1.051		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MIKKOLA QUARRY 55-16-014-QRY Created On: 08/15/17 Updated On:	Q	NE	NE	35	48N	11W	Douglas	0-225-254-2017		0.0	0.9	3.1	13.9	2.620	2.643	0.891		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MIKKOLA QUARRY 55-16-014-QRY Created On: 01/06/20 Updated On:	Q	NE	NE	35	48N	11W	Douglas	0-225-30-2020	0.1	0.0	4.9	3.1	13.9	2.582	2.615	1.247		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MIKKOLA QUARRY 55-16-014-QRY Created On: 01/04/23 Updated On:	Q	NE	NE	35	48N	11W	Douglas	0-225-89-2023	0.6	2.4	2.9	3.4	15.0	2.645	2.682	1.392		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MILESTONE-BUCKLEY 55-16-002-QRY Created On: 02/05/14 Updated On:	Q	NW	NW	32	48N	12W	Douglas	0-225-80-2014		0.0	7.2	5.0	22.5	2.783	2.813	1.084		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
MILESTONE-BUCKLEY 55-16-002-QRY Created On: 02/13/17 Updated On:	Q	NW	NW	32	48N	12W	Douglas	0-225-69-2017		0.0	9.5	4.8	21.2	2.880	2.910	1.027		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
MILESTONE-BUCKLEY 55-16-002-QRY Created On: 08/15/17 Updated On:	Q	NW	NW	32	48N	12W	Douglas	0-225-253-2017	0.1	0.0	6.7	5.6	22.4	2.870	2.887	0.584		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse					
	P/Q	Qrt	Qrt	Sect	Town	Range	County	LA Wear (%)					Sp. Gravity		Absorp. %			
								100					500	OD	SSD	Crse	Fine	
DOUGLAS -- WI																		
MILESTONE-BUCKLEY 55-16-002-QRY Created On: 01/08/20 Updated On:	Q	NW	NW	32	48N	12W	Douglas	0-225-58-2020	0.0	0.0	5.6	5.3	22.3	2.816	2.841	0.882		
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
MILESTONE-BUCKLEY 55-16-002-QRY Created On: 01/03/23 Updated On:	Q	NW	NW	32	48N	12W	Douglas	0-225-59-2023	0.0	1.5	2.3	3.5	17.3	2.817	2.845	1.009		
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
*OLSON 55-16-017-QRY Created On: 06/13/16 Updated On:	Q	NW	NW	24	48N	10W	Douglas	0-225-198-2016		1.7	0.2	2.4	11.9	2.853	2.885	1.121		
Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																		
*OLSON 55-16-017-QRY Created On: 06/03/21 Updated On:	Q	NW	NW	24	48N	10W	Douglas	0-225-218-2021	0.7	0.0	4.0	4.4	18.7	2.844	2.872	1.016		
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
SOLON SPRINGS 55-16-024-QRY Created On: 05/09/16 Updated On:	Q	NE	NW	18	45N	11W	Douglas	0-225-167-2016		0.0	4.6	3.8	16.7	2.807	2.839	1.155		
Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																		
SOLON SPRINGS 55-16-024-QRY Created On: 01/07/19 Updated On:	Q	NE	NW	18	45N	11W	Douglas	0-225-60-2019	0.3	0.0	8.8	4.6	19.4	2.780	2.824	1.552		
Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																		
SOLON SPRINGS 55-16-024-QRY Created On: 07/07/22 Updated On:	Q	NE	NW	18	45N	11W	Douglas	0-225-245-2022	1.4	0.0	4.7	4.8	19.0	2.778	2.807	1.041		
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse						
	P/Q	Qrt	Qrt	Sect	Town	Range	County	LA Wear (%) 100 500					Sp. Gravity OD SSD	Absorp. % Crse Fine					
DOUGLAS -- WI																			
STUPAK 55-16-025-QRY Created On: 05/08/15 Updated On:	Q	NW	NW	29	47N	14W	Douglas	0-225-154-2015		0.0	3.2	2.9	15.0	2.791	2.810	0.680			
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																		
STUPAK 55-16-025-QRY Created On: 01/03/18 Updated On:	Q	NW	NW	29	47N	14W	Douglas	0-225-17-2018		0.0	9.1	3.5	15.5	2.686	2.719	1.235			
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																		
STUPAK 55-16-025-QRY Created On: 01/05/21 Updated On:	Q	NW	NW	29	47N	14W	Douglas	0-225-68-2021		0.0	16.5	10.9	3.5	15.2	2.715	2.749	1.259		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
STUPAK 55-16-025-QRY Created On: 01/02/24 Updated On:	Q	NW	NW	29	47N	14W	Douglas	0-225-92-2024		0.0	0.0	10.6	3.6	17.2	2.633	2.684	1.930		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
DUNN -- WI																			
GATES #238 55-17-011-QRY Created On: 01/08/15 Updated On:	Q	S	NW	17	28N	14W	Dunn	0-225-36-2015		0.7	0.0	4.5	7.3	32.3	2.629	2.688	2.238		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																		
GATES #238 55-17-011-QRY Created On: 07/17/15 Updated On:	Q	S	NW	17	28N	14W	Dunn	0-225-215-2015		0.0	1.9	7.5	31.3	2.608	2.669	2.323			
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																		
GATES #238 55-17-011-QRY Created On: 04/21/17 Updated On:	Q	S	NW	17	28N	14W	Dunn	0-225-142-2017		1.3	0.0	2.0	7.7	31.1	2.610	2.672	2.371		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Coarse Sp. Gravity		Coarse Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
DUNN -- WI																		
GATES #238 55-17-011-QRY Created On: 08/09/19 Updated On:	Q	S	NW	17	28N	14W	Dunn	0-225-259-2019	2.9	0.0	5.3	11.3	39.7	2.558	2.641	3.218		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
GATES #238 55-17-011-QRY Created On: 04/05/22 Updated On:	Q	S	NW	17	28N	14W	Dunn	0-225-157-2022	6.5	1.8	10.6	11.6	43.4	2.537	2.614	3.053		
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																	
HAFELDER 55-17-013-QRY Created On: 06/08/15 Updated On:	Q	NE	NE	23	28N	14W	Dunn	0-225-189-2015		0.0	4.4	7.5	39.1	2.571	2.641	2.714		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
HAFELDER 55-17-013-QRY Created On: 01/03/18 Updated On:	Q	NE	NE	23	28N	14W	Dunn	0-225-32-2018	2.0	0.0	6.3	10.5	36.9	2.531	2.616	3.356		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
HAFELDER 55-17-013-QRY Created On: 01/05/21 Updated On:	Q	NE	NE	23	28N	14W	Dunn	0-225-75-2021	1.4	0.0	0.8	9.7	35.3	2.559	2.641	3.186		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
HAFELDER 55-17-013-QRY Created On: 01/02/24 Updated On:	Q	NE	NE	23	28N	14W	Dunn	0-225-75-2024	1.7	6.7	6.7	12.2	43.3	2.548	2.629	3.169		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
HUGHES 55-17-015-QRY Created On: 02/05/14 Updated On:	Q		SW	15	28N	14W	Dunn	0-225-78-2014		0.0	3.0	9.3	34.6	2.582	2.655	2.826		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse				
	P/Q	Qrt	Qrt	Sect	Town	Range	County					LA Wear (%)		Sp. Gravity		Absorp. %
											100	500	OD	SSD	Crse	Fine
DUNN -- WI																
HUGHES 55-17-015-QRY Created On: 01/05/17 Updated On:	Q		SW	15	28N	14W	Dunn	0-225-47-2017		0.0	5.4	9.0	35.8	2.594	2.661	2.585
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate															
HUGHES 55-17-015-QRY Created On: 08/15/19 Updated On:	Q		SW	15	28N	14W	Dunn	0-225-261-2019	0.9	0.0	5.5	7.9	33.5	2.601	2.668	2.584
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate															
HUGHES 55-17-015-QRY Created On: 04/05/22 Updated On:	Q		SW	15	28N	14W	Dunn	0-225-161-2022	2.3	1.4	5.0	11.4	41.0	2.586	2.650	2.464
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate															
EAU CLAIRE -- WI																
AMERICAN MATERIALS #31 55-18-003-PIT Created On: 01/05/17 Updated On:	P	N	NE	2	26N	10W	Eau Claire	0-225-32-2017		0.0	2.9	4.4	20.9	2.635	2.666	1.171
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate															
AMERICAN MATERIALS #31 55-18-003-PIT Created On: 01/04/21 Updated On:	P	N	NE	2	26N	10W	Eau Claire	0-225-36-2021	1.1	5.4	5.7	4.1	20.2	2.638	2.668	1.166
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate															
MILESTONE RIEKEMANN PIT #222 55-18-011-PIT Created On: 01/03/18 Updated On:	P	SE	SW	4	26N	10W	Eau Claire	0-225-41-2018	1.7	0.0	2.0	3.8	19.4	2.641	2.670	1.078
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate															
MILESTONE RIEKEMANN PIT #222 55-18-011-PIT Created On: 01/03/23 Updated On:	P	SE	SW	4	26N	10W	Eau Claire	0-225-52-2023	0.7	4.4	3.1	4.2	20.9	2.632	2.665	1.261
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate															

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Coarse Sp. Gravity		Coarse Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
FLORENCE -- WI																		
DELARULLE 55-19-003-PIT Created On: 06/19/14 Updated On:	P	SE	SW	12	39N	17E	Florence	0-225-200-2014			2.3	8.0	28.2					
Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																		
DELARULLE 55-19-003-PIT Created On: 01/04/19 Updated On:	P	SE	SW	12	39N	17E	Florence	0-225-12-2019	0.0	0.0	3.2	6.2	29.1	2.619	2.664	1.744		
Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																		
DELARULLE 55-19-003-PIT Created On: 01/02/24 Updated On:	P	SE	SW	12	39N	17E	Florence	0-225-12-2024	1.1	0.0	0.5	5.9	26.0	2.641	2.682	1.551		
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
SANICKI 55-19-012-PIT Created On: 05/13/21 Updated On:	P		SE	31	38N	17E	Florence	0-225-207-2021	0.2	0.4	0.7	4.9	21.1	2.725	2.747	0.805		
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
SPREAD EAGLE 55-19-009-QRY Created On: 01/12/16 Updated On:	Q	NW	SE	11	39N	19E	Florence	0-225-50-2016		0.0	0.3	2.9	12.4	2.895	2.903	0.294		
Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																		
SPREAD EAGLE 55-19-009-QRY Created On: 01/04/19 Updated On:	Q	NW	SE	11	39N	19E	Florence	0-225-11-2019		0.2	0.1	1.9	9.1	2.951	2.964	0.429		
Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																		
SPREAD EAGLE 55-19-009-QRY Created On: 01/04/22 Updated On:	Q	NW	SE	11	39N	19E	Florence	0-225-24-2022	0.0	1.0	0.2	6.1	12.4	2.973	2.982	0.291		
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
FOND DU LAC -- WI																		
*175 WEST 55-20-054-QRY Created On: 07/15/20 Updated On:	Q	NE	SW	10	14N	17E	Fond Du Lac	0-225-214-2020	0.0	4.9	1.4	7.7	32.8	2.724	2.757	1.200		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
BATTERMAN 55-20-050-QRY Created On: 02/03/17 Updated On:	Q	SW	SW	11	14N	17E	Fond Du Lac	0-225-60-2017		0.6	1.4	9.1	40.8	2.696	2.725	1.060		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
BATTERMAN 55-20-050-QRY Created On: 03/02/20 Updated On:	Q	SW	SW	11	14N	17E	Fond Du Lac	0-225-116-2020	0.2	0.5	2.1	8.2	34.7	2.753	2.775	0.821		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
BATTERMAN 55-20-050-QRY Created On: 01/04/23 Updated On:	Q	SW	SW	11	14N	17E	Fond Du Lac	0-225-101-2023	0.0	3.0	1.2	6.5	28.9	2.794	2.808	0.508		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
BREAKNECK ROAD 55-20-055-QRY Created On: 01/14/21 Updated On:	Q	NE	NW	34	14N	16E	Fond Du Lac	0-225-121-2021	0.0	0.7	0.6	5.8	25.8	2.773	2.792	0.676		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
BREAKNECK ROAD 55-20-055-QRY Created On: 01/02/24 Updated On:	Q	NE	NW	34	14N	16E	Fond Du Lac	0-225-50-2024	0.1	1.3	1.0	5.9	26.7	2.772	2.790	0.646		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
*BUECHEL STONE OAKFIELD 55-20-056-QRY Created On: 03/24/21 Updated On:	Q	NE	NE	34	14N	16E	Fond Du Lac	0-225-158-2021	0.0	1.0	2.7	5.5	26.0	2.738	2.766	1.007		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Coarse Sp. Gravity		Coarse Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
FOND DU LAC -- WI																		
*BYRON 55-20-012-QRY Created On: 01/08/15 Updated On:	Q	N	SE	10	14N	17E	Fond Du Lac	0-225-29-2015		0.5	1.5	5.5	26.4	2.735	2.765	1.106		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
*BYRON 55-20-012-QRY Created On: 03/16/18 Updated On:	Q	N	SE	10	14N	17E	Fond Du Lac	0-225-122-2018		0.6	0.7	5.5	27.8	2.725	2.758	1.203		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
*BYRON 55-20-012-QRY Created On: 01/05/21 Updated On:	Q	N	SE	10	14N	17E	Fond Du Lac	0-225-49-2021	0.0	1.2	0.9	5.8	28.1	2.738	2.767	1.045		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
CAREW - EDEN 55-20-058-PIT Created On: 01/25/16 Updated On:	P	W	SE	23	14N	18E	Fond Du Lac	0-225-81-2016	0.3	0.0	2.9	8.0	33.0	2.742	2.772	1.093		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
CAREW - EDEN 55-20-058-PIT Created On: 02/08/21 Updated On:	P	W	SE	23	14N	18E	Fond Du Lac	0-225-123-2021	0.5	2.9	3.6	7.6	33.2	2.752	2.783	1.128		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
CAREW ALTO/WAUPUN 55-20-008-QRY Created On: 01/06/14 Updated On:	Q	S	NE	36	14N	14E	Fond Du Lac	0-225-8-2014		1.0	1.9	6.2	28.2	2.770	2.794	0.879		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
CAREW ALTO/WAUPUN 55-20-008-QRY Created On: 03/08/17 Updated On:	Q	S	NE	36	14N	14E	Fond Du Lac	0-225-78-2017		6.0	4.4	6.3	27.9	2.767	2.790	0.826		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse							
	P/Q	Qrt	Qrt	Sect	Town	Range	County	LA Wear (%) 100					500	Sp. Gravity OD SSD		Absorp. % Crse Fine				
FOND DU LAC -- WI																				
CAREW ALTO/WAUPUN 55-20-008-QRY Created On: 01/30/20 Updated On:	Q	S	NE	36	14N	14E	Fond Du Lac	0-225-99-2020	0.0	4.0	3.5	6.2	27.1	2.764	2.791	0.974				
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																			
CAREW ALTO/WAUPUN 55-20-008-QRY Created On: 01/04/23 Updated On:	Q	S	NE	36	14N	14E	Fond Du Lac	0-225-100-2023	0.0	3.9	1.6	6.3	28.2	2.771	2.794	0.821				
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																			
EVENSON - BERTRAM 55-20-011-QRY Created On: 01/08/15 Updated On:	Q	NE	NW	15	16N	18E	Fond Du Lac	0-225-26-2015		0.2	3.1	11.2	41.8	2.715	2.748	1.245				
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																			
EVENSON - BERTRAM 55-20-011-QRY Created On: 04/13/17 Updated On:	Q	NE	NW	15	16N	18E	Fond Du Lac	0-225-128-2017		1.0	1.2	12.9	44.2	2.714	2.750	1.348				
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																			
EVENSON - BERTRAM 55-20-011-QRY Created On: 01/30/20 Updated On:	Q	NE	NW	15	16N	18E	Fond Du Lac	0-225-106-2020	0.0	0.6	1.1	11.0	42.5	2.720	2.758	1.424				
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																			
EVENSON - BERTRAM 55-20-011-QRY Created On: 01/04/24 Updated On:	Q	NE	NW	15	16N	18E	Fond Du Lac	0-225-149-2024	0.3	0.6	1.0	8.7	36.6	2.759	2.783	0.870				
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																			
GRAHL-EMPIRE 55-20-014-PIT Created On: 05/12/16 Updated On:	P	S	SE	36	15N	18E	Fond Du Lac	0-225-173-2016	0.1	0.0	2.2	6.5	29.8	2.740	2.768	1.052				
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																			

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Coarse Sp. Gravity		Coarse Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
FOND DU LAC -- WI																		
GRAHL-EMPIRE 55-20-014-PIT Created On: 04/13/21 Updated On:	P	S	SE	36	15N	18E	Fond Du Lac	0-225-178-2021	1.0	4.9	3.2	5.7	28.7	2.734	2.765	1.105		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
GUELIG 55-20-015-PIT Created On: 01/21/16 Updated On:	P	NW	SE	9	16N	19E	Fond Du Lac	0-225-66-2016	0.0	3.3	4.7	7.4	31.7	2.739	2.774	1.295		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
GUELIG 55-20-015-PIT Created On: 01/05/21 Updated On:	P	NW	SE	9	16N	19E	Fond Du Lac	0-225-102-2021	0.0	3.6	1.1	7.5	31.4	2.738	2.771	1.206		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
GUELIG NORTH 55-20-059-PIT Created On: 10/21/21 Updated On:	P	NW	NE	9	16N	19E	Fond Du Lac	0-225-270-2021	0.3	0.0	4.6	7.5	32.3	2.761	2.789	1.047		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
HOLLATZ 55-20-017-PIT Created On: 01/12/16 Updated On:	P	NE	NW	17	16N	14E	Fond Du Lac	0-225-51-2016		0.0	1.4	5.0	24.2	2.729	2.760	1.132		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
HOLLATZ 55-20-017-PIT Created On: 01/04/21 Updated On:	P	NE	NW	17	16N	14E	Fond Du Lac	0-225-45-2021	0.0	3.7	2.4	4.7	23.3	2.718	2.754	1.341		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
LINCK #26 55-20-028-QRY Created On: 05/09/19 Updated On:	Q	NW	SE	36	14N	14E	Fond Du Lac	0-225-183-2019	0.0	0.9	0.9	6.3	26.4	2.778	2.800	0.809		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse					
	P/Q	Qrt	Qrt	Sect	Town	Range	County	LA Wear (%)					Sp. Gravity		Absorp. %			
												100	500	OD	SSD	Crse	Fine	
FOND DU LAC -- WI																		
LINCK #26 55-20-028-QRY Created On: 06/28/22 Updated On:	Q	NW	SE	36	14N	14E	Fond Du Lac	0-225-236-2022	0.0	4.4	0.5	6.4	25.6	2.780	2.802	0.798		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MICHELS - TAYCHEEDAH 55-20-021-QRY Created On: 01/06/14 Updated On:	Q	SW	NE	16	16N	18E	Fond Du Lac	0-225-13-2014		0.3	1.9	8.4	37.6	2.718	2.750	1.170		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
MICHELS - TAYCHEEDAH 55-20-021-QRY Created On: 01/04/17 Updated On:	Q	SW	NE	16	16N	18E	Fond Du Lac	0-225-11-2017	1.3	0.6	1.4	7.6	33.4	2.749	2.777	1.027		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
MICHELS - TAYCHEEDAH 55-20-021-QRY Created On: 01/08/20 Updated On:	Q	SW	NE	16	16N	18E	Fond Du Lac	0-225-70-2020	0.2	0.9	1.4	9.2	38.3	2.740	2.770	1.088		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MICHELS - TAYCHEEDAH 55-20-021-QRY Created On: 01/03/23 Updated On:	Q	SW	NE	16	16N	18E	Fond Du Lac	0-225-43-2023	0.2	0.7	2.1	7.3	33.5	2.742	2.774	1.175		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
*MICHELS HAMILTON HILL 55-20-024-QRY Created On: 07/07/21 Updated On:	Q		NW	10	14N	17E	Fond Du Lac	0-225-243-2021	1.6	7.4	7.9	12.7	41.3	2.697	2.742	1.665		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MICHELS KETTER 55-20-025-PIT Created On: 11/06/14 Updated On:	P		SW	4	13N	19E	Fond Du Lac	0-225-269-2014	1.1	0.0	4.1	7.9	32.8	2.725	2.757	1.176		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
FOND DU LAC -- WI																		
MICHELS KETTER 55-20-025-PIT Created On: 03/19/15 Updated On:	P		SW	4	13N	19E	Fond Du Lac	0-225-100-2015	1.1	0.0	4.1	7.9	32.8	2.725	2.758	1.180		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
MICHELS KETTER 55-20-025-PIT Created On: 01/08/20 Updated On:	P		SW	4	13N	19E	Fond Du Lac	0-225-74-2020	2.0	8.5	4.0	8.5	34.3	2.715	2.755	1.466		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MICHELS MARBLEHEAD 55-20-026-QRY Created On: 01/04/16 Updated On:	Q	NE	NE	7	14N	18E	Fond Du Lac	0-225-13-2016		2.3	1.1	8.4	34.6	2.760	2.782	0.806		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
MICHELS MARBLEHEAD 55-20-026-QRY Created On: 01/04/19 Updated On:	Q	NE	NE	7	14N	18E	Fond Du Lac	0-225-19-2019		5.0	2.7	9.3	36.0	2.739	2.766	0.981		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MICHELS MARBLEHEAD 55-20-026-QRY Created On: 01/04/22 Updated On:	Q	NE	NE	7	14N	18E	Fond Du Lac	0-225-23-2022	0.0	2.6	1.6	8.8	35.3	2.739	2.770	1.140		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MICHELS-WAUPUN 55-20-031-QRY Created On: 01/04/16 Updated On:	Q	S	NW	36	14N	14E	Fond Du Lac	0-225-8-2016		4.5	4.2	6.5	27.5	2.778	2.801	0.828		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
MICHELS-WAUPUN 55-20-031-QRY Created On: 01/08/19 Updated On:	Q	S	NW	36	14N	14E	Fond Du Lac	0-225-71-2019	0.0	9.5	6.0	6.7	30.9	2.798	2.822	0.865		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Coarse Sp. Gravity		Coarse Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine		
FOND DU LAC -- WI																			
MICHELS-WAUPUN 55-20-031-QRY Created On: 01/04/22 Updated On:	Q	S	NW	36	14N	14E	Fond Du Lac	0-225-19-2022	0.0	5.6	2.8	6.0	28.6	2.764	2.791	0.973			
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
MICHELS/BERRES 55-20-004-PIT Created On: 09/11/14 Updated On:	P	SW	SE	32	14N	19E	Fond Du Lac	0-225-259-2014	1.4	0.0	2.8	7.0	28.7	2.721	2.754	1.231			
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																		
MICHELS/BERRES 55-20-004-PIT Created On: 01/04/19 Updated On:	P	SW	SE	32	14N	19E	Fond Du Lac	0-225-17-2019	0.8	0.0	2.2	8.9	34.6	2.728	2.764	1.316			
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																		
MICHELS/BERRES 55-20-004-PIT Created On: 01/02/24 Updated On:	P	SW	SE	32	14N	19E	Fond Du Lac	0-225-52-2024	1.0	0.0	2.9	8.6	34.2	2.735	2.764	1.025			
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
*OAKFIELD STONE FOND DU LAC 55-20-033-QRY Created On: 04/22/20 Updated On:	Q	SE	SE	10	14N	17E	Fond Du Lac	0-225-154-2020	0.0	2.2	1.7	5.7	26.5	2.771	2.796	0.879			
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
*R & R WASH 55-20-035-PIT Created On: 03/07/14 Updated On:	P	E	SW	7	16N	14E	Fond Du Lac	0-225-93-2014	0.2	0.0	4.3	8.4	32.8	2.689	2.731	1.582			
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																		
*R & R WASH 55-20-035-PIT Created On: 04/24/19 Updated On:	P	E	SW	7	16N	14E	Fond Du Lac	0-225-164-2019	1.9	4.4	4.0	7.8	31.5	2.704	2.743	1.446			
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																		

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse									
	P/Q	Qrt	Qrt	Sect	Town	Range	County	LA Wear (%) 100					500	Sp. Gravity OD SSD		Absorp. % Crse Fine						
FOND DU LAC -- WI																						
RADEMANN STONE 55-20-036-QRY Created On: 05/08/15 Updated On:	Q	NE	SW	11	14N	17E	Fond Du Lac	0-225-156-2015		1.2	0.4	6.9	29.4	2.778	2.795	0.615						
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																					
RADEMANN STONE 55-20-036-QRY Created On: 06/27/18 Updated On:	Q	NE	SW	11	14N	17E	Fond Du Lac	0-225-241-2018		1.0	1.0	6.3	30.2	2.759	2.781	0.797						
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																					
RADEMANN STONE 55-20-036-QRY Created On: 04/30/21 Updated On:	Q	NE	SW	11	14N	17E	Fond Du Lac	0-225-197-2021		0.7	1.1	0.5	7.7	31.5	2.739	2.763	0.867					
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																					
RADEMANN STONE 55-20-036-QRY Created On: 01/02/24 Updated On:	Q	NE	SW	11	14N	17E	Fond Du Lac	0-225-108-2024		0.0	0.7	0.7	6.2	28.4	2.770	2.790	0.719					
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																					
REEDS CORNER 55-20-039-PIT Created On: 01/16/15 Updated On:	P	E	NW	12	15N	14E	Fond Du Lac	0-225-67-2015		0.0	3.0	7.0	30.3	2.751	2.785	1.215						
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																					
REEDS CORNER 55-20-039-PIT Created On: 05/19/20 Updated On:	P	E	NW	12	15N	14E	Fond Du Lac	0-225-181-2020		0.0	0.0	4.3	5.5	25.8	2.774	2.801	0.973					
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																					
RLAM (RIPON LIME & 55-20-035-QRY Created On: 06/05/14 Updated On:	Q	SW	NW	20	16N	14E	Fond Du Lac	0-225-182-2014		6.6	1.4	9.1	34.4	2.685	2.735	1.871						
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																					

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse					
	P/Q	Qrt	Qrt	Sect	Town	Range	County	LA Wear (%) 100 500					Sp. Gravity OD SSD		Absorp. % Crse Fine			
FOND DU LAC -- WI RLAM (RIPON LIME & 55-20-035-QRY Created On: 02/06/23 Updated On:	Q	SW	NW	20	16N	14E	Fond Du Lac	0-225-135-2023	0.2	13.7	5.9	7.7	32.3	2.702	2.744	1.525		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
RUDINGER 55-20-041-QRY Created On: 01/08/15 Updated On:	Q		NW	11	14N	17E	Fond Du Lac	0-225-28-2015		0.4	1.9	8.0	34.1	2.730	2.758	1.030		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
RUDINGER 55-20-041-QRY Created On: 03/07/16 Updated On:	Q		NW	11	14N	17E	Fond Du Lac	0-225-95-2016		1.0	1.3	5.2	25.1	2.762	2.785	0.866		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
RUDINGER 55-20-041-QRY Created On: 01/04/19 Updated On:	Q		NW	11	14N	17E	Fond Du Lac	0-225-20-2019	0.7	1.5	0.9	5.7	27.2	2.760	2.786	0.950		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
RUDINGER 55-20-041-QRY Created On: 01/04/22 Updated On:	Q		NW	11	14N	17E	Fond Du Lac	0-225-21-2022	0.0	0.7	1.5	6.2	28.8	2.727	2.761	1.255		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
RUDINGER 55-20-041-QRY Created On: 01/02/24 Updated On:	Q		NW	11	14N	17E	Fond Du Lac	0-225-101-2024	0.0	0.7	0.8	5.6	27.1	2.775	2.794	0.692		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
STEGER 55-20-057-PIT Created On: 01/06/14 Updated On:	P	SW	SW	24	13N	18E	Fond Du Lac	0-225-7-2014		0.0	1.5	6.1	27.0	2.759	2.783	0.846		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse					
	P/Q	Qrt	Qrt	Sect	Town	Range	County	LA Wear (%) 100					500	Sp. Gravity OD	SSD	Absorp. % Crse	Fine	
FOND DU LAC -- WI																		
STEGER 55-20-057-PIT Created On: 03/24/21 Updated On:	P	SW	SW	24	13N	18E	Fond Du Lac	0-225-157-2021	0.1	0.0	3.0	6.4	29.3	2.767	2.790	0.822		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
STRAUB 55-20-006-PIT Created On: 01/06/14 Updated On:	P		W	23	14N	18E	Fond Du Lac	0-225-16-2014		0.0	0.7	5.4	25.2	2.784	2.805	0.740		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
STRAUB 55-20-006-PIT Created On: 01/04/19 Updated On:	P		W	23	14N	18E	Fond Du Lac	0-225-18-2019		4.9	0.8	7.1	30.0	2.758	2.785	0.984		
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																	
STRAUB 55-20-006-PIT Created On: 01/02/24 Updated On:	P		W	23	14N	18E	Fond Du Lac	0-225-100-2024	0.8	2.9	0.2	6.1	26.3	2.772	2.795	0.806		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
THACKRAY 55-20-048-PIT Created On: 09/11/14 Updated On:	P			13	15N	19E	Fond Du Lac	0-225-256-2014		0.0	2.7	8.1	33.5	2.747	2.775	1.000		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
THACKRAY 55-20-048-PIT Created On: 04/10/19 Updated On:	P			13	15N	19E	Fond Du Lac	0-225-129-2019	0.3	0.0	0.9	7.6	33.6	2.748	2.775	0.967		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
THACKRAY 55-20-048-PIT Created On: 01/02/24 Updated On:	P			13	15N	19E	Fond Du Lac	0-225-53-2024	1.1	0.0	1.1	6.0	28.0	2.766	2.787	0.752		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse					
	P/Q	Qrt	Qrt	Sect	Town	Range	County	LA Wear (%) 100 500					Sp. Gravity OD SSD		Absorp. % Crse Fine			
FOND DU LAC -- WI																		
THACKRAY SOUTH 55-20-053-PIT Created On: 05/15/20 Updated On:	P	SE	NW	13	15N	19E	Fond Du Lac	0-225-179-2020	0.0	0.0	2.3	7.8	36.0	2.725	2.760	1.289		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
FOREST -- WI																		
FLANNERY 55-21-004-PIT Created On: 05/11/15 Updated On:	P	SW	SE	33	36N	13E	Forest	0-225-165-2015		0.0	0.5	5.4	23.3	2.701	2.729	1.042		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
FLANNERY 55-21-004-PIT Created On: 07/16/20 Updated On:	P	SW	SE	33	36N	13E	Forest	0-225-221-2020	0.0	0.0	0.4	5.2	23.5	2.743	2.762	0.685		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
ISON 55-21-011-PIT Created On: 08/16/16 Updated On:	P	SE	NW	19	37N	13E	Forest	0-225-240-2016		0.0	0.6	6.5	26.2	2.696	2.713	0.646		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
ISON 55-21-011-PIT Created On: 01/04/21 Updated On:	P	SE	NW	19	37N	13E	Forest	0-225-12-2021	0.0	1.6	0.8	4.8	21.3	2.673	2.695	0.795		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
LABINE 55-21-21-PIT Created On: 08/22/17 Updated On:	P	S	SW	12	37N	16E	Forest	0-225-258-2017	0.8	0.0	0.5	5.1	19.9	2.741	2.762	0.732		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
LABINE 55-21-21-PIT Created On: 06/13/22 Updated On:	P	S	SW	12	37N	16E	Forest	0-225-227-2022	0.0	0.6	0.8	4.0	18.0	2.724	2.743	0.691		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse					
	P/Q	Qrt	Qrt	Sect	Town	Range	County	LA Wear (%) 100 500					Sp. Gravity OD SSD		Absorp. % Crse Fine			
FOREST -- WI																		
POPPLE RIVER 55-21-016-PIT Created On: 07/01/21 Updated On:	P	SW	NW	12	38N	14E	Forest	0-225-240-2021	0.0	0.2	0.2	3.6	17.1	2.734	2.749	0.556		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
SCHALLOCK 55-21-018-PIT Created On: 08/03/16 Updated On:	P	SE	NE	36	36N	12E	Forest	0-225-234-2016	0.4	0.0	1.5	5.0	21.9	2.695	2.721	0.939		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
SCHALLOCK 55-21-018-PIT Created On: 01/04/21 Updated On:	P	SE	NE	36	36N	12E	Forest	0-225-13-2021	0.0	1.4	0.3	4.8	20.7	2.675	2.707	1.208		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
SMITH-PIT 55-21-021-PIT Created On: 02/28/24 Updated On:	P	SE	SW	7	34N	15E	Forest	0-225-195-2024	0.9	0.0	0.3	4.4	20.3	2.731	2.746	0.545		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
GRANT -- WI																		
ADAMETZ 55-22-001-QRY Created On: 05/23/14 Updated On:	Q	SE	SE	11	6N	1W	Grant	0-225-170-2014	1.6	2.1	4.1	8.0	31.3	2.613	2.668	2.133		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
ADAMETZ 55-22-001-QRY Created On: 01/05/17 Updated On:	Q	SE	SE	11	6N	1W	Grant	0-225-29-2017	0.3	5.4	4.1	8.5	34.9	2.631	2.680	1.878		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
ADAMETZ 55-22-001-QRY Created On: 01/04/19 Updated On:	Q	SE	SE	11	6N	1W	Grant	0-225-27-2019	1.2	7.9	7.2	12.6	40.8	2.608	2.665	2.185		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine		
GRANT -- WI																			
ADAMETZ 55-22-001-QRY Created On: 01/04/22 Updated On:	Q	SE	SE	11	6N	1W	Grant	0-225-52-2022	1.1	5.0	2.7	8.0	29.5	2.644	2.693	1.825			
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
ASHTON 55-22-003-QRY Created On: 06/30/16 Updated On:	Q	SW	SW	26	4N	3W	Grant	0-225-218-2016		3.6	1.1	12.3	42.2	2.588	2.663	2.893			
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																		
ASHTON 55-22-003-QRY Created On: 01/07/19 Updated On:	Q	SW	SW	26	4N	3W	Grant	0-225-52-2019	0.4	9.8	2.8	14.0	45.7	2.570	2.646	2.946			
	Approved Use : CONCRETE, Base Aggregate																		
ASHTON 55-22-003-QRY Created On: 04/05/23 Updated On:	Q	SW	SW	26	4N	3W	Grant	0-225-189-2023	0.4	9.2	9.4	12.3	42.9	2.591	2.662	2.716			
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
*BAKER 55-22-065-QRY Created On: 06/17/21 Updated On:	Q	NE	NE	35	4N	2W	Grant	0-225-224-2021	0.5	8.2	11.6	15.3	48.3	2.557	2.638	3.177			
	Approved Use : CONCRETE, OGBC, Base Aggregate																		
*BENDORF 55-22-006-QRY Created On: 05/23/14 Updated On:	Q	SW	NE	19	4N	2W	Grant	0-225-166-2014	0.0	3.4	3.9	13.5	45.0	2.538	2.621	3.287			
	Approved Use : CONCRETE, OGBC, Base Aggregate																		
*BENDORF 55-22-006-QRY Created On: 01/05/17 Updated On:	Q	SW	NE	19	4N	2W	Grant	0-225-28-2017		4.1	6.3	14.9	47.5	2.572	2.644	2.778			
	Approved Use : CONCRETE, Base Aggregate																		

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse					
	P/Q	Qrt	Qrt	Sect	Town	Range	County					LA Wear (%)		Sp. Gravity		Absorp. %	
												100	500	OD	SSD	Crse	Fine
GRANT -- WI																	
*BENDORF 55-22-006-QRY Created On: 01/04/19 Updated On:	Q	SW	NE	19	4N	2W	Grant	0-225-24-2019	1.0	6.4	2.7	13.9	47.1	2.565	2.641	2.934	
	Approved Use : CONCRETE, OGBC, Base Aggregate																
*BODE 55-22-008-QRY Created On: 05/23/14 Updated On:	Q	NW	SE	4	2N	3W	Grant	0-225-175-2014	0.5	1.5	6.0	10.9	38.6	2.567	2.636	2.675	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
*BODE 55-22-008-QRY Created On: 04/25/17 Updated On:	Q	NW	SE	4	2N	3W	Grant	0-225-154-2017	0.5	6.5	7.7	11.6	42.5	2.564	2.638	2.909	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
*BODE 55-22-008-QRY Created On: 04/19/19 Updated On:	Q	NW	SE	4	2N	3W	Grant	0-225-154-2019	0.5	4.9	9.0	9.8	36.9	2.577	2.644	2.593	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
BOSCOBEL 55-22-060-QRY Created On: 01/05/17 Updated On:	Q	NE	SE	14	7N	3W	Grant	0-225-25-2017	0.7	5.6	2.2	7.5	29.9	2.611	2.674	2.416	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
BOSCOBEL 55-22-060-QRY Created On: 08/03/18 Updated On:	Q	NE	SE	14	7N	3W	Grant	0-225-263-2018	0.8	4.1	6.1	7.5	30.8	2.625	2.678	2.014	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
BOSCOBEL 55-22-060-QRY Created On: 04/07/21 Updated On:	Q	NE	SE	14	7N	3W	Grant	0-225-172-2021	0.0	1.9	6.8	8.1	31.0	2.621	2.680	2.252	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse					
	P/Q	Qrt	Qrt	Sect	Town	Range	County					LA Wear (%)		Sp. Gravity		Absorp. %	
												100	500	OD	SSD	Crse	Fine
GRANT -- WI																	
BOSCOBEL 55-22-060-QRY Created On: 01/02/24 Updated On:	Q	NE	SE	14	7N	3W	Grant	0-225-3-2024	0.2	1.9	1.1	5.8	25.7	2.662	2.707	1.683	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
CASSVILLE 55-22-009-QRY Created On: 06/30/16 Updated On:	Q	NW	SW	27	3N	5W	Grant	0-225-214-2016	1.2	1.9	0.8	8.8	36.7	2.592	2.659	2.573	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
CASSVILLE 55-22-009-QRY Created On: 01/07/19 Updated On:	Q	NW	SW	27	3N	5W	Grant	0-225-47-2019	0.4	5.2	3.1	8.3	34.7	2.590	2.656	2.564	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
CASSVILLE 55-22-009-QRY Created On: 01/10/22 Updated On:	Q	NW	SW	27	3N	5W	Grant	0-225-104-2022	2.3	5.0	8.0	8.4	36.4	2.594	2.658	2.469	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
CROFT 55-22-010-QRY Created On: 04/07/16 Updated On:	Q	NW	SE	24	6N	3W	Grant	0-225-132-2016	0.8	24.3	17.5	12.0	41.8	2.577	2.651	2.876	
	Approved Use : CONCRETE, Base Aggregate																
CROFT 55-22-010-QRY Created On: 01/05/17 Updated On:	Q	NW	SE	24	6N	3W	Grant	0-225-23-2017	0.4	16.9	9.9	16.7	49.6	2.554	2.632	3.042	
	Approved Use : CONCRETE, Base Aggregate																
CROFT 55-22-010-QRY Created On: 04/25/17 Updated On:	Q	NW	SE	24	6N	3W	Grant	0-225-153-2017	0.2	17.2	12.9	11.8	41.4	2.579	2.651	2.777	
	Approved Use : Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse					
	P/Q	Qrt	Qrt	Sect	Town	Range	County					LA Wear (%)		Sp. Gravity		Absorp. %	
												100	500	OD	SSD	Crse	Fine
GRANT -- WI																	
CROFT 55-22-010-QRY Created On: 05/21/18 Updated On:	Q	NW	SE	24	6N	3W	Grant	0-225-216-2018	0.3	14.9	10.3	13.4	44.3	2.561	2.639	3.057	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
CROFT 55-22-010-QRY Created On: 01/05/21 Updated On:	Q	NW	SE	24	6N	3W	Grant	0-225-56-2021	2.7	15.3	17.5	15.9	48.0	2.515	2.606	3.633	
	Approved Use : Base Aggregate																
CROFT 55-22-010-QRY Created On: 01/02/24 Updated On:	Q	NW	SE	24	6N	3W	Grant	0-225-39-2024	1.4	11.8	5.2	12.8	39.8	2.530	2.617	3.433	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
DEITER 55-22-013-QRY Created On: 04/24/14 Updated On:	Q	NW	NW	29	2N	1W	Grant	0-225-140-2014		1.1	5.5	10.9	37.5	2.617	2.684	2.567	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
DEITER 55-22-013-QRY Created On: 04/06/17 Updated On:	Q	NW	NW	29	2N	1W	Grant	0-225-112-2017	0.7	1.4	1.4	10.0	38.1	2.573	2.644	2.760	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
DEITER 55-22-013-QRY Created On: 07/28/17 Updated On:	Q	NW	NW	29	2N	1W	Grant	0-225-242-2017	0.4	2.1	2.1	12.5	43.6	2.554	2.630	2.995	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
DEITER 55-22-013-QRY Created On: 04/28/20 Updated On:	Q	NW	NW	29	2N	1W	Grant	0-225-158-2020	2.1	1.7	2.6	12.9	42.2	2.548	2.627	3.105	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse		Absorp. %						
	P/Q	Qrt	Qrt	Sect	Town	Range	County					LA Wear (%) 100 500	Sp. Gravity OD SSD	Crse Fine						
GRANT -- WI																				
DEITER 55-22-013-QRY Created On: 01/03/23 Updated On:	Q	NW	NW	29	2N	1W	Grant	0-225-6-2023	0.1	2.0	3.6	11.7	42.0	2.536	2.625	3.500				
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																			
FREY 55-22-017-QRY Created On: 06/30/16 Updated On:	Q	NW	SE	15	7N	3W	Grant	0-225-216-2016		3.9	4.5	12.0	39.2	2.605	2.668	2.431				
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																			
FREY 55-22-017-QRY Created On: 05/12/20 Updated On:	Q	NW	SE	15	7N	3W	Grant	0-225-175-2020	0.7	4.6	3.7	10.5	37.5	2.577	2.646	2.654				
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																			
FREY 55-22-017-QRY Created On: 01/10/23 Updated On:	Q	NW	SE	15	7N	3W	Grant	0-225-117-2023	0.4	5.1	4.0	11.0	38.6	2.544	2.631	3.430				
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																			
HAMPTON 55-22-021-QRY Created On: 04/07/16 Updated On:	Q			21	4N	5W	Grant	0-225-136-2016	1.2	8.5	6.9	9.4	36.5	2.576	2.646	2.698				
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																			
HAMPTON 55-22-021-QRY Created On: 04/19/19 Updated On:	Q			21	4N	5W	Grant	0-225-156-2019	1.5	7.6	5.4	10.0	38.0	2.594	2.656	2.424				
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																			
HAMPTON 55-22-021-QRY Created On: 01/04/22 Updated On:	Q			21	4N	5W	Grant	0-225-46-2022	0.9	14.6	1.1	10.6	36.4	2.569	2.638	2.693				
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																			

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Coarse Sp. Gravity		Coarse Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
GRANT -- WI																		
*HARTNETT 55-22-022-QRY Created On: 08/16/16 Updated On:	Q	NW	SW	27	4N	2W	Grant	0-225-244-2016	4.9	9.5	12.7	9.2	38.0	2.577	2.645	2.658		
	Approved Use : Base Aggregate																	
*HARTNETT 55-22-022-QRY Created On: 04/19/19 Updated On:	Q	NW	SW	27	4N	2W	Grant	0-225-155-2019	3.1	14.9	12.9	11.3	42.3	2.589	2.663	2.849		
	Approved Use : Base Aggregate																	
*HAVERLAND 55-22-023-QRY Created On: 04/24/14 Updated On:	Q	NE	NW	26	2N	2W	Grant	0-225-146-2014	0.3	8.8	10.8	11.4	39.1	2.576	2.654	3.001		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
*HAVERLAND 55-22-023-QRY Created On: 04/06/17 Updated On:	Q	NE	NW	26	2N	2W	Grant	0-225-106-2017	1.0	2.4	2.5	12.7	39.1	2.528	2.616	3.516		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
*HAVERLAND 55-22-023-QRY Created On: 03/23/18 Updated On:	Q	NE	NW	26	2N	2W	Grant	0-225-137-2018	1.0	2.9	2.5	13.4	41.0	2.552	2.627	2.962		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
*HAVERLAND 55-22-023-QRY Created On: 03/17/21 Updated On:	Q	NE	NW	26	2N	2W	Grant	0-225-150-2021	0.1	3.9	4.1	18.0	49.1	2.507	2.598	3.604		
	Approved Use : Base Aggregate																	
*HWY-11 55-22-025-QRY Created On: 05/23/14 Updated On:	Q	SE	NW	26	1N	2W	Grant	0-225-171-2014	0.3	1.1	2.2	10.5	38.0	2.591	2.660	2.646		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse					
	P/Q	Qrt	Qrt	Sect	Town	Range	County					LA Wear (%)		Sp. Gravity		Absorp. %	
												100	500	OD	SSD	Crse	Fine
GRANT -- WI																	
*HWY-11 55-22-025-QRY Created On: 06/01/21 Updated On:	Q	SE	NW	26	1N	2W	Grant	0-225-217-2021	0.8	2.9	3.4	9.4	37.2	2.608	2.667	2.256	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
*HWY-11 55-22-025-QRY Created On: 01/02/24 Updated On:	Q	SE	NW	26	1N	2W	Grant	0-225-32-2024	0.7	3.4	4.9	10.7	36.8	2.561	2.636	2.904	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
JULIUS WIEST 55-22-028-QRY Created On: 05/23/14 Updated On:	Q	NE	NW	26	3N	5W	Grant	0-225-173-2014		2.5	2.7	9.0	35.6	2.621	2.677	2.149	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
JULIUS WIEST 55-22-028-QRY Created On: 04/25/17 Updated On:	Q	NE	NW	26	3N	5W	Grant	0-225-152-2017	0.2	15.9	7.0	10.9	41.3	2.562	2.639	2.987	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
JULIUS WIEST 55-22-028-QRY Created On: 04/19/19 Updated On:	Q	NE	NW	26	3N	5W	Grant	0-225-158-2019	0.8	11.1	10.9	12.4	42.9	2.584	2.652	2.647	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
JULIUS WIEST 55-22-028-QRY Created On: 01/04/22 Updated On:	Q	NE	NW	26	3N	5W	Grant	0-225-48-2022	0.9	15.9	0.8	9.7	36.0	2.578	2.651	2.840	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
*KIRSCHBAUM 55-22-030-QRY Created On: 04/07/16 Updated On:	Q	NE	SW	26	5N	5W	Grant	0-225-135-2016	1.6	7.0	5.7	15.1	47.0	2.596	2.665	2.643	
	Approved Use : CONCRETE, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse					
	P/Q	Qrt	Qrt	Sect	Town	Range	County					LA Wear (%)		Sp. Gravity		Absorp. %	
												100	500	OD	SSD	Crse	Fine
GRANT -- WI																	
*KIRSCHBAUM 55-22-030-QRY Created On: 04/19/19 Updated On:	Q	NE	SW	26	5N	5W	Grant	0-225-157-2019	2.3	3.1	7.1	14.4	46.8	2.588	2.656	2.648	
	Approved Use : CONCRETE, Base Aggregate																
KLAR 55-22-031-QRY Created On: 06/30/16 Updated On:	Q	NW	NW	33	3N	2W	Grant	0-225-217-2016		5.4	4.3	11.7	40.9	2.580	2.653	2.810	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
KLAR 55-22-031-QRY Created On: 07/28/17 Updated On:	Q	NW	NW	33	3N	2W	Grant	0-225-244-2017	2.3	6.0	2.2	11.1	40.3	2.575	2.649	2.872	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
KLAR 55-22-031-QRY Created On: 04/28/20 Updated On:	Q	NW	NW	33	3N	2W	Grant	0-225-157-2020	0.7	3.3	1.8	9.8	36.6	2.604	2.667	2.432	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
KLAR 55-22-031-QRY Created On: 01/03/23 Updated On:	Q	NW	NW	33	3N	2W	Grant	0-225-11-2023	1.0	2.8	4.2	9.3	35.6	2.575	2.646	2.751	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
KUNKEL QUARRY 55-22-066-QRY Created On: 05/22/23 Updated On:	Q	SE	NE	15	1N	2W	Grant	0-225-220-2023	2.0	2.8	2.7	13.2	42.6	2.529	2.615	3.406	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
*KUSSMAUL 55-22-036-QRY Created On: 04/07/16 Updated On:	Q	NW	SE	34	6N	4W	Grant	0-225-137-2016	0.5	3.1	3.8	10.4	37.8	2.598	2.657	2.284	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Coarse Sp. Gravity		Coarse Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
GRANT -- WI																		
*KUSSMAUL 55-22-036-QRY Created On: 01/04/19 Updated On:	Q	NW	SE	34	6N	4W	Grant	0-225-26-2019	0.9	3.8	3.7	10.8	39.0	2.631	2.682	1.954		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
*LOEFFELHOLZ 55-22-037-QRY Created On: 05/09/16 Updated On:	Q	SE	SE	5	2N	1W	Grant	0-225-168-2016	1.3	6.9	9.1	12.5	43.7	2.560	2.639	3.061		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
*LOEFFELHOLZ 55-22-037-QRY Created On: 06/13/19 Updated On:	Q	SE	SE	5	2N	1W	Grant	0-225-213-2019	1.7	6.1	11.6	15.0	46.0	2.536	2.630	3.696		
	Approved Use : CONCRETE, Base Aggregate																	
MILESTONE-ARNOLD ANDERSON 55-22-002-QRY Created On: 04/07/16 Updated On:	Q	SW	SE	34	3N	1W	Grant	0-225-131-2016	1.5	6.1	7.6	12.8	44.0	2.549	2.631	3.202		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
MILESTONE-ARNOLD ANDERSON 55-22-002-QRY Created On: 01/04/19 Updated On:	Q	SW	SE	34	3N	1W	Grant	0-225-25-2019	3.4	9.9	9.4	15.0	48.1	2.537	2.618	3.195		
	Approved Use : CONCRETE, Base Aggregate																	
MILESTONE-ARNOLD ANDERSON 55-22-002-QRY Created On: 05/01/23 Updated On:	Q	SW	SE	34	3N	1W	Grant	0-225-214-2023	1.9	7.0	12.0	12.8	44.9	2.546	2.628	3.224		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MORRIS 55-22-040-QRY Created On: 04/09/15 Updated On:	Q	NW	NW	3	5N	3W	Grant	0-225-116-2015	1.3	2.4	3.9	11.4	39.8	2.671	2.733	2.297		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse		Absorp. %							
	P/Q	Qrt	Qrt	Sect	Town	Range	County					LA Wear (%) 100 500	Sp. Gravity OD SSD	Crse	Fine						
GRANT -- WI																					
MORRIS 55-22-040-QRY Created On: 04/05/23 Updated On:	Q	NW	NW	3	5N	3W	Grant	0-225-188-2023		17.6	2.7	9.5	37.8	2.657	2.685	1.057					
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																				
ROSEMEYER 55-22-045-QRY Created On: 04/07/16 Updated On:	Q	SW	NW	14	3N	1W	Grant	0-225-134-2016		0.7	13.0	8.1	10.9	38.2	2.603	2.672	2.635				
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																				
ROSEMEYER 55-22-045-QRY Created On: 01/04/19 Updated On:	Q	SW	NW	14	3N	1W	Grant	0-225-22-2019		1.8	13.7	4.9	12.2	41.3	2.601	2.667	2.505				
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																				
ROSEMEYER 55-22-045-QRY Created On: 01/04/22 Updated On:	Q	SW	NW	14	3N	1W	Grant	0-225-47-2022		1.3	9.9	0.1	8.5	32.6	2.581	2.651	2.706				
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																				
SALZGERBER 55-22-046-QRY Created On: 01/02/14 Updated On:	Q	NE	SW	2	7N	3W	Grant	0-225-2-2014		2.6	1.8	7.3	8.3	34.6	2.612	2.673	2.320				
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																				
SALZGERBER 55-22-046-QRY Created On: 01/05/17 Updated On:	Q	NE	SW	2	7N	3W	Grant	0-225-34-2017		3.1	4.8	5.6	9.1	37.2	2.619	2.670	1.925				
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																				
SALZGERBER 55-22-046-QRY Created On: 01/09/20 Updated On:	Q	NE	SW	2	7N	3W	Grant	0-225-85-2020		2.8	3.8	7.1	10.2	40.5	2.603	2.659	2.124				
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																				

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse					
	P/Q	Qrt	Qrt	Sect	Town	Range	County					LA Wear (%)		Sp. Gravity		Absorp. %	
												100	500	OD	SSD	Crse	Fine
GRANT -- WI																	
SALZGERBER 55-22-046-QRY Created On: 01/03/23 Updated On:	Q	NE	SW	2	7N	3W	Grant	0-225-63-2023	1.4	5.6	1.3	11.5	39.5	2.592	2.657	2.498	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
SCHNEIDER 55-22-048-QRY Created On: 04/16/15 Updated On:	Q	NW	SE	18	4N	3W	Grant	0-225-122-2015	2.2	10.4	6.7	12.8	43.4	2.598	2.665	2.571	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
SCHNEIDER 55-22-048-QRY Created On: 07/28/17 Updated On:	Q	NW	SE	18	4N	3W	Grant	0-225-243-2017	0.3	4.2	8.3	14.4	44.3	2.599	2.667	2.610	
	Approved Use : CONCRETE, OGBC, Base Aggregate																
SCHNEIDER 55-22-048-QRY Created On: 04/28/20 Updated On:	Q	NW	SE	18	4N	3W	Grant	0-225-161-2020	0.1	3.5	2.1	10.8	39.6	2.547	2.631	3.309	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
SCHNEIDER 55-22-048-QRY Created On: 01/03/23 Updated On:	Q	NW	SE	18	4N	3W	Grant	0-225-7-2023	0.4	4.4	7.9	13.0	42.6	2.567	2.640	2.852	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
SIMMON 55-22-049-QRY Created On: 05/23/14 Updated On:	Q	SW	NW	21	4N	4W	Grant	0-225-165-2014	0.1	1.6	6.0	11.3	41.3	2.553	2.628	2.904	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
SIMMON 55-22-049-QRY Created On: 01/04/18 Updated On:	Q	SW	NW	21	4N	4W	Grant	0-225-71-2018	0.8	10.7	10.0	11.2	40.4	2.575	2.642	2.590	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse					
	P/Q	Qrt	Qrt	Sect	Town	Range	County					LA Wear (%)		Sp. Gravity		Absorp. %	
												100	500	OD	SSD	Crse	Fine
GRANT -- WI																	
SIMMON 55-22-049-QRY Created On: 01/04/22 Updated On:	Q	SW	NW	21	4N	4W	Grant	0-225-45-2022	1.1	10.1	0.7	10.9	39.0	2.559	2.629	2.746	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
TENNYSON 55-22-052-QRY Created On: 04/24/14 Updated On:	Q	NW	NE	36	3N	3W	Grant	0-225-141-2014		5.8	4.8	10.0	37.2	2.595	2.661	2.528	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
TENNYSON 55-22-052-QRY Created On: 04/06/17 Updated On:	Q	NW	NE	36	3N	3W	Grant	0-225-116-2017	2.6	7.7	3.2	11.3	35.1	2.562	2.636	2.888	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
TENNYSON 55-22-052-QRY Created On: 07/28/17 Updated On:	Q	NW	NE	36	3N	3W	Grant	0-225-241-2017	0.3	3.3	1.1	7.5	31.0	2.624	2.678	2.073	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
TENNYSON 55-22-052-QRY Created On: 04/28/20 Updated On:	Q	NW	NE	36	3N	3W	Grant	0-225-160-2020	0.0	3.7	2.2	8.8	33.6	2.642	2.693	1.941	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
TENNYSON 55-22-052-QRY Created On: 01/03/23 Updated On:	Q	NW	NE	36	3N	3W	Grant	0-225-9-2023	0.3	7.0	10.6	10.1	36.8	2.543	2.627	3.277	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
ZART 55-22-061-QRY Created On: 04/17/15 Updated On:	Q	SE	SE	7	6N	3W	Grant	0-225-126-2015	2.2	1.3	6.2	9.9	35.6	2.595	2.655	2.302	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse						
	P/Q	Qrt	Qrt	Sect	Town	Range	County	LA Wear (%) 100 500					Sp. Gravity OD SSD		Absorp. % Crse Fine				
GRANT -- WI																			
ZART 55-22-061-QRY Created On: 08/15/17 Updated On:	Q	SE	SE	7	6N	3W	Grant	0-225-255-2017	2.4	6.1	2.1	9.4	34.1	2.606	2.663	2.158			
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																		
ZART 55-22-061-QRY Created On: 01/04/18 Updated On:	Q	SE	SE	7	6N	3W	Grant	0-225-67-2018	1.0	5.6	7.7	10.6	38.6	2.620	2.677	2.196			
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
ZART 55-22-061-QRY Created On: 01/05/21 Updated On:	Q	SE	SE	7	6N	3W	Grant	0-225-59-2021	1.3	5.7	9.4	13.7	43.9	2.628	2.684	2.135			
	Approved Use : CONCRETE, OGBC, Base Aggregate																		
ZART 55-22-061-QRY Created On: 01/02/24 Updated On:	Q	SE	SE	7	6N	3W	Grant	0-225-36-2024	0.3	3.3	2.4	9.2	33.7	2.627	2.684	2.189			
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
GREEN -- WI																			
*BLACKHAWK 55-23-003-QRY Created On: 05/11/15 Updated On:	Q	SW	NE	20	1N	6E	Green	0-225-162-2015		11.7	9.3	11.0	32.8	2.622	2.676	2.068			
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																		
*BLACKHAWK 55-23-003-QRY Created On: 03/23/18 Updated On:	Q	SW	NE	20	1N	6E	Green	0-225-142-2018	0.1	13.5	1.6	8.1	29.9	2.601	2.668	2.568			
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																		
*BLACKHAWK 55-23-003-QRY Created On: 03/17/21 Updated On:	Q	SW	NE	20	1N	6E	Green	0-225-151-2021	1.6	7.8	2.3	8.1	26.9	2.578	2.652	2.885			
	Approved Use : Base Aggregate																		

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Coarse Sp. Gravity		Coarse Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine		
GREEN -- WI																			
INDERGAND 55-23-007-QRY Created On: 07/16/15 Updated On:	Q	SE	SE	20	2N	7E	Green	0-225-210-2015		10.9	6.6	5.5	27.0	2.637	2.698	2.309			
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																		
INDERGAND 55-23-007-QRY Created On: 04/12/16 Updated On:	Q	SE	SE	20	2N	7E	Green	0-225-140-2016		9.3	7.7	5.0	28.1	2.632	2.689	2.175			
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																		
INDERGAND 55-23-007-QRY Created On: 05/16/19 Updated On:	Q	SE	SE	20	2N	7E	Green	0-225-190-2019		0.0	7.5	10.2	5.6	25.2	2.637	2.697	2.259		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
INDERGAND 55-23-007-QRY Created On: 04/05/22 Updated On:	Q	SE	SE	20	2N	7E	Green	0-225-155-2022		0.5	8.6	7.6	5.3	26.5	2.607	2.676	2.659		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
*KLITZKE 55-23-009-QRY Created On: 03/19/15 Updated On:	Q			16	4N	7E	Green	0-225-97-2015		5.6	6.7	14.1	46.7	2.510	2.611	4.014			
	Approved Use : CONCRETE, Base Aggregate																		
*KLITZKE 55-23-009-QRY Created On: 05/11/18 Updated On:	Q			16	4N	7E	Green	0-225-211-2018		1.7	6.8	7.7	12.3	41.5	2.546	2.634	3.485		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																		
*KLITZKE 55-23-009-QRY Created On: 04/30/21 Updated On:	Q			16	4N	7E	Green	0-225-195-2021		0.1	22.4	3.8	10.4	38.2	2.582	2.655	2.836		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																		

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse					
	P/Q	Qrt	Qrt	Sect	Town	Range	County	LA Wear (%)					Sp. Gravity		Absorp. %			
												100	500	OD	SSD	Crse	Fine	
GREEN -- WI																		
*KLITZKE 55-23-009-QRY Created On: 08/11/21 Updated On:	Q			16	4N	7E	Green	0-225-258-2021	0.1	5.0	7.4	10.8	37.5	2.595	2.654	2.282		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MONROE CONSTRUCTION 55-23-014-QRY Created On: 07/17/14 Updated On:	Q	SE	NE	32	2N	7E	Green	0-225-222-2014		14.1	1.9	10.0	39.2	2.597	2.669	2.741		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
MONROE CONSTRUCTION 55-23-014-QRY Created On: 03/08/17 Updated On:	Q	SE	NE	32	2N	7E	Green	0-225-76-2017	0.2	11.2	2.6	11.5	40.7	2.573	2.650	2.974		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MONROE CONSTRUCTION 55-23-014-QRY Created On: 04/17/23 Updated On:	Q	SE	NE	32	2N	7E	Green	0-225-196-2023	0.9	4.2	6.3	12.0	43.5	2.514	2.611	3.860		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
RUFERS 55-23-020-QRY Created On: 03/08/17 Updated On:	Q			30	2N	8E	Green	0-225-77-2017	0.4	16.0	5.1	10.6	38.0	2.554	2.639	3.342		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
RUFERS 55-23-020-QRY Created On: 04/17/23 Updated On:	Q			30	2N	8E	Green	0-225-195-2023	0.6	18.1	4.6	6.4	28.8	2.582	2.658	2.934		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
SCHWARZENBERGER 55-23-023-QRY Created On: 05/06/15 Updated On:	Q	NW	NW	5	1N	8E	Green	0-225-146-2015	2.4	7.6	13.7	12.8	44.9	2.541	2.634	3.654		
	Approved Use : Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
GREEN -- WI																	
SCHWARZENBERGER 55-23-023-QRY Created On: 04/25/17 Updated On:	Q	NW	NW	5	1N	8E	Green	0-225-158-2017	0.4	6.7	10.1	10.7	39.9	2.598	2.674	2.921	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
SCHWARZENBERGER 55-23-023-QRY Created On: 02/12/20 Updated On:	Q	NW	NW	5	1N	8E	Green	0-225-111-2020	0.4	17.9	21.9	9.3	37.7	2.628	2.691	2.410	
SCHWARZENBERGER 55-23-023-QRY Created On: 03/13/24 Updated On:	Q	NW	NW	5	1N	8E	Green	0-225-196-2024	1.1	2.9	5.2	11.6	42.8	2.559	2.645	3.354	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
*VOEGGLI 55-23-027-QRY Created On: 04/02/14 Updated On:	Q	NE	NE	35	4N	7E	Green	0-225-109-2014	5.1	1.2	3.7	8.9	34.8	2.522	2.619	3.823	
	Approved Use : HMA<E-3, HMA>=E-3, OGBC, Base Aggregate																
*VOEGGLI 55-23-027-QRY Created On: 04/11/18 Updated On:	Q	NE	NE	35	4N	7E	Green	0-225-165-2018	0.7	15.6	14.2	13.5	46.4	2.523	2.640	4.674	
	Approved Use : Base Aggregate																
*VOEGGLI 55-23-027-QRY Created On: 07/28/21 Updated On:	Q	NE	NE	35	4N	7E	Green	0-225-254-2021	0.9	6.7	2.8	6.1	29.7	2.608	2.668	2.301	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
GREEN LAKE -- WI																	
MARKESAN 55-24-007-QRY Created On: 01/16/15 Updated On:	Q		NE	3	14N	13E	Green Lake	0-225-70-2015	0.1	0.9	7.9	6.3	28.2	2.693	2.741	1.785	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse				
	P/Q	Qrt	Qrt	Sect	Town	Range	County					LA Wear (%)		Sp. Gravity		Absorp. %
											100	500	OD	SSD	Crse	Fine
GREEN LAKE -- WI																
MARKESAN 55-24-007-QRY Created On: 04/11/18 Updated On:	Q		NE 3	14N	13E	Green Lake	0-225-166-2018	0.3	15.1	10.2	7.5	31.5	2.671	2.722	1.926	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate															
MARKESAN 55-24-007-QRY Created On: 01/10/19 Updated On:	Q		NE 3	14N	13E	Green Lake	0-225-83-2019		12.5	8.9	7.6	31.8	2.681	2.733	1.931	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate															
MARKESAN 55-24-007-QRY Created On: 03/07/22 Updated On:	Q		NE 3	14N	13E	Green Lake	0-225-139-2022	0.0	10.9	6.7	6.2	28.0	2.703	2.744	1.507	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate															
MASHUDA UPPER 55-24-008-QRY Created On: 03/20/14 Updated On:	Q	NE	NW 28	16N	12E	Green Lake	0-225-100-2014	0.0	0.3	1.1	6.3	30.2	2.689	2.728	1.472	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate															
MASHUDA UPPER 55-24-008-QRY Created On: 03/31/17 Updated On:	Q	NE	NW 28	16N	12E	Green Lake	0-225-95-2017	0.4	1.7	2.6	10.7	38.6	2.640	2.701	2.315	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate															
MASHUDA UPPER 55-24-008-QRY Created On: 05/07/20 Updated On:	Q	NE	NW 28	16N	12E	Green Lake	0-225-172-2020	0.6	1.8	2.2	8.5	37.7				
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate															
MASHUDA UPPER 55-24-008-QRY Created On: 04/04/23 Updated On:	Q	NE	NW 28	16N	12E	Green Lake	0-225-176-2023	0.5	1.6	1.8	10.9	37.5	2.665	2.718	1.975	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate															

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse					
	P/Q	Qrt	Qrt	Sect	Town	Range	County	LA Wear (%) 100 500					Sp. Gravity OD SSD		Absorp. % Crse Fine			
GREEN LAKE -- WI MICHELS MANCHESTER 55-24-010-PIT Created On: 07/08/15 Updated On:	P	SW	SE	16	14N	12E	Green Lake	0-225-207-2015	7.7	0.0	7.3	7.3	33.6	2.573	2.632	2.258		
	Approved Use : HMA<E-3, HMA>=E-3, Base Aggregate																	
MICHELS MANCHESTER 55-24-010-PIT Created On: 01/07/20 Updated On:	P	SW	SE	16	14N	12E	Green Lake	0-225-40-2020	1.7	14.5	9.5	6.5	32.3	2.570	2.630	2.356		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MICHELS MARKESAN 55-24-011-QRY Created On: 01/04/16 Updated On:	Q	SW	SW	9	14N	13E	Green Lake	0-225-14-2016		13.7	6.0	6.1	27.0	2.678	2.724	1.714		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
MICHELS MARKESAN 55-24-011-QRY Created On: 01/03/23 Updated On:	Q	SW	SW	9	14N	13E	Green Lake	0-225-41-2023	0.0	14.9	9.3	6.6	29.0	2.673	2.724	1.902		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
*MORRIS 55-24-012-QRY Created On: 03/20/14 Updated On:	Q	SE	SW	3	16N	13E	Green Lake	0-225-99-2014	0.9	1.8	1.9	6.6	28.8	2.692	2.728	1.332		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
*MORRIS 55-24-012-QRY Created On: 04/03/17 Updated On:	Q	SE	SW	3	16N	13E	Green Lake	0-225-99-2017	0.7	6.4	5.3	12.7	37.1	2.648	2.698	1.874		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
*MORRIS 55-24-012-QRY Created On: 05/07/20 Updated On:	Q	SE	SW	3	16N	13E	Green Lake	0-225-171-2020	3.2	22.9	3.8	10.4	38.1	2.648	2.703	2.072		

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
GREEN LAKE -- WI																		
*MORRIS 55-24-012-QRY Created On: 05/27/21 Updated On:	Q	SE	SW	3	16N	13E	Green Lake	0-225-216-2021	2.1	5.7	3.6	7.7	29.8	2.682	2.722	1.487		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
*RIDGESTONE 55-24-015-QRY Created On: 10/14/16 Updated On:	Q	SW	SE	15	17N	13E	Green Lake	0-225-270-2016	0.9	2.9	1.3	9.5	37.8	2.672	2.719	1.778		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
*RIDGESTONE 55-24-015-QRY Created On: 05/24/19 Updated On:	Q	SW	SE	15	17N	13E	Green Lake	0-225-200-2019	0.1	9.3	2.1	10.1	38.9	2.686	2.730	1.634		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
UTLEY 55-24-019-QRY Created On: 01/04/16 Updated On:	Q	SE	NW	36	15N	13E	Green Lake	0-225-12-2016		0.2	0.1	4.5	18.8	2.632	2.639	0.240		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
UTLEY 55-24-019-QRY Created On: 06/13/19 Updated On:	Q	SE	NW	36	15N	13E	Green Lake	0-225-221-2019	0.0	0.3	0.5	4.9	20.1	2.620	2.632	0.455		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
UTLEY 55-24-019-QRY Created On: 01/04/22 Updated On:	Q	SE	NW	36	15N	13E	Green Lake	0-225-38-2022	0.0	0.4	0.3	4.9	19.9	2.621	2.631	0.372		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
UTLEY 55-24-019-QRY Created On: 01/29/24 Updated On:	Q	SE	NW	36	15N	13E	Green Lake	0-225-156-2024	0.0	1.1	0.9	4.9	20.6	2.620	2.630	0.363		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
IOWA -- WI																		
*19TH HOLE (BURGESS) 55-25-001-QRY Created On: 03/23/17 Updated On:	Q	SE	SW	15	5N	3E	Iowa	0-225-88-2017	1.7	6.2	9.7	10.0	36.9	2.536	2.629	3.681		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
*19TH HOLE (BURGESS) 55-25-001-QRY Created On: 07/15/20 Updated On:	Q	SE	SW	15	5N	3E	Iowa	0-225-217-2020	1.3	4.7	10.0	8.0	32.9	2.543	2.628	3.350		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
BERNING 55-25-005-QRY Created On: 08/08/16 Updated On:	Q	NE	SW	26	5N	3E	Iowa	0-225-237-2016	1.1	6.2	7.1	8.1	35.0	2.582	2.664	3.184		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
BERNING 55-25-005-QRY Created On: 02/11/19 Updated On:	Q	NE	SW	26	5N	3E	Iowa	0-225-103-2019	1.1	10.8	12.5	8.8	35.3	2.560	2.645	3.316		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
BERNING 55-25-005-QRY Created On: 03/17/21 Updated On:	Q	NE	SW	26	5N	3E	Iowa	0-225-143-2021	1.3	14.6	6.1	6.0	30.6	2.642	2.706	2.400		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
BERNING 55-25-005-QRY Created On: 02/28/24 Updated On:	Q	NE	SW	26	5N	3E	Iowa	0-225-184-2024	1.2	13.1	9.3	7.2	32.5	2.616	2.686	2.682		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
EHLER-COBB 55-25-008-QRY Created On: 04/24/14 Updated On:	Q	SE	SE	14	6N	1E	Iowa	0-225-145-2014	0.8	8.1	8.6	13.5	40.5	2.593	2.662	2.637		
	Approved Use : CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse					
	P/Q	Qrt	Qrt	Sect	Town	Range	County	LA Wear (%) 100 500					Sp. Gravity OD SSD		Absorp. % Crse Fine			
IOWA -- WI																		
EHLER-COBB 55-25-008-QRY Created On: 04/06/17 Updated On:	Q	SE	SE	14	6N	1E	Iowa	0-225-114-2017	1.1	6.2	4.5	14.4	40.1	2.531	2.607	3.013		
	Approved Use : CONCRETE, OGBC, Base Aggregate																	
EHLER-COBB 55-25-008-QRY Created On: 04/28/20 Updated On:	Q	SE	SE	14	6N	1E	Iowa	0-225-162-2020	0.7	5.4	5.1	15.0	46.7	2.554	2.633	3.079		
	Approved Use : CONCRETE, OGBC, Base Aggregate																	
EHLER-COBB 55-25-008-QRY Created On: 01/03/23 Updated On:	Q	SE	SE	14	6N	1E	Iowa	0-225-10-2023	0.7	7.0	9.0	12.5	44.2	2.551	2.631	3.167		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
GOLD THORPE 55-25-032-QRY Created On: 06/13/19 Updated On:	Q	SE	SW	15	5N	3E	Iowa	0-225-214-2019	0.1	1.6	3.4	7.6	30.1	2.601	2.669	2.626		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
GOLD THORPE 55-25-032-QRY Created On: 01/10/22 Updated On:	Q	SE	SW	15	5N	3E	Iowa	0-225-100-2022	0.8	3.4	6.9	7.4	35.1	2.573	2.643	2.721		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
HACKL 55-25-010-QRY Created On: 05/23/14 Updated On:	Q	SW	SW	21	8N	1E	Iowa	0-225-172-2014	1.1	2.0	1.9	8.9	35.1	2.603	2.662	2.248		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
HACKL 55-25-010-QRY Created On: 01/05/17 Updated On:	Q	SW	SW	21	8N	1E	Iowa	0-225-24-2017	6.9	4.5	4.6	8.9	34.3	2.645	2.696	1.917		
	Approved Use : HMA<E-3, HMA>=E-3, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %			
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine		
IOWA -- WI																			
HACKL 55-25-010-QRY Created On: 01/04/19 Updated On:	Q	SW	SW	21	8N	1E	Iowa	0-225-23-2019	0.9	7.7	2.9	8.3	32.4	2.662	2.707	1.711			
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																		
HACKL 55-25-010-QRY Created On: 01/04/22 Updated On:	Q	SW	SW	21	8N	1E	Iowa	0-225-49-2022	0.2	6.2	0.4	10.3	34.8	2.648	2.698	1.890			
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
*JONES 55-25-016-QRY Created On: 05/08/15 Updated On:	Q	SE	NE	22	5N	1E	Iowa	0-225-158-2015	0.6	3.4	6.9	14.6	48.5	2.522	2.616	3.719			
	Approved Use : CONCRETE, Base Aggregate																		
*JONES 55-25-016-QRY Created On: 03/23/18 Updated On:	Q	SE	NE	22	5N	1E	Iowa	0-225-140-2018	2.0	5.7	1.9	13.5	45.8	2.529	2.615	3.401			
	Approved Use : CONCRETE, Base Aggregate																		
*JONES 55-25-016-QRY Created On: 03/17/21 Updated On:	Q	SE	NE	22	5N	1E	Iowa	0-225-145-2021	1.0	7.6	2.1	15.8	48.7	2.489	2.591	4.117			
	Approved Use : CONCRETE, OGBC, Base Aggregate																		
*LEIGHTY 55-25-017-QRY Created On: 02/09/18 Updated On:	Q	N	NE	4	4N	1E	Iowa	0-225-93-2018	0.9	1.6	6.7	10.6	39.6	2.556	2.628	2.822			
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
*LEIGHTY 55-25-017-QRY Created On: 03/17/21 Updated On:	Q	N	NE	4	4N	1E	Iowa	0-225-140-2021	1.6	12.7	4.0	8.2	34.8	2.539	2.621	3.259			
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse					
	P/Q	Qrt	Qrt	Sect	Town	Range	County	LA Wear (%) 100					500	Sp. Gravity OD SSD		Absorp. % Crse Fine		
IOWA -- WI LINDEN 55-25-018-QRY Created On: 06/30/16 Updated On:	Q	SW	SW	14	5N	2E	Iowa	0-225-215-2016		0.8	0.5	10.7	39.8	2.676	2.720	1.661		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
LINDEN 55-25-018-QRY Created On: 01/07/19 Updated On:	Q	SW	SW	14	5N	2E	Iowa	0-225-54-2019		0.2	1.8	4.1	10.8	35.9	2.603	2.669	2.522	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
LINDEN 55-25-018-QRY Created On: 01/10/22 Updated On:	Q	SW	SW	14	5N	2E	Iowa	0-225-103-2022		0.4	3.0	4.2	11.0	37.1	2.602	2.670	2.617	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MILLER 55-25-019-QRY Created On: 04/16/15 Updated On:	Q	NW	NW	31	6N	3E	Iowa	0-225-124-2015		4.7	7.2	6.9	30.0	2.588	2.661	2.840		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
MILLER 55-25-019-QRY Created On: 03/28/17 Updated On:	Q	NW	NW	31	6N	3E	Iowa	0-225-91-2017		0.0	4.6	9.2	6.9	30.1	2.594	2.666	2.762	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MILLER 55-25-019-QRY Created On: 02/09/18 Updated On:	Q	NW	NW	31	6N	3E	Iowa	0-225-96-2018		3.0	4.0	6.8	10.8	42.3	2.580	2.650	2.707	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
MILLER 55-25-019-QRY Created On: 03/17/21 Updated On:	Q	NW	NW	31	6N	3E	Iowa	0-225-142-2021		0.1	5.9	3.6	7.7	33.2	2.579	2.651	2.796	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse					
	P/Q	Qrt	Qrt	Sect	Town	Range	County					LA Wear (%)		Sp. Gravity		Absorp. %	
												100	500	OD	SSD	Crse	Fine
IOWA -- WI																	
MILLER 55-25-019-QRY Created On: 02/28/24 Updated On:	Q	NW	NW	31	6N	3E	Iowa	0-225-179-2024	0.8	8.1	10.1	10.2	38.4	2.537	2.627	3.577	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
NANKEY 55-25-020-QRY Created On: 05/23/14 Updated On:	Q	SE	NE	14	7N	1E	Iowa	0-225-167-2014		1.3	2.4	7.9	31.0	2.604	2.670	2.519	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
NANKEY 55-25-020-QRY Created On: 01/05/17 Updated On:	Q	SE	NE	14	7N	1E	Iowa	0-225-26-2017	0.9	3.4	5.2	7.2	30.2	2.634	2.685	1.932	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
NANKEY 55-25-020-QRY Created On: 01/04/19 Updated On:	Q	SE	NE	14	7N	1E	Iowa	0-225-28-2019	0.6	6.4	4.8	6.7	28.9	2.645	2.692	1.786	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
NANKEY 55-25-020-QRY Created On: 01/02/24 Updated On:	Q	SE	NE	14	7N	1E	Iowa	0-225-40-2024	0.2	5.1	2.3	9.2	32.6	2.621	2.677	2.131	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
*SWIGGUM 55-25-025-QRY Created On: 04/16/15 Updated On:	Q	NE	NE	30	6N	3E	Iowa	0-225-120-2015	0.5	2.1	3.3	12.6	44.3	2.494	2.587	3.719	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
*SWIGGUM 55-25-025-QRY Created On: 03/23/18 Updated On:	Q	NE	NE	30	6N	3E	Iowa	0-225-144-2018	1.8	1.3	0.5	9.8	37.3	2.506	2.596	3.617	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse					
	P/Q	Qrt	Qrt	Sect	Town	Range	County	LA Wear (%) 100					500	Sp. Gravity OD SSD		Absorp. % Crse Fine		
IOWA -- WI																		
*SWIGGUM 55-25-025-QRY Created On: 03/17/21 Updated On:	Q	NE	NE	30	6N	3E	Iowa	0-225-146-2021	0.8	1.6	0.9	9.9	38.7	2.491	2.591	4.004		
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
THOMAS COBB 55-25-026-QRY Created On: 02/09/18 Updated On:	Q	NE	NE	30	6N	2E	Iowa	0-225-97-2018	2.1	3.9	8.9	10.5	42.6	2.504	2.601	3.891		
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
THOMAS COBB 55-25-026-QRY Created On: 03/17/21 Updated On:	Q	NE	NE	30	6N	2E	Iowa	0-225-139-2021	2.6	11.0	9.5	12.7	43.9	2.534	2.625	3.573		
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
THOMAS COBB 55-25-026-QRY Created On: 02/28/24 Updated On:	Q	NE	NE	30	6N	2E	Iowa	0-225-181-2024	2.3	12.5	12.4	9.2	38.7	2.526	2.613	3.425		
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
THOMAS\RIDGE 55-25-029-QRY Created On: 04/07/16 Updated On:	Q	NW	NE	33	6N	4E	Iowa	0-225-129-2016	5.6	7.4	5.3	12.3	43.2	2.560	2.633	2.859		
Approved Use : HMA<E-3, HMA>=E-3, Base Aggregate																		
THOMAS\RIDGE 55-25-029-QRY Created On: 02/11/19 Updated On:	Q	NW	NE	33	6N	4E	Iowa	0-225-104-2019	1.8	3.0	5.5	10.6	39.8	2.544	2.631	3.408		
Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																		
THOMAS\RIDGE 55-25-029-QRY Created On: 03/17/21 Updated On:	Q	NW	NE	33	6N	4E	Iowa	0-225-141-2021	1.5	5.3	2.9	9.2	38.2	2.613	2.676	2.415		
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse						
	P/Q	Qrt	Qrt	Sect	Town	Range	County	LA Wear (%) 100 500					Sp. Gravity OD SSD	Absorp. % Crse Fine					
IOWA -- WI																			
THOMAS\RIDGE 55-25-029-QRY Created On: 02/28/24 Updated On:	Q	NW	NE	33	6N	4E	Iowa	0-225-183-2024	2.0	5.4	10.5	9.2	37.6	2.542	2.626	3.275			
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
*THONI 55-25-030-QRY Created On: 03/23/18 Updated On:	Q	SW	SE	3	6N	5E	Iowa	0-225-139-2018	2.7	3.9	1.3	10.9	41.2	2.549	2.632	3.232			
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
*THONI 55-25-030-QRY Created On: 03/17/21 Updated On:	Q	SW	SE	3	6N	5E	Iowa	0-225-147-2021	1.9	2.5	0.6	14.9	46.7	2.562	2.632	2.712			
	Approved Use : CONCRETE, OGBC, Base Aggregate																		
IRON -- WI																			
BRACKETT QUARRY 55-26-002-QRY Created On: 07/21/17 Updated On:	Q	NE	NW	31	46N	2E	Iron	0-225-239-2017	0.1	0.0	0.5	2.6	11.9	2.697	2.710	0.487			
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
BRACKETT QUARRY 55-26-002-QRY Created On: 01/06/20 Updated On:	Q	NE	NW	31	46N	2E	Iron	0-225-31-2020	0.0	0.0	9.1	3.8	16.2	2.683	2.705	0.816			
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
BRACKETT QUARRY 55-26-002-QRY Created On: 01/04/23 Updated On:	Q	NE	NW	31	46N	2E	Iron	0-225-95-2023	0.1	2.9	1.6	3.0	13.4	2.662	2.682	0.759			
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
*KIMBALL 55-26-013-QRY Created On: 04/23/15 Updated On:	Q		S	1	46N	1E	Iron	0-225-129-2015		0.0	1.6	2.6	12.0	2.733	2.764	1.142			
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																		

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse		Absorp. %								
	P/Q	Qrt	Qrt	Sect	Town	Range	County					LA Wear (%) 100 500	Sp. Gravity OD SSD	Crse Fine	Fine							
IRON -- WI																						
*KIMBALL 55-26-013-QRY Created On: 01/04/18 Updated On:	Q		S	1	46N	1E	Iron	0-225-60-2018	0.3	0.0	2.3	2.6	12.2	2.685	2.719	1.274						
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																					
*KIMBALL 55-26-013-QRY Created On: 04/30/21 Updated On:	Q		S	1	46N	1E	Iron	0-225-194-2021	0.3	0.0	2.4	2.6	12.3	2.700	2.736	1.344						
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																					
LUPPINO KIMBALL 55-26-030-QRY Created On: 06/13/18 Updated On:	Q			NW 4	46N	2E	Iron	0-225-230-2018				5.0	27.1	2.826	2.890	2.262						
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																					
LUPPINO KIMBALL 55-26-030-QRY Created On: 04/01/21 Updated On:	Q			NW 4	46N	2E	Iron	0-225-165-2021			0.0	1.7	2.9	12.4	2.796	2.832	1.285					
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																					
LUPPINO KIMBALL 55-26-030-QRY Created On: 01/02/24 Updated On:	Q			NW 4	46N	2E	Iron	0-225-62-2024	0.1	0.0	9.4	3.5	15.9	2.608	2.671	2.430						
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																					
LUPPINO MERCER 55-26-029-PIT Created On: 01/05/17 Updated On:	P		NW	NE 1	42N	3E	Iron	0-225-37-2017			0.0	2.8	3.9	18.8	2.710	2.740	1.085					
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																					
LUPPINO MERCER 55-26-029-PIT Created On: 04/04/23 Updated On:	P		NW	NE 1	42N	3E	Iron	0-225-182-2023			0.0	2.7	4.3	18.7	2.721	2.753	1.167					
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																					

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse						
	P/Q	Qrt	Qrt	Sect	Town	Range	County	LA Wear (%) 100 500					Sp. Gravity OD SSD		Absorp. % Crse Fine				
IRON -- WI																			
NLC MERCER 55-26-024-PIT Created On: 05/02/16 Updated On:	P	S	NW	6	42N	4E	Iron	0-225-159-2016		0.0	0.5	3.7	18.2	2.734	2.760	0.963			
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																		
NLC MERCER 55-26-024-PIT Created On: 01/05/21 Updated On:	P	S	NW	6	42N	4E	Iron	0-225-55-2021	1.1	0.0	1.7	3.4	17.9	2.731	2.756	0.924			
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
SAXON 55-26-019-PIT Created On: 06/13/18 Updated On:	P	SW	SW	18	46N	1E	Iron	0-225-231-2018		1.0	7.5	5.5	27.2	2.617	2.680	2.440			
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																		
SAXON 55-26-019-PIT Created On: 04/04/23 Updated On:	P	SW	SW	18	46N	1E	Iron	0-225-181-2023		0.0	14.3	5.2	21.7	2.615	2.681	2.528			
	Approved Use : Base Aggregate																		
JACKSON -- WI																			
JACKSON COUNTY IRON MINE 55-27-004-QRY Created On: 01/06/14 Updated On:	Q			22	21N	3W	Jackson	0-225-11-2014		0.0	13.2	8.7	29.4	2.732	2.793	2.215			
	Approved Use : Base Aggregate																		
JACKSON COUNTY IRON MINE 55-27-004-QRY Created On: 04/10/17 Updated On:	Q			22	21N	3W	Jackson	0-225-120-2017		0.0	0.7	6.2	24.1	2.812	2.850	1.356			
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																		
JACKSON COUNTY IRON MINE 55-27-004-QRY Created On: 01/08/20 Updated On:	Q			22	21N	3W	Jackson	0-225-62-2020		0.0	1.5	6.1	23.6	2.871	2.897	0.882			
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																		

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
JACKSON -- WI																	
JACKSON COUNTY IRON MINE 55-27-004-QRY Created On: 01/03/23 Updated On:	Q			22	21N	3W	Jackson	0-225-60-2023	0.5	5.5	5.7	6.6	25.0	2.785	2.832	1.679	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
JACKSON COUNTY IRON MINE 55-27-004-QRY Created On: 11/29/23 Updated On:	Q			22	21N	3W	Jackson	0-225-251-2023	1.2	2.9	2.5	6.7	24.3	2.805	2.837	1.125	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
*SMITH 55-27-011-PIT Created On: 08/22/19 Updated On:	P	NE	SE	20	22N	3W	Jackson	0-225-265-2019	2.8	1.1	5.2	2.3	19.0	2.661	2.691	1.122	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
JEFFERSON -- WI																	
ASPHALT CONTRACTORS JEFFERSON 55-28-019-PIT Created On: 01/08/21 Updated On:	P		NE	3	6N	13E	Jefferson	0-225-117-2021	2.3	3.8	0.8	8.6	35.4	2.634	2.681	1.789	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
BRATTSET 55-28-020-PIT Created On: 01/04/22 Updated On:	P	NW	NW	5	5N	16E	Jefferson	0-225-41-2022	1.6	5.2	1.1	4.3	22.8	2.694	2.732	1.401	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
HAUSZ BROS. 55-28-021-QRY Created On: 04/05/22 Updated On:	Q	S	SW	11	5N	14E	Jefferson	0-225-154-2022	1.0	7.1	16.6	17.7	43.4	2.523	2.614	3.645	
	Approved Use : Base Aggregate																
NABER 55-28-009-PIT Created On: 03/20/20 Updated On:	P	NE	NW	31	5N	14E	Jefferson	0-225-133-2020	0.7	0.0	1.7	6.3	30.2	2.654	2.697	1.606	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
JEFFERSON -- WI																	
NABER QUARRY 55-28-022-QRY Created On: 09/06/22 Updated On:	Q	NE	NW	31	5N	14E	Jefferson	0-225-255-2022	2.2	15.6	10.6	9.7	39.0	2.633	2.694	2.328	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
NABER QUARRY 55-28-022-QRY Created On: 11/07/22 Updated On:	Q	NE	NW	31	5N	14E	Jefferson	0-225-261-2022	0.2	10.9	6.1	4.9	26.5	2.693	2.736	1.614	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
TIMBERLANE S & G 55-28-015-PIT Created On: 01/04/22 Updated On:	P	NW	SW	19	6N	14E	Jefferson	0-225-88-2022	0.6	6.2	1.8	4.8	25.5	2.677	2.710	1.234	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
JUNEAU -- WI																	
GEIER ROAD 55-29-009-QRY Created On: 05/18/18 Updated On:	Q			27	14N	3E	Juneau	0-225-213-2018	0.6	0.0	4.4	12.3	45.7	2.608	2.672	2.457	
	Approved Use : HMA<MT, CONCRETE, OGBC, Base Aggregate																
GEIER ROAD 55-29-009-QRY Created On: 01/05/21 Updated On:	Q			27	14N	3E	Juneau	0-225-64-2021	0.8	6.2	8.4	10.9	42.9	2.645	2.697	1.973	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
GEIER ROAD 55-29-009-QRY Created On: 01/02/24 Updated On:	Q			27	14N	3E	Juneau	0-225-116-2024	1.8	4.2	1.6	8.4	34.6	2.577	2.634	2.197	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse				
	P/Q	Qrt	Qrt	Sect	Town	Range	County					LA Wear (%)		Sp. Gravity		Absorp. %
											100	500	OD	SSD	Crse	Fine
KENOSHA -- WI																
HOLCIM-DYER LAKE 55-30-004-PIT Created On: 05/11/18 Updated On:	P		W	29	2N	19E	Kenosha	0-225-209-2018	2.4	10.7	6.7	5.2	25.1	2.673	2.713	1.500
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate															
HOLCIM-DYER LAKE 55-30-004-PIT Created On: 01/03/23 Updated On:	P		W	29	2N	19E	Kenosha	0-225-31-2023	0.0	12.3	1.3	6.6	28.2	2.628	2.683	2.079
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate															
KEWAUNEE -- WI																
*BOULANGER 55-31-002-QRY Created On: 07/31/18 Updated On:	Q	NE	SE	15	22N	23E	Kewaunee	0-225-261-2018	1.9	0.0	2.1	6.7	31.1	2.769	2.794	0.885
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate															
*BOULANGER 55-31-002-QRY Created On: 01/06/21 Updated On:	Q	NE	SE	15	22N	23E	Kewaunee	0-225-112-2021	1.2	0.0	0.6	7.2	31.5	2.781	2.800	0.657
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate															
JADIN 55-31-006-PIT Created On: 07/31/18 Updated On:	P	NE	SE	31	25N	25E	Kewaunee	0-225-260-2018	4.5	0.0	3.0	7.2	30.8	2.667	2.697	1.107
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate															
JADIN 55-31-006-PIT Created On: 05/09/23 Updated On:	P	NE	SE	31	25N	25E	Kewaunee	0-225-217-2023	1.4	0.0	3.1	5.8	28.8	2.691	2.733	1.554
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate															
KROPP AB 55-31-020-QRY Created On: 02/11/19 Updated On:	Q	NE	SE	15	22N	23E	Kewaunee	0-225-105-2019		0.0	1.7	7.9	34.6	2.810	2.823	0.456
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate															

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse					
	P/Q	Qrt	Qrt	Sect	Town	Range	County	LA Wear (%) 100 500					Sp. Gravity OD SSD	Absorp. % Crse Fine				
KEWAUNEE -- WI																		
KROPP AB 55-31-020-QRY Created On: 04/28/22 Updated On:	Q	NE	SE	15	22N	23E	Kewaunee	0-225-187-2022	0.2	0.0	3.4	8.1	35.0	2.780	2.801	0.737		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
SWAGEL 55-31-017-PIT Created On: 11/03/17 Updated On:	P		N	29	23N	24E	Kewaunee	0-225-285-2017	1.5	0.0	5.6	7.9	32.9	2.710	2.748	1.420		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
SWAGEL 55-31-017-PIT Created On: 03/07/22 Updated On:	P		N	29	23N	24E	Kewaunee	0-225-140-2022	3.1	0.0	4.2	6.2	30.8	2.693	2.730	1.368		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
LA CROSSE -- WI																		
KINGS BLUFF 55-32-010-QRY Created On: 09/02/15 Updated On:	Q	W	NE	25	18N	8W	La Crosse	0-225-235-2015	1.6	0.0	3.6	10.9	40.9	2.580	2.649	2.670		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
KINGS BLUFF 55-32-010-QRY Created On: 04/25/17 Updated On:	Q	W	NE	25	18N	8W	La Crosse	0-225-156-2017		0.0	3.0	12.0	44.3	2.584	2.650	2.532		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
KINGS BLUFF 55-32-010-QRY Created On: 03/23/18 Updated On:	Q	W	NE	25	18N	8W	La Crosse	0-225-145-2018	0.9	0.0	9.9	13.7	45.3	2.572	2.644	2.793		
	Approved Use : CONCRETE, Base Aggregate																	
KINGS BLUFF 55-32-010-QRY Created On: 01/07/19 Updated On:	Q	W	NE	25	18N	8W	La Crosse	0-225-48-2019	1.9	0.0	3.2	11.0	42.9	2.593	2.654	2.373		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse				
	P/Q	Qrt	Qrt	Sect	Town	Range	County					LA Wear (%)		Sp. Gravity		Absorp. %
											100	500	OD	SSD	Crse	Fine
LA CROSSE -- WI																
MILESTONE-CLEMENTS YY 55-32-004-QRY Created On: 06/05/15 Updated On:	Q	SW	NE	3	15N	6W	La Crosse	0-225-186-2015		0.0	2.3	10.4	36.9	2.597	2.656	2.237
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate															
MILESTONE-CLEMENTS YY 55-32-004-QRY Created On: 01/03/18 Updated On:	Q	SW	NE	3	15N	6W	La Crosse	0-225-11-2018	3.0	0.0	2.6	12.2	41.9	2.551	2.620	2.700
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate															
MILESTONE-CLEMENTS YY 55-32-004-QRY Created On: 01/04/21 Updated On:	Q	SW	NE	3	15N	6W	La Crosse	0-225-30-2021	2.9	0.0	0.0	10.7	38.2	2.536	2.612	3.006
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate															
MILESTONE-CLEMENTS YY 55-32-004-QRY Created On: 01/02/24 Updated On:	Q	SW	NE	3	15N	6W	La Crosse	0-225-25-2024	2.5	6.8	2.3	10.4	39.4	2.568	2.636	2.657
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate															
MINDORO 55-32-012-QRY Created On: 01/07/14 Updated On:	Q	SW	SW	33	18N	6W	La Crosse	0-225-45-2014		0.0	4.5	8.1	32.4	2.625	2.675	1.919
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate															
MINDORO 55-32-012-QRY Created On: 05/04/17 Updated On:	Q	SW	SW	33	18N	6W	La Crosse	0-225-174-2017		0.0	2.7	10.2	32.7	2.611	2.669	2.187
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate															
MINDORO 55-32-012-QRY Created On: 01/08/20 Updated On:	Q	SW	SW	33	18N	6W	La Crosse	0-225-67-2020	0.7	0.0	7.4	10.3	38.6	2.584	2.650	2.549
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate															

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse					
	P/Q	Qrt	Qrt	Sect	Town	Range	County	LA Wear (%) 100					500	Sp. Gravity OD SSD		Absorp. % Crse Fine		
LA CROSSE -- WI																		
MINDORO 55-32-012-QRY Created On: 01/04/23 Updated On:	Q	SW	SW	33	18N	6W	La Crosse	0-225-87-2023	0.6	3.5	1.5	9.7	38.3	2.596	2.659	2.442		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
ROMSKOG 55-32-014-QRY Created On: 01/07/14 Updated On:	Q	NE	SE	18	17N	6W	La Crosse	0-225-47-2014		0.0	6.2	9.0	34.7	2.621	2.672	1.938		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
ROMSKOG 55-32-014-QRY Created On: 04/28/17 Updated On:	Q	NE	SE	18	17N	6W	La Crosse	0-225-162-2017		0.0	5.4	9.8	38.9	2.552	2.636	3.288		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
ROMSKOG 55-32-014-QRY Created On: 01/08/20 Updated On:	Q	NE	SE	18	17N	6W	La Crosse	0-225-64-2020	0.2	0.0	6.3	10.2	37.2	2.567	2.639	2.815		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
ROMSKOG 55-32-014-QRY Created On: 01/03/23 Updated On:	Q	NE	SE	18	17N	6W	La Crosse	0-225-24-2023	0.5	3.8	3.4	12.4	43.5	2.567	2.636	2.683		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
WALDENBERGER 55-32-017-QRY Created On: 04/24/14 Updated On:	Q			23	17N	7W	La Crosse	0-225-138-2014		0.0	5.3	12.0	45.3	2.561	2.633	2.809		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
WALDENBERGER 55-32-017-QRY Created On: 03/29/17 Updated On:	Q			23	17N	7W	La Crosse	0-225-93-2017	0.3	0.0	3.2	11.8	44.2	2.521	2.610	3.526		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse					
	P/Q	Qrt	Qrt	Sect	Town	Range	County	LA Wear (%) 100 500					Sp. Gravity OD SSD		Absorp. % Crse Fine			
LA CROSSE -- WI																		
WALDENBERGER 55-32-017-QRY Created On: 01/03/20 Updated On:	Q		23	17N	7W	La Crosse		0-225-22-2020	1.1	0.0	6.3	10.8	40.5	2.557	2.633	2.981		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
WALDENBERGER 55-32-017-QRY Created On: 01/03/23 Updated On:	Q		23	17N	7W	La Crosse		0-225-22-2023	0.4	6.7	7.8	12.7	45.5	2.529	2.611	3.230		
	Approved Use : HMA<MT, CONCRETE, OGBC, Base Aggregate																	
LAFAYETTE -- WI																		
*APPEL 55-33-002-QRY Created On: 04/23/15 Updated On:	Q	NW	SW	11	1N	3E	Lafayette	0-225-132-2015	0.2	0.4	3.5	10.1	38.7	2.635	2.686	1.954		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
*APPEL 55-33-002-QRY Created On: 01/04/18 Updated On:	Q	NW	SW	11	1N	3E	Lafayette	0-225-70-2018	0.5	8.4	4.5	12.6	42.9	2.575	2.643	2.644		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
*APPEL 55-33-002-QRY Created On: 01/05/21 Updated On:	Q	NW	SW	11	1N	3E	Lafayette	0-225-61-2021	0.8	3.1	5.0	11.2	39.6	2.619	2.677	2.213		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
BLACKHAWK QUARRY PRODUCTS 55-33-017-QRY Created On: 02/13/20 Updated On:	Q	NE	NE	15	1N	5E	Lafayette	0-225-112-2020	0.5	4.2	5.6	11.6	42.5	2.538	2.627	3.508		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
BLACKHAWK QUARRY PRODUCTS 55-33-017-QRY Created On: 01/02/24 Updated On:	Q	NE	NE	15	1N	5E	Lafayette	0-225-71-2024	0.1	4.6	2.6	9.9	36.0	2.609	2.676	2.559		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse				
	P/Q	Qrt	Qrt	Sect	Town	Range	County					LA Wear (%)		Sp. Gravity		Absorp. %
											100	500	OD	SSD	Crse	Fine
LAFAYETTE -- WI																
DUNN 55-33-008-QRY Created On: 03/23/17 Updated On:	Q		SW	22	2N	3E	Lafayette	0-225-89-2017	1.8	5.3	7.4	10.5	38.9	2.584	2.654	2.710
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate															
DUNN 55-33-008-QRY Created On: 02/09/18 Updated On:	Q		SW	22	2N	3E	Lafayette	0-225-92-2018	1.1	3.0	9.0	7.5	33.8	2.563	2.639	2.964
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate															
DUNN 55-33-008-QRY Created On: 03/17/21 Updated On:	Q		SW	22	2N	3E	Lafayette	0-225-138-2021	0.7	14.2	2.4	9.1	36.3	2.581	2.650	2.678
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate															
DUNN 55-33-008-QRY Created On: 02/28/24 Updated On:	Q		SW	22	2N	3E	Lafayette	0-225-182-2024	1.6	12.4	8.3	9.5	38.3	2.578	2.649	2.754
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate															
FLANNERY 55-33-009-QRY Created On: 04/16/15 Updated On:	Q	NW	SW	6	2N	5E	Lafayette	0-225-125-2015	1.3	8.1	2.4	7.7	31.6	2.643	2.692	1.852
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate															
FLANNERY 55-33-009-QRY Created On: 03/23/18 Updated On:	Q	NW	SW	6	2N	5E	Lafayette	0-225-141-2018	2.4	17.0	4.0	7.4	28.8	2.597	2.658	2.340
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate															
FLANNERY 55-33-009-QRY Created On: 01/07/19 Updated On:	Q	NW	SW	6	2N	5E	Lafayette	0-225-53-2019	1.5	9.5	5.4	7.5	29.9	2.603	2.660	2.196
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate															

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse					
	P/Q	Qrt	Qrt	Sect	Town	Range	County					LA Wear (%)		Sp. Gravity		Absorp. %	
												100	500	OD	SSD	Crse	Fine
LAFAYETTE -- WI																	
FLANNERY 55-33-009-QRY Created On: 04/28/20 Updated On:	Q	NW	SW	6	2N	5E	Lafayette	0-225-163-2020	0.9	6.5	3.5	9.8	34.6	2.599	2.662	2.392	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
FLANNERY 55-33-009-QRY Created On: 03/17/21 Updated On:	Q	NW	SW	6	2N	5E	Lafayette	0-225-148-2021	3.0	8.3	3.4	9.8	35.3	2.560	2.634	2.864	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
FLANNERY 55-33-009-QRY Created On: 03/15/22 Updated On:	Q	NW	SW	6	2N	5E	Lafayette	0-225-143-2022	1.3	5.4	7.0	10.0	35.1	2.635	2.688	1.987	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
FLANNERY 55-33-009-QRY Created On: 01/03/23 Updated On:	Q	NW	SW	6	2N	5E	Lafayette	0-225-5-2023	1.2	4.1	3.8	6.9	29.0	2.609	2.669	2.290	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
FLANNERY 55-33-009-QRY Created On: 01/04/24 Updated On:	Q	NW	SW	6	2N	5E	Lafayette	0-225-139-2024	0.8	6.9	8.1	8.8	36.9	2.610	2.671	2.312	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
LANGE (CAREY) 55-33-013-QRY Created On: 10/10/16 Updated On:	Q	NE	SE	6	2N	3E	Lafayette	0-225-266-2016	3.3	2.6	1.6	8.3	33.3	2.545	2.620	2.968	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
LANGE (CAREY) 55-33-013-QRY Created On: 01/07/19 Updated On:	Q	NE	SE	6	2N	3E	Lafayette	0-225-56-2019	3.2	6.2	3.8	10.9	38.1	2.530	2.609	3.125	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
LAFAYETTE -- WI																		
LANGE (CAREY) 55-33-013-QRY Created On: 01/10/22 Updated On:	Q	NE	SE	6	2N	3E	Lafayette	0-225-106-2022	2.2	8.1	8.8	10.4	39.6	2.502	2.594	3.681		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MOUNDS BRANCH 55-33-018-QRY Created On: 01/29/24 Updated On:	Q	NW	NE	33	4N	1E	Lafayette	0-225-150-2024	1.0	5.8	3.2	9.2	34.9	2.574	2.645	2.755		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
RUEF 55-33-024-QRY Created On: 04/24/14 Updated On:	Q	SW	SE	11	2N	3E	Lafayette	0-225-143-2014	1.9	3.2	2.8	9.5	34.1	2.531	2.586	2.175		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
RUEF 55-33-024-QRY Created On: 04/06/17 Updated On:	Q	SW	SE	11	2N	3E	Lafayette	0-225-111-2017	1.9	2.4	1.5	10.1	35.5	2.591	2.657	2.532		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
RUEF 55-33-024-QRY Created On: 04/28/20 Updated On:	Q	SW	SE	11	2N	3E	Lafayette	0-225-159-2020	1.1	4.1	1.6	9.3	35.1	2.586	2.665	3.055		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
RUEF 55-33-024-QRY Created On: 01/03/23 Updated On:	Q	SW	SE	11	2N	3E	Lafayette	0-225-8-2023	0.4	4.9	4.3	10.8	38.2	2.551	2.632	3.191		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
W.E. ROCK 55-33-029-QRY Created On: 04/13/21 Updated On:	Q	NE	NE	30	1N	1E	Lafayette	0-225-182-2021	0.0	3.6	1.6	16.1	44.6	2.594	2.664	2.668		
	Approved Use : CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse					
	P/Q	Qrt	Qrt	Sect	Town	Range	County	LA Wear (%) 100					500	Sp. Gravity OD	SSD	Absorp. % Crse	Fine	
LAFAYETTE -- WI																		
W.E. ROCK 55-33-029-QRY Created On: 01/29/24 Updated On:	Q	NE	NE	30	1N	1E	Lafayette	0-225-151-2024	0.2	4.1	4.6	8.7	34.9	2.552	2.640	3.426		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
LANGLADE -- WI																		
*AINSWORTH 55-34-001-PIT Created On: 07/31/14 Updated On:	P	SW	SW	1	33N	12E	Langlade	0-225-234-2014		0.0	1.7	3.7	16.9	2.690	2.715	0.919		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
*AINSWORTH 55-34-001-PIT Created On: 01/04/19 Updated On:	P	SW	SW	1	33N	12E	Langlade	0-225-13-2019	0.0	0.0	0.2	5.3	22.9	2.693	2.709	0.613		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
ANTIGO 55-34-002-PIT Created On: 01/06/14 Updated On:	P	SE	NE	13	31N	11E	Langlade	0-225-21-2014		0.0	0.5	4.6	22.0	2.679	2.697	0.693		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
ANTIGO 55-34-002-PIT Created On: 01/04/19 Updated On:	P	SE	NE	13	31N	11E	Langlade	0-225-15-2019	0.0	0.7	1.4	7.8	32.6	2.650	2.672	0.802		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
ANTIGO 55-34-002-PIT Created On: 01/02/24 Updated On:	P	SE	NE	13	31N	11E	Langlade	0-225-11-2024	0.2	0.0	0.2	6.6	27.5	2.676	2.695	0.719		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
BENES 55-34-004-PIT Created On: 07/18/19 Updated On:	P	SW	NE	8	32N	11E	Langlade	0-225-241-2019	0.1	0.0	0.5	4.6	20.5	2.709	2.735	0.935		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Coarse Sp. Gravity		Coarse Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
LANGLADE -- WI																		
BENES 55-34-004-PIT Created On: 01/02/24 Updated On:	P	SW	NE	8	32N	11E	Langlade	0-225-63-2024	0.1	0.0	2.0	5.2	22.0	2.719	2.747	1.035		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
BRIGGS PIT 55-34-008-PIT Created On: 08/20/19 Updated On:	P	SW	NE	1	34N	10E	Langlade	0-225-263-2019	0.6	0.0	1.1	4.3	19.0	2.680	2.703	0.860		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
BRIGGS PIT 55-34-008-PIT Created On: 04/24/23 Updated On:	P	SW	NE	1	34N	10E	Langlade	0-225-207-2023	0.2	0.0	0.7	4.8	22.0	2.691	2.711	0.762		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
HESS 55-34-014-PIT Created On: 01/08/16 Updated On:	P	SW	SW	2	30N	11E	Langlade	0-225-45-2016		0.0	1.8	5.8	27.2	2.677	2.695	0.664		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
HESS 55-34-014-PIT Created On: 01/04/21 Updated On:	P	SW	SW	2	30N	11E	Langlade	0-225-15-2021	0.0	0.6	0.8	5.6	25.3	2.680	2.711	1.180		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
KOEPEL 55-34-015-PIT Created On: 06/13/22 Updated On:	P		NW	12	30N	12E	Langlade	0-225-228-2022	0.0	0.5	0.3	6.6	29.3	2.671	2.691	0.743		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
*MEVERDAN MATERIALS HWY T 55-34-026-PIT Created On: 07/18/19 Updated On:	P	SW	SW	2	33N	9E	Langlade	0-225-238-2019	0.7	0.0	1.3	5.2	21.1	2.666	2.693	1.031		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse					
	P/Q	Qrt	Qrt	Sect	Town	Range	County	LA Wear (%) 100					500	Sp. Gravity OD	SSD	Absorp. % Crse	Fine	
LANGLADE -- WI																		
SAMBS STONE 55-34-022-PIT Created On: 03/09/15 Updated On:	P	NW	NW	11	30N	11E	Langlade	0-225-94-2015		0.0	1.6	6.2	26.7	2.675	2.698	0.884		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
SAMBS STONE 55-34-022-PIT Created On: 01/07/20 Updated On:	P	NW	NW	11	30N	11E	Langlade	0-225-46-2020		0.0	1.6	0.5	6.9	29.4	2.687	2.706	0.724	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
WOLF RIVER 55-34-025-PIT Created On: 05/26/16 Updated On:	P	NW	SW	36	31N	14E	Langlade	0-225-189-2016		0.4	0.0	2.1	7.7	26.8	2.635	2.658	0.870	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
WOLF RIVER 55-34-025-PIT Created On: 01/04/21 Updated On:	P	NW	SW	36	31N	14E	Langlade	0-225-14-2021		0.0	0.4	0.3	4.1	23.0	2.664	2.684	0.772	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
LINCOLN -- WI																		
*BEYER 55-35-042-PIT Created On: 01/04/19 Updated On:	P			33	31N	8E	Lincoln	0-225-5-2019		0.7	0.0	4.4	7.3	28.7	2.614	2.656	1.613	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
BROCK 55-35-003-PIT Created On: 03/09/15 Updated On:	P		NE	29	31N	7E	Lincoln	0-225-93-2015		0.0	3.2	4.1	19.0	2.685	2.714	1.094		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
BROCK 55-35-003-PIT Created On: 01/08/20 Updated On:	P		NE	29	31N	7E	Lincoln	0-225-47-2020		0.0	2.0	0.5	6.0	24.4	2.690	2.715	0.948	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse				
	P/Q	Qrt	Qrt	Sect	Town	Range	County					LA Wear (%)		Sp. Gravity		Absorp. %
											100	500	OD	SSD	Crse	Fine
LINCOLN -- WI																
COOMBS 55-35-004-PIT Created On: 01/03/18 Updated On:	P			16	34N	7E	Lincoln	0-225-4-2018	0.2	0.0	1.2	4.3	21.1	2.724	2.745	0.766
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate															
COOMBS 55-35-004-PIT Created On: 05/22/23 Updated On:	P			16	34N	7E	Lincoln	0-225-224-2023	0.3	0.0	2.8	4.5	20.3	2.749	2.773	0.858
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate															
COOMBS SOUTH 55-35-005-PIT Created On: 05/10/18 Updated On:	P		NW	21	34N	7E	Lincoln	0-225-204-2018	1.3	0.0	1.4	4.7	22.9	2.709	2.732	0.819
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate															
COOMBS SOUTH 55-35-005-PIT Created On: 01/02/24 Updated On:	P		NW	21	34N	7E	Lincoln	0-225-67-2024	0.3	2.9	3.2	4.2	20.5	2.683	2.714	1.138
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate															
CTH R 55-35-009-PIT Created On: 07/07/14 Updated On:	P	SE	NE	7	32N	7E	Lincoln	0-225-209-2014		0.0	1.5	4.3	20.3	2.744	2.773	1.068
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate															
CTH R 55-35-009-PIT Created On: 07/26/21 Updated On:	P	SE	NE	7	32N	7E	Lincoln	0-225-251-2021	0.4	0.0	5.1	4.7	21.3	2.715	2.748	1.217
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate															
DALKA 55-35-043-PIT Created On: 04/24/19 Updated On:	P	SW	SW	3	35N	8E	Lincoln	0-225-170-2019	0.6	0.0	0.3	4.6	21.5	2.671	2.694	0.868
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate															

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Coarse Sp. Gravity		Coarse Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
LINCOLN -- WI																		
DALKA 55-35-043-PIT Created On: 01/02/24 Updated On:	P	SW	SW	3	35N	8E	Lincoln	0-225-66-2024	0.0	0.0	1.3	4.3	18.7	2.699	2.724	0.917		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
EVERSON PIT 55-35-044-PIT Created On: 01/02/24 Updated On:	P	SE	SW	2	35N	8E	Lincoln	0-225-58-2024	0.3	0.0	0.2	3.4	16.1	2.735	2.753	0.641		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
JAECKS 55-35-027-PIT Created On: 06/25/20 Updated On:	P	SE	SW	1	34N	6E	Lincoln	0-225-208-2020	0.3	0.0	0.5	4.6	21.3	2.689	2.718	1.096		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
*LATZIG 55-35-024-PIT Created On: 07/07/14 Updated On:	P	SW	NW	31	33N	8E	Lincoln	0-225-214-2014		0.0	0.9	3.2	17.7	2.685	2.714	1.085		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
*LATZIG 55-35-024-PIT Created On: 01/04/19 Updated On:	P	SW	NW	31	33N	8E	Lincoln	0-225-4-2019	0.7	0.0	2.7	4.2	19.4	2.673	2.708	1.311		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
LINCOLN CTH W 55-35-041-PIT Created On: 01/02/20 Updated On:	P	E	SW	33	31N	7E	Lincoln	0-225-11-2020	3.2	0.0	6.2	5.1	22.7	2.613	2.655	1.617		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
PETERSON 55-35-029-PIT Created On: 07/16/20 Updated On:	P	NW	SE	30	32N	6E	Lincoln	0-225-218-2020	1.4	0.0	0.8	4.2	20.6	2.688	2.717	1.087		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse					
	P/Q	Qrt	Qrt	Sect	Town	Range	County	LA Wear (%) 100 500					Sp. Gravity OD SSD	Absorp. % Crse Fine				
LINCOLN -- WI																		
PINE RIDGE 55-35-030-PIT Created On: 05/11/15 Updated On:	P	NW	SW	8	31N	7E	Lincoln	0-225-168-2015		0.0	0.9	4.5	19.8	2.675	2.708	1.256		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
PINE RIDGE 55-35-030-PIT Created On: 05/12/20 Updated On:	P	NW	SW	8	31N	7E	Lincoln	0-225-176-2020	1.9	0.0	2.3	4.4	20.6	2.679	2.708	1.085		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MANITOWOC -- WI																		
AGGRECON 55-36-001-QRY Created On: 06/03/15 Updated On:	Q		SE	33	17N	21E	Manitowoc	0-225-182-2015	1.5	0.0	1.4	7.6	32.9	2.719	2.751	1.152		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
AGGRECON 55-36-001-QRY Created On: 02/15/18 Updated On:	Q		SE	33	17N	21E	Manitowoc	0-225-99-2018	0.9	3.3	2.7	6.6	32.2	2.745	2.770	0.917		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
AGGRECON 55-36-001-QRY Created On: 01/04/21 Updated On:	Q		SE	33	17N	21E	Manitowoc	0-225-43-2021	0.3	1.2	0.3	5.3	25.5	2.764	2.785	0.755		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
AGGRECON 55-36-001-QRY Created On: 01/29/24 Updated On:	Q		SE	33	17N	21E	Manitowoc	0-225-166-2024	0.0	0.9	1.2	6.4	29.4	2.780	2.799	0.659		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
BADGERLAND 55-36-031-PIT Created On: 05/01/14 Updated On:	P			33	21N	23E	Manitowoc	0-225-156-2014	3.6	0.0	0.0	7.0	33.1	2.698	2.739	1.504		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse					
	P/Q	Qrt	Qrt	Sect	Town	Range	County	LA Wear (%) 100					500	Sp. Gravity OD SSD		Absorp. % Crse Fine		
MANITOWOC -- WI BADGERLAND-SHOTO 55-36-005-QRY Created On: 01/25/19 Updated On:	Q	SE	SW	20	20N	24E	Manitowoc	0-225-92-2019		0.0	4.1	8.5	32.5	2.746	2.781	1.284		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
BADGERLAND-SHOTO 55-36-005-QRY Created On: 01/04/22 Updated On:	Q	SE	SW	20	20N	24E	Manitowoc	0-225-67-2022		0.0	0.0	8.5	7.9	32.3	2.785	2.806	0.771	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
BIESE 55-36-006-PIT Created On: 01/04/18 Updated On:	P	SW	NE	34	18N	21E	Manitowoc	0-225-83-2018		0.3	1.3	2.7	6.4	30.5	2.752	2.780	1.013	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
BIESE 55-36-006-PIT Created On: 01/02/24 Updated On:	P	SW	NE	34	18N	21E	Manitowoc	0-225-131-2024		2.2	4.7	3.6	9.5	34.1	2.730	2.764	1.220	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
*BLATZ 55-36-047-QRY Created On: 01/07/20 Updated On:	Q	SW	NE	35	17N	21E	Manitowoc	0-225-37-2020		0.1	0.0	2.4	6.3	28.3	2.769	2.792	0.815	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
*BLATZ-CAPSTONE 55-36-046-QRY Created On: 06/26/19 Updated On:	Q	SW	NE	33	17N	21E	Manitowoc	0-225-230-2019		0.6	1.3	1.4	6.1	27.8	2.761	2.785	0.885	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
BONDE 55-36-008-PIT Created On: 01/05/17 Updated On:	P		NE	5	17N	22E	Manitowoc	0-225-18-2017		0.9	1.9	2.2	8.0	33.1	2.768	2.790	0.797	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Coarse Sp. Gravity		Coarse Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
MANITOWOC -- WI																		
BONDE 55-36-008-PIT Created On: 04/28/22 Updated On:	P		NE	5	17N	22E	Manitowoc	0-225-184-2022	2.1	0.0	0.4	7.8	34.3	2.766	2.790	0.873		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
BROCKER 55-36-009-PIT Created On: 08/28/14 Updated On:	P	NW	SW	20	18N	21E	Manitowoc	0-225-248-2014	0.0	0.0	1.0	6.0	27.5	2.758	2.782	0.866		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
BROCKER 55-36-009-PIT Created On: 04/19/19 Updated On:	P	NW	SW	20	18N	21E	Manitowoc	0-225-147-2019	0.8	0.0	1.3	6.5	29.2	2.764	2.789	0.902		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
BROCKER 55-36-009-PIT Created On: 01/02/24 Updated On:	P	NW	SW	20	18N	21E	Manitowoc	0-225-51-2024	1.1	0.0	2.2	7.9	33.4	2.749	2.777	1.001		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
CAREW-MARIBEL 55-36-013-PIT Created On: 08/09/18 Updated On:	P	NE	NW	19	21N	22E	Manitowoc	0-225-267-2018	1.2	0.0	2.9	7.6	34.2	2.707	2.748	1.491		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
CAREW-MARIBEL 55-36-013-PIT Created On: 01/04/23 Updated On:	P	NE	NW	19	21N	22E	Manitowoc	0-225-102-2023	0.8	0.0	3.7	8.2	34.9	2.691	2.731	1.486		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
GRIMMS 55-36-015-QRY Created On: 01/04/16 Updated On:	Q	NE	SE	6	19N	22E	Manitowoc	0-225-6-2016		0.2	1.4	7.8	30.5	2.690	2.727	1.362		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
MANITOWOC -- WI																		
GRIMMS 55-36-015-QRY Created On: 05/09/19 Updated On:	Q	NE	SE	6	19N	22E	Manitowoc	0-225-182-2019	0.0	0.0	0.7	8.0	32.0	2.693	2.731	1.426		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
GRIMMS 55-36-015-QRY Created On: 01/04/22 Updated On:	Q	NE	SE	6	19N	22E	Manitowoc	0-225-33-2022	0.0	0.0	1.6	9.6	38.6	2.727	2.758	1.133		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
GRIMMS 55-36-015-QRY Created On: 01/02/24 Updated On:	Q	NE	SE	6	19N	22E	Manitowoc	0-225-102-2024	0.0	0.5	1.2	8.9	36.6	2.712	2.744	1.200		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
KOSSUTH QUARRY 55-36-048-QRY Created On: 03/28/18 Updated On:	Q	W	SE	36	20N	23E	Manitowoc	0-225-151-2018	0.0	0.8	0.4	7.4	33.2	2.794	2.811	0.633		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
KOSSUTH QUARRY 55-36-048-QRY Created On: 01/05/21 Updated On:	Q	W	SE	36	20N	23E	Manitowoc	0-225-106-2021	0.0	1.0	2.2	8.1	33.3	2.752	2.780	1.045		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
KOSSUTH QUARRY 55-36-048-QRY Created On: 01/04/24 Updated On:	Q	W	SE	36	20N	23E	Manitowoc	0-225-135-2024	0.0	0.0	0.8	10.1	37.8	2.766	2.790	0.852		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
LEMBERGER QUARRY 55-36-049-QRY Created On: 01/29/24 Updated On:	Q	SE	NE	34	20N	22E	Manitowoc	0-225-164-2024	0.2	0.0	0.6	9.6	34.6	2.716	2.747	1.116		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse								
	P/Q	Qrt	Qrt	Sect	Town	Range	County	LA Wear (%) 100					500	Sp. Gravity OD SSD		Absorp. % Crse Fine					
MANITOWOC -- WI																					
MICHELS - MISHICOT 55-36-025-PIT Created On: 01/05/21 Updated On:	P	SE	SE	27	21N	23E	Manitowoc	0-225-46-2021	0.8	0.0	3.6	6.0	29.8	2.698	2.741	1.612					
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																				
MISHICOT 55-36-027-PIT Created On: 01/12/16 Updated On:	P	NE	SE	27	21N	23E	Manitowoc	0-225-55-2016		0.0	1.3	6.1	28.9	2.727	2.757	1.109					
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																				
MISHICOT 55-36-027-PIT Created On: 01/05/21 Updated On:	P	NE	SE	27	21N	23E	Manitowoc	0-225-105-2021	0.0	3.7	0.9	5.7	27.3	2.675	2.721	1.710					
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																				
*OLM 55-36-030-PIT Created On: 04/18/19 Updated On:	P	E	NE	9	18N	21E	Manitowoc	0-225-137-2019	0.8	2.7	0.4	8.5	31.1	2.763	2.788	0.920					
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																				
*REESE 55-36-034-PIT Created On: 06/26/19 Updated On:	P	SW	SW	22	17N	21E	Manitowoc	0-225-228-2019	1.1	2.2	0.8	5.4	29.4	2.753	2.776	0.833					
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																				
ROCKWELL LIMESTONE 55-36-035-QRY Created On: 04/13/16 Updated On:	Q			36	20N	23E	Manitowoc	0-225-146-2016		0.0	2.0	12.6	41.7	2.693	2.735	1.577					
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																				
ROCKWELL LIMESTONE 55-36-035-QRY Created On: 04/19/19 Updated On:	Q			36	20N	23E	Manitowoc	0-225-148-2019		0.0	2.9	12.7	42.1	2.692	2.739	1.722					
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																				

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Coarse Sp. Gravity		Coarse Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
MANITOWOC -- WI																		
ROCKWELL LIMESTONE 55-36-035-QRY Created On: 03/07/22 Updated On:	Q			36	20N	23E	Manitowoc	0-225-137-2022	0.0	0.0	3.0	9.6	32.0	2.728	2.759	1.126		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
SCHOOL HILL 55-36-036-PIT Created On: 04/17/14 Updated On:	P	NE	NW	16	17N	22E	Manitowoc	0-225-130-2014	0.5	0.0	1.3	6.4	27.3	2.761	2.783	0.812		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
SCHOOL HILL 55-36-036-PIT Created On: 04/19/19 Updated On:	P	NE	NW	16	17N	22E	Manitowoc	0-225-146-2019	0.6	2.1	0.5	7.2	29.7	2.786	2.807	0.767		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
SCHOOL HILL 55-36-036-PIT Created On: 01/02/24 Updated On:	P	NE	NW	16	17N	22E	Manitowoc	0-225-130-2024	0.0	2.0	0.7	6.4	30.1	2.785	2.806	0.764		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
SCOTT CONSTRUCTION - COOPERSTOWN 55-36-044-QRY Created On: 05/30/17 Updated On:	Q	W	NW	19	21N	22E	Manitowoc	0-225-200-2017	11.6	0.0	6.4	6.1	26.7	2.673	2.722	1.843		
	Approved Use : HMA<MT, HMA>=MT, Base Aggregate																	
SCOTT CONSTRUCTION - COOPERSTOWN 55-36-044-QRY Created On: 02/28/23 Updated On:	Q	W	NW	19	21N	22E	Manitowoc	0-225-157-2023	9.6	5.6	5.2	5.8	27.5	2.665	2.712	1.737		
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																	
ST NAZIANZ 55-36-043-PIT Created On: 01/05/17 Updated On:	P		S	30	18N	22E	Manitowoc	0-225-20-2017	0.5	1.6	2.0	7.8	33.3	2.750	2.778	1.033		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse				
	P/Q	Qrt	Qrt	Sect	Town	Range	County					LA Wear (%)		Sp. Gravity		Absorp. %
											100	500	OD	SSD	Crse	Fine
MANITOWOC -- WI																
ST NAZIANZ 55-36-043-PIT Created On: 04/28/22 Updated On:	P		S	30	18N	22E	Manitowoc	0-225-185-2022	1.1	0.0	1.3	7.2	33.0	2.761	2.788	0.983
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate															
VALDERS 55-36-026-QRY Created On: 01/05/17 Updated On:	Q	SE	NE	32	19N	22E	Manitowoc	0-225-19-2017		0.0	0.8	9.4	39.7	2.730	2.755	0.932
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate															
VALDERS 55-36-026-QRY Created On: 03/09/20 Updated On:	Q	SE	NE	32	19N	22E	Manitowoc	0-225-122-2020	0.2	0.2	1.9	7.9	36.2	2.745	2.768	0.810
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate															
VALDERS 55-36-026-QRY Created On: 02/09/23 Updated On:	Q	SE	NE	32	19N	22E	Manitowoc	0-225-142-2023	0.0	0.0	1.5	7.9	35.3	2.740	2.762	0.806
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate															
MARATHON -- WI																
*3M 55-37-001-QRY Created On: 08/14/14 Updated On:	Q	NW	SE	11	29N	7E	Marathon	0-225-242-2014		0.0	2.5	3.7	16.2	2.812	2.833	0.760
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate															
*3M 55-37-001-QRY Created On: 09/19/19 Updated On:	Q	NW	SE	11	29N	7E	Marathon	0-225-272-2019	0.6	0.0	0.7	4.7	20.5	2.644	2.679	1.338
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate															
ATHENS 55-37-005-QRY Created On: 08/16/16 Updated On:	Q	S	SE	24	30N	4E	Marathon	0-225-243-2016		0.0	0.2	5.1	24.8	2.695	2.710	0.573
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate															

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse						
	P/Q	Qrt	Qrt	Sect	Town	Range	County	LA Wear (%) 100					500	Sp. Gravity OD	SSD	Absorp. % Crse	Fine		
MARATHON -- WI																			
ATHENS 55-37-005-QRY Created On: 05/10/18 Updated On:	Q	S	SE	24	30N	4E	Marathon	0-225-203-2018		0.0	0.2	3.0	16.1	2.837	2.845	0.255			
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
ATHENS 55-37-005-QRY Created On: 01/05/21 Updated On:	Q	S	SE	24	30N	4E	Marathon	0-225-87-2021		0.0	0.0	0.6	4.8	23.1	2.711	2.724	0.492		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
ATHENS 55-37-005-QRY Created On: 01/02/24 Updated On:	Q	S	SE	24	30N	4E	Marathon	0-225-81-2024		0.0	0.0	0.3	5.4	25.3	2.708	2.718	0.397		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
BEVENT 55-37-008-PIT Created On: 09/24/14 Updated On:	P	SW	NW	5	26N	9E	Marathon	0-225-264-2014		0.0	1.0	7.4	30.8	2.639	2.673	1.259			
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																		
BEVENT 55-37-008-PIT Created On: 04/30/21 Updated On:	P	SW	NW	5	26N	9E	Marathon	0-225-196-2021		2.0	0.0	0.6	5.8	26.5	2.654	2.675	0.771		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
*BLACKBERRY 55-37-015-QRY Created On: 05/11/15 Updated On:	Q	SW	NE	36	28N	2E	Marathon	0-225-169-2015		0.0	0.1	5.6	29.1	2.561	2.586	0.956			
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																		
*BLACKBERRY 55-37-015-QRY Created On: 05/02/19 Updated On:	Q	SW	NE	36	28N	2E	Marathon	0-225-177-2019		0.1	0.0	1.2	6.6	29.1	2.582	2.601	0.725		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																		

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Coarse Sp. Gravity		Coarse Absorp. %			
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine		
MARATHON -- WI																			
BOHLMON 55-37-009-PIT Created On: 05/01/18 Updated On:	P		SE	36	28N	10E	Marathon	0-225-187-2018		0.6	2.1	7.5	30.8	2.653	2.682	1.105			
	Approved Use : HMA<MT, HMA>=MT, Base Aggregate																		
BOHLMON 55-37-009-PIT Created On: 01/03/23 Updated On:	P		SE	36	28N	10E	Marathon	0-225-16-2023		0.0	0.4	8.6	33.4	2.646	2.673	1.028			
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																		
CISLER 55-37-016-QRY Created On: 01/06/16 Updated On:	Q	NW	NW	5	26N	7E	Marathon	0-225-29-2016		0.0	0.5	3.9	17.2	2.680	2.691	0.411			
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																		
CISLER 55-37-016-QRY Created On: 01/04/19 Updated On:	Q	NW	NW	5	26N	7E	Marathon	0-225-32-2019		0.0	0.2	2.6	13.6	2.683	2.691	0.319			
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																		
CISLER 55-37-016-QRY Created On: 04/01/19 Updated On:	Q	NW	NW	5	26N	7E	Marathon	0-225-121-2019		0.0	0.0	0.4	4.3	18.4	2.678	2.688	0.350		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																		
CISLER 55-37-016-QRY Created On: 01/04/22 Updated On:	Q	NW	NW	5	26N	7E	Marathon	0-225-37-2022		0.0	1.3	1.9	4.2	18.7	2.660	2.677	0.650		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
COLDSPRING QUARRY 55-37-099-QRY Created On: 01/29/24 Updated On:	Q	SW	SE	34	30N	8E	Marathon	0-225-154-2024		0.2	0.0	1.2	7.1	32.9	2.597	2.612	0.590		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse					
	P/Q	Qrt	Qrt	Sect	Town	Range	County	LA Wear (%)					Sp. Gravity		Absorp. %			
												100	500	OD	SSD	Crse	Fine	
MARATHON -- WI																		
CTH "N" / MILESTONE 345 55-37-021-QRY Created On: 01/06/16 Updated On:	Q	NW	NE	19	28N	7E	Marathon	0-225-30-2016		0.0	0.5	11.3	45.4	2.579	2.600	0.795		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
CTH "N" / MILESTONE 345 55-37-021-QRY Created On: 01/04/19 Updated On:	Q	NW	NE	19	28N	7E	Marathon	0-225-34-2019		0.0	0.0	0.7	9.8	42.2	2.276	2.286	0.431	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
CTH "N" / MILESTONE 345 55-37-021-QRY Created On: 01/04/22 Updated On:	Q	NW	NE	19	28N	7E	Marathon	0-225-25-2022		0.0	0.2	0.6	7.6	36.6	2.603	2.617	0.563	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
H&H 55-37-096-QRY Created On: 01/19/23 Updated On:	Q	NW	SW	5	28N	6E	Marathon	0-225-124-2023		0.2	2.6	1.0	4.7	19.0	2.627	2.670	1.619	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
KAFKA QUARRY 55-37-039-QRY Created On: 01/03/17 Updated On:	Q	NE	NW	3	27N	3E	Marathon	0-225-6-2017		0.0	0.5	2.0	10.6	2.776	2.785	0.325		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
KAFKA QUARRY 55-37-039-QRY Created On: 01/07/20 Updated On:	Q	NE	NW	3	27N	3E	Marathon	0-225-42-2020		0.0	0.0	0.1	2.5	10.8	2.800	2.805	0.201	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
KAFKA QUARRY 55-37-039-QRY Created On: 01/03/23 Updated On:	Q	NE	NW	3	27N	3E	Marathon	0-225-37-2023		0.0	0.8	0.6	3.5	14.6	2.749	2.766	0.638	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Coarse Sp. Gravity		Coarse Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
MARATHON -- WI																		
KAFKA ROAD MATERIALS 55-37-097-QRY Created On: 05/09/23 Updated On:	Q	NE	SW	20	27N	6E	Marathon	0-225-216-2023	0.3	0.0	1.8	8.8	37.4	2.554	2.582	1.083		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
KAFKA ROAD MATERIALS 55-37-097-QRY Created On: 03/13/24 Updated On:	Q	NE	SW	20	27N	6E	Marathon	0-225-201-2024	0.0	0.0	1.1	7.3	28.7	2.571	2.596	0.979		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MARTIN ROAD 55-37-091-QRY Created On: 06/26/19 Updated On:	Q	SE	SE	6	27N	9E	Marathon	0-225-232-2019	1.3	0.0	1.3	9.6	38.3	2.591	2.609	0.713		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
MARTIN ROAD 55-37-091-QRY Created On: 02/17/22 Updated On:	Q	SE	SE	6	27N	9E	Marathon	0-225-132-2022	0.0	0.0	0.5	6.8	33.7	2.610	2.623	0.500		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MATTHIAE 55-37-047-PIT Created On: 03/13/23 Updated On:	P	SE	SE	35	29N	5E	Marathon	0-225-167-2023	0.3	0.0	1.8	3.3	15.5	2.764	2.786	0.796		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
*MEADOW LANE 55-37-089-PIT Created On: 01/04/19 Updated On:	P		NE	8	25N	10E	Marathon	0-225-36-2019	0.1	0.0	1.8	9.8	35.1	2.674	2.698	0.885		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
*MEVERDEN MATERIALS 55-37-048-QRY Created On: 01/22/16 Updated On:	Q	NE	SW	19	28N	7E	Marathon	0-225-76-2016		0.0	0.5	8.1	36.7	2.594	2.622	1.074		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Coarse Sp. Gravity		Coarse Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
MARATHON -- WI																		
*MEVERDEN MATERIALS 55-37-048-QRY Created On: 05/09/19 Updated On:	Q	NE	SW	19	28N	7E	Marathon	0-225-185-2019	0.0	0.0	0.6	9.4	40.9	2.616	2.635	0.702		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
MICHELS-RIB 55-37-093-QRY Created On: 01/04/22 Updated On:	Q	SW	SE	9	30N	7E	Marathon	0-225-16-2022	0.0	0.0	0.8	7.7	32.4	2.579	2.597	0.687		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MITCH KING 55-37-051-PIT Created On: 01/07/14 Updated On:	P	SW	NE	6	26N	9E	Marathon	0-225-38-2014		0.0	3.4	9.5	35.0	2.596	2.630	1.277		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
MITCH KING 55-37-051-PIT Created On: 01/03/17 Updated On:	P	SW	NE	6	26N	9E	Marathon	0-225-3-2017		0.0	2.2	8.2	33.4	2.619	2.650	1.173		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
MITCH KING 55-37-051-PIT Created On: 02/17/22 Updated On:	P	SW	NE	6	26N	9E	Marathon	0-225-133-2022	1.3	0.0	2.5	9.0	34.2	2.628	2.655	1.035		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MORGAN 55-37-052-PIT Created On: 07/31/14 Updated On:	P	SE	SW	35	29N	5E	Marathon	0-225-237-2014		0.0	2.7	4.7	21.9	2.644	2.681	1.409		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
MORGAN 55-37-052-PIT Created On: 04/05/19 Updated On:	P	SE	SW	35	29N	5E	Marathon	0-225-123-2019	0.6	0.0	0.8	5.1	21.5	2.642	2.673	1.161		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse					
	P/Q	Qrt	Qrt	Sect	Town	Range	County	LA Wear (%) 100 500					Sp. Gravity OD SSD		Absorp. % Crse Fine			
MARATHON -- WI																		
MORGAN 55-37-052-PIT Created On: 01/02/24 Updated On:	P	SE	SW	35	29N	5E	Marathon	0-225-57-2024	0.6	0.0	1.6	3.8	20.9	2.615	2.650	1.356		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MROCZINSKI 55-37-054-PIT Created On: 04/24/19 Updated On:	P	SW	NW	16	29N	5E	Marathon	0-225-169-2019	0.0	0.0	0.2	3.5	17.8	2.638	2.656	0.675		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
MROCZINSKI 55-37-054-PIT Created On: 01/02/24 Updated On:	P	SW	NW	16	29N	5E	Marathon	0-225-60-2024	0.0	0.0	6.9	6.3	25.7	2.637	2.673	1.372		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
PAUL BUGAR "N" 55-37-057-QRY Created On: 05/21/15 Updated On:	Q	N	NE	2	27N	2E	Marathon	0-225-176-2015		0.0	1.2	4.5	22.0	2.573	2.603	1.159		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
PAUL BUGAR "N" 55-37-057-QRY Created On: 04/25/18 Updated On:	Q	N	NE	2	27N	2E	Marathon	0-225-184-2018		0.0	0.2	5.0	23.3	2.617	2.631	0.534		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
PAUL BUGAR "N" 55-37-057-QRY Created On: 06/17/21 Updated On:	Q	N	NE	2	27N	2E	Marathon	0-225-228-2021	0.3	0.0	0.7	6.7	30.4	2.597	2.616	0.747		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
PAUL BUGAR "N" 55-37-057-QRY Created On: 02/28/24 Updated On:	Q	N	NE	2	27N	2E	Marathon	0-225-193-2024	0.1	0.0	0.6	5.3	24.7	2.607	2.621	0.550		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse						
	P/Q	Qrt	Qrt	Sect	Town	Range	County	LA Wear (%) 100 500					Sp. Gravity OD SSD		Absorp. % Crse Fine				
MARATHON -- WI																			
PAUL BUGAR "R" 55-37-058-QRY Created On: 05/21/15 Updated On:	Q	NE	NW	1	27N	2E	Marathon	0-225-177-2015		0.0	0.9	4.7	23.1	2.626	2.654	1.037			
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																		
PAUL BUGAR "R" 55-37-058-QRY Created On: 04/25/18 Updated On:	Q	NE	NW	1	27N	2E	Marathon	0-225-183-2018		0.1	0.0	0.6	5.2	25.9	2.593	2.610	0.655		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																		
PAUL BUGAR "R" 55-37-058-QRY Created On: 06/17/21 Updated On:	Q	NE	NW	1	27N	2E	Marathon	0-225-227-2021		0.0	0.0	0.3	5.5	26.8	2.607	2.618	0.450		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
PAUL BUGAR "R" 55-37-058-QRY Created On: 02/28/24 Updated On:	Q	NE	NW	1	27N	2E	Marathon	0-225-194-2024		0.0	0.0	0.3	7.3	32.2	2.601	2.618	0.644		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
RC HOGARTY 55-37-092-QRY Created On: 07/01/21 Updated On:	Q	SW	SE	32	30N	10E	Marathon	0-225-241-2021		0.1	0.0	1.0	6.7	34.0	2.656	2.673	0.648		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
RC HOGARTY 55-37-092-QRY Created On: 01/29/24 Updated On:	Q	SW	SE	32	30N	10E	Marathon	0-225-155-2024		0.0	0.0	0.6	11.8	38.5	2.676	2.685	0.360		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
*RED ROCK GRANITE 55-37-063-QRY Created On: 07/01/21 Updated On:	Q	N	NW	19	27N	6E	Marathon	0-225-238-2021		0.0	0.0	2.2	10.7	44.0	2.594	2.613	0.722		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
MARATHON -- WI																		
RESCH 55-37-066-PIT Created On: 01/05/17 Updated On:	P	NW	NW	1	29N	10E	Marathon	0-225-16-2017		0.0	2.8	8.3	32.8	2.651	2.672	0.760		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
RESCH 55-37-066-PIT Created On: 05/17/22 Updated On:	P	NW	NW	1	29N	10E	Marathon	0-225-202-2022	0.0	0.0	2.8	8.7	33.5	2.636	2.663	1.047		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
*RIVER 55-37-069-PIT Created On: 06/19/14 Updated On:	P	NW	SE	9	27N	7E	Marathon	0-225-201-2014		0.0	1.1	3.8	18.9	2.634	2.661	1.031		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
*RIVER 55-37-069-PIT Created On: 04/19/19 Updated On:	P	NW	SE	9	27N	7E	Marathon	0-225-152-2019	0.6	0.0	1.0	4.0	19.0	2.634	2.662	1.062		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
ROSE 55-37-071-QRY Created On: 01/06/14 Updated On:	Q	NE	NW	36	30N	8E	Marathon	0-225-31-2014		0.1	0.3	6.4	27.3	2.601	2.615	0.539		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
ROSE 55-37-071-QRY Created On: 01/05/17 Updated On:	Q	NE	NW	36	30N	8E	Marathon	0-225-39-2017		0.0	0.2	6.0	26.7	2.615	2.625	0.399		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
ROSE 55-37-071-QRY Created On: 01/03/20 Updated On:	Q	NE	NW	36	30N	8E	Marathon	0-225-14-2020	0.0	0.0	0.5	6.9	32.0	2.598	2.614	0.622		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse					
	P/Q	Qrt	Qrt	Sect	Town	Range	County	LA Wear (%) 100 500					Sp. Gravity OD SSD		Absorp. % Crse Fine			
MARATHON -- WI																		
ROSE 55-37-071-QRY Created On: 01/03/23 Updated On:	Q	NE	NW	36	30N	8E	Marathon	0-225-19-2023	0.0	0.0	0.3	6.6	29.7	2.605	2.621	0.603		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
RUBY 55-37-072-QRY Created On: 01/06/14 Updated On:	Q	SE	NW	22	30N	7E	Marathon	0-225-30-2014		0.2	0.5	7.5	32.5	2.577	2.596	0.732		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
RUBY 55-37-072-QRY Created On: 01/05/17 Updated On:	Q	SE	NW	22	30N	7E	Marathon	0-225-38-2017		0.0	0.8	5.7	26.7	2.598	2.611	0.485		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
RUBY 55-37-072-QRY Created On: 01/03/20 Updated On:	Q	SE	NW	22	30N	7E	Marathon	0-225-13-2020		0.0	1.1	8.0	37.1	2.581	2.602	0.827		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
RUBY 55-37-072-QRY Created On: 01/03/23 Updated On:	Q	SE	NW	22	30N	7E	Marathon	0-225-18-2023	0.0	0.0	0.6	5.8	28.0	2.596	2.613	0.650		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
SIEKIERZYNSKI 55-37-094-PIT Created On: 06/13/22 Updated On:	P	SW	NE	29	27N	9E	Marathon	0-225-216-2022	0.5	0.0	1.0	7.9	32.2	2.614	2.645	1.188		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
SIEKIERZYNSKI 55-37-095-QRY Created On: 06/13/22 Updated On:	Q	SW	NE	29	27N	9E	Marathon	0-225-217-2022	0.1	0.0	0.9	7.6	34.2	2.643	2.659	0.630		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse					
	P/Q	Qrt	Qrt	Sect	Town	Range	County	LA Wear (%) 100 500					Sp. Gravity OD SSD		Absorp. % Crse Fine			
MARATHON -- WI STROETZ 55-37-075-QRY Created On: 03/21/18 Updated On:	Q	SW	NW	10	26N	3E	Marathon	0-225-131-2018	0.0	2.9	6.2	28.0	2.593	2.616	0.874			
	Approved Use : HMA<MT, HMA>=MT, Base Aggregate																	
STROETZ 55-37-075-QRY Created On: 06/28/22 Updated On:	Q	SW	NW	10	26N	3E	Marathon	0-225-241-2022	0.0	1.7	7.6	29.3	2.592	2.620	1.073			
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																	
SZEWS 55-37-077-PIT Created On: 09/15/16 Updated On:	P	SW	SW	4	28N	10E	Marathon	0-225-257-2016	0.0	0.4	8.2	32.3	2.669	2.689	0.741			
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
SZEWS 55-37-077-PIT Created On: 01/04/21 Updated On:	P	SW	SW	4	28N	10E	Marathon	0-225-17-2021	0.0	0.4	0.4	6.9	30.9	2.669	2.691	0.807		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
THURS 55-37-090-QRY Created On: 04/05/19 Updated On:	Q	NE	SW	27	29N	5E	Marathon	0-225-124-2019	0.0	1.4	4.2	18.4	2.715	2.736	0.766			
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
THURS 55-37-090-QRY Created On: 04/11/22 Updated On:	Q	NE	SW	27	29N	5E	Marathon	0-225-172-2022	0.0	0.0	0.6	3.2	14.1	2.769	2.780	0.397		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
WEISENBERGER 55-37-083-QRY Created On: 01/06/16 Updated On:	Q		N	1	28N	5E	Marathon	0-225-32-2016	0.0	0.9	4.5	19.3	2.689	2.720	1.154			
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse					
	P/Q	Qrt	Qrt	Sect	Town	Range	County					LA Wear (%)		Sp. Gravity		Absorp. %	
											100	500	OD	SSD	Crse	Fine	
MARATHON -- WI																	
WEISENBERGER 55-37-083-QRY Created On: 01/04/19 Updated On:	Q		N	1	28N	5E	Marathon	0-225-35-2019		0.0	0.4	4.8	19.6	2.673	2.712	1.471	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
WEISENBERGER 55-37-083-QRY Created On: 01/13/22 Updated On:	Q		N	1	28N	5E	Marathon	0-225-109-2022		0.0	0.3	0.2	4.5	17.7	2.829	2.846	0.615
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
ZIOLKOWSKI 55-37-087-PIT Created On: 01/02/18 Updated On:	P	SW	SE	29	27N	9'E	Marathon	0-225-3-2018		0.6	0.0	1.0	7.0	30.2	2.647	2.672	0.940
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
ZIOLKOWSKI 55-37-087-PIT Created On: 01/02/24 Updated On:	P	SW	SE	29	27N	9'E	Marathon	0-225-44-2024		0.7	1.4	4.8	7.5	32.2	2.645	2.670	0.970
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
MARINETTE -- WI																	
BEAVER 55-38-003-QRY Created On: 03/07/14 Updated On:	Q	NE	NE	26	31N	20E	Marinette	0-225-94-2014		1.0	3.1	6.3	27.4	2.726	2.758	1.181	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
BEAVER 55-38-003-QRY Created On: 06/13/22 Updated On:	Q	NE	NE	26	31N	20E	Marinette	0-225-223-2022		5.6	10.7	5.8	10.6	37.9	2.627	2.679	1.973
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																
BEECHER 55-38-004-PIT Created On: 07/26/23 Updated On:	P	NW	NE	20	36N	21E	Marinette	0-225-239-2023		1.1	0.0	6.2	27.3	2.716	2.745	1.072	
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse					
	P/Q	Qrt	Qrt	Sect	Town	Range	County					LA Wear (%)		Sp. Gravity		Absorp. %	
											100	500	OD	SSD	Crse	Fine	
MARINETTE -- WI																	
BIEHL 55-38-007-QRY Created On: 01/08/16 Updated On:	Q		SE	4	31N	22E	Marinette	0-225-44-2016		7.6	4.9	7.9	34.4	2.675	2.711	1.343	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
BIEHL 55-38-007-QRY Created On: 05/24/19 Updated On:	Q		SE	4	31N	22E	Marinette	0-225-197-2019		0.0	12.3	2.3	9.0	35.0	2.684	2.720	1.314
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
BIEHL 55-38-007-QRY Created On: 05/17/22 Updated On:	Q		SE	4	31N	22E	Marinette	0-225-206-2022		0.0	8.4	2.3	9.5	37.4	2.654	2.704	1.876
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
BIEHL 11TH ROAD 55-38-008-QRY Created On: 01/06/14 Updated On:	Q	NW	NW	19	30N	21E	Marinette	0-225-18-2014		2.1	0.3	5.9	27.1	2.727	2.757	1.100	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
BIEHL 11TH ROAD 55-38-008-QRY Created On: 01/05/17 Updated On:	Q	NW	NW	19	30N	21E	Marinette	0-225-53-2017		1.0	0.9	5.9	25.9	2.726	2.762	1.322	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
BIEHL 11TH ROAD 55-38-008-QRY Created On: 07/15/20 Updated On:	Q	NW	NW	19	30N	21E	Marinette	0-225-213-2020		0.0	0.9	1.3	4.1	25.9	2.723	2.754	1.157
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
BIEHL 11TH ROAD 55-38-008-QRY Created On: 01/03/23 Updated On:	Q	NW	NW	19	30N	21E	Marinette	0-225-48-2023		0.1	2.3	1.3	7.7	30.3	2.717	2.750	1.219
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse					
	P/Q	Qrt	Qrt	Sect	Town	Range	County	LA Wear (%) 100 500					Sp. Gravity OD SSD		Absorp. % Crse Fine			
MARINETTE -- WI																		
BIEHL 9TH ROAD 55-38-007-PIT Created On: 01/04/18 Updated On:	P	S	NW	18	30N	21E	Marinette	0-225-85-2018	0.9	0.0	3.5	5.1	26.3	2.711	2.741	1.131		
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
BIEHL 9TH ROAD 55-38-007-PIT Created On: 01/03/23 Updated On:	P	S	NW	18	30N	21E	Marinette	0-225-34-2023		4.7	1.9	5.9	25.7	2.686	2.720	1.250		
Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																		
*CRIVITZ 55-38-043-PIT Created On: 03/05/19 Updated On:	P		SE	15	32N	20E	Marinette	0-225-108-2019	1.1	0.0	3.3	6.1	28.2	2.705	2.745	1.444		
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
DE LAET 55-38-012-PIT Created On: 06/13/22 Updated On:	P	SE	SE	14	34N	20E	Marinette	0-225-222-2022	3.0	0.0	1.8	6.6	31.8	2.718	2.745	0.977		
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
FOSTER 55-38-015-QRY Created On: 01/04/22 Updated On:	Q	SE	SE	19	31N	22E	Marinette	0-225-91-2022	0.0	7.3	6.6	6.9	32.0	2.696	2.731	1.314		
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
NOLL 55-38-022-PIT Created On: 03/02/15 Updated On:	P	NW	SW	8	30N	21E	Marinette	0-225-85-2015	0.5	0.0	3.4	5.0	29.2	2.716	2.746	1.104		
Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																		
NOLL 55-38-022-PIT Created On: 01/02/20 Updated On:	P	NW	SW	8	30N	21E	Marinette	0-225-2-2020	0.5	0.0	5.7	5.5	27.2	2.713	2.745	1.177		
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse					
	P/Q	Qrt	Qrt	Sect	Town	Range	County	LA Wear (%) 100					500	Sp. Gravity OD SSD		Absorp. % Crse Fine		
MARINETTE -- WI																		
PETERS - PESHTIGO QUARRY 55-38-026-QRY Created On: 07/07/14 Updated On:	Q	SE	NW	33	30N	22E	Marinette	0-225-213-2014	1.3	1.1	1.2	5.3	26.6	2.725	2.765	1.462		
Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																		
PETERS - PESHTIGO QUARRY 55-38-026-QRY Created On: 01/05/17 Updated On:	Q	SE	NW	33	30N	22E	Marinette	0-225-52-2017	1.8	4.4	3.7	8.9	33.7	2.663	2.715	1.953		
Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																		
PETERS - PESHTIGO QUARRY 55-38-026-QRY Created On: 01/02/20 Updated On:	Q	SE	NW	33	30N	22E	Marinette	0-225-5-2020	0.1	3.7	4.0	5.3	24.7	2.737	2.766	1.056		
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
PETERS - PESHTIGO QUARRY 55-38-026-QRY Created On: 01/12/23 Updated On:	Q	SE	NW	33	30N	22E	Marinette	0-225-119-2023	0.1	3.8	4.0	7.0	31.0	2.676	2.730	2.000		
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
RISNER 55-38-029-PIT Created On: 06/13/22 Updated On:	P	S	SW	16	30N	20E	Marinette	0-225-225-2022	1.2	0.0	0.6	6.0	26.4	2.711	2.741	1.083		
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
RIVERVIEW 55-38-046-PIT Created On: 06/13/22 Updated On:	P	SW	SW	18	31N	21E	Marinette	0-225-224-2022	0.5	0.0	2.5	4.6	24.8	2.719	2.743	0.897		
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
STAUDENMAIER 55-38-032-QRY Created On: 03/31/17 Updated On:	Q	NW	SW	7	29N	22E	Marinette	0-225-97-2017	0.0	1.9	3.7	5.8	26.2	2.717	2.752	1.294		
Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																		

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse					
	P/Q	Qrt	Qrt	Sect	Town	Range	County	LA Wear (%) 100 500					Sp. Gravity OD SSD		Absorp. % Crse Fine			
MARINETTE -- WI																		
STAUDENMAIER 55-38-032-QRY Created On: 06/13/22 Updated On:	Q	NW	SW	7	29N	22E	Marinette	0-225-220-2022	0.0	2.6	1.0	7.2	28.8	2.706	2.741	1.263		
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
TOWER 55-38-036-PIT Created On: 01/12/16 Updated On:	P	W	NE	34	31N	20E	Marinette	0-225-53-2016		0.0	1.3	4.6	24.4	2.712	2.741	1.081		
Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																		
TOWER 55-38-036-PIT Created On: 01/06/21 Updated On:	P	W	NE	34	31N	20E	Marinette	0-225-109-2021	0.3	3.5	1.8	4.6	23.0	2.706	2.737	1.142		
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
V.M.I. 55-38-039-PIT Created On: 08/14/17 Updated On:	P	NE	SW	17	31N	21E	Marinette	0-225-250-2017	0.8	6.4	3.9	5.5	25.8	2.730	2.763	1.216		
Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																		
V.M.I. 55-38-039-PIT Created On: 04/28/22 Updated On:	P	NE	SW	17	31N	21E	Marinette	0-225-181-2022	0.5	0.0	2.8	5.5	26.9	2.716	2.745	1.046		
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
WAGNER 55-38-041-QRY Created On: 08/28/14 Updated On:	Q		NW	17	33N	22E	Marinette	0-225-252-2014		0.5	1.3	6.8	29.9	2.733	2.771	1.375		
Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																		
WAGNER 55-38-041-QRY Created On: 05/10/18 Updated On:	Q		NW	17	33N	22E	Marinette	0-225-202-2018	0.0	1.8	0.9	7.8	31.9	2.726	2.761	1.250		
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
MARINETTE -- WI																	
WAGNER 55-38-041-QRY Created On: 04/28/22 Updated On:	Q		NW 17	33N	22E	Marinette	0-225-183-2022	0.3	1.0	1.8	6.3	28.1	2.711	2.750	1.442		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
*WALTERS ROAD PIT 55-38-045-PIT Created On: 06/13/19 Updated On:	P		NW SW 7	31N	22E	Marinette	0-225-219-2019	0.6	0.0	3.5	5.8	27.6	2.712	2.750	1.384		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
*WALTERS ROAD QUARRY 55-38-044-QRY Created On: 06/13/19 Updated On:	Q		NW SW 7	31N	22E	Marinette	0-225-218-2019	0.4	7.4	3.6	6.5	26.4	2.691	2.732	1.533		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
MILWAUKEE -- WI																	
FRANKLIN 55-40-008-QRY Created On: 01/21/16 Updated On:	Q		NE 10	5N	21E	Milwaukee	0-225-70-2016	3.5	15.1	2.8	4.4	21.7	2.636	2.695	2.235		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
FRANKLIN 55-40-008-QRY Created On: 05/26/16 Updated On:	Q		NE 10	5N	21E	Milwaukee	0-225-188-2016	0.3	1.3	1.1	5.6	26.0	2.639	2.677	1.453		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
FRANKLIN 55-40-008-QRY Created On: 08/25/17 Updated On:	Q		NE 10	5N	21E	Milwaukee	0-225-266-2017		0.0	1.0	7.9	29.7	2.649	2.704	2.074		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
FRANKLIN 55-40-008-QRY Created On: 01/09/20 Updated On:	Q		NE 10	5N	21E	Milwaukee	0-225-95-2020	1.5	0.0	3.0	4.5	21.8	2.730	2.760	1.098		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse					
	P/Q	Qrt	Qrt	Sect	Town	Range	County					LA Wear (%)		Sp. Gravity		Absorp. %	
											100	500	OD	SSD	Crse	Fine	
MILWAUKEE -- WI																	
FRANKLIN 55-40-008-QRY Created On: 01/03/23 Updated On:	Q		NE	10	5N	21E	Milwaukee	0-225-82-2023	1.0	3.3	0.3	6.2	29.0	2.578	2.634	2.163	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
MONROE -- WI																	
*BJORNSTAD 55-41-001-QRY Created On: 01/09/15 Updated On:	Q	NE	SW	35	15N	4W	Monroe	0-225-52-2015		0.0	6.3	12.9	41.3	2.562	2.632	2.743	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
*BJORNSTAD 55-41-001-QRY Created On: 01/03/18 Updated On:	Q	NE	SW	35	15N	4W	Monroe	0-225-14-2018	1.2	0.0	1.9	10.4	38.2	2.615	2.671	2.140	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
*BJORNSTAD 55-41-001-QRY Created On: 01/04/21 Updated On:	Q	NE	SW	35	15N	4W	Monroe	0-225-27-2021	1.2	0.0	0.9	9.3	34.7	2.620	2.671	1.962	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
BRUEGGEMAN 55-41-003-QRY Created On: 01/07/14 Updated On:	Q	NE	NW	29	15N	2W	Monroe	0-225-46-2014	0.4	0.0	5.0	9.6	39.4	2.587	2.655	2.639	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
BRUEGGEMAN 55-41-003-QRY Created On: 04/06/17 Updated On:	Q	NE	NW	29	15N	2W	Monroe	0-225-115-2017	0.3	0.0	1.5	9.8	37.6	2.618	2.673	2.081	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
BRUEGGEMAN 55-41-003-QRY Created On: 04/02/20 Updated On:	Q	NE	NW	29	15N	2W	Monroe	0-225-139-2020	0.0	0.0	2.6	10.7	38.1	2.610	2.671	2.342	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse							
	P/Q	Qrt	Qrt	Sect	Town	Range	County	LA Wear (%) 100 500					Sp. Gravity OD SSD		Absorp. % Crse Fine					
MONROE -- WI																				
BRUEGGEMAN 55-41-003-QRY Created On: 01/04/24 Updated On:	Q	NE	NW	29	15N	2W	Monroe	0-225-134-2024	1.0	2.7	3.6	8.8	35.6	2.631	2.682	1.936				
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																			
DONSKEY 55-41-004-QRY Created On: 04/08/15 Updated On:	Q	NW	SE	11	16N	3W	Monroe	0-225-112-2015		0.0	2.4	9.2	37.6	2.625	2.677	1.979				
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																			
DONSKEY 55-41-004-QRY Created On: 05/04/17 Updated On:	Q	NW	SE	11	16N	3W	Monroe	0-225-169-2017	1.6	0.0	3.3	10.0	38.4	2.622	2.674	1.956				
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																			
DONSKEY 55-41-004-QRY Created On: 03/23/18 Updated On:	Q	NW	SE	11	16N	3W	Monroe	0-225-146-2018	0.5	0.0	7.9	11.2	41.2	2.589	2.653	2.482				
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																			
DONSKEY 55-41-004-QRY Created On: 01/03/20 Updated On:	Q	NW	SE	11	16N	3W	Monroe	0-225-18-2020	1.2	0.0	3.7	9.7	38.3	2.608	2.670	2.375				
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																			
DONSKEY 55-41-004-QRY Created On: 01/03/23 Updated On:	Q	NW	SE	11	16N	3W	Monroe	0-225-65-2023	2.3	1.8	6.3	11.9	44.4	2.567	2.635	2.661				
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																			
ENDRES 55-41-006-QRY Created On: 07/26/16 Updated On:	Q	NE	SW	22	18N	4W	Monroe	0-225-229-2016	3.2	0.0	5.0	17.2	56.1	2.548	2.623	2.945				

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine		
MONROE -- WI																			
ENDRES 55-41-006-QRY Created On: 08/03/16 Updated On:	Q	NE	SW	22	18N	4W	Monroe	0-225-235-2016	0.4	0.0	4.0	11.4	41.7	2.637	2.687	1.913			
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																		
ENDRES 55-41-006-QRY Created On: 05/13/20 Updated On:	Q	NE	SW	22	18N	4W	Monroe	0-225-178-2020	0.8	0.0	4.6	10.7	39.7	2.629	2.684	2.110			
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
ENDRES 55-41-006-QRY Created On: 01/03/23 Updated On:	Q	NE	SW	22	18N	4W	Monroe	0-225-70-2023	0.5	3.9	1.6	11.3	42.2	2.589	2.658	2.665			
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
GERKE 55-41-009-QRY Created On: 04/25/17 Updated On:	Q	NE	SE	36	17N	1W	Monroe	0-225-157-2017	0.2	0.0	11.8	13.1	48.9	2.523	2.606	3.298			
	Approved Use : HMA<E-3, CONCRETE, Base Aggregate																		
GERKE 55-41-009-QRY Created On: 01/24/22 Updated On:	Q	NE	SE	36	17N	1W	Monroe	0-225-116-2022	0.0	0.0	4.8	12.8	45.8	2.541	2.619	3.035			
	Approved Use : HMA<MT, CONCRETE, OGBC, Base Aggregate																		
KING 55-41-011-QRY Created On: 04/07/16 Updated On:	Q	SE	SE	1	16N	1W	Monroe	0-225-130-2016		0.0	3.0	8.1	34.4	2.637	2.690	1.999			
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																		
KING 55-41-011-QRY Created On: 05/04/17 Updated On:	Q	SE	SE	1	16N	1W	Monroe	0-225-172-2017		0.0	11.7	8.3	36.6	2.621	2.680	2.244			
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																		

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
MONROE -- WI																		
KING 55-41-011-QRY Created On: 04/02/20 Updated On:	Q	SE	SE	1	16N	1W	Monroe	0-225-140-2020	0.0	0.0	4.4	8.6	34.7	2.616	2.675	2.257		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
KING 55-41-011-QRY Created On: 05/22/23 Updated On:	Q	SE	SE	1	16N	1W	Monroe	0-225-221-2023	0.8	10.5	6.1	10.3	39.6	2.593	2.661	2.622		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MENN 55-41-013-QRY Created On: 03/07/16 Updated On:	Q	SW	NW	2	15N	2W	Monroe	0-225-92-2016	0.4	0.0	3.4	19.1	45.9	2.532	2.614	3.242		
	Approved Use : CONCRETE, Base Aggregate																	
MENN 55-41-013-QRY Created On: 04/19/18 Updated On:	Q	SW	NW	2	15N	2W	Monroe	0-225-176-2018	0.3	0.0	1.7	10.1	37.5	2.598	2.659	2.360		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
MENN 55-41-013-QRY Created On: 03/12/20 Updated On:	Q	SW	NW	2	15N	2W	Monroe	0-225-127-2020	0.0	0.0	3.7	11.8	40.5	2.551	2.626	2.945		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MENN 55-41-013-QRY Created On: 04/10/23 Updated On:	Q	SW	NW	2	15N	2W	Monroe	0-225-192-2023	1.3	3.6	5.5	10.8	40.1	2.608	2.663	2.102		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
REVELS QUARRY 55-41-018-QRY Created On: 04/10/14 Updated On:	Q	NW	SE	1	16N	3W	Monroe	0-225-121-2014	0.2	0.0	9.2	13.9	44.2	2.523	2.604	3.227		
	Approved Use : CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Coarse Sp. Gravity		Coarse Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
MONROE -- WI																		
REVELS QUARRY 55-41-018-QRY Created On: 04/25/17 Updated On:	Q	NW	SE	1	16N	3W	Monroe	0-225-155-2017	0.6	0.0	7.0	12.0	42.7	2.547	2.624	3.030		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
REVELS QUARRY 55-41-018-QRY Created On: 02/13/20 Updated On:	Q	NW	SE	1	16N	3W	Monroe	0-225-115-2020	0.0	0.0	3.2	12.9	44.7	2.558	2.631	2.866		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
REVELS QUARRY 55-41-018-QRY Created On: 04/10/23 Updated On:	Q	NW	SE	1	16N	3W	Monroe	0-225-193-2023	2.9	3.5	8.3	11.2	41.9	2.580	2.645	2.540		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
SCHMITZ 55-41-020-QRY Created On: 01/07/14 Updated On:	Q		SW	18	15N	2W	Monroe	0-225-44-2014		0.0	3.3	9.7	35.3	2.630	2.679	1.862		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
SCHMITZ 55-41-020-QRY Created On: 08/03/18 Updated On:	Q		SW	18	15N	2W	Monroe	0-225-262-2018	0.7	0.0	5.4	12.4	41.2	2.594	2.657	2.406		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
SCHMITZ 55-41-020-QRY Created On: 01/05/21 Updated On:	Q		SW	18	15N	2W	Monroe	0-225-65-2021	0.7	0.0	0.3	7.3	30.7	2.634	2.685	1.921		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
SCHMITZ 55-41-020-QRY Created On: 01/02/24 Updated On:	Q		SW	18	15N	2W	Monroe	0-225-26-2024	0.9	2.2	4.2	10.5	39.3	2.599	2.663	2.464		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse					
	P/Q	Qrt	Qrt	Sect	Town	Range	County	LA Wear (%) 100 500					Sp. Gravity OD SSD		Absorp. % Crse Fine			
MONROE -- WI																		
WIEDL 55-41-024-QRY Created On: 06/10/16 Updated On:	Q	NW	NW	29	16N	2W	Monroe	0-225-195-2016	2.0	0.0	4.6	11.3	39.7	2.547	2.618	2.814		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
WIEDL 55-41-024-QRY Created On: 05/03/18 Updated On:	Q	NW	NW	29	16N	2W	Monroe	0-225-190-2018	0.7	0.0	3.2	8.4	35.2	2.591	2.650	2.294		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
WIEDL 55-41-024-QRY Created On: 08/12/21 Updated On:	Q	NW	NW	29	16N	2W	Monroe	0-225-261-2021	3.4	0.0	8.4	11.4	41.1	2.566	2.633	2.614		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
WIEDL 55-41-024-QRY Created On: 01/02/24 Updated On:	Q	NW	NW	29	16N	2W	Monroe	0-225-23-2024	2.0	2.6	5.0	11.8	40.5	2.576	2.642	2.565		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
WILTON 55-41-027-QRY Created On: 07/25/19 Updated On:	Q		SW	35	16N	1W	Monroe	0-225-250-2019		0.0	4.4	14.1	46.6	2.573	2.637	2.467		
	Approved Use : Base Aggregate																	
WILTON 55-41-027-QRY Created On: 01/04/22 Updated On:	Q		SW	35	16N	1W	Monroe	0-225-73-2022		1.2	5.3	13.9	45.7	2.556	2.627	2.796		
	Approved Use : OGBC, Base Aggregate																	
OCONTO -- WI																		
CAELWAERTS 55-42-002-QRY Created On: 08/16/16 Updated On:	Q	NE	SE	31	29N	22E	Oconto	0-225-241-2016		7.7	2.6	4.6	25.7	2.721	2.753	1.160		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse						
	P/Q	Qrt	Qrt	Sect	Town	Range	County	LA Wear (%) 100					500	Sp. Gravity OD SSD		Absorp. % Crse Fine			
OCONTO -- WI																			
CAELWAERTS 55-42-002-QRY Created On: 04/24/19 Updated On:	Q	NE	SE	31	29N	22E	Oconto	0-225-165-2019		7.7	1.3	5.5	25.2	2.707	2.741	1.245			
Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																			
CAELWAERTS 55-42-002-QRY Created On: 01/04/22 Updated On:	Q	NE	SE	31	29N	22E	Oconto	0-225-92-2022		0.0	4.5	4.7	6.2	28.2	2.709	2.739	1.115		
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																			
CHASE (NEA) 55-42-003-QRY Created On: 01/12/16 Updated On:	Q	NW	NE	17	26N	19E	Oconto	0-225-48-2016		0.2	1.2	3.9	20.7	2.759	2.782	0.821			
Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																			
CHASE (NEA) 55-42-003-QRY Created On: 05/12/21 Updated On:	Q	NW	NE	17	26N	19E	Oconto	0-225-205-2021		0.0	0.9	0.2	4.7	20.7	2.776	2.795	0.714		
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																			
CHASE (NEA) 55-42-003-QRY Created On: 01/02/24 Updated On:	Q	NW	NE	17	26N	19E	Oconto	0-225-10-2024		0.6	3.6	0.2	6.2	25.9	2.765	2.788	0.815		
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																			
*CLEEREMAN 55-42-044-PIT Created On: 05/24/19 Updated On:	P	SE	SE	32	33N	16E	Oconto	0-225-199-2019		0.0	0.0	0.5	4.6	22.0	2.681	2.703	0.812		
Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																			
D and J CHASE 55-42-006-QRY Created On: 04/01/16 Updated On:	Q	E	NE	17	26N	19E	Oconto	0-225-118-2016		0.4	8.3	1.3	6.2	26.8	2.718	2.753	1.279		
Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																			

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse						
	P/Q	Qrt	Qrt	Sect	Town	Range	County	LA Wear (%) 100					500	Sp. Gravity OD SSD		Absorp. % Crse Fine			
OCONTO -- WI																			
D and J CHASE 55-42-006-QRY Created On: 04/24/19 Updated On:	Q	E	NE	17	26N	19E	Oconto	0-225-163-2019	0.0	0.8	1.2	5.1	22.9	2.858	2.879	0.705			
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																		
D and J CHASE 55-42-006-QRY Created On: 01/04/22 Updated On:	Q	E	NE	17	26N	19E	Oconto	0-225-70-2022	1.1	3.7	3.0	5.2	24.6	2.749	2.770	0.762			
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
*DUAME #1 55-42-001-QRY Created On: 04/27/17 Updated On:	Q	SE	SE	31	29N	21E	Oconto	0-225-160-2017	0.7	5.9	8.7	10.1	36.8	2.683	2.722	1.456			
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																		
*DUAME #1 55-42-001-QRY Created On: 02/24/21 Updated On:	Q	SE	SE	31	29N	21E	Oconto	0-225-130-2021	0.1	1.8	4.3	8.8	36.6	2.705	2.746	1.532			
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
GOHR 55-42-011-QRY Created On: 05/30/17 Updated On:	Q	SW	NE	4	26N	19E	Oconto	0-225-196-2017		1.2	1.2	5.7	26.2	2.772	2.793	0.751			
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																		
GOHR 55-42-011-QRY Created On: 01/02/20 Updated On:	Q	SW	NE	4	26N	19E	Oconto	0-225-3-2020	0.0	2.9	2.4	5.7	25.5	2.748	2.771	0.823			
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
GOHR 55-42-011-QRY Created On: 01/12/23 Updated On:	Q	SW	NE	4	26N	19E	Oconto	0-225-121-2023	0.0	2.1	1.9	6.8	23.7	2.755	2.780	0.884			
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
OCONTO -- WI																		
HODGE PIT 55-42-046-PIT Created On: 01/02/24 Updated On:	P	SE	SE	8	29N	20E	Oconto	0-225-96-2024	0.1	0.0	4.0	5.8	27.9	2.709	2.741	1.198		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
KRUEGER 55-42-017-QRY Created On: 01/07/16 Updated On:	Q	SE	SE	6	27N	21E	Oconto	0-225-35-2016	0.0	1.2	2.5	6.3	29.1	2.693	2.728	1.313		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
KRUEGER 55-42-017-QRY Created On: 01/25/19 Updated On:	Q	SE	SE	6	27N	21E	Oconto	0-225-91-2019	0.3	13.2	4.0	6.4	29.0	2.668	2.708	1.509		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
KRUEGER 55-42-017-QRY Created On: 01/04/22 Updated On:	Q	SE	SE	6	27N	21E	Oconto	0-225-93-2022	0.1	2.4	3.4	5.7	27.8	2.710	2.740	1.084		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
LAUERSDORF 55-42-019-QRY Created On: 03/17/16 Updated On:	Q	NE	SW	35	29N	18E	Oconto	0-225-99-2016	0.9	1.4	0.7	8.5	35.6	2.700	2.738	1.396		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
LAUERSDORF 55-42-019-QRY Created On: 01/08/20 Updated On:	Q	NE	SW	35	29N	18E	Oconto	0-225-71-2020	0.1	0.9	3.0	8.7	35.9	2.728	2.756	1.027		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
LAUERSDORF 55-42-019-QRY Created On: 01/12/23 Updated On:	Q	NE	SW	35	29N	18E	Oconto	0-225-120-2023	0.0	4.8	4.8	10.1	41.3	2.648	2.700	1.964		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse							
	P/Q	Qrt	Qrt	Sect	Town	Range	County	LA Wear (%) 100 500					Sp. Gravity OD SSD		Absorp. % Crse Fine					
OCONTO -- WI																				
MCKEEFRY - CHASE 55-42-023-PIT Created On: 08/16/16 Updated On:	P	NW	SE	3	26N	19E	Oconto	0-225-242-2016	0.8	1.3	0.4	6.5	29.0	2.743	2.769	0.970				
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																			
MCKEEFRY - CHASE 55-42-023-PIT Created On: 04/13/21 Updated On:	P	NW	SE	3	26N	19E	Oconto	0-225-179-2021	0.4	3.3	5.2	8.5	36.8	2.710	2.745	1.303				
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																			
MICHELS CHASE 55-42-024-QRY Created On: 01/07/15 Updated On:	Q	NE	SW	17	26N	19E	Oconto	0-225-21-2015		2.0	2.4	4.8	22.1	2.733	2.759	0.924				
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																			
MICHELS CHASE 55-42-024-QRY Created On: 01/04/19 Updated On:	Q	NE	SW	17	26N	19E	Oconto	0-225-40-2019		5.7	3.2	5.9	25.8	2.738	2.764	0.975				
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																			
MICHELS CHASE 55-42-024-QRY Created On: 04/11/22 Updated On:	Q	NE	SW	17	26N	19E	Oconto	0-225-174-2022	0.1	3.4	3.4	5.8	24.7	2.730	2.760	1.129				
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																			
*MONTEVIDEO QUARRY 55-42-025-QRY Created On: 07/07/14 Updated On:	Q	NW	SE	3	26N	20E	Oconto	0-225-212-2014	0.2	5.8	2.3	5.9	25.6	2.734	2.762	0.989				
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																			
*MONTEVIDEO QUARRY 55-42-025-QRY Created On: 07/23/19 Updated On:	Q	NW	SE	3	26N	20E	Oconto	0-225-245-2019	0.5	7.0	4.1	5.8	25.6	2.738	2.768	1.114				
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																			

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse					
	P/Q	Qrt	Qrt	Sect	Town	Range	County					LA Wear (%)		Sp. Gravity		Absorp. %	
											100	500	OD	SSD	Crse	Fine	
OCONTO -- WI																	
PETERS CHASE #5 55-42-030-QRY Created On: 01/27/14 Updated On:	Q		NW	17	26N	19E	Oconto	0-225-61-2014		2.5	2.8	5.2	23.3	2.750	2.774	0.857	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
PETERS CHASE #5 55-42-030-QRY Created On: 01/30/15 Updated On:	Q		NW	17	26N	19E	Oconto	0-225-81-2015		0.7	4.2	3.9	5.6	24.9	2.731	2.759	0.995
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
PETERS CHASE #5 55-42-030-QRY Created On: 01/07/16 Updated On:	Q		NW	17	26N	19E	Oconto	0-225-39-2016		1.8	2.6	5.3	24.4	2.720	2.748	1.033	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
PETERS CHASE #5 55-42-030-QRY Created On: 01/25/19 Updated On:	Q		NW	17	26N	19E	Oconto	0-225-90-2019		0.1	6.5	1.7	5.2	23.6	2.756	2.780	0.879
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
PETERS CHASE #5 55-42-030-QRY Created On: 01/04/22 Updated On:	Q		NW	17	26N	19E	Oconto	0-225-90-2022		0.0	2.7	1.9	5.0	23.5	2.736	2.760	0.876
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
PETERSON "CC" 55-42-032-PIT Created On: 03/30/15 Updated On:	P	S	NW	32	28N	19E	Oconto	0-225-102-2015		0.2	0.0	3.3	6.8	30.5	2.734	2.765	1.134
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
PETERSON "CC" 55-42-032-PIT Created On: 01/08/20 Updated On:	P	S	NW	32	28N	19E	Oconto	0-225-75-2020		0.2	0.0	2.8	6.1	29.9	2.732	2.759	0.996
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse					
	P/Q	Qrt	Qrt	Sect	Town	Range	County	LA Wear (%) 100					500	Sp. Gravity OD SSD		Absorp. % Crse Fine		
OCONTO -- WI																		
ROUER 55-42-033-QRY Created On: 01/04/22 Updated On:	Q	NW	NE	28	29N	21E	Oconto	0-225-89-2022	0.1	6.3	5.2	6.7	31.5	2.682	2.719	1.359		
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
SPRAGUE 55-42-037-PIT Created On: 01/06/16 Updated On:	P	SE	NE	16	30N	19E	Oconto	0-225-33-2016	1.2	0.0	7.4	8.1	31.2	2.687	2.722	1.305		
Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																		
SPRAGUE 55-42-037-PIT Created On: 02/10/21 Updated On:	P	SE	NE	16	30N	19E	Oconto	0-225-126-2021	2.5	0.0	5.9	6.8	29.5	2.683	2.722	1.449		
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
THOMSON LIMESTONE 55-42-038-QRY Created On: 01/04/22 Updated On:	Q	SE	SE	20	30N	19E	Oconto	0-225-14-2022	1.4	6.9	6.5	6.0	33.8	2.696	2.736	1.489		
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
TOWNSEND 55-42-039-PIT Created On: 01/05/21 Updated On:	P	SE	SW	15	33N	15E	Oconto	0-225-104-2021	0.0	0.2	0.4	3.9	18.8	2.682	2.697	0.581		
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
ONEIDA -- WI																		
A-FRAME 55-43-001-PIT Created On: 05/12/16 Updated On:	P	NE	NE	22	37N	6E	Oneida	0-225-169-2016		0.0	0.3	4.6	20.3	2.681	2.712	1.169		
Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																		
A-FRAME 55-43-001-PIT Created On: 01/08/20 Updated On:	P	NE	NE	22	37N	6E	Oneida	0-225-49-2020	1.5	0.0	1.9	4.0	18.6	2.724	2.737	0.483		
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse					
	P/Q	Qrt	Qrt	Sect	Town	Range	County	LA Wear (%)					Sp. Gravity		Absorp. %			
												100	500	OD	SSD	Crse	Fine	
ONEIDA -- WI																		
BLUE LAKE 55-43-002-PIT Created On: 05/10/18 Updated On:	P	SW	SE	27	39N	6E	Oneida	0-225-205-2018	0.8	0.0	1.4	4.2	18.7	2.701	2.723	0.811		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
BLUE LAKE 55-43-002-PIT Created On: 01/03/23 Updated On:	P	SW	SE	27	39N	6E	Oneida	0-225-29-2023	2.4	0.0	2.5	4.9	20.8	2.670	2.698	1.026		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
HAZELHURST 55-43-005-PIT Created On: 06/01/18 Updated On:	P	NE	SE	15	37N	6E	Oneida	0-225-218-2018		0.0	0.5	4.3	20.6	2.689	2.713	0.896		
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																	
HAZELHURST 55-43-005-PIT Created On: 01/03/23 Updated On:	P	NE	SE	15	37N	6E	Oneida	0-225-17-2023		0.0	0.3	3.1	16.4	2.713	2.734	0.773		
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																	
*HIGH POINT 55-43-010-PIT Created On: 04/18/19 Updated On:	P	SW	NW	36	39N	7E	Oneida	0-225-139-2019	0.3	0.0	0.1	5.5	26.2	2.655	2.673	0.680		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
INDIAN LAKE 55-43-006-PIT Created On: 07/16/20 Updated On:	P	E	NE	6	38N	10E	Oneida	0-225-222-2020	0.1	0.0	1.2	4.5	20.1	2.688	2.711	0.856		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
K-PIT ONEIDA 55-43-011-PIT Created On: 06/13/18 Updated On:	P	NW	NW	6	36N	8E	Oneida	0-225-228-2018	1.8	0.0	1.8	7.3	28.2	2.690	2.715	0.914		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Coarse Sp. Gravity		Coarse Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
ONEIDA -- WI																		
K-PIT ONEIDA 55-43-011-PIT Created On: 01/19/23 Updated On:	P	NW	NW	6	36N	8E	Oneida	0-225-129-2023	1.0	0.0	3.5	5.7	24.7	2.664	2.698	1.299		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
KELLY 55-43-007-PIT Created On: 04/19/19 Updated On:	P	NE	SE	32	38N	11E	Oneida	0-225-151-2019	1.1	0.0	0.4	5.3	22.9	2.689	2.714	0.954		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
KELLY 55-43-007-PIT Created On: 07/30/20 Updated On:	P	NE	SE	32	38N	11E	Oneida	0-225-227-2020	0.0	0.0	0.2	4.1	22.0	2.751	2.767	0.581		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
KELLY QUARRY 55-43-034-QRY Created On: 01/03/23 Updated On:	Q	NE	SE	32	38N	11E	Oneida	0-225-25-2023	0.0	0.0	0.5	7.6	30.4	2.751	2.767	0.581		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
KING 55-43-008-QRY Created On: 04/05/16 Updated On:	Q	NW	NW	19	38N	10E	Oneida	0-225-121-2016		0.0	0.3	9.5	40.2	2.608	2.623	0.586		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
KING 55-43-008-QRY Created On: 01/07/19 Updated On:	Q	NW	NW	19	38N	10E	Oneida	0-225-69-2019		0.0	0.2	6.3	29.5	2.616	2.628	0.479		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
KING 55-43-008-QRY Created On: 07/16/20 Updated On:	Q	NW	NW	19	38N	10E	Oneida	0-225-219-2020	0.0	0.0	0.2	7.6	36.4	2.608	2.622	0.563		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine		
ONEIDA -- WI																			
KING 55-43-008-QRY Created On: 01/03/23 Updated On:	Q	NW	NW	19	38N	10E	Oneida	0-225-20-2023	0.7	0.0	0.7	5.8	28.8	2.622	2.639	0.652			
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
KLAVER 55-43-009-PIT Created On: 08/28/14 Updated On:	P	NW	SE	4	36N	8E	Oneida	0-225-251-2014		0.0	1.0	4.8	22.5	2.715	2.747	1.157			
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																		
KLAVER 55-43-009-PIT Created On: 06/25/20 Updated On:	P	NW	SE	4	36N	8E	Oneida	0-225-209-2020	0.1	0.0	0.6	5.1	23.4	2.737	2.759	0.791			
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
KUCZMARSKI 55-43-037-PIT Created On: 01/02/24 Updated On:	P	W	SE	26	37N	10E	Oneida	0-225-64-2024	0.2	0.0	1.1	4.3	20.6	2.716	2.736	0.722			
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
LASSIG PIT 55-43-036-PIT Created On: 09/05/23 Updated On:	P	NW	NE	29	36N	9E	Oneida	0-225-249-2023	0.1	0.0	3.5	6.8	27.4	2.726	2.748	0.838			
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
LUND / RIOPEL 55-43-013-PIT Created On: 01/04/18 Updated On:	P	SW	SW	6	36N	8E	Oneida	0-225-59-2018		0.0	1.5	4.2	20.2	2.674	2.702	1.027			
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																		
LUND / RIOPEL 55-43-013-PIT Created On: 01/03/23 Updated On:	P	SW	SW	6	36N	8E	Oneida	0-225-15-2023		0.0	0.6	3.3	17.6	2.696	2.721	0.933			
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																		

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Coarse Sp. Gravity		Coarse Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
ONEIDA -- WI																		
MILITARY 55-43-015-PIT Created On: 01/05/21 Updated On:	P	NE	SE	2	39N	11E	Oneida	0-225-53-2021	0.9	0.0	0.6	3.0	15.7	2.702	2.725	0.847		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MONICO (MICHEL) 55-43-016-PIT Created On: 05/15/14 Updated On:	P	NW	SE	26	36N	11E	Oneida	0-225-164-2014		0.0	0.5	2.3	10.5	2.709	2.729	0.715		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
MONICO (MICHEL) 55-43-016-PIT Created On: 07/16/20 Updated On:	P	NW	SE	26	36N	11E	Oneida	0-225-220-2020	0.0	1.3	0.4	3.2	13.4	2.699	2.715	0.615		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
RIVER BEND 55-43-020-PIT Created On: 06/13/18 Updated On:	P			22	36N	9E	Oneida	0-225-229-2018	0.0	0.0	1.1	5.1	22.6	2.730	2.749	0.698		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
RIVER BEND 55-43-020-PIT Created On: 01/19/23 Updated On:	P			22	36N	9E	Oneida	0-225-125-2023	0.0	0.0	1.7	4.6	21.4	2.705	2.726	0.774		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
ROCKY RUN 55-43-024-PIT Created On: 04/11/18 Updated On:	P		SW	14	37N	6E	Oneida	0-225-168-2018	0.5	0.0	0.3	4.3	19.2	2.705	2.727	0.801		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
ROCKY RUN 55-43-024-PIT Created On: 01/03/23 Updated On:	P		SW	14	37N	6E	Oneida	0-225-28-2023	0.5	0.0	1.4	3.9	18.3	2.715	2.740	0.915		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse					
	P/Q	Qrt	Qrt	Sect	Town	Range	County	LA Wear (%) 100					500	Sp. Gravity OD SSD		Absorp. % Crse Fine		
ONEIDA -- WI																		
STAG LAKE 55-43-033-PIT Created On: 06/13/18 Updated On:	P	NW	NW	34	36N	7E	Oneida	0-225-226-2018	0.2	0.0	1.9	5.5	24.1	2.682	2.703	0.790		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
STAG LAKE 55-43-033-PIT Created On: 01/19/23 Updated On:	P	NW	NW	34	36N	7E	Oneida	0-225-127-2023	0.4	0.0	2.7	5.3	23.5	2.665	2.695	1.134		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
TAYLOR #1 55-43-028-PIT Created On: 06/13/18 Updated On:	P	NW	NW	16	36N	9E	Oneida	0-225-227-2018	0.2	0.0	0.9	5.1	23.4	2.637	2.655	0.647		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
TAYLOR #1 55-43-028-PIT Created On: 04/24/23 Updated On:	P	NW	NW	16	36N	9E	Oneida	0-225-206-2023	0.0	0.0	0.8	5.7	25.0	2.742	2.763	0.751		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
OUTAGAMIE -- WI																		
*BESCHTA 55-44-003-QRY Created On: 06/26/19 Updated On:	Q	E	SW	26	23N	16E	Outagamie	0-225-229-2019	1.4	6.0	3.0	8.2	34.6	2.698	2.743	1.685		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
CAREW - FREEDOM 55-44-006-QRY Created On: 06/05/14 Updated On:	Q	SW	NE	10	22N	18E	Outagamie	0-225-187-2014	0.1	0.5	0.1	3.8	17.0	2.805	2.818	0.463		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
CAREW - FREEDOM 55-44-006-QRY Created On: 01/16/15 Updated On:	Q	SW	NE	10	22N	18E	Outagamie	0-225-68-2015	0.8	0.8	1.0	4.6	20.6	2.791	2.808	0.616		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse					
	P/Q	Qrt	Qrt	Sect	Town	Range	County	LA Wear (%) 100					500	Sp. Gravity OD SSD		Absorp. % Crse Fine		
OUTAGAMIE -- WI CAREW - FREEDOM 55-44-006-QRY Created On: 03/06/17 Updated On:	Q	SW	NE	10	22N	18E	Outagamie	0-225-75-2017		2.8	1.5	4.6	21.2	2.774	2.796	0.794		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
CAREW - FREEDOM 55-44-006-QRY Created On: 01/30/20 Updated On:	Q	SW	NE	10	22N	18E	Outagamie	0-225-100-2020		0.0	2.4	1.2	4.0	18.3	2.796	2.812	0.572	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
CAREW - FREEDOM 55-44-006-QRY Created On: 01/04/23 Updated On:	Q	SW	NE	10	22N	18E	Outagamie	0-225-103-2023		0.0	1.2	1.2	4.4	19.9	2.788	2.804	0.572	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
CAREW - FREEDOM 55-44-006-QRY Created On: 02/28/24 Updated On:	Q	SW	NE	10	22N	18E	Outagamie	0-225-178-2024		0.0	1.2	1.3	4.8	21.3	2.771	2.791	0.732	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
CAREW - ROCK RD 55-44-007-QRY Created On: 01/25/16 Updated On:	Q	NE	NW	20	22N	17E	Outagamie	0-225-82-2016		0.7	3.7	5.6	27.6	2.701	2.738	1.363		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
CAREW - ROCK RD 55-44-007-QRY Created On: 01/10/19 Updated On:	Q	NE	NW	20	22N	17E	Outagamie	0-225-84-2019		0.1	4.1	3.0	6.1	27.9	2.746	2.775	1.045	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
CAREW - ROCK RD 55-44-007-QRY Created On: 03/17/22 Updated On:	Q	NE	NW	20	22N	17E	Outagamie	0-225-152-2022		0.2	2.7	3.6	5.9	27.4	2.725	2.756	1.124	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse					
	P/Q	Qrt	Qrt	Sect	Town	Range	County					LA Wear (%)		Sp. Gravity		Absorp. %	
											100	500	OD	SSD	Crse	Fine	
OUTAGAMIE -- WI																	
DREPHALS 55-44-011-QRY Created On: 04/17/14 Updated On:	Q		E	17	24N	17E	Outagamie	0-225-131-2014		0.3	2.1	6.9	30.6	2.721	2.758	1.348	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
DREPHALS 55-44-011-QRY Created On: 05/11/17 Updated On:	Q		E	17	24N	17E	Outagamie	0-225-181-2017		3.9	2.5	7.1	30.0	2.717	2.753	1.342	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
DREPHALS 55-44-011-QRY Created On: 03/17/22 Updated On:	Q		E	17	24N	17E	Outagamie	0-225-144-2022		0.5	1.0	1.2	10.2	36.8	2.727	2.762	1.293
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
FREEDOM - N.E.A. 55-44-012-QRY Created On: 01/06/14 Updated On:	Q	NE	NW	10	22N	18E	Outagamie	0-225-14-2014		0.5	0.4	4.6	20.5	2.790	2.809	0.671	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
FREEDOM - N.E.A. 55-44-012-QRY Created On: 01/04/22 Updated On:	Q	NE	NW	10	22N	18E	Outagamie	0-225-13-2022		0.0	2.5	0.3	4.6	21.2	2.757	2.783	0.941
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
MACKVILLE 55-44-019-QRY Created On: 09/11/14 Updated On:	Q	SW	NE	33	22N	17E	Outagamie	0-225-261-2014		0.1	0.8	0.2	4.0	18.9	2.755	2.782	0.997
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
MACKVILLE 55-44-019-QRY Created On: 03/30/15 Updated On:	Q	SW	NE	33	22N	17E	Outagamie	0-225-105-2015		0.1	0.5	2.4	4.3	18.8	2.767	2.789	0.789
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse					
	P/Q	Qrt	Qrt	Sect	Town	Range	County	LA Wear (%)					Sp. Gravity		Absorp. %			
												100	500	OD	SSD	Crse	Fine	
OUTAGAMIE -- WI																		
MACKVILLE 55-44-019-QRY Created On: 02/16/16 Updated On:	Q	SW	NE	33	22N	17E	Outagamie	0-225-84-2016	0.4	2.7	0.8	4.7	21.5	2.751	2.777	0.940		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
MACKVILLE 55-44-019-QRY Created On: 02/03/17 Updated On:	Q	SW	NE	33	22N	17E	Outagamie	0-225-58-2017	0.2	3.7	1.5	6.1	24.5	2.724	2.759	1.284		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
MACKVILLE 55-44-019-QRY Created On: 03/16/18 Updated On:	Q	SW	NE	33	22N	17E	Outagamie	0-225-123-2018	0.5	3.0	1.0	4.2	19.6	2.765	2.788	0.856		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
MACKVILLE 55-44-019-QRY Created On: 04/24/19 Updated On:	Q	SW	NE	33	22N	17E	Outagamie	0-225-168-2019	0.6	2.5	0.4	5.2	21.5	2.771	2.795	0.870		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MACKVILLE 55-44-019-QRY Created On: 06/24/20 Updated On:	Q	SW	NE	33	22N	17E	Outagamie	0-225-205-2020	0.2	8.5	1.7	4.4	22.2	2.773	2.795	0.800		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MACKVILLE 55-44-019-QRY Created On: 01/17/23 Updated On:	Q	SW	NE	33	22N	17E	Outagamie	0-225-122-2023	0.1	4.7	1.2	4.6	20.4	2.762	2.788	0.923		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MACKVILLE 55-44-019-QRY Created On: 01/02/24 Updated On:	Q	SW	NE	33	22N	17E	Outagamie	0-225-105-2024	0.3	6.4	1.0	5.0	21.7	2.764	2.788	0.882		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
OUTAGAMIE -- WI																		
MCC ROCK ROAD 55-44-031-QRY Created On: 01/05/21 Updated On:	Q	SE	SW	17	22N	17E	Outagamie	0-225-100-2021	0.2	0.8	3.2	6.7	30.2	2.716	2.756	1.469		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MCC ROCK ROAD 55-44-031-QRY Created On: 01/02/24 Updated On:	Q	SE	SW	17	22N	17E	Outagamie	0-225-6-2024	0.6	1.5	0.4	7.3	31.6	2.712	2.743	1.120		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MCC- FREEDOM WEST 55-44-020-QRY Created On: 05/02/16 Updated On:	Q	NE	SE	17	22N	18E	Outagamie	0-225-160-2016	0.4	12.0	0.2	5.6	23.7	2.768	2.790	0.823		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
MCC- FREEDOM WEST 55-44-020-QRY Created On: 04/19/19 Updated On:	Q	NE	SE	17	22N	18E	Outagamie	0-225-150-2019	0.3	3.8	2.5	4.8	21.6	2.768	2.793	0.907		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
MCC- FREEDOM WEST 55-44-020-QRY Created On: 06/24/20 Updated On:	Q	NE	SE	17	22N	18E	Outagamie	0-225-206-2020	0.6	7.9	2.2	5.2	21.5	2.769	2.792	0.841		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MCC- FREEDOM WEST 55-44-020-QRY Created On: 01/05/21 Updated On:	Q	NE	SE	17	22N	18E	Outagamie	0-225-101-2021	0.1	2.2	2.4	5.2	22.4	2.762	2.787	0.909		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MCC- FREEDOM WEST 55-44-020-QRY Created On: 01/02/24 Updated On:	Q	NE	SE	17	22N	18E	Outagamie	0-225-5-2024	0.0	5.9	1.7	5.0	22.2	2.763	2.789	0.919		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse					
	P/Q	Qrt	Qrt	Sect	Town	Range	County	LA Wear (%)					Sp. Gravity		Absorp. %			
												100	500	OD	SSD	Crse	Fine	
OUTAGAMIE -- WI																		
MEDINA 55-44-016-PIT Created On: 03/17/22 Updated On:	P		SW	19	21N	16E	Outagamie	0-225-146-2022	0.5	0.0	0.3	5.2	25.2	2.754	2.780	0.924		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MICHEL'S GARVEY 55-44-021-QRY Created On: 01/07/16 Updated On:	Q	SE	SE	17	22N	17E	Outagamie	0-225-36-2016		0.6	1.9	7.0	31.4	2.682	2.720	1.428		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
MICHEL'S GARVEY 55-44-021-QRY Created On: 01/07/19 Updated On:	Q	SE	SE	17	22N	17E	Outagamie	0-225-42-2019	0.2	3.9	5.1	6.9	31.6	2.741	2.769	1.022		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MICHEL'S GARVEY 55-44-021-QRY Created On: 01/04/22 Updated On:	Q	SE	SE	17	22N	17E	Outagamie	0-225-34-2022	0.2	0.8	1.7	5.8	27.9	2.720	2.753	1.221		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MICHEL'S GARVEY 55-44-021-QRY Created On: 01/02/24 Updated On:	Q	SE	SE	17	22N	17E	Outagamie	0-225-106-2024	1.2	3.9	4.1	7.8	32.4	2.688	2.728	1.509		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
NEW LONDON 55-44-025-QRY Created On: 05/26/16 Updated On:	Q			30	22N	15E	Outagamie	0-225-192-2016		8.3	8.8	7.4	31.7	2.691	2.731	1.467		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
NEW LONDON 55-44-025-QRY Created On: 01/25/19 Updated On:	Q			30	22N	15E	Outagamie	0-225-89-2019	0.4	2.6	1.1	8.0	31.3	2.731	2.759	1.005		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse					
	P/Q	Qrt	Qrt	Sect	Town	Range	County	LA Wear (%) 100 500					Sp. Gravity OD SSD		Absorp. % Crse Fine			
OUTAGAMIE -- WI																		
NEW LONDON 55-44-025-QRY Created On: 04/28/22 Updated On:	Q			30	22N	15E	Outagamie	0-225-186-2022	0.4	7.3	2.1	6.3	29.8	2.722	2.754	1.193		
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
SEYMOUR 55-44-027-QRY Created On: 05/15/14 Updated On:	Q	SW	SE	31	24N	18E	Outagamie	0-225-162-2014		3.4	1.8	6.1	24.2	2.749	2.779	1.062		
Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																		
SEYMOUR 55-44-027-QRY Created On: 05/11/17 Updated On:	Q	SW	SE	31	24N	18E	Outagamie	0-225-180-2017		3.9	1.1	7.5	30.5	2.724	2.761	1.330		
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
SEYMOUR 55-44-027-QRY Created On: 04/08/20 Updated On:	Q	SW	SE	31	24N	18E	Outagamie	0-225-146-2020	0.2	12.6	2.4	8.0	30.9	2.758	2.784	0.918		
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
SEYMOUR 55-44-027-QRY Created On: 02/28/23 Updated On:	Q	SW	SE	31	24N	18E	Outagamie	0-225-160-2023	1.0	8.8	1.4	6.9	27.6	2.741	2.772	1.124		
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
TIMM 55-44-029-QRY Created On: 03/17/22 Updated On:	Q	NE	NE	25	22N	16E	Outagamie	0-225-150-2022	0.0	9.0	1.1	5.2	23.6	2.746	2.776	1.083		
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
OZAUKEE -- WI																		
*HARTMAN SPRING LAKE 55-45-004-PIT Created On: 06/12/14 Updated On:	P	SE	NE	3	12N	21E	Ozaukee	0-225-193-2014	0.5	0.0	2.6	8.8	42.1	2.713	2.739	0.943		
Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																		

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse					
	P/Q	Qrt	Qrt	Sect	Town	Range	County	LA Wear (%) 100 500					Sp. Gravity OD SSD		Absorp. % Crse Fine			
OZAUKEE -- WI																		
*HARTMAN SPRING LAKE 55-45-004-PIT Created On: 04/26/19 Updated On:	P	SE	NE	3	12N	21E	Ozaukee	0-225-171-2019	0.4	1.5	0.6	8.4	35.2	2.717	2.746	1.084		
Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																		
PEPIN -- WI																		
DURAND 55-46-002-QRY Created On: 06/08/15 Updated On:	Q	SW	SW	33	25N	13W	Pepin	0-225-190-2015		0.0	3.0	10.4	37.9	2.586	2.654	2.632		
Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																		
DURAND 55-46-002-QRY Created On: 01/03/18 Updated On:	Q	SW	SW	33	25N	13W	Pepin	0-225-28-2018	1.0	0.0	1.8	9.1	34.5	2.588	2.656	2.604		
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
DURAND 55-46-002-QRY Created On: 01/05/21 Updated On:	Q	SW	SW	33	25N	13W	Pepin	0-225-69-2021	1.3	0.0	0.5	8.2	33.0	2.596	2.666	2.675		
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
DURAND 55-46-002-QRY Created On: 01/02/24 Updated On:	Q	SW	SW	33	25N	13W	Pepin	0-225-76-2024	0.8	1.4	4.9	9.8	37.9	2.592	2.660	2.613		
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
PIERCE -- WI																		
DON MILLER 55-47-006-QRY Created On: 06/08/15 Updated On:	Q	N	NE	10	27N	15W	Pierce	0-225-191-2015		0.0	6.3	10.3	36.1	2.555	2.625	2.717		
Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																		

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine		
PIERCE -- WI																			
DON MILLER 55-47-006-QRY Created On: 01/03/18 Updated On:	Q	N	NE	10	27N	15W	Pierce	0-225-34-2018	3.2	0.0	1.1	9.4	34.4	2.559	2.628	2.668			
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																		
DON MILLER 55-47-006-QRY Created On: 01/05/21 Updated On:	Q	N	NE	10	27N	15W	Pierce	0-225-73-2021	2.2	0.0	0.1	8.3	31.8	2.603	2.659	2.146			
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
DON MILLER 55-47-006-QRY Created On: 01/02/24 Updated On:	Q	N	NE	10	27N	15W	Pierce	0-225-77-2024	4.1	0.0	5.8	11.0	39.4	2.550	2.624	2.893			
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
ELMWOOD 55-47-008-QRY Created On: 05/09/16 Updated On:	Q	SE	SE	36	27N	15W	Pierce	0-225-164-2016		0.0	3.9	8.3	30.5	2.666	2.708	1.573			
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																		
ELMWOOD 55-47-008-QRY Created On: 01/07/19 Updated On:	Q	SE	SE	36	27N	15W	Pierce	0-225-64-2019	2.5	0.0	7.8	14.1	45.8	2.493	2.588	3.836			
	Approved Use : CONCRETE, Base Aggregate																		
ELMWOOD 55-47-008-QRY Created On: 04/05/22 Updated On:	Q	SE	SE	36	27N	15W	Pierce	0-225-160-2022	0.5	0.0	8.2	12.4	44.9	2.555	2.627	2.821			
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
ELMWOOD CTH G QUARRY 55-47-036-QRY Created On: 03/27/24 Updated On:	Q	SE	SE	34	27N	15W	Pierce	0-225-208-2024	4.1	0.0	6.1	12.9	41.6	2.562	2.631	2.703			
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Coarse Sp. Gravity		Coarse Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine		
PIERCE -- WI																			
ELMWOOD CTH S QUARRY 55-47-037-QRY Created On: 03/27/24 Updated On:	Q	SE	SW	15	26N	15W	Pierce	0-225-209-2024	7.2	0.0	5.8	7.7	32.7	2.618	2.668	1.893			
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																		
HOLST 55-47-010-PIT Created On: 01/03/18 Updated On:	P		W	33	25N	18W	Pierce	0-225-40-2018	1.5	0.0	1.9	5.5	24.5	2.660	2.699	1.455			
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																		
HOLST 55-47-010-PIT Created On: 08/22/23 Updated On:	P		W	33	25N	18W	Pierce	0-225-247-2023	1.5	0.0	0.6	6.2	25.1	2.645	2.675	1.167			
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
*KAASA 55-47-015-QRY Created On: 01/12/15 Updated On:	Q			15	24N	16W	Pierce	0-225-61-2015		0.0	5.4	11.6	42.0	2.551	2.623	2.801			
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																		
*KAASA 55-47-015-QRY Created On: 01/03/18 Updated On:	Q			15	24N	16W	Pierce	0-225-35-2018	1.4	0.0	5.1	8.3	30.5	2.637	2.683	1.757			
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																		
*KAASA 55-47-015-QRY Created On: 01/05/21 Updated On:	Q			15	24N	16W	Pierce	0-225-72-2021	1.8	0.0	0.6	9.0	32.3	2.660	2.701	1.557			
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
*MILESTONE-WAYNE ANDERSON 55-47-030-QRY Created On: 01/03/18 Updated On:	Q	NW	NE	9	25N	18W	Pierce	0-225-39-2018	2.1	0.0	4.2	8.7	33.4	2.615	2.674	2.258			
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																		

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse					
	P/Q	Qrt	Qrt	Sect	Town	Range	County	LA Wear (%) 100 500					Sp. Gravity OD SSD	Absorp. % Crse Fine				
PIERCE -- WI																		
*MILESTONE-WAYNE ANDERSON 55-47-030-QRY Created On: 01/05/21 Updated On:	Q	NW	NE	9	25N	18W	Pierce	0-225-76-2021	1.9	0.0	0.4	7.7	31.3	2.605	2.667	2.360		
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
MORRISON 55-47-018-QRY Created On: 06/10/16 Updated On:	Q	SE	NW	35	25N	18W	Pierce	0-225-196-2016	2.1	0.0	2.1	7.3	31.2	2.665	2.709	1.622		
Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																		
MORRISON 55-47-018-QRY Created On: 01/07/19 Updated On:	Q	SE	NW	35	25N	18W	Pierce	0-225-62-2019	2.2	0.0	5.7	9.5	38.5	2.614	2.669	2.125		
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
MORRISON 55-47-018-QRY Created On: 03/07/22 Updated On:	Q	SE	NW	35	25N	18W	Pierce	0-225-141-2022		3.2	5.1	8.5	34.9	2.640	2.690	1.900		
Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																		
PRESCOTT 55-47-020-QRY Created On: 09/02/16 Updated On:	Q	NW	NW	12	26N	20W	Pierce	0-225-252-2016		0.0	3.5	8.6	34.8	2.604	2.664	2.321		
Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																		
PRESCOTT 55-47-020-QRY Created On: 01/07/19 Updated On:	Q	NW	NW	12	26N	20W	Pierce	0-225-61-2019	1.2	0.0	7.4	8.4	34.6	2.622	2.679	2.160		
Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																		
PRESCOTT 55-47-020-QRY Created On: 01/04/22 Updated On:	Q	NW	NW	12	26N	20W	Pierce	0-225-75-2022	4.6	7.0	5.2	7.8	33.1	2.635	2.685	1.901		
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse							
	P/Q	Qrt	Qrt	Sect	Town	Range	County	LA Wear (%) 100					500	Sp. Gravity OD SSD		Absorp. % Crse Fine				
PIERCE -- WI																				
*RUMPCA CTH MM 55-47-014-PIT Created On: 01/04/19 Updated On:	P	NE	SE	29	27N	19W	Pierce	0-225-8-2019	1.1	13.3	5.9	6.8	26.3	2.652	2.678	0.962				
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																			
SPRINGVALLEY 55-47-026-QRY Created On: 01/30/14 Updated On:	Q	NE	NE	16	27N	15W	Pierce	0-225-63-2014		0.0	0.7	6.4	30.2	2.596	2.651	2.114				
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																			
SPRINGVALLEY 55-47-026-QRY Created On: 01/05/17 Updated On:	Q	NE	NE	16	27N	15W	Pierce	0-225-44-2017		0.0	0.9	4.4	23.2	2.694	2.725	1.175				
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																			
SPRINGVALLEY 55-47-026-QRY Created On: 03/02/20 Updated On:	Q	NE	NE	16	27N	15W	Pierce	0-225-117-2020	0.1	0.0	0.2	6.3	28.5	2.653	2.698	1.693				
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																			
SPRINGVALLEY 55-47-026-QRY Created On: 01/10/23 Updated On:	Q	NE	NE	16	27N	15W	Pierce	0-225-104-2023	0.9	7.4	0.2	6.0	30.5	2.634	2.686	1.981				
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																			
SVEC 55-47-027-QRY Created On: 03/24/16 Updated On:	Q	E	NW	17	26N	18W	Pierce	0-225-115-2016		0.0	7.8	9.9	34.2	2.609	2.674	2.499				
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																			
SVEC 55-47-027-QRY Created On: 01/07/19 Updated On:	Q	E	NW	17	26N	18W	Pierce	0-225-63-2019	0.5	0.0	5.8	9.2	33.8	2.611	2.675	2.469				
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																			

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
PIERCE -- WI																	
SVEC 55-47-027-QRY Created On: 01/04/22 Updated On:	Q	E	NW	17	26N	18W	Pierce	0-225-77-2022	5.5	16.0	16.4	15.0	45.0	2.551	2.630	3.087	
Approved Use : Base Aggregate																	
SVEC 55-47-027-PIT Created On: 03/15/22 Updated On:	P	E	NW	17	26N	18W	Pierce	0-225-142-2022	2.4	8.7	11.1	10.7	37.6	2.633	2.691	2.177	
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
*TRIMBELLE 55-47-029-QRY Created On: 09/24/20 Updated On:	Q		SW	21	26N	18W	Pierce	0-225-242-2020	3.8	0.0	11.3	12.4	44.8	2.574	2.643	2.668	
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
WIESER 55-47-033-QRY Created On: 06/08/17 Updated On:	Q	E	NE	9	25N	16W	Pierce	0-225-206-2017		0.0	3.9	11.8	40.5	2.581	2.644	2.458	
Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
WIESER 55-47-033-QRY Created On: 06/06/19 Updated On:	Q	E	NE	9	25N	16W	Pierce	0-225-206-2019	1.9	0.0	7.6	9.7	39.9	2.555	2.626	2.814	
Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
WIESER 55-47-033-QRY Created On: 04/19/22 Updated On:	Q	E	NE	9	25N	16W	Pierce	0-225-180-2022	2.8	0.0	4.9	12.8	42.9	2.566	2.637	2.779	
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
POLK -- WI																	
ANTZCAK TRUCKING POLK LIME QUARRY 55-48-034-QRY Created On: 03/17/21 Updated On:	Q	NW	NE	10	32N	18W	Polk	0-225-153-2021	2.3	0.0	6.4	9.7	36.0	2.552	2.637	3.334	
Approved Use : Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse					
	P/Q	Qrt	Qrt	Sect	Town	Range	County	LA Wear (%) 100 500					Sp. Gravity OD SSD		Absorp. % Crse Fine			
POLK -- WI																		
ANTZCAK TRUCKING POLK LIME QUARRY 55-48-034-QRY Created On: 10/14/21 Updated On:	Q	NW	NE	10	32N	18W	Polk		0-225-269-2021	5.3	0.0	15.1	12.3	44.9	2.509	2.604	3.803	
Approved Use : Base Aggregate																		
ANTZCAK TRUCKING POLK LIME QUARRY 55-48-034-QRY Created On: 01/13/22 Updated On:	Q	NW	NE	10	32N	18W	Polk		0-225-113-2022	2.4	0.0	8.8	9.2	38.0	2.529	2.621	3.641	
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
DRESSER TRAP 55-48-007-QRY Created On: 01/05/16 Updated On:	Q			5	33N	18W	Polk		0-225-25-2016		0.0	3.6	4.6	16.8	2.880	2.903	0.792	
Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																		
DRESSER TRAP 55-48-007-QRY Created On: 01/10/22 Updated On:	Q			5	33N	18W	Polk		0-225-108-2022	0.0	1.4	1.2	2.1	9.2	2.933	2.948	0.522	
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
LAKETOWN 55-48-015-QRY Created On: 05/07/15 Updated On:	Q	SW	SE	12	36N	18W	Polk		0-225-149-2015		0.0	0.5	0.9	9.3	2.993	3.000	0.243	
Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																		
LAKETOWN 55-48-015-QRY Created On: 05/21/18 Updated On:	Q	SW	SE	12	36N	18W	Polk		0-225-215-2018	0.0	0.0	1.4	2.5	11.3	2.967	2.979	0.405	
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
LAKETOWN 55-48-015-QRY Created On: 01/04/21 Updated On:	Q	SW	SE	12	36N	18W	Polk		0-225-38-2021	0.0	0.3	0.2	1.7	8.0	2.998	3.009	0.384	
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse					
	P/Q	Qrt	Qrt	Sect	Town	Range	County	LA Wear (%) 100					500	Sp. Gravity OD SSD		Absorp. % Crse Fine		
POLK -- WI																		
LAKETOWN 55-48-015-QRY Created On: 01/04/24 Updated On:	Q	SW	SE	12	36N	18W	Polk	0-225-142-2024	0.0	0.1	0.2	1.9	9.2	2.989	3.001	0.384		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MILESTONE-ANSEL JOHNSON 55-48-013-PIT Created On: 01/05/16 Updated On:	P	NW	SW	35	34N	16W	Polk	0-225-22-2016		0.0	1.6	2.9	14.7	2.744	2.773	1.035		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
MILESTONE-ANSEL JOHNSON 55-48-013-PIT Created On: 01/04/21 Updated On:	P	NW	SW	35	34N	16W	Polk	0-225-37-2021	0.7	1.2	2.3	2.7	14.1	2.747	2.779	1.159		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MILESTONE-WALKER 8 55-48-030-PIT Created On: 06/21/18 Updated On:	P	SE	SE	23	34N	17W	Polk	0-225-238-2018	0.3	0.0	1.6	4.8	17.4	2.823	2.853	1.051		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MILESTONE-WALKER 8 55-48-030-PIT Created On: 05/01/23 Updated On:	P	SE	SE	23	34N	17W	Polk	0-225-209-2023	0.1	0.0	1.1	2.6	13.1	2.854	2.880	0.911		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
OSCEOLA 55-48-018-PIT Created On: 01/09/15 Updated On:	P	NW	SE	16	33N	18W	Polk	0-225-42-2015		0.0	3.4	5.8	18.3	2.780	2.809	1.068		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
OSCEOLA 55-48-018-PIT Created On: 01/02/24 Updated On:	P	NW	SE	16	33N	18W	Polk	0-225-80-2024	4.0	0.0	2.4	5.3	19.9	2.737	2.772	1.263		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse					
	P/Q	Qrt	Qrt	Sect	Town	Range	County	LA Wear (%) 100 500					Sp. Gravity OD SSD		Absorp. % Crse Fine			
PORTAGE -- WI																		
DB 55-49-007-QRY Created On: 06/28/22 Updated On:	Q	SW	SW	1	25N	7E	Portage	0-225-240-2022		0.0	1.3	5.2	21.1	2.680	2.699	0.713		
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																	
*DEWEY 55-49-029-QRY Created On: 07/18/19 Updated On:	Q	NE	SW	25	25N	7E	Portage	0-225-240-2019		0.0	0.0	1.2	6.8	25.7	2.981	3.009	0.950	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
JET BLACK QUARRY 55-49-031-QRY Created On: 03/13/24 Updated On:	Q	NE	SW	25	25N	7E	Portage	0-225-200-2024		0.0	0.0	0.7	4.5	18.3	2.971	2.993	0.733	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MILESTONE SOMERS 55-49-015-PIT Created On: 01/07/15 Updated On:	P	NE	NE	29	23N	9E	Portage	0-225-18-2015		0.0	2.5	6.9	28.8	2.685	2.718	1.206		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
MILESTONE SOMERS 55-49-015-PIT Created On: 01/07/20 Updated On:	P	NE	NE	29	23N	9E	Portage	0-225-43-2020		2.6	0.0	3.9	9.4	33.4	2.663	2.698	1.321	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
PERZINSKI 55-49-018-PIT Created On: 01/07/14 Updated On:	P	SE	SE	20	23N	9E	Portage	0-225-32-2014		0.0	1.5	6.7	27.3	2.681	2.712	1.145		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
PERZINSKI 55-49-018-PIT Created On: 04/15/24 Updated On:	P	SE	SE	20	23N	9E	Portage	0-225-218-2024		1.9	2.2	2.3	6.1	29.3	2.659	2.693	1.263	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse					
	P/Q	Qrt	Qrt	Sect	Town	Range	County	LA Wear (%) 100					500	Sp. Gravity OD SSD		Absorp. % Crse Fine		
PORTAGE -- WI																		
PLOVER 55-49-019-PIT Created On: 03/06/17 Updated On:	P	SW	SW	5	22N	9E	Portage	0-225-74-2017	0.2	0.0	1.8	7.1	29.0	2.661	2.691	1.110		
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
PLOVER 55-49-019-PIT Created On: 02/17/22 Updated On:	P	SW	SW	5	22N	9E	Portage	0-225-131-2022	0.9	0.0	3.2	6.3	27.2	2.652	2.681	1.107		
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
STUCZYNSKI (DUFFEK) 55-49-024-PIT Created On: 09/25/14 Updated On:	P	NE	NW	4	23N	9E	Portage	0-225-267-2014		0.0	2.5	7.6	26.9	2.631	2.661	1.153		
Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																		
STUCZYNSKI (DUFFEK) 55-49-024-PIT Created On: 07/26/21 Updated On:	P	NE	NW	4	23N	9E	Portage	0-225-250-2021	0.6	0.0	0.6	9.4	34.9	2.603	2.637	1.303		
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
WIMMIE 55-49-026-PIT Created On: 01/07/16 Updated On:	P		NW	28	23N	9E	Portage	0-225-43-2016	0.2	0.0	0.8	5.1	24.3	2.705	2.729	0.876		
Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																		
WIMMIE 55-49-026-PIT Created On: 01/04/21 Updated On:	P		NW	28	23N	9E	Portage	0-225-22-2021	0.4	2.2	0.4	6.2	26.9	2.726	2.747	0.792		
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
WIMMIE #2 55-49-030-PIT Created On: 09/05/23 Updated On:	P		SW	21	23N	9E	Portage	0-225-248-2023	1.0	1.6	1.7	6.1	28.2	2.682	2.709	0.997		
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Coarse Sp. Gravity		Coarse Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
PRICE -- WI																		
MILLER 55-50-014-PIT Created On: 05/17/22 Updated On:	P		NE 4	35N	1E	Price	0-225-201-2022	0.0	0.0	4.2	4.1	19.2	2.724	2.752	1.063			
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
NEECK READY MIX 55-50-016-PIT Created On: 03/20/14 Updated On:	P	NW	NW 31	39N	1E	Price	0-225-98-2014		0.0	0.9	3.8	18.1	2.745	2.765	0.739			
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
NEECK READY MIX 55-50-016-PIT Created On: 01/04/19 Updated On:	P	NW	NW 31	39N	1E	Price	0-225-3-2019	1.0	0.0	2.0	4.1	19.0	2.738	2.764	0.924			
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
NEECK READY MIX 55-50-016-PIT Created On: 01/02/24 Updated On:	P	NW	NW 31	39N	1E	Price	0-225-90-2024	0.3	2.6	2.8	3.6	17.5	2.722	2.750	1.034			
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
PHILLIPS 55-50-019-PIT Created On: 01/05/21 Updated On:	P	SW	SW 5	37N	1E	Price	0-225-54-2021	0.8	0.0	1.5	4.0	19.3	2.691	2.720	1.042			
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
PROHASKA 55-50-024-PIT Created On: 06/26/17 Updated On:	P	SW	SW 10	36N	1W	Price	0-225-220-2017		0.0	1.9	4.7	21.5	2.736	2.758	0.829			
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
PROHASKA 55-50-024-PIT Created On: 01/04/22 Updated On:	P	SW	SW 10	36N	1W	Price	0-225-86-2022	1.5	0.0	1.7	4.9	22.5	2.742	2.768	0.933			
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Coarse Sp. Gravity		Coarse Absorp. %			
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine		
PRICE -- WI																			
SMASAL 55-50-028-PIT Created On: 01/09/15 Updated On:	P		SE	25	39N	1W	Price	0-225-50-2015		0.0	1.7	15.5	16.6	2.724	2.751	0.993			
	Approved Use : CONCRETE, OGBC, Base Aggregate																		
SMASAL 55-50-028-PIT Created On: 01/07/20 Updated On:	P		SE	25	39N	1W	Price	0-225-45-2020		0.1	0.0	1.8	3.4	16.6	2.733	2.759	0.923		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
RACINE -- WI																			
A TO Z AGGREGATE SOLUTIONS 55-31-001-PIT Created On: 01/23/17 Updated On:	P		SW	3	3N	19E	Racine	0-225-56-2017		1.9	2.4	1.7	7.0	35.6	2.694	2.732	1.394		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																		
A TO Z AGGREGATE SOLUTIONS 55-31-001-PIT Created On: 01/05/21 Updated On:	P		SW	3	3N	19E	Racine	0-225-80-2021		0.0	8.4	5.3	4.4	23.6	2.680	2.720	1.503		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
BAUMEISTER 55-51-005-PIT Created On: 03/24/16 Updated On:	P		NW	19	2N	19E	Racine	0-225-112-2016		0.0	3.2	5.7	25.5	2.632	2.672	1.516			
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																		
BAUMEISTER 55-51-005-PIT Created On: 01/05/21 Updated On:	P		NW	19	2N	19E	Racine	0-225-83-2021		0.0	0.0	5.1	4.8	25.6	2.671	2.712	1.544		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
BURLINGTON SPRING VALLEY 55-51-006-PIT Created On: 03/24/16 Updated On:	P			6	2N	19E	Racine	0-225-114-2016		2.0	8.5	3.3	7.2	31.9	2.646	2.696	1.913		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																		

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse					
	P/Q	Qrt	Qrt	Sect	Town	Range	County	LA Wear (%) 100 500					Sp. Gravity OD SSD	Absorp. % Crse Fine				
RACINE -- WI BURLINGTON SPRING VALLEY 55-51-006-PIT Created On: 01/05/21 Updated On:	P		6	2N	19E	Racine		0-225-81-2021	0.0	0.0	5.4	4.9	26.3	2.655	2.702	1.768		
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
CLEARWATER ACRES LLP 55-51-056-PIT Created On: 01/09/20 Updated On:	P		NE 17	4N	19E	Racine		0-225-94-2020		0.0	4.6	5.6	28.7	2.625	2.673	1.797		
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
CRETEX-MAIN 55-51-015-PIT Created On: 05/21/18 Updated On:	P		NW 6	2N	19E	Racine		0-225-214-2018	1.8	13.1	7.1	5.5	26.6	2.667	2.708	1.560		
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
CRETEX-MAIN 55-51-015-PIT Created On: 04/05/23 Updated On:	P		NW 6	2N	19E	Racine		0-225-186-2023	1.4	16.2	11.6	7.4	36.9	2.557	2.612	2.148		
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
*CRETEX-WARREN 55-51-007-QRY Created On: 03/24/16 Updated On:	Q		NE 4	2N	19E	Racine		0-225-108-2016		0.0	11.1	7.6	27.3	2.615	2.668	2.026		
Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																		
*CRETEX-WARREN 55-51-007-QRY Created On: 06/18/21 Updated On:	Q		NE 4	2N	19E	Racine		0-225-229-2021	0.0	18.0	10.3	6.1	26.3	2.549	2.630	3.176		
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
HILLSIDE 55-51-010-PIT Created On: 04/02/14 Updated On:	P		SE 7	2N	19E	Racine		0-225-108-2014	0.5	0.0	1.0	5.1	24.4	2.696	2.729	1.239		
Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																		

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse					
	P/Q	Qrt	Qrt	Sect	Town	Range	County					LA Wear (%)		Sp. Gravity		Absorp. %	
											100	500	OD	SSD	Crse	Fine	
RACINE -- WI																	
HILLSIDE 55-51-010-PIT Created On: 02/20/19 Updated On:	P		SE	7	2N	19E	Racine	0-225-107-2019	0.7	7.1	1.8	5.4	26.0	2.663	2.712	1.877	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
HILLSIDE 55-51-010-PIT Created On: 02/28/24 Updated On:	P		SE	7	2N	19E	Racine	0-225-188-2024	2.0	11.7	7.6	5.6	25.7	2.670	2.712	1.603	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
KORDUS AGGREGATES 55-51-057-PIT Created On: 06/25/21 Updated On:	P	S	SW	7	2N	19E	Racine	0-225-235-2021	1.2	10.9	5.3	7.4	31.0	2.656	2.708	1.942	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
*LDV 55-51-055-PIT Created On: 05/13/19 Updated On:	P		SE	NW	5	2N	19E	Racine	0-225-189-2019		0.0	5.6	5.7	27.0	2.681	2.723	1.543
	Approved Use : HMA<MT, HMA>=MT, Base Aggregate																
P&D HONEY CREEK 55-51-020-PIT Created On: 01/04/18 Updated On:	P			NW	6	3N	19E	Racine	0-225-78-2018	0.5	5.8	1.8	4.1	26.4	2.675	2.720	1.666
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
P&D HONEY CREEK 55-51-020-PIT Created On: 01/03/23 Updated On:	P			NW	6	3N	19E	Racine	0-225-74-2023	0.2	11.5	1.3	5.3	24.4	2.673	2.719	1.722
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
PAYNE AND DOLAN / RACINE 55-51-022-QRY Created On: 01/07/14 Updated On:	Q			S	29	4N	23E	Racine	0-225-43-2014	0.1	0.0	0.9	4.7	20.5	2.758	2.785	0.999
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
RACINE -- WI																		
PAYNE AND DOLAN / RACINE 55-51-022-QRY Created On: 02/03/17 Updated On:	Q		S	29	4N	23E	Racine	0-225-57-2017	1.2	0.0	0.9	6.4	27.3	2.633	2.685	1.970		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
PAYNE AND DOLAN / RACINE 55-51-022-QRY Created On: 01/08/20 Updated On:	Q		S	29	4N	23E	Racine	0-225-78-2020	3.2	0.0	4.1	6.3	27.8	2.638	2.693	2.102		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
PAYNE AND DOLAN / RACINE 55-51-022-QRY Created On: 01/03/23 Updated On:	Q		S	29	4N	23E	Racine	0-225-50-2023	0.0	0.4	0.1	5.9	26.0	2.665	2.691	0.999		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
PINE LAKE MATERIALS 55-51-025-PIT Created On: 03/24/16 Updated On:	P		NE	35	3N	19E	Racine	0-225-117-2016	0.6	7.3	2.3	5.7	29.6	2.676	2.724	1.793		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
PINE LAKE MATERIALS 55-51-025-PIT Created On: 01/05/21 Updated On:	P		NE	35	3N	19E	Racine	0-225-82-2021	0.0	14.4	4.8	5.0	25.0	2.654	2.703	1.880		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
*PRAGER 55-51-026-PIT Created On: 01/07/14 Updated On:	P	N	SW	7	4N	19E	Racine	0-225-40-2014	0.4	0.0	1.0	4.6	21.3	2.724	2.754	1.120		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
*PRAGER 55-51-026-PIT Created On: 02/05/19 Updated On:	P	N	SW	7	4N	19E	Racine	0-225-95-2019	1.1	6.6	0.4	4.7	22.8	2.706	2.741	1.305		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse					
	P/Q	Qrt	Qrt	Sect	Town	Range	County					LA Wear (%)		Sp. Gravity		Absorp. %	
												100	500	OD	SSD	Crse	Fine
RACINE -- WI																	
REESMAN-HUGHES PIT 55-51-059-PIT Created On: 06/26/23 Updated On:	P	NW	SW	5	2N	19E	Racine	0-225-235-2023	0.7	17.6	3.0	6.4	23.6	2.629	2.689	2.274	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
*SUPER AGGREGATE / WATERFORD 55-51-028-PIT Created On: 01/06/14 Updated On:	P	SW	SE	28	4N	19E	Racine	0-225-29-2014	0.6	0.0	4.5	6.3	29.5	2.649	2.690	1.544	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
*SUPER AGGREGATE / WATERFORD 55-51-028-PIT Created On: 02/11/19 Updated On:	P	SW	SE	28	4N	19E	Racine	0-225-102-2019	3.1	0.0	7.8	4.6	23.0	2.646	2.692	1.748	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
RICHLAND -- WI																	
ALVA MILLER 55-52-001-QRY Created On: 06/30/16 Updated On:	Q			17	9N	2W	Richland	0-225-219-2016		0.0	2.2	7.3	30.3	2.692	2.727	1.299	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
ALVA MILLER 55-52-001-QRY Created On: 06/20/22 Updated On:	Q			17	9N	2W	Richland	0-225-232-2022	1.2	1.6	1.1	7.9	32.9	2.680	2.718	1.430	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
*BROWN 55-52-027-QRY Created On: 06/02/20 Updated On:	Q			4	11N	1W	Richland	0-225-184-2020	1.3	0.0	0.5	10.0	34.5	2.603	2.661	2.216	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
DOOLEY 55-52-008-QRY Created On: 06/05/15 Updated On:	Q			9	12N	2E	Richland	0-225-187-2015		0.0	1.7	9.2	35.8	2.637	2.685	1.851	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Coarse Sp. Gravity		Coarse Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
RICHLAND -- WI																		
DOOLEY 55-52-008-QRY Created On: 01/04/18 Updated On:	Q		9	12N	2E	Richland		0-225-50-2018	0.5	0.0	3.1	9.1	36.1	2.628	2.683	2.076		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
DOOLEY 55-52-008-QRY Created On: 01/04/21 Updated On:	Q		9	12N	2E	Richland		0-225-31-2021	0.4	0.0	2.2	9.2	35.8	2.615	2.673	2.222		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
DOOLEY 55-52-008-QRY Created On: 01/02/24 Updated On:	Q		9	12N	2E	Richland		0-225-122-2024	0.8	4.6	1.2	9.5	35.6	2.631	2.691	2.285		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
*FRAWLEY 55-52-010-QRY Created On: 06/21/18 Updated On:	Q		9	10N	2W	Richland		0-225-237-2018	0.8	6.3	9.4	10.2	30.6	2.669	2.716	1.752		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
*FRAWLEY 55-52-010-QRY Created On: 03/17/21 Updated On:	Q		9	10N	2W	Richland		0-225-149-2021	1.2	11.2	8.6	12.0	38.9	2.593	2.664	2.737		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
HOUSEHOLDER 55-52-014-QRY Created On: 01/07/14 Updated On:	Q	NW	SE	15	10N	1E	Richland		0-225-37-2014		0.0	8.6	12.7	41.0	2.556	2.624	2.657	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
HOUSEHOLDER 55-52-014-QRY Created On: 05/09/17 Updated On:	Q	NW	SE	15	10N	1E	Richland		0-225-178-2017		0.0	7.0	9.9	37.3	2.569	2.649	3.125	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse					
	P/Q	Qrt	Qrt	Sect	Town	Range	County	LA Wear (%) 100 500					Sp. Gravity OD SSD		Absorp. % Crse Fine			
RICHLAND -- WI																		
HOUSEHOLDER 55-52-014-QRY Created On: 03/12/20 Updated On:	Q	NW	SE	15	10N	1E	Richland	0-225-128-2020	1.9	0.0	2.8	10.6	36.4	2.517	2.600	3.306		
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
HOUSEHOLDER 55-52-014-QRY Created On: 01/03/23 Updated On:	Q	NW	SE	15	10N	1E	Richland	0-225-21-2023	0.3	8.4	0.7	9.4	36.8	2.596	2.660	2.456		
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
KOCH QUARRY 55-52-028-QRY Created On: 05/03/22 Updated On:	Q	SE	NE	18	11N	2E	Richland	0-225-198-2022	0.7	7.5	9.3	11.3	42.4	2.588	2.661	2.816		
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
SHANNON 55-52-021-QRY Created On: 05/19/16 Updated On:	Q	NW	SW	32	10N	1W	Richland	0-225-179-2016	1.0	4.2	4.9	8.4	35.3	2.625	2.677	1.988		
Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																		
SHANNON 55-52-021-QRY Created On: 07/25/19 Updated On:	Q	NW	SW	32	10N	1W	Richland	0-225-249-2019	0.6	3.2	2.5	7.3	33.2	2.662	2.705	1.623		
Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																		
SHANNON 55-52-021-QRY Created On: 04/05/22 Updated On:	Q	NW	SW	32	10N	1W	Richland	0-225-165-2022	0.5	4.5	5.7	8.0	34.4	2.648	2.695	1.803		
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
ROCK -- WI																		
BJOIN 55-53-003-QRY Created On: 06/12/14 Updated On:	Q	SW	SW	36	3N	11E	Rock	0-225-195-2014		0.9	1.1	6.0	27.9	2.640	2.703	2.415		
Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																		

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse								
	P/Q	Qrt	Qrt	Sect	Town	Range	County	LA Wear (%) 100 500					Sp. Gravity OD SSD	Absorp. % Crse Fine							
ROCK -- WI																					
BJOIN 55-53-003-QRY Created On: 03/22/17 Updated On:	Q	SW	SW	36	3N	11E	Rock	0-225-86-2017	0.6	2.6	8.0	7.2	31.1	2.622	2.690	2.597					
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																				
BJOIN 55-53-003-QRY Created On: 03/02/20 Updated On:	Q	SW	SW	36	3N	11E	Rock	0-225-118-2020	0.6	12.3	10.5	7.3	32.1	2.626	2.689	2.400					
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																				
BJOIN 55-53-003-QRY Created On: 01/30/23 Updated On:	Q	SW	SW	36	3N	11E	Rock	0-225-133-2023	0.6	26.4	10.2	8.1	34.8	2.624	2.696	2.733					
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																				
BJOIN 55-53-003-QRY Created On: 03/21/23 Updated On:	Q	SW	SW	36	3N	11E	Rock	0-225-174-2023	0.4	15.0	4.4	5.4	26.7	2.678	2.735	2.129					
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																				
BRAUKHOFF 55-53-004-QRY Created On: 05/17/22 Updated On:	Q	S	SW	26	2N	14E	Rock	0-225-203-2022	0.4	6.5	2.7	7.7	34.7	2.652	2.707	2.091					
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																				
*CCI BELOIT QUARRY 55-53-42-QRY Created On: 08/08/17 Updated On:	Q		NW	22	1N	13E	Rock	0-225-246-2017	1.8	1.8	1.3	7.8	35.1	2.480	2.584	4.225					
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																				
*CCI BELOIT QUARRY 55-53-42-QRY Created On: 07/09/20 Updated On:	Q		NW	22	1N	13E	Rock	0-225-211-2020	2.1	9.2	14.6	9.2	36.6	2.571	2.653	3.188					
	Approved Use : Base Aggregate																				

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse				
	P/Q	Qrt	Qrt	Sect	Town	Range	County					LA Wear (%)		Sp. Gravity		Absorp. %
											100	500	OD	SSD	Crse	Fine
ROCK -- WI																
CRONIN 55-53-006-PIT Created On: 05/18/18 Updated On:	P	S	SE	5	2N	13E	Rock	0-225-212-2018	1.1	0.0	4.2	5.6	27.8	2.663	2.702	1.458
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate															
CRONIN 55-53-006-PIT Created On: 01/03/23 Updated On:	P	S	SE	5	2N	13E	Rock	0-225-13-2023		0.0	1.4	4.8	25.3	2.637	2.679	1.577
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate															
DW 55-53-043-PIT Created On: 05/02/19 Updated On:	P		SW	7	3N	13E	Rock	0-225-174-2019	2.7	0.0	6.2	7.5	33.2	2.608	2.677	2.644
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate															
DW 55-53-043-PIT Created On: 02/10/22 Updated On:	P		SW	7	3N	13E	Rock	0-225-122-2022	5.5	4.3	1.6	8.1	29.0	2.651	2.692	1.551
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate															
EMPIRE LIME 55-53-010-QRY Created On: 08/08/16 Updated On:	Q	SW	NE	21	1N	12E	Rock	0-225-239-2016	1.5	6.3	12.6	11.8	41.4	2.564	2.649	3.333
	Approved Use : Base Aggregate															
EMPIRE LIME 55-53-010-QRY Created On: 03/21/23 Updated On:	Q	SW	NE	21	1N	12E	Rock	0-225-175-2023	0.4	12.2	12.9	11.9	42.0	2.566	2.650	3.286
	Approved Use : Base Aggregate															
*FOOTVILLE ROCK & LIME 55-53-011-QRY Created On: 03/22/19 Updated On:	Q	SE	NW	2	2N	10E	Rock	0-225-115-2019	0.1	5.8	10.5	6.0	28.3	2.648	2.703	2.051
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate															

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
ROCK -- WI																		
*FOOTVILLE ROCK & LIME 55-53-011-QRY Created On: 01/03/23 Updated On:	Q	SE	NW	2	2N	10E	Rock	0-225-61-2023	1.0	16.2	17.4	11.1	40.6	2.570	2.654	3.255		
	Approved Use : Base Aggregate																	
HURD PIT 55-53-017-PIT Created On: 03/30/15 Updated On:	P	NW	SW	15	4N	12E	Rock	0-225-108-2015	4.2	0.0	2.2	5.7	27.5	2.645	2.691	1.736		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
HURD PIT 55-53-017-PIT Created On: 04/20/23 Updated On:	P	NW	SW	15	4N	12E	Rock	0-225-202-2023	4.9	8.0	2.3	5.9	27.1	2.673	2.721	1.814		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
*HURD QUARRY 55-53-044-QRY Created On: 07/02/19 Updated On:	Q	NW	SW	15	4N	12E	Rock	0-225-233-2019		5.1	9.9	7.3	35.1	2.630	2.691	2.326		
	Approved Use : HMA<MT, HMA>=MT, Base Aggregate																	
*HURD QUARRY 55-53-044-QRY Created On: 01/05/21 Updated On:	Q	NW	SW	15	4N	12E	Rock	0-225-78-2021		9.1	6.0	4.8	30.0	2.659	2.712	1.997		
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																	
JANESVILLE SAND & GRAVEL 55-53-018-PIT Created On: 03/02/15 Updated On:	P	SE	SW	24	3N	12E	Rock	0-225-84-2015	2.0	6.2	2.1	6.7	30.0	2.628	2.679	1.925		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
JANESVILLE SAND & GRAVEL 55-53-018-PIT Created On: 01/08/20 Updated On:	P	SE	SW	24	3N	12E	Rock	0-225-50-2020	2.8	0.0	2.7	6.3	29.9	2.624	2.676	1.986		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse							
	P/Q	Qrt	Qrt	Sect	Town	Range	County	LA Wear (%) 100 500					Sp. Gravity OD SSD		Absorp. % Crse Fine					
ROCK -- WI																				
LATHER 55-53-022-PIT Created On: 04/12/16 Updated On:	P	NW	NW	16	1N	13E	Rock	0-225-141-2016	0.9	3.6	4.1	4.7	25.0	2.638	2.679	1.560				
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																			
LATHER 55-53-022-PIT Created On: 02/06/18 Updated On:	P	NW	NW	16	1N	13E	Rock	0-225-88-2018	3.0	0.0	2.2	4.7	23.8	2.640	2.683	1.638				
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																			
LATHER 55-53-022-PIT Created On: 01/07/19 Updated On:	P	NW	NW	16	1N	13E	Rock	0-225-67-2019	3.8	0.0	5.1	5.1	26.9	2.632	2.676	1.690				
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																			
LATHER 55-53-022-PIT Created On: 03/13/24 Updated On:	P	NW	NW	16	1N	13E	Rock	0-225-197-2024	4.9	6.0	1.8	4.4	23.9	2.637	2.677	1.504				
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																			
LITTLE LIMESTONE 55-53-023-QRY Created On: 07/14/14 Updated On:	Q	SW	NE	6	1N	14E	Rock	0-225-220-2014	6.3	2.9	14.7	10.7	39.4	2.500	2.608	4.326				
	Approved Use : Base Aggregate																			
LITTLE LIMESTONE 55-53-023-QRY Created On: 03/29/17 Updated On:	Q	SW	NE	6	1N	14E	Rock	0-225-92-2017	2.2	3.4	14.9	10.8	39.0	2.547	2.634	3.414				
	Approved Use : Base Aggregate																			
LITTLE LIMESTONE 55-53-023-QRY Created On: 03/19/20 Updated On:	Q	SW	NE	6	1N	14E	Rock	0-225-132-2020	3.1	10.1	16.8	10.4	39.8	2.536	2.624	3.457				
	Approved Use : Base Aggregate																			

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse				
	P/Q	Qrt	Qrt	Sect	Town	Range	County					LA Wear (%)		Sp. Gravity		Absorp. %
											100	500	OD	SSD	Crse	Fine
ROCK -- WI																
LITTLE LIMESTONE 55-53-023-QRY Created On: 01/03/23 Updated On:	Q	SW	NE	6	1N	14E	Rock	0-225-2-2023	3.1	13.3	18.0	99.7	46.6	2.484	2.585	4.090
	Approved Use : Base Aggregate															
LITTLE LIMESTONE 55-53-023-QRY Created On: 04/05/23 Updated On:	Q	SW	NE	6	1N	14E	Rock	0-225-190-2023	4.0	9.2	8.8	10.5	39.3	2.640	2.702	2.352
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate															
PRAIRIE AVE S&G 55-53-030-PIT Created On: 02/16/16 Updated On:	P		SW	6	1N	13E	Rock	0-225-87-2016	0.4	2.2	0.8	8.1	39.5	2.669	2.708	1.481
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate															
PRAIRIE AVE S&G 55-53-030-PIT Created On: 02/06/18 Updated On:	P		SW	6	1N	13E	Rock	0-225-87-2018	4.5	0.0	2.4	5.5	26.7	2.672	2.709	1.399
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate															
PRAIRIE AVE S&G 55-53-030-PIT Created On: 01/07/19 Updated On:	P		SW	6	1N	13E	Rock	0-225-68-2019	4.6	0.0	4.7	5.3	26.2	2.654	2.694	1.490
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate															
PRAIRIE AVE S&G 55-53-030-PIT Created On: 01/02/24 Updated On:	P		SW	6	1N	13E	Rock	0-225-1-2024	4.5	0.0	4.1	5.0	25.8	2.662	2.701	1.464
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate															
SILHA MH 55-53-014-QRY Created On: 04/09/14 Updated On:	Q	SW	NE	2	3N	13E	Rock	0-225-117-2014	5.7	1.8	12.3	10.3	41.9	2.481	2.590	4.392
	Approved Use : HMA<E-3, HMA>=E-3, OGBC, Base Aggregate															

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse					
	P/Q	Qrt	Qrt	Sect	Town	Range	County	LA Wear (%) 100 500					Sp. Gravity OD SSD	Absorp. % Crse Fine				
ROCK -- WI																		
SILHA MH 55-53-012-PIT Created On: 04/16/15 Updated On:	P	SW	NE	2	3N	13E	Rock	0-225-121-2015	0.9	0.0	5.1	6.5	30.2	2.650	2.703	2.026		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
SILHA MH 55-53-014-QRY Created On: 04/12/16 Updated On:	Q	SW	NE	2	3N	13E	Rock	0-225-143-2016	0.2	4.0	8.7	8.5	35.5	2.626	2.687	2.347		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
SILHA MH 55-53-014-QRY Created On: 06/02/17 Updated On:	Q	SW	NE	2	3N	13E	Rock	0-225-203-2017	1.1	2.1	7.9	8.1	34.2	2.603	2.669	2.559		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
SILHA MH 55-53-014-QRY Created On: 09/11/19 Updated On:	Q	SW	NE	2	3N	13E	Rock	0-225-269-2019	1.4	2.6	7.2	8.7	37.7	2.587	2.660	2.819		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
SILHA MH 55-53-014-QRY Created On: 06/23/20 Updated On:	Q	SW	NE	2	3N	13E	Rock	0-225-202-2020	1.8	12.3	13.2	9.8	39.3	2.621	2.672	1.928		
	Approved Use : Base Aggregate																	
SILHA MH 55-53-012-PIT Created On: 06/23/20 Updated On:	P	SW	NE	2	3N	13E	Rock	0-225-203-2020	4.3	0.0	5.3	5.4	28.6	2.621	2.672	1.928		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
SILHA MH 55-53-014-QRY Created On: 01/03/23 Updated On:	Q	SW	NE	2	3N	13E	Rock	0-225-14-2023	2.1	6.9	8.7	10.0	39.4	2.553	2.632	3.119		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse						
	P/Q	Qrt	Qrt	Sect	Town	Range	County	LA Wear (%) 100 500					Sp. Gravity OD SSD	Absorp. % Crse Fine					
ROCK -- WI																			
TOWNLINE 55-53-038-PIT Created On: 04/12/16 Updated On:	P	NE	NE	1	1N	12E	Rock	0-225-142-2016	0.7	3.5	3.1	5.3	24.9	2.646	2.688	1.575			
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																		
TOWNLINE 55-53-038-PIT Created On: 02/06/18 Updated On:	P	NE	NE	1	1N	12E	Rock	0-225-89-2018	2.8	0.0	3.4	5.9	26.5	2.639	2.682	1.629			
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
TOWNLINE 55-53-038-PIT Created On: 01/07/19 Updated On:	P	NE	NE	1	1N	12E	Rock	0-225-66-2019	3.1	0.0	3.4	4.5	24.8	2.646	2.689	1.614			
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																		
TOWNLINE 55-53-038-PIT Created On: 03/13/24 Updated On:	P	NE	NE	1	1N	12E	Rock	0-225-198-2024	0.7	8.8	3.0	5.0	24.3	2.689	2.727	1.429			
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
*VAN ALLEN 55-53-040-QRY Created On: 03/30/15 Updated On:	Q	SE	SE	15	2N	13E	Rock	0-225-109-2015	3.8	4.1	15.4	12.1	44.3	2.533	2.623	3.539			
	Approved Use : Base Aggregate																		
*VAN ALLEN 55-53-040-QRY Created On: 06/02/17 Updated On:	Q	SE	SE	15	2N	13E	Rock	0-225-202-2017	0.2	1.4	8.7	9.3	38.7	2.601	2.669	2.632			
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
*VAN ALLEN 55-53-040-QRY Created On: 03/09/20 Updated On:	Q	SE	SE	15	2N	13E	Rock	0-225-126-2020	0.1	2.2	8.2	8.9	36.4	2.576	2.653	3.012			
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse		Absorp. %						
	P/Q	Qrt	Qrt	Sect	Town	Range	County					LA Wear (%) 100 500	Sp. Gravity OD SSD	Crse Fine						
RUSK -- WI																				
BESTWAY 55-54-002-PIT Created On: 01/09/15 Updated On:	P		NW	18	33N	9W	Rusk	0-225-40-2015		0.0	4.8	4.8	20.3	2.724	2.756	1.187				
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																			
BESTWAY 55-54-002-PIT Created On: 01/08/20 Updated On:	P		NW	18	33N	9W	Rusk	0-225-52-2020	0.4	0.0	1.2	4.0	18.8	2.760	2.783	0.837				
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																			
*BURMEISTER 55-54-029-QRY Created On: 08/20/20 Updated On:	Q	NE	SW	33	33N	5W	Rusk	0-225-234-2020	0.3	0.0	0.4	3.3	14.9	2.814	2.830	0.569				
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																			
BURMEISTER 55-54-030-PIT Created On: 01/04/22 Updated On:	P	NE	SW	33	33N	5W	Rusk	0-225-84-2022	0.4	0.0	1.5	3.6	17.6	2.708	2.736	1.037				
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																			
BURMEISTER 55-54-030-PIT Created On: 01/10/23 Updated On:	P	NE	SW	33	33N	5W	Rusk	0-225-108-2023	0.0	0.0	0.2	2.1	9.6	2.878	2.887	0.328				
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																			
GLEN FLORA PETERSON 55-54-020-PIT Created On: 06/24/21 Updated On:	P		NE	30	35N	4W	Rusk	0-225-232-2021	1.3	0.0	1.2	4.7	20.5	2.751	2.777	0.939				
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																			
HAAS 0-M PIT 55-54-032-PIT Created On: 07/27/23 Updated On:	P	NW	SE	19	33N	9W	Rusk	0-225-240-2023	1.9	0.0	1.0	5.1	22.5	2.685	2.712	1.002				
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																			

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse					
	P/Q	Qrt	Qrt	Sect	Town	Range	County	LA Wear (%) 100 500					Sp. Gravity OD SSD		Absorp. % Crse Fine			
RUSK -- WI																		
HAAS LEHMAN PIT 55-54-033-PIT Created On: 07/27/23 Updated On:	P	SE	NE	3	33N	7W	Rusk	0-225-244-2023	0.5	0.0	0.5	3.7	18.1	2.688	2.715	1.000		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
HAWKINS 286 55-54-008-PIT Created On: 01/05/16 Updated On:	P	S	NW	15	35N	3W	Rusk	0-225-24-2016		0.0	1.4	4.3	19.4	2.731	2.751	0.758		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
HAWKINS 286 55-54-008-PIT Created On: 10/12/21 Updated On:	P	S	NW	15	35N	3W	Rusk	0-225-268-2021	0.4	1.2	1.5	3.5	17.4	2.755	2.770	0.579		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
HAWKINS 286 55-54-008-PIT Created On: 01/10/23 Updated On:	P	S	NW	15	35N	3W	Rusk	0-225-115-2023	0.5	0.0	1.3	3.9	20.0	2.718	2.741	0.826		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
HEATH 55-54-009-PIT Created On: 04/11/18 Updated On:	P	NW	NW	30	35N	4W	Rusk	0-225-163-2018	0.5	0.0	2.4	3.8	17.9	2.760	2.785	0.898		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
HEATH 55-54-009-PIT Created On: 01/10/23 Updated On:	P	NW	NW	30	35N	4W	Rusk	0-225-113-2023	0.7	0.0	1.6	3.5	17.4	2.763	2.782	0.705		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
KAZMIERKOWSKI PIT 55-54-011-PIT Created On: 07/12/23 Updated On:	P	SW	SE	9	34N	8W	Rusk	0-225-237-2023	1.3	0.0	0.7	5.4	23.8	2.677	2.697	0.724		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse					
	P/Q	Qrt	Qrt	Sect	Town	Range	County	LA Wear (%)					Sp. Gravity		Absorp. %			
								100					500	OD	SSD	Crse	Fine	
RUSK -- WI																		
LADYSMITH EAST 55-54-012-PIT Created On: 01/03/18 Updated On:	P	S	NW	15	35N	6W	Rusk	0-225-30-2018	1.0	0.0	1.3	4.2	19.1	2.727	2.752	0.906		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
LADYSMITH EAST 55-54-012-PIT Created On: 01/10/23 Updated On:	P	S	NW	15	35N	6W	Rusk	0-225-109-2023	1.1	0.0	2.6	3.8	19.1	2.687	2.718	1.173		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
LADYSMITH WEST 55-54-022-PIT Created On: 03/08/18 Updated On:	P	SE	NW	16	35N	6W	Rusk	0-225-117-2018	1.8	0.0	2.4	4.0	18.9	2.688	2.721	1.225		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
LADYSMITH WEST 55-54-022-PIT Created On: 03/06/23 Updated On:	P	SE	NW	16	35N	6W	Rusk	0-225-163-2023	0.0	0.0	1.0	4.4	19.1	2.733	2.761	1.051		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
NOVAK 55-54-016-PIT Created On: 08/24/17 Updated On:	P	SE	NE	32	34N	9W	Rusk	0-225-261-2017		0.0	2.9	5.1	21.4	2.734	2.764	1.081		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
NOVAK 55-54-016-PIT Created On: 07/19/21 Updated On:	P	SE	NE	32	34N	9W	Rusk	0-225-246-2021	1.1	0.0	0.7	4.0	20.2	2.754	2.774	0.726		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
WEBSTER PIT 55-54-031-PIT Created On: 01/10/23 Updated On:	P	NE	NE	7	34N	4W	Rusk	0-225-116-2023	1.1	0.0	2.2	4.1	18.5	2.768	2.790	0.815		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse						
	P/Q	Qrt	Qrt	Sect	Town	Range	County	LA Wear (%) 100					500	Sp. Gravity OD SSD		Absorp. % Crse Fine			
SAUK -- WI																			
*ALT 55-56-033-QRY Created On: 06/02/20 Updated On:	Q			12	9N	3E	Sauk		0-225-183-2020	1.2	0.0	8.5	10.9	37.6	2.574	2.644	2.715		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
BALFANZ 55-56-001-QRY Created On: 07/16/15 Updated On:	Q	NE	NE	14	10N	5E	Sauk		0-225-211-2015		0.0	3.8	9.0	42.8	2.557	2.628	2.758		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																		
BALFANZ 55-56-001-QRY Created On: 01/03/18 Updated On:	Q	NE	NE	14	10N	5E	Sauk		0-225-24-2018	0.7	6.7	8.1	12.8	45.6	2.527	2.607	3.151		
	Approved Use : HMA<MT, CONCRETE, Base Aggregate																		
BALFANZ 55-56-001-QRY Created On: 04/06/21 Updated On:	Q	NE	NE	14	10N	5E	Sauk		0-225-171-2021	0.6	1.4	1.3	10.9	41.1	2.597	2.655	2.257		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
BALFANZ 55-56-001-QRY Created On: 01/02/24 Updated On:	Q	NE	NE	14	10N	5E	Sauk		0-225-70-2024	0.3	1.7	2.0	11.6	42.5	2.574	2.635	2.381		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
CHARLIE MILLER 55-56-005-QRY Created On: 01/09/15 Updated On:	Q			17	13N	2E	Sauk		0-225-53-2015		0.0	4.6	10.2	36.6	2.615	2.668	2.057		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																		
CHARLIE MILLER 55-56-005-QRY Created On: 01/03/18 Updated On:	Q			17	13N	2E	Sauk		0-225-13-2018	1.0	0.0	1.9	8.5	34.8	2.626	2.676	1.939		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																		

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Coarse Sp. Gravity		Coarse Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
SAUK -- WI																		
CHARLIE MILLER 55-56-005-QRY Created On: 01/04/21 Updated On:	Q			17	13N	2E	Sauk	0-225-24-2021	1.2	0.0	1.7	7.6	32.3	2.626	2.681	2.083		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
CHARLIE MILLER 55-56-005-QRY Created On: 01/02/24 Updated On:	Q			17	13N	2E	Sauk	0-225-123-2024	2.4	6.3	1.5	10.7	38.5	2.599	2.656	2.198		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
HILLPOINT 55-56-010-QRY Created On: 05/14/15 Updated On:	Q		SW	22	11N	3E	Sauk	0-225-175-2015	0.3	1.2	2.5	10.5	41.7	2.629	2.682	2.011		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
HILLPOINT 55-56-010-QRY Created On: 04/10/18 Updated On:	Q		SW	22	11N	3E	Sauk	0-225-158-2018	0.3	0.0	7.6	12.1	44.8	2.609	2.670	2.362		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
HILLPOINT 55-56-010-QRY Created On: 01/29/24 Updated On:	Q		SW	22	11N	3E	Sauk	0-225-152-2024	0.9	7.9	10.9	13.2	45.9	2.575	2.644	2.665		
	Approved Use : HMA<MT, CONCRETE, OGBC, Base Aggregate																	
*HWY 154 QUARRY 55-56-034-QRY Created On: 05/04/21 Updated On:	Q	SW	SW	30	11N	3E	Sauk	0-225-200-2021	3.1	9.8	4.1	11.7	41.4	2.606	2.657	1.943		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
JACKSON 55-56-011-QRY Created On: 01/09/15 Updated On:	Q	SW	SW	6	10N	4E	Sauk	0-225-54-2015		0.0	4.0	11.9	40.5	2.561	2.632	2.764		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
SAUK -- WI																		
JACKSON 55-56-011-QRY Created On: 01/03/18 Updated On:	Q	SW	SW	6	10N	4E	Sauk	0-225-9-2018	1.0	0.0	2.1	8.8	33.8	2.610	2.668	2.230		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
JACKSON 55-56-011-QRY Created On: 01/04/21 Updated On:	Q	SW	SW	6	10N	4E	Sauk	0-225-34-2021	0.5	0.0	0.4	7.9	32.5	2.635	2.685	1.882		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
JACKSON 55-56-011-QRY Created On: 01/29/24 Updated On:	Q	SW	SW	6	10N	4E	Sauk	0-225-153-2024	1.5	5.1	7.7	11.8	42.9	2.577	2.643	2.571		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
*JESSE 55-56-012-PIT Created On: 07/10/14 Updated On:	P	SE	SW	17	11N	7E	Sauk	0-225-219-2014		0.0	2.0	16.6		2.641	2.653	0.481		
	Approved Use : CONCRETE, OGBC, Base Aggregate																	
*JESSE 55-56-012-PIT Created On: 01/04/19 Updated On:	P	SE	SW	17	11N	7E	Sauk	0-225-30-2019	0.7	0.0	0.2	5.7	22.8	2.651	2.658	0.260		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
KLINGAMEYER-LARUE 55-56-015-QRY Created On: 08/16/16 Updated On:	Q		NW	22	11N	5E	Sauk	0-225-245-2016		0.0	0.2	5.5	24.1	2.619	2.632	0.495		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
KLINGAMEYER-LARUE 55-56-015-QRY Created On: 04/06/21 Updated On:	Q		NW	22	11N	5E	Sauk	0-225-170-2021	1.3	0.4	0.5	6.5	26.6	2.599	2.621	0.843		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse					
	P/Q	Qrt	Qrt	Sect	Town	Range	County					LA Wear (%)		Sp. Gravity		Absorp. %	
											100	500	OD	SSD	Crse	Fine	
SAUK -- WI																	
KLINGAMEYER-LARUE 55-56-015-QRY Created On: 01/02/24 Updated On:	Q		NW	22	11N	5E	Sauk	0-225-69-2024	0.5	0.2	0.4	6.0	23.8	2.603	2.627	0.914	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
LEATHERBERRY 55-56-017-PIT Created On: 06/12/14 Updated On:	P	E	NW	26	12N	6E	Sauk	0-225-191-2014		0.0	1.6	7.0	26.8	2.630	2.666	1.370	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
LEATHERBERRY 55-56-017-PIT Created On: 01/08/20 Updated On:	P	E	NW	26	12N	6E	Sauk	0-225-66-2020		0.0	2.1	8.8	29.4	2.649	2.681	1.198	
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																
LINS 55-56-019-QRY Created On: 09/21/15 Updated On:	Q		NW	NE	22	9N	3E	Sauk	0-225-238-2015	3.5	2.7	5.9	10.6	40.5	2.568	2.643	2.897
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
LINS 55-56-019-QRY Created On: 07/24/18 Updated On:	Q		NW	NE	22	9N	3E	Sauk	0-225-257-2018	2.7	3.8	6.5	9.9	38.5	2.587	2.656	2.656
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
LINS 55-56-019-QRY Created On: 04/07/21 Updated On:	Q		NW	NE	22	9N	3E	Sauk	0-225-173-2021	2.6	8.3	7.1	8.5	35.6	2.600	2.665	2.493
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
LINS 55-56-019-QRY Created On: 03/27/24 Updated On:	Q		NW	NE	22	9N	3E	Sauk	0-225-210-2024	1.3	5.8	5.6	8.1	30.0	2.601	2.660	2.259
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Coarse Sp. Gravity		Coarse Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine		
SAUK -- WI																			
*MATOUSHEK 55-56-021-QRY Created On: 07/14/14 Updated On:	Q			28	10N	6E	Sauk	0-225-221-2014		0.0	3.5	9.4	35.7	2.628	2.684	2.136			
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																		
*MATOUSHEK 55-56-021-QRY Created On: 05/11/17 Updated On:	Q			28	10N	6E	Sauk	0-225-185-2017		0.0	4.1	10.7	37.6	2.598	2.661	2.459			
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																		
*MATOUSHEK 55-56-021-QRY Created On: 01/06/20 Updated On:	Q			28	10N	6E	Sauk	0-225-25-2020		0.9	0.0	0.2	8.5	33.6	2.619	2.677	2.204		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
MYKLEBUST 55-56-023-PIT Created On: 01/03/18 Updated On:	P		NE	26	13N	6E	Sauk	0-225-7-2018		1.5	0.0	1.5	6.5	26.3	2.720	2.753	1.219		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																		
MYKLEBUST 55-56-023-PIT Created On: 04/17/23 Updated On:	P		NE	26	13N	6E	Sauk	0-225-199-2023		0.4	0.0	2.6	5.4	24.8	2.697	2.720	0.856		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
ROCK SPRINGS 55-56-024-QRY Created On: 04/17/15 Updated On:	Q		SW	28	12N	5E	Sauk	0-225-127-2015		0.0	0.1	4.0	19.4	2.641	2.649	0.302			
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																		
ROCK SPRINGS 55-56-024-QRY Created On: 02/09/18 Updated On:	Q		SW	28	12N	5E	Sauk	0-225-95-2018		0.2	0.0	0.4	5.6	23.8	2.650	2.658	0.313		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																		

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse				
	P/Q	Qrt	Qrt	Sect	Town	Range	County					LA Wear (%)		Sp. Gravity		Absorp. %
											100	500	OD	SSD	Crse	Fine
SAUK -- WI																
ROCK SPRINGS 55-56-024-QRY Created On: 01/05/21 Updated On:	Q		SW	28	12N	5E	Sauk	0-225-62-2021	0.1	0.2	0.4	5.1	22.2	2.656	2.666	0.351
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate															
ROCK SPRINGS 55-56-024-QRY Created On: 01/02/24 Updated On:	Q		SW	28	12N	5E	Sauk	0-225-124-2024	0.0	0.5	0.3	5.2	22.5	2.657	2.664	0.273
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate															
SCHUCKNECHT 55-56-026-QRY Created On: 09/11/14 Updated On:	Q	SW	SW	25	9N	4E	Sauk	0-225-262-2014		0.0	4.9	8.3	32.9	2.643	2.693	1.901
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate															
SCHUCKNECHT 55-56-026-QRY Created On: 01/03/18 Updated On:	Q	SW	SW	25	9N	4E	Sauk	0-225-10-2018	0.1	0.0	1.2	8.1	31.4	2.644	2.696	1.973
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate															
SCHUCKNECHT 55-56-026-QRY Created On: 01/04/21 Updated On:	Q	SW	SW	25	9N	4E	Sauk	0-225-32-2021	0.5	0.0	0.4	8.9	33.1	2.635	2.690	2.091
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate															
SCHUCKNECHT 55-56-026-QRY Created On: 01/02/24 Updated On:	Q	SW	SW	25	9N	4E	Sauk	0-225-21-2024	0.4	7.3	1.5	8.8	33.0	2.653	2.703	1.892
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate															
ZOBEL 55-56-031-QRY Created On: 06/05/15 Updated On:	Q			21	12N	4E	Sauk	0-225-188-2015		0.0	1.5	10.3	36.7	2.620	2.673	2.006
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate															

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
SAUK -- WI																	
ZOBEL 55-56-031-QRY Created On: 01/04/18 Updated On:	Q		21	12N	4E	Sauk	0-225-51-2018	0.4	0.0	1.7	9.1	35.2	2.631	2.682	1.951		
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
ZOBEL 55-56-031-QRY Created On: 01/04/21 Updated On:	Q		21	12N	4E	Sauk	0-225-33-2021	0.6	0.0	0.6	11.4	39.0	2.584	2.644	2.334		
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
ZOBEL 55-56-031-QRY Created On: 01/02/24 Updated On:	Q		21	12N	4E	Sauk	0-225-22-2024	0.7	12.9	1.4	8.6	33.4	2.653	2.699	1.758		
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
SAWYER -- WI																	
*HAYWARD SAND AND GRAVEL 55-57-016-PIT Created On: 03/05/19 Updated On:	P	E	SE	10	41N	9W	Sawyer	0-225-109-2019	2.7	0.0	6.0	4.6	18.8	2.780	2.813	1.178	
Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
MROTEK 55-57-013-PIT Created On: 01/03/18 Updated On:	P		SW	1	41N	8W	Sawyer	0-225-16-2018	0.8	0.0	2.2	3.6	15.8	2.810	2.837	0.969	
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MROTEK 55-57-013-PIT Created On: 01/03/23 Updated On:	P		SW	1	41N	8W	Sawyer	0-225-57-2023	1.9	1.5	1.1	3.8	16.1	2.769	2.800	1.122	
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
OLSON 55-57-017-PIT Created On: 02/13/17 Updated On:	P	NW	SW	14	41N	9W	Sawyer	0-225-71-2017		0.0	4.6	3.1	15.6	2.815	2.840	0.882	
Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse					
	P/Q	Qrt	Qrt	Sect	Town	Range	County	LA Wear (%) 100 500					Sp. Gravity OD SSD	Absorp. % Crse Fine				
SAWYER -- WI																		
OLSON 55-57-017-PIT Created On: 01/10/22 Updated On:	P	NW	SW	14	41N	9W	Sawyer	0-225-105-2022	1.7	3.7	4.9	3.6	16.3	2.778	2.808	1.089		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
POINT SPORT 55-57-020-PIT Created On: 01/03/18 Updated On:	P		NE	2	41N	7W	Sawyer	0-225-19-2018	0.9	0.0	1.5	4.1	18.3	2.763	2.788	0.877		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
POINT SPORT 55-57-020-PIT Created On: 01/03/23 Updated On:	P		NE	2	41N	7W	Sawyer	0-225-58-2023	0.2	0.9	1.5	3.5	16.4	2.756	2.787	1.133		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
SAND LAKE 55-57-023-PIT Created On: 01/25/16 Updated On:	P	NW	NW	15	38N	9W	Sawyer	0-225-78-2016		0.0	1.6	4.2	17.0	2.787	2.816	1.030		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
SAND LAKE 55-57-023-PIT Created On: 05/23/23 Updated On:	P	NW	NW	15	38N	9W	Sawyer	0-225-226-2023	1.4	0.0	0.8	4.5	19.6	2.750	2.773	0.843		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
SKILLE V 55-57-025-PIT Created On: 01/23/14 Updated On:	P	NW	NE	33	40N	9W	Sawyer	0-225-56-2014		0.0	3.4	6.2	21.8	2.779	2.811	1.130		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
SKILLE V 55-57-025-PIT Created On: 05/02/19 Updated On:	P	NW	NE	33	40N	9W	Sawyer	0-225-175-2019	1.1	0.0	1.8	3.4	15.3	2.836	2.858	0.787		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse						
	P/Q	Qrt	Qrt	Sect	Town	Range	County	LA Wear (%) 100 500					Sp. Gravity OD SSD	Absorp. % Crse Fine					
SAWYER -- WI																			
SKILLE V 55-57-025-PIT Created On: 01/04/24 Updated On:	P	NW	NE	33	40N	9W	Sawyer	0-225-140-2024	1.9	4.4	2.5	4.2	18.1	2.776	2.811	1.259			
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
SHAWANO -- WI																			
BONDUEL 55-58-002-QRY Created On: 01/20/16 Updated On:	Q		NE	29	25N	17E	Shawano	0-225-60-2016		1.1	0.9	7.2	30.9	2.719	2.749	1.102			
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																		
BONDUEL 55-58-002-QRY Created On: 01/04/19 Updated On:	Q		NE	29	25N	17E	Shawano	0-225-14-2019		4.3	0.7	6.3	31.0	2.721	2.752	1.162			
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																		
BONDUEL 55-58-002-QRY Created On: 01/04/22 Updated On:	Q		NE	29	25N	17E	Shawano	0-225-35-2022	0.0	2.9	1.8	6.3	28.3	2.717	2.747	1.083			
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
GRUNEWALD 55-58-009-QRY Created On: 05/10/18 Updated On:	Q			33	27N	17E	Shawano	0-225-206-2018	0.0	6.2	3.4	7.8	32.4	2.715	2.753	1.389			
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
GRUNEWALD 55-58-009-QRY Created On: 04/30/21 Updated On:	Q			33	27N	17E	Shawano	0-225-198-2021	0.9	2.3	6.4	8.1	34.6	2.687	2.733	1.703			
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
GRUNEWALD 55-58-009-QRY Created On: 01/02/24 Updated On:	Q			33	27N	17E	Shawano	0-225-68-2024	0.0	3.9	3.7	8.2	35.1	2.676	2.719	1.606			
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
SHAWANO -- WI																		
KROENING 55-58-014-QRY Created On: 01/07/15 Updated On:	Q			24	26N	17E	Shawano	0-225-16-2015		11.1	12.8	7.5	28.7	2.674	2.721	1.762		
KROENING 55-58-014-QRY Created On: 01/04/18 Updated On:	Q			24	26N	17E	Shawano	0-225-58-2018	0.6	11.6	15.2	8.8	32.3	2.640	2.696	2.126		
KROENING 55-58-014-QRY Created On: 01/04/19 Updated On:	Q			24	26N	17E	Shawano	0-225-38-2019	1.4	20.7	15.4	7.2	28.0	2.638	2.698	2.278		
KROENING 55-58-014-QRY Created On: 01/02/20 Updated On:	Q			24	26N	17E	Shawano	0-225-10-2020	1.6	14.3	13.1	7.0	28.2	2.662	2.713	1.937		
KROENING 55-58-014-QRY Created On: 01/03/23 Updated On:	Q			24	26N	17E	Shawano	0-225-78-2023	1.8	8.0	7.0	6.0	25.7	2.715	2.748	1.198		
MCKEEFRY 55-58-021-QRY Created On: 01/27/14 Updated On:	Q	NW		23	25N	18E	Shawano	0-225-60-2014		0.2	1.7	4.5	19.3	2.781	2.799	0.657		
MCKEEFRY 55-58-021-QRY Created On: 03/30/15 Updated On:	Q	NW		23	25N	18E	Shawano	0-225-106-2015	0.9	2.2	2.2	4.9	21.5	2.776	2.796	0.723		

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse				
	P/Q	Qrt	Qrt	Sect	Town	Range	County					LA Wear (%)		Sp. Gravity		Absorp. %
											100	500	OD	SSD	Crse	Fine
SHAWANO -- WI																
MCKEEFRY 55-58-021-QRY Created On: 02/16/16 Updated On:	Q		NW 23	25N	18E	Shawano	0-225-85-2016	0.1	2.4	0.4	5.2	22.6	2.765	2.786	0.749	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate															
MCKEEFRY 55-58-021-QRY Created On: 05/24/19 Updated On:	Q		NW 23	25N	18E	Shawano	0-225-196-2019	0.7	9.6	3.1	5.7	25.1	2.746	2.773	1.014	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate															
MCKEEFRY 55-58-021-QRY Created On: 05/17/22 Updated On:	Q		NW 23	25N	18E	Shawano	0-225-207-2022	0.3	7.7	0.6	6.2	30.0	2.747	2.772	0.921	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate															
MCKEEFRY #3 55-58-049-QRY Created On: 10/19/17 Updated On:	Q	N	SW 14	25N	18E	Shawano	0-225-282-2017	0.2	5.2	2.7	6.1	25.7	2.748	2.779	1.112	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate															
MCKEEFRY #3 55-58-049-QRY Created On: 04/08/20 Updated On:	Q	N	SW 14	25N	18E	Shawano	0-225-145-2020	0.5	2.2	3.4	5.5	23.9	2.767	2.790	0.861	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate															
MCKEEFRY #3 55-58-049-QRY Created On: 06/12/23 Updated On:	Q	N	SW 14	25N	18E	Shawano	0-225-228-2023	0.0	17.0	10.1	4.8	30.4	2.703	2.743	1.501	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate															
PETERS-BONDUEL 55-58-050-PIT Created On: 01/06/21 Updated On:	P		NW NE 30	26N	17E	Shawano	0-225-110-2021	3.4	4.9	4.9	9.7	35.2	2.645	2.694	1.844	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate															

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse					
	P/Q	Qrt	Qrt	Sect	Town	Range	County	LA Wear (%) 100 500					Sp. Gravity OD SSD		Absorp. % Crse Fine			
SHAWANO -- WI																		
SHAWANO 55-58-036-QRY Created On: 05/11/15 Updated On:	Q	NE	NW	2	26N	16E	Shawano	0-225-164-2015	0.4	3.1	2.5	8.8	33.8	2.684	2.727	1.613		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
SHAWANO 55-58-036-QRY Created On: 01/04/18 Updated On:	Q	NE	NW	2	26N	16E	Shawano	0-225-61-2018		2.4	2.3	6.7	30.8	2.700	2.734	1.259		
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																	
SHAWANO 55-58-036-QRY Created On: 01/04/21 Updated On:	Q	NE	NW	2	26N	16E	Shawano	0-225-11-2021	0.2	4.1	3.1	5.3	26.5	2.699	2.737	1.410		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
SHAWANO 55-58-036-QRY Created On: 01/02/24 Updated On:	Q	NE	NW	2	26N	16E	Shawano	0-225-8-2024	0.0	2.3	0.3	5.7	26.9	2.722	2.754	1.151		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
ZEINERT 55-58-045-PIT Created On: 05/12/16 Updated On:	P	SE	SW	3	28N	12E	Shawano	0-225-170-2016	0.4	0.0	0.9	8.8	34.6	2.631	2.662	1.205		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
ZEINERT 55-58-045-PIT Created On: 01/04/21 Updated On:	P	SE	SW	3	28N	12E	Shawano	0-225-16-2021	0.3	1.4	2.1	9.6	34.0	2.641	2.665	0.920		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
SHEBOYGAN -- WI																		
BADGERLAND BISON 55-59-003-PIT Created On: 01/04/16 Updated On:	P	SW	NE	19	15N	20E	Sheboygan	0-225-5-2016	2.0	0.7	0.9	5.9	29.2	2.744	2.770	0.961		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Coarse Sp. Gravity		Coarse Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
SHEBOYGAN -- WI																		
BADGERLAND BISON 55-59-003-PIT Created On: 03/10/21 Updated On:	P	SW	NE	19	15N	20E	Sheboygan	0-225-132-2021	2.0	2.8	2.8	6.5	31.6	2.735	2.765	1.079		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
BATES RD PIT 55-59-024-PIT Created On: 02/17/22 Updated On:	P	E	SE	33	14N	21E	Sheboygan	0-225-129-2022	0.1	2.5	3.2	10.0	38.5	2.715	2.749	1.239		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
DIPPEL 55-59-005-PIT Created On: 02/15/18 Updated On:	P	NE	SE	32	15N	20E	Sheboygan	0-225-100-2018		1.8	1.3	6.6	30.2	2.728	2.760	1.155		
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																	
DIPPEL 55-59-005-PIT Created On: 01/03/23 Updated On:	P	NE	SE	32	15N	20E	Sheboygan	0-225-47-2023	1.4	0.0	0.7	7.2	32.5	2.720	2.754	1.254		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
KRAEMER 55-59-008-PIT Created On: 01/21/16 Updated On:	P	SW	NE	13	14N	20E	Sheboygan	0-225-64-2016	0.5	0.0	0.8	6.0	28.8	2.752	2.778	0.927		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
KRAEMER 55-59-008-PIT Created On: 01/05/21 Updated On:	P	SW	NE	13	14N	20E	Sheboygan	0-225-108-2021	0.5	2.2	0.7	5.6	26.9	2.740	2.767	0.981		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MICHELS BEECHWOOD 55-59-023-PIT Created On: 01/05/21 Updated On:	P	W	NE	4	13N	20E	Sheboygan	0-225-85-2021	0.6	0.0	3.7	9.5	35.9	2.715	2.753	1.391		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse		Absorp. %			
	P/Q	Qrt	Qrt	Sect	Town	Range	County					LA Wear (%) 100 500	Sp. Gravity OD SSD	Crse Fine			
ST. CROIX -- WI DOWNING (RIEMANN) 55-55-004-QRY Created On: 06/20/22 Updated On:	Q	E	SE	1	29N	15W	St. Croix	0-225-231-2022	2.2	1.2	5.8	11.2	46.6	2.542	2.623	3.188	
	Approved Use : HMA<MT, CONCRETE, OGBC, Base Aggregate																
GILLEN 55-55-006-QRY Created On: 06/26/14 Updated On:	Q	E	NW	10	30N	17W	St. Croix	0-225-205-2014		0.0	4.9	9.9	35.8	2.637	2.691	2.011	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
GILLEN 55-55-006-QRY Created On: 04/06/17 Updated On:	Q	E	NW	10	30N	17W	St. Croix	0-225-117-2017		0.0	1.1	10.9	39.7	2.605	2.666	2.322	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
GILLEN 55-55-006-QRY Created On: 01/08/20 Updated On:	Q	E	NW	10	30N	17W	St. Croix	0-225-54-2020	1.6	0.0	17.0	12.5	42.2	2.599	2.663	2.479	
	Approved Use : Base Aggregate																
GILLEN 55-55-006-QRY Created On: 01/03/23 Updated On:	Q	E	NW	10	30N	17W	St. Croix	0-225-54-2023	0.5	0.0	10.4	11.7	39.3	2.579	2.656	2.966	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
MCNAMARA 55-55-007-QRY Created On: 04/21/17 Updated On:	Q	SE	NW	25	31N	15W	St. Croix	0-225-145-2017		0.0	5.2	10.4	38.0	2.558	2.633	2.956	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
MCNAMARA 55-55-007-QRY Created On: 01/06/20 Updated On:	Q	SE	NW	25	31N	15W	St. Croix	0-225-27-2020	1.8	0.0	7.5	10.2	34.7	2.533	2.620	3.440	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse					
	P/Q	Qrt	Qrt	Sect	Town	Range	County	LA Wear (%) 100					500	Sp. Gravity OD SSD		Absorp. % Crse Fine		
ST. CROIX -- WI																		
MCNAMARA 55-55-007-QRY Created On: 04/05/23 Updated On:	Q	SE	NW	25	31N	15W	St. Croix	0-225-187-2023	6.2	0.0	10.0	11.8	40.8	2.511	2.598	3.462		
Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																		
MIMBACH 55-55-008-QRY Created On: 01/08/15 Updated On:	Q	SW	NW	5	28N	19W	St. Croix	0-225-38-2015		0.0	6.4	7.6	29.5	2.694	2.735	1.497		
Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																		
MIMBACH 55-55-008-QRY Created On: 04/21/17 Updated On:	Q	SW	NW	5	28N	19W	St. Croix	0-225-140-2017	0.1	0.0	2.7	6.7	28.5	2.675	2.720	1.702		
Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																		
MIMBACH 55-55-008-QRY Created On: 01/08/20 Updated On:	Q	SW	NW	5	28N	19W	St. Croix	0-225-60-2020	2.2	0.0	8.1	10.0	37.8	2.562	2.639	2.990		
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
MIMBACH 55-55-008-QRY Created On: 01/03/23 Updated On:	Q	SW	NW	5	28N	19W	St. Croix	0-225-55-2023	0.7	7.7	12.4	13.9	44.8	2.559	2.642	3.214		
Approved Use : CONCRETE, OGBC, Base Aggregate																		
MIMBACH 55-55-008-QRY Created On: 03/01/23 Updated On:	Q	SW	NW	5	28N	19W	St. Croix	0-225-161-2023	0.3	2.6	2.3	8.2	32.7	2.643	2.700	2.160		
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
RIVARD 55-55-012-QRY Created On: 01/12/15 Updated On:	Q	SE	NE	12	30N	20W	St. Croix	0-225-63-2015		0.0	10.9	12.2	39.7	2.522	2.611	3.564		
Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																		

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse				
	P/Q	Qrt	Qrt	Sect	Town	Range	County					LA Wear (%)		Sp. Gravity		Absorp. %
											100	500	OD	SSD	Crse	Fine
ST. CROIX -- WI																
TAMMEC QUARRY 55-55-017-QRY Created On: 01/08/15 Updated On:	Q		SW	16	30N	18W	St. Croix	0-225-39-2015	4.9	0.0	10.3	12.2	41.8	2.497	2.579	3.319
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate															
TAMMEC QUARRY 55-55-017-QRY Created On: 04/21/17 Updated On:	Q		SW	16	30N	18W	St. Croix	0-225-144-2017	2.8	0.0	6.7	9.2	35.1	2.562	2.626	2.475
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate															
TAMMEC QUARRY 55-55-017-QRY Created On: 05/04/20 Updated On:	Q		SW	16	30N	18W	St. Croix	0-225-165-2020	2.6	0.0	7.1	9.5	37.0	2.572	2.644	2.800
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate															
TAMMEC QUARRY 55-55-017-QRY Created On: 01/03/23 Updated On:	Q		SW	16	30N	18W	St. Croix	0-225-53-2023	9.1	14.4	4.2	12.0	43.2	2.481	2.564	3.359
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate															
UTECHT 55-55-018-PIT Created On: 01/12/15 Updated On:	P	NE	NE	21	30N	18W	St. Croix	0-225-62-2015		0.0	4.1	5.5	22.4	2.644	2.683	1.496
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate															
UTECHT 55-55-018-PIT Created On: 01/30/20 Updated On:	P	NE	NE	21	30N	18W	St. Croix	0-225-102-2020	1.1	0.0	5.5	6.0	24.8	2.634	2.678	1.662
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate															
TAYLOR -- WI																
BROOKS 55-60-003-PIT Created On: 08/08/17 Updated On:	P	SW	SE	7	33N	3W	Taylor	0-225-247-2017		0.0	2.2	5.3	21.5	2.734	2.765	1.125
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate															

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse					
	P/Q	Qrt	Qrt	Sect	Town	Range	County	LA Wear (%) 100 500					Sp. Gravity OD SSD		Absorp. % Crse Fine			
TAYLOR -- WI																		
BROOKS 55-60-003-PIT Created On: 01/04/22 Updated On:	P	SW	SE	7	33N	3W	Taylor	0-225-81-2022	1.1	0.0	3.8	3.9	19.8	2.697	2.731	1.242		
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
CHELSEA 55-60-036-PIT Created On: 01/02/24 Updated On:	P	N	SE	10	32N	1E	Taylor	0-225-114-2024	0.5	0.0	3.4	3.1	17.2	2.688	2.716	1.029		
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
DUESSING 55-60-007-PIT Created On: 06/26/17 Updated On:	P	N	SW	33	32N	1E	Taylor	0-225-221-2017		0.0	0.6	3.5	17.4	2.743	2.769	0.947		
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
DUESSING 55-60-007-PIT Created On: 06/28/22 Updated On:	P	N	SW	33	32N	1E	Taylor	0-225-238-2022	0.7	0.0	2.0	4.1	18.4	2.742	2.768	0.948		
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
FOSTERS 55-60-008-PIT Created On: 07/07/22 Updated On:	P	NW	SE	20	33N	3W	Taylor	0-225-244-2022	1.9	0.0	3.3	4.5	21.1	2.711	2.739	1.036		
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
GOSBEE 55-60-009-PIT Created On: 06/26/17 Updated On:	P	SE	NE	28	32N	1E	Taylor	0-225-219-2017		0.0	0.6	4.2	19.4	2.697	2.733	1.354		
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
GOSBEE 55-60-009-PIT Created On: 06/28/22 Updated On:	P	SE	NE	28	32N	1E	Taylor	0-225-242-2022	0.6	0.0	2.7	4.1	18.0	2.728	2.753	0.921		
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse					
	P/Q	Qrt	Qrt	Sect	Town	Range	County	LA Wear (%)					Sp. Gravity		Absorp. %			
												100	500	OD	SSD	Crse	Fine	
TAYLOR -- WI																		
HAAS EMSTROM PIT 55-60-035-PIT Created On: 07/27/23 Updated On:	P	NE	NW	3	31N	2W	Taylor	0-225-243-2023	1.8	0.0	1.5	4.5	21.2	2.742	2.762	0.718		
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
JUMP RIVER 55-60-015-QRY Created On: 07/07/22 Updated On:	Q	NE	SE	14	33N	4W	Taylor	0-225-247-2022	0.0	0.0	0.5	4.7	21.6	2.662	2.676	0.519		
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
JUMP RIVER PIT 55-60-037-PIT Created On: 01/02/24 Updated On:	P	SW	NE	13	33N	4W	Taylor	0-225-115-2024	0.2	0.0	5.5	4.3	19.9	2.732	2.770	1.387		
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
KRUG 55-60-012-PIT Created On: 08/07/14 Updated On:	P			28	32N	1E	Taylor	0-225-241-2014		0.0	0.2	4.4	20.5	2.703	2.737	1.245		
Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																		
KRUG 55-60-012-PIT Created On: 05/24/19 Updated On:	P			28	32N	1E	Taylor	0-225-201-2019	0.1	0.0	1.7	3.9	17.5	2.723	2.750	0.972		
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
KRUG 55-60-012-PIT Created On: 01/02/24 Updated On:	P			28	32N	1E	Taylor	0-225-112-2024	0.1	0.0	4.2	3.8	17.9	2.717	2.751	1.222		
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
LISSNER 55-60-014-PIT Created On: 01/09/15 Updated On:	P		SW	27	32N	1E	Taylor	0-225-46-2015		0.0	2.7	3.7	17.7	2.718	2.749	1.133		
Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																		

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Coarse Sp. Gravity		Coarse Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
TAYLOR -- WI																		
LISSNER 55-60-014-PIT Created On: 01/08/20 Updated On:	P		SW	27	32N	1E	Taylor	0-225-48-2020	1.0	0.0	2.6	4.2	18.8	2.760	2.781	0.771		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MAIN PIT 55-60-016-PIT Created On: 01/10/23 Updated On:	P	NE	SE	14	33N	4W	Taylor	0-225-114-2023	0.4	0.0	1.9	4.2	20.3	2.727	2.751	0.902		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MAYER 55-60-017-PIT Created On: 06/26/17 Updated On:	P	SE	SW	2	32N	1E	Taylor	0-225-218-2017		0.0	2.5	4.9	21.9	2.739	2.766	1.004		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MAYER 55-60-017-PIT Created On: 01/10/23 Updated On:	P	SE	SW	2	32N	1E	Taylor	0-225-112-2023	0.2	0.0	4.0	5.2	23.7	2.762	2.792	1.080		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
NEUMAN 55-60-018-PIT Created On: 06/26/17 Updated On:	P	NE	SE	28	32N	1E	Taylor	0-225-222-2017		0.0	0.6	3.5	17.8	2.729	2.758	1.052		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
NEUMAN 55-60-018-PIT Created On: 06/28/22 Updated On:	P	NE	SE	28	32N	1E	Taylor	0-225-239-2022	1.1	0.0	2.4	3.6	17.3	2.751	2.778	0.995		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
OVYN 55-60-020-QRY Created On: 02/14/17 Updated On:	Q	NE	SW	28	30N	2W	Taylor	0-225-72-2017		0.0	0.2	3.2	15.2	3.004	3.024	0.683		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse					
	P/Q	Qrt	Qrt	Sect	Town	Range	County	LA Wear (%) 100 500					Sp. Gravity OD SSD	Absorp. % Crse Fine				
TAYLOR -- WI																		
*SHADY NOOK 55-60-032-QRY Created On: 05/21/21 Updated On:	Q	NW	SW	23	30N	2W	Taylor	0-225-211-2021	0.0	0.0	0.3	4.8	21.9	2.735	2.747	0.467		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
TREMPEALEAU -- WI																		
ARCADIA 55-61-003-QRY Created On: 01/16/14 Updated On:	Q	NW	SE	16	20N	9W	Trempealeau	0-225-50-2014		0.0	10.4	11.3	41.6	2.563	2.631	2.648		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
ARCADIA 55-61-003-QRY Created On: 04/25/17 Updated On:	Q	NW	SE	16	20N	9W	Trempealeau	0-225-150-2017		0.0	2.3	12.5	43.4	2.536	2.613	3.068		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
ARCADIA 55-61-003-QRY Created On: 06/02/20 Updated On:	Q	NW	SE	16	20N	9W	Trempealeau	0-225-185-2020	0.8	0.0	4.5	8.6	37.7	2.554	2.635	3.170		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
ARCADIA 55-61-003-QRY Created On: 01/03/23 Updated On:	Q	NW	SE	16	20N	9W	Trempealeau	0-225-64-2023	1.8	0.8	3.6	10.6	42.9	2.548	2.614	2.607		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
BONDLEI 55-61-004-QRY Created On: 03/13/17 Updated On:	Q	NE	SW	20	20N	8W	Trempealeau	0-225-81-2017	0.5	0.0	4.5	8.8	34.8	2.612	2.668	2.142		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
BONDLEI 55-61-004-QRY Created On: 03/12/20 Updated On:	Q	NE	SW	20	20N	8W	Trempealeau	0-225-129-2020	0.0	0.0	9.4	12.7	40.5	2.544	2.623	3.084		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse					
	P/Q	Qrt	Qrt	Sect	Town	Range	County	LA Wear (%) 100 500					Sp. Gravity OD SSD		Absorp. % Crse Fine			
TREMPEALEAU -- WI																		
BONDLEI 55-61-004-QRY Created On: 04/04/23 Updated On:	Q	NE	SW	20	20N	8W	Trempealeau	0-225-178-2023	0.0	0.0	5.5	8.4	34.2	2.595	2.658	2.396		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
HAEF 55-61-007-PIT Created On: 03/28/17 Updated On:	P	SW	NE	19	18N	8W	Trempealeau	0-225-90-2017		0.0	0.3	4.3	19.1	2.630	2.664	1.291		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
HAEF 55-61-007-PIT Created On: 01/04/22 Updated On:	P	SW	NE	19	18N	8W	Trempealeau	0-225-50-2022	0.0	0.3	0.5	3.2	14.5	2.635	2.674	1.478		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
IRVINE 55-61-009-QRY Created On: 07/02/15 Updated On:	Q	SW	NE	18	19N	7W	Trempealeau	0-225-205-2015		0.0	2.5	10.4	38.3	2.591	2.648	2.208		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
IRVINE 55-61-009-QRY Created On: 01/04/18 Updated On:	Q	SW	NE	18	19N	7W	Trempealeau	0-225-48-2018	0.7	0.0	5.8	9.3	36.2	2.603	2.667	2.483		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
IRVINE 55-61-009-QRY Created On: 01/04/21 Updated On:	Q	SW	NE	18	19N	7W	Trempealeau	0-225-4-2021	1.3	0.0	2.8	9.6	35.9	2.610	2.666	2.135		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
IRVINE 55-61-009-QRY Created On: 01/02/24 Updated On:	Q	SW	NE	18	19N	7W	Trempealeau	0-225-24-2024	0.6	7.8	10.6	13.5	46.5	2.572	2.645	2.820		
	Approved Use : CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse					
	P/Q	Qrt	Qrt	Sect	Town	Range	County	LA Wear (%) 100					500	Sp. Gravity OD SSD		Absorp. % Crse Fine		
TREMPEALEAU -- WI																		
TWESME 55-61-020-QRY Created On: 01/30/15 Updated On:	Q	SW	SE	34	21N	8W	Trempealeau	0-225-83-2015		0.0	7.1	12.1	41.4	2.590	2.651	2.378		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
TWESME 55-61-020-QRY Created On: 01/04/18 Updated On:	Q	SW	SE	34	21N	8W	Trempealeau	0-225-45-2018	1.4	0.0	6.0	13.1	42.2	2.578	2.646	2.646		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
TWESME 55-61-020-QRY Created On: 01/04/21 Updated On:	Q	SW	SE	34	21N	8W	Trempealeau	0-225-35-2021	1.2	0.0	2.7	10.4	38.7	2.586	2.650	2.496		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
TWESME 55-61-020-QRY Created On: 01/02/24 Updated On:	Q	SW	SE	34	21N	8W	Trempealeau	0-225-120-2024	0.7	6.4	8.8	11.6	40.6	2.584	2.652	2.624		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
VERNON -- WI																		
BAKKESTUEN / COON VALLEY 55-62-002-PIT Created On: 06/12/17 Updated On:	Q	NW	NW	22	14N	5W	Vernon	0-225-211-2017		0.0	1.7	9.7	36.4	2.646	2.694	1.843		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
BAKKESTUEN / COON VALLEY 55-62-002-PIT Created On: 01/10/22 Updated On:	Q	NW	NW	22	14N	5W	Vernon	0-225-107-2022	0.7	1.3	0.3	11.4	35.8	2.639	2.687	1.788		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
BROOKVILLE 55-62-004-QRY Created On: 05/19/16 Updated On:	Q			22	12N	4W	Vernon	0-225-184-2016		0.0	4.0	11.0	38.1	2.637	2.689	1.954		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse				
	P/Q	Qrt	Qrt	Sect	Town	Range	County					LA Wear (%)		Sp. Gravity		Absorp. %
											100	500	OD	SSD	Crse	Fine
VERNON -- WI																
BROOKVILLE 55-62-004-QRY Created On: 01/04/18 Updated On:	Q			22	12N	4W	Vernon	0-225-44-2018	0.4	0.0	2.1	9.8	37.3	2.636	2.685	1.861
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate															
BROOKVILLE 55-62-004-QRY Created On: 01/05/21 Updated On:	Q			22	12N	4W	Vernon	0-225-63-2021	0.4	0.0	0.4	8.1	33.7	2.634	2.687	1.993
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate															
BROOKVILLE 55-62-004-QRY Created On: 01/02/24 Updated On:	Q			22	12N	4W	Vernon	0-225-35-2024	1.7	0.8	5.1	11.6	42.3	2.617	2.677	2.278
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate															
BUGBEE QUARRY 55-62-035-QRY Created On: 02/28/24 Updated On:	Q	SE	SW	21	14N	1W	Vernon	0-225-191-2024	1.2	3.7	6.4	8.5	36.8	2.608	2.667	2.226
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate															
BURT(MUELLER) 55-62-005-QRY Created On: 05/18/17 Updated On:	Q	NW	SW	33	13N	2W	Vernon	0-225-190-2017		0.0	2.1	8.7	33.2	2.626	2.681	2.133
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate															
BURT(MUELLER) 55-62-005-QRY Created On: 01/08/20 Updated On:	Q	NW	SW	33	13N	2W	Vernon	0-225-65-2020	0.5	0.0	5.6	8.2	32.2	2.650	2.696	1.760
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate															
BURT(MUELLER) 55-62-005-QRY Created On: 01/30/23 Updated On:	Q	NW	SW	33	13N	2W	Vernon	0-225-134-2023	1.5	1.6	1.7	8.5	33.4	2.654	2.703	1.858
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate															

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse					
	P/Q	Qrt	Qrt	Sect	Town	Range	County	LA Wear (%) 100 500					Sp. Gravity OD SSD		Absorp. % Crse Fine			
VERNON -- WI																		
GUDGEON 55-62-012-QRY Created On: 01/06/14 Updated On:	Q	NW	NE	27	13N	4E	Vernon	0-225-12-2014		10.0	2.8	13.6	33.1	2.577	2.635	2.231		
Approved Use : CONCRETE, OGBC, Base Aggregate																		
GUDGEON 55-62-012-QRY Created On: 01/09/20 Updated On:	Q	NW	NE	27	13N	4E	Vernon	0-225-84-2020	0.0	1.9	3.3	10.5	41.7	2.589	2.655	2.518		
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
GUDGEON 55-62-012-QRY Created On: 01/10/23 Updated On:	Q	NW	NE	27	13N	4E	Vernon	0-225-107-2023	0.5	3.6	3.0	11.2	40.6	2.580	2.653	2.842		
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
*HOHFELD 55-62-015-QRY Created On: 02/03/20 Updated On:	Q	NE	NE	8	14N	6W	Vernon	0-225-109-2020	2.7	0.0	8.2	12.8	46.2	2.550	2.627	3.035		
Approved Use : HMA<MT, CONCRETE, OGBC, Base Aggregate																		
MILESTONE-THOMPSON F 55-62-030-QRY Created On: 01/07/14 Updated On:	Q	SE	SW	8	14N	1E	Vernon	0-225-35-2014		0.0	9.8	15.3	43.9	2.493	2.575	3.312		
Approved Use : CONCRETE, OGBC, Base Aggregate																		
MILESTONE-THOMPSON F 55-62-030-QRY Created On: 05/04/17 Updated On:	Q	SE	SW	8	14N	1E	Vernon	0-225-171-2017		0.0	3.2	8.8	36.4	2.615	2.669	2.066		
Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																		
MILESTONE-THOMPSON F 55-62-030-QRY Created On: 01/03/20 Updated On:	Q	SE	SW	8	14N	1E	Vernon	0-225-24-2020	1.2	0.0	5.1	9.7	34.7	2.597	2.661	2.461		
Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																		

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse					
	P/Q	Qrt	Qrt	Sect	Town	Range	County	LA Wear (%) 100					500	Sp. Gravity OD SSD		Absorp. % Crse Fine		
VERNON -- WI MILESTONE-THOMPSON F 55-62-030-QRY Created On: 01/03/23 Updated On:	Q	SE	SW	8	14N	1E	Vernon	0-225-30-2023	1.0	3.6	0.6	9.7	35.5	2.623	2.674	1.940		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MOLLETT 55-62-022-QRY Created On: 05/19/16 Updated On:	Q	NE	SE	4	12N	4W	Vernon	0-225-180-2016		0.0	4.6	9.4	35.5	2.636	2.686	1.903		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
MOLLETT 55-62-022-QRY Created On: 01/07/19 Updated On:	Q	NE	SE	4	12N	4W	Vernon	0-225-51-2019	0.5	0.0	2.0	8.1	33.7	2.632	2.683	1.931		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MOLLETT 55-62-022-QRY Created On: 01/10/22 Updated On:	Q	NE	SE	4	12N	4W	Vernon	0-225-101-2022	0.2	6.0	0.5	9.4	35.2	2.635	2.690	2.091		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
PEDRETTI 55-62-028-QRY Created On: 01/09/15 Updated On:	Q	SW	NW	27	13N	7W	Vernon	0-225-51-2015		0.0	9.2	10.8	40.0	2.575	2.641	2.576		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
PEDRETTI 55-62-028-QRY Created On: 01/03/18 Updated On:	Q	SW	NW	27	13N	7W	Vernon	0-225-15-2018	0.5	0.0	2.1	8.5	32.3	2.594	2.659	2.520		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
PEDRETTI 55-62-028-QRY Created On: 01/04/21 Updated On:	Q	SW	NW	27	13N	7W	Vernon	0-225-25-2021	0.4	0.0	0.9	10.0	34.8	2.573	2.646	2.835		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse					
	P/Q	Qrt	Qrt	Sect	Town	Range	County	LA Wear (%) 100 500					Sp. Gravity OD SSD		Absorp. % Crse Fine			
VERNON -- WI																		
PEDRETTI 55-62-028-QRY Created On: 01/02/24 Updated On:	Q	SW	NW	27	13N	7W	Vernon	0-225-29-2024	2.1	9.0	11.7	13.4	45.6	2.538	2.619	3.220		
	Approved Use : HMA<MT, CONCRETE, OGBC, Base Aggregate																	
SEAS BRANCH 55-62-029-QRY Created On: 08/21/14 Updated On:	Q	NE	NW	15	13N	4W	Vernon	0-225-247-2014		0.0	1.6	8.2	33.9	2.624	2.675	1.938		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
SEAS BRANCH 55-62-029-QRY Created On: 01/04/23 Updated On:	Q	NE	NW	15	13N	4W	Vernon	0-225-84-2023	0.5	1.5	2.4	9.6	33.9	2.681	2.720	1.471		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
VICTORY 55-62-034-QRY Created On: 08/22/22 Updated On:	Q	NE	NE	34	12N	7W	Vernon	0-225-254-2022	1.2	10.4	7.0	14.5	48.1	2.578	2.646	2.654		
	Approved Use : CONCRETE, OGBC, Base Aggregate																	
ZOGG 55-62-033-QRY Created On: 07/02/15 Updated On:	Q	SW	SE	27	14N	7W	Vernon	0-225-206-2015		0.0	6.9	11.5	39.7	2.594	2.656	2.412		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
ZOGG 55-62-033-QRY Created On: 01/03/18 Updated On:	Q	SW	SE	27	14N	7W	Vernon	0-225-12-2018	1.0	0.0	3.8	9.9	35.4	2.605	2.667	2.408		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
ZOGG 55-62-033-QRY Created On: 01/04/21 Updated On:	Q	SW	SE	27	14N	7W	Vernon	0-225-29-2021	0.9	0.0	1.2	7.8	32.3	2.600	2.667	2.583		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse					
	P/Q	Qrt	Qrt	Sect	Town	Range	County	LA Wear (%) 100 500					Sp. Gravity OD SSD	Absorp. % Crse Fine				
VERNON -- WI																		
ZOGG 55-62-033-QRY Created On: 01/02/24 Updated On:	Q	SW	SE	27	14N	7W	Vernon	0-225-38-2024	0.2	8.9	6.8	9.9	36.6	2.601	2.667	2.529		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
VILAS -- WI																		
GATEWAY 55-63-023-PIT Created On: 07/18/19 Updated On:	P	SE	NE	11	42N	10E	Vilas	0-225-236-2019	0.3	0.0	0.6	3.5	16.4	2.744	2.763	0.689		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
GATEWAY 55-63-023-PIT Created On: 01/02/24 Updated On:	P	SE	NE	11	42N	10E	Vilas	0-225-59-2024	0.7	0.0	0.5	3.9	18.0	2.727	2.749	0.824		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
HARRY'S 55-63-006-PIT Created On: 05/08/15 Updated On:	P	SE	SE	14	40N	6E	Vilas	0-225-153-2015		0.0	0.5	4.4	20.0	2.692	2.717	0.937		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
HARRY'S 55-63-006-PIT Created On: 01/08/20 Updated On:	P	SE	SE	14	40N	6E	Vilas	0-225-72-2020	0.8	0.0	0.9	3.4	16.6	2.702	2.728	0.958		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
HOLTAN 55-63-007-PIT Created On: 06/13/19 Updated On:	P	NW	NW	33	43N	8E	Vilas	0-225-220-2019	0.3	0.0	1.8	3.9	19.2	2.742	2.767	0.888		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
HOLTAN 55-63-007-PIT Created On: 01/03/23 Updated On:	P	NW	NW	33	43N	8E	Vilas	0-225-27-2023	1.5	0.0	1.0	4.6	20.4	2.720	2.756	1.307		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse					
	P/Q	Qrt	Qrt	Sect	Town	Range	County	LA Wear (%) 100 500					Sp. Gravity OD SSD		Absorp. % Crse Fine			
VILAS -- WI																		
NLC WOODRUFF 55-63-013-PIT Created On: 04/11/18 Updated On:	P	NW	SE	14	40N	6E	Vilas	0-225-169-2018	0.6	0.0	0.6	3.6	18.2	2.691	2.713	0.818		
Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																		
NLC WOODRUFF 55-63-013-PIT Created On: 01/03/23 Updated On:	P	NW	SE	14	40N	6E	Vilas	0-225-23-2023	1.2	0.0	1.0	4.5	20.2	2.701	2.722	0.812		
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
ROSS 55-63-017-PIT Created On: 01/02/24 Updated On:	P	NE	SW	28	41N	10E	Vilas	0-225-61-2024	1.6	0.0	2.1	4.7	20.5	2.670	2.702	1.179		
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
VOLKMAN 55-63-022-PIT Created On: 07/18/19 Updated On:	P	S	NE	17	41N	12E	Vilas	0-225-237-2019	2.4	0.0	0.6	4.8	19.0	2.682	2.709	1.012		
Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																		
VOLKMAN 55-63-022-PIT Created On: 01/02/24 Updated On:	P	S	NE	17	41N	12E	Vilas	0-225-56-2024	0.8	0.0	0.3	4.2	18.4	2.701	2.729	1.041		
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
WALWORTH -- WI																		
AMON / WILSON 55-64-002-PIT Created On: 06/30/17 Updated On:	P	NE	SE	25	3N	18E	Walworth	0-225-226-2017		0.0	0.9	7.4	37.2	2.669	2.708	1.467		
Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																		
AMON / WILSON 55-64-002-PIT Created On: 04/05/22 Updated On:	P	NE	SE	25	3N	18E	Walworth	0-225-169-2022	0.9	0.0	4.5	4.8	26.5	2.680	2.720	1.491		
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Coarse Sp. Gravity		Coarse Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
WALWORTH -- WI																		
ATKINSON 55-64-005-PIT Created On: 01/18/19 Updated On:	P	NE	SW	6	3N	18E	Walworth	0-225-87-2019	4.6	4.2	0.7	5.1	26.3	2.681	2.717	1.342		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
ATKINSON 55-64-005-PIT Created On: 01/02/24 Updated On:	P	NE	SW	6	3N	18E	Walworth	0-225-15-2024	0.4	4.9	2.9	5.0	25.8	2.668	2.704	1.323		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
*BLOOMFIELD 55-64-008-PIT Created On: 01/07/14 Updated On:	P	E	SW	1	1N	19E	Walworth	0-225-41-2014	0.1	0.0	1.0	3.5	17.6	2.690	2.726	1.334		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
*BLOOMFIELD 55-64-008-PIT Created On: 01/18/19 Updated On:	P	E	SW	1	1N	19E	Walworth	0-225-86-2019	1.5	7.4	0.9	4.0	21.5	2.669	2.711	1.566		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
*BOSS 55-64-009-PIT Created On: 06/07/19 Updated On:	P		NW	33	3N	15E	Walworth	0-225-209-2019	1.2	0.0	1.3	5.4	25.4	2.700	2.735	1.304		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
COUNTRY SIDE WOODS 55-64-054-PIT Created On: 05/13/19 Updated On:	P		SW	20	3N	16E	Walworth	0-225-187-2019	1.7	2.8	0.8	6.3	26.9	2.649	2.689	1.508		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
COUNTRY SIDE WOODS 55-64-054-PIT Created On: 02/10/22 Updated On:	P		SW	20	3N	16E	Walworth	0-225-120-2022	3.3	6.8	1.6	5.1	26.1	2.676	2.714	1.430		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse					
	P/Q	Qrt	Qrt	Sect	Town	Range	County	LA Wear (%) 100 500					Sp. Gravity OD SSD		Absorp. % Crse Fine			
WALWORTH -- WI																		
DARIEN 55-64-055-PIT Created On: 06/25/21 Updated On:	P	W	NW	7	2N	15E	Walworth	0-225-234-2021	0.1	5.3	6.7	6.2	25.6	2.662	2.706	1.648		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
JOHNSON S&G BOWERS ROAD 55-64-015-PIT Created On: 04/03/14 Updated On:	P		NE	2	3N	17E	Walworth	0-225-114-2014	2.6	0.0	5.3	5.6	27.2	2.687	2.722	1.309		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
JOHNSON S&G BOWERS ROAD 55-64-015-PIT Created On: 04/24/19 Updated On:	P		NE	2	3N	17E	Walworth	0-225-159-2019	2.1	0.0	3.8	4.0	26.4	2.678	2.713	1.293		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
JOHNSON S&G BOWERS ROAD 55-64-015-PIT Created On: 03/27/24 Updated On:	P		NE	2	3N	17E	Walworth	0-225-214-2024	0.8	9.2	0.8	4.2	25.8	2.711	2.748	1.365		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
LAGRANGE 55-64-024-PIT Created On: 01/07/14 Updated On:	P	W	SE	20	4N	16E	Walworth	0-225-42-2014		0.0	2.3	6.5	27.3	2.704	2.738	1.237		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
LAGRANGE 55-64-024-PIT Created On: 02/05/19 Updated On:	P	W	SE	20	4N	16E	Walworth	0-225-94-2019	0.9	7.0	0.5	4.3	22.4	2.695	2.731	1.337		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
LAGRANGE 55-64-024-PIT Created On: 01/02/24 Updated On:	P	W	SE	20	4N	16E	Walworth	0-225-17-2024	0.0	4.5	2.9	4.8	23.2	2.705	2.738	1.224		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse					
	P/Q	Qrt	Qrt	Sect	Town	Range	County	LA Wear (%) 100					500	Sp. Gravity OD SSD		Absorp. % Crse Fine		
WALWORTH -- WI																		
ODLING 55-64-013-PIT Created On: 01/19/23 Updated On:	P	NW	SE	36	2N	16E	Walworth	0-225-123-2023	1.9	2.6	2.4	4.7	30.5	2.664	2.704	1.503		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
PADDOCK 55-64-028-PIT Created On: 04/10/18 Updated On:	P	E	SE	1	3N	16E	Walworth	0-225-161-2018	1.4	0.0	1.3	5.3	25.7	2.670	2.709	1.457		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
PADDOCK 55-64-028-PIT Created On: 05/14/21 Updated On:	P	E	SE	1	3N	16E	Walworth	0-225-208-2021	4.9	7.2	3.0	4.6	29.8	2.696	2.732	1.316		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
REESMAN CO. - BOLTON 55-64-020-PIT Created On: 02/16/18 Updated On:	P		SW	4	3N	18E	Walworth	0-225-106-2018	1.0	0.0	0.2	5.1	27.2	2.678	2.714	1.341		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
REESMAN CO. - BOLTON 55-64-020-PIT Created On: 01/19/23 Updated On:	P		SW	4	3N	18E	Walworth	0-225-126-2023	0.7	0.0	4.4	5.1	24.9	2.682	2.719	1.366		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
RICHMOND 55-64-035-PIT Created On: 01/12/16 Updated On:	P	NW	NW	15	3N	15E	Walworth	0-225-58-2016	2.4	0.0	1.6	5.2	25.2	2.697	2.736	1.466		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
RICHMOND 55-64-035-PIT Created On: 01/04/21 Updated On:	P	NW	NW	15	3N	15E	Walworth	0-225-10-2021	0.4	3.4	2.3	5.3	26.2	2.696	2.731	1.293		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse					
	P/Q	Qrt	Qrt	Sect	Town	Range	County	LA Wear (%) 100 500					Sp. Gravity OD SSD		Absorp. % Crse Fine			
WALWORTH -- WI																		
*SUPER AGGREGATE-SUGAR CREEK 55-64-037-PIT Created On: 07/17/14 Updated On:	P	SE	NW	9	3N	16E	Walworth	0-225-228-2014	4.7	0.0	3.8	9.6	33.9	2.681	2.715	1.274		
Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																		
*SUPER AGGREGATE-SUGAR CREEK 55-64-037-PIT Created On: 02/11/19 Updated On:	P	SE	NW	9	3N	16E	Walworth	0-225-106-2019	3.0	0.0	7.0	3.9	24.2	2.651	2.692	1.527		
Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																		
THELEN-LANGE ROAD 55-64-025-PIT Created On: 06/12/14 Updated On:	P	SE	SE	32	1N	18E	Walworth	0-225-190-2014	2.1	0.0	3.1	7.6	37.9	2.679	2.716	1.397		
Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																		
THELEN-LANGE ROAD 55-64-025-PIT Created On: 06/25/15 Updated On:	P	SE	SE	32	1N	18E	Walworth	0-225-202-2015	1.0	0.0	1.1	5.7	33.5	2.674	2.713	1.439		
Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																		
THELEN-LANGE ROAD 55-64-025-PIT Created On: 05/09/18 Updated On:	P	SE	SE	32	1N	18E	Walworth	0-225-197-2018	0.3	10.4	0.9	5.5	25.8	2.699	2.737	1.421		
Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																		
THELEN-LANGE ROAD 55-64-025-PIT Created On: 01/03/23 Updated On:	P	SE	SE	32	1N	18E	Walworth	0-225-49-2023	0.7	14.4	6.6	5.9	28.4	2.671	2.704	1.241		
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
WHELAN 55-64-039-PIT Created On: 03/24/16 Updated On:	P	SE	NE	1	1N	15E	Walworth	0-225-110-2016		0.0	2.7	5.6	26.6	2.693	2.726	1.229		
Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																		

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse					
	P/Q	Qrt	Qrt	Sect	Town	Range	County	LA Wear (%) 100 500					Sp. Gravity OD SSD	Absorp. % Crse Fine				
WALWORTH -- WI																		
WHELAN 55-64-039-PIT Created On: 01/05/21 Updated On:	P	SE	NE	1	1N	15E	Walworth	0-225-84-2021	0.0	5.1	3.6	5.2	29.6	2.689	2.727	1.400		
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
WASHBURN -- WI																		
FRAATZ 55-65-006-PIT Created On: 06/08/17 Updated On:	P		SW	18	41N	12W	Washburn	0-225-207-2017		0.0	3.8	6.0	24.3	2.629	2.682	2.020		
Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																		
FRAATZ 55-65-006-PIT Created On: 03/01/23 Updated On:	P		SW	18	41N	12W	Washburn	0-225-162-2023	4.4	0.0	6.9	5.0	22.5	2.661	2.707	1.738		
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
MINONG 55-65-009-QRY Created On: 10/08/15 Updated On:	Q	NE	NW	27	42N	11W	Washburn	0-225-241-2015		0.0	0.4	2.9	11.8	2.903	2.915	0.400		
Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																		
MINONG 55-65-009-QRY Created On: 06/07/18 Updated On:	Q	NE	NW	27	42N	11W	Washburn	0-225-219-2018		0.0	0.5	2.3	10.1	2.930	2.940	0.320		
Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																		
MINONG 55-65-009-QRY Created On: 07/07/22 Updated On:	Q	NE	NW	27	42N	11W	Washburn	0-225-246-2022	0.0	0.5	0.3	2.0	10.7	2.914	2.924	0.339		
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
PAFFEL 55-65-010-PIT Created On: 01/24/14 Updated On:	P	NE	NE	21	39N	12W	Washburn	0-225-59-2014		0.0	2.9	3.6	16.4	2.715	2.740	0.932		
Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																		

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse					
	P/Q	Qrt	Qrt	Sect	Town	Range	County	LA Wear (%) 100					500	Sp. Gravity OD SSD		Absorp. % Crse Fine		
WASHBURN -- WI																		
PAFFEL 55-65-010-PIT Created On: 01/07/19 Updated On:	P	NE	NE	21	39N	12W	Washburn	0-225-59-2019	0.3	0.0	2.3	3.8	17.3	2.708	2.743	1.323		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
PAFFEL 55-65-010-PIT Created On: 01/02/24 Updated On:	P	NE	NE	21	39N	12W	Washburn	0-225-94-2024	0.9	3.3	2.0	3.9	18.6	2.706	2.742	1.313		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
PINE BROOK 55-65-012-PIT Created On: 05/14/15 Updated On:	P		N	21	38N	11W	Washburn	0-225-174-2015		0.0	3.1	4.1	18.5	2.788	2.815	0.978		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
PINE BROOK 55-65-012-PIT Created On: 01/08/21 Updated On:	P		N	21	38N	11W	Washburn	0-225-118-2021	0.3	0.0	4.3	4.9	20.4	2.736	2.776	1.464		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
*SCHRICKER 55-65-013-PIT Created On: 02/28/14 Updated On:	P	NE	SW	4	38N	12W	Washburn	0-225-88-2014		0.0	5.7	4.1	18.9	2.680	2.721	1.527		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
*SCHRICKER 55-65-013-PIT Created On: 04/05/19 Updated On:	P	NE	SW	4	38N	12W	Washburn	0-225-126-2019	1.5	0.0	4.1	4.3	19.6	2.739	2.768	1.077		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
SUGAR BUSH 55-65-020-PIT Created On: 06/18/20 Updated On:	P		NW	23	37N	10W	Washburn	0-225-198-2020	2.0	0.0	2.1	4.6	20.7	2.753	2.778	0.915		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse					
	P/Q	Qrt	Qrt	Sect	Town	Range	County	LA Wear (%) 100					500	Sp. Gravity OD SSD		Absorp. % Crse Fine		
WASHBURN -- WI																		
TUBBS 55-65-017-PIT Created On: 01/23/14 Updated On:	P	NE	SE	18	41N	12W	Washburn	0-225-57-2014		0.0	7.9	5.7	22.7	2.705	2.745	1.495		
Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																		
TUBBS 55-65-017-PIT Created On: 06/09/20 Updated On:	P	NE	SE	18	41N	12W	Washburn	0-225-189-2020	1.7	0.0	2.3	4.0	18.7	2.735	2.771	1.325		
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
WASHINGTON -- WI																		
CEDAR LAKE 55-66-004-PIT Created On: 01/04/16 Updated On:	P	N	SW	35	11N	18E	Washington	0-225-15-2016	1.9	1.3	2.1	5.7	26.4	2.712	2.743	1.165		
Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																		
CEDAR LAKE 55-66-004-PIT Created On: 01/08/21 Updated On:	P	N	SW	35	11N	18E	Washington	0-225-116-2021	0.8	8.7	1.1	5.9	32.1	2.749	2.772	0.830		
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
LANNON STONE - JACKSON 55-66-012-QRY Created On: 01/22/16 Updated On:	Q		NE	12	10N	20E	Washington	0-225-75-2016		0.3	0.2	9.4	34.0	2.705	2.734	1.068		
Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																		
LANNON STONE - JACKSON 55-66-012-QRY Created On: 01/18/19 Updated On:	Q		NE	12	10N	20E	Washington	0-225-88-2019		0.9	0.2	8.9	34.4	2.658	2.697	1.478		
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
LANNON STONE - JACKSON 55-66-012-QRY Created On: 01/13/22 Updated On:	Q		NE	12	10N	20E	Washington	0-225-111-2022	0.0	0.7	0.6	8.1	36.5	2.608	2.648	1.554		
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse				
	P/Q	Qrt	Qrt	Sect	Town	Range	County					LA Wear (%)		Sp. Gravity		Absorp. %
											100	500	OD	SSD	Crse	Fine
WASHINGTON -- WI																
LANNON STONE - JACKSON 55-66-012-QRY Created On: 01/03/23 Updated On:	Q		NE	12	10N	20E	Washington	0-225-80-2023	1.6	1.6	0.6	7.4	31.6	2.620	2.670	1.914
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate															
LANNON STONE - RICHFIELD 55-66-013-PIT Created On: 02/16/16 Updated On:	P		SE	24	9N	19E	Washington	0-225-89-2016		2.6	1.1	8.2	35.1			
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate															
LANNON STONE - RICHFIELD 55-66-013-PIT Created On: 01/08/21 Updated On:	P		SE	24	9N	19E	Washington	0-225-114-2021	0.0	2.2	2.3	6.9	28.6	2.710	2.740	1.116
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate															
MICHEL'S BECKER 55-66-016-PIT Created On: 01/08/15 Updated On:	P	SW	SW	27	11N	18E	Washington	0-225-32-2015	0.2	3.6	3.7	6.6	29.1	2.704	2.738	1.262
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate															
MICHEL'S BECKER 55-66-016-PIT Created On: 01/08/20 Updated On:	P	SW	SW	27	11N	18E	Washington	0-225-77-2020	2.2	10.5	2.7	6.1	28.8	2.678	2.718	1.499
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate															
*WEST BEND S & G 55-66-020-PIT Created On: 02/28/14 Updated On:	P	SW	SE	8	11N	19E	Washington	0-225-91-2014	0.2	0.6	1.1	5.3	24.6	2.725	2.752	1.019
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate															
*WEST BEND S & G 55-66-020-PIT Created On: 03/22/19 Updated On:	P	SW	SE	8	11N	19E	Washington	0-225-116-2019	0.0	1.1	0.3	4.8	27.3	2.757	2.780	0.819
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate															

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse					
	P/Q	Qrt	Qrt	Sect	Town	Range	County	LA Wear (%) 100 500					Sp. Gravity OD SSD		Absorp. % Crse Fine			
WASHINGTON -- WI																		
WISSOTA RUGBY S&G 55-66-021-PIT Created On: 02/07/14 Updated On:	P	SE	NE	34	10N	19E	Washington	0-225-85-2014	1.2	1.2	1.4	5.1	26.4	2.740	2.762	0.789		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
WISSOTA RUGBY S&G 55-66-021-PIT Created On: 01/07/19 Updated On:	P	SE	NE	34	10N	19E	Washington	0-225-43-2019	0.2	4.6	1.1	5.2	27.4	2.731	2.760	1.095		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
WISSOTA RUGBY S&G 55-66-021-PIT Created On: 01/29/24 Updated On:	P	SE	NE	34	10N	19E	Washington	0-225-160-2024	0.4	9.7	1.1	6.8	31.2	2.725	2.755	1.095		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
WAUKESHA -- WI																		
GENESEE 55-67-007-PIT Created On: 01/05/16 Updated On:	P	NE	SE	29	6N	18E	Waukesha	0-225-21-2016	0.2	1.9	2.4	8.0	34.9	2.708	2.745	1.346		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
GENESEE 55-67-007-PIT Created On: 01/05/21 Updated On:	P	NE	SE	29	6N	18E	Waukesha	0-225-95-2021	0.0	6.1	2.8	6.1	27.5	2.727	2.759	1.189		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
GENESEE / HILLVIEW 55-67-005-PIT Created On: 01/08/15 Updated On:	P		SE	8	8N	19E	Waukesha	0-225-30-2015	0.5	4.6	3.9	5.9	28.1	2.686	2.725	1.439		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
GENESEE / HILLVIEW 55-67-005-PIT Created On: 02/16/16 Updated On:	P		SE	8	8N	19E	Waukesha	0-225-90-2016		1.6	1.6	7.6	34.6	2.711	2.743	1.180		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
WAUKESHA -- WI GENESEE / HILLVIEW 55-67-005-PIT Created On: 01/05/21 Updated On:	P		SE 8	8N	19E	Waukesha	0-225-97-2021	0.4	6.1	3.8	7.4	31.0	2.578	2.643	2.498		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
GENESEE/OTTAWA PIT 55-67-006-PIT Created On: 01/05/16 Updated On:	P		SW 1	6N	17E	Waukesha	0-225-19-2016	0.0	3.0	4.9	8.4	37.1	2.688	2.723	1.324		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
GENESEE/OTTAWA PIT 55-67-006-PIT Created On: 01/05/21 Updated On:	P		SW 1	6N	17E	Waukesha	0-225-94-2021	0.0	5.2	6.8	5.5	26.7	2.677	2.716	1.452		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
HALQUIST NORTH LAKE 55-67-032-PIT Created On: 06/27/18 Updated On:	P		SE 9	8N	18E	Waukesha	0-225-239-2018	1.1	0.8	1.0	5.6	27.3	2.721	2.749	1.042		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
HALQUIST NORTH LAKE 55-67-032-PIT Created On: 03/21/23 Updated On:	P		SE 9	8N	18E	Waukesha	0-225-171-2023	0.6	17.3	0.0	5.3	25.1	2.720	2.744	0.900		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
HOLCIM-COLGATE 55-67-021-PIT Created On: 01/08/15 Updated On:	P	S	NW 3	8N	19E	Waukesha	0-225-35-2015	0.9	2.5	2.4	4.5	23.9	2.736	2.759	0.827		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
HOLCIM-COLGATE 55-67-021-PIT Created On: 03/16/18 Updated On:	P	S	NW 3	8N	19E	Waukesha	0-225-129-2018		3.7	3.6	5.6	25.7	2.742	2.765	0.840		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse				
	P/Q	Qrt	Qrt	Sect	Town	Range	County					LA Wear (%)		Sp. Gravity		Absorp. %
											100	500	OD	SSD	Crse	Fine
WAUKESHA -- WI																
*LANNON STONE - LANNON 55-67-026-QRY Created On: 01/08/21 Updated On:	Q		E	20	8N	20E	Waukesha	0-225-115-2021	0.0	2.7	4.1	4.8	21.8	2.746	2.772	0.936
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate															
LANNON STONE - SUSSEX 55-67-025-QRY Created On: 02/28/14 Updated On:	Q		NE	35	8N	19E	Waukesha	0-225-92-2014	0.2	0.4	0.7	4.7	22.7	2.692	2.730	1.403
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate															
LANNON STONE - SUSSEX 55-67-025-QRY Created On: 04/04/17 Updated On:	Q		NE	35	8N	19E	Waukesha	0-225-103-2017		1.5	1.2	5.7	25.8	2.721	2.748	0.980
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate															
LANNON STONE - SUSSEX 55-67-025-QRY Created On: 01/08/20 Updated On:	Q		NE	35	8N	19E	Waukesha	0-225-80-2020	0.0	0.9	0.6	5.0	24.9	2.715	2.747	1.167
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate															
LANNON STONE - SUSSEX 55-67-025-QRY Created On: 02/27/23 Updated On:	Q		NE	35	8N	19E	Waukesha	0-225-145-2023	3.7	3.1	0.9	5.3	24.7	2.735	2.767	1.176
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate															
LANNON STONE - WEST QUARRY 55-67-008-QRY Created On: 01/08/15 Updated On:	Q		NW	35	8N	19E	Waukesha	0-225-33-2015		0.8	1.3	5.8	26.1	2.738	2.766	1.027
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate															
LANNON STONE - WEST QUARRY 55-67-008-QRY Created On: 01/12/16 Updated On:	Q		NW	35	8N	19E	Waukesha	0-225-57-2016		0.6	0.4	8.2	39.7	2.716	2.743	0.974
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate															

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse				
	P/Q	Qrt	Qrt	Sect	Town	Range	County					LA Wear (%)		Sp. Gravity		Absorp. %
											100	500	OD	SSD	Crse	Fine
WAUKESHA -- WI																
LANNON STONE - WEST QUARRY 55-67-008-QRY Created On: 02/11/19 Updated On:	Q		NW 35	8N	19E	Waukesha	0-225-101-2019	6.2	5.1	1.2	4.1	22.4	2.715	2.750	1.282	
	Approved Use : HMA<MT, HMA>=MT, Base Aggregate															
LANNON STONE - WEST QUARRY 55-67-008-QRY Created On: 01/13/22 Updated On:	Q		NW 35	8N	19E	Waukesha	0-225-110-2022	0.0	11.1	4.1	5.3	25.5	2.684	2.725	1.512	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate															
LANNON STONE - WEST QUARRY 55-67-008-QRY Created On: 01/03/23 Updated On:	Q		NW 35	8N	19E	Waukesha	0-225-81-2023	2.7	12.1	0.5	5.5	25.4	2.718	2.748	1.109	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate															
*LEMKE STONE 55-67-046-QRY Created On: 05/07/20 Updated On:	Q	NE	NW 19	8N	20E	Waukesha	0-225-174-2020	0.0	2.1	3.1	5.3	25.3	2.755	2.792	1.319	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate															
MUSKEGO 55-67-029-PIT Created On: 01/04/18 Updated On:	P	SW	SW 18	5N	20E	Waukesha	0-225-76-2018	0.3	2.9	1.8	3.8	24.9	2.676	2.723	1.774	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate															
MUSKEGO 55-67-029-PIT Created On: 01/03/23 Updated On:	P	SW	SW 18	5N	20E	Waukesha	0-225-73-2023	0.1	3.6	0.9	4.7	22.7	2.700	2.735	1.314	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate															
WAUKESHA LIME & STONE 55-67-042-QRY Created On: 01/04/16 Updated On:	Q	SE	SE 26	7N	19E	Waukesha	0-225-4-2016		9.0	3.0	4.3	20.5	2.712	2.751	1.426	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate															

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse				
	P/Q	Qrt	Qrt	Sect	Town	Range	County					LA Wear (%)		Sp. Gravity		Absorp. %
											100	500	OD	SSD	Crse	Fine
WAUKESHA -- WI																
WAUKESHA LIME & STONE 55-67-041-PIT Created On: 01/21/16 Updated On:	P	SE	SE	26	7N	8E	Waukesha	0-225-71-2016	1.2	4.7	2.3	4.7	23.4	2.713	2.748	1.311
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate															
WAUKESHA LIME & STONE 55-67-042-QRY Created On: 02/05/19 Updated On:	Q	SE	SE	26	7N	19E	Waukesha	0-225-98-2019	0.3	1.2	0.2	5.7	27.4	2.682	2.718	1.370
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate															
WAUKESHA LIME & STONE 55-67-041-PIT Created On: 01/05/21 Updated On:	P	SE	SE	26	7N	8E	Waukesha	0-225-96-2021	0.4	2.2	2.1	5.7	29.2	2.693	2.733	1.502
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate															
WAUKESHA LIME & STONE 55-67-042-QRY Created On: 01/04/22 Updated On:	Q	SE	SE	26	7N	19E	Waukesha	0-225-54-2022	0.3	0.9	0.5	4.1	20.0	2.776	2.793	0.639
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate															
WOLF 55-67-043-PIT Created On: 04/03/17 Updated On:	P		E	6	6N	18E	Waukesha	0-225-102-2017		2.8	2.7	5.2	24.9	2.723	2.750	1.000
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate															
WOLF 55-67-043-PIT Created On: 08/03/21 Updated On:	P		E	6	6N	18E	Waukesha	0-225-257-2021	0.8	1.3	2.4	4.1	23.0	2.736	2.766	1.064
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate															
WAUPACA -- WI																
COLRUE 55-68-033-PIT Created On: 03/01/18 Updated On:	P	SW	NE	31	23N	12E	Waupaca	0-225-110-2018	0.3	0.0	1.3	6.0	27.0	2.680	2.705	0.935
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate															

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse					
	P/Q	Qrt	Qrt	Sect	Town	Range	County	LA Wear (%) 100					500	Sp. Gravity OD SSD		Absorp. % Crse Fine		
WAUPACA -- WI																		
READFIELD 55-68-025-QRY Created On: 01/10/19 Updated On:	Q	NE	SW	26	21N	14E	Waupaca	0-225-85-2019	0.3	0.0	2.4	6.1	29.8	2.712	2.752	1.453		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
READFIELD 55-68-025-QRY Created On: 03/17/22 Updated On:	Q	NE	SW	26	21N	14E	Waupaca	0-225-147-2022	0.9	0.0	1.2	9.2	39.7	2.635	2.686	1.905		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
THIEL 55-68-028-PIT Created On: 06/21/16 Updated On:	P	NE	NW	5	22N	13E	Waupaca	0-225-209-2016		0.0	1.1	5.7	27.5	2.691	2.712	0.794		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
THIEL 55-68-028-PIT Created On: 01/04/21 Updated On:	P	NE	NW	5	22N	13E	Waupaca	0-225-21-2021	0.6	3.1	2.0	5.5	26.6	2.703	2.727	0.913		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
WAUSHARA -- WI																		
HEYN 55-69-006-PIT Created On: 04/13/17 Updated On:	P	W	NE	22	19N	8E	Waushara	0-225-131-2017		0.0	2.8	6.7	25.8	2.737	2.775	1.388		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
HEYN 55-69-006-PIT Created On: 04/30/21 Updated On:	P	W	NE	22	19N	8E	Waushara	0-225-191-2021	3.3	2.5	4.9	7.6	31.0	2.705	2.741	1.330		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
KELLEY 55-69-018-PIT Created On: 11/12/18 Updated On:	P	NE	NE	22	19N	3E	Waushara	0-225-291-2018	1.5	0.0	1.7	6.9	27.9	2.730	2.756	0.975		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse					
	P/Q	Qrt	Qrt	Sect	Town	Range	County	LA Wear (%) 100					500	Sp. Gravity OD	SSD	Absorp. % Crse	Fine	
WAUSHARA -- WI																		
KELLEY 55-69-018-PIT Created On: 06/26/23 Updated On:	P	NE	NE	22	19N	3E	Waushara	0-225-236-2023		0.0	0.1	5.6	25.5	2.739	2.766	0.991		
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																	
MEYER 55-69-012-PIT Created On: 01/04/22 Updated On:	P	NW	NW	36	20N	9E	Waushara	0-225-39-2022	1.0	0.0	6.4	6.9	29.2	2.699	2.733	1.256		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
SPRINGWATER 55-69-019-PIT Created On: 05/13/21 Updated On:	P	NW	NW	6	20N	11E	Waushara	0-225-206-2021	0.2	2.9	1.3	4.7	21.2	2.700	2.730	1.097		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
WINNEBAGO -- WI																		
BEN CARRIE 55-70-001-QRY Created On: 01/06/14 Updated On:	Q	NW	SW	29	20N	17E	Winnebago	0-225-28-2014	0.5	3.3	3.6	5.8	26.3	2.751	2.779	1.003		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
BEN CARRIE 55-70-001-QRY Created On: 01/09/15 Updated On:	Q	NW	SW	29	20N	17E	Winnebago	0-225-49-2015	0.1	2.1	1.4	5.6	24.3	2.768	2.792	0.891		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
BEN CARRIE 55-70-001-QRY Created On: 05/12/16 Updated On:	Q	NW	SW	29	20N	17E	Winnebago	0-225-171-2016		0.9	1.3	4.5	21.5	2.780	2.803	0.825		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
BEN CARRIE 55-70-001-QRY Created On: 03/13/17 Updated On:	Q	NW	SW	29	20N	17E	Winnebago	0-225-79-2017	0.2	1.8	4.6	5.0	23.4	2.768	2.792	0.846		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Coarse Sp. Gravity		Coarse Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
WINNEBAGO -- WI																		
BEN CARRIE 55-70-001-QRY Created On: 03/28/18 Updated On:	Q	NW	SW	29	20N	17E	Winnebago	0-225-150-2018	0.1	2.1	1.4	4.3	20.6	2.773	2.799	0.919		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
BEN CARRIE 55-70-001-QRY Created On: 04/10/19 Updated On:	Q	NW	SW	29	20N	17E	Winnebago	0-225-128-2019		5.6	2.9	4.6	22.2	2.761	2.788	0.978		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
BEN CARRIE 55-70-001-QRY Created On: 04/08/20 Updated On:	Q	NW	SW	29	20N	17E	Winnebago	0-225-148-2020	0.0	6.3	3.2	4.9	22.4	2.765	2.794	1.042		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
BEN CARRIE 55-70-001-QRY Created On: 01/03/23 Updated On:	Q	NW	SW	29	20N	17E	Winnebago	0-225-76-2023	0.0	6.0	3.2	6.6	29.7	2.717	2.753	1.322		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
*JORGENSEN 55-70-004-QRY Created On: 01/09/15 Updated On:	Q		NE	5	20N	17E	Winnebago	0-225-48-2015	0.1	9.2	4.4	6.2	28.8	2.729	2.761	1.149		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
*JORGENSEN 55-70-004-QRY Created On: 01/04/18 Updated On:	Q		NE	5	20N	17E	Winnebago	0-225-55-2018		13.2	6.0	5.8	28.4	2.749	2.778	1.060		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
*JORGENSEN 55-70-004-QRY Created On: 01/05/21 Updated On:	Q		NE	5	20N	17E	Winnebago	0-225-51-2021	0.0	10.5	2.0	6.4	30.2	2.729	2.761	1.202		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse						
	P/Q	Qrt	Qrt	Sect	Town	Range	County	LA Wear (%) 100					500	Sp. Gravity OD SSD		Absorp. % Crse Fine			
WINNEBAGO -- WI																			
LARSEN 55-70-007-QRY Created On: 01/02/24 Updated On:	Q	N	NE	19	20N	16E	Winnebago	0-225-97-2024	0.5	0.7	0.2	4.8	21.3	2.756	2.779	0.800	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate		
MCC - LARSEN 55-70-010-QRY Created On: 05/26/16 Updated On:	Q	NE	NW	19	20N	16E	Winnebago	0-225-193-2016	2.8	1.4	1.2	5.3	24.4	2.737	2.761	0.873	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate		
MCC - LARSEN 55-70-010-QRY Created On: 03/16/18 Updated On:	Q	NE	NW	19	20N	16E	Winnebago	0-225-125-2018	0.3	3.3	1.4	5.6	24.2	2.729	2.756	1.003	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate		
MCC - LARSEN 55-70-010-QRY Created On: 01/05/21 Updated On:	Q	NE	NW	19	20N	16E	Winnebago	0-225-103-2021	0.2	10.0	11.3	6.8	28.9	2.708	2.750	1.553	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate		
MCC - LARSEN 55-70-010-QRY Created On: 01/02/24 Updated On:	Q	NE	NW	19	20N	16E	Winnebago	0-225-7-2024	0.0	13.8	3.9	7.5	32.3	2.723	2.757	1.260	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate		
MICHELS ALLEN 55-70-011-QRY Created On: 01/21/16 Updated On:	Q	NE	SW	9	18N	14E	Winnebago	0-225-68-2016	0.5	1.4	6.8	11.6	39.5	2.645	2.700	2.056	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate		
MICHELS ALLEN 55-70-011-QRY Created On: 01/07/19 Updated On:	Q	NE	SW	9	18N	14E	Winnebago	0-225-70-2019	0.0	1.7	2.3	7.2	32.0	2.753	2.785	1.180	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate		

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse				
	P/Q	Qrt	Qrt	Sect	Town	Range	County					LA Wear (%)		Sp. Gravity		Absorp. %
											100	500	OD	SSD	Crse	Fine
WINNEBAGO -- WI																
MICHELS DIETZ 55-70-014-QRY Created On: 01/07/20 Updated On:	Q		8	20N	17E	Winnebago	0-225-39-2020	0.1	12.5	2.1	5.5	26.0	2.742	2.777	1.297	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate															
MICHELS DIETZ 55-70-014-QRY Created On: 01/03/23 Updated On:	Q		8	20N	17E	Winnebago	0-225-79-2023	0.1	13.6	10.6	6.6	28.8	2.717	2.760	1.576	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate															
MICHELS GRUNSKA 55-70-016-QRY Created On: 05/10/18 Updated On:	Q	SE	SE	8	20N	16E	Winnebago	0-225-201-2018	1.4	10.5	3.9	6.9	30.0	2.695	2.730	1.298
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate															
MICHELS GRUNSKA 55-70-016-QRY Created On: 01/05/21 Updated On:	Q	SE	SE	8	20N	16E	Winnebago	0-225-50-2021	1.5	5.7	4.8	7.0	30.6	2.705	2.743	1.392
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate															
MICHELS GRUNSKA 55-70-016-QRY Created On: 01/02/24 Updated On:	Q	SE	SE	8	20N	16E	Winnebago	0-225-46-2024	1.3	7.9	5.8	6.8	28.5	2.705	2.740	1.265
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate															
MICHELS KOCH 55-70-017-QRY Created On: 01/04/22 Updated On:	Q	NW	NE	29	20N	17E	Winnebago	0-225-20-2022	0.2	1.7	2.0	5.2	23.9	2.758	2.787	1.050
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate															
MICHELS KOCH 55-70-017-QRY Created On: 01/04/24 Updated On:	Q	NW	NE	29	20N	17E	Winnebago	0-225-147-2024	0.0	2.9	2.4	5.4	25.6	2.759	2.788	1.039
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate															

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse					
	P/Q	Qrt	Qrt	Sect	Town	Range	County					LA Wear (%)		Sp. Gravity		Absorp. %	
											100	500	OD	SSD	Crse	Fine	
WINNEBAGO -- WI																	
MICHELS OSHKOSH 55-70-018-QRY Created On: 01/04/16 Updated On:	Q		NE	27	18N	16E	Winnebago	0-225-11-2016		3.1	2.8	5.0	22.1	2.755	2.782	0.992	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
MICHELS OSHKOSH 55-70-018-QRY Created On: 01/04/19 Updated On:	Q		NE	27	18N	16E	Winnebago	0-225-6-2019		8.9	2.1	4.1	19.8	2.766	2.792	0.929	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
MICHELS OSHKOSH 55-70-018-QRY Created On: 01/04/22 Updated On:	Q		NE	27	18N	16E	Winnebago	0-225-22-2022		0.1	7.3	5.0	4.9	22.8	2.730	2.766	1.321
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
MICHELS OSHKOSH 55-70-018-QRY Created On: 01/02/24 Updated On:	Q		NE	27	18N	16E	Winnebago	0-225-103-2024		0.0	6.3	2.3	4.8	22.8	2.753	2.781	1.035
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
MICHELS-HUGHES 55-70-019-QRY Created On: 01/06/14 Updated On:	Q	SW	NW	32	17N	16E	Winnebago	0-225-26-2014		11.3	9.7	6.7	28.5	2.734	2.768	1.253	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
MICHELS-HUGHES 55-70-019-QRY Created On: 01/05/17 Updated On:	Q	SW	NW	32	17N	16E	Winnebago	0-225-13-2017		0.3	11.7	9.9	6.6	28.9	2.731	2.765	1.269
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
MICHELS-HUGHES 55-70-019-QRY Created On: 01/04/19 Updated On:	Q	SW	NW	32	17N	16E	Winnebago	0-225-7-2019		0.5	22.5	8.7	7.3	30.2	2.708	2.752	1.629

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse				
	P/Q	Qrt	Qrt	Sect	Town	Range	County					LA Wear (%)		Sp. Gravity		Absorp. %
											100	500	OD	SSD	Crse	Fine
WINNEBAGO -- WI																
SCHMOKER 55-70-029-QRY Created On: 01/09/15 Updated On:	Q		NE	20	19N	16E	Winnebago	0-225-47-2015		3.1	2.0	4.5	20.9	2.773	2.795	0.803
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate															
SCHMOKER 55-70-029-QRY Created On: 01/04/18 Updated On:	Q		NE	20	19N	16E	Winnebago	0-225-57-2018		4.0	2.1	4.7	21.5	2.771	2.796	0.877
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate															
SCHMOKER 55-70-029-QRY Created On: 01/05/21 Updated On:	Q		NE	20	19N	16E	Winnebago	0-225-52-2021	0.0	2.9	6.3	6.4	29.9	2.787	2.811	0.841
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate															
SCHMOKER 55-70-029-QRY Created On: 01/02/24 Updated On:	Q		NE	20	19N	16E	Winnebago	0-225-55-2024	0.2	5.9	7.4	6.1	25.9	2.768	2.793	0.921
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate															
VINLAND 55-70-032-QRY Created On: 06/05/14 Updated On:	Q	E	NW	21	19N	16E	Winnebago	0-225-180-2014		2.6	3.0	6.0	25.6	2.762	2.791	1.040
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate															
VINLAND 55-70-032-QRY Created On: 01/02/24 Updated On:	Q	E	NW	21	19N	16E	Winnebago	0-225-99-2024	0.0	2.9	0.5	5.0	22.1	2.785	2.806	0.751
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate															
WOOD -- WI																
BIG RACK (VENDEN) 55-71-004-QRY Created On: 10/19/17 Updated On:	Q	S	SW	31	24N	3E	Wood	0-225-283-2017		0.0	0.4	4.0	18.2	2.606	2.617	0.389
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate															

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse					
	P/Q	Qrt	Qrt	Sect	Town	Range	County					LA Wear (%)		Sp. Gravity		Absorp. %	
											100	500	OD	SSD	Crse	Fine	
WOOD -- WI																	
MARSHFIELD 55-71-021-QRY Created On: 01/03/17 Updated On:	Q	SE	NW	2	25N	3E	Wood	0-225-1-2017		0.0	0.3	5.1	23.8	2.676	2.690	0.520	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
MARSHFIELD 55-71-021-QRY Created On: 01/03/20 Updated On:	Q	SE	NW	2	25N	3E	Wood	0-225-12-2020		0.0	0.0	0.3	5.0	22.6	2.719	2.731	0.460
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
MARSHFIELD 55-71-021-QRY Created On: 01/03/23 Updated On:	Q	SE	NW	2	25N	3E	Wood	0-225-36-2023		0.0	1.2	3.0	5.5	24.2	2.763	2.783	0.708
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
SCHILL 55-71-025-QRY Created On: 01/06/14 Updated On:	Q	NW	SW	1	23N	4E	Wood	0-225-22-2014		0.0	0.8	5.4	22.4	2.598	2.614	0.606	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
SCHILL 55-71-025-QRY Created On: 01/03/17 Updated On:	Q	NW	SW	1	23N	4E	Wood	0-225-4-2017		0.0	0.2	4.9	22.8	2.605	2.617	0.487	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
SCHILL 55-71-025-QRY Created On: 01/02/20 Updated On:	Q	NW	SW	1	23N	4E	Wood	0-225-9-2020		0.9	0.0	0.9	5.1	21.6	2.617	2.629	0.464
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
SCHILL 55-71-025-QRY Created On: 01/03/23 Updated On:	Q	NW	SW	1	23N	4E	Wood	0-225-32-2023		0.2	1.3	1.0	5.7	24.1	2.606	2.619	0.509
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
WOOD -- WI																		
TORK 55-71-029-QRY Created On: 01/06/14 Updated On:	Q	NE	SW	1	22N	5E	Wood	0-225-20-2014		0.0	1.0	7.0	28.2	2.649	2.666	0.659		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
TORK 55-71-029-QRY Created On: 01/03/17 Updated On:	Q	NE	SW	1	22N	5E	Wood	0-225-2-2017		0.0	0.1	5.8	25.1	2.668	2.682	0.538		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
TORK 55-71-029-QRY Created On: 01/02/20 Updated On:	Q	NE	SW	1	22N	5E	Wood	0-225-1-2020	0.2	0.0	1.6	6.6	27.4	2.664	2.679	0.584		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
TORK 55-71-029-QRY Created On: 01/03/23 Updated On:	Q	NE	SW	1	22N	5E	Wood	0-225-33-2023	0.0	1.0	1.7	6.6	27.6	2.624	2.640	0.608		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
HOUSTON -- MN																		
ABNET 27-00-008-QRY Created On: 06/26/14 Updated On:	Q			2	104N	5W	Houston	0-225-204-2014		1.9	2.3	10.4	35.2	2.590	2.649	2.276		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
ABNET 27-00-008-QRY Created On: 05/04/17 Updated On:	Q			2	104N	5W	Houston	0-225-170-2017	0.8	2.2	4.8	8.1	32.9	2.644	2.690	1.769		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
ABNET 27-00-008-QRY Created On: 02/03/20 Updated On:	Q			2	104N	5W	Houston	0-225-108-2020	2.4	1.0	4.1	8.0	33.1	2.617	2.672	2.083		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse					
	P/Q	Qrt	Qrt	Sect	Town	Range	County	LA Wear (%) 100 500					Sp. Gravity OD SSD	Absorp. % Crse Fine				
HOUSTON -- MN																		
ABNET 27-00-008-QRY Created On: 01/03/23 Updated On:	Q		2	104N	5W	Houston		0-225-66-2023	0.9	1.3	3.2	9.8	37.1	2.599	2.658	2.268		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
LAKELAND -- MN																		
GREY CLOUD NELSON 27-00-010-PIT Created On: 04/07/16 Updated On:	P	S	NW	31	27N	21W	Lakeland	0-225-127-2016	0.1	1.9	3.9	4.2	24.0	2.674	2.712	1.422		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
GREY CLOUD NELSON 27-00-010-PIT Created On: 08/12/21 Updated On:	P	S	NW	31	27N	21W	Lakeland	0-225-262-2021	1.5	4.4	1.6	5.2	24.1	2.694	2.722	1.023		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
PINE -- MN																		
CLARK 27-00-013-PIT Created On: 05/09/16 Updated On:	P	NW	SW	26	41N	17W	Pine	0-225-166-2016		3.9	3.1	3.1	15.9	2.781	2.820	1.402		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
CLARK 27-00-013-PIT Created On: 06/10/21 Updated On:	P	NW	SW	26	41N	17W	Pine	0-225-219-2021	2.0	2.9	1.6	4.2	19.2	2.797	2.820	0.837		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
ST LOUIS -- MN																		
ROBERTSON 27-00-014-PIT Created On: 03/16/16 Updated On:	P	NW	SW	11	52N	17W	St Louis	0-225-98-2016		0.6	0.4	2.3	13.4	2.753	2.781	1.035		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse					
	P/Q	Qrt	Qrt	Sect	Town	Range	County	LA Wear (%) 100 500					Sp. Gravity OD SSD	Absorp. % Crse Fine				
ST LOUIS -- MN																		
ROBERTSON 27-00-014-PIT Created On: 04/19/21 Updated On:	P	NW	SW	11	52N	17W	St Louis	0-225-184-2021	2.0	1.3	1.6	4.2	19.2	2.797	2.820	0.837		
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
WABASHA -- MN																		
WABASHA SAND & GRAVEL 27-00-020-PIT Created On: 08/12/21 Updated On:	P			32	11N	10W	Wabasha	0-225-263-2021	0.5	1.7	1.4	3.3	17.7	2.685	2.706	0.757		
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
WINONA -- MN																		
MILESTONE #43 27-00-024-QRY Created On: 01/07/19 Updated On:	Q			16	106N	7W	Winona	0-225-49-2019	0.6	2.0	2.5	8.7	34.9	2.619	2.676	2.192		
Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																		
MILESTONE #43 27-00-024-QRY Created On: 01/03/23 Updated On:	Q			16	106N	7W	Winona	0-225-72-2023	0.8	1.1	3.8	10.1	39.4	2.614	2.672	2.223		
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
WINONA, MN -- MN																		
*PICKWICK 27-00-030-QRY Created On: 06/14/18 Updated On:	Q			1	105N	6W	Winona, Mn	0-225-233-2018	1.6	1.1	2.3	7.8	34.8	2.618	2.674	2.145		
Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																		
*PICKWICK 27-00-030-QRY Created On: 01/07/19 Updated On:	Q			1	105N	6W	Winona, Mn	0-225-50-2019	1.5	4.0	4.0	9.4	39.4	2.586	2.650	2.471		
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse					
	P/Q	Qrt	Qrt	Sect	Town	Range	County					LA Wear (%)		Sp. Gravity		Absorp. %	
											100	500	OD	SSD	Crse	Fine	
GOGEBIC -- MI																	
MARHAR - MICHIGAN 26-00-003-PIT Created On: 01/04/22 Updated On:	P	S	NW	34	45N	35E	Gogebic	0-225-28-2022	0.0	1.4	1.4	3.0	14.2	2.769	2.783	0.519	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
WIEMEIR 26-00-005-PIT Created On: 04/23/15 Updated On:	P	SW	NW	33	48N	47W	Gogebic	0-225-130-2015		6.3	13.9	5.4	23.0	2.717	2.760	1.581	
	Approved Use : Base Aggregate																
WIEMEIR 26-00-005-PIT Created On: 04/30/21 Updated On:	P	SW	NW	33	48N	47W	Gogebic	0-225-193-2021	1.8	11.1	17.7	5.6	24.9	2.715	2.754	1.456	
	Approved Use : Base Aggregate																
IRON -- MI																	
BEECHWOOD 26-00-013-PIT Created On: 06/11/20 Updated On:	P	NE	NW	1	43N	36W	Iron	0-225-193-2020	0.0	2.0	0.3	3.0	15.8	2.734	2.752	0.676	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
CZAPIGA 55-26-005-PIT Created On: 06/11/20 Updated On:	P	NE	SE	26	42N	35W	Iron	0-225-194-2020		1.6	0.9	3.2	16.6	2.736	2.754	0.681	
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																
IRON RIVER 26-00-008-PIT Created On: 01/05/17 Updated On:	P	SW	NW	22	43N	35W	Iron	0-225-40-2017	0.8	0.5	0.5	3.6	14.8	2.712	2.740	1.030	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
IRON RIVER 26-00-008-PIT Created On: 01/04/22 Updated On:	P	SW	NW	22	43N	35W	Iron	0-225-27-2022	0.0	0.5	0.6	3.4	15.1	2.715	2.736	0.752	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse					
	P/Q	Qrt	Qrt	Sect	Town	Range	County	LA Wear (%) 100 500					Sp. Gravity OD SSD	Absorp. % Crse Fine				
IRON, MI -- MI																		
FA 26-00-014-PIT Created On: 04/19/21 Updated On:	P		8	43N	35W	Iron, Mi		0-225-183-2021	0.0	1.0	0.8	4.4	19.1	2.694	2.716	0.810		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
DUNDEE -- IL																		
BEVERLY MATERIALS 17-00-018-PIT Created On: 01/24/22 Updated On:	P	NE	SE	36	42N	8E	Dundee	0-225-115-2022	2.4	12.9	2.8	5.2	26.5	2.674	2.713	1.458		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
KENDALL, IL -- IL																		
*LAFARGE KENDALL 17-00-017-QRY Created On: 04/30/21 Updated On:	Q		W	29	35N	7E	Kendall, Il	0-225-199-2021	0.6	1.9	0.4	6.8	29.0	2.695	2.727	1.213		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
LAKE -- IL																		
THELEN-ANTIOCH 17-00-002-PIT Created On: 06/12/14 Updated On:	P			9	46N	9E	Lake	0-225-189-2014	2.2	0.0	4.8	7.9	33.9	2.695	2.727	1.184		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
THELEN-ANTIOCH 17-00-002-PIT Created On: 05/09/18 Updated On:	P			9	46N	9E	Lake	0-225-196-2018	0.2	11.9	0.9	5.7	26.1	2.695	2.733	1.439		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
THELEN-ANTIOCH 17-00-002-PIT Created On: 01/03/23 Updated On:	P			9	46N	9E	Lake	0-225-51-2023	1.0	16.2	6.6	4.5	25.1	2.662	2.701	1.465		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse					
	P/Q	Qrt	Qrt	Sect	Town	Range	County	LA Wear (%) 100 500					Sp. Gravity OD SSD	Absorp. % Crse Fine				
MCHENRY -- IL																		
HOLCIM-MCHENRY 17-00-011-PIT Created On: 04/24/23 Updated On:	P	NE	NE	29	45N	8E	Mchenry	0-225-205-2023	0.5	7.9	5.2	4.6	24.9	2.631	2.678	1.807		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
SUPER AGGREGATE - BURGETT LAKES 17-00-007-PIT Created On: 02/16/16 Updated On:	P		SE	1	46N	7E	Mchenry	0-225-88-2016	1.6	3.2	1.7	6.9	34.8	2.677	2.718	1.525		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
SUPER AGGREGATE - BURGETT LAKES 17-00-007-PIT Created On: 01/04/21 Updated On:	P		SE	1	46N	7E	Mchenry	0-225-9-2021	0.7	4.7	0.3	4.5	23.4	2.676	2.708	1.199		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
STATEWIDE -- IL																		
*IRENE 17-01-010-QRY Created On: 05/01/18 Updated On:	Q		NW	9	43N	3E	Statewide	0-225-188-2018	0.2	4.8	4.8	7.6	37.9	2.599	2.662	2.393		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
*IRENE 17-01-010-QRY Created On: 08/10/20 Updated On:	Q		NW	9	43N	3E	Statewide	0-225-230-2020	0.2	10.2	3.9	8.5	35.5	2.603	2.665	2.378		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
WINNEBAGO IL -- IL																		
*ROGERS 17-00-013-PIT Created On: 06/14/18 Updated On:	P		SW	9	46N	2E	Winnebago Il	0-225-235-2018		1.1	1.8	4.8	23.9	2.663	2.702	1.461		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse				
	P/Q	Qrt	Qrt	Sect	Town	Range	County					LA Wear (%)		Sp. Gravity		Absorp. %
											100	500	OD	SSD	Crse	Fine
WINNEBAGO IL -- IL																
*ROGERS 17-00-013-PIT Created On: 06/03/19 Updated On:	P		SW 9	46N	2E	Winnebago Il	0-225-202-2019	5.0	4.7	0.7	4.3	26.0	2.672	2.706	1.270	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate															
CLAYTON -- IA																
FRENCHTOWN 19-00-008-QRY Created On: 05/22/19 Updated On:	Q			18	93N	2W Clayton	0-225-191-2019	0.4	1.4	0.2	5.9	26.6	2.647	2.685	1.444	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate															
FRENCHTOWN 19-00-008-QRY Created On: 05/22/19 Updated On:	Q			18	93N	2W Clayton	0-225-192-2019	0.1	4.3	0.7	6.2	27.7	2.661	2.703	1.558	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate															
FRENCHTOWN 19-00-008-QRY Created On: 01/13/22 Updated On:	Q			18	93N	2W Clayton	0-225-112-2022	1.8	3.6	2.8	7.5	32.1	2.606	2.660	2.069	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate															
FRENCHTOWN 19-00-008-QRY Created On: 03/27/24 Updated On:	Q			18	93N	2W Clayton	0-225-207-2024	1.4	14.4	3.9	9.5	36.7	2.580	2.650	2.724	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate															
DUBUQUE -- IA																
*BROWNS BOTTOM 19-00-002-QRY Created On: 04/23/15 Updated On:	Q		NE 24	88N	3E	Dubuque	0-225-131-2015		0.2	0.8	7.0	28.0	2.670	2.706	1.367	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate															

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
DUBUQUE -- IA																		
*BROWNS BOTTOM 19-00-002-QRY Created On: 01/04/18 Updated On:	Q		NE	24	88N	3E	Dubuque	0-225-72-2018	0.2	1.3	1.1	6.4	27.3	2.661	2.701	1.506		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
*BROWNS BOTTOM 19-00-002-QRY Created On: 01/05/21 Updated On:	Q		NE	24	88N	3E	Dubuque	0-225-57-2021	0.2	0.5	0.6	7.3	29.1	2.676	2.715	1.430		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
*BROWNS BOTTOM 19-00-002-QRY Created On: 01/02/24 Updated On:	Q		NE	24	88N	3E	Dubuque	0-225-34-2024	0.3	3.1	1.0	8.4	32.0	2.620	2.673	2.026		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
*ROSE SPUR 19-00-005-QRY Created On: 07/30/15 Updated On:	Q	NE	SE	27	90N	2E	Dubuque	0-225-221-2015	1.9	3.5	3.4	10.5	38.6	2.585	2.651	2.533		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
*ROSE SPUR 19-00-005-QRY Created On: 01/04/18 Updated On:	Q	NE	SE	27	90N	2E	Dubuque	0-225-69-2018	2.5	11.3	4.1	9.7	36.4	2.582	2.646	2.493		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
*ROSE SPUR 19-00-005-QRY Created On: 01/05/21 Updated On:	Q	NE	SE	27	90N	2E	Dubuque	0-225-58-2021	1.2	5.2	10.0	9.3	35.3	2.567	2.638	2.764		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
*ROSE SPUR 19-00-005-QRY Created On: 01/02/24 Updated On:	Q	NE	SE	27	90N	2E	Dubuque	0-225-28-2024	2.0	9.4	3.5	9.8	35.8	2.584	2.652	2.603		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 05/06/2024

Report Date Range 2014 AND 2024

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
DUBUQUE -- IA																		
RUBIE 19-00-007-QRY Created On: 01/04/18 Updated On:	Q		SE	6	88N	3E	Dubuque	0-225-66-2018	0.6	4.6	2.5	8.5	35.4	2.578	2.639	2.392		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
RUBIE 19-00-007-QRY Created On: 03/17/21 Updated On:	Q		SE	6	88N	3E	Dubuque	0-225-144-2021	1.1	3.5	3.7	7.6	33.0	2.614	2.670	2.141		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
RUBIE 19-00-007-QRY Created On: 01/02/24 Updated On:	Q		SE	6	88N	3E	Dubuque	0-225-30-2024	0.4	2.9	0.7	8.4	31.8	2.625	2.678	1.997		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

Prepared by:

Wisconsin Department of Transportation
Bureau of Highway Construction
Quality Management Section