

WisDOT Pit and Quarry Listing for Use in 2025.

Acceptable “Pit” sources are those tested in 2021 to 2025.

Acceptable “Quarry” sources are those tested in 2023 to 2025.

All source test data (both satisfactory and non-satisfactory) is shown, please check source data to ensure source meets specification requirements for the intended usage.

Certified sources expire at end of allocated calendar years.

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
* 175 WEST 55-20-054-QRY Created On: 07/15/20 Updated On:	Q	NE	SW	10	14N	17E	Fond Du Lac	0-225-214-2020	0.0	4.9	1.4	7.7	32.8	2.724	2.757	1.200	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
19TH HOLE (BURGESS) 55-25-001-QRY Created On: 03/23/17 Updated On:	Q	SE	SW	15	5N	3E	Iowa	0-225-88-2017	1.7	6.2	9.7	10.0	36.9	2.536	2.629	3.681	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
19TH HOLE (BURGESS) 55-25-001-QRY Created On: 07/15/20 Updated On:	Q	SE	SW	15	5N	3E	Iowa	0-225-217-2020	1.3	4.7	10.0	8.0	32.9	2.543	2.628	3.350	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
19TH HOLE (BURGESS) 55-25-001-QRY Created On: 02/28/24 Updated On:	Q	SE	SW	15	5N	3E	Iowa	0-225-185-2024	1.8	8.1	11.7	9.8	37.4	2.487	2.588	4.051	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
29 PINES PIT 55-09-085-PIT Created On: 07/23/25 Updated On:	P	SE	SW	24	28N	10W	Chippewa	0-225-227-2025	1.0	0.0	9.8	8.2	28.0	2.623	2.665	1.591	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
A TO Z AGGREGATE SOLUTIONS 55-51-001-PIT Created On: 01/23/17 Updated On:	P		SW	3	3N	19E	Racine	0-225-56-2017	1.9	2.4	1.7	7.0	35.6	2.694	2.732	1.394	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
A TO Z AGGREGATE SOLUTIONS 55-51-001-PIT Created On: 01/05/21 Updated On:	P		SW	3	3N	19E	Racine	0-225-80-2021	0.0	8.4	5.3	4.4	23.6	2.680	2.720	1.503	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
A-FRAME 55-43-001-PIT Created On: 05/12/16 Updated On:	P	NE	NE	22	37N	6E	Oneida	0-225-169-2016		0.0	0.3	4.6	20.3	2.681	2.712	1.169	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
A-FRAME 55-43-001-PIT Created On: 01/08/20 Updated On:	P	NE	NE	22	37N	6E	Oneida	0-225-49-2020	1.5	0.0	1.9	4.0	18.6	2.724	2.737	0.483	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
A-FRAME 55-43-001-PIT Created On: 01/02/25 Updated On:	P	NE	NE	22	37N	6E	Oneida	0-225-67-2025	1.7	0.0	2.1	4.7	20.7	2.674	2.698	0.878	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
ABNET 27-00-008-QRY Created On: 05/04/17 Updated On:	Q			2	104N	5W	Houston	0-225-170-2017	0.8	2.2	4.8	8.1	32.9	2.644	2.690	1.769	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
ABNET 27-00-008-QRY Created On: 02/03/20 Updated On:	Q			2	104N	5W	Houston	0-225-108-2020	2.4	1.0	4.1	8.0	33.1	2.617	2.672	2.083	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
ABNET 27-00-008-QRY Created On: 01/03/23 Updated On:	Q			2	104N	5W	Houston	0-225-66-2023	0.9	1.3	3.2	9.8	37.1	2.599	2.658	2.268	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
ADAMETZ 55-22-001-QRY Created On: 01/05/17 Updated On:	Q	SE	SE	11	6N	1W	Grant	0-225-29-2017	0.3	5.4	4.1	8.5	34.9	2.631	2.680	1.878	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
ADAMETZ 55-22-001-QRY Created On: 01/04/19 Updated On:	Q	SE	SE	11	6N	1W	Grant	0-225-27-2019	1.2	7.9	7.2	12.6	40.8	2.608	2.665	2.185	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
ADAMETZ 55-22-001-QRY Created On: 01/04/22 Updated On:	Q	SE	SE	11	6N	1W	Grant	0-225-52-2022	1.1	5.0	2.7	8.0	29.5	2.644	2.693	1.825	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
ADAMETZ 55-22-001-QRY Created On: 01/02/25 Updated On:	Q	SE	SE	11	6N	1W	Grant	0-225-31-2025	0.9	3.3	1.2	8.4	31.0	2.637	2.690	1.977	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
ADAMS PIT 55-03-044-PIT Created On: 01/08/20 Updated On:	P	NW	NE	12	33N	10W	Barron	0-225-51-2020	0.8	0.0	1.4	4.8	20.9	2.708	2.736	1.032	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
ADAMS PIT 55-03-044-PIT Created On: 04/29/25 Updated On:	P	NW	NE	12	33N	10W	Barron	0-225-202-2025	0.8	0.0	1.3	5.1	21.2	2.711	2.739	1.031	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
AGGRECON 55-36-001-QRY Created On: 06/03/15 Updated On:	Q		SE	33	17N	21E	Manitowoc	0-225-182-2015	1.5	0.0	1.4	7.6	32.9	2.719	2.751	1.152	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
AGGRECON 55-36-001-QRY Created On: 02/15/18 Updated On:	Q		SE	33	17N	21E	Manitowoc	0-225-99-2018	0.9	3.3	2.7	6.6	32.2	2.745	2.770	0.917	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
AGGRECON 55-36-001-QRY Created On: 01/04/21 Updated On:	Q		SE	33	17N	21E	Manitowoc	0-225-43-2021	0.3	1.2	0.3	5.3	25.5	2.764	2.785	0.755	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
AGGRECON 55-36-001-QRY Created On: 01/29/24 Updated On:	Q		SE	33	17N	21E	Manitowoc	0-225-166-2024	0.0	0.9	1.2	6.4	29.4	2.780	2.799	0.659	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
AINSWORTH 55-34-001-PIT Created On: 01/04/19 Updated On:	P	SW	SW	1	33N	12E	Langlade	0-225-13-2019	0.0	0.0	0.2	5.3	22.9	2.693	2.709	0.613	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
AINSWORTH 55-34-001-PIT Created On: 08/14/24 Updated On:	P	SW	SW	1	33N	12E	Langlade	0-225-295-2024	0.9	1.0	0.6	5.1	21.5	2.703	2.719	0.615	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
ALT 55-56-033-QRY Created On: 06/02/20 Updated On:	Q			12	9N	3E	Sauk	0-225-183-2020	1.2	0.0	8.5	10.9	37.6	2.574	2.644	2.715	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
ALT 55-56-033-QRY Created On: 01/02/24 Updated On:	Q			12	9N	3E	Sauk	0-225-119-2024	0.9	5.9	1.3	9.3	34.1	2.600	2.662	2.370	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
* ALVA MILLER 55-52-001-QRY Created On: 06/30/16 Updated On:	Q			17	9N	2W	Richland	0-225-219-2016		0.0	2.2	7.3	30.3	2.692	2.727	1.299	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
* ALVA MILLER 55-52-001-QRY Created On: 06/20/22 Updated On:	Q			17	9N	2W	Richland	0-225-232-2022	1.2	1.6	1.1	7.9	32.9	2.680	2.718	1.430		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
AMERICAN MATERIALS #31 55-18-003-PIT Created On: 01/05/17 Updated On:	P	N	NE	2	26N	10W	Eau Claire	0-225-32-2017		0.0	2.9	4.4	20.9	2.635	2.666	1.171		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
AMERICAN MATERIALS #31 55-18-003-PIT Created On: 01/04/21 Updated On:	P	N	NE	2	26N	10W	Eau Claire	0-225-36-2021	1.1	5.4	5.7	4.1	20.2	2.638	2.668	1.166		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
AMON / WILSON 55-64-002-PIT Created On: 06/30/17 Updated On:	P	NE	SE	25	3N	18E	Walworth	0-225-226-2017		0.0	0.9	7.4	37.2	2.669	2.708	1.467		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
AMON / WILSON 55-64-002-PIT Created On: 04/05/22 Updated On:	P	NE	SE	25	3N	18E	Walworth	0-225-169-2022	0.9	0.0	4.5	4.8	26.5	2.680	2.720	1.491		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
AMRIZE - CONCO 17-00-023-QRY Created On: 03/06/25 Updated On:	Q	SE	SE	3	38N	7E	Statewide	0-225-170-2025	0.2	2.4	2.6	6.0	27.1	2.635	2.683	1.786		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
AMRIZE-COLGATE 55-67-021-PIT Created On: 01/08/15 Updated On:	P	S	NW	3	8N	19E	Waukesha	0-225-35-2015	0.9	2.5	2.4	4.5	23.9	2.736	2.759	0.827		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
AMRIZE-COLGATE 55-67-021-PIT Created On: 03/16/18 Updated On:	P	S	NW	3	8N	19E	Waukesha	0-225-129-2018		3.7	3.6	5.6	25.7	2.742	2.765	0.840	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
AMRIZE-COLGATE 55-67-021-PIT Created On: 01/03/23 Updated On:	P	S	NW	3	8N	19E	Waukesha	0-225-26-2023	0.0	5.6	1.0	6.0	27.6	2.691	2.728	1.408	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
AMRIZE-DYER LAKE 55-30-004-PIT Created On: 05/11/18 Updated On:	P		W	29	2N	19E	Kenosha	0-225-209-2018	2.4	10.7	6.7	5.2	25.1	2.673	2.713	1.500	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
AMRIZE-DYER LAKE 55-30-004-PIT Created On: 01/03/23 Updated On:	P		W	29	2N	19E	Kenosha	0-225-31-2023	0.0	12.3	1.3	6.6	28.2	2.628	2.683	2.079	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
AMRIZE-ELBURN 17-00-024-PIT Created On: 03/24/25 Updated On:	P			20	39N	7E	Statewide	0-225-175-2025	0.0	10.6	10.0	5.8	29.0	2.646	2.697	1.932	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
AMRIZE-JOLIET 17-00-022-QRY Created On: 03/06/25 Updated On:	Q			20	39N	7E	Statewide	0-225-169-2025	0.0	0.8	1.1	6.0	27.6	2.660	2.702	1.568	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
AMRIZE-KENDALL, ILL 17-00-021-QRY Created On: 04/30/24 Updated On:	Q	NW	SE	29	35N	7E	Statewide	0-225-242-2024	0.3	5.9	0.9	7.7	31.3	2.683	2.724	1.513	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse					
	P/Q	Qrt	Qrt	Sect	Town	Range	County	LA Wear (%)					Sp. Gravity		Absorp. %			
								100					500	OD	SSD	Crse	Fine	
AMRIZE-MCHENRY 17-00-011-PIT Created On: 04/24/23 Updated On:	P	NE	NE	29	45N	8E	Mchenry	0-225-205-2023	0.5	7.9	5.2	4.6	24.9	2.631	2.678	1.807		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
ANDERSON 55-13-001-PIT Created On: 01/05/17 Updated On:	P	E	NW	10	5N	11E	Dane	0-225-51-2017	1.7	16.3	16.8	11.2	42.5	2.545	2.630	3.316		
	Approved Use : Base Aggregate																	
ANDERSON 55-13-001-PIT Created On: 01/03/23 Updated On:	P	E	NW	10	5N	11E	Dane	0-225-4-2023	0.3	3.2	13.1	8.1	35.2	2.586	2.655	2.679		
	Approved Use : Base Aggregate																	
ANDERSON 55-13-001-PIT Created On: 07/31/24 Updated On:	P	E	NW	10	5N	11E	Dane	0-225-288-2024	4.0	13.6	7.0	11.2	41.1	2.574	2.649	2.935		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
ANTIGO 55-34-002-PIT Created On: 01/04/19 Updated On:	P	SE	NE	13	31N	11E	Langlade	0-225-15-2019	0.0	0.7	1.4	7.8	32.6	2.650	2.672	0.802		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
ANTIGO 55-34-002-PIT Created On: 01/02/24 Updated On:	P	SE	NE	13	31N	11E	Langlade	0-225-11-2024	0.2	0.0	0.2	6.6	27.5	2.676	2.695	0.719		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
APPEL 55-33-002-QRY Created On: 04/23/15 Updated On:	Q	NW	SW	11	1N	3E	Lafayette	0-225-132-2015	0.2	0.4	3.5	10.1	38.7	2.635	2.686	1.954		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse					
	P/Q	Qrt	Qrt	Sect	Town	Range	County	LA Wear (%)					Sp. Gravity		Absorp. %			
								100					500	OD	SSD	Crse	Fine	
APPEL 55-33-002-QRY Created On: 01/04/18 Updated On:	Q	NW	SW	11	1N	3E	Lafayette	0-225-70-2018	0.5	8.4	4.5	12.6	42.9	2.575	2.643	2.644		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
APPEL 55-33-002-QRY Created On: 01/05/21 Updated On:	Q	NW	SW	11	1N	3E	Lafayette	0-225-61-2021	0.8	3.1	5.0	11.2	39.6	2.619	2.677	2.213		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
APPEL 55-33-002-QRY Created On: 06/12/25 Updated On:	Q	NW	SW	11	1N	3E	Lafayette	0-225-222-2025	1.0	10.0	5.1	9.5	37.6	2.608	2.671	2.411		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
ARCADIA 55-61-003-QRY Created On: 04/25/17 Updated On:	Q	NW	SE	16	20N	9W	Trempealeau	0-225-150-2017		0.0	2.3	12.5	43.4	2.536	2.613	3.068		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
ARCADIA 55-61-003-QRY Created On: 06/02/20 Updated On:	Q	NW	SE	16	20N	9W	Trempealeau	0-225-185-2020	0.8	0.0	4.5	8.6	37.7	2.554	2.635	3.170		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
ARCADIA 55-61-003-QRY Created On: 01/03/23 Updated On:	Q	NW	SE	16	20N	9W	Trempealeau	0-225-64-2023	1.8	0.8	3.6	10.6	42.9	2.548	2.614	2.607		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
ARLINGTON 55-11-002-PIT Created On: 05/04/17 Updated On:	P			23	10N	9E	Columbia	0-225-166-2017	2.4	0.0	4.2	5.7	26.4	2.674	2.724	1.863		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Coarse Sp. Gravity		Coarse Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
ARLINGTON 55-11-002-PIT Created On: 06/01/22 Updated On:	P			23	10N	9E	Columbia	0-225-210-2022	1.7	0.0	4.8	5.4	26.5	2.705	2.746	1.502	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
ASHTON 55-22-003-QRY Created On: 06/30/16 Updated On:	Q	SW	SW	26	4N	3W	Grant	0-225-218-2016		3.6	1.1	12.3	42.2	2.588	2.663	2.893	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
ASHTON 55-22-003-QRY Created On: 01/07/19 Updated On:	Q	SW	SW	26	4N	3W	Grant	0-225-52-2019	0.4	9.8	2.8	14.0	45.7	2.570	2.646	2.946	
	Approved Use : CONCRETE, Base Aggregate																
ASHTON 55-22-003-QRY Created On: 04/05/23 Updated On:	Q	SW	SW	26	4N	3W	Grant	0-225-189-2023	0.4	9.2	9.4	12.3	42.9	2.591	2.662	2.716	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
ASPHALT CONTRACTORS JEFFERSON 55-28-019-PIT Created On: 01/08/21 Updated On:	P		NE	3	6N	13E	Jefferson	0-225-117-2021	2.3	3.8	0.8	8.6	35.4	2.634	2.681	1.789	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
ATHENS 55-37-005-QRY Created On: 08/16/16 Updated On:	Q	S	SE	24	30N	4E	Marathon	0-225-243-2016		0.0	0.2	5.1	24.8	2.695	2.710	0.573	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
ATHENS 55-37-005-QRY Created On: 05/10/18 Updated On:	Q	S	SE	24	30N	4E	Marathon	0-225-203-2018		0.0	0.2	3.0	16.1	2.837	2.845	0.255	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
ATHENS 55-37-005-QRY Created On: 01/05/21 Updated On:	Q	S	SE	24	30N	4E	Marathon	0-225-87-2021	0.0	0.0	0.6	4.8	23.1	2.711	2.724	0.492	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
ATHENS 55-37-005-QRY Created On: 01/02/24 Updated On:	Q	S	SE	24	30N	4E	Marathon	0-225-81-2024	0.0	0.0	0.3	5.4	25.3	2.708	2.718	0.397	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
ATKINSON 55-64-005-PIT Created On: 01/18/19 Updated On:	P	NE	SW	6	3N	18E	Walworth	0-225-87-2019	4.6	4.2	0.7	5.1	26.3	2.681	2.717	1.342	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
ATKINSON 55-64-005-PIT Created On: 01/02/24 Updated On:	P	NE	SW	6	3N	18E	Walworth	0-225-15-2024	0.4	4.9	2.9	5.0	25.8	2.668	2.704	1.323	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
BADGERLAND 55-36-031-PIT Created On: 01/25/19 Updated On:	P			33	21N	23E	Manitowoc	0-225-93-2019	1.8	0.0	3.5	5.9	29.5	2.697	2.738	1.535	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
BADGERLAND 55-36-031-PIT Created On: 02/28/24 Updated On:	P			33	21N	23E	Manitowoc	0-225-170-2024	4.2	0.0	2.5	6.5	30.4	2.719	2.753	1.245	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
BADGERLAND - LARABEE 55-36-033-QRY Created On: 04/24/19 Updated On:	Q			33	21N	23E	Manitowoc	0-225-166-2019	0.0	0.0	3.7	6.5	29.6	2.743	2.764	0.768	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse		Absorp. %	
Source Name	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
BADGERLAND - LARABEE 55-36-033-QRY Created On: 01/04/22 Updated On:	Q			33	21N	23E	Manitowoc	0-225-63-2022	3.7	0.0	5.3	8.1	34.8	2.661	2.711	1.890		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
BADGERLAND - LARABEE 55-36-033-QRY Created On: 04/15/24 Updated On:	Q			33	21N	23E	Manitowoc	0-225-230-2024	0.0	0.0	0.9	9.0	38.7	2.794	2.811	0.625		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
BADGERLAND BISON 55-59-003-PIT Created On: 01/04/16 Updated On:	P	SW	NE	19	15N	20E	Sheboygan	0-225-5-2016	2.0	0.7	0.9	5.9	29.2	2.744	2.770	0.961		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
BADGERLAND BISON 55-59-003-PIT Created On: 03/10/21 Updated On:	P	SW	NE	19	15N	20E	Sheboygan	0-225-132-2021	2.0	2.8	2.8	6.5	31.6	2.735	2.765	1.079		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
BADGERLAND X PIT 55-36-039-PIT Created On: 08/28/18 Updated On:	P		SW	9	17N	22E	Manitowoc	0-225-278-2018	0.1	0.0	1.3	6.0	27.5	2.774	2.799	0.870		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
BADGERLAND X PIT 55-36-039-PIT Created On: 03/21/23 Updated On:	P		SW	9	17N	22E	Manitowoc	0-225-172-2023	0.8	0.0	2.9	6.3	30.2	2.763	2.790	0.948		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
BADGERLAND-SHOTO 55-36-005-QRY Created On: 01/21/16 Updated On:	Q	SE	SW	20	20N	24E	Manitowoc	0-225-67-2016	0.8	1.1	1.2	8.0	32.1	2.798	2.817	0.704		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
BADGERLAND-SHOTO 55-36-005-QRY Created On: 01/25/19 Updated On:	Q	SE	SW	20	20N	24E	Manitowoc	0-225-92-2019		0.0	4.1	8.5	32.5	2.746	2.781	1.284	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
BADGERLAND-SHOTO 55-36-005-QRY Created On: 01/04/22 Updated On:	Q	SE	SW	20	20N	24E	Manitowoc	0-225-67-2022	0.0	0.0	8.5	7.9	32.3	2.785	2.806	0.771	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
BADGERLAND-SHOTO 55-36-005-QRY Created On: 04/07/25 Updated On:	Q	SE	SW	20	20N	24E	Manitowoc	0-225-183-2025	0.0	1.0	0.5	7.4	29.9	2.813	2.825	0.437	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
BAILEYS HARBOR 55-15-001-QRY Created On: 01/21/16 Updated On:	Q	SW	NW	17	30N	28E	Door	0-225-73-2016	4.5	0.0	4.4	7.7	33.0	2.631	2.687	2.132	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
BAILEYS HARBOR 55-15-001-QRY Created On: 04/13/17 Updated On:	Q	SW	NW	17	30N	28E	Door	0-225-130-2017	1.3	0.0	2.9	7.6	32.6	2.637	2.692	2.074	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
BAILEYS HARBOR 55-15-001-QRY Created On: 01/02/20 Updated On:	Q	SW	NW	17	30N	28E	Door	0-225-6-2020		0.0	1.4	6.6	30.3	2.548	2.605	2.233	
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																
BAILEYS HARBOR 55-15-001-QRY Created On: 01/03/23 Updated On:	Q	SW	NW	17	30N	28E	Door	0-225-38-2023	0.2	3.9	1.3	6.0	26.9	2.742	2.773	1.137	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
* BAKER 55-22-065-QRY Created On: 06/17/21 Updated On:	Q	NE	NE	35	4N	2W	Grant	0-225-224-2021	0.5	8.2	11.6	15.3	48.3	2.557	2.638	3.177	
	Approved Use : CONCRETE, OGBC, Base Aggregate																
* BAKKESTUEN / COON VALLEY 55-62-002-PIT Created On: 06/12/17 Updated On:	Q	NW	NW	22	14N	5W	Vernon	0-225-211-2017		0.0	1.7	9.7	36.4	2.646	2.694	1.843	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
* BAKKESTUEN / COON VALLEY 55-62-002-PIT Created On: 01/10/22 Updated On:	Q	NW	NW	22	14N	5W	Vernon	0-225-107-2022	0.7	1.3	0.3	11.4	35.8	2.639	2.687	1.788	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
BALFANZ 55-56-001-QRY Created On: 07/16/15 Updated On:	Q	NE	NE	14	10N	5E	Sauk	0-225-211-2015		0.0	3.8	9.0	42.8	2.557	2.628	2.758	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
BALFANZ 55-56-001-QRY Created On: 01/03/18 Updated On:	Q	NE	NE	14	10N	5E	Sauk	0-225-24-2018	0.7	6.7	8.1	12.8	45.6	2.527	2.607	3.151	
	Approved Use : HMA<MT, CONCRETE, Base Aggregate																
BALFANZ 55-56-001-QRY Created On: 04/06/21 Updated On:	Q	NE	NE	14	10N	5E	Sauk	0-225-171-2021	0.6	1.4	1.3	10.9	41.1	2.597	2.655	2.257	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
BALFANZ 55-56-001-QRY Created On: 01/02/24 Updated On:	Q	NE	NE	14	10N	5E	Sauk	0-225-70-2024	0.3	1.7	2.0	11.6	42.5	2.574	2.635	2.381	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
Source Name	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
BALLWEG 55-11-003-QRY Created On: 01/21/16 Updated On:	Q		SE	25	10N	7E	Columbia	0-225-63-2016	0.8	1.1	1.0	7.2	30.7	2.590	2.656	2.547	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
BALLWEG 55-11-003-QRY Created On: 04/01/19 Updated On:	Q		SE	25	10N	7E	Columbia	0-225-119-2019	0.9	3.4	5.8	8.7	33.7	2.615	2.669	2.090	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
BALLWEG 55-11-003-QRY Created On: 01/04/22 Updated On:	Q		SE	25	10N	7E	Columbia	0-225-57-2022	0.8	1.3	3.0	7.7	30.0	2.618	2.672	2.065	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
BALLWEG 55-11-003-QRY Created On: 02/07/25 Updated On:	Q		SE	25	10N	7E	Columbia	0-225-150-2025	0.1	1.6	2.8	7.4	30.9	2.609	2.670	2.326	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
BARNES 55-04-001-QRY Created On: 05/08/15 Updated On:	Q	NW	NE	21	44N	9W	Bayfield	0-225-157-2015		0.0	7.1	3.9	15.4	2.874	2.891	0.570	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
BARNES 55-04-001-QRY Created On: 01/03/18 Updated On:	Q	NW	NE	21	44N	9W	Bayfield	0-225-18-2018	0.2	0.0	3.9	2.8	12.6	2.854	2.881	0.943	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
BARNES 55-04-001-QRY Created On: 05/06/21 Updated On:	Q	NW	NE	21	44N	9W	Bayfield	0-225-203-2021	0.1	1.2	2.9	2.5	11.1	2.884	2.907	0.802	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
BARNES 55-04-001-QRY Created On: 01/02/24 Updated On:	Q	NW	NE	21	44N	9W	Bayfield	0-225-93-2024	0.1	6.2	11.3	4.6	18.3	2.804	2.844	1.422	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
BATES RD PIT 55-59-024-PIT Created On: 02/17/22 Updated On:	P	E	SE	33	14N	21E	Sheboygan	0-225-129-2022	0.1	2.5	3.2	10.0	38.5	2.715	2.749	1.239	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
BATTERMAN 55-20-050-QRY Created On: 02/03/17 Updated On:	Q	SW	SW	11	14N	17E	Fond Du Lac	0-225-60-2017		0.6	1.4	9.1	40.8	2.696	2.725	1.060	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
BATTERMAN 55-20-050-QRY Created On: 03/02/20 Updated On:	Q	SW	SW	11	14N	17E	Fond Du Lac	0-225-116-2020	0.2	0.5	2.1	8.2	34.7	2.753	2.775	0.821	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
BATTERMAN 55-20-050-QRY Created On: 01/04/23 Updated On:	Q	SW	SW	11	14N	17E	Fond Du Lac	0-225-101-2023	0.0	3.0	1.2	6.5	28.9	2.794	2.808	0.508	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
BAUMEISTER 55-51-005-PIT Created On: 03/24/16 Updated On:	P		NW	19	2N	19E	Racine	0-225-112-2016		0.0	3.2	5.7	25.5	2.632	2.672	1.516	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
BAUMEISTER 55-51-005-PIT Created On: 01/05/21 Updated On:	P		NW	19	2N	19E	Racine	0-225-83-2021	0.0	0.0	5.1	4.8	25.6	2.671	2.712	1.544	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
BAUMEISTER 55-51-005-PIT Created On: 06/02/25 Updated On:	P		NW	19	2N	19E	Racine	0-225-215-2025	1.5	0.0	0.8	5.0	24.4	2.676	2.721	1.664	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
* BAY SETTLEMENT 55-05-012-QRY Created On: 05/17/22 Updated On:	Q			5	24N	22E	Brown	0-225-208-2022	1.8	4.9	1.2	10.5	35.4	2.655	2.711	2.090	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
* BEAVER 55-38-003-QRY Created On: 06/13/22 Updated On:	Q	NE	NE	26	31N	20E	Marinette	0-225-223-2022	5.6	10.7	5.8	10.6	37.9	2.627	2.679	1.973	
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																
BECKER 55-11-004-PIT Created On: 01/07/16 Updated On:	P		SW	34	13N	10E	Columbia	0-225-42-2016		0.0	2.0	6.8	29.1	2.658	2.707	1.856	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
BECKER 55-11-004-PIT Created On: 01/05/21 Updated On:	P		SW	34	13N	10E	Columbia	0-225-79-2021	0.0	2.9	2.9	5.6	26.3	2.686	2.732	1.714	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
BECKS QUARRY 27-00-028-QRY Created On: 07/31/24 Updated On:	Q	N	SE	4	48N	15W	Statewide	0-225-294-2024	0.0	1.8	0.7	4.0	11.3	2.786	2.807	0.767	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
BEECHER 55-38-004-PIT Created On: 07/26/23 Updated On:	P	NW	NE	20	36N	21E	Marinette	0-225-239-2023		1.1	0.0	6.2	27.3	2.716	2.745	1.072	
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
* BEECHWOOD 26-00-013-PIT Created On: 06/11/20 Updated On:	P	NE	NW	1	43N	36W	Iron	0-225-193-2020	0.0	2.0	0.3	3.0	15.8	2.734	2.752	0.676	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
BEN CARRIE 55-70-001-QRY Created On: 01/09/15 Updated On:	Q	NW	SW	29	20N	17E	Winnebago	0-225-49-2015	0.1	2.1	1.4	5.6	24.3	2.768	2.792	0.891	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
BEN CARRIE 55-70-001-QRY Created On: 05/12/16 Updated On:	Q	NW	SW	29	20N	17E	Winnebago	0-225-171-2016		0.9	1.3	4.5	21.5	2.780	2.803	0.825	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
BEN CARRIE 55-70-001-QRY Created On: 03/13/17 Updated On:	Q	NW	SW	29	20N	17E	Winnebago	0-225-79-2017	0.2	1.8	4.6	5.0	23.4	2.768	2.792	0.846	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
BEN CARRIE 55-70-001-QRY Created On: 03/28/18 Updated On:	Q	NW	SW	29	20N	17E	Winnebago	0-225-150-2018	0.1	2.1	1.4	4.3	20.6	2.773	2.799	0.919	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
BEN CARRIE 55-70-001-QRY Created On: 04/10/19 Updated On:	Q	NW	SW	29	20N	17E	Winnebago	0-225-128-2019		5.6	2.9	4.6	22.2	2.761	2.788	0.978	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
BEN CARRIE 55-70-001-QRY Created On: 04/08/20 Updated On:	Q	NW	SW	29	20N	17E	Winnebago	0-225-148-2020	0.0	6.3	3.2	4.9	22.4	2.765	2.794	1.042	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	LA Wear (%)					OD		SSD			
								100					500			Crse	Fine	
BEN CARRIE 55-70-001-QRY Created On: 01/03/23 Updated On:	Q	NW	SW	29	20N	17E	Winnebago	0-225-76-2023	0.0	6.0	3.2	6.6	29.7	2.717	2.753	1.322		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
* BENECKER 55-12-002-QRY Created On: 01/04/21 Updated On:	Q			5	6N	6W	Crawford	0-225-28-2021	11.3	7.8	17.1	18.7	50.3	2.423	2.521	4.012		
	Approved Use : Base Aggregate																	
BENES 55-34-004-PIT Created On: 07/18/19 Updated On:	P	SW	NE	8	32N	11E	Langlade	0-225-241-2019	0.1	0.0	0.5	4.6	20.5	2.709	2.735	0.935		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
BENES 55-34-004-PIT Created On: 01/02/24 Updated On:	P	SW	NE	8	32N	11E	Langlade	0-225-63-2024	0.1	0.0	2.0	5.2	22.0	2.719	2.747	1.035		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
BERNING 55-25-005-QRY Created On: 08/08/16 Updated On:	Q	NE	SW	26	5N	3E	Iowa	0-225-237-2016	1.1	6.2	7.1	8.1	35.0	2.582	2.664	3.184		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
BERNING 55-25-005-QRY Created On: 02/11/19 Updated On:	Q	NE	SW	26	5N	3E	Iowa	0-225-103-2019	1.1	10.8	12.5	8.8	35.3	2.560	2.645	3.316		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
BERNING 55-25-005-QRY Created On: 03/17/21 Updated On:	Q	NE	SW	26	5N	3E	Iowa	0-225-143-2021	1.3	14.6	6.1	6.0	30.6	2.642	2.706	2.400		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County						100	500	OD	SSD	Crse	Fine
BERNING 55-25-005-QRY Created On: 02/28/24 Updated On:	Q	NE	SW	26	5N	3E	Iowa		0-225-184-2024	1.2	13.1	9.3	7.2	32.5	2.616	2.686	2.682	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
BESTWAY 55-54-002-PIT Created On: 01/09/15 Updated On:	P		NW	18	33N	9W	Rusk		0-225-40-2015		0.0	4.8	4.8	20.3	2.724	2.756	1.187	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
BESTWAY 55-54-002-PIT Created On: 01/08/20 Updated On:	P		NW	18	33N	9W	Rusk		0-225-52-2020	0.4	0.0	1.2	4.0	18.8	2.760	2.783	0.837	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
BESTWAY 55-54-002-PIT Created On: 01/02/25 Updated On:	P		NW	18	33N	9W	Rusk		0-225-15-2025	0.9	3.7	3.6	4.3	18.6	2.676	2.719	1.609	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
BEVENT 55-37-008-PIT Created On: 04/30/21 Updated On:	P	SW	NW	5	26N	9E	Marathon		0-225-196-2021	2.0	0.0	0.6	5.8	26.5	2.654	2.675	0.771	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
BEVERLY MATERIALS 17-00-018-PIT Created On: 01/24/22 Updated On:	P	NE	SE	36	42N	8E	Dundee		0-225-115-2022	2.4	12.9	2.8	5.2	26.5	2.674	2.713	1.458	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
BIBBY 55-49-028-PIT Created On: 01/02/24 Updated On:	P	NE	NW	8	22N	9E	Portage		0-225-65-2024	0.2	6.0	0.1	6.7	27.7	2.672	2.698	0.982	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Coarse Sp. Gravity		Coarse Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
BIEHL 55-38-007-QRY Created On: 01/08/16 Updated On:	Q		SE	4	31N	22E	Marinette	0-225-44-2016		7.6	4.9	7.9	34.4	2.675	2.711	1.343	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
BIEHL 55-38-007-QRY Created On: 05/24/19 Updated On:	Q		SE	4	31N	22E	Marinette	0-225-197-2019	0.0	12.3	2.3	9.0	35.0	2.684	2.720	1.314	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
BIEHL 55-38-007-QRY Created On: 05/17/22 Updated On:	Q		SE	4	31N	22E	Marinette	0-225-206-2022	0.0	8.4	2.3	9.5	37.4	2.654	2.704	1.876	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
BIEHL 55-38-007-QRY Created On: 01/02/25 Updated On:	Q		SE	4	31N	22E	Marinette	0-225-64-2025	0.0	10.2	3.0	7.9	34.4	2.677	2.712	1.309	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
BIEHL 11TH ROAD 55-38-008-QRY Created On: 01/05/17 Updated On:	Q	NW	NW	19	30N	21E	Marinette	0-225-53-2017		1.0	0.9	5.9	25.9	2.726	2.762	1.322	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
BIEHL 11TH ROAD 55-38-008-QRY Created On: 07/15/20 Updated On:	Q	NW	NW	19	30N	21E	Marinette	0-225-213-2020	0.0	0.9	1.3	4.1	25.9	2.723	2.754	1.157	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
BIEHL 11TH ROAD 55-38-008-QRY Created On: 01/03/23 Updated On:	Q	NW	NW	19	30N	21E	Marinette	0-225-48-2023	0.1	2.3	1.3	7.7	30.3	2.717	2.750	1.219	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
BIEHL 9TH ROAD 55-38-007-PIT Created On: 01/04/18 Updated On:	P	S	NW	18	30N	21E	Marinette	0-225-85-2018	0.9	0.0	3.5	5.1	26.3	2.711	2.741	1.131	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
BIEHL 9TH ROAD 55-38-007-PIT Created On: 01/03/23 Updated On:	P	S	NW	18	30N	21E	Marinette	0-225-34-2023		4.7	1.9	5.9	25.7	2.686	2.720	1.250	
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																
BIESE 55-36-006-PIT Created On: 01/04/18 Updated On:	P	SW	NE	34	18N	21E	Manitowoc	0-225-83-2018	0.3	1.3	2.7	6.4	30.5	2.752	2.780	1.013	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
BIESE 55-36-006-PIT Created On: 01/02/24 Updated On:	P	SW	NE	34	18N	21E	Manitowoc	0-225-131-2024	2.2	4.7	3.6	9.5	34.1	2.730	2.764	1.220	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
BIG RACK (VENDEN) 55-71-004-QRY Created On: 10/19/17 Updated On:	Q	S	SW	31	24N	3E	Wood	0-225-283-2017		0.0	0.4	4.0	18.2	2.606	2.617	0.389	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
BIG RACK (VENDEN) 55-71-004-QRY Created On: 01/08/20 Updated On:	Q	S	SW	31	24N	3E	Wood	0-225-73-2020	0.0	0.0	0.3	3.6	16.9	2.603	2.616	0.495	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
BIG RACK (VENDEN) 55-71-004-QRY Created On: 01/10/23 Updated On:	Q	S	SW	31	24N	3E	Wood	0-225-105-2023	0.2	0.0	0.3	3.2	16.1	2.615	2.625	0.377	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
BIRCHWOOD 55-63-024-PIT Created On: 05/20/24 Updated On:	P	NW	NE	27	40N	8E	Vilas	0-225-253-2024	0.7	0.0	0.4	3.2	15.9	2.730	2.754	0.868	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
BIWERS 55-15-002-QRY Created On: 04/27/15 Updated On:	Q	NW	SE	10	30N	27E	Door	0-225-139-2015		0.0	1.0	6.4	24.1	2.760	2.783	0.829	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
BIWERS 55-15-002-QRY Created On: 02/15/18 Updated On:	Q	NW	SE	10	30N	27E	Door	0-225-102-2018	0.1	1.0	1.0	6.3	25.9	2.759	2.783	0.876	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
BIWERS 55-15-002-QRY Created On: 01/06/21 Updated On:	Q	NW	SE	10	30N	27E	Door	0-225-113-2021	0.0	0.5	0.7	5.5	23.3	2.760	2.784	0.886	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
BIWERS 55-15-002-QRY Created On: 01/29/24 Updated On:	Q	NW	SE	10	30N	27E	Door	0-225-157-2024	0.1	0.8	0.4	5.4	22.7	2.760	2.783	0.837	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
BJOIN 55-53-003-QRY Created On: 03/22/17 Updated On:	Q	SW	SW	36	3N	11E	Rock	0-225-86-2017	0.6	2.6	8.0	7.2	31.1	2.622	2.690	2.597	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
BJOIN 55-53-003-QRY Created On: 03/02/20 Updated On:	Q	SW	SW	36	3N	11E	Rock	0-225-118-2020	0.6	12.3	10.5	7.3	32.1	2.626	2.689	2.400	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
BJOIN 55-53-003-QRY Created On: 01/30/23 Updated On:	Q	SW	SW	36	3N	11E	Rock	0-225-133-2023	0.6	26.4	10.2	8.1	34.8	2.624	2.696	2.733	
BJOIN 55-53-003-QRY Created On: 03/21/23 Updated On:	Q	SW	SW	36	3N	11E	Rock	0-225-174-2023	0.4	15.0	4.4	5.4	26.7	2.678	2.735	2.129	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
BJORNSTAD 55-41-001-QRY Created On: 01/09/15 Updated On:	Q	NE	SW	35	15N	4W	Monroe	0-225-52-2015		0.0	6.3	12.9	41.3	2.562	2.632	2.743	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
BJORNSTAD 55-41-001-QRY Created On: 01/03/18 Updated On:	Q	NE	SW	35	15N	4W	Monroe	0-225-14-2018	1.2	0.0	1.9	10.4	38.2	2.615	2.671	2.140	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
BJORNSTAD 55-41-001-QRY Created On: 01/04/21 Updated On:	Q	NE	SW	35	15N	4W	Monroe	0-225-27-2021	1.2	0.0	0.9	9.3	34.7	2.620	2.671	1.962	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
BJORNSTAD 55-41-001-QRY Created On: 06/05/24 Updated On:	Q	NE	SW	35	15N	4W	Monroe	0-225-264-2024	1.2	2.1	1.3	9.1	38.2	2.602	2.664	2.376	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
* BLACKHAWK 55-23-003-QRY Created On: 05/11/15 Updated On:	Q	SW	NE	20	1N	6E	Green	0-225-162-2015		11.7	9.3	11.0	32.8	2.622	2.676	2.068	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Coarse Sp. Gravity		Coarse Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
* BLACKHAWK 55-23-003-QRY Created On: 03/23/18 Updated On:	Q	SW	NE	20	1N	6E	Green	0-225-142-2018	0.1	13.5	1.6	8.1	29.9	2.601	2.668	2.568		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
* BLACKHAWK 55-23-003-QRY Created On: 03/17/21 Updated On:	Q	SW	NE	20	1N	6E	Green	0-225-151-2021	1.6	7.8	2.3	8.1	26.9	2.578	2.652	2.885		
	Approved Use : Base Aggregate																	
BLACKHAWK QUARRY PRODUCTS 55-33-017-QRY Created On: 02/13/20 Updated On:	Q	NE	NE	15	1N	5E	Lafayette	0-225-112-2020	0.5	4.2	5.6	11.6	42.5	2.538	2.627	3.508		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
BLACKHAWK QUARRY PRODUCTS 55-33-017-QRY Created On: 01/02/24 Updated On:	Q	NE	NE	15	1N	5E	Lafayette	0-225-71-2024	0.1	4.6	2.6	9.9	36.0	2.609	2.676	2.559		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
* BLANCHARD PIT 55-99-044-PIT Created On: 04/02/20 Updated On:	P			26	31N	7W		0-225-143-2020	1.0	0.0	3.7	4.6	20.3	2.728	2.754	0.943		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
BLATZ - QRY 55-36-047-QRY Created On: 01/07/20 Updated On:	Q	SW	NE	35	17N	21E	Manitowoc	0-225-37-2020	0.1	0.0	2.4	6.3	28.3	2.769	2.792	0.815		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
BLATZ - QRY 55-36-047-QRY Created On: 05/20/24 Updated On:	Q	SW	NE	35	17N	21E	Manitowoc	0-225-256-2024	1.4	0.9	2.3	8.9	35.8	2.746	2.771	0.889		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
BLAU (LYCON) 55-11-006-PIT Created On: 01/20/17 Updated On:	P	NE	NW	2	11N	8E	Columbia	0-225-54-2017	1.4	0.0	2.6	7.1	30.0	2.674	2.708	1.266	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
BLAU (LYCON) 55-11-006-PIT Created On: 01/04/22 Updated On:	P	NE	NW	2	11N	8E	Columbia	0-225-42-2022	1.2	0.0	2.8	6.3	28.7	2.692	2.725	1.213	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
BLOOMFIELD 55-64-008-PIT Created On: 01/18/19 Updated On:	P	E	SW	1	1N	19E	Walworth	0-225-86-2019	1.5	7.4	0.9	4.0	21.5	2.669	2.711	1.566	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
BLOOMFIELD 55-64-008-PIT Created On: 04/15/24 Updated On:	P	E	SW	1	1N	19E	Walworth	0-225-223-2024	4.3	17.4	0.1	4.4	24.1	2.164	2.201	1.737	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
BLUE LAKE 55-43-002-PIT Created On: 05/10/18 Updated On:	P	SW	SE	27	39N	6E	Oneida	0-225-205-2018	0.8	0.0	1.4	4.2	18.7	2.701	2.723	0.811	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
BLUE LAKE 55-43-002-PIT Created On: 01/03/23 Updated On:	P	SW	SE	27	39N	6E	Oneida	0-225-29-2023	2.4	0.0	2.5	4.9	20.8	2.670	2.698	1.026	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
BOHL #720 55-03-006-PIT Created On: 02/13/17 Updated On:	P	NW	SE	10	32N	11W	Barron	0-225-70-2017		0.0	2.2	4.4	18.9	2.687	2.715	1.015	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
BOHL #720 55-03-006-PIT Created On: 03/01/22 Updated On:	P	NW	SE	10	32N	11W	Barron	0-225-135-2022	2.5	2.3	2.3	4.0	18.5	2.685	2.715	1.106	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
BOHLMON 55-37-009-PIT Created On: 05/01/18 Updated On:	P		SE	36	28N	10E	Marathon	0-225-187-2018		0.6	2.1	7.5	30.8	2.653	2.682	1.105	
	Approved Use : HMA<MT, HMA>=MT, Base Aggregate																
BOHLMON 55-37-009-PIT Created On: 01/03/23 Updated On:	P		SE	36	28N	10E	Marathon	0-225-16-2023		0.0	0.4	8.6	33.4	2.646	2.673	1.028	
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																
BONDE 55-36-008-PIT Created On: 01/05/17 Updated On:	P		NE	5	17N	22E	Manitowoc	0-225-18-2017	0.9	1.9	2.2	8.0	33.1	2.768	2.790	0.797	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
BONDE 55-36-008-PIT Created On: 04/28/22 Updated On:	P		NE	5	17N	22E	Manitowoc	0-225-184-2022	2.1	0.0	0.4	7.8	34.3	2.766	2.790	0.873	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
BONDLEI 55-61-004-QRY Created On: 03/13/17 Updated On:	Q	NE	SW	20	20N	8W	Trempealeau	0-225-81-2017	0.5	0.0	4.5	8.8	34.8	2.612	2.668	2.142	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
BONDLEI 55-61-004-QRY Created On: 03/12/20 Updated On:	Q	NE	SW	20	20N	8W	Trempealeau	0-225-129-2020	0.0	0.0	9.4	12.7	40.5	2.544	2.623	3.084	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
BONDLEI 55-61-004-QRY Created On: 04/04/23 Updated On:	Q	NE	SW	20	20N	8W	Trempealeau	0-225-178-2023	0.0	0.0	5.5	8.4	34.2	2.595	2.658	2.396	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
BONDUEL 55-58-002-QRY Created On: 01/20/16 Updated On:	Q		NE	29	25N	17E	Shawano	0-225-60-2016		1.1	0.9	7.2	30.9	2.719	2.749	1.102	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
BONDUEL 55-58-002-QRY Created On: 01/04/19 Updated On:	Q		NE	29	25N	17E	Shawano	0-225-14-2019		4.3	0.7	6.3	31.0	2.721	2.752	1.162	
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																
BONDUEL 55-58-002-QRY Created On: 01/04/22 Updated On:	Q		NE	29	25N	17E	Shawano	0-225-35-2022	0.0	2.9	1.8	6.3	28.3	2.717	2.747	1.083	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
BONDUEL 55-58-002-QRY Created On: 01/02/25 Updated On:	Q		NE	29	25N	17E	Shawano	0-225-55-2025	0.0	1.5	1.2	6.2	27.4	2.738	2.765	0.955	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
BONG 55-13-004-QRY Created On: 05/11/18 Updated On:	Q	SW	SE	11	8N	9E	Dane	0-225-210-2018	4.1	1.9	3.7	11.9	39.2	2.537	2.611	2.930	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
BONG 55-13-004-QRY Created On: 02/15/21 Updated On:	Q	SW	SE	11	8N	9E	Dane	0-225-127-2021	5.2	3.4	3.4	9.2	36.4	2.570	2.638	2.624	
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
BONG 55-13-004-QRY Created On: 01/04/24 Updated On:	Q	SW	SE	11	8N	9E	Dane	0-225-148-2024	3.2	5.5	2.5	9.8	40.1	2.560	2.625	2.530	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
BONG (YAHARA) 55-13-004-QRY Created On: 04/18/24 Updated On:	Q	SW	SE	11	8N	9E	Dane	0-225-235-2024	0.6	7.4	5.3	12.0	46.5	2.489	2.579	3.606	
	Approved Use : HMA<MT, CONCRETE, OGBC, Base Aggregate																
BORK 55-06-005-QRY Created On: 09/09/16 Updated On:	Q	NW	NE	30	19N	10W	Buffalo	0-225-253-2016		0.0	5.3	8.8	32.6	2.627	2.678	1.932	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
BORK 55-06-005-QRY Created On: 01/08/19 Updated On:	Q	NW	NE	30	19N	10W	Buffalo	0-225-78-2019	0.8	0.0	2.9	10.1	35.8	2.610	2.667	2.156	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
BORK 55-06-005-QRY Created On: 01/04/22 Updated On:	Q	NW	NE	30	19N	10W	Buffalo	0-225-11-2022	0.3	2.4	4.8	9.1	35.3	2.648	2.694	1.717	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
BORK 55-06-005-QRY Created On: 01/02/25 Updated On:	Q	NW	NE	30	19N	10W	Buffalo	0-225-49-2025	0.7	2.3	5.7	12.0	43.8	2.573	2.642	2.661	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
BOSCOBEL 55-22-060-QRY Created On: 01/05/17 Updated On:	Q	NE	SE	14	7N	3W	Grant	0-225-25-2017	0.7	5.6	2.2	7.5	29.9	2.611	2.674	2.416	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
BOSCOBEL 55-22-060-QRY Created On: 08/03/18 Updated On:	Q	NE	SE	14	7N	3W	Grant	0-225-263-2018	0.8	4.1	6.1	7.5	30.8	2.625	2.678	2.014		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
BOSCOBEL 55-22-060-QRY Created On: 04/07/21 Updated On:	Q	NE	SE	14	7N	3W	Grant	0-225-172-2021	0.0	1.9	6.8	8.1	31.0	2.621	2.680	2.252		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
BOSCOBEL 55-22-060-QRY Created On: 01/02/24 Updated On:	Q	NE	SE	14	7N	3W	Grant	0-225-3-2024	0.2	1.9	1.1	5.8	25.7	2.662	2.707	1.683		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
* BOULANGER 55-31-002-QRY Created On: 07/31/18 Updated On:	Q	NE	SE	15	22N	23E	Kewaunee	0-225-261-2018	1.9	0.0	2.1	6.7	31.1	2.769	2.794	0.885		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
* BOULANGER 55-31-002-QRY Created On: 01/06/21 Updated On:	Q	NE	SE	15	22N	23E	Kewaunee	0-225-112-2021	1.2	0.0	0.6	7.2	31.5	2.781	2.800	0.657		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
BOULDER HILL 55-49-003-PIT Created On: 01/04/18 Updated On:	P	SW	NE	22	22N	9E	Portage	0-225-86-2018	0.9	0.0	4.2	8.7	31.8	2.678	2.707	1.106		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
BOULDER HILL 55-49-003-PIT Created On: 01/03/23 Updated On:	P	SW	NE	22	22N	9E	Portage	0-225-12-2023	0.4	3.5	3.3	7.9	31.2	2.667	2.700	1.234		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
BRACKETT QUARRY 55-26-002-QRY Created On: 07/21/17 Updated On:	Q	NE	NW	31	46N	2E	Iron	0-225-239-2017	0.1	0.0	0.5	2.6	11.9	2.697	2.710	0.487	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
BRACKETT QUARRY 55-26-002-QRY Created On: 01/06/20 Updated On:	Q	NE	NW	31	46N	2E	Iron	0-225-31-2020	0.0	0.0	9.1	3.8	16.2	2.683	2.705	0.816	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
BRACKETT QUARRY 55-26-002-QRY Created On: 01/04/23 Updated On:	Q	NE	NW	31	46N	2E	Iron	0-225-95-2023	0.1	2.9	1.6	3.0	13.4	2.662	2.682	0.759	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
* BRAGGER 55-06-006-QRY Created On: 04/21/17 Updated On:	Q	W	NW	13	22N	10W	Buffalo	0-225-141-2017	0.4	0.0	7.5	10.3	41.1	2.571	2.646	2.915	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
* BRAGGER 55-06-006-QRY Created On: 06/18/20 Updated On:	Q	W	NW	13	22N	10W	Buffalo	0-225-196-2020	0.0	0.0	5.6	10.2	39.6	2.566	2.641	2.936	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
BRATTSET 55-28-020-PIT Created On: 01/04/22 Updated On:	P	NW	NW	5	5N	16E	Jefferson	0-225-41-2022	1.6	5.2	1.1	4.3	22.8	2.694	2.732	1.401	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
BRAUKHOFF 55-53-004-QRY Created On: 05/17/22 Updated On:	Q	S	SW	26	2N	14E	Rock	0-225-203-2022	0.4	6.5	2.7	7.7	34.7	2.652	2.707	2.091	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
BRAUKHOFF 55-53-004-QRY Created On: 01/14/25 Updated On:	Q	S	SW	26	2N	14E	Rock	0-225-98-2025	0.0	7.4	2.4	9.0	37.2	2.603	2.672	2.628	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
BREAKNECK ROAD 55-20-055-QRY Created On: 01/14/21 Updated On:	Q	NE	NW	34	14N	16E	Fond Du Lac	0-225-121-2021	0.0	0.7	0.6	5.8	25.8	2.773	2.792	0.676	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
BREAKNECK ROAD 55-20-055-QRY Created On: 01/02/24 Updated On:	Q	NE	NW	34	14N	16E	Fond Du Lac	0-225-50-2024	0.1	1.3	1.0	5.9	26.7	2.772	2.790	0.646	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
BREUNIG 55-13-006-PIT Created On: 01/20/17 Updated On:	P	NE	NW	7	9N	7E	Dane	0-225-55-2017	1.5	0.0	5.2	7.6	30.6	2.677	2.724	1.745	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
BREUNIG 55-13-006-PIT Created On: 01/04/22 Updated On:	P	NE	NW	7	9N	7E	Dane	0-225-43-2022	2.1	0.0	6.8	7.2	31.4	2.671	2.720	1.819	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
BRIGGS PIT 55-34-008-PIT Created On: 08/20/19 Updated On:	P	SW	NE	1	34N	10E	Langlade	0-225-263-2019	0.6	0.0	1.1	4.3	19.0	2.680	2.703	0.860	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
BRIGGS PIT 55-34-008-PIT Created On: 04/24/23 Updated On:	P	SW	NE	1	34N	10E	Langlade	0-225-207-2023	0.2	0.0	0.7	4.8	22.0	2.691	2.711	0.762	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
BROCK 55-35-003-PIT Created On: 03/09/15 Updated On:	P		NE	29	31N	7E	Lincoln	0-225-93-2015		0.0	3.2	4.1	19.0	2.685	2.714	1.094	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
BROCK 55-35-003-PIT Created On: 01/08/20 Updated On:	P		NE	29	31N	7E	Lincoln	0-225-47-2020	0.0	2.0	0.5	6.0	24.4	2.690	2.715	0.948	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
BROCK 55-35-003-PIT Created On: 01/14/25 Updated On:	P		NE	29	31N	7E	Lincoln	0-225-111-2025	2.2	8.0	0.9	4.1	18.2	2.672	2.708	1.315	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
BROCKER 55-36-009-PIT Created On: 04/19/19 Updated On:	P	NW	SW	20	18N	21E	Manitowoc	0-225-147-2019	0.8	0.0	1.3	6.5	29.2	2.764	2.789	0.902	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
BROCKER 55-36-009-PIT Created On: 01/02/24 Updated On:	P	NW	SW	20	18N	21E	Manitowoc	0-225-51-2024	1.1	0.0	2.2	7.9	33.4	2.749	2.777	1.001	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
* BROMMER 55-06-008-QRY Created On: 06/13/16 Updated On:	Q	SW	NE	30	23N	12W	Buffalo	0-225-203-2016		0.0	4.8	8.8	34.7	2.568	2.637	2.681	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
* BROMMER 55-06-008-QRY Created On: 01/05/21 Updated On:	Q	SW	NE	30	23N	12W	Buffalo	0-225-71-2021	2.4	0.0	0.9	8.5	34.4	2.592	2.656	2.470	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse					
	P/Q	Qrt	Qrt	Sect	Town	Range	County					LA Wear (%)		Sp. Gravity		Absorp. %	
												100	500	OD	SSD	Crse	Fine
BROOKS 55-60-003-PIT Created On: 08/08/17 Updated On:	P	SW	SE	7	33N	3W	Taylor	0-225-247-2017		0.0	2.2	5.3	21.5	2.734	2.765	1.125	
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																
BROOKS 55-60-003-PIT Created On: 01/04/22 Updated On:	P	SW	SE	7	33N	3W	Taylor	0-225-81-2022	1.1	0.0	3.8	3.9	19.8	2.697	2.731	1.242	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
BROOKVILLE 55-62-004-QRY Created On: 05/19/16 Updated On:	Q			22	12N	4W	Vernon	0-225-184-2016		0.0	4.0	11.0	38.1	2.637	2.689	1.954	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
BROOKVILLE 55-62-004-QRY Created On: 01/04/18 Updated On:	Q			22	12N	4W	Vernon	0-225-44-2018	0.4	0.0	2.1	9.8	37.3	2.636	2.685	1.861	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
BROOKVILLE 55-62-004-QRY Created On: 01/05/21 Updated On:	Q			22	12N	4W	Vernon	0-225-63-2021	0.4	0.0	0.4	8.1	33.7	2.634	2.687	1.993	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
BROOKVILLE 55-62-004-QRY Created On: 01/02/24 Updated On:	Q			22	12N	4W	Vernon	0-225-35-2024	1.7	0.8	5.1	11.6	42.3	2.617	2.677	2.278	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
BROWN 55-11-010-PIT Created On: 01/03/18 Updated On:	P	NW	SW	18	12N	10E	Columbia	0-225-25-2018	0.3	5.0	1.3	9.8	31.8	2.666	2.718	1.932	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
* BROWN 55-52-027-QRY Created On: 06/02/20 Updated On:	Q			4	11N	1W	Richland	0-225-184-2020	1.3	0.0	0.5	10.0	34.5	2.603	2.661	2.216	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
BROWN 55-11-010-PIT Created On: 01/04/23 Updated On:	P	NW	SW	18	12N	10E	Columbia	0-225-93-2023	0.4	0.0	1.8	6.9	30.3	2.691	2.732	1.523	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
BROWNS BOTTOM 19-00-002-QRY Created On: 04/23/15 Updated On:	Q		NW	33	89N	2E	Dubuque	0-225-131-2015		0.2	0.8	7.0	28.0	2.670	2.706	1.367	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
BROWNS BOTTOM 19-00-002-QRY Created On: 01/04/18 Updated On:	Q		NW	33	89N	2E	Dubuque	0-225-72-2018	0.2	1.3	1.1	6.4	27.3	2.661	2.701	1.506	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
BROWNS BOTTOM 19-00-002-QRY Created On: 01/05/21 Updated On:	Q		NW	33	89N	2E	Dubuque	0-225-57-2021	0.2	0.5	0.6	7.3	29.1	2.676	2.715	1.430	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
BROWNS BOTTOM 19-00-002-QRY Created On: 01/02/24 Updated On:	Q		NW	33	89N	2E	Dubuque	0-225-34-2024	0.3	3.1	1.0	8.4	32.0	2.620	2.673	2.026	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
BRUEGGEMAN 55-41-003-QRY Created On: 04/06/17 Updated On:	Q	NE	NW	29	15N	2W	Monroe	0-225-115-2017	0.3	0.0	1.5	9.8	37.6	2.618	2.673	2.081	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
BRUEGGEMAN 55-41-003-QRY Created On: 04/02/20 Updated On:	Q	NE	NW	29	15N	2W	Monroe	0-225-139-2020	0.0	0.0	2.6	10.7	38.1	2.610	2.671	2.342		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
BRUEGGEMAN 55-41-003-QRY Created On: 01/04/24 Updated On:	Q	NE	NW	29	15N	2W	Monroe	0-225-134-2024	1.0	2.7	3.6	8.8	35.6	2.631	2.682	1.936		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
BRUHA 55-03-008-PIT Created On: 01/09/15 Updated On:	P	SW	NE	13	36N	12W	Barron	0-225-44-2015		0.0	2.8	3.5	15.8	2.755	2.789	1.234		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
BRUHA 55-03-008-PIT Created On: 01/08/20 Updated On:	P	SW	NE	13	36N	12W	Barron	0-225-55-2020	0.7	0.0	2.4	3.6	16.5	2.767	2.794	0.973		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
BRUHA 55-03-008-PIT Created On: 01/02/25 Updated On:	P	SW	NE	13	36N	12W	Barron	0-225-14-2025	1.2	1.1	2.6	3.9	17.9	2.764	2.796	1.145		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
BUCHDA 55-14-004-QRY Created On: 01/04/16 Updated On:	Q	NE	NW	5	12N	14E	Dodge	0-225-3-2016	0.5	2.2	1.4	6.8	27.7	2.745	2.779	1.209		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
BUCHDA 55-14-004-QRY Created On: 06/06/19 Updated On:	Q	NE	NW	5	12N	14E	Dodge	0-225-204-2019		2.1	1.0	7.6	29.5	2.752	2.779	0.973		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
BUCHDA 55-14-004-QRY Created On: 01/04/22 Updated On:	Q	NE	NW	5	12N	14E	Dodge	0-225-95-2022	0.0	2.4	2.5	8.0	27.1	2.738	2.772	1.252	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
BUCHDA 55-14-004-QRY Created On: 02/07/25 Updated On:	Q	NE	NW	5	12N	14E	Dodge	0-225-149-2025	0.0	2.8	1.9	6.9	25.7	2.760	2.786	0.955	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
BUCKEYE 55-13-008-QRY Created On: 01/21/15 Updated On:	Q	SW	NE	14	7N	10E	Dane	0-225-74-2015		6.1	4.4	9.7	38.9	2.563	2.636	2.824	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
BUCKEYE 55-13-008-QRY Created On: 01/05/17 Updated On:	Q	SW	NE	14	7N	10E	Dane	0-225-35-2017	1.1	3.7	2.1	6.2	27.2	2.603	2.667	2.481	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
BUCKEYE 55-13-008-QRY Created On: 05/13/19 Updated On:	Q	SW	NE	14	7N	10E	Dane	0-225-186-2019	0.3	1.1	0.9	6.9	28.7	2.619	2.678	2.260	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
BUCKEYE 55-13-008-QRY Created On: 03/09/20 Updated On:	Q	SW	NE	14	7N	10E	Dane	0-225-121-2020	0.1	1.6	4.7	6.3	25.1	2.644	2.695	1.895	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
BUCKEYE 55-13-008-QRY Created On: 03/16/21 Updated On:	Q	SW	NE	14	7N	10E	Dane	0-225-136-2021	0.8	1.6	3.4	6.4	26.8	2.634	2.689	2.079	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
BUCKEYE 55-13-008-QRY Created On: 01/02/24 Updated On:	Q	SW	NE	14	7N	10E	Dane	0-225-88-2024	0.2	3.0	2.4	10.1	35.4	2.583	2.646	2.430		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
BUCKEYE 55-13-008-QRY Created On: 01/02/25 Updated On:	Q	SW	NE	14	7N	10E	Dane	0-225-80-2025	1.2	15.9	7.9	10.9	42.0	2.507	2.595	3.518		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
* BUECHEL STONE OAKFIELD 55-20-056-QRY Created On: 03/24/21 Updated On:	Q	NE	NE	34	14N	16E	Fond Du Lac	0-225-158-2021	0.0	1.0	2.7	5.5	26.0	2.738	2.766	1.007		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
BUENA VISTA RIDGE 55-49-032-PIT Created On: 06/10/24 Updated On:	P	SW	NW	33	22N	9E	Portage	0-225-268-2024	0.7	0.0	1.6	5.5	24.9	2.705	2.735	1.138		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
BUGBEE QUARRY 55-62-035-QRY Created On: 02/28/24 Updated On:	Q	SE	SW	21	14N	1W	Vernon	0-225-191-2024	1.2	3.7	6.4	8.5	36.8	2.608	2.667	2.226		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
BURIC 55-03-009-PIT Created On: 06/13/16 Updated On:	P	NW	NW	14	33N	10W	Barron	0-225-204-2016		0.0	1.2	5.6	22.0	2.730	2.754	0.876		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
BURIC 55-03-009-PIT Created On: 01/04/22 Updated On:	P	NW	NW	14	33N	10W	Barron	0-225-85-2022	2.7	0.0	1.9	4.6	21.2	2.667	2.689	0.853		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
BURLINGTON SPRING VALLEY 55-51-006-PIT Created On: 03/24/16 Updated On:	P			6	2N	19E	Racine	0-225-114-2016	2.0	8.5	3.3	7.2	31.9	2.646	2.696	1.913	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
BURLINGTON SPRING VALLEY 55-51-006-PIT Created On: 01/05/21 Updated On:	P			6	2N	19E	Racine	0-225-81-2021	0.0	0.0	5.4	4.9	26.3	2.655	2.702	1.768	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
BURMEISTER 55-54-029-QRY Created On: 08/20/20 Updated On:	Q	NE	SW	33	33N	5W	Rusk	0-225-234-2020	0.3	0.0	0.4	3.3	14.9	2.814	2.830	0.569	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
BURMEISTER 55-54-030-PIT Created On: 01/04/22 Updated On:	P	NE	SW	33	33N	5W	Rusk	0-225-84-2022	0.4	0.0	1.5	3.6	17.6	2.708	2.736	1.037	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
BURMEISTER 55-54-029-QRY Created On: 01/10/23 Updated On:	Q	NE	SW	33	33N	5W	Rusk	0-225-108-2023	0.0	0.0	0.2	2.1	9.6	2.878	2.887	0.328	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
BURT(MUELLER) 55-62-005-QRY Created On: 05/18/17 Updated On:	Q	NW	SW	33	13N	2W	Vernon	0-225-190-2017		0.0	2.1	8.7	33.2	2.626	2.681	2.133	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
BURT(MUELLER) 55-62-005-QRY Created On: 01/08/20 Updated On:	Q	NW	SW	33	13N	2W	Vernon	0-225-65-2020	0.5	0.0	5.6	8.2	32.2	2.650	2.696	1.760	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
BURT(MUELLER) 55-62-005-QRY Created On: 01/30/23 Updated On:	Q	NW	SW	33	13N	2W	Vernon	0-225-134-2023	1.5	1.6	1.7	8.5	33.4	2.654	2.703	1.858	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
* BYRON 55-20-012-QRY Created On: 01/08/15 Updated On:	Q	N	SE	10	14N	17E	Fond Du Lac	0-225-29-2015		0.5	1.5	5.5	26.4	2.735	2.765	1.106	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
* BYRON 55-20-012-QRY Created On: 03/16/18 Updated On:	Q	N	SE	10	14N	17E	Fond Du Lac	0-225-122-2018		0.6	0.7	5.5	27.8	2.725	2.758	1.203	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
* BYRON 55-20-012-QRY Created On: 01/05/21 Updated On:	Q	N	SE	10	14N	17E	Fond Du Lac	0-225-49-2021	0.0	1.2	0.9	5.8	28.1	2.738	2.767	1.045	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
C6 QUARRY 55-13-126-QRY Created On: 09/05/23 Updated On:	Q	NE	NW	17	6N	8E	Dane	0-225-250-2023	0.7	2.8	0.5	5.4	23.9	2.680	2.720	1.486	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
CAELWAERTS 55-42-002-QRY Created On: 08/16/16 Updated On:	Q	NE	SE	31	29N	22E	Oconto	0-225-241-2016		7.7	2.6	4.6	25.7	2.721	2.753	1.160	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
CAELWAERTS 55-42-002-QRY Created On: 04/24/19 Updated On:	Q	NE	SE	31	29N	22E	Oconto	0-225-165-2019		7.7	1.3	5.5	25.2	2.707	2.741	1.245	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse		Absorp. %	
Source Name	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
CAELWAERTS 55-42-002-QRY Created On: 01/04/22 Updated On:	Q	NE	SE	31	29N	22E	Oconto	0-225-92-2022	0.0	4.5	4.7	6.2	28.2	2.709	2.739	1.115		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
CAELWAERTS 55-42-002-QRY Created On: 01/14/25 Updated On:	Q	NE	SE	31	29N	22E	Oconto	0-225-107-2025	0.0	4.7	3.7	7.2	30.5	2.698	2.734	1.342		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
CAMPIA PIT 55-03-010-PIT Created On: 01/02/24 Updated On:	P	NE	NE	8	35N	10W	Barron	0-225-87-2024	1.3	0.0	0.9	4.2	19.6	2.708	2.734	0.959		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
CAPITOL SAND & GRAVEL 55-13-010-PIT Created On: 09/26/18 Updated On:	P			11	7N	7E	Dane	0-225-283-2018	9.2	5.8	3.1	8.1	32.1	2.587	2.639	1.997		
	Approved Use : HMA<MT, HMA>=MT, Base Aggregate																	
CAPITOL SAND & GRAVEL 55-13-010-PIT Created On: 01/09/20 Updated On:	P			11	7N	7E	Dane	0-225-92-2020	4.2	9.1	0.9	11.0	38.5	2.635	2.681	1.729		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
CAPITOL SAND & GRAVEL 55-13-010-PIT Created On: 01/02/24 Updated On:	P			11	7N	7E	Dane	0-225-41-2024	1.7	2.8	5.7	11.0	38.2	2.649	2.691	1.584		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
CAREW - BRUSSELS 55-15-004-QRY Created On: 01/16/15 Updated On:	Q	NW	NW	21	26N	24E	Door	0-225-69-2015		0.0	3.3	7.2	27.5	2.749	2.778	1.052		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
CAREW - BRUSSELS 55-15-004-QRY Created On: 03/01/18 Updated On:	Q	NW	NW	21	26N	24E	Door	0-225-111-2018		0.0	5.2	6.0	26.6	2.773	2.793	0.717	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
CAREW - BRUSSELS 55-15-004-QRY Created On: 01/14/21 Updated On:	Q	NW	NW	21	26N	24E	Door	0-225-120-2021	0.0	0.0	0.9	5.4	24.8	2.780	2.798	0.655	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
CAREW - BRUSSELS 55-15-004-QRY Created On: 02/28/24 Updated On:	Q	NW	NW	21	26N	24E	Door	0-225-177-2024	0.0	0.0	1.7	6.4	27.4	2.772	2.790	0.650	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
CAREW - EDEN 55-20-058-PIT Created On: 01/25/16 Updated On:	P	W	SE	23	14N	18E	Fond Du Lac	0-225-81-2016	0.3	0.0	2.9	8.0	33.0	2.742	2.772	1.093	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
CAREW - EDEN 55-20-058-PIT Created On: 02/08/21 Updated On:	P	W	SE	23	14N	18E	Fond Du Lac	0-225-123-2021	0.5	2.9	3.6	7.6	33.2	2.752	2.783	1.128	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
CAREW - FREEDOM 55-44-006-QRY Created On: 01/16/15 Updated On:	Q	SW	NE	10	22N	18E	Outagamie	0-225-68-2015	0.8	0.8	1.0	4.6	20.6	2.791	2.808	0.616	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
CAREW - FREEDOM 55-44-006-QRY Created On: 03/06/17 Updated On:	Q	SW	NE	10	22N	18E	Outagamie	0-225-75-2017		2.8	1.5	4.6	21.2	2.774	2.796	0.794	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
CAREW - FREEDOM 55-44-006-QRY Created On: 01/30/20 Updated On:	Q	SW	NE	10	22N	18E	Outagamie	0-225-100-2020	0.0	2.4	1.2	4.0	18.3	2.796	2.812	0.572		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
CAREW - FREEDOM 55-44-006-QRY Created On: 01/04/23 Updated On:	Q	SW	NE	10	22N	18E	Outagamie	0-225-103-2023	0.0	1.2	1.2	4.4	19.9	2.788	2.804	0.572		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
CAREW - FREEDOM 55-44-006-QRY Created On: 02/28/24 Updated On:	Q	SW	NE	10	22N	18E	Outagamie	0-225-178-2024	0.0	1.2	1.3	4.8	21.3	2.771	2.791	0.732		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
* CAREW - ROCK RD 55-44-007-QRY Created On: 01/25/16 Updated On:	Q	NE	NW	20	22N	17E	Outagamie	0-225-82-2016		0.7	3.7	5.6	27.6	2.701	2.738	1.363		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
* CAREW - ROCK RD 55-44-007-QRY Created On: 01/10/19 Updated On:	Q	NE	NW	20	22N	17E	Outagamie	0-225-84-2019	0.1	4.1	3.0	6.1	27.9	2.746	2.775	1.045		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
* CAREW - ROCK RD 55-44-007-QRY Created On: 03/17/22 Updated On:	Q	NE	NW	20	22N	17E	Outagamie	0-225-152-2022	0.2	2.7	3.6	5.9	27.4	2.725	2.756	1.124		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
CAREW ALTO/WAUPUN 55-20-008-QRY Created On: 03/08/17 Updated On:	Q	S	NE	36	14N	14E	Fond Du Lac	0-225-78-2017		6.0	4.4	6.3	27.9	2.767	2.790	0.826		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
CAREW ALTO/WAUPUN 55-20-008-QRY Created On: 01/30/20 Updated On:	Q	S	NE	36	14N	14E	Fond Du Lac	0-225-99-2020	0.0	4.0	3.5	6.2	27.1	2.764	2.791	0.974		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
CAREW ALTO/WAUPUN 55-20-008-QRY Created On: 01/04/23 Updated On:	Q	S	NE	36	14N	14E	Fond Du Lac	0-225-100-2023	0.0	3.9	1.6	6.3	28.2	2.771	2.794	0.821		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
CAREW-MARIBEL 55-36-013-PIT Created On: 08/09/18 Updated On:	P	NE	NW	19	21N	22E	Manitowoc	0-225-267-2018	1.2	0.0	2.9	7.6	34.2	2.707	2.748	1.491		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
CAREW-MARIBEL 55-36-013-PIT Created On: 01/04/23 Updated On:	P	NE	NW	19	21N	22E	Manitowoc	0-225-102-2023	0.8	0.0	3.7	8.2	34.9	2.691	2.731	1.486		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
CASSVILLE 55-22-009-QRY Created On: 06/30/16 Updated On:	Q	NW	SW	27	3N	5W	Grant	0-225-214-2016	1.2	1.9	0.8	8.8	36.7	2.592	2.659	2.573		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
CASSVILLE 55-22-009-QRY Created On: 01/07/19 Updated On:	Q	NW	SW	27	3N	5W	Grant	0-225-47-2019	0.4	5.2	3.1	8.3	34.7	2.590	2.656	2.564		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
CASSVILLE 55-22-009-QRY Created On: 01/10/22 Updated On:	Q	NW	SW	27	3N	5W	Grant	0-225-104-2022	2.3	5.0	8.0	8.4	36.4	2.594	2.658	2.469		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
CASSVILLE 55-22-009-QRY Created On: 01/02/25 Updated On:	Q	NW	SW	27	3N	5W	Grant	0-225-84-2025	1.6	15.6	5.5	9.3	35.1	2.556	2.630	2.913	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
* CCI BELOIT QUARRY 55-53-42-QRY Created On: 08/08/17 Updated On:	Q		NW	22	1N	13E	Rock	0-225-246-2017	1.8	1.8	1.3	7.8	35.1	2.480	2.584	4.225	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
* CCI BELOIT QUARRY 55-53-42-QRY Created On: 07/09/20 Updated On:	Q		NW	22	1N	13E	Rock	0-225-211-2020	2.1	9.2	14.6	9.2	36.6	2.571	2.653	3.188	
	Approved Use : Base Aggregate																
CEDAR LAKE 55-66-004-PIT Created On: 01/04/16 Updated On:	P	N	SW	35	11N	18E	Washington	0-225-15-2016	1.9	1.3	2.1	5.7	26.4	2.712	2.743	1.165	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
CEDAR LAKE 55-66-004-PIT Created On: 01/08/21 Updated On:	P	N	SW	35	11N	18E	Washington	0-225-116-2021	0.8	8.7	1.1	5.9	32.1	2.749	2.772	0.830	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
CEMSTONE CUMBERLAND PIT 55-03-037-PIT Created On: 01/25/16 Updated On:	P	S	SE	35	36N	13W	Barron	0-225-80-2016		0.0	3.2	3.9	18.3	2.726	2.758	1.181	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
CEMSTONE CUMBERLAND PIT 55-03-037-PIT Created On: 01/05/21 Updated On:	P	S	SE	35	36N	13W	Barron	0-225-86-2021	4.1	0.0	2.5	4.0	18.0	2.698	2.731	1.198	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Coarse Sp. Gravity		Coarse Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
* CEPRESS 55-71-010-QRY Created On: 03/21/18 Updated On:	Q	SE	NE	2	23N	2E	Wood	0-225-132-2018		0.0	1.3	2.4	12.3	2.723	2.734	0.403	
	Approved Use : HMA<MT, HMA>=MT, Base Aggregate																
* CEPRESS 55-71-010-QRY Created On: 06/28/22 Updated On:	Q	SE	NE	2	23N	2E	Wood	0-225-243-2022		0.0	1.0	3.5	14.4	2.706	2.722	0.602	
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																
CHARLIE MILLER 55-56-005-QRY Created On: 01/09/15 Updated On:	Q			17	13N	2E	Sauk	0-225-53-2015		0.0	4.6	10.2	36.6	2.615	2.668	2.057	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
CHARLIE MILLER 55-56-005-QRY Created On: 01/03/18 Updated On:	Q			17	13N	2E	Sauk	0-225-13-2018	1.0	0.0	1.9	8.5	34.8	2.626	2.676	1.939	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
CHARLIE MILLER 55-56-005-QRY Created On: 01/04/21 Updated On:	Q			17	13N	2E	Sauk	0-225-24-2021	1.2	0.0	1.7	7.6	32.3	2.626	2.681	2.083	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
CHARLIE MILLER 55-56-005-QRY Created On: 01/02/24 Updated On:	Q			17	13N	2E	Sauk	0-225-123-2024	2.4	6.3	1.5	10.7	38.5	2.599	2.656	2.198	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
CHASE (NEA) 55-42-003-QRY Created On: 01/12/16 Updated On:	Q	NW	NE	17	26N	19E	Oconto	0-225-48-2016		0.2	1.2	3.9	20.7	2.759	2.782	0.821	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
CHASE (NEA) 55-42-003-QRY Created On: 05/12/21 Updated On:	Q	NW	NE	17	26N	19E	Oconto	0-225-205-2021	0.0	0.9	0.2	4.7	20.7	2.776	2.795	0.714	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
CHASE (NEA) 55-42-003-QRY Created On: 01/02/24 Updated On:	Q	NW	NE	17	26N	19E	Oconto	0-225-10-2024	0.6	3.6	0.2	6.2	25.9	2.765	2.788	0.815	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
CHELSEA 55-60-036-PIT Created On: 01/02/24 Updated On:	P	N	SE	10	32N	1E	Taylor	0-225-114-2024	0.5	0.0	3.4	3.1	17.2	2.688	2.716	1.029	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
CHRISTIAN - GADE 55-14-006-PIT Created On: 01/07/16 Updated On:	P	W	SW	33	12N	15E	Dodge	0-225-41-2016		11.7	2.6	5.4	25.5	2.743	2.779	1.332	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
CHRISTIAN - GADE 55-14-006-PIT Created On: 01/04/21 Updated On:	P	W	SW	33	12N	15E	Dodge	0-225-5-2021	0.0	14.4	2.5	5.7	25.9	2.728	2.772	1.598	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
CISLER 55-37-016-QRY Created On: 01/06/16 Updated On:	Q	NW	NW	5	26N	7E	Marathon	0-225-29-2016		0.0	0.5	3.9	17.2	2.680	2.691	0.411	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
CISLER 55-37-016-QRY Created On: 01/04/19 Updated On:	Q	NW	NW	5	26N	7E	Marathon	0-225-32-2019		0.0	0.2	2.6	13.6	2.683	2.691	0.319	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
CISLER 55-37-016-QRY Created On: 04/01/19 Updated On:	Q	NW	NW	5	26N	7E	Marathon	0-225-121-2019	0.0	0.0	0.4	4.3	18.4	2.678	2.688	0.350	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
CISLER 55-37-016-QRY Created On: 01/04/22 Updated On:	Q	NW	NW	5	26N	7E	Marathon	0-225-37-2022	0.0	1.3	1.9	4.2	18.7	2.660	2.677	0.650	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
CISLER 55-37-016-QRY Created On: 01/02/25 Updated On:	Q	NW	NW	5	26N	7E	Marathon	0-225-10-2025	0.0	0.3	0.2	2.6	13.3	2.670	2.681	0.425	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
CLARK 27-00-013-PIT Created On: 05/09/16 Updated On:	P	NW	SW	26	41N	17W	Pine	0-225-166-2016		3.9	3.1	3.1	15.9	2.781	2.820	1.402	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
CLARK 55-62-006-QRY Created On: 05/19/16 Updated On:	Q	SE	SW	28	13N	1E	Vernon	0-225-181-2016	1.0	5.4	6.6	8.5	37.3	2.615	2.673	2.211	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
CLARK 55-62-006-QRY Created On: 07/25/19 Updated On:	Q	SE	SW	28	13N	1E	Vernon	0-225-251-2019	0.8	5.4	4.8	8.2	37.1	2.639	2.693	2.033	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
CLARK 27-00-013-PIT Created On: 06/10/21 Updated On:	P	NW	SW	26	41N	17W	Pine	0-225-219-2021	2.0	2.9	1.6	4.2	19.2	2.797	2.820	0.837	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Coarse Sp. Gravity		Coarse Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
CLARK 55-62-006-QRY Created On: 04/05/22 Updated On:	Q	SE	SW	28	13N	1E	Vernon	0-225-167-2022	0.7	9.7	6.6	8.3	36.1	2.625	2.683	2.213	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
CLARK 55-62-006-QRY Created On: 01/02/25 Updated On:	Q	SE	SW	28	13N	1E	Vernon	0-225-89-2025	0.5	8.4	8.4	8.9	37.2	2.630	2.683	2.021	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
CLEARWATER ACRES LLP 55-51-056-PIT Created On: 01/09/20 Updated On:	P		NE	17	4N	19E	Racine	0-225-94-2020		0.0	4.6	5.6	28.7	2.625	2.673	1.797	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
CLEARWATER ACRES LLP 55-51-056-PIT Created On: 04/01/25 Updated On:	P		NE	17	4N	19E	Racine	0-225-182-2025	2.5	0.0	1.8	7.1	30.3	2.641	2.691	1.878	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
CLOCKMAKER 55-62-007-QRY Created On: 01/05/17 Updated On:	Q	SE	NW	26	14N	4W	Vernon	0-225-31-2017		0.0	5.1	10.0	38.3	2.585	2.650	2.489	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
CLOCKMAKER 55-62-007-QRY Created On: 01/08/20 Updated On:	Q	SE	NW	26	14N	4W	Vernon	0-225-63-2020	0.6	0.0	1.5	7.6	33.1	2.644	2.692	1.815	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
CLOCKMAKER 55-62-007-QRY Created On: 01/03/23 Updated On:	Q	SE	NW	26	14N	4W	Vernon	0-225-68-2023	0.7	3.0	1.6	9.8	31.8	2.646	2.694	1.833	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
CLOVERLEAF QUARRY 55-15-032-QRY Created On: 03/13/24 Updated On:	Q	NW	SE	19	27N	25E	Door	0-225-202-2024	0.0	0.0	0.7	6.5	30.6	2.754	2.775	0.759	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
COLBY 55-16-005-QRY Created On: 02/13/17 Updated On:	Q	NE	SW	25	48N	11W	Douglas	0-225-66-2017		0.0	14.4	4.5	20.3	2.798	2.834	1.297	
	Approved Use : Base Aggregate																
COLBY 55-16-005-QRY Created On: 01/08/20 Updated On:	Q	NE	SW	25	48N	11W	Douglas	0-225-59-2020	0.4	0.0	15.5	5.4	21.6	2.818	2.857	1.368	
	Approved Use : Base Aggregate																
COLBY 55-16-005-QRY Created On: 01/04/23 Updated On:	Q	NE	SW	25	48N	11W	Douglas	0-225-90-2023	0.0	7.7	13.7	4.7	19.0	2.801	2.841	1.421	
	Approved Use : Base Aggregate																
COLDSPRING QUARRY 55-37-099-QRY Created On: 01/29/24 Updated On:	Q	SW	SE	34	30N	8E	Marathon	0-225-154-2024	0.2	0.0	1.2	7.1	32.9	2.597	2.612	0.590	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
COLRUE 55-68-033-PIT Created On: 03/01/18 Updated On:	P	SW	NE	31	23N	12E	Waupaca	0-225-110-2018	0.3	0.0	1.3	6.0	27.0	2.680	2.705	0.935	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
COLRUE 55-68-033-PIT Created On: 04/17/23 Updated On:	P	SW	NE	31	23N	12E	Waupaca	0-225-198-2023	1.1	1.6	2.6	5.9	26.9	2.612	2.646	1.298	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
Source Name	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
COOMBS 55-35-004-PIT Created On: 01/03/18 Updated On:	P			16	34N	7E	Lincoln	0-225-4-2018	0.2	0.0	1.2	4.3	21.1	2.724	2.745	0.766	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
COOMBS 55-35-004-PIT Created On: 05/22/23 Updated On:	P			16	34N	7E	Lincoln	0-225-224-2023	0.3	0.0	2.8	4.5	20.3	2.749	2.773	0.858	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
COOMBS SOUTH 55-35-005-PIT Created On: 05/10/18 Updated On:	P	NW	21	34N	7E	Lincoln		0-225-204-2018	1.3	0.0	1.4	4.7	22.9	2.709	2.732	0.819	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
COOMBS SOUTH 55-35-005-PIT Created On: 01/02/24 Updated On:	P	NW	21	34N	7E	Lincoln		0-225-67-2024	0.3	2.9	3.2	4.2	20.5	2.683	2.714	1.138	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
COUNTRY SIDE WOODS 55-64-054-PIT Created On: 05/13/19 Updated On:	P	SW	20	3N	16E	Walworth		0-225-187-2019	1.7	2.8	0.8	6.3	26.9	2.649	2.689	1.508	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
COUNTRY SIDE WOODS 55-64-054-PIT Created On: 02/10/22 Updated On:	P	SW	20	3N	16E	Walworth		0-225-120-2022	3.3	6.8	1.6	5.1	26.1	2.676	2.714	1.430	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
CRETEX-MAIN 55-51-015-PIT Created On: 05/21/18 Updated On:	P	NW	6	2N	19E	Racine		0-225-214-2018	1.8	13.1	7.1	5.5	26.6	2.667	2.708	1.560	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
CRETEX-MAIN 55-51-015-PIT Created On: 04/05/23 Updated On:	P		NW	6	2N	19E	Racine	0-225-186-2023	1.4	16.2	11.6	7.4	36.9	2.557	2.612	2.148	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
CRETEX-WARREN 55-51-007-QRY Created On: 03/24/16 Updated On:	Q		NE	4	2N	19E	Racine	0-225-108-2016		0.0	11.1	7.6	27.3	2.615	2.668	2.026	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
CRETEX-WARREN 55-51-007-QRY Created On: 06/18/21 Updated On:	Q		NE	4	2N	19E	Racine	0-225-229-2021	0.0	18.0	10.3	6.1	26.3	2.549	2.630	3.176	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
CRETEX-WARREN 55-51-007-QRY Created On: 05/21/24 Updated On:	Q		NE	4	2N	19E	Racine	0-225-262-2024		21.9	11.9	7.6	27.8	2.602	2.669	2.560	
CROFT 55-22-010-QRY Created On: 04/07/16 Updated On:	Q	NW	SE	24	6N	3W	Grant	0-225-132-2016	0.8	24.3	17.5	12.0	41.8	2.577	2.651	2.876	
	Approved Use : CONCRETE, Base Aggregate																
CROFT 55-22-010-QRY Created On: 01/05/17 Updated On:	Q	NW	SE	24	6N	3W	Grant	0-225-23-2017	0.4	16.9	9.9	16.7	49.6	2.554	2.632	3.042	
	Approved Use : CONCRETE, Base Aggregate																
CROFT 55-22-010-QRY Created On: 04/25/17 Updated On:	Q	NW	SE	24	6N	3W	Grant	0-225-153-2017	0.2	17.2	12.9	11.8	41.4	2.579	2.651	2.777	
	Approved Use : Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse					
	P/Q	Qrt	Qrt	Sect	Town	Range	County	LA Wear (%)					Sp. Gravity		Absorp. %			
								100					500	OD	SSD	Crse	Fine	
CROFT 55-22-010-QRY Created On: 05/21/18 Updated On:	Q	NW	SE	24	6N	3W	Grant	0-225-216-2018	0.3	14.9	10.3	13.4	44.3	2.561	2.639	3.057		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
CROFT 55-22-010-QRY Created On: 01/05/21 Updated On:	Q	NW	SE	24	6N	3W	Grant	0-225-56-2021	2.7	15.3	17.5	15.9	48.0	2.515	2.606	3.633		
	Approved Use : Base Aggregate																	
CROFT 55-22-010-QRY Created On: 01/02/24 Updated On:	Q	NW	SE	24	6N	3W	Grant	0-225-39-2024	1.4	11.8	5.2	12.8	39.8	2.530	2.617	3.433		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
CRONIN 55-53-006-PIT Created On: 05/18/18 Updated On:	P	S	SE	5	2N	13E	Rock	0-225-212-2018	1.1	0.0	4.2	5.6	27.8	2.663	2.702	1.458		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
CRONIN 55-53-006-PIT Created On: 01/03/23 Updated On:	P	S	SE	5	2N	13E	Rock	0-225-13-2023		0.0	1.4	4.8	25.3	2.637	2.679	1.577		
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																	
CROOKED LAKE 55-04-003-PIT Created On: 01/07/19 Updated On:	P	SW	NW	36	47N	8W	Bayfield	0-225-58-2019	1.7	0.0	1.9	5.9	22.7	2.814	2.844	1.078		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
CROOKED LAKE 55-04-003-PIT Created On: 01/02/24 Updated On:	P	SW	NW	36	47N	8W	Bayfield	0-225-91-2024	1.4	2.1	2.7	3.4	16.6	2.817	2.843	0.926		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
Source Name	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
CTH "N" / MILESTONE 345 55-37-021-QRY Created On: 01/06/16 Updated On:	Q	NW	NE	19	28N	7E	Marathon	0-225-30-2016		0.0	0.5	11.3	45.4	2.579	2.600	0.795		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
CTH "N" / MILESTONE 345 55-37-021-QRY Created On: 01/04/19 Updated On:	Q	NW	NE	19	28N	7E	Marathon	0-225-34-2019	0.0	0.0	0.7	9.8	42.2	2.276	2.286	0.431		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
CTH "N" / MILESTONE 345 55-37-021-QRY Created On: 01/04/22 Updated On:	Q	NW	NE	19	28N	7E	Marathon	0-225-25-2022	0.0	0.2	0.6	7.6	36.6	2.603	2.617	0.563		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
CTH "N" / MILESTONE 345 55-37-021-QRY Created On: 01/02/25 Updated On:	Q	NW	NE	19	28N	7E	Marathon	0-225-5-2025	0.0	0.3	0.8	7.7	37.7	2.598	2.613	0.605		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
CTH R 55-35-009-PIT Created On: 07/26/21 Updated On:	P	SE	NE	7	32N	7E	Lincoln	0-225-251-2021	0.4	0.0	5.1	4.7	21.3	2.715	2.748	1.217		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
CTH XX PIT 55-09-029-PIT Created On: 07/23/25 Updated On:	P	SW	SW	35	29N	7W	Chippewa	0-225-229-2025	0.2	0.0	0.5	5.2	23.3	2.704	2.720	0.587		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
CURTIS QUARRY 55-70-040-QRY Created On: 07/02/24 Updated On:	Q	SW	NW	4	20N	17E	Winnebago	0-225-287-2024		10.6	1.8	8.1	33.4	2.729	2.759	1.092		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
CUSTER 55-49-004-PIT Created On: 01/06/16 Updated On:	P	E	4	23N	9E	Portage		0-225-31-2016		0.0	1.9	7.1	27.6	2.680	2.703	0.868	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
CUSTER 55-49-004-PIT Created On: 01/04/21 Updated On:	P	E	4	23N	9E	Portage		0-225-20-2021	0.0	0.0	0.7	7.3	29.0	2.650	2.683	1.214	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
* CZAPIGA 55-26-005-PIT Created On: 06/11/20 Updated On:	P	NE	SE	26	42N	35W	Iron	0-225-194-2020		1.6	0.9	3.2	16.6	2.736	2.754	0.681	
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																
* D AND J SCRAYS HILL 55-05-004-QRY Created On: 04/05/16 Updated On:	Q		NW	6	22N	21E	Brown	0-225-120-2016	0.1	2.9	1.3	9.1	36.3	2.702	2.748	1.721	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
* D AND J SCRAYS HILL 55-05-004-QRY Created On: 02/24/21 Updated On:	Q		NW	6	22N	21E	Brown	0-225-129-2021		2.4	2.4	9.3	37.7	2.681	2.727	1.712	
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																
* D and J CHASE 55-42-006-QRY Created On: 04/01/16 Updated On:	Q	E	NE	17	26N	19E	Oconto	0-225-118-2016	0.4	8.3	1.3	6.2	26.8	2.718	2.753	1.279	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
* D and J CHASE 55-42-006-QRY Created On: 04/24/19 Updated On:	Q	E	NE	17	26N	19E	Oconto	0-225-163-2019	0.0	0.8	1.2	5.1	22.9	2.858	2.879	0.705	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
* D and J CHASE 55-42-006-QRY Created On: 01/04/22 Updated On:	Q	E	NE	17	26N	19E	Oconto	0-225-70-2022	1.1	3.7	3.0	5.2	24.6	2.749	2.770	0.762		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
DALKA 55-35-043-PIT Created On: 04/24/19 Updated On:	P	SW	SW	3	35N	8E	Lincoln	0-225-170-2019	0.6	0.0	0.3	4.6	21.5	2.671	2.694	0.868		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
DALKA 55-35-043-PIT Created On: 01/02/24 Updated On:	P	SW	SW	3	35N	8E	Lincoln	0-225-66-2024	0.0	0.0	1.3	4.3	18.7	2.699	2.724	0.917		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
DAMMER 27-00-032-PIT Created On: 03/04/25 Updated On:	P	NE	NE	10	52N	17W	Statewide	0-225-160-2025	0.6	1.3	1.5	2.9	14.7	2.709	2.733	0.872		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
DARIEN 55-64-055-PIT Created On: 06/25/21 Updated On:	P	W	NW	7	2N	15E	Walworth	0-225-234-2021	0.1	5.3	6.7	6.2	25.6	2.662	2.706	1.648		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
* DB 55-49-007-QRY Created On: 03/21/18 Updated On:	Q	SW	SW	1	25N	7E	Portage	0-225-133-2018		0.0	2.1	5.7	22.6	2.647	2.666	0.741		
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																	
* DB 55-49-007-QRY Created On: 06/28/22 Updated On:	Q	SW	SW	1	25N	7E	Portage	0-225-240-2022		0.0	1.3	5.2	21.1	2.680	2.699	0.713		
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
DE LAET 55-38-012-PIT Created On: 06/13/22 Updated On:	P	SE	SE	14	34N	20E	Marinette	0-225-222-2022	3.0	0.0	1.8	6.6	31.8	2.718	2.745	0.977	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
DEITER 55-22-013-QRY Created On: 04/06/17 Updated On:	Q	NW	NW	29	2N	1W	Grant	0-225-112-2017	0.7	1.4	1.4	10.0	38.1	2.573	2.644	2.760	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
DEITER 55-22-013-QRY Created On: 07/28/17 Updated On:	Q	NW	NW	29	2N	1W	Grant	0-225-242-2017	0.4	2.1	2.1	12.5	43.6	2.554	2.630	2.995	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
DEITER 55-22-013-QRY Created On: 04/28/20 Updated On:	Q	NW	NW	29	2N	1W	Grant	0-225-158-2020	2.1	1.7	2.6	12.9	42.2	2.548	2.627	3.105	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
DEITER 55-22-013-QRY Created On: 01/03/23 Updated On:	Q	NW	NW	29	2N	1W	Grant	0-225-6-2023	0.1	2.0	3.6	11.7	42.0	2.536	2.625	3.500	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
DELARULLE 55-19-003-PIT Created On: 01/04/19 Updated On:	P	SE	SW	12	39N	17E	Florence	0-225-12-2019	0.0	0.0	3.2	6.2	29.1	2.619	2.664	1.744	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
DELARULLE 55-19-003-PIT Created On: 01/02/24 Updated On:	P	SE	SW	12	39N	17E	Florence	0-225-12-2024	1.1	0.0	0.5	5.9	26.0	2.641	2.682	1.551	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
DENMARK 55-05-005-QRY Created On: 01/05/17 Updated On:	Q		E	36	22N	22E	Brown	0-225-41-2017		2.0	0.4	4.5	21.6	2.792	2.809	0.627	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
DENMARK 55-05-005-QRY Created On: 01/02/20 Updated On:	Q		E	36	22N	22E	Brown	0-225-8-2020		14.4	0.4	6.0	25.9	2.791	2.821	1.089	
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																
DENMARK 55-05-005-QRY Created On: 01/03/23 Updated On:	Q		E	36	22N	22E	Brown	0-225-44-2023	0.0	1.8	0.4	5.5	25.1	2.792	2.809	0.618	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
DIPPEL 55-59-005-PIT Created On: 02/15/18 Updated On:	P	NE	SE	32	15N	20E	Sheboygan	0-225-100-2018		1.8	1.3	6.6	30.2	2.728	2.760	1.155	
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																
DIPPEL 55-59-005-PIT Created On: 01/03/23 Updated On:	P	NE	SE	32	15N	20E	Sheboygan	0-225-47-2023	1.4	0.0	0.7	7.2	32.5	2.720	2.754	1.254	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
DISCH-WAELCHLI 55-23-028-QRY Created On: 01/02/25 Updated On:	Q	NW	NE	16	3N	8E	Green	0-225-51-2025	0.0	17.9	9.0	10.1	37.1	2.591	2.668	2.965	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
DON MILLER 55-47-006-QRY Created On: 06/08/15 Updated On:	Q	N	NE	10	27N	15W	Pierce	0-225-191-2015		0.0	6.3	10.3	36.1	2.555	2.625	2.717	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
DON MILLER 55-47-006-QRY Created On: 01/03/18 Updated On:	Q	N	NE	10	27N	15W	Pierce	0-225-34-2018	3.2	0.0	1.1	9.4	34.4	2.559	2.628	2.668	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
DON MILLER 55-47-006-QRY Created On: 01/05/21 Updated On:	Q	N	NE	10	27N	15W	Pierce	0-225-73-2021	2.2	0.0	0.1	8.3	31.8	2.603	2.659	2.146	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
DON MILLER 55-47-006-QRY Created On: 01/02/24 Updated On:	Q	N	NE	10	27N	15W	Pierce	0-225-77-2024	4.1	0.0	5.8	11.0	39.4	2.550	2.624	2.893	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
DONSKEY 55-41-004-QRY Created On: 04/08/15 Updated On:	Q	NW	SE	11	16N	3W	Monroe	0-225-112-2015		0.0	2.4	9.2	37.6	2.625	2.677	1.979	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
DONSKEY 55-41-004-QRY Created On: 05/04/17 Updated On:	Q	NW	SE	11	16N	3W	Monroe	0-225-169-2017	1.6	0.0	3.3	10.0	38.4	2.622	2.674	1.956	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
DONSKEY 55-41-004-QRY Created On: 03/23/18 Updated On:	Q	NW	SE	11	16N	3W	Monroe	0-225-146-2018	0.5	0.0	7.9	11.2	41.2	2.589	2.653	2.482	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
DONSKEY 55-41-004-QRY Created On: 01/03/20 Updated On:	Q	NW	SE	11	16N	3W	Monroe	0-225-18-2020	1.2	0.0	3.7	9.7	38.3	2.608	2.670	2.375	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
DONSKEY 55-41-004-QRY Created On: 01/03/23 Updated On:	Q	NW	SE	11	16N	3W	Monroe	0-225-65-2023	2.3	1.8	6.3	11.9	44.4	2.567	2.635	2.661	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
DOOLEY 55-52-008-QRY Created On: 06/05/15 Updated On:	Q			9	12N	2E	Richland	0-225-187-2015		0.0	1.7	9.2	35.8	2.637	2.685	1.851	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
DOOLEY 55-52-008-QRY Created On: 01/04/18 Updated On:	Q			9	12N	2E	Richland	0-225-50-2018	0.5	0.0	3.1	9.1	36.1	2.628	2.683	2.076	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
DOOLEY 55-52-008-QRY Created On: 01/04/21 Updated On:	Q			9	12N	2E	Richland	0-225-31-2021	0.4	0.0	2.2	9.2	35.8	2.615	2.673	2.222	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
DOOLEY 55-52-008-QRY Created On: 01/02/24 Updated On:	Q			9	12N	2E	Richland	0-225-122-2024	0.8	4.6	1.2	9.5	35.6	2.631	2.691	2.285	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
DOSKOCIL QUARRY 55-12-007-QRY Created On: 05/19/17 Updated On:	Q	S	SE	2	9N	5W	Crawford	0-225-191-2017		1.4	5.9	10.4	39.6	2.566	2.637	2.788	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
DOSKOCIL QUARRY 55-12-007-QRY Created On: 01/09/20 Updated On:	Q	S	SE	2	9N	5W	Crawford	0-225-83-2020	0.4	3.5	2.0	13.1	46.3	2.502	2.569	2.645	
	Approved Use : HMA<MT, CONCRETE, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
DOSKOCIL QUARRY 55-12-007-QRY Created On: 01/02/24 Updated On:	Q	S	SE	2	9N	5W	Crawford	0-225-37-2024	1.2	3.5	0.5	9.3	39.2	2.606	2.664	2.235	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
DOWNING (RIEMANN) 55-55-004-QRY Created On: 06/20/22 Updated On:	Q	E	SE	1	29N	15W	St. Croix	0-225-231-2022	2.2	1.2	5.8	11.2	46.6	2.542	2.623	3.188	
	Approved Use : HMA<MT, CONCRETE, OGBC, Base Aggregate																
DOWNING (RIEMANN) 55-55-004-QRY Created On: 01/02/25 Updated On:	Q	E	SE	1	29N	15W	St. Croix	0-225-35-2025		3.5	9.9	24.2	67.3	2.417	2.532	4.755	
DOWNING (RIEMANN) 55-55-004-QRY Created On: 06/12/25 Updated On:	Q	E	SE	1	29N	15W	St. Croix	0-225-223-2025	1.9	1.1	4.1	9.5	39.2	2.601	2.666	2.506	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
DREPHALS 55-44-011-QRY Created On: 05/11/17 Updated On:	Q		E	17	24N	17E	Outagamie	0-225-181-2017		3.9	2.5	7.1	30.0	2.717	2.753	1.342	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
DREPHALS 55-44-011-QRY Created On: 03/17/22 Updated On:	Q		E	17	24N	17E	Outagamie	0-225-144-2022	0.5	1.0	1.2	10.2	36.8	2.727	2.762	1.293	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
DREPHALS 55-44-011-QRY Created On: 01/30/25 Updated On:	Q		E	17	24N	17E	Outagamie	0-225-143-2025	0.0	1.1	5.7	11.8	40.8	2.683	2.732	1.802	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
DRESSER TRAP 55-48-007-QRY Created On: 01/05/16 Updated On:	Q			5	33N	18W	Polk	0-225-25-2016		0.0	3.6	4.6	16.8	2.880	2.903	0.792		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
DRESSER TRAP 55-48-007-QRY Created On: 01/10/22 Updated On:	Q			5	33N	18W	Polk	0-225-108-2022	0.0	1.4	1.2	2.1	9.2	2.933	2.948	0.522		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
DRESSER TRAP 55-48-007-QRY Created On: 01/02/25 Updated On:	Q			5	33N	18W	Polk	0-225-48-2025	0.0	0.0	1.7	2.6	11.6	2.925	2.942	0.595		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
DUAME #1 55-42-001-QRY Created On: 04/27/17 Updated On:	Q	SE	SE	31	29N	21E	Oconto	0-225-160-2017	0.7	5.9	8.7	10.1	36.8	2.683	2.722	1.456		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
DUAME #1 55-42-001-QRY Created On: 02/24/21 Updated On:	Q	SE	SE	31	29N	21E	Oconto	0-225-130-2021	0.1	1.8	4.3	8.8	36.6	2.705	2.746	1.532		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
DUAME #1 55-42-001-QRY Created On: 06/25/24 Updated On:	Q	SE	SE	31	29N	21E	Oconto	0-225-277-2024	0.0	9.2	2.9	6.5	29.9	2.713	2.742	1.050		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
DUESSING 55-60-007-PIT Created On: 06/26/17 Updated On:	P	N	SW	33	32N	1E	Taylor	0-225-221-2017		0.0	0.6	3.5	17.4	2.743	2.769	0.947		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
Source Name	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
DUESSING 55-60-007-PIT Created On: 06/28/22 Updated On:	P	N	SW	33	32N	1E	Taylor	0-225-238-2022	0.7	0.0	2.0	4.1	18.4	2.742	2.768	0.948		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
DUNN 55-33-008-QRY Created On: 03/23/17 Updated On:	Q		SW	22	2N	3E	Lafayette	0-225-89-2017	1.8	5.3	7.4	10.5	38.9	2.584	2.654	2.710		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
DUNN 55-33-008-QRY Created On: 02/09/18 Updated On:	Q		SW	22	2N	3E	Lafayette	0-225-92-2018	1.1	3.0	9.0	7.5	33.8	2.563	2.639	2.964		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
DUNN 55-33-008-QRY Created On: 03/17/21 Updated On:	Q		SW	22	2N	3E	Lafayette	0-225-138-2021	0.7	14.2	2.4	9.1	36.3	2.581	2.650	2.678		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
DUNN 55-33-008-QRY Created On: 02/28/24 Updated On:	Q		SW	22	2N	3E	Lafayette	0-225-182-2024	1.6	12.4	8.3	9.5	38.3	2.578	2.649	2.754		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
DURAND 55-46-002-QRY Created On: 06/08/15 Updated On:	Q	SW	SW	33	25N	13W	Pepin	0-225-190-2015		0.0	3.0	10.4	37.9	2.586	2.654	2.632		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
DURAND 55-46-002-QRY Created On: 01/03/18 Updated On:	Q	SW	SW	33	25N	13W	Pepin	0-225-28-2018	1.0	0.0	1.8	9.1	34.5	2.588	2.656	2.604		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
DURAND 55-46-002-QRY Created On: 01/05/21 Updated On:	Q	SW	SW	33	25N	13W	Pepin	0-225-69-2021	1.3	0.0	0.5	8.2	33.0	2.596	2.666	2.675	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
DURAND 55-46-002-QRY Created On: 01/02/24 Updated On:	Q	SW	SW	33	25N	13W	Pepin	0-225-76-2024	0.8	1.4	4.9	9.8	37.9	2.592	2.660	2.613	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
DUSICK 55-09-024-PIT Created On: 05/17/22 Updated On:	P	SE	NW	17	29N	5W	Chippewa	0-225-205-2022	0.3	0.0	1.0	3.5	17.6	2.763	2.782	0.682	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
DW 55-53-043-PIT Created On: 05/02/19 Updated On:	P		SW	7	3N	13E	Rock	0-225-174-2019	2.7	0.0	6.2	7.5	33.2	2.608	2.677	2.644	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
DW 55-53-043-PIT Created On: 02/10/22 Updated On:	P		SW	7	3N	13E	Rock	0-225-122-2022	5.5	4.3	1.6	8.1	29.0	2.651	2.692	1.551	
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																
EARL'S 55-10-005-QRY Created On: 03/24/16 Updated On:	Q	NE	NE	10	28N	4W	Clark	0-225-116-2016		0.0	2.3	5.4	22.3	2.819	2.833	0.495	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
EARL'S 55-10-005-QRY Created On: 01/08/19 Updated On:	Q	NE	NE	10	28N	4W	Clark	0-225-76-2019		0.0	1.5	4.7	21.8	2.824	2.835	0.380	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
EARL'S 55-10-005-QRY Created On: 05/17/22 Updated On:	Q	NE	NE	10	28N	4W	Clark	0-225-204-2022	0.0	0.0	0.3	3.7	18.2	2.777	2.786	0.322	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
EARL'S 55-10-005-QRY Created On: 01/16/25 Updated On:	Q	NE	NE	10	28N	4W	Clark	0-225-139-2025	0.1	0.0	2.0	4.5	18.9	2.739	2.756	0.598	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
EASTON 55-37-026-PIT Created On: 01/05/17 Updated On:	P		SW	23	29N	9E	Marathon	0-225-43-2017		0.0	2.1	6.1	25.3	2.670	2.695	0.921	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
EASTON 55-37-026-PIT Created On: 01/14/25 Updated On:	P		SW	23	29N	9E	Marathon	0-225-113-2025	0.8	7.1	3.3	3.6	17.6	2.729	2.752	0.860	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
EGSTAD 55-03-014-PIT Created On: 05/18/17 Updated On:	P	S	SW	34	35N	14W	Barron	0-225-188-2017		0.0	4.0	5.3	20.3	2.727	2.766	1.421	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
EGSTAD 55-03-014-PIT Created On: 04/05/22 Updated On:	P	S	SW	34	35N	14W	Barron	0-225-159-2022	1.9	4.8	7.2	5.2	20.0	2.741	2.773	1.151	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
EHLER-COBB 55-25-008-QRY Created On: 04/06/17 Updated On:	Q	SE	SE	14	6N	1E	Iowa	0-225-114-2017	1.1	6.2	4.5	14.4	40.1	2.531	2.607	3.013	
	Approved Use : CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
EHLER-COBB 55-25-008-QRY Created On: 04/28/20 Updated On:	Q	SE	SE	14	6N	1E	Iowa	0-225-162-2020	0.7	5.4	5.1	15.0	46.7	2.554	2.633	3.079		
	Approved Use : CONCRETE, OGBC, Base Aggregate																	
EHLER-COBB 55-25-008-QRY Created On: 01/03/23 Updated On:	Q	SE	SE	14	6N	1E	Iowa	0-225-10-2023	0.7	7.0	9.0	12.5	44.2	2.551	2.631	3.167		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
EL PASO 55-47-007-QRY Created On: 01/02/25 Updated On:	Q	NE	SE	5	26N	16W	Pierce	0-225-45-2025	0.8	6.8	4.8	9.0	36.2	2.612	2.671	2.243		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
ELK RIVER PIT 27-00-034-PIT Created On: 04/29/25 Updated On:	P	SE	SE	9	33N	26W	Statewide	0-225-201-2025	1.3	2.0	1.4	2.3	15.0	2.690	2.718	1.047		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
ELMWOOD 55-47-008-QRY Created On: 05/09/16 Updated On:	Q	SE	SE	36	27N	15W	Pierce	0-225-164-2016		0.0	3.9	8.3	30.5	2.666	2.708	1.573		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
ELMWOOD 55-47-008-QRY Created On: 01/07/19 Updated On:	Q	SE	SE	36	27N	15W	Pierce	0-225-64-2019	2.5	0.0	7.8	14.1	45.8	2.493	2.588	3.836		
	Approved Use : CONCRETE, Base Aggregate																	
ELMWOOD 55-47-008-QRY Created On: 04/05/22 Updated On:	Q	SE	SE	36	27N	15W	Pierce	0-225-160-2022	0.5	0.0	8.2	12.4	44.9	2.555	2.627	2.821		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse		Absorp. %	
Source Name	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
ELMWOOD 55-47-008-QRY Created On: 01/02/25 Updated On:	Q	SE	SE	36	27N	15W	Pierce	0-225-41-2025	0.8	1.4	8.5	10.7	42.2	2.547	2.629	3.221		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
ELMWOOD CTH G QUARRY 55-47-036-QRY Created On: 03/27/24 Updated On:	Q	SE	SE	34	27N	15W	Pierce	0-225-208-2024	4.1	0.0	6.1	12.9	41.6	2.562	2.631	2.703		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
ELMWOOD CTH S QUARRY 55-47-037-QRY Created On: 03/27/24 Updated On:	Q	SE	SW	15	26N	15W	Pierce	0-225-209-2024	7.2	0.0	5.8	7.7	32.7	2.618	2.668	1.893		
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																	
ELMWOOD CTH S QUARRY 55-47-037-QRY Created On: 10/15/24 Updated On:	Q	SE	SW	15	26N	15W	Pierce	0-225-314-2024	1.0	0.0	3.2	5.8	26.1	2.666	2.704	1.424		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
EMPIRE LIME 55-53-010-QRY Created On: 08/08/16 Updated On:	Q	SW	NE	21	1N	12E	Rock	0-225-239-2016	1.5	6.3	12.6	11.8	41.4	2.564	2.649	3.333		
	Approved Use : Base Aggregate																	
EMPIRE LIME 55-53-010-QRY Created On: 03/21/23 Updated On:	Q	SW	NE	21	1N	12E	Rock	0-225-175-2023	0.4	12.2	12.9	11.9	42.0	2.566	2.650	3.286		
	Approved Use : Base Aggregate																	
EMPIRE PIT 27-00-031-PIT Created On: 08/14/24 Updated On:	P	NE	SE	5	114N	19W	Statewide	0-225-301-2024		3.0	1.5	4.5	20.6	2.692	2.720	1.057		
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse					
	P/Q	Qrt	Qrt	Sect	Town	Range	County	LA Wear (%)					Sp. Gravity		Absorp. %			
								100					500	OD	SSD	Crse	Fine	
ENDRES 55-41-006-QRY Created On: 07/26/16 Updated On:	Q	NE	SW	22	18N	4W	Monroe	0-225-229-2016	3.2	0.0	5.0	17.2	56.1	2.548	2.623	2.945		
ENDRES 55-41-006-QRY Created On: 08/03/16 Updated On:	Q	NE	SW	22	18N	4W	Monroe	0-225-235-2016	0.4	0.0	4.0	11.4	41.7	2.637	2.687	1.913		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
ENDRES 55-41-006-QRY Created On: 05/13/20 Updated On:	Q	NE	SW	22	18N	4W	Monroe	0-225-178-2020	0.8	0.0	4.6	10.7	39.7	2.629	2.684	2.110		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
ENDRES 55-41-006-QRY Created On: 01/03/23 Updated On:	Q	NE	SW	22	18N	4W	Monroe	0-225-70-2023	0.5	3.9	1.6	11.3	42.2	2.589	2.658	2.665		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
ERVIN STIEMKE 55-11-013-QRY Created On: 01/05/17 Updated On:	Q	NW	SW	18	10N	10E	Columbia	0-225-49-2017	1.3	2.5	2.5	11.3	35.5	2.549	2.614	2.559		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
ERVIN STIEMKE 55-11-013-QRY Created On: 01/08/20 Updated On:	Q	NW	SW	18	10N	10E	Columbia	0-225-68-2020	0.1	1.3	3.2	7.9	31.2	2.598	2.658	2.286		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
ERVIN STIEMKE 55-11-013-QRY Created On: 04/04/23 Updated On:	Q	NW	SW	18	10N	10E	Columbia	0-225-177-2023	0.6	1.2	2.2	7.3	29.8	2.556	2.631	2.952		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
ERVIN STIEMKE 55-11-013-QRY Created On: 04/18/24 Updated On:	Q	NW	SW	18	10N	10E	Columbia	0-225-234-2024	0.3	1.1	2.4	7.8	32.9	2.564	2.634	2.741	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
EVANS 55-13-017-QRY Created On: 01/06/20 Updated On:	Q	NW	SW	24	9N	9E	Dane	0-225-29-2020	0.8	1.4	1.9	7.6	31.7	2.614	2.660	1.742	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
EVANS 55-13-017-QRY Created On: 01/04/23 Updated On:	Q	NW	SW	24	9N	9E	Dane	0-225-92-2023	0.7	1.1	1.4	8.8	34.9	2.602	2.661	2.297	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
EVENSON - BERTRAM 55-20-011-QRY Created On: 01/08/15 Updated On:	Q	NE	NW	15	16N	18E	Fond Du Lac	0-225-26-2015		0.2	3.1	11.2	41.8	2.715	2.748	1.245	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
EVENSON - BERTRAM 55-20-011-QRY Created On: 04/13/17 Updated On:	Q	NE	NW	15	16N	18E	Fond Du Lac	0-225-128-2017		1.0	1.2	12.9	44.2	2.714	2.750	1.348	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
EVENSON - BERTRAM 55-20-011-QRY Created On: 01/30/20 Updated On:	Q	NE	NW	15	16N	18E	Fond Du Lac	0-225-106-2020	0.0	0.6	1.1	11.0	42.5	2.720	2.758	1.424	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
EVENSON - BERTRAM 55-20-011-QRY Created On: 01/04/24 Updated On:	Q	NE	NW	15	16N	18E	Fond Du Lac	0-225-149-2024	0.3	0.6	1.0	8.7	36.6	2.759	2.783	0.870	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse					
	P/Q	Qrt	Qrt	Sect	Town	Range	County	LA Wear (%)					Sp. Gravity		Absorp. %			
								100					500	OD	SSD	Crse	Fine	
EVERSON PIT 55-35-044-PIT Created On: 01/02/24 Updated On:	P	SE	SW	2	35N	8E	Lincoln	0-225-58-2024	0.3	0.0	0.2	3.4	16.1	2.735	2.753	0.641		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
FA 26-00-014-PIT Created On: 04/19/21 Updated On:	P			8	43N	35W	Iron, Mi	0-225-183-2021	0.0	1.0	0.8	4.4	19.1	2.694	2.716	0.810		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
FAIRVIEW QUARRY 55-12-008-QRY Created On: 01/05/17 Updated On:	Q	SW	NE	2	10N	5W	Crawford	0-225-30-2017		2.3	5.1	12.0	41.0	2.557	2.625	2.668		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
FAIRVIEW QUARRY 55-12-008-QRY Created On: 01/03/20 Updated On:	Q	SW	NE	2	10N	5W	Crawford	0-225-19-2020	2.6	2.1	1.3	11.1	38.1	2.593	2.653	2.326		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
FAIRVIEW QUARRY 55-12-008-QRY Created On: 01/03/23 Updated On:	Q	SW	NE	2	10N	5W	Crawford	0-225-67-2023	2.3	3.8	1.5	11.6	38.1	2.593	2.658	2.498		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
* FARMERSVILLE 55-14-007-QRY Created On: 04/18/22 Updated On:	Q	S	SW	30	13N	17E	Dodge	0-225-176-2022	0.0	0.8	1.5	9.1	37.5	2.690	2.725	1.322		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
FAULKES Q-PIT 55-68-010-PIT Created On: 08/03/16 Updated On:	P	SW	SE	17	22N	11E	Waupaca	0-225-232-2016	0.8	0.0	1.9	9.0	24.8	2.601	2.634	1.287		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
FAULKES Q-PIT 55-68-010-PIT Created On: 06/10/24 Updated On:	P	SW	SE	17	22N	11E	Waupaca	0-225-267-2024	0.1	12.6	3.8	8.7	36.9	2.685	2.731	1.719	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
FELTES 55-06-010-QRY Created On: 04/23/15 Updated On:	Q	NE	SE	6	20N	10W	Buffalo	0-225-135-2015		0.0	2.3	10.9	38.7	2.613	2.670	2.180	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
FELTES 55-06-010-QRY Created On: 01/04/18 Updated On:	Q	NE	SE	6	20N	10W	Buffalo	0-225-46-2018	0.7	0.0	1.7	9.2	34.6	2.612	2.672	2.320	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
FELTES 55-06-010-QRY Created On: 04/17/23 Updated On:	Q	NE	SE	6	20N	10W	Buffalo	0-225-197-2023		0.0	5.2	11.3	41.9	2.613	2.672	2.283	
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																
FELTES 55-06-010-QRY Created On: 05/22/23 Updated On:	Q	NE	SE	6	20N	10W	Buffalo	0-225-219-2023	0.2	0.0	2.9	7.4	33.6	2.647	2.697	1.875	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
FINK 55-13-020-QRY Created On: 01/04/22 Updated On:	Q	NW	NW	14	6N	6E	Dane	0-225-44-2022	0.8	7.7	11.0	11.7	43.2	2.552	2.628	2.944	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
FINK 55-13-020-QRY Created On: 01/02/25 Updated On:	Q	NW	NW	14	6N	6E	Dane	0-225-53-2025	3.9	7.1	6.7	12.1	44.0	2.580	2.653	2.794	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	LA Wear (%)					OD		SSD			
								100					500	Crse	Fine			
* FINK (YAHARA) 55-13-021-QRY Created On: 03/19/15 Updated On:	Q	SE	NW	14	6N	6E	Dane	0-225-98-2015		8.2	4.0	10.4	38.4	2.563	2.635	2.807		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
* FINK (YAHARA) 55-13-021-QRY Created On: 01/03/18 Updated On:	Q	SE	NW	14	6N	6E	Dane	0-225-27-2018	1.0	10.3	8.2	10.5	40.7	2.506	2.599	3.703		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
* FINK (YAHARA) 55-13-021-QRY Created On: 06/20/22 Updated On:	Q	SE	NW	14	6N	6E	Dane	0-225-234-2022	0.6	0.8	2.1	7.7	33.0	2.679	2.719	1.507		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
FITCHBURG HILLS QUARRY 55-13-127-QRY Created On: 03/27/24 Updated On:	Q	NE	NE	18	6N	9E	Dane	0-225-217-2024	0.2	9.2	4.7	8.9	37.8	2.602	2.672	2.669		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
FITCHBURG MINERALS 55-13-121-QRY Created On: 01/14/25 Updated On:	Q	SE	SW	7	6N	9E	Dane	0-225-123-2025	1.6	2.8	5.7	9.0	34.8	2.586	2.649	2.419		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
FLANNERY 55-33-009-QRY Created On: 04/16/15 Updated On:	Q	NW	SW	6	2N	5E	Lafayette	0-225-125-2015	1.3	8.1	2.4	7.7	31.6	2.643	2.692	1.852		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
FLANNERY 55-21-004-PIT Created On: 05/11/15 Updated On:	P	SW	SE	33	36N	13E	Forest	0-225-165-2015		0.0	0.5	5.4	23.3	2.701	2.729	1.042		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
Source Name	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
FLANNERY 55-33-009-QRY Created On: 03/23/18 Updated On:	Q	NW	SW	6	2N	5E	Lafayette	0-225-141-2018	2.4	17.0	4.0	7.4	28.8	2.597	2.658	2.340		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
FLANNERY 55-33-009-QRY Created On: 01/07/19 Updated On:	Q	NW	SW	6	2N	5E	Lafayette	0-225-53-2019	1.5	9.5	5.4	7.5	29.9	2.603	2.660	2.196		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
FLANNERY 55-33-009-QRY Created On: 04/28/20 Updated On:	Q	NW	SW	6	2N	5E	Lafayette	0-225-163-2020	0.9	6.5	3.5	9.8	34.6	2.599	2.662	2.392		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
FLANNERY 55-21-004-PIT Created On: 07/16/20 Updated On:	P	SW	SE	33	36N	13E	Forest	0-225-221-2020	0.0	0.0	0.4	5.2	23.5	2.743	2.762	0.685		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
FLANNERY 55-33-009-QRY Created On: 03/17/21 Updated On:	Q	NW	SW	6	2N	5E	Lafayette	0-225-148-2021	3.0	8.3	3.4	9.8	35.3	2.560	2.634	2.864		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
FLANNERY 55-33-009-QRY Created On: 03/15/22 Updated On:	Q	NW	SW	6	2N	5E	Lafayette	0-225-143-2022	1.3	5.4	7.0	10.0	35.1	2.635	2.688	1.987		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
FLANNERY 55-33-009-QRY Created On: 01/03/23 Updated On:	Q	NW	SW	6	2N	5E	Lafayette	0-225-5-2023	1.2	4.1	3.8	6.9	29.0	2.609	2.669	2.290		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
Source Name	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
FLANNERY 55-33-009-QRY Created On: 01/04/24 Updated On:	Q	NW	SW	6	2N	5E	Lafayette	0-225-139-2024	0.8	6.9	8.1	8.8	36.9	2.610	2.671	2.312		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
FLANNERY 55-21-004-PIT Created On: 02/24/25 Updated On:	P	SW	SE	33	36N	13E	Forest	0-225-157-2025	0.8	0.0	1.1	4.6	21.3	2.731	2.756	0.901		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
FLANNERY MATERIALS LAKE TOMAHAWK 55-43-010-PIT Created On: 04/18/19 Updated On:	P	SW	NW	36	39N	7E	Oneida	0-225-139-2019	0.3	0.0	0.1	5.5	26.2	2.655	2.673	0.680		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
FLANNERY MATERIALS LAKE TOMAHAWK 55-43-010-PIT Created On: 07/31/24 Updated On:	P	SW	NW	36	39N	7E	Oneida	0-225-290-2024	0.7	0.0	1.4	6.2	27.2	2.636	2.666	1.148		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
FOOTVILLE ROCK & LIME 55-53-011-QRY Created On: 03/22/19 Updated On:	Q	SE	NW	2	2N	10E	Rock	0-225-115-2019	0.1	5.8	10.5	6.0	28.3	2.648	2.703	2.051		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
FOOTVILLE ROCK & LIME 55-53-011-QRY Created On: 01/03/23 Updated On:	Q	SE	NW	2	2N	10E	Rock	0-225-61-2023	1.0	16.2	17.4	11.1	40.6	2.570	2.654	3.255		
	Approved Use : Base Aggregate																	
FOOTVILLE ROCK & LIME 55-53-011-QRY Created On: 03/27/24 Updated On:	Q	SE	NW	2	2N	10E	Rock	0-225-212-2024	0.6	17.6	15.6	8.7	37.0	2.582	2.667	3.288		
	Approved Use : Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse					
	P/Q	Qrt	Qrt	Sect	Town	Range	County					LA Wear (%)		Sp. Gravity		Absorp. %	
												100	500	OD	SSD	Crse	Fine
FORDE 55-12-009-QRY Created On: 01/04/24 Updated On:	Q	SE	NE	5	10N	6W	Crawford	0-225-137-2024	0.2	16.0	4.6	9.5	34.9	2.606	2.672	2.521	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
FOSTERS 55-60-008-PIT Created On: 07/07/22 Updated On:	P	NW	SE	20	33N	3W	Taylor	0-225-244-2022	1.9	0.0	3.3	4.5	21.1	2.711	2.739	1.036	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
FOX RIDGE 55-56-008-PIT Created On: 04/29/25 Updated On:	P		NE	22	12N	6E	Sauk	0-225-199-2025	0.4	0.7	2.2	8.5	28.7	2.662	2.692	1.132	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
FRAATZ 55-65-006-PIT Created On: 06/08/17 Updated On:	P		SW	18	41N	12W	Washburn	0-225-207-2017		0.0	3.8	6.0	24.3	2.629	2.682	2.020	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
FRAATZ 55-65-006-PIT Created On: 03/01/23 Updated On:	P		SW	18	41N	12W	Washburn	0-225-162-2023	4.4	0.0	6.9	5.0	22.5	2.661	2.707	1.738	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
FRANKLIN 55-40-008-QRY Created On: 01/21/16 Updated On:	Q		NE	10	5N	21E	Milwaukee	0-225-70-2016	3.5	15.1	2.8	4.4	21.7	2.636	2.695	2.235	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
FRANKLIN 55-40-008-QRY Created On: 05/26/16 Updated On:	Q		NE	10	5N	21E	Milwaukee	0-225-188-2016	0.3	1.3	1.1	5.6	26.0	2.639	2.677	1.453	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					LA Wear (%)		Sp. Gravity		Absorp. %	
												100	500	OD	SSD	Crse	Fine
FRANKLIN 55-40-008-QRY Created On: 08/25/17 Updated On:	Q		NE	10	5N	21E	Milwaukee	0-225-266-2017		0.0	1.0	7.9	29.7	2.649	2.704	2.074	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
FRANKLIN 55-40-008-QRY Created On: 01/09/20 Updated On:	Q		NE	10	5N	21E	Milwaukee	0-225-95-2020	1.5	0.0	3.0	4.5	21.8	2.730	2.760	1.098	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
FRANKLIN 55-40-008-QRY Created On: 01/03/23 Updated On:	Q		NE	10	5N	21E	Milwaukee	0-225-82-2023	1.0	3.3	0.3	6.2	29.0	2.578	2.634	2.163	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
* FRAWLEY 55-52-010-QRY Created On: 06/21/18 Updated On:	Q			9	10N	2W	Richland	0-225-237-2018	0.8	6.3	9.4	10.2	30.6	2.669	2.716	1.752	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
* FRAWLEY 55-52-010-QRY Created On: 03/17/21 Updated On:	Q			9	10N	2W	Richland	0-225-149-2021	1.2	11.2	8.6	12.0	38.9	2.593	2.664	2.737	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
FREEDOM - N.E.A. 55-44-012-QRY Created On: 01/04/22 Updated On:	Q	NE	NW	10	22N	18E	Outagamie	0-225-13-2022	0.0	2.5	0.3	4.6	21.2	2.757	2.783	0.941	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
FREEDOM - N.E.A. 55-44-012-QRY Created On: 01/02/25 Updated On:	Q	NE	NW	10	22N	18E	Outagamie	0-225-58-2025	0.0	4.0	1.1	4.7	21.4	2.775	2.799	0.869	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
Source Name	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
FRENCHTOWN 19-00-008-QRY Created On: 05/22/19 Updated On:	Q			18	93N	2W	Clayton	0-225-191-2019	0.4	1.4	0.2	5.9	26.6	2.647	2.685	1.444	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
FRENCHTOWN 19-00-008-QRY Created On: 05/22/19 Updated On:	Q			18	93N	2W	Clayton	0-225-192-2019	0.1	4.3	0.7	6.2	27.7	2.661	2.703	1.558	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
FRENCHTOWN 19-00-008-QRY Created On: 01/13/22 Updated On:	Q			18	93N	2W	Clayton	0-225-112-2022	1.8	3.6	2.8	7.5	32.1	2.606	2.660	2.069	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
FRENCHTOWN 19-00-008-QRY Created On: 03/27/24 Updated On:	Q			18	93N	2W	Clayton	0-225-207-2024	1.4	14.4	3.9	9.5	36.7	2.580	2.650	2.724	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
* FRENS 55-14-038-QRY Created On: 04/05/21 Updated On:	Q	NW	3		13N	14E	Dodge	0-225-169-2021	0.6	3.0	2.9	5.9	25.8	2.770	2.795	0.906	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
FREY 55-22-017-QRY Created On: 06/30/16 Updated On:	Q	NW	SE	15	7N	3W	Grant	0-225-216-2016		3.9	4.5	12.0	39.2	2.605	2.668	2.431	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
FREY 55-22-017-QRY Created On: 05/12/20 Updated On:	Q	NW	SE	15	7N	3W	Grant	0-225-175-2020	0.7	4.6	3.7	10.5	37.5	2.577	2.646	2.654	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
FREY 55-22-017-QRY Created On: 01/10/23 Updated On:	Q	NW	SE	15	7N	3W	Grant	0-225-117-2023	0.4	5.1	4.0	11.0	38.6	2.544	2.631	3.430	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
FROSTMAN 55-04-004-PIT Created On: 01/07/19 Updated On:	P		NW	26	47N	8W	Bayfield	0-225-57-2019	2.3	0.0	2.6	8.8	20.9	2.684	2.715	1.154	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
FROSTMAN 55-04-004-PIT Created On: 01/02/25 Updated On:	P		NW	26	47N	8W	Bayfield	0-225-39-2025	1.1	1.4	1.7	4.5	18.8	2.774	2.803	1.033	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
GATES #238 55-17-011-QRY Created On: 01/08/15 Updated On:	Q	S	NW	17	28N	14W	Dunn	0-225-36-2015	0.7	0.0	4.5	7.3	32.3	2.629	2.688	2.238	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
GATES #238 55-17-011-QRY Created On: 07/17/15 Updated On:	Q	S	NW	17	28N	14W	Dunn	0-225-215-2015		0.0	1.9	7.5	31.3	2.608	2.669	2.323	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
GATES #238 55-17-011-QRY Created On: 04/21/17 Updated On:	Q	S	NW	17	28N	14W	Dunn	0-225-142-2017	1.3	0.0	2.0	7.7	31.1	2.610	2.672	2.371	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
GATES #238 55-17-011-QRY Created On: 08/09/19 Updated On:	Q	S	NW	17	28N	14W	Dunn	0-225-259-2019	2.9	0.0	5.3	11.3	39.7	2.558	2.641	3.218	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
GATES #238 55-17-011-QRY Created On: 04/05/22 Updated On:	Q	S	NW	17	28N	14W	Dunn	0-225-157-2022	6.5	1.8	10.6	11.6	43.4	2.537	2.614	3.053	
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																
GATES #238 55-17-011-QRY Created On: 01/02/25 Updated On:	Q	S	NW	17	28N	14W	Dunn	0-225-43-2025	2.0	1.7	6.7	10.8	41.2	2.568	2.640	2.794	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
GATEWAY 55-63-023-PIT Created On: 07/18/19 Updated On:	P	SE	NE	11	42N	10E	Vilas	0-225-236-2019	0.3	0.0	0.6	3.5	16.4	2.744	2.763	0.689	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
GATEWAY 55-63-023-PIT Created On: 01/02/24 Updated On:	P	SE	NE	11	42N	10E	Vilas	0-225-59-2024	0.7	0.0	0.5	3.9	18.0	2.727	2.749	0.824	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
GAY 55-10-007-PIT Created On: 04/23/15 Updated On:	P	SE	SE	5	28N	2W	Clark	0-225-136-2015		0.0	1.4	4.1	19.4	2.670	2.698	1.050	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
GAY 55-10-007-PIT Created On: 01/04/23 Updated On:	P	SE	SE	5	28N	2W	Clark	0-225-96-2023	4.3	0.0	6.2	5.1	22.3	2.597	2.645	1.837	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
GEIER ROAD 55-29-009-QRY Created On: 05/18/18 Updated On:	Q			27	14N	3E	Juneau	0-225-213-2018	0.6	0.0	4.4	12.3	45.7	2.608	2.672	2.457	
	Approved Use : HMA<MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
Source Name	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
GEIER ROAD 55-29-009-QRY Created On: 01/05/21 Updated On:	Q			27	14N	3E	Juneau	0-225-64-2021	0.8	6.2	8.4	10.9	42.9	2.645	2.697	1.973		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
GEIER ROAD 55-29-009-QRY Created On: 01/02/24 Updated On:	Q			27	14N	3E	Juneau	0-225-116-2024	1.8	4.2	1.6	8.4	34.6	2.577	2.634	2.197		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
GENESEE 55-67-007-PIT Created On: 01/05/16 Updated On:	P	NE	SE	29	6N	18E	Waukesha	0-225-21-2016	0.2	1.9	2.4	8.0	34.9	2.708	2.745	1.346		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
GENESEE 55-67-007-PIT Created On: 01/05/21 Updated On:	P	NE	SE	29	6N	18E	Waukesha	0-225-95-2021	0.0	6.1	2.8	6.1	27.5	2.727	2.759	1.189		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
GENESEE / HILLVIEW 55-67-005-PIT Created On: 01/08/15 Updated On:	P		SE	8	8N	19E	Waukesha	0-225-30-2015	0.5	4.6	3.9	5.9	28.1	2.686	2.725	1.439		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
GENESEE / HILLVIEW 55-67-005-PIT Created On: 02/16/16 Updated On:	P		SE	8	8N	19E	Waukesha	0-225-90-2016		1.6	1.6	7.6	34.6	2.711	2.743	1.180		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
GENESEE / HILLVIEW 55-67-005-PIT Created On: 01/05/21 Updated On:	P		SE	8	8N	19E	Waukesha	0-225-97-2021	0.4	6.1	3.8	7.4	31.0	2.578	2.643	2.498		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
GENESEE/OTTAWA PIT 55-67-006-PIT Created On: 01/05/16 Updated On:	P		SW	1	6N	17E	Waukesha	0-225-19-2016	0.0	3.0	4.9	8.4	37.1	2.688	2.723	1.324	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
GENESEE/OTTAWA PIT 55-67-006-PIT Created On: 01/05/21 Updated On:	P		SW	1	6N	17E	Waukesha	0-225-94-2021	0.0	5.2	6.8	5.5	26.7	2.677	2.716	1.452	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
* GERKE 55-41-009-QRY Created On: 04/25/17 Updated On:	Q	NE	SE	36	17N	1W	Monroe	0-225-157-2017	0.2	0.0	11.8	13.1	48.9	2.523	2.606	3.298	
	Approved Use : HMA<E-3, CONCRETE, Base Aggregate																
* GERKE 55-41-009-QRY Created On: 01/24/22 Updated On:	Q	NE	SE	36	17N	1W	Monroe	0-225-116-2022	0.0	0.0	4.8	12.8	45.8	2.541	2.619	3.035	
	Approved Use : HMA<MT, CONCRETE, OGBC, Base Aggregate																
GILLEN 55-55-006-QRY Created On: 04/06/17 Updated On:	Q	E	NW	10	30N	17W	St. Croix	0-225-117-2017		0.0	1.1	10.9	39.7	2.605	2.666	2.322	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
GILLEN 55-55-006-QRY Created On: 01/08/20 Updated On:	Q	E	NW	10	30N	17W	St. Croix	0-225-54-2020	1.6	0.0	17.0	12.5	42.2	2.599	2.663	2.479	
	Approved Use : Base Aggregate																
GILLEN 55-55-006-QRY Created On: 01/03/23 Updated On:	Q	E	NW	10	30N	17W	St. Croix	0-225-54-2023	0.5	0.0	10.4	11.7	39.3	2.579	2.656	2.966	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
GILLES (DANE) 55-13-024-QRY Created On: 01/24/22 Updated On:	Q	NW	NW	4	9N	9E	Dane	0-225-117-2022	0.7	1.2	1.1	9.5	34.9	2.602	2.658	2.140	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
GILLES (DANE) 55-13-024-QRY Created On: 01/23/23 Updated On:	Q	NW	NW	4	9N	9E	Dane	0-225-131-2023	0.3	1.2	1.0	8.6	35.3	2.560	2.628	2.681	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
GILLES (DANE) 55-13-024-QRY Created On: 04/15/24 Updated On:	Q	NW	NW	4	9N	9E	Dane	0-225-225-2024	0.7	0.9	1.7	9.5	37.8	2.602	2.665	2.409	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
GILLES (DANE) 55-13-024-QRY Created On: 01/02/25 Updated On:	Q	NW	NW	4	9N	9E	Dane	0-225-38-2025	1.5	1.6	3.1	10.0	36.5	2.642	2.687	1.702	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
GLEN FLORA PETERSON 55-54-020-PIT Created On: 06/24/21 Updated On:	P		NE	30	35N	4W	Rusk	0-225-232-2021	1.3	0.0	1.2	4.7	20.5	2.751	2.777	0.939	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
GLENMORE 55-05-013-QRY Created On: 01/05/15 Updated On:	Q		NE	6	22N	21E	Brown	0-225-5-2015	0.1	0.4	1.2	6.5	30.3	2.730	2.765	1.294	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
GLENMORE 55-05-013-QRY Created On: 01/04/18 Updated On:	Q		NE	6	22N	21E	Brown	0-225-53-2018		1.1	1.8	6.4	30.0	2.725	2.755	1.090	
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
GLENMORE 55-05-013-QRY Created On: 01/04/21 Updated On:	Q		NE	6	22N	21E	Brown	0-225-6-2021	1.6	1.6	2.9	6.0	38.7	2.672	2.721	1.807	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
GLENMORE 55-05-013-QRY Created On: 01/02/24 Updated On:	Q		NE	6	22N	21E	Brown	0-225-49-2024	20.7	16.5	6.0	13.7	43.6	2.513	2.597	3.370	
	Approved Use : OGBC, Base Aggregate																
GLENMORE 55-05-013-QRY Created On: 06/25/24 Updated On:	Q		NE	6	22N	21E	Brown	0-225-276-2024	0.2	2.7	3.0	9.3	36.6	2.684	2.731	1.729	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
GO GREEN 55-68-019-QRY Created On: 09/02/15 Updated On:	Q		NW	13	21N	14E	Waupaca	0-225-236-2015		0.0	11.3	8.4	34.6	2.701	2.745	1.654	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
GO GREEN 55-68-019-QRY Created On: 02/15/18 Updated On:	Q		NW	13	21N	14E	Waupaca	0-225-101-2018		0.0	2.6	5.9	27.4	2.698	2.738	1.490	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
GO GREEN 55-68-019-QRY Created On: 02/28/23 Updated On:	Q		NW	13	21N	14E	Waupaca	0-225-159-2023	1.3	5.4	2.3	8.5	32.7	2.699	2.739	1.476	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
GOETZ 55-10-039-QRY Created On: 05/17/22 Updated On:	Q	NW	NE	26	24N	2W	Clark	0-225-200-2022	0.5	0.0	0.6	4.0	19.1	2.684	2.694	0.384	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
GOETZ 55-10-039-QRY Created On: 01/16/25 Updated On:	Q	NW	NE	26	24N	2W	Clark	0-225-140-2025	0.3	0.0	1.6	3.2	15.3	2.657	2.677	0.729	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
GOHR 55-42-011-QRY Created On: 05/30/17 Updated On:	Q	SW	NE	4	26N	19E	Oconto	0-225-196-2017		1.2	1.2	5.7	26.2	2.772	2.793	0.751	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
GOHR 55-42-011-QRY Created On: 01/02/20 Updated On:	Q	SW	NE	4	26N	19E	Oconto	0-225-3-2020	0.0	2.9	2.4	5.7	25.5	2.748	2.771	0.823	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
GOHR 55-42-011-QRY Created On: 01/12/23 Updated On:	Q	SW	NE	4	26N	19E	Oconto	0-225-121-2023	0.0	2.1	1.9	6.8	23.7	2.755	2.780	0.884	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
* GOLD THORPE 55-25-032-QRY Created On: 06/13/19 Updated On:	Q	SE	SW	15	5N	3E	Iowa	0-225-214-2019	0.1	1.6	3.4	7.6	30.1	2.601	2.669	2.626	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
* GOLD THORPE 55-25-032-QRY Created On: 01/10/22 Updated On:	Q	SE	SW	15	5N	3E	Iowa	0-225-100-2022	0.8	3.4	6.9	7.4	35.1	2.573	2.643	2.721	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
GOSBEE 55-60-009-PIT Created On: 06/26/17 Updated On:	P	SE	NE	28	32N	1E	Taylor	0-225-219-2017		0.0	0.6	4.2	19.4	2.697	2.733	1.354	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
GOSBEE 55-60-009-PIT Created On: 06/28/22 Updated On:	P	SE	NE	28	32N	1E	Taylor	0-225-242-2022	0.6	0.0	2.7	4.1	18.0	2.728	2.753	0.921		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
GRAHL-EMPIRE 55-20-014-PIT Created On: 05/12/16 Updated On:	P	S	SE	36	15N	18E	Fond Du Lac	0-225-173-2016	0.1	0.0	2.2	6.5	29.8	2.740	2.768	1.052		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
GRAHL-EMPIRE 55-20-014-PIT Created On: 04/13/21 Updated On:	P	S	SE	36	15N	18E	Fond Du Lac	0-225-178-2021	1.0	4.9	3.2	5.7	28.7	2.734	2.765	1.105		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
GRANITE HEIGHTS 55-37-100-QRY Created On: 07/31/24 Updated On:	Q	NE	NE	35	30N	7E	Marathon	0-225-289-2024	0.0	0.7	0.8	4.2	21.2	2.605	2.626	0.807		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
GREY CLOUD NELSON 27-00-010-PIT Created On: 04/07/16 Updated On:	P	S	NW	31	27N	21W	Lakeland	0-225-127-2016	0.1	1.9	3.9	4.2	24.0	2.674	2.712	1.422		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
GREY CLOUD NELSON 27-00-010-PIT Created On: 08/12/21 Updated On:	P	S	NW	31	27N	21W	Lakeland	0-225-262-2021	1.5	4.4	1.6	5.2	24.1	2.694	2.722	1.023		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
GREY CLOUD PIT 27-00-033-PIT Created On: 04/29/25 Updated On:	P	NW	NW	31	27N	21W	Statewide	0-225-200-2025	2.2	4.9	2.4	4.5	21.1	2.651	2.684	1.246		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
GRIMMS 55-36-015-QRY Created On: 01/04/16 Updated On:	Q	NE	SE	6	19N	22E	Manitowoc	0-225-6-2016		0.2	1.4	7.8	30.5	2.690	2.727	1.362	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
GRIMMS 55-36-015-QRY Created On: 05/09/19 Updated On:	Q	NE	SE	6	19N	22E	Manitowoc	0-225-182-2019	0.0	0.0	0.7	8.0	32.0	2.693	2.731	1.426	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
GRIMMS 55-36-015-QRY Created On: 01/04/22 Updated On:	Q	NE	SE	6	19N	22E	Manitowoc	0-225-33-2022	0.0	0.0	1.6	9.6	38.6	2.727	2.758	1.133	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
GRIMMS 55-36-015-QRY Created On: 01/02/24 Updated On:	Q	NE	SE	6	19N	22E	Manitowoc	0-225-102-2024	0.0	0.5	1.2	8.9	36.6	2.712	2.744	1.200	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
GRUNEWALD 55-58-009-QRY Created On: 05/10/18 Updated On:	Q			33	27N	17E	Shawano	0-225-206-2018	0.0	6.2	3.4	7.8	32.4	2.715	2.753	1.389	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
GRUNEWALD 55-58-009-QRY Created On: 04/30/21 Updated On:	Q			33	27N	17E	Shawano	0-225-198-2021	0.9	2.3	6.4	8.1	34.6	2.687	2.733	1.703	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
GRUNEWALD 55-58-009-QRY Created On: 01/02/24 Updated On:	Q			33	27N	17E	Shawano	0-225-68-2024	0.0	3.9	3.7	8.2	35.1	2.676	2.719	1.606	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
GUDGEON 55-62-012-QRY Created On: 01/09/20 Updated On:	Q	NW	NE	27	13N	4E	Vernon	0-225-84-2020	0.0	1.9	3.3	10.5	41.7	2.589	2.655	2.518	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
GUDGEON 55-62-012-QRY Created On: 01/10/23 Updated On:	Q	NW	NE	27	13N	4E	Vernon	0-225-107-2023	0.5	3.6	3.0	11.2	40.6	2.580	2.653	2.842	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
GUELIG 55-20-015-PIT Created On: 01/21/16 Updated On:	P	NW	SE	9	16N	19E	Fond Du Lac	0-225-66-2016	0.0	3.3	4.7	7.4	31.7	2.739	2.774	1.295	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
GUELIG 55-20-015-PIT Created On: 01/05/21 Updated On:	P	NW	SE	9	16N	19E	Fond Du Lac	0-225-102-2021	0.0	3.6	1.1	7.5	31.4	2.738	2.771	1.206	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
GUELIG NORTH 55-20-059-PIT Created On: 10/21/21 Updated On:	P	NW	NE	9	16N	19E	Fond Du Lac	0-225-270-2021	0.3	0.0	4.6	7.5	32.3	2.761	2.789	1.047	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
GULICH 55-09-079-PIT Created On: 01/30/20 Updated On:	P	NW	SE	10	32N	6W	Chippewa	0-225-101-2020	1.2	0.0	2.4	3.5	17.9	2.675	2.710	1.315	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
GULICH 55-09-079-PIT Created On: 01/16/25 Updated On:	P	NW	SE	10	32N	6W	Chippewa	0-225-134-2025	1.0	0.0	2.3	5.1	21.2	2.650	2.686	1.375	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
H&H 55-37-096-QRY Created On: 01/19/23 Updated On:	Q	NW	SW	5	28N	6E	Marathon	0-225-124-2023	0.2	2.6	1.0	4.7	19.0	2.627	2.670	1.619	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
HAAS 0-M PIT 55-54-032-PIT Created On: 07/27/23 Updated On:	P	NW	SE	19	33N	9W	Rusk	0-225-240-2023	1.9	0.0	1.0	5.1	22.5	2.685	2.712	1.002	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
HAAS 124 55-09-025-PIT Created On: 06/06/19 Updated On:	P	SE	SE	6	30N	8W	Chippewa	0-225-207-2019	7.8	0.0	3.5	5.3	21.6	2.659	2.687	1.060	
	Approved Use : HMA<MT, HMA>=MT, Base Aggregate																
HAAS 124 55-09-025-PIT Created On: 06/04/20 Updated On:	P	SE	SE	6	30N	8W	Chippewa	0-225-186-2020	1.1	0.0	0.9	3.7	19.7	2.712	2.745	1.204	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
HAAS 124 55-09-025-PIT Created On: 01/02/25 Updated On:	P	SE	SE	6	30N	8W	Chippewa	0-225-13-2025	0.2	1.8	0.0	5.3	20.0	2.742	2.771	1.075	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
HAAS EMSTROM PIT 55-60-035-PIT Created On: 07/27/23 Updated On:	P	NE	NW	3	31N	2W	Taylor	0-225-243-2023	1.8	0.0	1.5	4.5	21.2	2.742	2.762	0.718	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
HAAS LEHMAN PIT 55-54-033-PIT Created On: 07/27/23 Updated On:	P	SE	NE	3	33N	7W	Rusk	0-225-244-2023	0.5	0.0	0.5	3.7	18.1	2.688	2.715	1.000	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
HAAS RW PIT 55-50-029-PIT Created On: 07/27/23 Updated On:	P	NE	SW	36	35N	1E	Price	0-225-242-2023	1.1	0.0	0.7	4.0	18.8	2.717	2.737	0.754	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
HAAS SPORTS PIT 55-09-081-PIT Created On: 07/27/23 Updated On:	P	NE	NW	25	31N	7W	Chippewa	0-225-241-2023	2.0	0.0	1.0	4.4	20.1	2.723	2.748	0.897	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
HACKL 55-25-010-QRY Created On: 01/05/17 Updated On:	Q	SW	SW	21	8N	1E	Iowa	0-225-24-2017	6.9	4.5	4.6	8.9	34.3	2.645	2.696	1.917	
	Approved Use : HMA<E-3, HMA>=E-3, Base Aggregate																
HACKL 55-25-010-QRY Created On: 01/04/19 Updated On:	Q	SW	SW	21	8N	1E	Iowa	0-225-23-2019	0.9	7.7	2.9	8.3	32.4	2.662	2.707	1.711	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
HACKL 55-25-010-QRY Created On: 01/04/22 Updated On:	Q	SW	SW	21	8N	1E	Iowa	0-225-49-2022	0.2	6.2	0.4	10.3	34.8	2.648	2.698	1.890	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
HACKL 55-25-010-QRY Created On: 01/02/25 Updated On:	Q	SW	SW	21	8N	1E	Iowa	0-225-33-2025	0.5	2.8	0.3	6.4	26.4	2.664	2.709	1.684	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
HAEF 55-61-007-PIT Created On: 03/28/17 Updated On:	P	SW	NE	19	18N	8W	Trempealeau	0-225-90-2017		0.0	0.3	4.3	19.1	2.630	2.664	1.291	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
HAEF 55-61-007-PIT Created On: 01/04/22 Updated On:	P	SW	NE	19	18N	8W	Trempealeau	0-225-50-2022	0.0	0.3	0.5	3.2	14.5	2.635	2.674	1.478	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
HAFFELDER 55-17-013-QRY Created On: 06/08/15 Updated On:	Q	NE	NE	23	28N	14W	Dunn	0-225-189-2015		0.0	4.4	7.5	39.1	2.571	2.641	2.714	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
HAFFELDER 55-17-013-QRY Created On: 01/03/18 Updated On:	Q	NE	NE	23	28N	14W	Dunn	0-225-32-2018	2.0	0.0	6.3	10.5	36.9	2.531	2.616	3.356	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
HAFFELDER 55-17-013-QRY Created On: 01/05/21 Updated On:	Q	NE	NE	23	28N	14W	Dunn	0-225-75-2021	1.4	0.0	0.8	9.7	35.3	2.559	2.641	3.186	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
HAFFELDER 55-17-013-QRY Created On: 01/02/24 Updated On:	Q	NE	NE	23	28N	14W	Dunn	0-225-75-2024	1.7	6.7	6.7	12.2	43.3	2.548	2.629	3.169	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
HAGENY 55-21-008-PIT Created On: 08/14/24 Updated On:	P	NE	SE	2	35N	12E	Forest	0-225-296-2024	0.3	0.0	2.7	6.2	25.6	2.704	2.731	0.997	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
HAGGERTY 55-12-010-QRY Created On: 07/17/15 Updated On:	Q	SW	SW	10	9N	3W	Crawford	0-225-212-2015		2.6	3.4	8.2	33.6	2.625	2.678	2.011	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
HAGGERTY 55-12-010-QRY Created On: 07/09/20 Updated On:	Q	SW	SW	10	9N	3W	Crawford	0-225-210-2020	0.9	1.5	3.6	9.1	32.3	2.629	2.684	2.072	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
HAGGERTY 55-12-010-QRY Created On: 01/16/25 Updated On:	Q	SW	SW	10	9N	3W	Crawford	0-225-132-2025	2.1	10.2	3.4	13.2	42.7	2.572	2.634	2.388	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
HAHN 55-11-014-QRY Created On: 01/05/17 Updated On:	Q	NW	SE	11	12N	11E	Columbia	0-225-48-2017	0.9	2.6	1.6	13.7	38.3	2.548	2.625	3.010	
	Approved Use : CONCRETE, OGBC, Base Aggregate																
HAHN 55-11-014-QRY Created On: 01/08/20 Updated On:	Q	NW	SE	11	12N	11E	Columbia	0-225-69-2020	0.7	4.8	8.0	10.0	41.1	2.549	2.625	2.962	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
HAHN 55-11-014-QRY Created On: 01/04/23 Updated On:	Q	NW	SE	11	12N	11E	Columbia	0-225-94-2023	0.9	4.9	5.5	11.3	43.4	2.531	2.614	3.289	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
HALQUIST 55-67-048-QRY Created On: 04/29/25 Updated On:	Q	SE	SW	17	8N	20E	Waukesha	0-225-203-2025		3.6	0.1	4.6	22.7	2.755	2.778	0.840	
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																
HALQUIST NORTH LAKE 55-67-032-PIT Created On: 06/27/18 Updated On:	P		SE	9	8N	18E	Waukesha	0-225-239-2018	1.1	0.8	1.0	5.6	27.3	2.721	2.749	1.042	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
HALQUIST NORTH LAKE 55-67-032-PIT Created On: 03/21/23 Updated On:	P		SE	9	8N	18E	Waukesha	0-225-171-2023	0.6	17.3	0.0	5.3	25.1	2.720	2.744	0.900	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
HALQUIST NORTH LAKE 55-67-032-PIT Created On: 06/27/24 Updated On:	P		SE	9	8N	18E	Waukesha	0-225-283-2024	1.2	9.1	2.2	5.4	26.1	2.708	2.736	1.062	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
HAMPTON 55-22-021-QRY Created On: 04/07/16 Updated On:	Q			21	4N	5W	Grant	0-225-136-2016	1.2	8.5	6.9	9.4	36.5	2.576	2.646	2.698	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
HAMPTON 55-22-021-QRY Created On: 04/19/19 Updated On:	Q			21	4N	5W	Grant	0-225-156-2019	1.5	7.6	5.4	10.0	38.0	2.594	2.656	2.424	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
HAMPTON 55-22-021-QRY Created On: 01/04/22 Updated On:	Q			21	4N	5W	Grant	0-225-46-2022	0.9	14.6	1.1	10.6	36.4	2.569	2.638	2.693	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
HAMPTON 55-22-021-QRY Created On: 01/02/25 Updated On:	Q			21	4N	5W	Grant	0-225-27-2025	0.7	2.2	0.4	9.7	33.2	2.592	2.656	2.478	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
HANSON 55-12-011-QRY Created On: 01/02/24 Updated On:	Q	NW	SW	24	11N	7W	Crawford	0-225-121-2024	0.4	4.1	2.5	11.6	38.9	2.573	2.645	2.788	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
* HARRY'S 55-63-006-PIT Created On: 05/08/15 Updated On:	P	SE	SE	14	40N	6E	Vilas	0-225-153-2015		0.0	0.5	4.4	20.0	2.692	2.717	0.937	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
* HARRY'S 55-63-006-PIT Created On: 01/08/20 Updated On:	P	SE	SE	14	40N	6E	Vilas	0-225-72-2020	0.8	0.0	0.9	3.4	16.6	2.702	2.728	0.958	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
HARTMAN SPRING LAKE 55-45-004-PIT Created On: 04/26/19 Updated On:	P	SE	NE	3	12N	21E	Ozaukee	0-225-171-2019	0.4	1.5	0.6	8.4	35.2	2.717	2.746	1.084	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
HARTMAN SPRING LAKE 55-45-004-PIT Created On: 05/20/24 Updated On:	P	SE	NE	3	12N	21E	Ozaukee	0-225-258-2024	0.2	3.3	0.4	6.2	30.1	2.724	2.750	0.951	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
HARTMANN QUARRY 55-11-041-QRY Created On: 01/02/24 Updated On:	Q	NE	NE	36	10N	7E	Columbia	0-225-43-2024	1.6	2.9	9.7	9.0	34.8	2.566	2.633	2.631	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
HARVEST HAVEN / O'BRIAN 55-13-030-QRY Created On: 01/07/15 Updated On:	Q		SE	7	6N	9E	Dane	0-225-8-2015		21.1	10.1	6.0	28.1	2.614	2.680	2.509	
HARVEST HAVEN / O'BRIAN 55-13-030-QRY Created On: 06/03/15 Updated On:	Q		SE	7	6N	9E	Dane	0-225-181-2015		16.0	7.4	6.4	30.3	2.608	2.683	2.892	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Coarse Sp. Gravity		Coarse Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
HARVEST HAVEN / O'BRIAN 55-13-030-QRY Created On: 09/15/16 Updated On:	Q		SE	7	6N	9E	Dane	0-225-256-2016	0.5	15.9	9.8	7.2	32.5	2.596	2.666	2.711	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
HARVEST HAVEN / O'BRIAN 55-13-030-QRY Created On: 01/02/18 Updated On:	Q		SE	7	6N	9E	Dane	0-225-1-2018	0.8	8.7	13.9	6.1	30.7	2.597	2.665	2.601	
	Approved Use : Base Aggregate																
HARVEST HAVEN / O'BRIAN 55-13-030-QRY Created On: 03/18/21 Updated On:	Q		SE	7	6N	9E	Dane	0-225-154-2021	0.4	4.0	7.1	8.1	34.2	2.597	2.657	2.288	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
HARVEST HAVEN / O'BRIAN 55-13-030-QRY Created On: 01/04/24 Updated On:	Q		SE	7	6N	9E	Dane	0-225-146-2024	0.7	7.4	6.2	9.8	40.1	2.580	2.649	2.667	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
HASKE 55-71-017-QRY Created On: 01/07/15 Updated On:	Q	SW	SE	24	24N	2E	Wood	0-225-17-2015		0.0	0.5	5.0	20.6	2.619	2.629	0.374	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
HASKE 55-71-017-QRY Created On: 01/02/18 Updated On:	Q	SW	SE	24	24N	2E	Wood	0-225-2-2018		0.0	0.3	3.6	17.7	2.620	2.628	0.308	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
HASKE 55-71-017-QRY Created On: 01/04/21 Updated On:	Q	SW	SE	24	24N	2E	Wood	0-225-18-2021	0.0	0.1	0.1	5.2	22.0	2.622	2.633	0.416	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
HASKE 55-71-017-QRY Created On: 05/01/24 Updated On:	Q	SW	SE	24	24N	2E	Wood	0-225-245-2024	0.0	0.0	0.1	5.1	22.0	2.616	2.627	0.407	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
* HAUSZ BROS. 55-28-021-QRY Created On: 04/05/22 Updated On:	Q	S	SW	11	5N	14E	Jefferson	0-225-154-2022	1.0	7.1	16.6	17.7	43.4	2.523	2.614	3.645	
	Approved Use : Base Aggregate																
* HAVERLAND 55-22-023-QRY Created On: 04/06/17 Updated On:	Q	NE	NW	26	2N	2W	Grant	0-225-106-2017	1.0	2.4	2.5	12.7	39.1	2.528	2.616	3.516	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
* HAVERLAND 55-22-023-QRY Created On: 03/23/18 Updated On:	Q	NE	NW	26	2N	2W	Grant	0-225-137-2018	1.0	2.9	2.5	13.4	41.0	2.552	2.627	2.962	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
* HAVERLAND 55-22-023-QRY Created On: 03/17/21 Updated On:	Q	NE	NW	26	2N	2W	Grant	0-225-150-2021	0.1	3.9	4.1	18.0	49.1	2.507	2.598	3.604	
	Approved Use : Base Aggregate																
HAWKINS 286 55-54-008-PIT Created On: 01/05/16 Updated On:	P	S	NW	15	35N	3W	Rusk	0-225-24-2016		0.0	1.4	4.3	19.4	2.731	2.751	0.758	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
HAWKINS 286 55-54-008-PIT Created On: 10/12/21 Updated On:	P	S	NW	15	35N	3W	Rusk	0-225-268-2021	0.4	1.2	1.5	3.5	17.4	2.755	2.770	0.579	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
Source Name	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
HAWKINS 286 55-54-008-PIT Created On: 01/10/23 Updated On:	P	S	NW	15	35N	3W	Rusk	0-225-115-2023	0.5	0.0	1.3	3.9	20.0	2.718	2.741	0.826		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
HAWKINSON 55-13-123-PIT Created On: 01/09/20 Updated On:	P	SE	SE	34	6N	10E	Dane	0-225-90-2020	3.9	0.0	4.1	5.7	31.2	2.634	2.687	1.999		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
HAWKINSON 55-13-123-PIT Created On: 01/02/25 Updated On:	P	SE	SE	34	6N	10E	Dane	0-225-52-2025	3.0	0.0	10.3	8.1	33.8	2.614	2.678	2.438		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
HAY CREEK (PRICE) 55-50-008-PIT Created On: 04/23/20 Updated On:	P		SE	4	35N	1E	Price	0-225-156-2020	1.1	0.0	3.9	4.8	20.3	2.707	2.740	1.226		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
HAY CREEK (PRICE) 55-50-008-PIT Created On: 01/02/25 Updated On:	P		SE	4	35N	1E	Price	0-225-66-2025	0.9	0.0	4.7	4.3	19.4	2.668	2.696	1.034		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
HAYTON 55-08-006-QRY Created On: 06/21/16 Updated On:	Q		SW	28	18N	20E	Calumet	0-225-206-2016		0.0	1.7	9.5	39.8	2.727	2.757	1.092		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
HAYTON 55-08-006-QRY Created On: 01/08/19 Updated On:	Q		SW	28	18N	20E	Calumet	0-225-72-2019		0.7	0.8	7.8	33.5	2.764	2.787	0.817		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
HAYTON 55-08-006-QRY Created On: 01/04/22 Updated On:	Q		SW	28	18N	20E	Calumet	0-225-29-2022	0.0	0.0	0.5	8.7	36.7	2.758	2.783	0.903	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
HAYTON 55-08-006-QRY Created On: 01/29/24 Updated On:	Q		SW	28	18N	20E	Calumet	0-225-165-2024	0.0	0.6	1.3	8.7	36.9	2.772	2.792	0.713	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
HAZELHURST 55-43-005-PIT Created On: 06/01/18 Updated On:	P	NE	SE	15	37N	6E	Oneida	0-225-218-2018		0.0	0.5	4.3	20.6	2.689	2.713	0.896	
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																
HAZELHURST 55-43-005-PIT Created On: 01/03/23 Updated On:	P	NE	SE	15	37N	6E	Oneida	0-225-17-2023		0.0	0.3	3.1	16.4	2.713	2.734	0.773	
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																
HEATH 55-54-009-PIT Created On: 04/11/18 Updated On:	P	NW	NW	30	35N	4W	Rusk	0-225-163-2018	0.5	0.0	2.4	3.8	17.9	2.760	2.785	0.898	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
HEATH 55-54-009-PIT Created On: 01/10/23 Updated On:	P	NW	NW	30	35N	4W	Rusk	0-225-113-2023	0.7	0.0	1.6	3.5	17.4	2.763	2.782	0.705	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
HELLICKSON 55-13-031-PIT Created On: 04/12/17 Updated On:	P	SE	NW	34	7N	11E	Dane	0-225-123-2017	2.7	0.0	3.9	7.1	31.6	2.635	2.687	1.966	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
HELLICKSON 55-13-031-PIT Created On: 04/18/22 Updated On:	P	SE	NW	34	7N	11E	Dane	0-225-175-2022	3.4	4.5	6.2	7.0	31.4	2.642	2.692	1.910	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
HERFEL 55-13-033-PIT Created On: 04/21/17 Updated On:	P	S	SE	28	6N	8E	Dane	0-225-139-2017	5.0	2.8	4.0	7.2	30.0	2.565	2.627	2.421	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
HERFEL 55-13-033-PIT Created On: 06/27/24 Updated On:	P	S	SE	28	6N	8E	Dane	0-225-284-2024	4.8	0.0	5.6	9.2	35.9	2.609	2.662	2.045	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
HERMAN 55-14-011-QRY Created On: 04/06/17 Updated On:	Q	SW	NW	6	11N	17E	Dodge	0-225-105-2017		1.1	1.3	6.9	29.6	2.733	2.764	1.114	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
HERMAN 55-14-011-QRY Created On: 06/04/20 Updated On:	Q	SW	NW	6	11N	17E	Dodge	0-225-187-2020		4.5	0.1	5.0	26.7	2.773	2.789	0.577	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
HERMAN 55-14-011-QRY Created On: 02/27/23 Updated On:	Q	SW	NW	6	11N	17E	Dodge	0-225-147-2023	0.4	6.2	3.1	10.4	33.0	2.734	2.764	1.085	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
HESS 55-34-014-PIT Created On: 01/08/16 Updated On:	P	SW	SW	2	30N	11E	Langlade	0-225-45-2016		0.0	1.8	5.8	27.2	2.677	2.695	0.664	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
Source Name	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
HESS 55-34-014-PIT Created On: 01/04/21 Updated On:	P	SW	SW	2	30N	11E	Langlade	0-225-15-2021	0.0	0.6	0.8	5.6	25.3	2.680	2.711	1.180		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
HEYN 55-69-006-PIT Created On: 04/13/17 Updated On:	P	W	NE	22	19N	8E	Waushara	0-225-131-2017		0.0	2.8	6.7	25.8	2.737	2.775	1.388		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
HEYN 55-69-006-PIT Created On: 04/30/21 Updated On:	P	W	NE	22	19N	8E	Waushara	0-225-191-2021	3.3	2.5	4.9	7.6	31.0	2.705	2.741	1.330		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
HIGH ROAD QUARRY 55-15-015-QRY Created On: 01/03/23 Updated On:	Q		NW	4	26N	24E	Door	0-225-42-2023	0.0	2.3	5.4	6.7	29.6	2.705	2.747	1.553		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
HIGH VIEW-SAND & GRAVEL 55-51-058-PIT Created On: 01/14/25 Updated On:	P	SE	NE	34	4N	19E	Racine	0-225-124-2025	3.9	9.1	4.7	4.0	24.1	2.674	2.706	1.200		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
HIGHBRIDGE 55-02-005-QRY Created On: 01/04/23 Updated On:	Q	S	SW	16	45N	3W	Ashland	0-225-91-2023	0.1	0.4	0.3	4.5	21.9	2.588	2.612	0.926		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
* HIGHBRIDGE NORTH 55-02-005-QRY Created On: 05/19/17 Updated On:	Q	S	SW	16	45N	3W	Ashland	0-225-192-2017		0.0	0.7	4.5	21.0	2.615	2.633	0.685		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
* HIGHBRIDGE NORTH 55-02-005-QRY Created On: 01/06/20 Updated On:	Q	S	SW	16	45N	3W	Ashland	0-225-33-2020	0.1	0.0	1.2	5.2	24.3	2.623	2.637	0.549		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
HILGER 55-09-031-PIT Created On: 01/08/19 Updated On:	P			8	30N	8W	Chippewa	0-225-75-2019	0.9	0.0	1.5	3.6	17.4	2.702	2.733	1.123		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
HILGER 55-09-031-PIT Created On: 01/02/24 Updated On:	P			8	30N	8W	Chippewa	0-225-84-2024	0.7	0.0	1.6	3.5	17.7	2.708	2.736	1.029		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
HILLPOINT 55-56-010-QRY Created On: 05/14/15 Updated On:	Q		SW	22	11N	3E	Sauk	0-225-175-2015	0.3	1.2	2.5	10.5	41.7	2.629	2.682	2.011		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
HILLPOINT 55-56-010-QRY Created On: 04/10/18 Updated On:	Q		SW	22	11N	3E	Sauk	0-225-158-2018	0.3	0.0	7.6	12.1	44.8	2.609	2.670	2.362		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
HILLPOINT 55-56-010-QRY Created On: 01/29/24 Updated On:	Q		SW	22	11N	3E	Sauk	0-225-152-2024	0.9	7.9	10.9	13.2	45.9	2.575	2.644	2.665		
	Approved Use : HMA<MT, CONCRETE, OGBC, Base Aggregate																	
HILLSIDE 55-51-010-PIT Created On: 02/20/19 Updated On:	P		SE	7	2N	19E	Racine	0-225-107-2019	0.7	7.1	1.8	5.4	26.0	2.663	2.712	1.877		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
Source Name	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
HILLSIDE 55-51-010-PIT Created On: 02/28/24 Updated On:	P		SE	7	2N	19E	Racine	0-225-188-2024	2.0	11.7	7.6	5.6	25.7	2.670	2.712	1.603		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
HOBART QUARRY 55-05-008-QRY Created On: 04/01/16 Updated On:	Q	NE	NE	27	23N	19E	Brown	0-225-119-2016	0.5	5.0	11.3	6.1	26.0	2.739	2.772	1.181		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
HOBART QUARRY 55-05-008-QRY Created On: 04/13/17 Updated On:	Q	NE	NE	27	23N	19E	Brown	0-225-129-2017		7.9	11.1	5.6	24.0	2.759	2.790	1.100		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
HOBART QUARRY 55-05-008-QRY Created On: 03/18/20 Updated On:	Q	NE	NE	27	23N	19E	Brown	0-225-130-2020		20.2	15.7	9.6	27.0	2.733	2.767	1.247		
HOBART QUARRY 55-05-008-QRY Created On: 06/09/20 Updated On:	Q	NE	NE	27	23N	19E	Brown	0-225-190-2020		11.0	4.2	5.4	24.5	2.750	2.779	1.040		
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																	
HOBART QUARRY 55-05-008-QRY Created On: 03/10/21 Updated On:	Q	NE	NE	27	23N	19E	Brown	0-225-134-2021	0.0	1.1	1.0	4.9	22.5	2.791	2.805	0.492		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
HOBART QUARRY 55-05-008-QRY Created On: 01/04/22 Updated On:	Q	NE	NE	27	23N	19E	Brown	0-225-69-2022	0.0	29.3	16.4	5.9	26.6	2.732	2.766	1.248		

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
HOBART QUARRY 55-05-008-QRY Created On: 02/17/22 Updated On:	Q	NE	NE	27	23N	19E	Brown	0-225-128-2022	0.1	2.1	5.3	4.7	22.5	2.770	2.792	0.811	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
HOBART QUARRY 55-05-008-QRY Created On: 03/21/23 Updated On:	Q	NE	NE	27	23N	19E	Brown	0-225-173-2023	0.0	1.1	0.4	5.3	22.7	2.769	2.789	0.707	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
HOBART QUARRY 55-05-008-QRY Created On: 01/02/24 Updated On:	Q	NE	NE	27	23N	19E	Brown	0-225-14-2024	0.0	2.7	0.4	6.2	27.0	2.765	2.788	0.836	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
HOBART QUARRY 55-05-008-QRY Created On: 01/14/25 Updated On:	Q	NE	NE	27	23N	19E	Brown	0-225-121-2025	0.1	3.7	0.2	5.1	21.7	2.784	2.804	0.726	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
HODGE PIT 55-42-046-PIT Created On: 01/02/24 Updated On:	P	SE	SE	8	29N	20E	Oconto	0-225-96-2024	0.1	0.0	4.0	5.8	27.9	2.709	2.741	1.198	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
* HOHFELD 55-62-015-QRY Created On: 02/03/20 Updated On:	Q	NE	NE	8	14N	6W	Vernon	0-225-109-2020	2.7	0.0	8.2	12.8	46.2	2.550	2.627	3.035	
	Approved Use : HMA<MT, CONCRETE, OGBC, Base Aggregate																
HOLDER PIT 55-11-017-PIT Created On: 01/03/17 Updated On:	P	NW	SE	30	12N	11E	Columbia	0-225-7-2017	6.6	0.0	7.8	11.5	37.8	2.625	2.680	2.079	
	Approved Use : HMA<E-3, HMA>=E-3, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
HOLDER PIT 55-11-017-PIT Created On: 01/04/22 Updated On:	P	NW	SE	30	12N	11E	Columbia	0-225-5-2022	6.6	0.0	9.7	11.0	37.6	2.638	2.687	1.882	
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																
HOLLATZ 55-20-017-PIT Created On: 01/12/16 Updated On:	P	NE	NW	17	16N	14E	Fond Du Lac	0-225-51-2016		0.0	1.4	5.0	24.2	2.729	2.760	1.132	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
HOLLATZ 55-20-017-PIT Created On: 01/04/21 Updated On:	P	NE	NW	17	16N	14E	Fond Du Lac	0-225-45-2021	0.0	3.7	2.4	4.7	23.3	2.718	2.754	1.341	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
HOLST 55-47-010-PIT Created On: 01/03/18 Updated On:	P		W	33	25N	18W	Pierce	0-225-40-2018	1.5	0.0	1.9	5.5	24.5	2.660	2.699	1.455	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
HOLST 55-47-010-PIT Created On: 08/22/23 Updated On:	P		W	33	25N	18W	Pierce	0-225-247-2023	1.5	0.0	0.6	6.2	25.1	2.645	2.675	1.167	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
HOLTAN 55-63-007-PIT Created On: 06/13/19 Updated On:	P	NW	NW	33	43N	8E	Vilas	0-225-220-2019	0.3	0.0	1.8	3.9	19.2	2.742	2.767	0.888	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
HOLTAN 55-63-007-PIT Created On: 01/03/23 Updated On:	P	NW	NW	33	43N	8E	Vilas	0-225-27-2023	1.5	0.0	1.0	4.6	20.4	2.720	2.756	1.307	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
Source Name	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
HOME RUN 55-16-008-QRY Created On: 05/19/17 Updated On:	Q	NE	SE	21	48N	10W	Douglas	0-225-193-2017		18.3	7.3	4.0	32.4	2.753	2.789	1.311		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
HOME RUN 55-16-008-QRY Created On: 04/16/20 Updated On:	Q	NE	SE	21	48N	10W	Douglas	0-225-153-2020		0.0	2.4	2.5	10.8	2.852	2.886	1.191		
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																	
HOME RUN 55-16-008-QRY Created On: 01/04/23 Updated On:	Q	NE	SE	21	48N	10W	Douglas	0-225-88-2023	0.0	0.0	2.1	2.7	13.4	2.837	2.869	1.105		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
HOME RUN 55-16-008-QRY Created On: 03/04/25 Updated On:	Q	NE	SE	21	48N	10W	Douglas	0-225-159-2025	0.5	7.0	4.8	3.7	15.9	2.767	2.802	1.275		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
HOUSEHOLDER 55-52-014-QRY Created On: 05/09/17 Updated On:	Q	NW	SE	15	10N	1E	Richland	0-225-178-2017		0.0	7.0	9.9	37.3	2.569	2.649	3.125		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
HOUSEHOLDER 55-52-014-QRY Created On: 03/12/20 Updated On:	Q	NW	SE	15	10N	1E	Richland	0-225-128-2020	1.9	0.0	2.8	10.6	36.4	2.517	2.600	3.306		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
HOUSEHOLDER 55-52-014-QRY Created On: 01/03/23 Updated On:	Q	NW	SE	15	10N	1E	Richland	0-225-21-2023	0.3	8.4	0.7	9.4	36.8	2.596	2.660	2.456		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
* HUBER 55-06-011-QRY Created On: 05/09/16 Updated On:	Q	SE	SE	4	22N	12W	Buffalo	0-225-165-2016		0.0	11.6	13.0	41.2	2.562	2.635	2.833	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
* HUBER 55-06-011-QRY Created On: 08/25/17 Updated On:	Q	SE	SE	4	22N	12W	Buffalo	0-225-263-2017		0.0	3.7	11.2	41.8	2.561	2.640	3.067	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
* HUBER 55-06-011-QRY Created On: 01/06/20 Updated On:	Q	SE	SE	4	22N	12W	Buffalo	0-225-26-2020	0.5	0.0	6.6	11.2	42.0	2.567	2.641	2.888	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
HUGHES 55-17-015-QRY Created On: 01/05/17 Updated On:	Q		SW	15	28N	14W	Dunn	0-225-47-2017		0.0	5.4	9.0	35.8	2.594	2.661	2.585	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
HUGHES 55-17-015-QRY Created On: 08/15/19 Updated On:	Q		SW	15	28N	14W	Dunn	0-225-261-2019	0.9	0.0	5.5	7.9	33.5	2.601	2.668	2.584	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
HUGHES 55-17-015-QRY Created On: 04/05/22 Updated On:	Q		SW	15	28N	14W	Dunn	0-225-161-2022	2.3	1.4	5.0	11.4	41.0	2.586	2.650	2.464	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
HUGHES 55-17-015-QRY Created On: 01/02/25 Updated On:	Q		SW	15	28N	14W	Dunn	0-225-36-2025	1.0	0.9	10.8	9.7	40.4	2.579	2.650	2.727	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
HUNZICKER 55-10-010-QRY Created On: 07/19/21 Updated On:	Q	SE	NE	16	26N	2W	Clark	0-225-245-2021	0.0	0.0	1.1	7.2	31.3	2.597	2.617	0.772	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
HUNZICKER 55-10-010-QRY Created On: 01/29/24 Updated On:	Q	SE	NE	16	26N	2W	Clark	0-225-162-2024	0.0	1.8	1.2	5.4	25.6	2.594	2.614	0.800	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
HURD PIT 55-53-017-PIT Created On: 03/30/15 Updated On:	P	NW	SW	15	4N	12E	Rock	0-225-108-2015	4.2	0.0	2.2	5.7	27.5	2.645	2.691	1.736	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
HURD PIT 55-53-017-PIT Created On: 04/20/23 Updated On:	P	NW	SW	15	4N	12E	Rock	0-225-202-2023	4.9	8.0	2.3	5.9	27.1	2.673	2.721	1.814	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
* HURD QUARRY 55-53-044-QRY Created On: 07/02/19 Updated On:	Q	NW	SW	15	4N	12E	Rock	0-225-233-2019		5.1	9.9	7.3	35.1	2.630	2.691	2.326	
	Approved Use : HMA<MT, HMA>=MT, Base Aggregate																
* HURD QUARRY 55-53-044-QRY Created On: 01/05/21 Updated On:	Q	NW	SW	15	4N	12E	Rock	0-225-78-2021		9.1	6.0	4.8	30.0	2.659	2.712	1.997	
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																
HUSTISFORD 55-14-012-QRY Created On: 01/21/16 Updated On:	Q	SE	SW	33	10N	16E	Dodge	0-225-69-2016		4.4	5.3	5.1	24.4	2.669	2.718	1.859	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
HUSTISFORD 55-14-012-QRY Created On: 02/05/19 Updated On:	Q	SE	SW	33	10N	16E	Dodge	0-225-97-2019		3.7	1.2	5.5	25.9	2.697	2.737	1.487	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
HUSTISFORD 55-14-012-QRY Created On: 01/04/22 Updated On:	Q	SE	SW	33	10N	16E	Dodge	0-225-87-2022	0.0	3.5	1.2	5.5	28.1	2.680	2.723	1.620	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
HUSTISFORD 55-14-012-QRY Created On: 01/02/25 Updated On:	Q	SE	SW	33	10N	16E	Dodge	0-225-4-2025	0.0	4.1	4.0	6.3	27.7	2.711	2.744	1.206	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
HWY 154 QUARRY 55-56-034-QRY Created On: 05/04/21 Updated On:	Q	SW	SW	30	11N	3E	Sauk	0-225-200-2021	3.1	9.8	4.1	11.7	41.4	2.606	2.657	1.943	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
HWY 154 QUARRY 55-56-034-QRY Created On: 03/12/25 Updated On:	Q	SW	SW	30	11N	3E	Sauk	0-225-172-2025	3.2	6.5	5.2	9.3	37.2	2.599	2.667	2.615	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
HWY 51 55-13-042-QRY Created On: 01/21/15 Updated On:	Q	SW	NE	17	8N	10E	Dane	0-225-73-2015	0.8	1.6	2.7	7.9	32.6	2.609	2.666	2.187	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
HWY 51 55-13-042-QRY Created On: 05/08/17 Updated On:	Q	SW	NE	17	8N	10E	Dane	0-225-176-2017	1.1	0.7	2.6	7.3	31.9	2.610	2.669	2.267	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
HWY 51 55-13-042-QRY Created On: 04/10/18 Updated On:	Q	SW	NE	17	8N	10E	Dane	0-225-162-2018	1.9	3.5	2.9	7.6	32.3	2.586	2.647	2.375	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
HWY 51 55-13-042-QRY Created On: 03/27/19 Updated On:	Q	SW	NE	17	8N	10E	Dane	0-225-117-2019	0.8	2.2	3.0	7.4	31.4	2.647	2.687	1.511	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
HWY 51 55-13-042-QRY Created On: 03/09/20 Updated On:	Q	SW	NE	17	8N	10E	Dane	0-225-120-2020	0.2	1.5	2.8	7.3	30.8	2.613	2.664	1.961	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
HWY 51 55-13-042-QRY Created On: 03/29/21 Updated On:	Q	SW	NE	17	8N	10E	Dane	0-225-159-2021	0.4	1.9	1.6	7.8	30.5	2.607	2.662	2.141	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
HWY 51 55-13-042-QRY Created On: 01/04/22 Updated On:	Q	SW	NE	17	8N	10E	Dane	0-225-6-2022	1.8	5.3	2.3	6.9	30.3	2.579	2.644	2.541	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
HWY 51 55-13-042-QRY Created On: 01/23/23 Updated On:	Q	SW	NE	17	8N	10E	Dane	0-225-130-2023	0.5	2.1	1.3	7.0	30.9	2.588	2.650	2.406	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
HWY 51 55-13-042-QRY Created On: 01/02/24 Updated On:	Q	SW	NE	17	8N	10E	Dane	0-225-74-2024	0.4	2.3	3.0	6.7	30.2	2.567	2.635	2.653	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
Source Name	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
HWY 51	Q	SW	NE	17	8N	10E	Dane	0-225-78-2025	1.7	2.4	1.3	7.0	29.9	2.605	2.660	2.105		
55-13-042-QRY	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
Created On: 01/02/25																		
Updated On:																		
HWY-11	Q	SE	NW	26	1N	2W	Grant	0-225-217-2021	0.8	2.9	3.4	9.4	37.2	2.608	2.667	2.256		
55-22-025-QRY	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
Created On: 06/01/21																		
Updated On:																		
HWY-11	Q	SE	NW	26	1N	2W	Grant	0-225-32-2024	0.7	3.4	4.9	10.7	36.8	2.561	2.636	2.904		
55-22-025-QRY	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
Created On: 01/02/24																		
Updated On:																		
HYDE	Q	NW	NE	26	6N	4E	Iowa	0-225-280-2024	0.8	17.6	3.3	10.1	38.6	2.580	2.657	2.974		
55-25-014-QRY	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
Created On: 06/25/24																		
Updated On:																		
HYDE	Q	NW	NE	26	6N	4E	Iowa	0-225-282-2024	0.9	8.5	3.6	10.9	38.2	2.584	2.655	2.744		
55-25-014-QRY	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
Created On: 06/27/24																		
Updated On:																		
INDERGAND	Q	SE	SE	20	2N	7E	Green	0-225-210-2015		10.9	6.6	5.5	27.0	2.637	2.698	2.309		
55-23-007-QRY	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
Created On: 07/16/15																		
Updated On:																		
INDERGAND	Q	SE	SE	20	2N	7E	Green	0-225-140-2016		9.3	7.7	5.0	28.1	2.632	2.689	2.175		
55-23-007-QRY	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
Created On: 04/12/16																		
Updated On:																		

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
INDERGAND 55-23-007-QRY Created On: 05/16/19 Updated On:	Q	SE	SE	20	2N	7E	Green	0-225-190-2019	0.0	7.5	10.2	5.6	25.2	2.637	2.697	2.259	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
INDERGAND 55-23-007-QRY Created On: 04/05/22 Updated On:	Q	SE	SE	20	2N	7E	Green	0-225-155-2022	0.5	8.6	7.6	5.3	26.5	2.607	2.676	2.659	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
INDERGAND 55-23-007-QRY Created On: 01/14/25 Updated On:	Q	SE	SE	20	2N	7E	Green	0-225-96-2025	0.1	12.5	4.8	5.5	29.7	2.656	2.713	2.129	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
* INDIAN LAKE 55-43-006-PIT Created On: 07/16/20 Updated On:	P	E	NE	6	38N	10E	Oneida	0-225-222-2020	0.1	0.0	1.2	4.5	20.1	2.688	2.711	0.856	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
* IRENE 17-01-010-QRY Created On: 05/01/18 Updated On:	Q		NW	9	43N	3E	Statewide	0-225-188-2018	0.2	4.8	4.8	7.6	37.9	2.599	2.662	2.393	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
* IRENE 17-01-010-QRY Created On: 08/10/20 Updated On:	Q		NW	9	43N	3E	Statewide	0-225-230-2020	0.2	10.2	3.9	8.5	35.5	2.603	2.665	2.378	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
IRON RIVER 26-00-008-PIT Created On: 01/05/17 Updated On:	P	SW	NW	22	43N	35W	Iron	0-225-40-2017	0.8	0.5	0.5	3.6	14.8	2.712	2.740	1.030	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
IRON RIVER 26-00-008-PIT Created On: 01/04/22 Updated On:	P	SW	NW	22	43N	35W	Iron	0-225-27-2022	0.0	0.5	0.6	3.4	15.1	2.715	2.736	0.752		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
IRVINE 55-61-009-QRY Created On: 07/02/15 Updated On:	Q	SW	NE	18	19N	7W	Trempealeau	0-225-205-2015		0.0	2.5	10.4	38.3	2.591	2.648	2.208		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
IRVINE 55-61-009-QRY Created On: 01/04/18 Updated On:	Q	SW	NE	18	19N	7W	Trempealeau	0-225-48-2018	0.7	0.0	5.8	9.3	36.2	2.603	2.667	2.483		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
IRVINE 55-61-009-QRY Created On: 01/04/21 Updated On:	Q	SW	NE	18	19N	7W	Trempealeau	0-225-4-2021	1.3	0.0	2.8	9.6	35.9	2.610	2.666	2.135		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
IRVINE 55-61-009-QRY Created On: 01/02/24 Updated On:	Q	SW	NE	18	19N	7W	Trempealeau	0-225-24-2024	0.6	7.8	10.6	13.5	46.5	2.572	2.645	2.820		
	Approved Use : CONCRETE, OGBC, Base Aggregate																	
ISENBERGER 55-10-011-QRY Created On: 09/28/16 Updated On:	Q	SW	NW	6	28N	4W	Clark	0-225-265-2016		0.0	1.0	4.3	18.6	3.015	3.026	0.342		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
ISENBERGER 55-10-011-QRY Created On: 01/08/19 Updated On:	Q	SW	NW	6	28N	4W	Clark	0-225-79-2019		0.0	0.6	3.1	14.9	3.038	3.046	0.289		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
ISENBERGER 55-10-011-QRY Created On: 01/04/22 Updated On:	Q	SW	NW	6	28N	4W	Clark	0-225-82-2022	0.0	0.0	2.0	3.9	17.7	2.785	2.797	0.442		
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
ISENBERGER 55-10-011-QRY Created On: 01/16/25 Updated On:	Q	SW	NW	6	28N	4W	Clark	0-225-137-2025	0.0	0.0	2.7	4.6	17.6	2.758	2.778	0.703		
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
* ISLAND STONE 55-15-030-QRY Created On: 06/28/22 Updated On:	Q	SW	SW	32	34N	30E	Door	0-225-237-2022	1.4	0.0	7.7	5.6	26.8	2.658	2.705	1.777		
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
ISON 55-21-011-PIT Created On: 08/16/16 Updated On:	P	SE	NW	19	37N	13E	Forest	0-225-240-2016		0.0	0.6	6.5	26.2	2.696	2.713	0.646		
Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																		
ISON 55-21-011-PIT Created On: 01/04/21 Updated On:	P	SE	NW	19	37N	13E	Forest	0-225-12-2021	0.0	1.6	0.8	4.8	21.3	2.673	2.695	0.795		
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
JACKSON 55-56-011-QRY Created On: 01/09/15 Updated On:	Q	SW	SW	6	10N	4E	Sauk	0-225-54-2015		0.0	4.0	11.9	40.5	2.561	2.632	2.764		
Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																		
JACKSON 55-56-011-QRY Created On: 01/03/18 Updated On:	Q	SW	SW	6	10N	4E	Sauk	0-225-9-2018	1.0	0.0	2.1	8.8	33.8	2.610	2.668	2.230		
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Coarse Sp. Gravity		Coarse Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
JACKSON 55-56-011-QRY Created On: 01/04/21 Updated On:	Q	SW	SW	6	10N	4E	Sauk	0-225-34-2021	0.5	0.0	0.4	7.9	32.5	2.635	2.685	1.882	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
JACKSON 55-56-011-QRY Created On: 01/29/24 Updated On:	Q	SW	SW	6	10N	4E	Sauk	0-225-153-2024	1.5	5.1	7.7	11.8	42.9	2.577	2.643	2.571	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
JACKSON COUNTY IRON MINE 55-27-004-QRY Created On: 04/10/17 Updated On:	Q	SE	SE	22	21N	3W	Jackson	0-225-120-2017		0.0	0.7	6.2	24.1	2.812	2.850	1.356	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
JACKSON COUNTY IRON MINE 55-27-004-QRY Created On: 01/08/20 Updated On:	Q	SE	SE	22	21N	3W	Jackson	0-225-62-2020		0.0	1.5	6.1	23.6	2.871	2.897	0.882	
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																
JACKSON COUNTY IRON MINE 55-27-004-QRY Created On: 01/03/23 Updated On:	Q	SE	SE	22	21N	3W	Jackson	0-225-60-2023	0.5	5.5	5.7	6.6	25.0	2.785	2.832	1.679	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
JACKSON COUNTY IRON MINE 55-27-004-QRY Created On: 11/29/23 Updated On:	Q	SE	SE	22	21N	3W	Jackson	0-225-251-2023	1.2	2.9	2.5	6.7	24.3	2.805	2.837	1.125	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
JACKSON COUNTY IRON MINE 55-27-004-QRY Created On: 01/02/25 Updated On:	Q	SE	SE	22	21N	3W	Jackson	0-225-82-2025	1.6	8.3	5.6	7.6	27.0	2.758	2.808	1.840	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
JADIN 55-31-006-PIT Created On: 07/31/18 Updated On:	P	NE	SE	31	25N	25E	Kewaunee	0-225-260-2018	4.5	0.0	3.0	7.2	30.8	2.667	2.697	1.107		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
JADIN 55-31-006-PIT Created On: 05/09/23 Updated On:	P	NE	SE	31	25N	25E	Kewaunee	0-225-217-2023	1.4	0.0	3.1	5.8	28.8	2.691	2.733	1.554		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
JADIN #2 55-15-009-QRY Created On: 06/27/18 Updated On:	Q	SW	NE	33	26N	24E	Door	0-225-242-2018		0.0	1.4	7.2	30.8	2.740	2.769	1.054		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
JADIN #2 55-15-009-QRY Created On: 01/14/21 Updated On:	Q	SW	NE	33	26N	24E	Door	0-225-122-2021	0.0	0.0	0.3	6.9	31.1	2.709	2.742	1.219		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
JADIN #2 55-15-009-QRY Created On: 04/15/24 Updated On:	Q	SW	NE	33	26N	24E	Door	0-225-232-2024	0.0	0.0	2.5	6.8	31.7	2.708	2.743	1.286		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
* JAECKS 55-35-027-PIT Created On: 06/25/20 Updated On:	P	SE	SW	1	34N	6E	Lincoln	0-225-208-2020	0.3	0.0	0.5	4.6	21.3	2.689	2.718	1.096		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
JANESVILLE SAND & GRAVEL 55-53-018-PIT Created On: 03/02/15 Updated On:	P	SE	SW	24	3N	12E	Rock	0-225-84-2015	2.0	6.2	2.1	6.7	30.0	2.628	2.679	1.925		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
JANESVILLE SAND & GRAVEL 55-53-018-PIT Created On: 01/08/20 Updated On:	P	SE	SW	24	3N	12E	Rock	0-225-50-2020	2.8	0.0	2.7	6.3	29.9	2.624	2.676	1.986	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
JANESVILLE SAND & GRAVEL 55-53-018-PIT Created On: 01/14/25 Updated On:	P	SE	SW	24	3N	12E	Rock	0-225-110-2025	4.0	0.0	3.5	6.2	29.1	2.622	2.669	1.794	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
JANNETTE CHILTON QUARRY 55-08-019-QRY Created On: 01/04/24 Updated On:	Q	SW	SW	20	18N	20E	Calumet	0-225-136-2024	0.1	0.0	0.4	5.4	25.3	2.791	2.806	0.552	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
JENKINS 55-11-018-QRY Created On: 05/11/17 Updated On:	Q			11	13N	10E	Columbia	0-225-184-2017		0.9	2.5	11.1	39.9	2.599	2.663	2.473	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
JENKINS 55-11-018-QRY Created On: 01/06/20 Updated On:	Q			11	13N	10E	Columbia	0-225-34-2020	0.2	0.9	2.7	9.9	38.8	2.602	2.663	2.366	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
JENKINS 55-11-018-QRY Created On: 01/03/23 Updated On:	Q			11	13N	10E	Columbia	0-225-69-2023	0.2	1.3	1.8	10.3	38.1	2.607	2.662	2.126	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
JENNEMAN 55-09-032-PIT Created On: 01/08/19 Updated On:	P		NE	6	30N	8W	Chippewa	0-225-77-2019	0.3	0.0	0.9	3.6	17.3	2.726	2.754	1.035	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
JENNEMAN 55-09-032-PIT Created On: 01/02/24 Updated On:	P		NE	6	30N	8W	Chippewa	0-225-85-2024	0.7	0.0	2.0	4.2	20.1	2.708	2.733	0.929	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
JET BLACK QUARRY 55-49-031-QRY Created On: 03/13/24 Updated On:	Q	NE	SW	25	25N	7E	Portage	0-225-200-2024	0.0	0.0	0.7	4.5	18.3	2.971	2.993	0.733	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
JOE KOHEGYI 55-26-012-PIT Created On: 07/21/17 Updated On:	P	NE	SW	31	43N	4E	Iron	0-225-238-2017		0.0	1.5	3.9	19.0	2.745	2.765	0.734	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
JOE KOHEGYI 55-26-012-PIT Created On: 04/15/24 Updated On:	P	NE	SW	31	43N	4E	Iron	0-225-231-2024	0.3	0.0	2.0	3.0	14.8	2.749	2.776	0.970	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
JOHNSON 55-03-024-PIT Created On: 05/23/23 Updated On:	P	NE	NW	5	35N	10W	Barron	0-225-227-2023	3.4	0.0	1.0	4.2	18.8	2.744	2.768	0.869	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
JOHNSON S&G - CROWBAR 55-67-016-PIT Created On: 03/06/25 Updated On:	P		NW	6	5N	20E	Waukesha	0-225-171-2025	1.9	12.3	3.1	4.3	22.5	2.683	2.721	1.429	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
JOHNSON S&G BOWERS ROAD 55-64-015-PIT Created On: 04/24/19 Updated On:	P		NE	2	3N	17E	Walworth	0-225-159-2019	2.1	0.0	3.8	4.0	26.4	2.678	2.713	1.293	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
JOHNSON S&G BOWERS ROAD 55-64-015-PIT Created On: 03/27/24 Updated On:	P		NE	2	3N	17E	Walworth	0-225-214-2024	0.8	9.2	0.8	4.2	25.8	2.711	2.748	1.365	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
* JONES 55-25-016-QRY Created On: 05/08/15 Updated On:	Q	SE	NE	22	5N	1E	Iowa	0-225-158-2015	0.6	3.4	6.9	14.6	48.5	2.522	2.616	3.719	
	Approved Use : CONCRETE, Base Aggregate																
* JONES 55-25-016-QRY Created On: 03/23/18 Updated On:	Q	SE	NE	22	5N	1E	Iowa	0-225-140-2018	2.0	5.7	1.9	13.5	45.8	2.529	2.615	3.401	
	Approved Use : CONCRETE, Base Aggregate																
* JONES 55-25-016-QRY Created On: 03/17/21 Updated On:	Q	SE	NE	22	5N	1E	Iowa	0-225-145-2021	1.0	7.6	2.1	15.8	48.7	2.489	2.591	4.117	
	Approved Use : CONCRETE, OGBC, Base Aggregate																
JORGENSEN 55-70-004-QRY Created On: 01/09/15 Updated On:	Q		NE	5	20N	17E	Winnebago	0-225-48-2015	0.1	9.2	4.4	6.2	28.8	2.729	2.761	1.149	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
JORGENSEN 55-70-004-QRY Created On: 01/04/18 Updated On:	Q		NE	5	20N	17E	Winnebago	0-225-55-2018		13.2	6.0	5.8	28.4	2.749	2.778	1.060	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
JORGENSEN 55-70-004-QRY Created On: 01/05/21 Updated On:	Q		NE	5	20N	17E	Winnebago	0-225-51-2021	0.0	10.5	2.0	6.4	30.2	2.729	2.761	1.202	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
JORGENSON 55-70-004-QRY Created On: 01/02/24 Updated On:	Q		NE	5	20N	17E	Winnebago	0-225-54-2024	0.0	14.4	10.1	9.0	34.9	2.695	2.734	1.468	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
JULIUS WIEST 55-22-028-QRY Created On: 04/25/17 Updated On:	Q	NE	NW	26	3N	5W	Grant	0-225-152-2017	0.2	15.9	7.0	10.9	41.3	2.562	2.639	2.987	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
JULIUS WIEST 55-22-028-QRY Created On: 04/19/19 Updated On:	Q	NE	NW	26	3N	5W	Grant	0-225-158-2019	0.8	11.1	10.9	12.4	42.9	2.584	2.652	2.647	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
JULIUS WIEST 55-22-028-QRY Created On: 01/04/22 Updated On:	Q	NE	NW	26	3N	5W	Grant	0-225-48-2022	0.9	15.9	0.8	9.7	36.0	2.578	2.651	2.840	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
JULIUS WIEST 55-22-028-QRY Created On: 01/02/25 Updated On:	Q	NE	NW	26	3N	5W	Grant	0-225-30-2025	0.2	3.4	0.5	11.2	38.2	2.571	2.645	2.874	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
* JUMP RIVER 55-60-015-QRY Created On: 07/07/22 Updated On:	Q	NE	SE	14	33N	4W	Taylor	0-225-247-2022	0.0	0.0	0.5	4.7	21.6	2.662	2.676	0.519	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
JUMP RIVER PIT 55-60-037-PIT Created On: 01/02/24 Updated On:	P	SW	NE	13	33N	4W	Taylor	0-225-115-2024	0.2	0.0	5.5	4.3	19.9	2.732	2.770	1.387	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
K & N 55-67-019-PIT Created On: 02/05/19 Updated On:	P	S	9	8N	19E	Waukesha		0-225-96-2019		4.0	1.1	4.5	23.4	2.733	2.758	0.908	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
K & N 55-67-019-PIT Created On: 01/02/24 Updated On:	P	S	9	8N	19E	Waukesha		0-225-16-2024	0.1	2.3	1.8	5.2	23.9	2.730	2.756	0.960	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
K QUARRY 55-71-018-QRY Created On: 04/14/16 Updated On:	Q	SW	SW	13	24N	4E	Wood	0-225-147-2016		0.0	0.7	4.0	17.1	2.701	2.728	1.012	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
K QUARRY 55-71-018-QRY Created On: 01/04/21 Updated On:	Q	SW	SW	13	24N	4E	Wood	0-225-1-2021	0.5	0.0	2.9	3.4	15.5	2.699	2.718	0.710	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
K QUARRY 55-71-018-QRY Created On: 02/28/24 Updated On:	Q	SW	SW	13	24N	4E	Wood	0-225-172-2024	0.2	0.0	1.9	2.9	17.0	2.755	2.775	0.739	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
K-PIT ONEIDA 55-43-011-PIT Created On: 06/13/18 Updated On:	P	NW	NW	6	36N	8E	Oneida	0-225-228-2018	1.8	0.0	1.8	7.3	28.2	2.690	2.715	0.914	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
K-PIT ONEIDA 55-43-011-PIT Created On: 01/19/23 Updated On:	P	NW	NW	6	36N	8E	Oneida	0-225-129-2023	1.0	0.0	3.5	5.7	24.7	2.664	2.698	1.299	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
* KAASA 55-47-015-QRY Created On: 01/12/15 Updated On:	Q			15	24N	16W	Pierce	0-225-61-2015		0.0	5.4	11.6	42.0	2.551	2.623	2.801	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
* KAASA 55-47-015-QRY Created On: 01/03/18 Updated On:	Q			15	24N	16W	Pierce	0-225-35-2018	1.4	0.0	5.1	8.3	30.5	2.637	2.683	1.757	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
* KAASA 55-47-015-QRY Created On: 01/05/21 Updated On:	Q			15	24N	16W	Pierce	0-225-72-2021	1.8	0.0	0.6	9.0	32.3	2.660	2.701	1.557	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
KAFKA QUARRY 55-37-039-QRY Created On: 01/03/17 Updated On:	Q	NE	NW	3	27N	3E	Marathon	0-225-6-2017		0.0	0.5	2.0	10.6	2.776	2.785	0.325	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
KAFKA QUARRY 55-37-039-QRY Created On: 01/07/20 Updated On:	Q	NE	NW	3	27N	3E	Marathon	0-225-42-2020	0.0	0.0	0.1	2.5	10.8	2.800	2.805	0.201	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
KAFKA QUARRY 55-37-039-QRY Created On: 01/03/23 Updated On:	Q	NE	NW	3	27N	3E	Marathon	0-225-37-2023	0.0	0.8	0.6	3.5	14.6	2.749	2.766	0.638	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
KALATA 55-70-005-QRY Created On: 01/12/16 Updated On:	Q	NE	NE	27	19N	14E	Winnebago	0-225-52-2016	0.2	1.7	3.3	9.1	36.0	2.692	2.731	1.436	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Coarse Sp. Gravity		Coarse Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
KALATA 55-70-005-QRY Created On: 05/24/19 Updated On:	Q	NE	NE	27	19N	14E	Winnebago	0-225-198-2019	0.9	0.8	1.9	8.0	33.5	2.701	2.739	1.422	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
KALATA 55-70-005-QRY Created On: 01/04/22 Updated On:	Q	NE	NE	27	19N	14E	Winnebago	0-225-17-2022	1.8	2.0	4.5	9.9	37.6	2.656	2.703	1.751	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
KALATA 55-70-005-QRY Created On: 01/02/24 Updated On:	Q	NE	NE	27	19N	14E	Winnebago	0-225-107-2024	0.3	1.2	3.9	8.0	35.0	2.679	2.720	1.510	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
KAMPMEIER 55-13-045-QRY Created On: 04/09/15 Updated On:	Q	SW	SW	26	7N	10E	Dane	0-225-119-2015	7.0	16.1	17.1	12.4	44.0	2.493	2.591	3.926	
	Approved Use : Base Aggregate																
KAMPMEIER 55-13-045-QRY Created On: 01/04/22 Updated On:	Q	SW	SW	26	7N	10E	Dane	0-225-58-2022	3.1	6.8	5.2	10.1	37.7	2.574	2.641	2.610	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
KAMPMEIER 55-13-045-QRY Created On: 01/02/25 Updated On:	Q	SW	SW	26	7N	10E	Dane	0-225-54-2025	3.4	2.8	7.8	8.3	34.0	2.575	2.641	2.577	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
KAUKAUNA 55-44-017-QRY Created On: 05/26/16 Updated On:	Q			18	21N	19E	Outagamie	0-225-190-2016	0.2	23.1	17.0	5.3	24.3	2.732	2.766	1.242	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Coarse Sp. Gravity		Coarse Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
KAUKAUNA 55-44-017-QRY Created On: 02/03/17 Updated On:	Q			18	21N	19E	Outagamie	0-225-62-2017		23.5	16.7	4.8	21.2	2.766	2.789	0.824	
KAUKAUNA 55-44-017-QRY Created On: 01/15/25 Updated On:	Q			18	21N	19E	Outagamie	0-225-128-2025	0.3	25.2	14.6	5.6	24.6	2.719	2.753	1.272	
KAUKAUNA 55-44-017-QRY Created On: 04/21/25 Updated On:	Q			18	21N	19E	Outagamie	0-225-196-2025		11.2	8.0	4.9	20.8	2.756	2.783	0.987	
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																
KAUKAUNA 55-44-017-QRY Created On: 05/14/25 Updated On:	Q			18	21N	19E	Outagamie	0-225-213-2025		12.8	3.7	5.2	22.6	2.742	2.777	1.301	
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																
KAZMIERKOWSKI PIT 55-54-011-PIT Created On: 07/12/23 Updated On:	P	SW	SE	9	34N	8W	Rusk	0-225-237-2023	1.3	0.0	0.7	5.4	23.8	2.677	2.697	0.724	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
KEILER 55-22-068-QRY Created On: 01/02/25 Updated On:	Q	NW	SW	4	1N	2W	Grant	0-225-88-2025	15.4	8.5	16.2	7.1	35.6	2.497	2.587	3.576	
	Approved Use : Base Aggregate																
KELLEY 55-69-018-PIT Created On: 11/12/18 Updated On:	P	NE	NE	22	19N	3E	Waushara	0-225-291-2018	1.5	0.0	1.7	6.9	27.9	2.730	2.756	0.975	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
Source Name	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
KELLEY 55-69-018-PIT Created On: 06/26/23 Updated On:	P	NE	NE	22	19N	3E	Waushara	0-225-236-2023		0.0	0.1	5.6	25.5	2.739	2.766	0.991		
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																	
KELLEY 55-04-019-PIT Created On: 10/04/21 Updated On:	P	SW	NW	25	43N	8W	Bayfield	0-225-266-2021	0.9	0.0	1.6	3.8	17.5	2.811	2.837	0.950		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
KELLY 55-13-047-QRY Created On: 04/06/16 Updated On:	Q	SW	SW	14	6N	7E	Dane	0-225-125-2016	0.2	15.7	7.7	9.7	36.0	2.582	2.655	2.854		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
* KELLY 55-43-007-PIT Created On: 04/19/19 Updated On:	P	NE	SE	32	38N	11E	Oneida	0-225-151-2019	1.1	0.0	0.4	5.3	22.9	2.689	2.714	0.954		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
KELLY 55-13-047-QRY Created On: 06/03/19 Updated On:	Q	SW	SW	14	6N	7E	Dane	0-225-203-2019	0.7	5.3	0.5	8.1	33.6	2.583	2.656	2.826		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
* KELLY 55-43-007-PIT Created On: 07/30/20 Updated On:	P	NE	SE	32	38N	11E	Oneida	0-225-227-2020	0.0	0.0	0.2	4.1	22.0	2.751	2.767	0.581		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
KELLY 55-13-047-QRY Created On: 01/04/22 Updated On:	Q	SW	SW	14	6N	7E	Dane	0-225-56-2022	0.7	5.0	2.4	6.7	28.9	2.581	2.648	2.573		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
KELLY 55-13-047-QRY Created On: 02/07/25 Updated On:	Q	SW	SW	14	6N	7E	Dane	0-225-151-2025	0.5	5.3	1.7	7.1	29.0	2.581	2.647	2.543	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
KELLY QUARRY 55-43-034-QRY Created On: 01/03/23 Updated On:	Q	NE	SE	32	38N	11E	Oneida	0-225-25-2023	0.0	0.0	0.5	7.6	30.4	2.751	2.767	0.581	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
KESSLER 55-99-068-PIT Created On: 01/04/22 Updated On:	P	SE	SE	6	41N	4E		0-225-26-2022	0.0	0.6	2.1	3.0	15.6	2.775	2.802	0.979	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
KETTLESON 55-11-041-PIT Created On: 05/02/17 Updated On:	P	NW	NE	6	13N	7E	Columbia	0-225-163-2017		0.0	3.7	9.4	33.1	2.770	2.803	1.191	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
KETTLESON 55-11-041-PIT Created On: 01/04/22 Updated On:	P	NW	NE	6	13N	7E	Columbia	0-225-12-2022	0.5	0.0	1.5	6.4	27.6	2.773	2.803	1.093	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
KIMBALL 55-26-013-QRY Created On: 04/23/15 Updated On:	Q		S	1	46N	1E	Iron	0-225-129-2015		0.0	1.6	2.6	12.0	2.733	2.764	1.142	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
KIMBALL 55-26-013-QRY Created On: 01/04/18 Updated On:	Q		S	1	46N	1E	Iron	0-225-60-2018	0.3	0.0	2.3	2.6	12.2	2.685	2.719	1.274	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
KIMBALL 55-26-013-QRY Created On: 04/30/21 Updated On:	Q		S	1	46N	1E	Iron	0-225-194-2021	0.3	0.0	2.4	2.6	12.3	2.700	2.736	1.344	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
KIMBALL 55-26-013-QRY Created On: 11/25/24 Updated On:	Q		S	1	46N	1E	Iron	0-225-315-2024	0.0	0.0	0.8	2.5	12.1	2.642	2.676	1.278	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
KIMMES 55-16-011-QRY Created On: 02/13/17 Updated On:	Q	SW	NW	14	47N	14W	Douglas	0-225-67-2017		0.0	10.0	4.9	20.6	2.692	2.731	1.468	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
KIMMES 55-16-011-QRY Created On: 01/08/20 Updated On:	Q	SW	NW	14	47N	14W	Douglas	0-225-56-2020	0.0	0.0	4.2	2.8	13.6	2.756	2.786	1.086	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
KIMMES 55-16-011-QRY Created On: 01/03/23 Updated On:	Q	SW	NW	14	47N	14W	Douglas	0-225-56-2023	0.0	4.8	1.6	3.3	13.3	2.771	2.800	1.051	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
KING 55-43-008-QRY Created On: 04/05/16 Updated On:	Q	NW	NW	19	38N	10E	Oneida	0-225-121-2016		0.0	0.3	9.5	40.2	2.608	2.623	0.586	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
KING 55-41-011-QRY Created On: 04/07/16 Updated On:	Q	SE	SE	1	16N	1W	Monroe	0-225-130-2016		0.0	3.0	8.1	34.4	2.637	2.690	1.999	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Coarse Sp. Gravity		Coarse Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
KING 55-41-011-QRY Created On: 05/04/17 Updated On:	Q	SE	SE	1	16N	1W	Monroe	0-225-172-2017		0.0	11.7	8.3	36.6	2.621	2.680	2.244	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
KING 55-43-008-QRY Created On: 01/07/19 Updated On:	Q	NW	NW	19	38N	10E	Oneida	0-225-69-2019		0.0	0.2	6.3	29.5	2.616	2.628	0.479	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
KING 55-41-011-QRY Created On: 04/02/20 Updated On:	Q	SE	SE	1	16N	1W	Monroe	0-225-140-2020	0.0	0.0	4.4	8.6	34.7	2.616	2.675	2.257	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
KING 55-43-008-QRY Created On: 07/16/20 Updated On:	Q	NW	NW	19	38N	10E	Oneida	0-225-219-2020	0.0	0.0	0.2	7.6	36.4	2.608	2.622	0.563	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
KING 55-43-008-QRY Created On: 01/03/23 Updated On:	Q	NW	NW	19	38N	10E	Oneida	0-225-20-2023	0.7	0.0	0.7	5.8	28.8	2.622	2.639	0.652	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
KING 55-41-011-QRY Created On: 05/22/23 Updated On:	Q	SE	SE	1	16N	1W	Monroe	0-225-221-2023	0.8	10.5	6.1	10.3	39.6	2.593	2.661	2.622	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
KINGS BLUFF 55-32-010-QRY Created On: 09/02/15 Updated On:	Q	W	NE	25	18N	8W	La Crosse	0-225-235-2015	1.6	0.0	3.6	10.9	40.9	2.580	2.649	2.670	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse					
	P/Q	Qrt	Qrt	Sect	Town	Range	County	LA Wear (%)					Sp. Gravity		Absorp. %			
								100					500	OD	SSD	Crse	Fine	
KINGS BLUFF 55-32-010-QRY Created On: 04/25/17 Updated On:	Q	W	NE	25	18N	8W	La Crosse	0-225-156-2017		0.0	3.0	12.0	44.3	2.584	2.650	2.532		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
KINGS BLUFF 55-32-010-QRY Created On: 03/23/18 Updated On:	Q	W	NE	25	18N	8W	La Crosse	0-225-145-2018	0.9	0.0	9.9	13.7	45.3	2.572	2.644	2.793		
	Approved Use : CONCRETE, Base Aggregate																	
KINGS BLUFF 55-32-010-QRY Created On: 01/07/19 Updated On:	Q	W	NE	25	18N	8W	La Crosse	0-225-48-2019	1.9	0.0	3.2	11.0	42.9	2.593	2.654	2.373		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
KINGS BLUFF 55-32-010-QRY Created On: 01/04/22 Updated On:	Q	W	NE	25	18N	8W	La Crosse	0-225-10-2022	1.1	3.0	6.6	11.0	42.6	2.589	2.655	2.544		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
KINGS BLUFF 55-32-010-QRY Created On: 01/14/25 Updated On:	Q	W	NE	25	18N	8W	La Crosse	0-225-101-2025	0.6	1.8	4.8	9.7	40.8	2.591	2.656	2.512		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
KIPPLEY 55-13-048-QRY Created On: 05/26/16 Updated On:	Q	NW	NE	11	8N	9E	Dane	0-225-186-2016	1.0	2.8	1.4	10.0	37.1	2.548	2.619	2.798		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
KIPPLEY 55-13-048-QRY Created On: 01/04/23 Updated On:	Q	NW	NE	11	8N	9E	Dane	0-225-99-2023	1.9	2.5	3.0	12.0	41.6	2.510	2.590	3.200		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
KISSER 55-15-013-QRY Created On: 01/04/16 Updated On:	Q	NW	NW	20	27N	25E	Door	0-225-9-2016		3.0	2.5	6.4	26.3	2.762	2.788	0.957	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
KISSER 55-15-013-QRY Created On: 01/08/19 Updated On:	Q	NW	NW	20	27N	25E	Door	0-225-73-2019		0.0	3.0	7.8	32.2	2.790	2.817	0.997	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
KISSER 55-15-013-QRY Created On: 01/10/22 Updated On:	Q	NW	NW	20	27N	25E	Door	0-225-97-2022	0.0	1.7	1.7	6.5	29.2	2.750	2.778	0.995	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
KISSER 55-15-013-QRY Created On: 01/02/25 Updated On:	Q	NW	NW	20	27N	25E	Door	0-225-60-2025	0.0	2.3	2.0	6.2	26.3	2.763	2.788	0.880	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
KLAR 55-22-031-QRY Created On: 06/30/16 Updated On:	Q	NW	NW	33	3N	2W	Grant	0-225-217-2016		5.4	4.3	11.7	40.9	2.580	2.653	2.810	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
KLAR 55-22-031-QRY Created On: 07/28/17 Updated On:	Q	NW	NW	33	3N	2W	Grant	0-225-244-2017	2.3	6.0	2.2	11.1	40.3	2.575	2.649	2.872	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
KLAR 55-22-031-QRY Created On: 04/28/20 Updated On:	Q	NW	NW	33	3N	2W	Grant	0-225-157-2020	0.7	3.3	1.8	9.8	36.6	2.604	2.667	2.432	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
KLAR 55-22-031-QRY Created On: 01/03/23 Updated On:	Q	NW	NW	33	3N	2W	Grant	0-225-11-2023	1.0	2.8	4.2	9.3	35.6	2.575	2.646	2.751	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
* KLAVER 55-43-009-PIT Created On: 06/25/20 Updated On:	P	NW	SE	4	36N	8E	Oneida	0-225-209-2020	0.1	0.0	0.6	5.1	23.4	2.737	2.759	0.791	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
KLINGAMEYER-LARUE 55-56-015-QRY Created On: 08/16/16 Updated On:	Q		NW	22	11N	5E	Sauk	0-225-245-2016		0.0	0.2	5.5	24.1	2.619	2.632	0.495	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
KLINGAMEYER-LARUE 55-56-015-QRY Created On: 04/06/21 Updated On:	Q		NW	22	11N	5E	Sauk	0-225-170-2021	1.3	0.4	0.5	6.5	26.6	2.599	2.621	0.843	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
KLINGAMEYER-LARUE 55-56-015-QRY Created On: 01/02/24 Updated On:	Q		NW	22	11N	5E	Sauk	0-225-69-2024	0.5	0.2	0.4	6.0	23.8	2.603	2.627	0.914	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
* KLITZKE 55-23-009-QRY Created On: 03/19/15 Updated On:	Q			16	4N	7E	Green	0-225-97-2015		5.6	6.7	14.1	46.7	2.510	2.611	4.014	
	Approved Use : CONCRETE, Base Aggregate																
* KLITZKE 55-23-009-QRY Created On: 05/11/18 Updated On:	Q			16	4N	7E	Green	0-225-211-2018	1.7	6.8	7.7	12.3	41.5	2.546	2.634	3.485	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
* KLITZKE 55-23-009-QRY Created On: 04/30/21 Updated On:	Q			16	4N	7E	Green	0-225-195-2021	0.1	22.4	3.8	10.4	38.2	2.582	2.655	2.836	
* KLITZKE 55-23-009-QRY Created On: 08/11/21 Updated On:	Q			16	4N	7E	Green	0-225-258-2021	0.1	5.0	7.4	10.8	37.5	2.595	2.654	2.282	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
KNUTSON 55-03-026-PIT Created On: 04/07/16 Updated On:	P	SW	SE	22	32N	11W	Barron	0-225-128-2016		0.0	1.7	4.6	20.3	2.698	2.729	1.168	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
KNUTSON 55-03-026-PIT Created On: 07/19/21 Updated On:	P	SW	SE	22	32N	11W	Barron	0-225-247-2021	3.5	0.0	1.3	4.3	20.2	2.677	2.709	1.178	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
* KOCH QUARRY 55-52-028-QRY Created On: 05/03/22 Updated On:	Q	SE	NE	18	11N	2E	Richland	0-225-198-2022	0.7	7.5	9.3	11.3	42.4	2.588	2.661	2.816	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
KOEPEL 55-34-015-PIT Created On: 06/13/22 Updated On:	P		NW	12	30N	12E	Langlade	0-225-228-2022	0.0	0.5	0.3	6.6	29.3	2.671	2.691	0.743	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
KOHN 55-11-019-PIT Created On: 05/03/22 Updated On:	P			30	12N	11E	Columbia	0-225-193-2022	2.7	4.5	3.6	5.9	27.9	2.717	2.754	1.376	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
KORDUS AGGREGATES 55-51-057-PIT Created On: 06/25/21 Updated On:	P	S	SW	7	2N	19E	Racine	0-225-235-2021	1.2	10.9	5.3	7.4	31.0	2.656	2.708	1.942	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
KOSSUTH QUARRY 55-36-048-QRY Created On: 03/28/18 Updated On:	Q	W	SE	36	20N	23E	Manitowoc	0-225-151-2018	0.0	0.8	0.4	7.4	33.2	2.794	2.811	0.633	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
KOSSUTH QUARRY 55-36-048-QRY Created On: 01/05/21 Updated On:	Q	W	SE	36	20N	23E	Manitowoc	0-225-106-2021	0.0	1.0	2.2	8.1	33.3	2.752	2.780	1.045	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
KOSSUTH QUARRY 55-36-048-QRY Created On: 01/04/24 Updated On:	Q	W	SE	36	20N	23E	Manitowoc	0-225-135-2024	0.0	0.0	0.8	10.1	37.8	2.766	2.790	0.852	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
KRAEMER 55-59-008-PIT Created On: 01/21/16 Updated On:	P	SW	NE	13	14N	20E	Sheboygan	0-225-64-2016	0.5	0.0	0.8	6.0	28.8	2.752	2.778	0.927	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
KRAEMER 55-59-008-PIT Created On: 01/05/21 Updated On:	P	SW	NE	13	14N	20E	Sheboygan	0-225-108-2021	0.5	2.2	0.7	5.6	26.9	2.740	2.767	0.981	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
KRAUS 55-50-011-PIT Created On: 06/26/19 Updated On:	P	E	NE	7	34N	3E	Price	0-225-231-2019	2.0	0.0	2.0	4.6	20.0	2.691	2.725	1.263	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
KRAUS 55-50-011-PIT Created On: 01/02/24 Updated On:	P	E	NE	7	34N	3E	Price	0-225-113-2024	7.1	0.0	5.9	6.4	24.0	2.674	2.714	1.513	
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																
KREPLINE 55-08-012-QRY Created On: 05/26/16 Updated On:	Q	NE	NE	34	19N	19E	Calumet	0-225-191-2016		0.0	2.8	8.3	35.1	2.689	2.727	1.415	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
KREPLINE 55-08-012-QRY Created On: 04/24/19 Updated On:	Q	NE	NE	34	19N	19E	Calumet	0-225-167-2019	0.1	0.0	0.5	13.1	49.1	2.671	2.706	1.319	
	Approved Use : HMA<MT, CONCRETE, Base Aggregate																
KREPLINE 55-08-012-QRY Created On: 04/15/25 Updated On:	Q	NE	NE	34	19N	19E	Calumet	0-225-190-2025	0.0	0.0	1.4	13.4	50.3	2.658	2.697	1.482	
	Approved Use : HMA<MT, CONCRETE, OGBC, Base Aggregate																
* KREUGER 55-13-050-QRY Created On: 06/10/15 Updated On:	Q	SW	SW	3	6N	11E	Dane	0-225-194-2015		24.6	6.9	6.0	30.0	2.641	2.699	2.220	
* KREUGER 55-13-050-QRY Created On: 08/05/15 Updated On:	Q	SW	SW	3	6N	11E	Dane	0-225-224-2015		9.1	11.1	7.1	31.7	2.641	2.701	2.300	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
* KREUGER 55-13-050-QRY Created On: 01/04/18 Updated On:	Q	SW	SW	3	6N	11E	Dane	0-225-65-2018	0.3	1.7	8.1	5.6	27.7	2.657	2.707	1.912	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Coarse Sp. Gravity		Coarse Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
* KREUGER 55-13-050-QRY Created On: 06/14/21 Updated On:	Q	SW	SW	3	6N	11E	Dane	0-225-223-2021	0.6	7.9	7.2	5.4	26.7	2.679	2.730	1.906	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
KROENING 55-58-014-QRY Created On: 01/07/15 Updated On:	Q			24	26N	17E	Shawano	0-225-16-2015		11.1	12.8	7.5	28.7	2.674	2.721	1.762	
	Approved Use : Base Aggregate																
KROENING 55-58-014-QRY Created On: 01/04/18 Updated On:	Q			24	26N	17E	Shawano	0-225-58-2018	0.6	11.6	15.2	8.8	32.3	2.640	2.696	2.126	
	Approved Use : Base Aggregate																
KROENING 55-58-014-QRY Created On: 01/04/19 Updated On:	Q			24	26N	17E	Shawano	0-225-38-2019	1.4	20.7	15.4	7.2	28.0	2.638	2.698	2.278	
KROENING 55-58-014-QRY Created On: 01/02/20 Updated On:	Q			24	26N	17E	Shawano	0-225-10-2020	1.6	14.3	13.1	7.0	28.2	2.662	2.713	1.937	
	Approved Use : Base Aggregate																
KROENING 55-58-014-QRY Created On: 01/03/23 Updated On:	Q			24	26N	17E	Shawano	0-225-78-2023	1.8	8.0	7.0	6.0	25.7	2.715	2.748	1.198	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
* KROPP AB 55-31-020-QRY Created On: 02/11/19 Updated On:	Q	NE	SE	15	22N	23E	Kewaunee	0-225-105-2019		0.0	1.7	7.9	34.6	2.810	2.823	0.456	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
* KROPP AB 55-31-020-QRY Created On: 04/28/22 Updated On:	Q	NE	SE	15	22N	23E	Kewaunee	0-225-187-2022	0.2	0.0	3.4	8.1	35.0	2.780	2.801	0.737		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
KRUEGER 55-42-017-QRY Created On: 01/07/16 Updated On:	Q	SE	SE	6	27N	21E	Oconto	0-225-35-2016	0.0	1.2	2.5	6.3	29.1	2.693	2.728	1.313		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
KRUEGER 55-42-017-QRY Created On: 01/25/19 Updated On:	Q	SE	SE	6	27N	21E	Oconto	0-225-91-2019	0.3	13.2	4.0	6.4	29.0	2.668	2.708	1.509		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
KRUEGER 55-42-017-QRY Created On: 01/04/22 Updated On:	Q	SE	SE	6	27N	21E	Oconto	0-225-93-2022	0.1	2.4	3.4	5.7	27.8	2.710	2.740	1.084		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
KRUEGER 55-13-051-QRY Created On: 04/04/23 Updated On:	Q	SE	SW	32	5N	8E	Dane	0-225-180-2023	0.6	14.7	10.1	10.1	39.8	2.523	2.614	3.604		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
KRUEGER 55-42-017-QRY Created On: 01/14/25 Updated On:	Q	SE	SE	6	27N	21E	Oconto	0-225-105-2025	0.6	9.4	6.3	6.2	29.0	2.657	2.698	1.530		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
KRUG 55-60-012-PIT Created On: 05/24/19 Updated On:	P			28	32N	1E	Taylor	0-225-201-2019	0.1	0.0	1.7	3.9	17.5	2.723	2.750	0.972		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
Source Name	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
KRUG 55-60-012-PIT Created On: 01/02/24 Updated On:	P			28	32N	1E	Taylor	0-225-112-2024	0.1	0.0	4.2	3.8	17.9	2.717	2.751	1.222		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
KUCZMARSKI 55-43-037-PIT Created On: 01/02/24 Updated On:	P	W	SE	26	37N	10E	Oneida	0-225-64-2024	0.2	0.0	1.1	4.3	20.6	2.716	2.736	0.722		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
KUNKEL QUARRY 55-22-066-QRY Created On: 05/22/23 Updated On:	Q	SE	NE	15	1N	2W	Grant	0-225-220-2023	2.0	2.8	2.7	13.2	42.6	2.529	2.615	3.406		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
LABINE 55-21-21-PIT Created On: 08/22/17 Updated On:	P	S	SW	12	37N	16E	Forest	0-225-258-2017	0.8	0.0	0.5	5.1	19.9	2.741	2.762	0.732		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
LABINE 55-21-21-PIT Created On: 06/13/22 Updated On:	P	S	SW	12	37N	16E	Forest	0-225-227-2022	0.0	0.6	0.8	4.0	18.0	2.724	2.743	0.691		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
LADYSMITH EAST 55-54-012-PIT Created On: 01/03/18 Updated On:	P	S	NW	15	35N	6W	Rusk	0-225-30-2018	1.0	0.0	1.3	4.2	19.1	2.727	2.752	0.906		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
LADYSMITH EAST 55-54-012-PIT Created On: 01/10/23 Updated On:	P	S	NW	15	35N	6W	Rusk	0-225-109-2023	1.1	0.0	2.6	3.8	19.1	2.687	2.718	1.173		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
LADYSMITH WEST 55-54-022-PIT Created On: 03/08/18 Updated On:	P	SE	NW	16	35N	6W	Rusk	0-225-117-2018	1.8	0.0	2.4	4.0	18.9	2.688	2.721	1.225	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
LADYSMITH WEST 55-54-022-PIT Created On: 03/06/23 Updated On:	P	SE	NW	16	35N	6W	Rusk	0-225-163-2023	0.0	0.0	1.0	4.4	19.1	2.733	2.761	1.051	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
* LAFARGE KENDALL 17-00-017-QRY Created On: 04/30/21 Updated On:	Q		W	29	35N	7E	Kendall, IL	0-225-199-2021	0.6	1.9	0.4	6.8	29.0	2.695	2.727	1.213	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
LAGESSE 55-09-036-PIT Created On: 08/19/15 Updated On:	P	SE	SE	7	30N	8W	Chippewa	0-225-228-2015		0.0	0.7	4.5	20.3	2.739	2.761	0.799	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
LAGESSE 55-09-036-PIT Created On: 01/09/20 Updated On:	P	SE	SE	7	30N	8W	Chippewa	0-225-86-2020	0.7	0.0	0.9	3.7	17.9	2.717	2.745	1.050	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
LAGESSE 55-09-036-PIT Created On: 01/02/25 Updated On:	P	SE	SE	7	30N	8W	Chippewa	0-225-16-2025	0.7	1.8	2.2	3.4	17.4	2.693	2.724	1.183	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
LAGRANGE 55-64-024-PIT Created On: 02/05/19 Updated On:	P	W	SE	20	4N	16E	Walworth	0-225-94-2019	0.9	7.0	0.5	4.3	22.4	2.695	2.731	1.337	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
LAGRANGE 55-64-024-PIT Created On: 01/02/24 Updated On:	P	W	SE	20	4N	16E	Walworth	0-225-17-2024	0.0	4.5	2.9	4.8	23.2	2.705	2.738	1.224		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
LAKETOWN 55-48-015-QRY Created On: 05/07/15 Updated On:	Q	SW	SE	12	36N	18W	Polk	0-225-149-2015		0.0	0.5	0.9	9.3	2.993	3.000	0.243		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
LAKETOWN 55-48-015-QRY Created On: 05/21/18 Updated On:	Q	SW	SE	12	36N	18W	Polk	0-225-215-2018	0.0	0.0	1.4	2.5	11.3	2.967	2.979	0.405		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
LAKETOWN 55-48-015-QRY Created On: 01/04/21 Updated On:	Q	SW	SE	12	36N	18W	Polk	0-225-38-2021	0.0	0.3	0.2	1.7	8.0	2.998	3.009	0.384		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
LAKETOWN 55-48-015-QRY Created On: 01/04/24 Updated On:	Q	SW	SE	12	36N	18W	Polk	0-225-142-2024	0.0	0.1	0.2	1.9	9.2	2.989	3.001	0.384		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
LANGE (CAREY) 55-33-013-QRY Created On: 10/10/16 Updated On:	Q	NE	SE	6	2N	3E	Lafayette	0-225-266-2016	3.3	2.6	1.6	8.3	33.3	2.545	2.620	2.968		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
LANGE (CAREY) 55-33-013-QRY Created On: 01/07/19 Updated On:	Q	NE	SE	6	2N	3E	Lafayette	0-225-56-2019	3.2	6.2	3.8	10.9	38.1	2.530	2.609	3.125		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
LANGE (CAREY) 55-33-013-QRY Created On: 01/10/22 Updated On:	Q	NE	SE	6	2N	3E	Lafayette	0-225-106-2022	2.2	8.1	8.8	10.4	39.6	2.502	2.594	3.681	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
LANGE (CAREY) 55-33-013-QRY Created On: 01/02/25 Updated On:	Q	NE	SE	6	2N	3E	Lafayette	0-225-85-2025	2.0	12.7	3.4	9.8	34.8	2.569	2.640	2.747	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
LANNON LISBON PIT 55-67-024-PIT Created On: 01/08/15 Updated On:	P		SW	24	8N	19E	Waukesha	0-225-31-2015	0.8	2.9	4.9	6.4	29.2	2.729	2.758	1.039	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
LANNON LISBON PIT 55-67-024-PIT Created On: 01/09/20 Updated On:	P		SW	24	8N	19E	Waukesha	0-225-93-2020	0.0	2.7	1.1	4.3	22.9	2.736	2.764	1.041	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
LANNON LISBON PIT 55-67-024-PIT Created On: 01/14/25 Updated On:	P		SW	24	8N	19E	Waukesha	0-225-93-2025	0.3	9.2	2.7	4.0	22.5	2.746	2.778	1.172	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
LANNON STONE - JACKSON 55-66-012-QRY Created On: 01/22/16 Updated On:	Q		NE	12	10N	20E	Washington	0-225-75-2016		0.3	0.2	9.4	34.0	2.705	2.734	1.068	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
LANNON STONE - JACKSON 55-66-012-QRY Created On: 01/18/19 Updated On:	Q		NE	12	10N	20E	Washington	0-225-88-2019		0.9	0.2	8.9	34.4	2.658	2.697	1.478	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
LANNON STONE - JACKSON 55-66-012-QRY Created On: 01/13/22 Updated On:	Q		NE	12	10N	20E	Washington	0-225-111-2022	0.0	0.7	0.6	8.1	36.5	2.608	2.648	1.554	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
LANNON STONE - JACKSON 55-66-012-QRY Created On: 01/03/23 Updated On:	Q		NE	12	10N	20E	Washington	0-225-80-2023	1.6	1.6	0.6	7.4	31.6	2.620	2.670	1.914	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
LANNON STONE - LANNON 55-67-026-QRY Created On: 01/08/15 Updated On:	Q		E	20	8N	20E	Waukesha	0-225-34-2015		0.9	4.6	6.1	28.5	2.720	2.748	1.026	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
LANNON STONE - LANNON 55-67-026-QRY Created On: 02/09/18 Updated On:	Q		E	20	8N	20E	Waukesha	0-225-91-2018		3.8	2.3	5.5	24.0	2.729	2.759	1.110	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
LANNON STONE - LANNON 55-67-026-QRY Created On: 01/08/21 Updated On:	Q		E	20	8N	20E	Waukesha	0-225-115-2021	0.0	2.7	4.1	4.8	21.8	2.746	2.772	0.936	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
LANNON STONE - LANNON 55-67-026-QRY Created On: 04/22/24 Updated On:	Q		E	20	8N	20E	Waukesha	0-225-237-2024	0.0	1.8	1.4	4.8	23.5	2.751	2.778	0.984	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
LANNON STONE - RICHFIELD 55-66-013-PIT Created On: 02/16/16 Updated On:	P		SE	24	9N	19E	Washington	0-225-89-2016		2.6	1.1	8.2	35.1				
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
LANNON STONE - RICHFIELD 55-66-013-PIT Created On: 01/08/21 Updated On:	P		SE	24	9N	19E	Washington	0-225-114-2021	0.0	2.2	2.3	6.9	28.6	2.710	2.740	1.116	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
LANNON STONE - SUSSEX 55-67-025-QRY Created On: 04/04/17 Updated On:	Q		NE	35	8N	19E	Waukesha	0-225-103-2017		1.5	1.2	5.7	25.8	2.721	2.748	0.980	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
LANNON STONE - SUSSEX 55-67-025-QRY Created On: 01/08/20 Updated On:	Q		NE	35	8N	19E	Waukesha	0-225-80-2020	0.0	0.9	0.6	5.0	24.9	2.715	2.747	1.167	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
LANNON STONE - SUSSEX 55-67-025-QRY Created On: 02/27/23 Updated On:	Q		NE	35	8N	19E	Waukesha	0-225-145-2023	3.7	3.1	0.9	5.3	24.7	2.735	2.767	1.176	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
LANNON STONE - WEST QUARRY 55-67-008-QRY Created On: 01/08/15 Updated On:	Q		NW	35	8N	19E	Waukesha	0-225-33-2015		0.8	1.3	5.8	26.1	2.738	2.766	1.027	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
LANNON STONE - WEST QUARRY 55-67-008-QRY Created On: 01/12/16 Updated On:	Q		NW	35	8N	19E	Waukesha	0-225-57-2016		0.6	0.4	8.2	39.7	2.716	2.743	0.974	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
LANNON STONE - WEST QUARRY 55-67-008-QRY Created On: 02/11/19 Updated On:	Q		NW	35	8N	19E	Waukesha	0-225-101-2019	6.2	5.1	1.2	4.1	22.4	2.715	2.750	1.282	
	Approved Use : HMA<MT, HMA>=MT, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
LANNON STONE - WEST QUARRY 55-67-008-QRY Created On: 01/13/22 Updated On:	Q		NW	35	8N	19E	Waukesha	0-225-110-2022	0.0	11.1	4.1	5.3	25.5	2.684	2.725	1.512	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
LANNON STONE - WEST QUARRY 55-67-008-QRY Created On: 01/03/23 Updated On:	Q		NW	35	8N	19E	Waukesha	0-225-81-2023	2.7	12.1	0.5	5.5	25.4	2.718	2.748	1.109	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
LANNON STONE-DOUSMAN 55-67-043-PIT Created On: 04/03/17 Updated On:	P		E	6	6N	18E	Waukesha	0-225-102-2017		2.8	2.7	5.2	24.9	2.723	2.750	1.000	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
LANNON STONE-DOUSMAN 55-67-043-PIT Created On: 08/03/21 Updated On:	P		E	6	6N	18E	Waukesha	0-225-257-2021	0.8	1.3	2.4	4.1	23.0	2.736	2.766	1.064	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
LANNON STONE-DOUSMAN 55-67-043-PIT Created On: 01/14/25 Updated On:	P		E	6	6N	18E	Waukesha	0-225-109-2025	2.0	7.6	2.2	5.3	27.2	2.718	2.750	1.170	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
LARSEN 55-70-007-QRY Created On: 01/05/15 Updated On:	Q	N	NE	19	20N	16E	Winnebago	0-225-2-2015	1.6	0.7	1.9	5.0	23.1	2.725	2.755	1.102	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
LARSEN 55-70-007-QRY Created On: 01/04/18 Updated On:	Q	N	NE	19	20N	16E	Winnebago	0-225-54-2018		0.7	0.7	4.8	22.8	2.716	2.749	1.211	
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
Source Name	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
LARSEN 55-70-007-QRY Created On: 01/05/21 Updated On:	Q	N	NE	19	20N	16E	Winnebago	0-225-47-2021	0.0	1.6	2.1	6.8	27.4	2.713	2.750	1.340		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
LARSEN 55-70-007-QRY Created On: 01/02/24 Updated On:	Q	N	NE	19	20N	16E	Winnebago	0-225-97-2024	0.5	0.7	0.2	4.8	21.3	2.756	2.779	0.800		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
LARSON 55-60-013-PIT Created On: 10/28/16 Updated On:	P	SE	SW	13	33N	1E	Taylor	0-225-272-2016		0.0	2.2	4.1	18.9	2.727	2.759	1.162		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
LARSON 55-60-013-PIT Created On: 09/30/24 Updated On:	P	SE	SW	13	33N	1E	Taylor	0-225-312-2024	0.1	0.0	1.7	4.1	19.5	2.700	2.736	1.319		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
LASSIG PIT 55-43-036-PIT Created On: 09/05/23 Updated On:	P	NW	NE	29	36N	9E	Oneida	0-225-249-2023	0.1	0.0	3.5	6.8	27.4	2.726	2.748	0.838		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
LATHER 55-53-022-PIT Created On: 04/12/16 Updated On:	P	NW	NW	16	1N	13E	Rock	0-225-141-2016	0.9	3.6	4.1	4.7	25.0	2.638	2.679	1.560		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
LATHER 55-53-022-PIT Created On: 02/06/18 Updated On:	P	NW	NW	16	1N	13E	Rock	0-225-88-2018	3.0	0.0	2.2	4.7	23.8	2.640	2.683	1.638		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
Source Name	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
LATHER 55-53-022-PIT Created On: 01/07/19 Updated On:	P	NW	NW	16	1N	13E	Rock	0-225-67-2019	3.8	0.0	5.1	5.1	26.9	2.632	2.676	1.690		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
LATHER 55-53-022-PIT Created On: 03/13/24 Updated On:	P	NW	NW	16	1N	13E	Rock	0-225-197-2024	4.9	6.0	1.8	4.4	23.9	2.637	2.677	1.504		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
LAUERSDORF 55-42-019-QRY Created On: 03/17/16 Updated On:	Q	NE	SW	35	29N	18E	Oconto	0-225-99-2016	0.9	1.4	0.7	8.5	35.6	2.700	2.738	1.396		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
LAUERSDORF 55-42-019-QRY Created On: 01/08/20 Updated On:	Q	NE	SW	35	29N	18E	Oconto	0-225-71-2020	0.1	0.9	3.0	8.7	35.9	2.728	2.756	1.027		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
LAUERSDORF 55-42-019-QRY Created On: 01/12/23 Updated On:	Q	NE	SW	35	29N	18E	Oconto	0-225-120-2023	0.0	4.8	4.8	10.1	41.3	2.648	2.700	1.964		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
LAWIN PIT 55-09-039-PIT Created On: 01/07/15 Updated On:	P		NE	18	30N	8W	Chippewa	0-225-12-2015		0.0	2.1	3.9	19.0	2.690	2.715	0.956		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
LAWIN PIT 55-09-039-PIT Created On: 01/08/19 Updated On:	P		NE	18	30N	8W	Chippewa	0-225-74-2019	2.8	0.0	1.9	3.8	19.9	2.706	2.734	1.029		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
LAWIN PIT 55-09-039-PIT Created On: 01/02/24 Updated On:	P		NE	18	30N	8W	Chippewa	0-225-83-2024	1.6	0.0	1.7	4.5	19.7	2.711	2.737	0.970	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
LAWRENCE 55-05-015-QRY Created On: 01/08/16 Updated On:	Q	SW	SW	30	23N	20E	Brown	0-225-46-2016	0.1	12.6	5.1	6.2	26.6	2.725	2.762	1.360	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
LAWRENCE 55-05-015-QRY Created On: 01/05/17 Updated On:	Q	SW	SW	30	23N	20E	Brown	0-225-36-2017	0.2	22.6	18.9	8.3	29.1	2.740	2.774	1.237	
LAWRENCE 55-05-015-QRY Created On: 03/22/17 Updated On:	Q	SW	SW	30	23N	20E	Brown	0-225-84-2017		5.0	15.9	6.8	24.4	2.745	2.776	1.122	
	Approved Use : Base Aggregate																
LAWRENCE 55-05-015-QRY Created On: 04/11/18 Updated On:	Q	SW	SW	30	23N	20E	Brown	0-225-167-2018	0.3	16.7	11.1	5.1	23.5	2.747	2.776	1.066	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
LAWRENCE 55-05-015-QRY Created On: 07/18/19 Updated On:	Q	SW	SW	30	23N	20E	Brown	0-225-239-2019	0.2	15.6	20.0	5.2	24.1	2.751	2.779	1.028	
LAWRENCE 55-05-015-QRY Created On: 06/09/20 Updated On:	Q	SW	SW	30	23N	20E	Brown	0-225-192-2020	0.2	8.2	4.0	5.0	21.8	2.778	2.801	0.853	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
LAWRENCE 55-05-015-QRY Created On: 01/10/22 Updated On:	Q	SW	SW	30	23N	20E	Brown	0-225-99-2022	0.6	3.4	4.6	5.0	22.0	2.752	2.779	0.979	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
LAWRENCE 55-05-015-QRY Created On: 01/03/23 Updated On:	Q	SW	SW	30	23N	20E	Brown	0-225-45-2023	0.4	6.2	3.8	6.4	25.9	2.723	2.759	1.313	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
* LEATHERBERRY 55-56-017-PIT Created On: 01/08/20 Updated On:	P	E	NW	26	12N	6E	Sauk	0-225-66-2020		0.0	2.1	8.8	29.4	2.649	2.681	1.198	
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																
LEIGHTY 55-25-017-QRY Created On: 02/09/18 Updated On:	Q	N	NE	4	4N	1E	Iowa	0-225-93-2018	0.9	1.6	6.7	10.6	39.6	2.556	2.628	2.822	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
LEIGHTY 55-25-017-QRY Created On: 03/17/21 Updated On:	Q	N	NE	4	4N	1E	Iowa	0-225-140-2021	1.6	12.7	4.0	8.2	34.8	2.539	2.621	3.259	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
LEIGHTY 55-25-017-QRY Created On: 02/28/24 Updated On:	Q	N	NE	4	4N	1E	Iowa	0-225-180-2024	1.7	8.3	6.3	8.1	33.7	2.591	2.658	2.562	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
LEMBERGER QUARRY 55-36-049-QRY Created On: 01/29/24 Updated On:	Q	SE	NE	34	20N	22E	Manitowoc	0-225-164-2024	0.2	0.0	0.6	9.6	34.6	2.716	2.747	1.116	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
LEMKE STONE 55-67-046-QRY Created On: 05/07/20 Updated On:	Q	NE	NW	19	8N	20E	Waukesha	0-225-174-2020	0.0	2.1	3.1	5.3	25.3	2.755	2.792	1.319	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
LEMKE STONE 55-67-046-QRY Created On: 05/14/25 Updated On:	Q	NE	NW	19	8N	20E	Waukesha	0-225-212-2025	0.0	0.9	1.0	5.2	24.6	2.690	2.733	1.618	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
LIBERTY 55-62-019-QRY Created On: 05/07/24 Updated On:	Q			15	12N	3W	Vernon	0-225-249-2024	0.5	3.2	3.0	12.6	45.3	2.593	2.660	2.583	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
LICHTS 55-09-080-PIT Created On: 04/02/20 Updated On:	P	SE	NW	23	29N	6W	Chippewa	0-225-144-2020	2.2	0.0	2.2	4.8	20.7	2.708	2.735	0.984	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
LICHTS 55-09-080-PIT Created On: 01/16/25 Updated On:	P	SE	NW	23	29N	6W	Chippewa	0-225-133-2025	1.5	0.0	4.5	6.1	22.1	2.705	2.738	1.219	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
LINCK #22 55-14-019-QRY Created On: 01/29/15 Updated On:	Q	SW	SW	9	12N	14E	Dodge	0-225-79-2015		2.4	0.9	6.3	29.1	2.764	2.786	0.794	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
LINCK #22 55-14-019-QRY Created On: 03/01/18 Updated On:	Q	SW	SW	9	12N	14E	Dodge	0-225-107-2018	0.3	3.8	2.2	6.9	28.9	2.743	2.777	1.239	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
LINCK #22 55-14-019-QRY Created On: 03/29/21 Updated On:	Q	SW	SW	9	12N	14E	Dodge	0-225-162-2021	0.0	10.4	0.5	6.8	27.2	2.768	2.794	0.938	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
LINCK #22 55-14-019-QRY Created On: 02/28/24 Updated On:	Q	SW	SW	9	12N	14E	Dodge	0-225-189-2024	0.0	5.0	0.3	5.3	24.0	2.778	2.799	0.762	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
LINCK #24 55-14-020-QRY Created On: 01/29/15 Updated On:	Q	SW	SW	16	9N	15E	Dodge	0-225-78-2015	0.6	18.4	10.7	6.4	29.7	2.669	2.718	1.840	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
LINCK #24 55-14-020-QRY Created On: 03/01/18 Updated On:	Q	SW	SW	16	9N	15E	Dodge	0-225-109-2018	0.3	20.5	8.1	8.3	32.3	2.651	2.709	2.191	
LINCK #24 55-14-020-QRY Created On: 10/01/18 Updated On:	Q	SW	SW	16	9N	15E	Dodge	0-225-286-2018	0.2	10.0	6.8	7.1	29.6	2.646	2.705	2.219	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
LINCK #24 55-14-020-QRY Created On: 08/17/22 Updated On:	Q	SW	SW	16	9N	15E	Dodge	0-225-253-2022		22.4	2.5	7.2	29.5				
LINCK #24 55-14-020-QRY Created On: 04/15/25 Updated On:	Q	SW	SW	16	9N	15E	Dodge	0-225-187-2025	0.8	14.8	3.4	8.2	32.4	2.665	2.713	1.809	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
LINCK #26 55-20-028-QRY Created On: 05/09/19 Updated On:	Q	NW	SE	36	14N	14E	Fond Du Lac	0-225-183-2019	0.0	0.9	0.9	6.3	26.4	2.778	2.800	0.809	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
LINCK #26 55-20-028-QRY Created On: 06/28/22 Updated On:	Q	NW	SE	36	14N	14E	Fond Du Lac	0-225-236-2022	0.0	4.4	0.5	6.4	25.6	2.780	2.802	0.798	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
LINCK #26 55-20-028-QRY Created On: 07/23/25 Updated On:	Q	NW	SE	36	14N	14E	Fond Du Lac	0-225-225-2025	0.2	2.7	0.4	6.6	26.9	2.770	2.793	0.824	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
LINCK #27 55-11-026-QRY Created On: 01/29/15 Updated On:	Q	SW	SW	24	10N	12E	Columbia	0-225-77-2015	0.3	1.4	3.6	5.6	22.9	2.622	2.673	1.954	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
LINCK #27 55-11-026-QRY Created On: 03/01/18 Updated On:	Q	SW	SW	24	10N	12E	Columbia	0-225-108-2018	0.3	3.2	2.5	8.3	35.0	2.577	2.657	3.087	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
LINCK #27 55-11-026-QRY Created On: 03/29/21 Updated On:	Q	SW	SW	24	10N	12E	Columbia	0-225-164-2021	5.0	14.3	1.2	10.5	38.5	2.587	2.654	2.563	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
LINCK #27 55-11-026-QRY Created On: 05/02/24 Updated On:	Q	SW	SW	24	10N	12E	Columbia	0-225-248-2024	4.0	4.6	2.0	9.3	37.0	2.585	2.648	2.432	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
LINCOLN CTH W 55-35-041-PIT Created On: 01/02/20 Updated On:	P	E	SW	33	31N	7E	Lincoln	0-225-11-2020	3.2	0.0	6.2	5.1	22.7	2.613	2.655	1.617	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
LINCOLN CTH W 55-35-041-PIT Created On: 01/02/25 Updated On:	P	E	SW	33	31N	7E	Lincoln	0-225-11-2025	0.1	4.5	7.7	4.8	21.9	2.630	2.668	1.443	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
LINDBERG AND SONS 26-99-001-PIT Created On: 01/04/19 Updated On:	P	NW	SW	5	40N	30W	Dickerson	0-225-37-2019	1.0	2.1	2.1	5.3	24.7	2.651	2.675	0.909	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
LINDBERG AND SONS 26-99-001-PIT Created On: 01/02/24 Updated On:	P	NW	SW	5	40N	30W	Dickerson	0-225-13-2024	1.6	0.0	1.6	5.6	27.6	2.661	2.683	0.805	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
LINDEN 55-25-018-QRY Created On: 06/30/16 Updated On:	Q	SW	SW	14	5N	2E	Iowa	0-225-215-2016		0.8	0.5	10.7	39.8	2.676	2.720	1.661	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
LINDEN 55-25-018-QRY Created On: 01/07/19 Updated On:	Q	SW	SW	14	5N	2E	Iowa	0-225-54-2019	0.2	1.8	4.1	10.8	35.9	2.603	2.669	2.522	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
LINDEN 55-25-018-QRY Created On: 01/10/22 Updated On:	Q	SW	SW	14	5N	2E	Iowa	0-225-103-2022	0.4	3.0	4.2	11.0	37.1	2.602	2.670	2.617	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
LINDEN 55-25-018-QRY Created On: 01/02/25 Updated On:	Q	SW	SW	14	5N	2E	Iowa	0-225-83-2025	0.0	3.5	2.5	8.8	34.5	2.616	2.678	2.386	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
LINS 55-56-019-QRY Created On: 09/21/15 Updated On:	Q	NW	NE	22	9N	3E	Sauk	0-225-238-2015	3.5	2.7	5.9	10.6	40.5	2.568	2.643	2.897	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
LINS 55-56-019-QRY Created On: 07/24/18 Updated On:	Q	NW	NE	22	9N	3E	Sauk	0-225-257-2018	2.7	3.8	6.5	9.9	38.5	2.587	2.656	2.656	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
LINS 55-56-019-QRY Created On: 04/07/21 Updated On:	Q	NW	NE	22	9N	3E	Sauk	0-225-173-2021	2.6	8.3	7.1	8.5	35.6	2.600	2.665	2.493	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
LINS 55-56-019-QRY Created On: 03/27/24 Updated On:	Q	NW	NE	22	9N	3E	Sauk	0-225-210-2024	1.3	5.8	5.6	8.1	30.0	2.601	2.660	2.259	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
LISSNER 55-60-014-PIT Created On: 01/09/15 Updated On:	P		SW	27	32N	1E	Taylor	0-225-46-2015		0.0	2.7	3.7	17.7	2.718	2.749	1.133	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
LISSNER 55-60-014-PIT Created On: 01/08/20 Updated On:	P		SW	27	32N	1E	Taylor	0-225-48-2020	1.0	0.0	2.6	4.2	18.8	2.760	2.781	0.771	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
LISSNER 55-60-014-PIT Created On: 01/02/25 Updated On:	P		SW	27	32N	1E	Taylor	0-225-69-2025	0.5	0.0	2.5	3.6	18.5	2.736	2.754	0.680	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
LITTLE LIMESTONE 55-53-023-QRY Created On: 03/29/17 Updated On:	Q	SW	NE	6	1N	14E	Rock	0-225-92-2017	2.2	3.4	14.9	10.8	39.0	2.547	2.634	3.414	
	Approved Use : Base Aggregate																
LITTLE LIMESTONE 55-53-023-QRY Created On: 03/19/20 Updated On:	Q	SW	NE	6	1N	14E	Rock	0-225-132-2020	3.1	10.1	16.8	10.4	39.8	2.536	2.624	3.457	
	Approved Use : Base Aggregate																
LITTLE LIMESTONE 55-53-023-QRY Created On: 01/03/23 Updated On:	Q	SW	NE	6	1N	14E	Rock	0-225-2-2023	3.1	13.3	18.0	99.7	46.6	2.484	2.585	4.090	
	Approved Use : Base Aggregate																
LITTLE LIMESTONE 55-53-023-QRY Created On: 04/05/23 Updated On:	Q	SW	NE	6	1N	14E	Rock	0-225-190-2023	4.0	9.2	8.8	10.5	39.3	2.640	2.702	2.352	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
LM WIEST 55-22-067-QRY Created On: 01/02/25 Updated On:	Q	NE	SE	10	3N	5W	Grant	0-225-87-2025	1.7	4.4	6.7	7.4	37.1	2.592	2.658	2.565	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
Longbranch 55-10-015-QRY Created On: 01/29/15 Updated On:	Q	N	SW	34	29N	4W	Clark	0-225-75-2015		0.0	0.9	3.2	14.3	2.720	2.740	0.731	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
LONGBRANCH 55-10-015-QRY Created On: 03/08/18 Updated On:	Q	N	SW	34	29N	4W	Clark	0-225-112-2018		0.0	0.5	2.6	13.4	2.751	2.764	0.489	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
LONGBRANCH 55-10-015-QRY Created On: 01/05/21 Updated On:	Q	N	SW	34	29N	4W	Clark	0-225-89-2021	0.3	0.0	0.8	3.4	16.0	2.742	2.755	0.472	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
LONGBRANCH 55-10-015-QRY Created On: 01/02/24 Updated On:	Q	N	SW	34	29N	4W	Clark	0-225-86-2024	0.1	0.0	1.1	3.3	16.2	2.756	2.769	0.465	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
LUND / RIOPEL 55-43-013-PIT Created On: 01/04/18 Updated On:	P	SW	SW	6	36N	8E	Oneida	0-225-59-2018		0.0	1.5	4.2	20.2	2.674	2.702	1.027	
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																
LUND / RIOPEL 55-43-013-PIT Created On: 01/03/23 Updated On:	P	SW	SW	6	36N	8E	Oneida	0-225-15-2023		0.0	0.6	3.3	17.6	2.696	2.721	0.933	
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																
LUPPINO BLACK RIVER PIT 26-00-015-PIT Created On: 09/30/24 Updated On:	P	NW	SW	19	49N	46W	Statewide	0-225-311-2024	4.8	0.0	15.1	6.9	26.9	2.581	2.640	2.268	
	Approved Use : Base Aggregate																
LUPPINO KIMBALL 55-26-030-QRY Created On: 06/13/18 Updated On:	Q		NW	4	46N	2E	Iron	0-225-230-2018		0.0	9.2	5.0	27.1	2.826	2.890	2.262	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
LUPPINO KIMBALL 55-26-030-QRY Created On: 04/01/21 Updated On:	Q		NW 4	46N	2E	Iron		0-225-165-2021		0.0	1.7	2.9	12.4	2.796	2.832	1.285	
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																
LUPPINO KIMBALL 55-26-030-QRY Created On: 01/02/24 Updated On:	Q		NW 4	46N	2E	Iron		0-225-62-2024	0.1	0.0	9.4	3.5	15.9	2.608	2.671	2.430	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
LUPPINO MERCER 55-26-029-PIT Created On: 01/05/17 Updated On:	P	NW	NE 1	42N	3E	Iron		0-225-37-2017		0.0	2.8	3.9	18.8	2.710	2.740	1.085	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
LUPPINO MERCER 55-26-029-PIT Created On: 04/04/23 Updated On:	P	NW	NE 1	42N	3E	Iron		0-225-182-2023		0.0	2.7	4.3	18.7	2.721	2.753	1.167	
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																
LUTZKE 55-36-022-PIT Created On: 10/05/18 Updated On:	P	SE	SE 20	18N	22E	Manitowoc		0-225-288-2018	1.2	0.0	1.0	6.7	31.6	2.766	2.789	0.835	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
LUTZKE 55-36-022-PIT Created On: 04/28/22 Updated On:	P	SE	SE 20	18N	22E	Manitowoc		0-225-189-2022	1.5	0.0	0.4	6.9	32.4	2.769	2.792	0.819	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
MACKVILLE 55-44-019-QRY Created On: 03/30/15 Updated On:	Q	SW	NE 33	22N	17E	Outagamie		0-225-105-2015	0.1	0.5	2.4	4.3	18.8	2.767	2.789	0.789	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
MACKVILLE 55-44-019-QRY Created On: 02/16/16 Updated On:	Q	SW	NE	33	22N	17E	Outagamie	0-225-84-2016	0.4	2.7	0.8	4.7	21.5	2.751	2.777	0.940	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
MACKVILLE 55-44-019-QRY Created On: 02/03/17 Updated On:	Q	SW	NE	33	22N	17E	Outagamie	0-225-58-2017	0.2	3.7	1.5	6.1	24.5	2.724	2.759	1.284	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
MACKVILLE 55-44-019-QRY Created On: 03/16/18 Updated On:	Q	SW	NE	33	22N	17E	Outagamie	0-225-123-2018	0.5	3.0	1.0	4.2	19.6	2.765	2.788	0.856	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
MACKVILLE 55-44-019-QRY Created On: 04/24/19 Updated On:	Q	SW	NE	33	22N	17E	Outagamie	0-225-168-2019	0.6	2.5	0.4	5.2	21.5	2.771	2.795	0.870	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
MACKVILLE 55-44-019-QRY Created On: 06/24/20 Updated On:	Q	SW	NE	33	22N	17E	Outagamie	0-225-205-2020	0.2	8.5	1.7	4.4	22.2	2.773	2.795	0.800	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
MACKVILLE 55-44-019-QRY Created On: 01/17/23 Updated On:	Q	SW	NE	33	22N	17E	Outagamie	0-225-122-2023	0.1	4.7	1.2	4.6	20.4	2.762	2.788	0.923	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
MACKVILLE 55-44-019-QRY Created On: 01/02/24 Updated On:	Q	SW	NE	33	22N	17E	Outagamie	0-225-105-2024	0.3	6.4	1.0	5.0	21.7	2.764	2.788	0.882	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
* MAHR 55-09-041-PIT Created On: 01/12/15 Updated On:	P	SW	SW	26	29N	5W	Chippewa	0-225-56-2015		0.0	3.2	3.8	18.3	2.733	2.758	0.923	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
* MAHR 55-09-041-PIT Created On: 01/09/20 Updated On:	P	SW	SW	26	29N	5W	Chippewa	0-225-87-2020	1.0	0.0	4.8	5.0	21.7	2.704	2.736	1.183	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
* MAHR 55-09-041-PIT Created On: 01/09/20 Updated On:	P	SW	SW	26	29N	5W	Chippewa	0-225-89-2020	1.7	0.0	3.0	3.9	18.6	2.684	2.719	1.297	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
MAIER 55-13-124-QRY Created On: 01/05/21 Updated On:	Q		NW	21	9N	9E	Dane	0-225-99-2021	3.4	4.0	10.0	10.2	37.4	2.553	2.623	2.714	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
MAIER 55-13-124-QRY Created On: 02/28/24 Updated On:	Q		NW	21	9N	9E	Dane	0-225-190-2024	2.5	4.5	4.3	7.5	32.2	2.602	2.665	2.428	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
MAIN PIT 55-60-016-PIT Created On: 01/10/23 Updated On:	P	NE	SE	14	33N	4W	Taylor	0-225-114-2023	0.4	0.0	1.9	4.2	20.3	2.727	2.751	0.902	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
MAIN QUARRY 55-60-039-QRY Created On: 01/16/25 Updated On:	Q	NE	SE	14	33N	4W	Taylor	0-225-138-2025	0.0	0.0	1.9	5.4	20.2	2.657	2.676	0.726	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
MALLARD RD PIT 55-09-083-PIT Created On: 07/23/25 Updated On:	P	NW	SE	3	29N	8W	Chippewa	0-225-226-2025	0.9	0.0	1.2	5.2	23.0	2.700	2.726	0.978	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
* MANITOWOC CO. STH 310 55-36-023-QRY Created On: 01/12/16 Updated On:	Q	E	SW	36	20N	23E	Manitowoc	0-225-49-2016		0.0	0.7	6.8	30.0	2.779	2.799	0.741	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
* MANITOWOC CO. STH 310 55-36-023-QRY Created On: 01/04/19 Updated On:	Q	E	SW	36	20N	23E	Manitowoc	0-225-16-2019		1.3	9.6	8.1	34.3	2.764	2.790	0.950	
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																
* MANITOWOC CO. STH 310 55-36-023-QRY Created On: 01/10/22 Updated On:	Q	E	SW	36	20N	23E	Manitowoc	0-225-98-2022	0.2	2.8	2.8	10.0	37.7	2.738	2.766	1.014	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
MANTHEY EAST 55-01-004-PIT Created On: 04/07/16 Updated On:	P			26	17N	7E	Adams	0-225-133-2016		0.0	1.9	8.8	32.4	2.697	2.737	1.494	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
MANTHEY EAST 55-01-004-PIT Created On: 01/04/21 Updated On:	P			26	17N	7E	Adams	0-225-23-2021	4.5	2.6	4.3	8.4	34.5	2.702	2.741	1.411	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
MAPLE RIDGE #2 55-71-020-QRY Created On: 05/11/17 Updated On:	Q	NW	NW	17	22N	3E	Wood	0-225-182-2017		0.0	1.3	6.8	25.7	2.707	2.728	0.774	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
MAPLE RIDGE #2 55-71-020-QRY Created On: 01/07/20 Updated On:	Q	NW	NW	17	22N	3E	Wood	0-225-44-2020	0.4	0.0	0.5	4.0	17.2	2.734	2.744	0.353	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
MAPLE RIDGE #2 55-71-020-QRY Created On: 05/22/23 Updated On:	Q	NW	NW	17	22N	3E	Wood	0-225-225-2023	0.4	0.0	1.0	4.0	17.5	2.759	2.772	0.473	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
MARHAR - MICHIGAN 26-00-003-PIT Created On: 01/04/22 Updated On:	P	S	NW	34	45N	35E	Gogebic	0-225-28-2022	0.0	1.4	1.4	3.0	14.2	2.769	2.783	0.519	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
MARION AGGREGATES 55-68-022-PIT Created On: 06/30/17 Updated On:	P	SW	NW	5	25N	13E	Waupaca	0-225-223-2017		0.0	0.3	4.8	24.9	2.701	2.722	0.801	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
MARION AGGREGATES 55-68-022-PIT Created On: 01/04/22 Updated On:	P	SW	NW	5	25N	13E	Waupaca	0-225-71-2022	0.0	0.9	0.6	5.0	23.6	2.700	2.724	0.904	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
MARKESAN 55-24-007-QRY Created On: 01/16/15 Updated On:	Q		NE	3	14N	13E	Green Lake	0-225-70-2015	0.1	0.9	7.9	6.3	28.2	2.693	2.741	1.785	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
MARKESAN 55-24-007-QRY Created On: 04/11/18 Updated On:	Q		NE	3	14N	13E	Green Lake	0-225-166-2018	0.3	15.1	10.2	7.5	31.5	2.671	2.722	1.926	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
Source Name	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
MARKESAN 55-24-007-QRY Created On: 01/10/19 Updated On:	Q		NE	3	14N	13E	Green Lake	0-225-83-2019		12.5	8.9	7.6	31.8	2.681	2.733	1.931		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MARKESAN 55-24-007-QRY Created On: 03/07/22 Updated On:	Q		NE	3	14N	13E	Green Lake	0-225-139-2022	0.0	10.9	6.7	6.2	28.0	2.703	2.744	1.507		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MARKESAN 55-24-007-QRY Created On: 03/24/25 Updated On:	Q		NE	3	14N	13E	Green Lake	0-225-176-2025	0.0	8.1	5.5	6.6	29.5	2.695	2.742	1.740		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MARSHFIELD 55-71-021-QRY Created On: 01/03/17 Updated On:	Q	SE	NW	2	25N	3E	Wood	0-225-1-2017		0.0	0.3	5.1	23.8	2.676	2.690	0.520		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
MARSHFIELD 55-71-021-QRY Created On: 01/03/20 Updated On:	Q	SE	NW	2	25N	3E	Wood	0-225-12-2020	0.0	0.0	0.3	5.0	22.6	2.719	2.731	0.460		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MARSHFIELD 55-71-021-QRY Created On: 01/03/23 Updated On:	Q	SE	NW	2	25N	3E	Wood	0-225-36-2023	0.0	1.2	3.0	5.5	24.2	2.763	2.783	0.708		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MARSOLEK 55-06-014-QRY Created On: 06/30/16 Updated On:	Q	NW	SE	36	23N	10W	Buffalo	0-225-213-2016		0.0	3.5	8.1	33.4	2.572	2.641	2.694		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
MARSOLEK 55-06-014-QRY Created On: 01/04/19 Updated On:	Q	NW	SE	36	23N	10W	Buffalo	0-225-29-2019	0.9	0.0	7.6	11.5	40.5	2.541	2.623	3.258	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
MARSOLEK 55-06-014-QRY Created On: 01/04/22 Updated On:	Q	NW	SE	36	23N	10W	Buffalo	0-225-76-2022	4.6	0.0	11.6	12.2	44.5	2.540	2.623	3.280	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
MARSOLEK 55-06-014-QRY Created On: 01/02/25 Updated On:	Q	NW	SE	36	23N	10W	Buffalo	0-225-19-2025	1.4	2.7	5.8	8.9	38.9	2.544	2.621	3.058	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
MARTIN ROAD 55-37-091-QRY Created On: 06/26/19 Updated On:	Q	SE	SE	6	27N	9E	Marathon	0-225-232-2019	1.3	0.0	1.3	9.6	38.3	2.591	2.609	0.713	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
MARTIN ROAD 55-37-091-QRY Created On: 02/17/22 Updated On:	Q	SE	SE	6	27N	9E	Marathon	0-225-132-2022	0.0	0.0	0.5	6.8	33.7	2.610	2.623	0.500	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
MARTIN ROAD 55-37-091-QRY Created On: 03/06/25 Updated On:	Q	SE	SE	6	27N	9E	Marathon	0-225-166-2025	0.0	0.0	0.2	6.1	29.4	2.610	2.621	0.389	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
MASHUDA UPPER 55-24-008-QRY Created On: 03/31/17 Updated On:	Q	NE	NW	28	16N	12E	Green Lake	0-225-95-2017	0.4	1.7	2.6	10.7	38.6	2.640	2.701	2.315	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
MASHUDA UPPER 55-24-008-QRY Created On: 05/07/20 Updated On:	Q	NE	NW	28	16N	12E	Green Lake	0-225-172-2020	0.6	1.8	2.2	8.5	37.7				
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
MASHUDA UPPER 55-24-008-QRY Created On: 04/04/23 Updated On:	Q	NE	NW	28	16N	12E	Green Lake	0-225-176-2023	0.5	1.6	1.8	10.9	37.5	2.665	2.718	1.975	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
MATHEY 55-15-014-QRY Created On: 07/08/15 Updated On:	Q	E	SE	22	28N	26E	Door	0-225-208-2015	0.1	0.0	0.6	5.7	25.8	2.793	2.811	0.616	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
MATHEY 55-15-014-QRY Created On: 01/04/18 Updated On:	Q	E	SE	22	28N	26E	Door	0-225-84-2018	1.0	3.3	1.7	8.0	30.8	2.748	2.780	1.144	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
MATHEY 55-15-014-QRY Created On: 01/05/21 Updated On:	Q	E	SE	22	28N	26E	Door	0-225-107-2021	0.0	1.5	0.7	5.7	24.7	2.778	2.802	0.831	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
MATHEY 55-15-014-QRY Created On: 01/02/24 Updated On:	Q	E	SE	22	28N	26E	Door	0-225-48-2024	0.1	0.0	0.6	0.9	29.5	2.778	2.797	0.705	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
* MATOUSHEK 55-56-021-QRY Created On: 05/11/17 Updated On:	Q			28	10N	6E	Sauk	0-225-185-2017		0.0	4.1	10.7	37.6	2.598	2.661	2.459	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
* MATOUSHEK 55-56-021-QRY Created On: 01/06/20 Updated On:	Q			28	10N	6E	Sauk	0-225-25-2020	0.9	0.0	0.2	8.5	33.6	2.619	2.677	2.204	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
MATTHIAE 55-37-047-PIT Created On: 03/13/23 Updated On:	P	SE	SE	35	29N	5E	Marathon	0-225-167-2023	0.3	0.0	1.8	3.3	15.5	2.764	2.786	0.796	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
MAYER 55-60-017-PIT Created On: 06/26/17 Updated On:	P	SE	SW	2	32N	1E	Taylor	0-225-218-2017		0.0	2.5	4.9	21.9	2.739	2.766	1.004	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
MAYER 55-60-017-PIT Created On: 01/10/23 Updated On:	P	SE	SW	2	32N	1E	Taylor	0-225-112-2023	0.2	0.0	4.0	5.2	23.7	2.762	2.792	1.080	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
MAYVILLE WHITELIME 55-14-023-QRY Created On: 08/08/17 Updated On:	Q			1	11N	16E	Dodge	0-225-248-2017	2.3	1.5	0.2	6.6	29.0	2.704	2.748	1.628	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
MAYVILLE WHITELIME 55-14-023-QRY Created On: 08/24/20 Updated On:	Q			1	11N	16E	Dodge	0-225-235-2020	1.8	3.3	0.2	6.8	30.1	2.725	2.764	1.419	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
MAYVILLE WHITELIME 55-14-023-QRY Created On: 02/27/23 Updated On:	Q			1	11N	16E	Dodge	0-225-151-2023	2.1	7.5	5.1	6.0	29.7	2.712	2.754	1.530	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
MCC - LARSEN 55-70-010-QRY Created On: 05/26/16 Updated On:	Q	NE	NW	19	20N	16E	Winnebago	0-225-193-2016	2.8	1.4	1.2	5.3	24.4	2.737	2.761	0.873	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
MCC - LARSEN 55-70-010-QRY Created On: 03/16/18 Updated On:	Q	NE	NW	19	20N	16E	Winnebago	0-225-125-2018	0.3	3.3	1.4	5.6	24.2	2.729	2.756	1.003	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
MCC - LARSEN 55-70-010-QRY Created On: 01/05/21 Updated On:	Q	NE	NW	19	20N	16E	Winnebago	0-225-103-2021	0.2	10.0	11.3	6.8	28.9	2.708	2.750	1.553	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
MCC - LARSEN 55-70-010-QRY Created On: 01/02/24 Updated On:	Q	NE	NW	19	20N	16E	Winnebago	0-225-7-2024	0.0	13.8	3.9	7.5	32.3	2.723	2.757	1.260	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
MCC FREEDOM EAST QUARRY 55-44-028-QRY Created On: 01/14/25 Updated On:	Q			16	22N	18E	Outagamie	0-225-122-2025	1.3	7.2	5.7	6.7	30.6	2.682	2.722	1.511	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
MCC ROCK ROAD 55-44-031-QRY Created On: 01/05/21 Updated On:	Q	SE	SW	17	22N	17E	Outagamie	0-225-100-2021	0.2	0.8	3.2	6.7	30.2	2.716	2.756	1.469	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
MCC ROCK ROAD 55-44-031-QRY Created On: 01/02/24 Updated On:	Q	SE	SW	17	22N	17E	Outagamie	0-225-6-2024	0.6	1.5	0.4	7.3	31.6	2.712	2.743	1.120	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
Source Name	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
MCC- FREEDOM WEST 55-44-020-QRY Created On: 05/02/16 Updated On:	Q	NE	SE	17	22N	18E	Outagamie	0-225-160-2016	0.4	12.0	0.2	5.6	23.7	2.768	2.790	0.823		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
MCC- FREEDOM WEST 55-44-020-QRY Created On: 04/19/19 Updated On:	Q	NE	SE	17	22N	18E	Outagamie	0-225-150-2019	0.3	3.8	2.5	4.8	21.6	2.768	2.793	0.907		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
MCC- FREEDOM WEST 55-44-020-QRY Created On: 06/24/20 Updated On:	Q	NE	SE	17	22N	18E	Outagamie	0-225-206-2020	0.6	7.9	2.2	5.2	21.5	2.769	2.792	0.841		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MCC- FREEDOM WEST 55-44-020-QRY Created On: 01/05/21 Updated On:	Q	NE	SE	17	22N	18E	Outagamie	0-225-101-2021	0.1	2.2	2.4	5.2	22.4	2.762	2.787	0.909		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MCC- FREEDOM WEST 55-44-020-QRY Created On: 01/02/24 Updated On:	Q	NE	SE	17	22N	18E	Outagamie	0-225-5-2024	0.0	5.9	1.7	5.0	22.2	2.763	2.789	0.919		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MCCLAINE 55-03-027-PIT Created On: 05/08/15 Updated On:	P	SW	NE	9	35N	13W	Barron	0-225-159-2015		0.0	2.9	2.8	14.0	2.795	2.817	0.788		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
MCCLAINE 55-03-027-PIT Created On: 04/18/22 Updated On:	P	SW	NE	9	35N	13W	Barron	0-225-177-2022		0.0	2.4	3.4	14.9	2.785	2.811	0.911		
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
* MCKEEFRY 55-58-021-QRY Created On: 03/30/15 Updated On:	Q		NW	23	25N	18E	Shawano	0-225-106-2015	0.9	2.2	2.2	4.9	21.5	2.776	2.796	0.723	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
* MCKEEFRY 55-58-021-QRY Created On: 02/16/16 Updated On:	Q		NW	23	25N	18E	Shawano	0-225-85-2016	0.1	2.4	0.4	5.2	22.6	2.765	2.786	0.749	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
* MCKEEFRY 55-58-021-QRY Created On: 05/24/19 Updated On:	Q		NW	23	25N	18E	Shawano	0-225-196-2019	0.7	9.6	3.1	5.7	25.1	2.746	2.773	1.014	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
* MCKEEFRY 55-58-021-QRY Created On: 05/17/22 Updated On:	Q		NW	23	25N	18E	Shawano	0-225-207-2022	0.3	7.7	0.6	6.2	30.0	2.747	2.772	0.921	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
MCKEEFRY #3 55-58-049-QRY Created On: 10/19/17 Updated On:	Q	N	SW	14	25N	18E	Shawano	0-225-282-2017	0.2	5.2	2.7	6.1	25.7	2.748	2.779	1.112	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
MCKEEFRY #3 55-58-049-QRY Created On: 04/08/20 Updated On:	Q	N	SW	14	25N	18E	Shawano	0-225-145-2020	0.5	2.2	3.4	5.5	23.9	2.767	2.790	0.861	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
MCKEEFRY #3 55-58-049-QRY Created On: 06/12/23 Updated On:	Q	N	SW	14	25N	18E	Shawano	0-225-228-2023	0.0	17.0	10.1	4.8	30.4	2.703	2.743	1.501	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
MCKEEFRY - CHASE 55-42-023-PIT Created On: 08/16/16 Updated On:	P	NW	SE	3	26N	19E	Oconto	0-225-242-2016	0.8	1.3	0.4	6.5	29.0	2.743	2.769	0.970	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
MCKEEFRY - CHASE 55-42-023-PIT Created On: 04/13/21 Updated On:	P	NW	SE	3	26N	19E	Oconto	0-225-179-2021	0.4	3.3	5.2	8.5	36.8	2.710	2.745	1.303	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
MCNAMARA 55-55-007-QRY Created On: 04/21/17 Updated On:	Q	SE	NW	25	31N	15W	St. Croix	0-225-145-2017		0.0	5.2	10.4	38.0	2.558	2.633	2.956	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
MCNAMARA 55-55-007-QRY Created On: 01/06/20 Updated On:	Q	SE	NW	25	31N	15W	St. Croix	0-225-27-2020	1.8	0.0	7.5	10.2	34.7	2.533	2.620	3.440	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
MCNAMARA 55-55-007-QRY Created On: 04/05/23 Updated On:	Q	SE	NW	25	31N	15W	St. Croix	0-225-187-2023	6.2	0.0	10.0	11.8	40.8	2.511	2.598	3.462	
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																
MEDINA 55-44-016-PIT Created On: 03/17/22 Updated On:	P		SW	19	21N	16E	Outagamie	0-225-146-2022	0.5	0.0	0.3	5.2	25.2	2.754	2.780	0.924	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
MEINHOLZ 55-13-064-QRY Created On: 01/20/16 Updated On:	Q			35	8N	8E	Dane	0-225-62-2016	1.0	1.4	0.8	7.6	33.0	2.563	2.627	2.493	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
MEINHOLZ 55-13-064-QRY Created On: 04/01/19 Updated On:	Q			35	8N	8E	Dane	0-225-120-2019	0.8	1.5	2.8	9.3	35.2	2.565	2.636	2.748	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
MEINHOLZ 55-13-064-QRY Created On: 03/29/21 Updated On:	Q			35	8N	8E	Dane	0-225-160-2021	0.8	2.4	2.5	7.7	30.4	2.593	2.656	2.426	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
MEINHOLZ 55-13-064-QRY Created On: 01/04/22 Updated On:	Q			35	8N	8E	Dane	0-225-40-2022	1.3	4.5	5.1	9.4	31.3	2.578	2.643	2.515	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
MEINHOLZ 55-13-064-QRY Created On: 01/23/23 Updated On:	Q			35	8N	8E	Dane	0-225-132-2023	0.6	2.3	2.3	9.4	37.8	2.533	2.602	2.715	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
MEINHOLZ 55-13-064-QRY Created On: 01/02/24 Updated On:	Q			35	8N	8E	Dane	0-225-72-2024	0.8	1.7	1.3	7.2	30.4	2.540	2.619	3.106	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
MEINHOLZ 55-13-064-QRY Created On: 01/02/25 Updated On:	Q			35	8N	8E	Dane	0-225-79-2025	1.4	2.2	1.5	7.9	32.1	2.562	2.631	2.684	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
MENN 55-41-013-QRY Created On: 03/07/16 Updated On:	Q	SW	NW	2	15N	2W	Monroe	0-225-92-2016	0.4	0.0	3.4	19.1	45.9	2.532	2.614	3.242	
	Approved Use : CONCRETE, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
MENN 55-41-013-QRY Created On: 04/19/18 Updated On:	Q	SW	NW	2	15N	2W	Monroe	0-225-176-2018	0.3	0.0	1.7	10.1	37.5	2.598	2.659	2.360	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
MENN 55-41-013-QRY Created On: 03/12/20 Updated On:	Q	SW	NW	2	15N	2W	Monroe	0-225-127-2020	0.0	0.0	3.7	11.8	40.5	2.551	2.626	2.945	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
MENN 55-41-013-QRY Created On: 04/10/23 Updated On:	Q	SW	NW	2	15N	2W	Monroe	0-225-192-2023	1.3	3.6	5.5	10.8	40.1	2.608	2.663	2.102	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
MERRILLAN-734 55-10-018-QRY Created On: 07/02/15 Updated On:	Q	NW	SW	13	23N	3W	Clark	0-225-203-2015		0.0	0.5	2.5	15.8	2.635	2.646	0.435	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
MERRILLAN-734 55-10-018-QRY Created On: 01/03/18 Updated On:	Q	NW	SW	13	23N	3W	Clark	0-225-37-2018		0.0	0.4	3.7	20.1	2.622	2.634	0.432	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
MERRILLAN-734 55-10-018-QRY Created On: 01/04/21 Updated On:	Q	NW	SW	13	23N	3W	Clark	0-225-19-2021	0.0	0.3	0.4	3.3	16.5	2.694	2.705	0.424	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
MERRILLAN-734 55-10-018-QRY Created On: 01/02/24 Updated On:	Q	NW	SW	13	23N	3W	Clark	0-225-110-2024	1.0	3.2	2.2	3.9	19.8	2.658	2.692	1.268	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
MERRILLAN-734 55-10-018-QRY Created On: 01/02/24 Updated On:	Q	NW	SW	13	23N	3W	Clark	0-225-111-2024	0.0	0.6	0.6	4.2	19.1	2.705	2.725	0.754	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
MEVERDEN MATERIALS 55-37-048-QRY Created On: 01/22/16 Updated On:	Q	NE	SW	19	28N	7E	Marathon	0-225-76-2016		0.0	0.5	8.1	36.7	2.594	2.622	1.074	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
MEVERDEN MATERIALS 55-37-048-QRY Created On: 05/09/19 Updated On:	Q	NE	SW	19	28N	7E	Marathon	0-225-185-2019	0.0	0.0	0.6	9.4	40.9	2.616	2.635	0.702	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
MEVERDEN MATERIALS 55-37-048-QRY Created On: 04/30/24 Updated On:	Q	NE	SW	19	28N	7E	Marathon	0-225-241-2024	0.0	0.0	0.4	9.2	38.6	2.617	2.634	0.663	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
MEYER 55-69-012-PIT Created On: 01/04/22 Updated On:	P	NW	NW	36	20N	9E	Waushara	0-225-39-2022	1.0	0.0	6.4	6.9	29.2	2.699	2.733	1.256	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
MICHELS - MISHICOT 55-36-025-PIT Created On: 01/08/15 Updated On:	P	SE	SE	27	21N	23E	Manitowoc	0-225-27-2015	0.5	0.0	3.7	7.1	32.4	2.679	2.720	1.537	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
MICHELS - MISHICOT 55-36-025-PIT Created On: 01/05/21 Updated On:	P	SE	SE	27	21N	23E	Manitowoc	0-225-46-2021	0.8	0.0	3.6	6.0	29.8	2.698	2.741	1.612	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
* MICHELS - BRILLION 55-08-014-QRY Created On: 01/07/15 Updated On:	Q		SW	24	20N	20E	Calumet	0-225-22-2015	0.4	0.0	2.6	9.8	39.9	2.627	2.680	2.009	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
* MICHELS - BRILLION 55-08-014-QRY Created On: 03/16/18 Updated On:	Q		SW	24	20N	20E	Calumet	0-225-124-2018		0.0	2.0	9.0	35.7	2.687	2.727	1.498	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
* MICHELS - BRILLION 55-08-014-QRY Created On: 01/05/21 Updated On:	Q		SW	24	20N	20E	Calumet	0-225-48-2021	0.8	0.0	1.2	8.0	34.5	2.661	2.711	1.903	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
MICHELS - TAYCHEEDAH 55-20-021-QRY Created On: 01/04/17 Updated On:	Q	SW	NE	16	16N	18E	Fond Du Lac	0-225-11-2017	1.3	0.6	1.4	7.6	33.4	2.749	2.777	1.027	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
MICHELS - TAYCHEEDAH 55-20-021-QRY Created On: 01/08/20 Updated On:	Q	SW	NE	16	16N	18E	Fond Du Lac	0-225-70-2020	0.2	0.9	1.4	9.2	38.3	2.740	2.770	1.088	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
MICHELS - TAYCHEEDAH 55-20-021-QRY Created On: 01/03/23 Updated On:	Q	SW	NE	16	16N	18E	Fond Du Lac	0-225-43-2023	0.2	0.7	2.1	7.3	33.5	2.742	2.774	1.175	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
MICHELS ALLEN 55-70-011-QRY Created On: 01/21/16 Updated On:	Q	NE	SW	9	18N	14E	Winnebago	0-225-68-2016	0.5	1.4	6.8	11.6	39.5	2.645	2.700	2.056	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
Source Name	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
MICHELS ALLEN 55-70-011-QRY Created On: 01/07/19 Updated On:	Q	NE	SW	9	18N	14E	Winnebago	0-225-70-2019	0.0	1.7	2.3	7.2	32.0	2.753	2.785	1.180		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
MICHELS ALLEN 55-70-011-QRY Created On: 01/04/22 Updated On:	Q	NE	SW	9	18N	14E	Winnebago	0-225-18-2022	0.0	1.1	1.2	7.9	33.9	2.738	2.769	1.142		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MICHELS ALLEN 55-70-011-QRY Created On: 01/02/24 Updated On:	Q	NE	SW	9	18N	14E	Winnebago	0-225-104-2024	0.8	2.2	2.8	9.3	36.2	2.693	2.734	1.512		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MICHELS BECKER 55-66-016-PIT Created On: 01/08/15 Updated On:	P	SW	SW	27	11N	18E	Washington	0-225-32-2015	0.2	3.6	3.7	6.6	29.1	2.704	2.738	1.262		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
MICHELS BECKER 55-66-016-PIT Created On: 01/08/20 Updated On:	P	SW	SW	27	11N	18E	Washington	0-225-77-2020	2.2	10.5	2.7	6.1	28.8	2.678	2.718	1.499		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MICHELS BECKER 55-66-016-PIT Created On: 01/02/25 Updated On:	P	SW	SW	27	11N	18E	Washington	0-225-76-2025	0.1	4.3	3.2	5.6	27.7	2.670	2.708	1.400		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MICHELS BEECHWOOD 55-59-023-PIT Created On: 01/05/21 Updated On:	P	W	NE	4	13N	20E	Sheboygan	0-225-85-2021	0.6	0.0	3.7	9.5	35.9	2.715	2.753	1.391		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
* MICHELS BROWN 55-08-015-QRY Created On: 01/04/16 Updated On:	Q	S	SW	32	20N	19E	Calumet	0-225-7-2016	0.1	0.0	1.4	6.0	26.8	2.767	2.789	0.787		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
* MICHELS BROWN 55-08-015-QRY Created On: 01/04/19 Updated On:	Q	S	SW	32	20N	19E	Calumet	0-225-39-2019	0.7	0.0	3.6	8.1	32.6	2.743	2.774	1.131		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
* MICHELS BROWN 55-08-015-QRY Created On: 01/04/22 Updated On:	Q	S	SW	32	20N	19E	Calumet	0-225-32-2022	1.2	0.0	3.2	9.6	37.0	2.713	2.752	1.440		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
* MICHELS CHASE 55-42-024-QRY Created On: 01/07/15 Updated On:	Q	NE	SW	17	26N	19E	Oconto	0-225-21-2015		2.0	2.4	4.8	22.1	2.733	2.759	0.924		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
* MICHELS CHASE 55-42-024-QRY Created On: 01/04/19 Updated On:	Q	NE	SW	17	26N	19E	Oconto	0-225-40-2019		5.7	3.2	5.9	25.8	2.738	2.764	0.975		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
* MICHELS CHASE 55-42-024-QRY Created On: 04/11/22 Updated On:	Q	NE	SW	17	26N	19E	Oconto	0-225-174-2022	0.1	3.4	3.4	5.8	24.7	2.730	2.760	1.129		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MICHELS COLUMBUS 55-11-028-QRY Created On: 01/03/17 Updated On:	Q			11	10N	12E	Columbia	0-225-9-2017	1.9	7.8	7.5	9.8	38.7	2.584	2.647	2.440		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
MICHELS COLUMBUS 55-11-028-QRY Created On: 03/09/20 Updated On:	Q			11	10N	12E	Columbia	0-225-124-2020	2.9	15.0	7.8	10.1	41.5	2.598	2.664	2.568		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MICHELS COLUMBUS 55-11-028-QRY Created On: 01/04/22 Updated On:	Q			11	10N	12E	Columbia	0-225-4-2022	2.7	6.5	9.5	10.0	40.5	2.542	2.616	2.925		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MICHELS COLUMBUS 55-11-028-QRY Created On: 01/02/25 Updated On:	Q			11	10N	12E	Columbia	0-225-24-2025	0.1	10.6	10.5	8.7	37.0	2.582	2.648	2.567		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MICHELS DEVENS 55-70-013-QRY Created On: 01/07/16 Updated On:	Q	NW	NW	21	19N	16E	Winnebago	0-225-40-2016		2.8	2.3	4.5	20.4	2.767	2.791	0.876		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
MICHELS DEVENS 55-70-013-QRY Created On: 01/07/20 Updated On:	Q	NW	NW	21	19N	16E	Winnebago	0-225-36-2020	0.2	9.9	2.0	6.1	26.0	2.736	2.772	1.323		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MICHELS DEVENS 55-70-013-QRY Created On: 01/02/24 Updated On:	Q	NW	NW	21	19N	16E	Winnebago	0-225-47-2024	0.1	5.1	3.8	6.1	26.0	2.763	2.791	0.999		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MICHELS DIETZ 55-70-014-QRY Created On: 03/31/17 Updated On:	Q			8	20N	17E	Winnebago	0-225-96-2017	0.1	3.8	5.4	6.9	30.5	2.741	2.770	1.060		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
MICHELS DIETZ 55-70-014-QRY Created On: 01/07/20 Updated On:	Q			8	20N	17E	Winnebago	0-225-39-2020	0.1	12.5	2.1	5.5	26.0	2.742	2.777	1.297	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
MICHELS DIETZ 55-70-014-QRY Created On: 01/03/23 Updated On:	Q			8	20N	17E	Winnebago	0-225-79-2023	0.1	13.6	10.6	6.6	28.8	2.717	2.760	1.576	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
MICHELS DIETZ 55-70-014-QRY Created On: 04/15/25 Updated On:	Q			8	20N	17E	Winnebago	0-225-191-2025	0.1	13.3	10.7	6.9	29.2	2.740	2.773	1.206	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
MICHELS GARVEY 55-44-021-QRY Created On: 01/07/16 Updated On:	Q	SE	SE	17	22N	17E	Outagamie	0-225-36-2016		0.6	1.9	7.0	31.4	2.682	2.720	1.428	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
MICHELS GARVEY 55-44-021-QRY Created On: 01/07/19 Updated On:	Q	SE	SE	17	22N	17E	Outagamie	0-225-42-2019	0.2	3.9	5.1	6.9	31.6	2.741	2.769	1.022	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
MICHELS GARVEY 55-44-021-QRY Created On: 01/04/22 Updated On:	Q	SE	SE	17	22N	17E	Outagamie	0-225-34-2022	0.2	0.8	1.7	5.8	27.9	2.720	2.753	1.221	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
MICHELS GARVEY 55-44-021-QRY Created On: 01/02/24 Updated On:	Q	SE	SE	17	22N	17E	Outagamie	0-225-106-2024	1.2	3.9	4.1	7.8	32.4	2.688	2.728	1.509	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
MICHELS GRUNSKA 55-70-016-QRY Created On: 05/10/18 Updated On:	Q	SE	SE	8	20N	16E	Winnebago	0-225-201-2018	1.4	10.5	3.9	6.9	30.0	2.695	2.730	1.298	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
MICHELS GRUNSKA 55-70-016-QRY Created On: 01/05/21 Updated On:	Q	SE	SE	8	20N	16E	Winnebago	0-225-50-2021	1.5	5.7	4.8	7.0	30.6	2.705	2.743	1.392	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
MICHELS GRUNSKA 55-70-016-QRY Created On: 01/02/24 Updated On:	Q	SE	SE	8	20N	16E	Winnebago	0-225-46-2024	1.3	7.9	5.8	6.8	28.5	2.705	2.740	1.265	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
* MICHELS HAMILTON HILL 55-20-024-QRY Created On: 07/07/21 Updated On:	Q		NW	10	14N	17E	Fond Du Lac	0-225-243-2021	1.6	7.4	7.9	12.7	41.3	2.697	2.742	1.665	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
* MICHELS KETTER 55-20-025-PIT Created On: 03/19/15 Updated On:	P		SW	4	13N	19E	Fond Du Lac	0-225-100-2015	1.1	0.0	4.1	7.9	32.8	2.725	2.758	1.180	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
* MICHELS KETTER 55-20-025-PIT Created On: 01/08/20 Updated On:	P		SW	4	13N	19E	Fond Du Lac	0-225-74-2020	2.0	8.5	4.0	8.5	34.3	2.715	2.755	1.466	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
MICHELS KOCH 55-70-017-QRY Created On: 01/04/22 Updated On:	Q	NW	NE	29	20N	17E	Winnebago	0-225-20-2022	0.2	1.7	2.0	5.2	23.9	2.758	2.787	1.050	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
MICHELS KOCH 55-70-017-QRY Created On: 01/04/24 Updated On:	Q	NW	NE	29	20N	17E	Winnebago	0-225-147-2024	0.0	2.9	2.4	5.4	25.6	2.759	2.788	1.039	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
* MICHELS MANCHESTER 55-24-010-PIT Created On: 07/08/15 Updated On:	P	SW	SE	16	14N	12E	Green Lake	0-225-207-2015	7.7	0.0	7.3	7.3	33.6	2.573	2.632	2.258	
	Approved Use : HMA<E-3, HMA>=E-3, Base Aggregate																
* MICHELS MANCHESTER 55-24-010-PIT Created On: 01/07/20 Updated On:	P	SW	SE	16	14N	12E	Green Lake	0-225-40-2020	1.7	14.5	9.5	6.5	32.3	2.570	2.630	2.356	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
MICHELS MARBLEHEAD 55-20-026-QRY Created On: 01/04/16 Updated On:	Q	NE	NE	7	14N	18E	Fond Du Lac	0-225-13-2016		2.3	1.1	8.4	34.6	2.760	2.782	0.806	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
MICHELS MARBLEHEAD 55-20-026-QRY Created On: 01/04/19 Updated On:	Q	NE	NE	7	14N	18E	Fond Du Lac	0-225-19-2019		5.0	2.7	9.3	36.0	2.739	2.766	0.981	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
MICHELS MARBLEHEAD 55-20-026-QRY Created On: 01/04/22 Updated On:	Q	NE	NE	7	14N	18E	Fond Du Lac	0-225-23-2022	0.0	2.6	1.6	8.8	35.3	2.739	2.770	1.140	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
MICHELS MARBLEHEAD 55-20-026-QRY Created On: 01/02/25 Updated On:	Q	NE	NE	7	14N	18E	Fond Du Lac	0-225-57-2025	0.0	2.2	2.7	8.3	34.9	2.739	2.765	0.925	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
MICHELS MARKESAN 55-24-011-QRY Created On: 01/04/16 Updated On:	Q	SW	SW	9	14N	13E	Green Lake	0-225-14-2016		13.7	6.0	6.1	27.0	2.678	2.724	1.714	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
MICHELS MARKESAN 55-24-011-QRY Created On: 01/03/23 Updated On:	Q	SW	SW	9	14N	13E	Green Lake	0-225-41-2023	0.0	14.9	9.3	6.6	29.0	2.673	2.724	1.902	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
MICHELS NASBRO 55-14-025-QRY Created On: 01/04/16 Updated On:	Q	W	SE	18	13N	17E	Dodge	0-225-1-2016		0.4	1.3	7.5	32.2	2.714	2.746	1.179	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
MICHELS NASBRO 55-14-025-QRY Created On: 01/04/19 Updated On:	Q	W	SE	18	13N	17E	Dodge	0-225-1-2019	0.1	0.9	1.4	9.1	35.7	2.710	2.744	1.269	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
MICHELS NASBRO 55-14-025-QRY Created On: 01/04/22 Updated On:	Q	W	SE	18	13N	17E	Dodge	0-225-2-2022	0.0	0.5	1.0	7.2	30.8	2.731	2.763	1.155	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
MICHELS NASBRO 55-14-025-QRY Created On: 01/02/25 Updated On:	Q	W	SE	18	13N	17E	Dodge	0-225-22-2025	0.0	0.5	1.2	8.5	34.4	2.714	2.748	1.240	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
MICHELS OSHKOSH 55-70-018-QRY Created On: 01/04/16 Updated On:	Q		NE	27	18N	16E	Winnebago	0-225-11-2016		3.1	2.8	5.0	22.1	2.755	2.782	0.992	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
MICHELS OSHKOSH 55-70-018-QRY Created On: 01/04/19 Updated On:	Q		NE	27	18N	16E	Winnebago	0-225-6-2019		8.9	2.1	4.1	19.8	2.766	2.792	0.929	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
MICHELS OSHKOSH 55-70-018-QRY Created On: 01/04/22 Updated On:	Q		NE	27	18N	16E	Winnebago	0-225-22-2022	0.1	7.3	5.0	4.9	22.8	2.730	2.766	1.321	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
MICHELS OSHKOSH 55-70-018-QRY Created On: 01/02/24 Updated On:	Q		NE	27	18N	16E	Winnebago	0-225-103-2024	0.0	6.3	2.3	4.8	22.8	2.753	2.781	1.035	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
MICHELS WARMKA 55-14-034-QRY Created On: 01/02/25 Updated On:	Q	NE	NW	9	12N	14E	Dodge	0-225-23-2025	0.0	2.2	1.7	5.3	24.3	2.755	2.781	0.937	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
* MICHELS-HUGHES 55-70-019-QRY Created On: 01/05/17 Updated On:	Q	SW	NW	32	17N	16E	Winnebago	0-225-13-2017	0.3	11.7	9.9	6.6	28.9	2.731	2.765	1.269	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
* MICHELS-HUGHES 55-70-019-QRY Created On: 01/04/19 Updated On:	Q	SW	NW	32	17N	16E	Winnebago	0-225-7-2019	0.5	22.5	8.7	7.3	30.2	2.708	2.752	1.629	
* MICHELS-HUGHES 55-70-019-QRY Created On: 05/09/19 Updated On:	Q	SW	NW	32	17N	16E	Winnebago	0-225-181-2019	0.5	10.8	10.4	6.9	30.8	2.735	2.770	1.282	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
* MICHELS-HUGHES 55-70-019-QRY Created On: 01/04/22 Updated On:	Q	SW	NW	32	17N	16E	Winnebago	0-225-31-2022	0.3	9.9	9.2	6.9	30.2	2.720	2.756	1.340		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MICHELS-RIB 55-37-093-QRY Created On: 01/04/22 Updated On:	Q	SW	SE	9	30N	7E	Marathon	0-225-16-2022	0.0	0.0	0.8	7.7	32.4	2.579	2.597	0.687		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MICHELS-RIB 55-37-093-QRY Created On: 01/02/25 Updated On:	Q	SW	SE	9	30N	7E	Marathon	0-225-12-2025	0.0	0.1	0.7	5.9	27.1	2.597	2.610	0.519		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MICHELS-WATERLOO 55-14-028-QRY Created On: 01/04/16 Updated On:	Q	NW	NW	34	9N	13E	Dodge	0-225-2-2016		0.4	0.5	4.1	21.8	2.655	2.667	0.461		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
MICHELS-WATERLOO 55-14-028-QRY Created On: 01/04/19 Updated On:	Q	NW	NW	34	9N	13E	Dodge	0-225-2-2019		0.8	0.3	4.1	22.0	2.651	2.667	0.604		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MICHELS-WATERLOO 55-14-028-QRY Created On: 01/04/22 Updated On:	Q	NW	NW	34	9N	13E	Dodge	0-225-1-2022	0.0	0.1	0.2	5.2	26.1	2.662	2.673	0.397		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MICHELS-WATERLOO 55-14-028-QRY Created On: 01/02/25 Updated On:	Q	NW	NW	34	9N	13E	Dodge	0-225-25-2025	0.0	0.6	0.4	4.9	24.2	2.649	2.667	0.673		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
* MICHELIS-WAUPUN 55-20-031-QRY Created On: 01/04/16 Updated On:	Q	S	NW	36	14N	14E	Fond Du Lac	0-225-8-2016		4.5	4.2	6.5	27.5	2.778	2.801	0.828		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
* MICHELIS-WAUPUN 55-20-031-QRY Created On: 01/08/19 Updated On:	Q	S	NW	36	14N	14E	Fond Du Lac	0-225-71-2019	0.0	9.5	6.0	6.7	30.9	2.798	2.822	0.865		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
* MICHELIS-WAUPUN 55-20-031-QRY Created On: 01/04/22 Updated On:	Q	S	NW	36	14N	14E	Fond Du Lac	0-225-19-2022	0.0	5.6	2.8	6.0	28.6	2.764	2.791	0.973		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MICHELIS/BERRES 55-20-004-PIT Created On: 01/04/19 Updated On:	P	SW	SE	32	14N	19E	Fond Du Lac	0-225-17-2019	0.8	0.0	2.2	8.9	34.6	2.728	2.764	1.316		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
MICHELIS/BERRES 55-20-004-PIT Created On: 01/02/24 Updated On:	P	SW	SE	32	14N	19E	Fond Du Lac	0-225-52-2024	1.0	0.0	2.9	8.6	34.2	2.735	2.764	1.025		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MICHELIS/BERRES 55-20-058-QRY Created On: 05/20/24 Updated On:	Q	SW	SE	32	14N	19E	Fond Du Lac	0-225-259-2024	6.6	10.0	4.7	7.9	32.2	2.655	2.703	1.820		
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																	
MIKKOLA QUARRY 55-16-014-QRY Created On: 08/15/17 Updated On:	Q	NE	NE	35	48N	11W	Douglas	0-225-254-2017		0.0	0.9	3.1	13.9	2.620	2.643	0.891		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse					
	P/Q	Qrt	Qrt	Sect	Town	Range	County	LA Wear (%)					Sp. Gravity		Absorp. %			
								100					500	OD	SSD	Crse	Fine	
MIKKOLA QUARRY 55-16-014-QRY Created On: 01/06/20 Updated On:	Q	NE	NE	35	48N	11W	Douglas	0-225-30-2020	0.1	0.0	4.9	3.1	13.9	2.582	2.615	1.247		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MIKKOLA QUARRY 55-16-014-QRY Created On: 01/04/23 Updated On:	Q	NE	NE	35	48N	11W	Douglas	0-225-89-2023	0.6	2.4	2.9	3.4	15.0	2.645	2.682	1.392		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MILAS 55-10-020-PIT Created On: 03/08/18 Updated On:	P	SE	NW	3	29N	3W	Clark	0-225-116-2018	1.4	0.0	2.5	4.3	19.4	2.686	2.713	1.011		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
MILAS 55-10-020-PIT Created On: 01/04/23 Updated On:	P	SE	NW	3	29N	3W	Clark	0-225-98-2023	1.2	0.0	2.8	3.6	18.0	2.733	2.759	0.969		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MILE ROAD 55-13-007-QRY Created On: 03/07/16 Updated On:	Q	NE	NE	13	9N	10E	Dane	0-225-97-2016	1.1	2.6	8.9	6.5	29.4	2.640	2.693	2.030		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
MILE ROAD 55-13-007-QRY Created On: 01/04/19 Updated On:	Q	NE	NE	13	9N	10E	Dane	0-225-9-2019	1.7	7.0	7.4	10.1	28.7	2.536	2.616	3.134		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
MILE ROAD 55-13-007-QRY Created On: 01/02/24 Updated On:	Q	NE	NE	13	9N	10E	Dane	0-225-42-2024	0.7	14.1	12.6	9.8	43.1	2.545	2.623	3.066		
	Approved Use : Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Coarse Sp. Gravity		Coarse Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
MILESTONE #43 27-00-024-QRY Created On: 01/07/19 Updated On:	Q			16	106N	7W	Winona	0-225-49-2019	0.6	2.0	2.5	8.7	34.9	2.619	2.676	2.192	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
MILESTONE #43 27-00-024-QRY Created On: 01/03/23 Updated On:	Q			16	106N	7W	Winona	0-225-72-2023	0.8	1.1	3.8	10.1	39.4	2.614	2.672	2.223	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
MILESTONE RIEKEMANN PIT #222 55-18-011-PIT Created On: 01/03/18 Updated On:	P	SE	SW	4	26N	10W	Eau Claire	0-225-41-2018	1.7	0.0	2.0	3.8	19.4	2.641	2.670	1.078	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
MILESTONE RIEKEMANN PIT #222 55-18-011-PIT Created On: 01/03/23 Updated On:	P	SE	SW	4	26N	10W	Eau Claire	0-225-52-2023	0.7	4.4	3.1	4.2	20.9	2.632	2.665	1.261	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
MILESTONE SOMERS 55-49-015-PIT Created On: 01/07/15 Updated On:	P	NE	NE	29	23N	9E	Portage	0-225-18-2015		0.0	2.5	6.9	28.8	2.685	2.718	1.206	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
MILESTONE SOMERS 55-49-015-PIT Created On: 01/07/20 Updated On:	P	NE	NE	29	23N	9E	Portage	0-225-43-2020	2.6	0.0	3.9	9.4	33.4	2.663	2.698	1.321	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
MILESTONE SOMERS 55-49-015-PIT Created On: 01/02/24 Updated On:	P	NE	NE	29	23N	9E	Portage	0-225-45-2024	0.4	3.9	2.0	7.1	29.2	2.683	2.715	1.188	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
Source Name	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
MILESTONE-ANDERSON EE 55-32-001-QRY Created On: 07/15/20 Updated On:	Q	SE	NW	33	18N	5W	La Crosse	0-225-216-2020	0.8	0.0	2.6	8.9	38.5	2.606	2.666	2.278		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MILESTONE-ANDERSON EE 55-32-001-QRY Created On: 01/04/23 Updated On:	Q	SE	NW	33	18N	5W	La Crosse	0-225-85-2023	0.2	1.0	0.9	8.1	35.4	2.628	2.678	1.910		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MILESTONE-ANSEL JOHNSON 55-48-013-PIT Created On: 01/05/16 Updated On:	P	NW	SW	35	34N	16W	Polk	0-225-22-2016		0.0	1.6	2.9	14.7	2.744	2.773	1.035		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
MILESTONE-ANSEL JOHNSON 55-48-013-PIT Created On: 01/04/21 Updated On:	P	NW	SW	35	34N	16W	Polk	0-225-37-2021	0.7	1.2	2.3	2.7	14.1	2.747	2.779	1.159		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MILESTONE-ARNOLD ANDERSON 55-22-002-QRY Created On: 04/07/16 Updated On:	Q	SW	SE	34	3N	1W	Grant	0-225-131-2016	1.5	6.1	7.6	12.8	44.0	2.549	2.631	3.202		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
MILESTONE-ARNOLD ANDERSON 55-22-002-QRY Created On: 01/04/19 Updated On:	Q	SW	SE	34	3N	1W	Grant	0-225-25-2019	3.4	9.9	9.4	15.0	48.1	2.537	2.618	3.195		
	Approved Use : CONCRETE, Base Aggregate																	
MILESTONE-ARNOLD ANDERSON 55-22-002-QRY Created On: 05/01/23 Updated On:	Q	SW	SE	34	3N	1W	Grant	0-225-214-2023	1.9	7.0	12.0	12.8	44.9	2.546	2.628	3.224		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
MILESTONE-BUCKLEY 55-16-002-QRY Created On: 02/13/17 Updated On:	Q	NW	NW	32	48N	12W	Douglas	0-225-69-2017		0.0	9.5	4.8	21.2	2.880	2.910	1.027	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
MILESTONE-BUCKLEY 55-16-002-QRY Created On: 08/15/17 Updated On:	Q	NW	NW	32	48N	12W	Douglas	0-225-253-2017	0.1	0.0	6.7	5.6	22.4	2.870	2.887	0.584	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
MILESTONE-BUCKLEY 55-16-002-QRY Created On: 01/08/20 Updated On:	Q	NW	NW	32	48N	12W	Douglas	0-225-58-2020	0.0	0.0	5.6	5.3	22.3	2.816	2.841	0.882	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
MILESTONE-BUCKLEY 55-16-002-QRY Created On: 01/03/23 Updated On:	Q	NW	NW	32	48N	12W	Douglas	0-225-59-2023	0.0	1.5	2.3	3.5	17.3	2.817	2.845	1.009	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
MILESTONE-CHARLES OLSEN 55-09-047-PIT Created On: 01/08/15 Updated On:	P	SW	NW	35	30N	8W	Chippewa	0-225-37-2015		0.0	3.3	3.9	17.9	2.704	2.735	1.139	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
MILESTONE-CHARLES OLSEN 55-09-047-PIT Created On: 01/08/20 Updated On:	P	SW	NW	35	30N	8W	Chippewa	0-225-53-2020	1.4	0.0	0.0	4.6	19.6	2.727	2.756	1.068	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
MILESTONE-CHARLES OLSEN 55-09-047-PIT Created On: 01/02/25 Updated On:	P	SW	NW	35	30N	8W	Chippewa	0-225-17-2025	1.7	3.0	3.1	3.8	18.2	2.717	2.750	1.216	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
Source Name	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
MILESTONE-CLEMENTS 33 55-32-003-QRY Created On: 04/06/17 Updated On:	Q	NW	NE	7	15N	5W	La Crosse	0-225-109-2017	1.3	0.0	1.6	10.0	41.0	2.529	2.607	3.051		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
MILESTONE-CLEMENTS 33 55-32-003-QRY Created On: 01/03/20 Updated On:	Q	NW	NE	7	15N	5W	La Crosse	0-225-17-2020	1.8	0.0	5.1	11.2	41.6	2.539	2.618	3.141		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MILESTONE-CLEMENTS 33 55-32-003-QRY Created On: 01/04/23 Updated On:	Q	NW	NE	7	15N	5W	La Crosse	0-225-86-2023	2.1	3.4	3.8	11.4	41.8	2.544	2.621	3.050		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MILESTONE-CLEMENTS YY 55-32-004-QRY Created On: 06/05/15 Updated On:	Q	SW	NE	3	15N	6W	La Crosse	0-225-186-2015		0.0	2.3	10.4	36.9	2.597	2.656	2.237		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
MILESTONE-CLEMENTS YY 55-32-004-QRY Created On: 01/03/18 Updated On:	Q	SW	NE	3	15N	6W	La Crosse	0-225-11-2018	3.0	0.0	2.6	12.2	41.9	2.551	2.620	2.700		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
MILESTONE-CLEMENTS YY 55-32-004-QRY Created On: 01/04/21 Updated On:	Q	SW	NE	3	15N	6W	La Crosse	0-225-30-2021	2.9	0.0	0.0	10.7	38.2	2.536	2.612	3.006		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MILESTONE-CLEMENTS YY 55-32-004-QRY Created On: 01/02/24 Updated On:	Q	SW	NE	3	15N	6W	La Crosse	0-225-25-2024	2.5	6.8	2.3	10.4	39.4	2.568	2.636	2.657		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
MILESTONE-DON JOHNSON 55-07-006-PIT Created On: 01/05/16 Updated On:	P	E	SW	21	39N	17W	Burnett	0-225-26-2016		0.0	6.6	3.8	16.9	2.739	2.771	1.148	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
MILESTONE-DON JOHNSON 55-07-006-PIT Created On: 10/12/21 Updated On:	P	E	SW	21	39N	17W	Burnett	0-225-267-2021	0.8	3.0	3.7	3.8	16.9	2.778	2.804	0.927	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
MILESTONE-DON JOHNSON 55-07-006-PIT Created On: 01/04/24 Updated On:	P	E	SW	21	39N	17W	Burnett	0-225-144-2024	1.0	4.8	6.4	3.5	16.6	2.747	2.794	1.701	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
MILESTONE-DONALD NELSON 55-11-029-PIT Created On: 01/04/19 Updated On:	P	SW	NW	12	13N	6E	Columbia	0-225-21-2019	0.5	0.0	4.1	8.0	31.3	2.693	2.735	1.561	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
MILESTONE-DONALD NELSON 55-11-029-PIT Created On: 01/02/24 Updated On:	P	SW	NW	12	13N	6E	Columbia	0-225-20-2024	1.0	4.2	3.0	7.4	29.3	2.702	2.739	1.355	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
MILESTONE-DONALD NELSON 55-11-029-PIT Created On: 05/14/25 Updated On:	P	SW	NW	12	13N	6E	Columbia	0-225-211-2025	0.0	1.1	0.7	6.9	27.7	2.725	2.760	1.291	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
MILESTONE-MONDOVI-BUCK RIDGE 55-06-016-QRY Created On: 01/05/17 Updated On:	Q	N	SE	28	24N	11W	Buffalo	0-225-46-2017	0.6	0.0	3.3	8.7	38.7	2.580	2.643	2.445	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
MILESTONE-MONDOVI-BUCK RIDGE 55-06-016-QRY Created On: 06/18/20 Updated On:	Q	N	SE	28	24N	11W	Buffalo	0-225-197-2020	0.6	0.0	6.6	13.3	48.2	2.533	2.615	3.220		
	Approved Use : HMA<MT, CONCRETE, OGBC, Base Aggregate																	
MILESTONE-MONDOVI-BUCK RIDGE 55-06-016-QRY Created On: 01/04/22 Updated On:	Q	N	SE	28	24N	11W	Buffalo	0-225-74-2022	0.6	0.0	40.6	14.7	50.3	2.537	2.622	3.360		
MILESTONE-MONDOVI-BUCK RIDGE 55-06-016-QRY Created On: 08/17/22 Updated On:	Q	N	SE	28	24N	11W	Buffalo	0-225-251-2022	0.1	7.8	12.6	15.3	49.4	2.594	2.660	2.567		
	Approved Use : Base Aggregate																	
MILESTONE-MONDOVI-BUCK RIDGE 55-06-016-QRY Created On: 01/02/25 Updated On:	Q	N	SE	28	24N	11W	Buffalo	0-225-20-2025	0.2	3.9	6.1	12.1	45.2	2.560	2.638	3.030		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MILESTONE-THOMPSON F 55-62-030-QRY Created On: 05/04/17 Updated On:	Q	SE	SW	8	14N	1E	Vernon	0-225-171-2017		0.0	3.2	8.8	36.4	2.615	2.669	2.066		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
MILESTONE-THOMPSON F 55-62-030-QRY Created On: 01/03/20 Updated On:	Q	SE	SW	8	14N	1E	Vernon	0-225-24-2020	1.2	0.0	5.1	9.7	34.7	2.597	2.661	2.461		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
MILESTONE-THOMPSON F 55-62-030-QRY Created On: 01/03/23 Updated On:	Q	SE	SW	8	14N	1E	Vernon	0-225-30-2023	1.0	3.6	0.6	9.7	35.5	2.623	2.674	1.940		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County						100	500	OD	SSD	Crse	Fine
MILESTONE-WALKER 8 55-48-030-PIT Created On: 06/21/18 Updated On:	P	SE	SE	23	34N	17W	Polk		0-225-238-2018	0.3	0.0	1.6	4.8	17.4	2.823	2.853	1.051	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MILESTONE-WALKER 8 55-48-030-PIT Created On: 05/01/23 Updated On:	P	SE	SE	23	34N	17W	Polk		0-225-209-2023	0.1	0.0	1.1	2.6	13.1	2.854	2.880	0.911	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
* MILESTONE-WAYNE ANDERSON 55-47-030-QRY Created On: 01/03/18 Updated On:	Q	NW	NE	9	25N	18W	Pierce		0-225-39-2018	2.1	0.0	4.2	8.7	33.4	2.615	2.674	2.258	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
* MILESTONE-WAYNE ANDERSON 55-47-030-QRY Created On: 01/05/21 Updated On:	Q	NW	NE	9	25N	18W	Pierce		0-225-76-2021	1.9	0.0	0.4	7.7	31.3	2.605	2.667	2.360	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MILITARY 55-43-015-PIT Created On: 01/05/21 Updated On:	P	NE	SE	2	39N	11E	Oneida		0-225-53-2021	0.9	0.0	0.6	3.0	15.7	2.702	2.725	0.847	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MILLER 55-25-019-QRY Created On: 04/16/15 Updated On:	Q	NW	NW	31	6N	3E	Iowa		0-225-124-2015		4.7	7.2	6.9	30.0	2.588	2.661	2.840	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
MILLER 55-25-019-QRY Created On: 03/28/17 Updated On:	Q	NW	NW	31	6N	3E	Iowa		0-225-91-2017	0.0	4.6	9.2	6.9	30.1	2.594	2.666	2.762	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
MILLER 55-50-014-PIT Created On: 05/11/17 Updated On:	P		NE	4	35N	1E	Price	0-225-179-2017		0.0	1.5	4.0	18.7	2.717	2.742	0.913	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
MILLER 55-25-019-QRY Created On: 02/09/18 Updated On:	Q	NW	NW	31	6N	3E	Iowa	0-225-96-2018	3.0	4.0	6.8	10.8	42.3	2.580	2.650	2.707	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
MILLER 55-25-019-QRY Created On: 03/17/21 Updated On:	Q	NW	NW	31	6N	3E	Iowa	0-225-142-2021	0.1	5.9	3.6	7.7	33.2	2.579	2.651	2.796	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
MILLER 55-50-014-PIT Created On: 05/17/22 Updated On:	P		NE	4	35N	1E	Price	0-225-201-2022	0.0	0.0	4.2	4.1	19.2	2.724	2.752	1.063	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
MILLER 55-25-019-QRY Created On: 02/28/24 Updated On:	Q	NW	NW	31	6N	3E	Iowa	0-225-179-2024	0.8	8.1	10.1	10.2	38.4	2.537	2.627	3.577	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
MIMBACH 55-55-008-QRY Created On: 01/08/15 Updated On:	Q	SW	NW	5	28N	19W	St. Croix	0-225-38-2015		0.0	6.4	7.6	29.5	2.694	2.735	1.497	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
MIMBACH 55-55-008-QRY Created On: 04/21/17 Updated On:	Q	SW	NW	5	28N	19W	St. Croix	0-225-140-2017	0.1	0.0	2.7	6.7	28.5	2.675	2.720	1.702	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
MIMBACH 55-55-008-QRY Created On: 01/08/20 Updated On:	Q	SW	NW	5	28N	19W	St. Croix	0-225-60-2020	2.2	0.0	8.1	10.0	37.8	2.562	2.639	2.990	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
MIMBACH 55-55-008-QRY Created On: 01/03/23 Updated On:	Q	SW	NW	5	28N	19W	St. Croix	0-225-55-2023	0.7	7.7	12.4	13.9	44.8	2.559	2.642	3.214	
	Approved Use : CONCRETE, OGBC, Base Aggregate																
MIMBACH 55-55-008-QRY Created On: 03/01/23 Updated On:	Q	SW	NW	5	28N	19W	St. Croix	0-225-161-2023	0.3	2.6	2.3	8.2	32.7	2.643	2.700	2.160	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
MINDORO 55-32-012-QRY Created On: 05/04/17 Updated On:	Q	SW	SW	33	18N	6W	La Crosse	0-225-174-2017		0.0	2.7	10.2	32.7	2.611	2.669	2.187	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
MINDORO 55-32-012-QRY Created On: 01/08/20 Updated On:	Q	SW	SW	33	18N	6W	La Crosse	0-225-67-2020	0.7	0.0	7.4	10.3	38.6	2.584	2.650	2.549	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
MINDORO 55-32-012-QRY Created On: 01/04/23 Updated On:	Q	SW	SW	33	18N	6W	La Crosse	0-225-87-2023	0.6	3.5	1.5	9.7	38.3	2.596	2.659	2.442	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
MINONG 55-65-009-QRY Created On: 10/08/15 Updated On:	Q	NE	NW	27	42N	11W	Washburn	0-225-241-2015		0.0	0.4	2.9	11.8	2.903	2.915	0.400	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
Source Name	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
MINONG 55-65-009-QRY Created On: 06/07/18 Updated On:	Q	NE	NW	27	42N	11W	Washburn	0-225-219-2018		0.0	0.5	2.3	10.1	2.930	2.940	0.320		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
MINONG 55-65-009-QRY Created On: 07/07/22 Updated On:	Q	NE	NW	27	42N	11W	Washburn	0-225-246-2022	0.0	0.5	0.3	2.0	10.7	2.914	2.924	0.339		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MINONG 55-65-009-QRY Created On: 01/02/25 Updated On:	Q	NE	NW	27	42N	11W	Washburn	0-225-18-2025	0.0	0.2	0.2	3.1	13.8	2.907	2.922	0.512		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MISHICOT 55-36-027-PIT Created On: 01/12/16 Updated On:	P	NE	SE	27	21N	23E	Manitowoc	0-225-55-2016		0.0	1.3	6.1	28.9	2.727	2.757	1.109		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
MISHICOT 55-36-027-PIT Created On: 01/05/21 Updated On:	P	NE	SE	27	21N	23E	Manitowoc	0-225-105-2021	0.0	3.7	0.9	5.7	27.3	2.675	2.721	1.710		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MITCH KING 55-37-051-PIT Created On: 01/03/17 Updated On:	P	SW	NE	6	26N	9E	Marathon	0-225-3-2017		0.0	2.2	8.2	33.4	2.619	2.650	1.173		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
MITCH KING 55-37-051-PIT Created On: 02/17/22 Updated On:	P	SW	NE	6	26N	9E	Marathon	0-225-133-2022	1.3	0.0	2.5	9.0	34.2	2.628	2.655	1.035		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
MOATS 55-09-044-PIT Created On: 03/08/18 Updated On:	P	SW	NE	15	29N	7W	Chippewa	0-225-114-2018	8.1	0.0	6.5	5.9	20.5	2.630	2.674	1.682	
	Approved Use : HMA<MT, HMA>=MT, Base Aggregate																
MOATS 55-09-044-PIT Created On: 01/05/21 Updated On:	P	SW	NE	15	29N	7W	Chippewa	0-225-90-2021	2.6	0.0	2.3	5.0	21.7	2.677	2.712	1.298	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
MOLLETT 55-62-022-QRY Created On: 05/19/16 Updated On:	Q	NE	SE	4	12N	4W	Vernon	0-225-180-2016		0.0	4.6	9.4	35.5	2.636	2.686	1.903	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
MOLLETT 55-62-022-QRY Created On: 01/07/19 Updated On:	Q	NE	SE	4	12N	4W	Vernon	0-225-51-2019	0.5	0.0	2.0	8.1	33.7	2.632	2.683	1.931	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
MOLLETT 55-62-022-QRY Created On: 01/10/22 Updated On:	Q	NE	SE	4	12N	4W	Vernon	0-225-101-2022	0.2	6.0	0.5	9.4	35.2	2.635	2.690	2.091	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
MOLLETT 55-62-022-QRY Created On: 01/02/25 Updated On:	Q	NE	SE	4	12N	4W	Vernon	0-225-92-2025	0.5	2.1	0.4	9.7	36.0	2.631	2.688	2.147	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
MONICO 55-43-016-PIT Created On: 07/16/20 Updated On:	P	NW	SE	26	36N	11E	Oneida	0-225-220-2020	0.0	1.3	0.4	3.2	13.4	2.699	2.715	0.615	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
MONICO 55-43-016-PIT Created On: 01/02/25 Updated On:	P	NW	SE	26	36N	11E	Oneida	0-225-70-2025	0.2	1.8	0.6	3.0	14.1	2.729	2.748	0.688	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
MONROE CONSTRUCTION 55-23-014-QRY Created On: 03/08/17 Updated On:	Q	SE	NE	32	2N	7E	Green	0-225-76-2017	0.2	11.2	2.6	11.5	40.7	2.573	2.650	2.974	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
MONROE CONSTRUCTION 55-23-014-QRY Created On: 04/17/23 Updated On:	Q	SE	NE	32	2N	7E	Green	0-225-196-2023	0.9	4.2	6.3	12.0	43.5	2.514	2.611	3.860	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
MORGAN 55-37-052-PIT Created On: 04/05/19 Updated On:	P	SE	SW	35	29N	5E	Marathon	0-225-123-2019	0.6	0.0	0.8	5.1	21.5	2.642	2.673	1.161	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
MORGAN 55-37-052-PIT Created On: 01/02/24 Updated On:	P	SE	SW	35	29N	5E	Marathon	0-225-57-2024	0.6	0.0	1.6	3.8	20.9	2.615	2.650	1.356	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
MORRIS 55-22-040-QRY Created On: 04/09/15 Updated On:	Q	NW	NW	3	5N	3W	Grant	0-225-116-2015	1.3	2.4	3.9	11.4	39.8	2.671	2.733	2.297	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
MORRIS 55-24-012-QRY Created On: 04/03/17 Updated On:	Q	SE	SW	3	16N	13E	Green Lake	0-225-99-2017	0.7	6.4	5.3	12.7	37.1	2.648	2.698	1.874	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
Source Name	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
MORRIS 55-24-012-QRY Created On: 05/07/20 Updated On:	Q	SE	SW	3	16N	13E	Green Lake	0-225-171-2020	3.2	22.9	3.8	10.4	38.1	2.648	2.703	2.072		
MORRIS 55-24-012-QRY Created On: 05/27/21 Updated On:	Q	SE	SW	3	16N	13E	Green Lake	0-225-216-2021	2.1	5.7	3.6	7.7	29.8	2.682	2.722	1.487		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MORRIS 55-22-040-QRY Created On: 04/05/23 Updated On:	Q	NW	NW	3	5N	3W	Grant	0-225-188-2023		17.6	2.7	9.5	37.8	2.657	2.685	1.057		
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																	
MORRIS 55-24-012-QRY Created On: 05/20/24 Updated On:	Q	SE	SW	3	16N	13E	Green Lake	0-225-254-2024	0.7	0.7	1.4	6.7	29.0	2.704	2.742	1.428		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MORRISON 55-47-018-QRY Created On: 06/10/16 Updated On:	Q	SE	NW	35	25N	18W	Pierce	0-225-196-2016	2.1	0.0	2.1	7.3	31.2	2.665	2.709	1.622		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
MORRISON 55-47-018-QRY Created On: 01/07/19 Updated On:	Q	SE	NW	35	25N	18W	Pierce	0-225-62-2019	2.2	0.0	5.7	9.5	38.5	2.614	2.669	2.125		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MORRISON 55-47-018-QRY Created On: 03/07/22 Updated On:	Q	SE	NW	35	25N	18W	Pierce	0-225-141-2022		3.2	5.1	8.5	34.9	2.640	2.690	1.900		
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
MORRISON 55-47-018-QRY Created On: 01/02/25 Updated On:	Q	SE	NW	35	25N	18W	Pierce	0-225-21-2025	1.1	4.5	7.9	9.6	38.4	2.618	2.678	2.308	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
MOUNDS BRANCH 55-33-018-QRY Created On: 01/29/24 Updated On:	Q	NW	NE	33	4N	1E	Lafayette	0-225-150-2024	1.0	5.8	3.2	9.2	34.9	2.574	2.645	2.755	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
MOUNTAIN STONEWORKS INC. 55-42-027-PIT Created On: 07/11/18 Updated On:	P		NW	3	31N	16E	Oconto	0-225-250-2018	0.5	0.0	1.4	5.2	23.8	2.706	2.727	0.754	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
MOUNTAIN STONEWORKS INC. 55-42-027-PIT Created On: 05/01/24 Updated On:	P		NW	3	31N	16E	Oconto	0-225-244-2024	0.1	0.0	2.3	4.9	22.5	2.687	2.706	0.712	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
MROCZINSKI 55-37-054-PIT Created On: 04/24/19 Updated On:	P	SW	NW	16	29N	5E	Marathon	0-225-169-2019	0.0	0.0	0.2	3.5	17.8	2.638	2.656	0.675	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
MROCZINSKI 55-37-054-PIT Created On: 01/02/24 Updated On:	P	SW	NW	16	29N	5E	Marathon	0-225-60-2024	0.0	0.0	6.9	6.3	25.7	2.637	2.673	1.372	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
MROTEK 55-57-013-PIT Created On: 01/03/18 Updated On:	P		SW	1	41N	8W	Sawyer	0-225-16-2018	0.8	0.0	2.2	3.6	15.8	2.810	2.837	0.969	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
MROTEK 55-57-013-PIT Created On: 01/03/23 Updated On:	P		SW	1	41N	8W	Sawyer	0-225-57-2023	1.9	1.5	1.1	3.8	16.1	2.769	2.800	1.122	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
* MURRAY 55-15-017-PIT Created On: 07/30/15 Updated On:	P	NE	SE	26	26N	23E	Door	0-225-220-2015	0.1	0.0	9.3	8.2	36.1	2.638	2.697	2.256	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
* MURRAY 55-15-017-PIT Created On: 08/25/20 Updated On:	P	NE	SE	26	26N	23E	Door	0-225-236-2020	1.5	0.0	3.4	6.5	30.2	2.693	2.736	1.598	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
MUSKEGO 55-67-029-PIT Created On: 01/04/18 Updated On:	P	SW	SW	18	5N	20E	Waukesha	0-225-76-2018	0.3	2.9	1.8	3.8	24.9	2.676	2.723	1.774	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
MUSKEGO 55-67-029-PIT Created On: 01/03/23 Updated On:	P	SW	SW	18	5N	20E	Waukesha	0-225-73-2023	0.1	3.6	0.9	4.7	22.7	2.700	2.735	1.314	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
MYKLEBUST 55-56-023-PIT Created On: 01/03/18 Updated On:	P		NE	26	13N	6E	Sauk	0-225-7-2018	1.5	0.0	1.5	6.5	26.3	2.720	2.753	1.219	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
MYKLEBUST 55-56-023-PIT Created On: 04/17/23 Updated On:	P		NE	26	13N	6E	Sauk	0-225-199-2023	0.4	0.0	2.6	5.4	24.8	2.697	2.720	0.856	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
NABER 55-28-009-PIT Created On: 03/20/20 Updated On:	P	NE	NW	31	5N	14E	Jefferson	0-225-133-2020	0.7	0.0	1.7	6.3	30.2	2.654	2.697	1.606	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
NABER 55-28-009-PIT Created On: 01/14/25 Updated On:	P	NE	NW	31	5N	14E	Jefferson	0-225-95-2025	1.0	10.1	3.2	5.4	26.7	2.684	2.726	1.556	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
NABER QUARRY 55-28-022-QRY Created On: 09/06/22 Updated On:	Q	NE	NW	31	5N	14E	Jefferson	0-225-255-2022	2.2	15.6	10.6	9.7	39.0	2.633	2.694	2.328	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
NABER QUARRY 55-28-022-QRY Created On: 11/07/22 Updated On:	Q	NE	NW	31	5N	14E	Jefferson	0-225-261-2022	0.2	10.9	6.1	4.9	26.5	2.693	2.736	1.614	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
NABER QUARRY 55-28-022-QRY Created On: 01/14/25 Updated On:	Q	NE	NW	31	5N	14E	Jefferson	0-225-97-2025	0.1	13.9	5.7	12.5	39.4	2.643	2.706	2.403	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
NAEDLER 55-10-021-QRY Created On: 06/12/17 Updated On:	Q	SE	NE	35	25N	1W	Clark	0-225-210-2017		0.0	2.2	4.9	23.9	2.632	2.647	0.562	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
NAEDLER 55-10-021-QRY Created On: 01/08/20 Updated On:	Q	SE	NE	35	25N	1W	Clark	0-225-57-2020	0.2	0.0	0.8	5.5	25.2	2.632	2.648	0.598	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
NAEDLER 55-10-021-QRY Created On: 01/03/23 Updated On:	Q	SE	NE	35	25N	1W	Clark	0-225-39-2023	0.3	2.9	3.1	6.4	27.9	2.614	2.634	0.783	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
NANKEY 55-25-020-QRY Created On: 01/05/17 Updated On:	Q	SE	NE	14	7N	1E	Iowa	0-225-26-2017	0.9	3.4	5.2	7.2	30.2	2.634	2.685	1.932	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
NANKEY 55-25-020-QRY Created On: 01/04/19 Updated On:	Q	SE	NE	14	7N	1E	Iowa	0-225-28-2019	0.6	6.4	4.8	6.7	28.9	2.645	2.692	1.786	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
NANKEY 55-25-020-QRY Created On: 01/02/24 Updated On:	Q	SE	NE	14	7N	1E	Iowa	0-225-40-2024	0.2	5.1	2.3	9.2	32.6	2.621	2.677	2.131	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
NEA MENASHA 55-70-024-QRY Created On: 01/05/15 Updated On:	Q		NW	4	20N	17E	Winnebago	0-225-3-2015		4.8	2.8	3.9	19.1	2.733	2.765	1.159	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
NEA MENASHA 55-70-024-QRY Created On: 01/04/18 Updated On:	Q		NW	4	20N	17E	Winnebago	0-225-56-2018		11.5	3.0	4.7	25.5	2.717	2.751	1.240	
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																
NEA MENASHA 55-70-024-QRY Created On: 01/04/21 Updated On:	Q		NW	4	20N	17E	Winnebago	0-225-44-2021	0.0	10.6	3.6	5.5	26.9	2.722	2.757	1.272	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
NEA MENASHA 55-70-024-QRY Created On: 01/02/24 Updated On:	Q		NW	4	20N	17E	Winnebago	0-225-98-2024	0.1	12.7	0.3	5.0	25.1	2.747	2.771	0.846	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
NEBEL 55-15-003-QRY Created On: 08/19/15 Updated On:	Q	NE	SW	20	26N	24E	Door	0-225-231-2015		0.0	8.1	4.9	22.7	2.780	2.807	0.971	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
NEBEL 55-15-003-QRY Created On: 04/01/25 Updated On:	Q	NE	SW	20	26N	24E	Door	0-225-181-2025	0.0	0.0	2.2	5.0	24.2	2.784	2.804	0.744	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
NEECK READY MIX 55-50-016-PIT Created On: 01/04/19 Updated On:	P	NW	NW	31	39N	1E	Price	0-225-3-2019	1.0	0.0	2.0	4.1	19.0	2.738	2.764	0.924	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
NEECK READY MIX 55-50-016-PIT Created On: 01/02/24 Updated On:	P	NW	NW	31	39N	1E	Price	0-225-90-2024	0.3	2.6	2.8	3.6	17.5	2.722	2.750	1.034	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
NEILLSVILLE 55-10-035-QRY Created On: 06/12/17 Updated On:	Q	SE	SW	10	24N	2W	Clark	0-225-208-2017		0.0	0.4	4.7	22.5	2.598	2.611	0.494	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
NEILLSVILLE 55-10-035-QRY Created On: 01/08/20 Updated On:	Q	SE	SW	10	24N	2W	Clark	0-225-61-2020	0.4	0.0	1.5	5.0	23.1	2.609	2.624	0.537	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
Source Name	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
NEILLSVILLE 55-10-035-QRY Created On: 01/02/24 Updated On:	Q	SE	SW	10	24N	2W	Clark	0-225-109-2024	1.2	0.4	1.4	5.2	22.9	2.585	2.605	0.767		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
NEKIMI QUARRY 55-70-041-QRY Created On: 08/14/24 Updated On:	Q	NE	NW	14	17N	16E	Winnebago	0-225-300-2024	0.0	2.9	2.3	6.2	26.6	2.753	2.782	1.050		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
* NELSON MINE 55-09-046-PIT Created On: 01/12/15 Updated On:	P	NW	NW	13	28N	9W	Chippewa	0-225-57-2015		0.0	3.7	5.0	21.5	2.627	2.657	1.113		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
* NELSON MINE 55-09-046-PIT Created On: 04/02/20 Updated On:	P	NW	NW	13	28N	9W	Chippewa	0-225-141-2020	1.5	0.0	1.2	5.1	20.8	2.721	2.739	0.692		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
* NERDRUM 55-10-038-PIT Created On: 10/05/20 Updated On:	P	SE	NW	15	29N	2W	Clark	0-225-243-2020	1.5	0.0	1.2	4.9	21.9	2.684	2.717	1.228		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
NESHKORO 55-24-013-PIT Created On: 05/14/25 Updated On:	P	NW	SW	23	17N	11E	Green Lake	0-225-210-2025	0.3	3.6	5.2	8.2	33.3	2.698	2.736	1.412		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
NEUMAN 55-60-018-PIT Created On: 06/26/17 Updated On:	P	NE	SE	28	32N	1E	Taylor	0-225-222-2017		0.0	0.6	3.5	17.8	2.729	2.758	1.052		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
Source Name	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
NEUMAN 55-60-018-PIT Created On: 06/28/22 Updated On:	P	NE	SE	28	32N	1E	Taylor	0-225-239-2022	1.1	0.0	2.4	3.6	17.3	2.751	2.778	0.995		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
NEW LONDON 55-44-025-QRY Created On: 05/26/16 Updated On:	Q			30	22N	15E	Outagamie	0-225-192-2016		8.3	8.8	7.4	31.7	2.691	2.731	1.467		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
NEW LONDON 55-44-025-QRY Created On: 01/25/19 Updated On:	Q			30	22N	15E	Outagamie	0-225-89-2019	0.4	2.6	1.1	8.0	31.3	2.731	2.759	1.005		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
NEW LONDON 55-44-025-QRY Created On: 04/28/22 Updated On:	Q			30	22N	15E	Outagamie	0-225-186-2022	0.4	7.3	2.1	6.3	29.8	2.722	2.754	1.193		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
NEW LONDON 55-44-025-QRY Created On: 01/14/25 Updated On:	Q			30	22N	15E	Outagamie	0-225-103-2025	0.0	3.0	3.3	6.9	29.3	2.709	2.743	1.248		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
NLC MERCER 55-26-024-PIT Created On: 05/02/16 Updated On:	P	S	NW	6	42N	4E	Iron	0-225-159-2016		0.0	0.5	3.7	18.2	2.734	2.760	0.963		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
NLC MERCER 55-26-024-PIT Created On: 01/05/21 Updated On:	P	S	NW	6	42N	4E	Iron	0-225-55-2021	1.1	0.0	1.7	3.4	17.9	2.731	2.756	0.924		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
NLC WOODRUFF 55-63-013-PIT Created On: 04/11/18 Updated On:	P	NW	SE	14	40N	6E	Vilas	0-225-169-2018	0.6	0.0	0.6	3.6	18.2	2.691	2.713	0.818	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
NLC WOODRUFF 55-63-013-PIT Created On: 01/03/23 Updated On:	P	NW	SE	14	40N	6E	Vilas	0-225-23-2023	1.2	0.0	1.0	4.5	20.2	2.701	2.722	0.812	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
NOLL 55-38-022-PIT Created On: 03/02/15 Updated On:	P	NW	SW	8	30N	21E	Marinette	0-225-85-2015	0.5	0.0	3.4	5.0	29.2	2.716	2.746	1.104	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
NOLL 55-38-022-PIT Created On: 01/02/20 Updated On:	P	NW	SW	8	30N	21E	Marinette	0-225-2-2020	0.5	0.0	5.7	5.5	27.2	2.713	2.745	1.177	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
NOLL 55-38-022-PIT Created On: 01/14/25 Updated On:	P	NW	SW	8	30N	21E	Marinette	0-225-106-2025	1.8	0.0	2.1	5.9	29.6	2.684	2.719	1.330	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
NORROK 55-38-023-QRY Created On: 05/10/18 Updated On:	Q	NE	SE	30	31N	22E	Marinette	0-225-199-2018	0.3	7.9	1.2	7.1	30.1	2.689	2.735	1.729	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
NORROK 55-38-023-QRY Created On: 04/28/22 Updated On:	Q	NE	SE	30	31N	22E	Marinette	0-225-182-2022	0.0	13.4	11.7	6.6	30.1	2.681	2.720	1.459	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
Source Name	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
NORROK 55-38-023-QRY Created On: 05/14/25 Updated On:	Q	NE	SE	30	31N	22E	Marinette	0-225-207-2025	0.0	13.1	7.7	7.9	33.4	2.676	2.716	1.499		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
NORWAY GROVE 55-13-068-PIT Created On: 10/27/22 Updated On:	P	NW	SW	14	9N	9E	Dane	0-225-260-2022	6.8	0.0	3.8	8.4	32.9	2.656	2.698	1.587		
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																	
NOVAK 55-54-016-PIT Created On: 08/24/17 Updated On:	P	SE	NE	32	34N	9W	Rusk	0-225-261-2017		0.0	2.9	5.1	21.4	2.734	2.764	1.081		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
NOVAK 55-54-016-PIT Created On: 07/19/21 Updated On:	P	SE	NE	32	34N	9W	Rusk	0-225-246-2021	1.1	0.0	0.7	4.0	20.2	2.754	2.774	0.726		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
NYRENE 55-48-017-PIT Created On: 01/02/25 Updated On:	P	SW	NE	23	36N	18W	Polk	0-225-46-2025	1.9	0.0	2.8	5.3	19.5	2.742	2.769	1.005		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
* O'NEIL 55-06-017-QRY Created On: 05/04/17 Updated On:	Q	SE	NW	36	24N	11W	Buffalo	0-225-167-2017		0.0	14.3	14.1	47.8	2.548	2.639	3.583		
	Approved Use : Base Aggregate																	
* O'NEIL 55-06-017-QRY Created On: 01/06/20 Updated On:	Q	SE	NW	36	24N	11W	Buffalo	0-225-28-2020	0.2	0.0	12.8	14.9	46.1	2.553	2.637	3.312		
	Approved Use : Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
OAK PARK 55-13-069-QRY Created On: 01/02/24 Updated On:	Q	NE	SW	29	7N	12E	Dane	0-225-89-2024	0.1	16.0	8.1	6.6	28.8	2.578	2.656	3.038	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
* OAKFIELD STONE FOND DU LAC 55-20-033-QRY Created On: 04/22/20 Updated On:	Q	SE	SE	10	14N	17E	Fond Du Lac	0-225-154-2020	0.0	2.2	1.7	5.7	26.5	2.771	2.796	0.879	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
ODLING 55-64-013-PIT Created On: 01/19/23 Updated On:	P	NW	SE	36	2N	16E	Walworth	0-225-123-2023	1.9	2.6	2.4	4.7	30.5	2.664	2.704	1.503	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
OLDENBURG 55-34-028-PIT Created On: 01/30/25 Updated On:	P	NE	SW	19	34N	9E	Langlade	0-225-147-2025	0.7	0.0	1.6	4.9	22.5	2.693	2.724	1.158	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
OLSON 55-16-017-QRY Created On: 06/13/16 Updated On:	Q	NW	NW	24	48N	10W	Douglas	0-225-198-2016		1.7	0.2	2.4	11.9	2.853	2.885	1.121	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
OLSON 55-57-017-PIT Created On: 02/13/17 Updated On:	P	NW	SW	14	41N	9W	Sawyer	0-225-71-2017		0.0	4.6	3.1	15.6	2.815	2.840	0.882	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
OLSON 55-16-017-QRY Created On: 06/03/21 Updated On:	Q	NW	NW	24	48N	10W	Douglas	0-225-218-2021	0.7	0.0	4.0	4.4	18.7	2.844	2.872	1.016	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
OLSON 55-57-017-PIT Created On: 01/10/22 Updated On:	P	NW	SW	14	41N	9W	Sawyer	0-225-105-2022	1.7	3.7	4.9	3.6	16.3	2.778	2.808	1.089	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
OLSON 55-16-017-QRY Created On: 04/15/24 Updated On:	Q	NW	NW	24	48N	10W	Douglas	0-225-228-2024	0.5	0.0	2.3	3.5	14.7	2.844	2.880	1.285	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
* OLYNICK - BOHLS 55-09-049-PIT Created On: 06/08/15 Updated On:	P			16	29N	5W	Chippewa	0-225-192-2015		0.0	2.4	5.1	20.3	2.716	2.752	1.321	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
* OLYNICK - BOHLS 55-09-049-PIT Created On: 04/02/20 Updated On:	P			16	29N	5W	Chippewa	0-225-142-2020	0.0	0.0	1.3	4.8	21.7	2.738	2.768	1.106	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
OPELT PIT 55-10-023-PIT Created On: 04/25/17 Updated On:	P	NE	NW	8	23N	2W	Clark	0-225-149-2017		0.0	1.1	3.9	18.9	2.709	2.734	0.920	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
OPELT PIT 55-10-023-PIT Created On: 04/05/22 Updated On:	P	NE	NW	8	23N	2W	Clark	0-225-158-2022	2.0	0.0	0.9	3.9	19.6	2.674	2.703	1.085	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
OPELT QUARRY 55-10-024-QRY Created On: 04/25/17 Updated On:	Q	NE	NW	8	23N	2W	Clark	0-225-148-2017		0.0	0.2	4.2	18.0	2.829	2.839	0.354	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
OPELT QUARRY 55-10-024-QRY Created On: 05/04/20 Updated On:	Q	NE	NW	8	23N	2W	Clark	0-225-164-2020	0.0	0.0	0.4	4.4	21.7	2.745	2.753	0.314	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
OPELT QUARRY 55-10-024-QRY Created On: 01/03/23 Updated On:	Q	NE	NW	8	23N	2W	Clark	0-225-35-2023	0.0	0.2	0.3	3.7	17.6	2.851	2.865	0.492	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
OREGON 55-13-112-PIT Created On: 01/05/17 Updated On:	P	NW	SE	36	5N	9E	Dane	0-225-50-2017	2.5	4.1	1.4	11.2	39.0	2.561	2.630	2.668	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
OREGON 55-13-112-PIT Created On: 01/04/22 Updated On:	P	NW	SE	36	5N	9E	Dane	0-225-59-2022	5.2	5.2	2.9	7.0	30.4	2.591	2.645	2.068	
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																
OSCAR 27-00-030-PIT Created On: 07/31/24 Updated On:	P	NW	NW	29	52N	14W	Statewide	0-225-293-2024	1.1	3.7	3.2	3.1	15.2	2.720	2.757	1.353	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
OSCEOLA 55-48-018-PIT Created On: 01/09/15 Updated On:	P	NW	SE	16	33N	18W	Polk	0-225-42-2015		0.0	3.4	5.8	18.3	2.780	2.809	1.068	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
OSCEOLA 55-48-018-PIT Created On: 01/02/24 Updated On:	P	NW	SE	16	33N	18W	Polk	0-225-80-2024	4.0	0.0	2.4	5.3	19.9	2.737	2.772	1.263	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
OVYN 55-60-020-QRY Created On: 02/14/17 Updated On:	Q	NE	SW	28	30N	2W	Taylor	0-225-72-2017		0.0	0.2	3.2	15.2	3.004	3.024	0.683	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
OVYN 55-60-030-PIT Created On: 02/14/17 Updated On:	P	NE	SW	28	30N	2W	Taylor	0-225-73-2017		0.0	1.4	4.2	20.3	2.659	2.700	1.526	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
OVYN 55-60-030-PIT Created On: 04/22/21 Updated On:	P	NE	SW	28	30N	2W	Taylor	0-225-187-2021	2.3	0.0	2.8	5.0	20.9	2.671	2.704	1.199	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
OVYN 55-60-020-QRY Created On: 04/22/21 Updated On:	Q	NE	SW	28	30N	2W	Taylor	0-225-188-2021	0.0	0.0	0.3	3.8	16.9	2.865	2.878	0.436	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
OVYN 55-60-020-QRY Created On: 04/15/24 Updated On:	Q	NE	SW	28	30N	2W	Taylor	0-225-219-2024	0.0	0.0	0.3	3.8	17.2	2.825	2.842	0.615	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
OWEN AVENUE QUARRY 55-10-040-QRY Created On: 08/28/24 Updated On:	Q	SW	SW	31	27N	1W	Clark	0-225-305-2024	0.4	0.0	1.1	6.1	29.9	2.621	2.635	0.549	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
OZINGA-CHANNAHON, IL 17-00-020-PIT Created On: 05/01/24 Updated On:	P	NE	E	17	34N	9E	Statewide	0-225-243-2024	2.0	15.0	2.8	5.1	25.3	2.638	2.688	1.905	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
P&D HONEY CREEK 55-51-020-PIT Created On: 01/04/18 Updated On:	P		NW 6	3N	19E	Racine		0-225-78-2018	0.5	5.8	1.8	4.1	26.4	2.675	2.720	1.666	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
P&D HONEY CREEK 55-51-020-PIT Created On: 01/03/23 Updated On:	P		NW 6	3N	19E	Racine		0-225-74-2023	0.2	11.5	1.3	5.3	24.4	2.673	2.719	1.722	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
PADDOCK 55-64-028-PIT Created On: 04/10/18 Updated On:	P	E	SE 1	3N	16E	Walworth		0-225-161-2018	1.4	0.0	1.3	5.3	25.7	2.670	2.709	1.457	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
PADDOCK 55-64-028-PIT Created On: 05/14/21 Updated On:	P	E	SE 1	3N	16E	Walworth		0-225-208-2021	4.9	7.2	3.0	4.6	29.8	2.696	2.732	1.316	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
PAFFEL 55-65-010-PIT Created On: 01/07/19 Updated On:	P	NE	NE 21	39N	12W	Washburn		0-225-59-2019	0.3	0.0	2.3	3.8	17.3	2.708	2.743	1.323	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
PAFFEL 55-65-010-PIT Created On: 01/02/24 Updated On:	P	NE	NE 21	39N	12W	Washburn		0-225-94-2024	0.9	3.3	2.0	3.9	18.6	2.706	2.742	1.313	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
PALECEK 55-02-012-PIT Created On: 06/16/22 Updated On:	P	NW	SW 24	47N	1W	Ashland		0-225-230-2022	0.6	2.1	2.4	4.2	18.9	2.753	2.780	1.004	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
PAUL BUGAR "B" 55-10-026-QRY Created On: 05/21/15 Updated On:	Q	SE	NE	26	25N	1W	Clark	0-225-178-2015		0.0	0.3	6.9	30.5	2.620	2.642	0.831		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
PAUL BUGAR "B" 55-10-026-QRY Created On: 04/25/18 Updated On:	Q	SE	NE	26	25N	1W	Clark	0-225-185-2018	0.4	0.0	0.3	5.3	26.4	2.641	2.656	0.597		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
PAUL BUGAR "B" 55-10-026-QRY Created On: 06/17/21 Updated On:	Q	SE	NE	26	25N	1W	Clark	0-225-226-2021	0.1	0.0	2.1	7.2	30.6	2.605	2.626	0.803		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
PAUL BUGAR "B" 55-10-026-QRY Created On: 02/28/24 Updated On:	Q	SE	NE	26	25N	1W	Clark	0-225-192-2024	0.5	0.0	0.5	7.2	32.6	2.615	2.628	0.490		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
PAUL BUGAR "N" 55-37-057-QRY Created On: 05/21/15 Updated On:	Q	N	NE	2	27N	2E	Marathon	0-225-176-2015		0.0	1.2	4.5	22.0	2.573	2.603	1.159		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
PAUL BUGAR "N" 55-37-057-QRY Created On: 04/25/18 Updated On:	Q	N	NE	2	27N	2E	Marathon	0-225-184-2018		0.0	0.2	5.0	23.3	2.617	2.631	0.534		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
PAUL BUGAR "N" 55-37-057-QRY Created On: 06/17/21 Updated On:	Q	N	NE	2	27N	2E	Marathon	0-225-228-2021	0.3	0.0	0.7	6.7	30.4	2.597	2.616	0.747		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Coarse Sp. Gravity		Coarse Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
PAUL BUGAR "N" 55-37-057-QRY Created On: 02/28/24 Updated On:	Q	N	NE	2	27N	2E	Marathon	0-225-193-2024	0.1	0.0	0.6	5.3	24.7	2.607	2.621	0.550	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
PAUL BUGAR "R" 55-37-058-QRY Created On: 05/21/15 Updated On:	Q	NE	NW	1	27N	2E	Marathon	0-225-177-2015		0.0	0.9	4.7	23.1	2.626	2.654	1.037	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
PAUL BUGAR "R" 55-37-058-QRY Created On: 04/25/18 Updated On:	Q	NE	NW	1	27N	2E	Marathon	0-225-183-2018	0.1	0.0	0.6	5.2	25.9	2.593	2.610	0.655	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
PAUL BUGAR "R" 55-37-058-QRY Created On: 06/17/21 Updated On:	Q	NE	NW	1	27N	2E	Marathon	0-225-227-2021	0.0	0.0	0.3	5.5	26.8	2.607	2.618	0.450	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
PAUL BUGAR "R" 55-37-058-QRY Created On: 02/28/24 Updated On:	Q	NE	NW	1	27N	2E	Marathon	0-225-194-2024	0.0	0.0	0.3	7.3	32.2	2.601	2.618	0.644	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
PAYNE AND DOLAN / RACINE 55-51-022-QRY Created On: 02/03/17 Updated On:	Q		S	29	4N	23E	Racine	0-225-57-2017	1.2	0.0	0.9	6.4	27.3	2.633	2.685	1.970	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
PAYNE AND DOLAN / RACINE 55-51-022-QRY Created On: 01/08/20 Updated On:	Q		S	29	4N	23E	Racine	0-225-78-2020	3.2	0.0	4.1	6.3	27.8	2.638	2.693	2.102	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse		Absorp. %	
Source Name	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
PAYNE AND DOLAN / RACINE 55-51-022-QRY Created On: 01/03/23 Updated On:	Q	S	29	4N	23E	Racine		0-225-50-2023	0.0	0.4	0.1	5.9	26.0	2.665	2.691	0.999	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
PEARL 55-44-014-QRY Created On: 01/02/25 Updated On:	Q	SW	SE	25	24N	18E	Outagamie	0-225-59-2025	0.0	4.9	1.4	4.9	21.2	2.794	2.811	0.641	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
PEDRETTI 55-62-028-QRY Created On: 01/09/15 Updated On:	Q	SW	NW	27	13N	7W	Vernon	0-225-51-2015		0.0	9.2	10.8	40.0	2.575	2.641	2.576	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
PEDRETTI 55-62-028-QRY Created On: 01/03/18 Updated On:	Q	SW	NW	27	13N	7W	Vernon	0-225-15-2018	0.5	0.0	2.1	8.5	32.3	2.594	2.659	2.520	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
PEDRETTI 55-62-028-QRY Created On: 01/04/21 Updated On:	Q	SW	NW	27	13N	7W	Vernon	0-225-25-2021	0.4	0.0	0.9	10.0	34.8	2.573	2.646	2.835	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
PEDRETTI 55-62-028-QRY Created On: 01/02/24 Updated On:	Q	SW	NW	27	13N	7W	Vernon	0-225-29-2024	2.1	9.0	11.7	13.4	45.6	2.538	2.619	3.220	
	Approved Use : HMA<MT, CONCRETE, OGBC, Base Aggregate																
PERZINSKI 55-49-018-PIT Created On: 04/15/24 Updated On:	P	SE	SE	20	23N	9E	Portage	0-225-218-2024	1.9	2.2	2.3	6.1	29.3	2.659	2.693	1.263	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
PETERS - PESHTIGO QUARRY 55-38-026-QRY Created On: 01/05/17 Updated On:	Q	SE	NW	33	30N	22E	Marinette	0-225-52-2017	1.8	4.4	3.7	8.9	33.7	2.663	2.715	1.953		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
PETERS - PESHTIGO QUARRY 55-38-026-QRY Created On: 01/02/20 Updated On:	Q	SE	NW	33	30N	22E	Marinette	0-225-5-2020	0.1	3.7	4.0	5.3	24.7	2.737	2.766	1.056		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
PETERS - PESHTIGO QUARRY 55-38-026-QRY Created On: 01/12/23 Updated On:	Q	SE	NW	33	30N	22E	Marinette	0-225-119-2023	0.1	3.8	4.0	7.0	31.0	2.676	2.730	2.000		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
PETERS CHASE #5 55-42-030-QRY Created On: 01/30/15 Updated On:	Q		NW	17	26N	19E	Oconto	0-225-81-2015	0.7	4.2	3.9	5.6	24.9	2.731	2.759	0.995		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
PETERS CHASE #5 55-42-030-QRY Created On: 01/07/16 Updated On:	Q		NW	17	26N	19E	Oconto	0-225-39-2016		1.8	2.6	5.3	24.4	2.720	2.748	1.033		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
PETERS CHASE #5 55-42-030-QRY Created On: 01/25/19 Updated On:	Q		NW	17	26N	19E	Oconto	0-225-90-2019	0.1	6.5	1.7	5.2	23.6	2.756	2.780	0.879		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
PETERS CHASE #5 55-42-030-QRY Created On: 01/04/22 Updated On:	Q		NW	17	26N	19E	Oconto	0-225-90-2022	0.0	2.7	1.9	5.0	23.5	2.736	2.760	0.876		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
PETERS CHASE #5 55-42-030-QRY Created On: 03/06/25 Updated On:	Q		NW	17	26N	19E	Oconto	0-225-162-2025	0.0	2.9	1.3	4.9	22.0	2.746	2.771	0.899	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
PETERS ELLISVILLE PIT 55-31-005-PIT Created On: 06/25/24 Updated On:	P	NW	NW	13	23N	23E	Kewaunee	0-225-275-2024	0.6	0.0	1.6	7.7	32.6	2.712	2.747	1.287	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
PETERS PORTERFIELD QRY 55-38-015-QRY Created On: 01/04/22 Updated On:	Q	SE	SE	19	31N	22E	Marinette	0-225-91-2022	0.0	7.3	6.6	6.9	32.0	2.696	2.731	1.314	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
PETERS PORTERFIELD QRY 55-38-015-QRY Created On: 01/14/25 Updated On:	Q	SE	SE	19	31N	22E	Marinette	0-225-104-2025	0.0	7.8	5.5	6.3	28.8	2.727	2.753	0.944	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
PETERS-BONDUEL 55-58-050-PIT Created On: 01/06/21 Updated On:	P	NW	NE	30	26N	17E	Shawano	0-225-110-2021	3.4	4.9	4.9	9.7	35.2	2.645	2.694	1.844	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
PETERS-BRUSSELS 55-15-003-PIT Created On: 04/14/16 Updated On:	P	SE	NW	26	26N	23E	Door	0-225-148-2016	0.4	0.0	9.4	8.0	25.5	2.691	2.736	1.676	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
PETERS-BRUSSELS 55-15-003-PIT Created On: 05/30/17 Updated On:	P	SE	NW	26	26N	23E	Door	0-225-195-2017	0.4	0.0	6.3	8.2	33.5	2.714	2.763	1.795	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
PETERS-BRUSSELS 55-15-003-PIT Created On: 04/20/23 Updated On:	P	SE	NW	26	26N	23E	Door	0-225-203-2023	0.2	0.0	6.9	6.1	28.5	2.719	2.757	1.393	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
PETERS-CRIVITZ QUARRY 55-38-018-QRY Created On: 06/12/25 Updated On:	Q	SW	NW	30	32N	21E	Marinette	0-225-220-2025	0.8	8.0	8.4	8.4	35.7	2.624	2.682	2.237	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
PETERSON 55-09-052-PIT Created On: 10/03/17 Updated On:	P	NE	SW	32	29N	5W	Chippewa	0-225-278-2017		0.0	0.9	4.0	19.1	2.685	2.720	1.273	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
* PETERSON 55-35-029-PIT Created On: 07/16/20 Updated On:	P	NW	SE	30	32N	6E	Lincoln	0-225-218-2020	1.4	0.0	0.8	4.2	20.6	2.688	2.717	1.087	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
PETERSON 55-09-052-PIT Created On: 01/04/22 Updated On:	P	NE	SW	32	29N	5W	Chippewa	0-225-83-2022	0.8	0.0	1.8	3.3	16.8	2.713	2.744	1.135	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
PETERSON "CC" 55-42-032-PIT Created On: 03/30/15 Updated On:	P	S	NW	32	28N	19E	Oconto	0-225-102-2015	0.2	0.0	3.3	6.8	30.5	2.734	2.765	1.134	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
PETERSON "CC" 55-42-032-PIT Created On: 01/08/20 Updated On:	P	S	NW	32	28N	19E	Oconto	0-225-75-2020	0.2	0.0	2.8	6.1	29.9	2.732	2.759	0.996	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
PETERSON "CC" 55-42-032-PIT Created On: 05/14/25 Updated On:	P	S	NW	32	28N	19E	Oconto	0-225-206-2025	0.4	0.0	1.7	6.3	29.0	2.711	2.746	1.302	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
PETERSON MARENGO 55-02-013-PIT Created On: 05/19/16 Updated On:	P	N	SW	18	45N	4W	Ashland	0-225-182-2016		0.0	2.6	5.4	23.1	2.639	2.693	2.050	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
PETERSON MARENGO 55-02-013-PIT Created On: 05/10/21 Updated On:	P	N	SW	18	45N	4W	Ashland	0-225-204-2021	2.5	0.0	14.2	5.8	23.7	2.686	2.741	2.034	
	Approved Use : Base Aggregate																
PHILLIPS 55-50-019-PIT Created On: 01/05/21 Updated On:	P	SW	SW	5	37N	1E	Price	0-225-54-2021	0.8	0.0	1.5	4.0	19.3	2.691	2.720	1.042	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
PINE BROOK 55-65-012-PIT Created On: 05/14/15 Updated On:	P		N	21	38N	11W	Washburn	0-225-174-2015		0.0	3.1	4.1	18.5	2.788	2.815	0.978	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
PINE BROOK 55-65-012-PIT Created On: 01/08/21 Updated On:	P		N	21	38N	11W	Washburn	0-225-118-2021	0.3	0.0	4.3	4.9	20.4	2.736	2.776	1.464	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
PINE LAKE MATERIALS 55-51-025-PIT Created On: 03/24/16 Updated On:	P		NE	35	3N	19E	Racine	0-225-117-2016	0.6	7.3	2.3	5.7	29.6	2.676	2.724	1.793	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
Source Name	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
PINE LAKE MATERIALS 55-51-025-PIT Created On: 01/05/21 Updated On:	P		NE	35	3N	19E	Racine	0-225-82-2021	0.0	14.4	4.8	5.0	25.0	2.654	2.703	1.880	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
* PINE RIDGE 55-35-030-PIT Created On: 05/11/15 Updated On:	P	NW	SW	8	31N	7E	Lincoln	0-225-168-2015		0.0	0.9	4.5	19.8	2.675	2.708	1.256	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
* PINE RIDGE 55-35-030-PIT Created On: 05/12/20 Updated On:	P	NW	SW	8	31N	7E	Lincoln	0-225-176-2020	1.9	0.0	2.3	4.4	20.6	2.679	2.708	1.085	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
PINE VALLEY 55-10-027-QRY Created On: 05/07/15 Updated On:	Q		NW	21	24N	2W	Clark	0-225-152-2015		0.0	0.8	5.9	25.6	2.608	2.621	0.498	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
PINE VALLEY 55-10-027-QRY Created On: 04/19/18 Updated On:	Q		NW	21	24N	2W	Clark	0-225-174-2018	0.8	0.0	1.5	6.7	28.0	2.571	2.596	0.973	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
PINE VALLEY 55-10-027-QRY Created On: 04/08/21 Updated On:	Q		NW	21	24N	2W	Clark	0-225-174-2021	2.4	1.1	3.3	8.8	32.2	2.548	2.579	1.207	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
PINE VALLEY 55-10-027-QRY Created On: 01/29/24 Updated On:	Q		NW	21	24N	2W	Clark	0-225-163-2024	1.0	1.4	0.8	4.1	21.0	2.598	2.613	0.582	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse		Sp. Gravity		Absorp. %	
Source Name	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
* PLENTY	Q			16	10N	9E	Columbia	0-225-179-2019	2.8	4.3	3.2	11.0	43.0	2.494	2.596	4.114		
55-11-030-QRY	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
Created On: 05/08/19																		
Updated On:																		
* PLENTY	Q			16	10N	9E	Columbia	0-225-250-2022	3.3	5.4	4.1	9.7	38.5	2.564	2.623	2.291		
55-11-030-QRY	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
Created On: 08/02/22																		
Updated On:																		
PLOVER	P	SW	SW	5	22N	9E	Portage	0-225-74-2017	0.2	0.0	1.8	7.1	29.0	2.661	2.691	1.110		
55-49-019-PIT	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
Created On: 03/06/17																		
Updated On:																		
PLOVER	P	SW	SW	5	22N	9E	Portage	0-225-131-2022	0.9	0.0	3.2	6.3	27.2	2.652	2.681	1.107		
55-49-019-PIT	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
Created On: 02/17/22																		
Updated On:																		
POINT SPORT	P		NE	2	41N	7W	Sawyer	0-225-19-2018	0.9	0.0	1.5	4.1	18.3	2.763	2.788	0.877		
55-57-020-PIT	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
Created On: 01/03/18																		
Updated On:																		
POINT SPORT	P		NE	2	41N	7W	Sawyer	0-225-58-2023	0.2	0.9	1.5	3.5	16.4	2.756	2.787	1.133		
55-57-020-PIT	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
Created On: 01/03/23																		
Updated On:																		
POLK LIME QUARRY	Q	NW	NE	10	32N	18W	Polk	0-225-153-2021	2.3	0.0	6.4	9.7	36.0	2.552	2.637	3.334		
55-48-034-QRY	Approved Use : Base Aggregate																	
Created On: 03/17/21																		
Updated On:																		

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
POLK LIME QUARRY 55-48-034-QRY Created On: 10/14/21 Updated On:	Q	NW	NE	10	32N	18W	Polk	0-225-269-2021	5.3	0.0	15.1	12.3	44.9	2.509	2.604	3.803	
	Approved Use : Base Aggregate																
POLK LIME QUARRY 55-48-034-QRY Created On: 01/13/22 Updated On:	Q	NW	NE	10	32N	18W	Polk	0-225-113-2022	2.4	0.0	8.8	9.2	38.0	2.529	2.621	3.641	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
POLK LIME QUARRY 55-48-034-QRY Created On: 04/01/25 Updated On:	Q	NW	NE	10	32N	18W	Polk	0-225-180-2025	0.7	0.0	12.4	8.3	34.9	2.540	2.628	3.466	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
POPPLE RIVER 55-21-016-PIT Created On: 07/01/21 Updated On:	P	SW	NW	12	38N	14E	Forest	0-225-240-2021	0.0	0.2	0.2	3.6	17.1	2.734	2.749	0.556	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
POTAPENKO 55-09-053-PIT Created On: 03/08/18 Updated On:	P	SE	SW	25	31N	5W	Chippewa	0-225-113-2018	3.3	0.0	1.4	3.9	21.1	2.655	2.691	1.380	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
POTAPENKO 55-09-053-PIT Created On: 01/10/23 Updated On:	P	SE	SW	25	31N	5W	Chippewa	0-225-118-2023	2.3	0.0	2.1	3.7	19.3	2.643	2.685	1.610	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
PRAIRIE AVE S&G 55-53-030-PIT Created On: 02/16/16 Updated On:	P		SW	6	1N	13E	Rock	0-225-87-2016	0.4	2.2	0.8	8.1	39.5	2.669	2.708	1.481	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
PRAIRIE AVE S&G 55-53-030-PIT Created On: 02/06/18 Updated On:	P		SW	6	1N	13E	Rock	0-225-87-2018	4.5	0.0	2.4	5.5	26.7	2.672	2.709	1.399	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
PRAIRIE AVE S&G 55-53-030-PIT Created On: 01/07/19 Updated On:	P		SW	6	1N	13E	Rock	0-225-68-2019	4.6	0.0	4.7	5.3	26.2	2.654	2.694	1.490	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
PRAIRIE AVE S&G 55-53-030-PIT Created On: 01/02/24 Updated On:	P		SW	6	1N	13E	Rock	0-225-1-2024	4.5	0.0	4.1	5.0	25.8	2.662	2.701	1.464	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
PRESCOTT 55-47-020-QRY Created On: 09/02/16 Updated On:	Q	NW	NW	12	26N	20W	Pierce	0-225-252-2016		0.0	3.5	8.6	34.8	2.604	2.664	2.321	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
PRESCOTT 55-47-020-QRY Created On: 01/07/19 Updated On:	Q	NW	NW	12	26N	20W	Pierce	0-225-61-2019	1.2	0.0	7.4	8.4	34.6	2.622	2.679	2.160	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
PRESCOTT 55-47-020-QRY Created On: 01/04/22 Updated On:	Q	NW	NW	12	26N	20W	Pierce	0-225-75-2022	4.6	7.0	5.2	7.8	33.1	2.635	2.685	1.901	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
PRESCOTT 55-47-020-QRY Created On: 01/02/25 Updated On:	Q	NW	NW	12	26N	20W	Pierce	0-225-34-2025	2.6	0.0	3.3	7.8	34.5	2.605	2.660	2.120	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
* PRIBBERNOW 55-10-032-QRY Created On: 01/03/17 Updated On:	Q	E	E	13	28N	2W	Clark	0-225-5-2017		0.0	0.8	4.6	21.0	2.626	2.647	0.784	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
* PRIBBERNOW 55-10-032-QRY Created On: 01/07/20 Updated On:	Q	E	E	13	28N	2W	Clark	0-225-41-2020	0.0	0.0	0.6	4.4	19.9	2.707	2.716	0.361	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
PROHASKA 55-50-024-PIT Created On: 06/26/17 Updated On:	P	SW	SW	10	36N	1W	Price	0-225-220-2017		0.0	1.9	4.7	21.5	2.736	2.758	0.829	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
PROHASKA 55-50-024-PIT Created On: 01/04/22 Updated On:	P	SW	SW	10	36N	1W	Price	0-225-86-2022	1.5	0.0	1.7	4.9	22.5	2.742	2.768	0.933	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
R & R WASH 55-20-035-PIT Created On: 04/24/19 Updated On:	P	E	SW	7	16N	14E	Fond Du Lac	0-225-164-2019	1.9	4.4	4.0	7.8	31.5	2.704	2.743	1.446	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
R & R WASH 55-20-035-PIT Created On: 01/02/24 Updated On:	P	E	SW	7	16N	14E	Fond Du Lac	0-225-132-2024	7.6	2.0	8.4	10.6	37.8	2.642	2.693	1.903	
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																
RADEMANN STONE 55-20-036-QRY Created On: 05/08/15 Updated On:	Q	NE	SW	11	14N	17E	Fond Du Lac	0-225-156-2015		1.2	0.4	6.9	29.4	2.778	2.795	0.615	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
RADEMANN STONE 55-20-036-QRY Created On: 06/27/18 Updated On:	Q	NE	SW	11	14N	17E	Fond Du Lac	0-225-241-2018		1.0	1.0	6.3	30.2	2.759	2.781	0.797	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
RADEMANN STONE 55-20-036-QRY Created On: 04/30/21 Updated On:	Q	NE	SW	11	14N	17E	Fond Du Lac	0-225-197-2021	0.7	1.1	0.5	7.7	31.5	2.739	2.763	0.867	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
RADEMANN STONE 55-20-036-QRY Created On: 01/02/24 Updated On:	Q	NE	SW	11	14N	17E	Fond Du Lac	0-225-108-2024	0.0	0.7	0.7	6.2	28.4	2.770	2.790	0.719	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
RAISBECK QUARRY 55-22-042-QRY Created On: 04/06/17 Updated On:	Q	SE	NE	12	4N	5W	Grant	0-225-113-2017	1.8	3.4	5.5	8.8	39.3	2.588	2.652	2.494	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
RAISBECK QUARRY 55-22-042-QRY Created On: 01/02/25 Updated On:	Q	SE	NE	12	4N	5W	Grant	0-225-86-2025	1.7	6.6	7.3	6.9	34.6	2.625	2.683	2.230	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
RANDY MAHR 55-09-055-PIT Created On: 01/07/15 Updated On:	P	NE	SW	23	29N	5W	Chippewa	0-225-10-2015		0.0	1.8	3.7	18.0	2.749	2.774	0.907	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
RANDY MAHR 55-09-055-PIT Created On: 01/05/21 Updated On:	P	NE	SW	23	29N	5W	Chippewa	0-225-92-2021	1.5	0.0	3.4	4.3	20.6	2.714	2.745	1.143	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
RATKOWSKI PIT 55-50-030-PIT Created On: 01/02/25 Updated On:	P			30	39N	1E	Price	0-225-68-2025	0.0	0.0	1.8	4.2	19.1	2.746	2.767	0.757	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
RATZ 55-06-020-QRY Created On: 04/23/15 Updated On:	Q	SW	SW	12	20N	11W	Buffalo	0-225-134-2015		0.0	3.2	11.9	41.4	2.595	2.659	2.438	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
RATZ 55-06-020-QRY Created On: 01/04/18 Updated On:	Q	SW	SW	12	20N	11W	Buffalo	0-225-47-2018	0.3	0.0	0.9	9.0	35.1	2.609	2.668	2.269	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
RATZ 55-06-020-QRY Created On: 01/04/21 Updated On:	Q	SW	SW	12	20N	11W	Buffalo	0-225-39-2021	0.9	0.0	0.4	7.8	33.7	2.590	2.650	2.320	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
RATZ 55-06-020-QRY Created On: 01/02/24 Updated On:	Q	SW	SW	12	20N	11W	Buffalo	0-225-117-2024	0.3	3.5	4.3	10.1	39.3	2.607	2.667	2.313	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
RC HOGARTY 55-37-092-QRY Created On: 07/01/21 Updated On:	Q	SW	SE	32	30N	10E	Marathon	0-225-241-2021	0.1	0.0	1.0	6.7	34.0	2.656	2.673	0.648	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
RC HOGARTY 55-37-092-QRY Created On: 01/29/24 Updated On:	Q	SW	SE	32	30N	10E	Marathon	0-225-155-2024	0.0	0.0	0.6	11.8	38.5	2.676	2.685	0.360	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
READFIELD 55-68-025-QRY Created On: 08/03/16 Updated On:	Q	NE	SW	26	21N	14E	Waupaca	0-225-231-2016		0.0	2.0	7.2	31.5	2.645	2.702	2.155	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
READFIELD 55-68-025-QRY Created On: 01/10/19 Updated On:	Q	NE	SW	26	21N	14E	Waupaca	0-225-85-2019	0.3	0.0	2.4	6.1	29.8	2.712	2.752	1.453	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
READFIELD 55-68-025-QRY Created On: 03/17/22 Updated On:	Q	NE	SW	26	21N	14E	Waupaca	0-225-147-2022	0.9	0.0	1.2	9.2	39.7	2.635	2.686	1.905	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
READFIELD 55-68-025-QRY Created On: 01/14/25 Updated On:	Q	NE	SW	26	21N	14E	Waupaca	0-225-102-2025		2.1	6.3	11.3	41.5	2.631	2.681	1.902	
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 01/07/15 Updated On:	Q							0-225-9-2015			0.0						
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 01/08/15 Updated On:	Q							0-225-24-2015		0.0	0.0	6.6	28.2				
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 01/21/15 Updated On:	Q							0-225-72-2015			0.0	9.0	34.7				
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
RECYCLED PCC 55-99-031-QRY Created On: 03/02/15 Updated On:	Q							0-225-86-2015		0.0	0.0	8.3	32.6				
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 03/09/15 Updated On:	Q							0-225-90-2015		0.0	0.0	12.6	40.9				
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 03/09/15 Updated On:	Q							0-225-91-2015			0.0	8.2	40.1				
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 03/19/15 Updated On:	Q							0-225-96-2015			0.0	6.7	33.9				
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 03/30/15 Updated On:	Q							0-225-110-2015			0.0	7.2	34.0				
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 04/08/15 Updated On:	Q							0-225-113-2015		0.0	0.0	10.4	40.2				
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 04/08/15 Updated On:	Q							0-225-114-2015		0.0	0.0	7.6	30.0				
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
RECYCLED PCC 55-99-031-QRY Created On: 04/08/15 Updated On:	Q							0-225-115-2015		0.0	0.0	7.3	30.0				
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 04/23/15 Updated On:	Q							0-225-133-2015		0.0	0.0	8.9	28.8				
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 04/23/15 Updated On:	Q							0-225-137-2015		0.0	0.0	8.9	31.9				
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 04/23/15 Updated On:	Q							0-225-138-2015		0.0	0.0	6.8	34.0				
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 04/28/15 Updated On:	Q							0-225-140-2015		0.0	0.0	11.4	34.2				
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 05/06/15 Updated On:	Q							0-225-143-2015		0.0	0.0	8.3	33.1				
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 05/06/15 Updated On:	Q							0-225-144-2015			0.0	9.1	34.9				
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
RECYCLED PCC 55-99-031-QRY Created On: 05/06/15 Updated On:	Q							0-225-145-2015		0.0	0.0	8.2	35.8				
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 05/07/15 Updated On:	Q							0-225-150-2015		0.0	0.0	8.1	29.8				
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 05/11/15 Updated On:	Q							0-225-161-2015			0.0	8.9	34.2				
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 05/11/15 Updated On:	Q							0-225-166-2015			0.0	7.8	27.4				
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 05/14/15 Updated On:	Q							0-225-173-2015		0.0	0.0	9.6	38.5				
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 06/17/15 Updated On:	Q							0-225-195-2015			0.0	12.0	35.0				
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 06/17/15 Updated On:	Q							0-225-196-2015			0.0	10.7	36.0				
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
RECYCLED PCC 55-99-031-QRY Created On: 06/23/15 Updated On:	Q							0-225-198-2015		0.0	0.0	9.3	34.0				
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 06/25/15 Updated On:	Q							0-225-201-2015		0.0	0.0	10.2	36.0				
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 07/23/15 Updated On:	Q							0-225-217-2015		0.0	0.0	7.5	29.2				
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 08/05/15 Updated On:	Q							0-225-225-2015		0.0	0.0	9.9	35.2				
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 08/05/15 Updated On:	Q							0-225-226-2015		0.0	0.0	7.0	28.7				
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 09/24/15 Updated On:	Q							0-225-239-2015			0.0	9.9	38.4				
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 10/08/15 Updated On:	Q							0-225-243-2015			0.0	7.5	28.0				
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
RECYCLED PCC 55-99-031-QRY Created On: 10/08/15 Updated On:	Q							0-225-244-2015			0.0	6.7	28.4				
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 11/04/15 Updated On:	Q							0-225-246-2015		0.0	0.0	7.7	26.1				
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 11/04/15 Updated On:	Q							0-225-247-2015		0.0	0.0	7.9	33.4				
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 01/20/16 Updated On:	Q							0-225-59-2016			0.0	10.6	36.1				
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 01/21/16 Updated On:	Q							0-225-72-2016		0.0	0.0	10.7	41.6				
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 03/18/16 Updated On:	Q							0-225-100-2016			0.0	9.1	33.9				
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 03/18/16 Updated On:	Q							0-225-101-2016			0.0	8.6	33.5				
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
RECYCLED PCC 55-99-031-QRY Created On: 03/24/16 Updated On:	Q							0-225-105-2016			0.0	7.6	31.8				
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 03/24/16 Updated On:	Q							0-225-106-2016		0.0	0.0	15.3	44.2				
	Approved Use : CONCRETE, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 03/24/16 Updated On:	Q							0-225-107-2016		0.0	0.0	14.4	43.0				
	Approved Use : CONCRETE, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 03/24/16 Updated On:	Q							0-225-111-2016		0.0	0.0	8.5	29.8				
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 04/05/16 Updated On:	Q							0-225-123-2016			0.0	11.2	35.8				
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 04/05/16 Updated On:	Q							0-225-124-2016		0.0	0.0	9.9	35.0				
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 04/13/16 Updated On:	Q							0-225-144-2016		0.0	0.0	9.2	33.2				
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
RECYCLED PCC 55-99-031-QRY Created On: 04/13/16 Updated On:	Q							0-225-145-2016		0.0	0.0	10.6	33.4				
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 04/14/16 Updated On:	Q							0-225-149-2016		0.0	0.0	7.5	29.6				
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 04/14/16 Updated On:	Q							0-225-150-2016		0.0	0.0	8.0	32.4				
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 04/14/16 Updated On:	Q							0-225-151-2016		0.0	0.0	7.5	29.3				
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 04/14/16 Updated On:	Q							0-225-152-2016		0.0	0.0	6.3	26.7				
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 04/14/16 Updated On:	Q							0-225-153-2016			0.0	8.7	34.0				
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 04/22/16 Updated On:	Q							0-225-158-2016		0.0	0.0	11.9	41.0				
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
RECYCLED PCC 55-99-031-QRY Created On: 05/02/16 Updated On:	Q							0-225-161-2016			0.0	8.8	35.5				
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 05/12/16 Updated On:	Q							0-225-174-2016		0.0	0.0	8.0	29.8				
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 05/12/16 Updated On:	Q							0-225-175-2016			0.0	8.5	35.2				
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 05/12/16 Updated On:	Q							0-225-176-2016		0.0	0.0	8.5	29.9				
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 05/19/16 Updated On:	Q							0-225-177-2016			0.0	8.9	37.9				
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 05/19/16 Updated On:	Q							0-225-178-2016			0.0	10.3	34.2				
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 05/26/16 Updated On:	Q							0-225-187-2016			0.0	11.7	38.1				
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
RECYCLED PCC 55-99-031-QRY Created On: 06/13/16 Updated On:	Q							0-225-199-2016		0.0	0.0	9.7	31.6				
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 06/13/16 Updated On:	Q							0-225-200-2016		0.0	0.0	11.3	36.7				
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 06/13/16 Updated On:	Q							0-225-201-2016		0.0	0.0	12.4	36.4				
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 06/13/16 Updated On:	Q							0-225-202-2016		0.0	0.0	9.5	32.2				
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 06/16/16 Updated On:	Q							0-225-205-2016		0.0	0.0	9.1	29.4				
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 06/30/16 Updated On:	Q							0-225-220-2016			0.0	7.5	29.1				
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 06/30/16 Updated On:	Q							0-225-221-2016		0.0	0.0	11.1	34.2				
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
RECYCLED PCC 55-99-031-QRY Created On: 06/30/16 Updated On:	Q							0-225-222-2016			0.0	10.5	37.5				
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 06/30/16 Updated On:	Q							0-225-223-2016			0.0	8.7	36.0				
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 08/08/16 Updated On:	Q							0-225-236-2016		0.0	0.0	5.7	26.2				
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 08/23/16 Updated On:	Q							0-225-246-2016			0.0	11.9	36.3				
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 08/25/16 Updated On:	Q							0-225-247-2016			0.0		36.7				
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 08/30/16 Updated On:	Q							0-225-250-2016		0.0	0.0	7.3	31.5				
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 09/09/16 Updated On:	Q							0-225-254-2016			0.0	9.9	37.8				
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
RECYCLED PCC 55-99-031-QRY Created On: 09/15/16 Updated On:	Q							0-225-255-2016			0.0	7.9	32.0				
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 09/16/16 Updated On:	Q							0-225-258-2016			0.0		34.7				
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 09/20/16 Updated On:	Q							0-225-259-2016		0.0	0.0	8.6	29.0				
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 09/22/16 Updated On:	Q							0-225-262-2016		0.0	0.0	11.7	35.4				
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 09/22/16 Updated On:	Q							0-225-263-2016			0.0	9.8	33.9				
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 10/11/16 Updated On:	Q							0-225-269-2016			0.0		35.3				
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 10/14/16 Updated On:	Q							0-225-271-2016		0.0	0.0	6.9	28.1				
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
RECYCLED PCC 55-99-031-QRY Created On: 11/11/16 Updated On:	Q							0-225-273-2016			0.0	7.6	31.7				
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 11/17/16 Updated On:	Q							0-225-274-2016			0.0	8.9	37.6				
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 12/31/16 Updated On:	Q							0-225-275-2016		0.0	0.0	10.1	36.1				
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 01/05/17 Updated On:	Q							0-225-27-2017		0.0	0.0	10.1	36.1				
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 02/13/17 Updated On:	Q							0-225-63-2017			0.0	8.4	34.0				
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 02/13/17 Updated On:	Q							0-225-64-2017			0.0	8.9	36.6				
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 02/13/17 Updated On:	Q							0-225-65-2017			0.0	7.9	33.4				
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
RECYCLED PCC 55-99-031-QRY Created On: 02/13/17 Updated On:	Q							0-225-68-2017			0.0	7.5	35.0				
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 03/13/17 Updated On:	Q							0-225-82-2017			0.0	8.2	34.8				
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 03/13/17 Updated On:	Q							0-225-83-2017		0.0	0.0	8.5	32.9				
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 03/22/17 Updated On:	Q							0-225-85-2017			0.0	9.9	35.7				
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 04/03/17 Updated On:	Q							0-225-98-2017		0.0	0.0	7.3	31.1				
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 04/03/17 Updated On:	Q							0-225-100-2017		0.0	0.0	8.1	32.3				
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 04/04/17 Updated On:	Q							0-225-104-2017			0.0	7.6	30.5				
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
RECYCLED PCC 55-99-031-QRY Created On: 04/06/17 Updated On:	Q							0-225-107-2017		0.0	0.0	11.3	42.5				
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 04/06/17 Updated On:	Q							0-225-108-2017		0.0	0.0	10.1	39.6				
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 04/10/17 Updated On:	Q							0-225-118-2017			0.0	10.9	32.2				
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 04/10/17 Updated On:	Q							0-225-119-2017			0.0	9.1	29.6				
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 04/12/17 Updated On:	Q							0-225-126-2017		0.0	0.0	12.4	37.9				
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 04/13/17 Updated On:	Q							0-225-132-2017			0.0	8.7	30.5				
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 04/13/17 Updated On:	Q							0-225-133-2017		0.0	0.0	12.1	40.2				
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
RECYCLED PCC 55-99-031-QRY Created On: 04/13/17 Updated On:	Q							0-225-136-2017		0.0	0.0	7.9	31.7				
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 04/17/17 Updated On:	Q							0-225-137-2017			0.0	9.1	32.1				
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 04/21/17 Updated On:	Q							0-225-146-2017		0.0	0.0	10.3	36.8				
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 05/04/17 Updated On:	Q							0-225-173-2017			0.0	11.6	44.1				
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 05/05/17 Updated On:	Q							0-225-175-2017			0.0	10.9	36.5				
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 05/18/17 Updated On:	Q							0-225-187-2017		0.0	0.0	10.5	37.3				
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 05/30/17 Updated On:	Q							0-225-194-2017			0.0	8.9	35.7				
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
RECYCLED PCC 55-99-031-QRY Created On: 05/30/17 Updated On:	Q							0-225-198-2017		0.0	0.0	6.2	28.8				
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 06/16/17 Updated On:	Q							0-225-213-2017		0.0	0.0	8.5	31.2				
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 06/16/17 Updated On:	Q							0-225-214-2017		0.0	0.0	8.9	26.0				
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 06/26/17 Updated On:	Q							0-225-217-2017			0.0	6.9	29.6				
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 07/14/17 Updated On:	Q							0-225-231-2017			0.0	8.8	34.2				
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 07/14/17 Updated On:	Q							0-225-232-2017			0.0	6.6	29.2				
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 07/14/17 Updated On:	Q							0-225-233-2017		0.0	0.0	9.0	30.9				
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
RECYCLED PCC 55-99-031-QRY Created On: 07/14/17 Updated On:	Q							0-225-234-2017			0.0	6.7	30.2				
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 07/28/17 Updated On:	Q							0-225-245-2017		0.0	0.0	8.1	29.5				
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 08/14/17 Updated On:	Q							0-225-251-2017			0.0	12.7	37.8				
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 08/14/17 Updated On:	Q							0-225-252-2017			0.0	10.7	34.4				
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 08/15/17 Updated On:	Q							0-225-257-2017		0.0	0.0	9.3	33.1				
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 08/22/17 Updated On:	Q							0-225-259-2017			0.0	7.6	30.7				
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 08/22/17 Updated On:	Q							0-225-260-2017			0.0	8.1	32.4				
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
RECYCLED PCC 55-99-031-QRY Created On: 08/31/17 Updated On:	Q							0-225-270-2017		0.0	0.0	11.8	38.2				
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 09/25/17 Updated On:	Q							0-225-276-2017		0.0	0.0	7.6	30.5				
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 10/16/17 Updated On:	Q							0-225-281-2017		0.0	0.0	8.1	32.0				
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 11/03/17 Updated On:	Q							0-225-286-2017		0.0	0.0	8.6	29.9				
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 11/03/17 Updated On:	Q							0-225-287-2017		0.0	0.0	7.7	29.4				
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 01/03/18 Updated On:	Q							0-225-38-2018		0.0	0.0	13.6	40.3				
	Approved Use : CONCRETE, OGBC, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 01/04/18 Updated On:	Q							0-225-62-2018		0.0	0.0	10.0	38.1				
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
RECYCLED PCC 55-99-031-QRY Created On: 01/04/18 Updated On:	Q							0-225-63-2018			0.0	7.3	29.7				
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 01/04/18 Updated On:	Q							0-225-79-2018			0.0	8.1	38.7				
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 02/16/18 Updated On:	Q							0-225-103-2018			0.0	13.8	37.2				
	Approved Use : CONCRETE, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 03/08/18 Updated On:	Q							0-225-118-2018		0.0	0.0	13.3	38.0				
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 03/16/18 Updated On:	Q							0-225-126-2018			0.0	8.5	33.2				
	Approved Use : HMA<MT, HMA>=MT, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 03/16/18 Updated On:	Q							0-225-127-2018			0.0	6.5	27.4				
	Approved Use : HMA<MT, HMA>=MT, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 03/16/18 Updated On:	Q							0-225-128-2018			0.0	6.9	28.6				
	Approved Use : HMA<MT, HMA>=MT, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
RECYCLED PCC 55-99-031-QRY Created On: 03/23/18 Updated On:	Q							0-225-138-2018		0.0	0.0	11.8	40.0				
	Approved Use : HMA<MT, HMA>=MT, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 03/23/18 Updated On:	Q							0-225-143-2018		0.0	0.0	10.3	39.3				
	Approved Use : HMA<MT, HMA>=MT, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 03/28/18 Updated On:	Q							0-225-147-2018		0.0	0.0	6.8	26.2				
	Approved Use : HMA<MT, HMA>=MT, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 03/28/18 Updated On:	Q							0-225-148-2018		0.0	0.0	7.2	27.9				
	Approved Use : HMA<MT, HMA>=MT, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 03/28/18 Updated On:	Q							0-225-149-2018		0.0	0.0	8.2	37.7				
	Approved Use : HMA<MT, HMA>=MT, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 03/29/18 Updated On:	Q							0-225-153-2018			0.0	5.3	25.6				
	Approved Use : HMA<MT, HMA>=MT, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 03/29/18 Updated On:	Q							0-225-154-2018			0.0	7.0	28.6				
	Approved Use : HMA<MT, HMA>=MT, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
RECYCLED PCC 55-99-031-QRY Created On: 04/10/18 Updated On:	Q							0-225-160-2018		0.0	0.0	7.9	30.2				
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 04/13/18 Updated On:	Q							0-225-170-2018			0.0	10.5	36.9				
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 04/13/18 Updated On:	Q							0-225-171-2018			0.0	10.1	35.9				
	Approved Use : HMA<MT, HMA>=MT, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 04/13/18 Updated On:	Q							0-225-172-2018			0.0	5.2	25.8				
	Approved Use : HMA<MT, HMA>=MT, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 04/19/18 Updated On:	Q							0-225-173-2018		0.0	0.0	9.2	34.0				
	Approved Use : HMA<MT, HMA>=MT, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 04/19/18 Updated On:	Q							0-225-175-2018		0.0	0.0	12.3	37.4				
	Approved Use : HMA<MT, HMA>=MT, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 04/19/18 Updated On:	Q							0-225-178-2018		0.0	0.0	11.8	34.9				
	Approved Use : HMA<MT, HMA>=MT, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
RECYCLED PCC 55-99-031-QRY Created On: 04/20/18 Updated On:	Q							0-225-179-2018			0.0	6.1	27.2				
	Approved Use : HMA<MT, HMA>=MT, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 04/20/18 Updated On:	Q							0-225-181-2018			0.0	6.2	30.2				
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 04/25/18 Updated On:	Q							0-225-182-2018		0.0	0.0	8.3	32.1				
	Approved Use : HMA<MT, HMA>=MT, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 05/01/18 Updated On:	Q							0-225-186-2018		0.0	0.0	10.2	31.4				
	Approved Use : HMA<MT, HMA>=MT, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 05/01/18 Updated On:	Q							0-225-189-2018			0.0	10.4	37.6				
	Approved Use : HMA<MT, HMA>=MT, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 05/07/18 Updated On:	Q							0-225-193-2018			0.0	9.7	32.0				
	Approved Use : HMA<MT, HMA>=MT, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 05/07/18 Updated On:	Q							0-225-194-2018		0.0	0.0	10.3	35.1				
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
RECYCLED PCC 55-99-031-QRY Created On: 05/10/18 Updated On:	Q							0-225-200-2018		0.0	0.0	9.4	33.5				
	Approved Use : HMA<MT, HMA>=MT, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 05/11/18 Updated On:	Q							0-225-207-2018			0.0	8.6	31.3				
	Approved Use : HMA<MT, HMA>=MT, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 05/11/18 Updated On:	Q							0-225-208-2018			0.0	6.8	24.8				
	Approved Use : HMA<MT, HMA>=MT, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 06/07/18 Updated On:	Q							0-225-221-2018		0.0	0.0	11.6	34.9				
	Approved Use : HMA<MT, HMA>=MT, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 06/27/18 Updated On:	Q							0-225-240-2018		0.0	0.0	8.6	31.4				
	Approved Use : HMA<MT, HMA>=MT, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 07/11/18 Updated On:	Q							0-225-248-2018		0.0	0.0	6.8	28.5				
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 07/11/18 Updated On:	Q							0-225-249-2018		0.0	0.0	12.4	36.8				
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
RECYCLED PCC 55-99-031-QRY Created On: 07/23/18 Updated On:	Q							0-225-254-2018			0.0	5.6	25.6				
	Approved Use : HMA<MT, HMA>=MT, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 07/23/18 Updated On:	Q							0-225-256-2018		0.0	0.0	6.3	29.8				
	Approved Use : HMA<MT, HMA>=MT, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 07/31/18 Updated On:	Q							0-225-258-2018		0.0	0.0	9.4	31.9				
	Approved Use : HMA<MT, HMA>=MT, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 07/31/18 Updated On:	Q							0-225-259-2018		0.0	0.0	8.3	30.0				
	Approved Use : HMA<MT, HMA>=MT, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 08/20/18 Updated On:	Q							0-225-269-2018		0.0	0.0	9.2	29.2				
	Approved Use : HMA<MT, HMA>=MT, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 08/20/18 Updated On:	Q							0-225-272-2018		0.0	0.0	11.0	40.0				
	Approved Use : HMA<MT, HMA>=MT, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 08/24/18 Updated On:	Q							0-225-274-2018		0.0	0.0	6.1	27.5				
	Approved Use : HMA<MT, HMA>=MT, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
RECYCLED PCC 55-99-031-QRY Created On: 08/28/18 Updated On:	Q							0-225-275-2018		0.0	0.0	8.1	31.7				
	Approved Use : HMA<MT, HMA>=MT, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 08/28/18 Updated On:	Q							0-225-276-2018		0.0	0.0	7.9	30.4				
	Approved Use : HMA<MT, HMA>=MT, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 08/28/18 Updated On:	Q							0-225-277-2018		0.0	0.0	90.7	93.1				
RECYCLED PCC 55-99-031-QRY Created On: 09/06/18 Updated On:	Q							0-225-279-2018		0.0	0.0	10.7	35.7				
	Approved Use : HMA<MT, HMA>=MT, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 09/26/18 Updated On:	Q							0-225-281-2018		0.0	0.0	11.6	41.4				
	Approved Use : HMA<MT, HMA>=MT, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 09/26/18 Updated On:	Q							0-225-284-2018		0.0	0.0	7.1	29.7				
	Approved Use : HMA<MT, HMA>=MT, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 09/26/18 Updated On:	Q							0-225-285-2018		0.0	0.0	10.0	33.2				
	Approved Use : HMA<MT, HMA>=MT, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
RECYCLED PCC 55-99-031-QRY Created On: 10/01/18 Updated On:	Q							0-225-287-2018		0.0	0.0	10.6	37.6				
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 10/09/18 Updated On:	Q							0-225-289-2018		0.0	0.0	8.0	31.0				
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 01/07/19 Updated On:	Q							0-225-44-2019		0.0	0.0	7.8	30.7				
	Approved Use : HMA<MT, HMA>=MT, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 02/05/19 Updated On:	Q							0-225-99-2019			0.0	9.7	30.9				
	Approved Use : HMA<MT, HMA>=MT, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 02/05/19 Updated On:	Q							0-225-100-2019			0.0	8.0	30.8				
	Approved Use : HMA<MT, HMA>=MT, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 03/21/19 Updated On:	Q							0-225-111-2019			0.0	10.5	30.8				
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 03/22/19 Updated On:	Q							0-225-114-2019		0.0	0.0	8.0	32.1				
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
RECYCLED PCC 55-99-031-QRY Created On: 04/05/19 Updated On:	Q							0-225-127-2019			0.0	9.2	31.8				
	Approved Use : HMA<MT, HMA>=MT, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 04/10/19 Updated On:	Q							0-225-130-2019		0.0	0.0	9.9	39.2				
	Approved Use : HMA<MT, HMA>=MT, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 04/10/19 Updated On:	Q							0-225-131-2019		0.0	0.0	10.6	35.1				
	Approved Use : HMA<MT, HMA>=MT, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 04/10/19 Updated On:	Q							0-225-134-2019		0.0	0.0	7.3	30.0				
	Approved Use : HMA<MT, HMA>=MT, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 04/10/19 Updated On:	Q							0-225-135-2019		0.0	0.0	7.1	29.0				
	Approved Use : HMA<MT, HMA>=MT, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 04/10/19 Updated On:	Q							0-225-136-2019		0.0	0.0	7.0	29.7				
	Approved Use : HMA<MT, HMA>=MT, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 04/18/19 Updated On:	Q							0-225-138-2019		0.0	0.0	8.6	26.5				
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
RECYCLED PCC 55-99-031-QRY Created On: 04/18/19 Updated On:	Q							0-225-140-2019		0.0	0.0	5.6	26.2				
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 04/18/19 Updated On:	Q							0-225-141-2019		0.0	0.0	10.0	33.0				
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 04/18/19 Updated On:	Q							0-225-142-2019			0.0	6.9	27.1				
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 04/19/19 Updated On:	Q							0-225-143-2019			0.0	8.4	30.4				
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 04/19/19 Updated On:	Q							0-225-144-2019		0.0	0.0	5.3	25.7				
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 04/19/19 Updated On:	Q							0-225-145-2019		0.0	0.0	5.9	27.8				
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 04/24/19 Updated On:	Q							0-225-160-2019		0.0	0.0	6.9	28.9				
	Approved Use : HMA<MT, HMA>=MT, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
RECYCLED PCC 55-99-031-QRY Created On: 04/24/19 Updated On:	Q							0-225-161-2019		0.0	0.0	8.3	30.7				
	Approved Use : HMA<MT, HMA>=MT, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 04/24/19 Updated On:	Q							0-225-162-2019		0.0	0.0	8.9	32.6				
	Approved Use : HMA<MT, HMA>=MT, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 04/26/19 Updated On:	Q							0-225-172-2019			0.0	5.4	26.4				
	Approved Use : HMA<MT, HMA>=MT, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 04/26/19 Updated On:	Q							0-225-173-2019			0.0	5.7	25.2				
	Approved Use : HMA<MT, HMA>=MT, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 05/02/19 Updated On:	Q							0-225-178-2019			0.0	8.0	34.5				
	Approved Use : HMA<MT, HMA>=MT, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 05/09/19 Updated On:	Q							0-225-184-2019		0.0	0.0	6.9	27.7				
	Approved Use : HMA<MT, HMA>=MT, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 05/13/19 Updated On:	Q							0-225-188-2019		0.0	0.0	5.6	26.8				
	Approved Use : HMA<MT, HMA>=MT, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
RECYCLED PCC 55-99-031-QRY Created On: 05/24/19 Updated On:	Q							0-225-193-2019		0.0	0.0	10.5	37.8				
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 05/24/19 Updated On:	Q							0-225-195-2019		0.0	0.0	9.0	33.0				
	Approved Use : HMA<MT, HMA>=MT, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 06/06/19 Updated On:	Q							0-225-208-2019		0.0	0.0	9.4	34.4				
	Approved Use : HMA<MT, HMA>=MT, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 06/07/19 Updated On:	Q							0-225-210-2019		0.0	0.0	7.1	30.3				
	Approved Use : HMA<MT, HMA>=MT, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 06/07/19 Updated On:	Q							0-225-211-2019		0.0	0.0	7.7	30.4				
	Approved Use : HMA<MT, HMA>=MT, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 06/07/19 Updated On:	Q							0-225-212-2019		0.0	0.0	5.9	27.9				
	Approved Use : HMA<MT, HMA>=MT, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 06/13/19 Updated On:	Q							0-225-215-2019		0.0	0.0	7.6	29.7				
	Approved Use : HMA<MT, HMA>=MT, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
RECYCLED PCC 55-99-031-QRY Created On: 06/13/19 Updated On:	Q							0-225-216-2019		0.0	0.0	9.1	35.0				
	Approved Use : HMA<MT, HMA>=MT, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 06/24/19 Updated On:	Q							0-225-226-2019		0.0	0.0		40.4				
	Approved Use : HMA<MT, HMA>=MT, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 07/16/19 Updated On:	Q							0-225-234-2019		0.0	0.0	9.6	32.3				
	Approved Use : HMA<MT, HMA>=MT, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 07/23/19 Updated On:	Q							0-225-242-2019		0.0	0.0	12.0	36.0				
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 07/23/19 Updated On:	Q							0-225-243-2019		0.0	0.0	9.6	29.6				
	Approved Use : HMA<MT, HMA>=MT, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 07/23/19 Updated On:	Q							0-225-244-2019		0.0	0.0	8.7	30.3				
	Approved Use : HMA<MT, HMA>=MT, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 07/25/19 Updated On:	Q							0-225-248-2019			0.0	10.1	32.6				
	Approved Use : HMA<MT, HMA>=MT, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
RECYCLED PCC 55-99-031-QRY Created On: 07/25/19 Updated On:	Q							0-225-253-2019		0.0	0.0	5.9	28.1				
	Approved Use : HMA<MT, HMA>=MT, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 07/31/19 Updated On:	Q							0-225-254-2019		0.0	0.0	7.6	30.6				
	Approved Use : HMA<MT, HMA>=MT, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 08/05/19 Updated On:	Q							0-225-255-2019			0.0	10.6	38.7				
	Approved Use : HMA<MT, HMA>=MT, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 08/09/19 Updated On:	Q							0-225-256-2019		0.0	0.0		43.1				
	Approved Use : HMA<MT, HMA>=MT, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 08/09/19 Updated On:	Q							0-225-257-2019		0.0	0.0		32.6				
	Approved Use : HMA<MT, HMA>=MT, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 09/16/19 Updated On:	Q							0-225-270-2019		0.0	0.0	9.0	32.9				
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 09/18/19 Updated On:	Q							0-225-271-2019		0.0	0.0	6.9	29.7				
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
RECYCLED PCC 55-99-031-QRY Created On: 09/19/19 Updated On:	Q							0-225-273-2019		0.0	0.0	6.9	27.3				
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 10/10/19 Updated On:	Q							0-225-275-2019		0.0	0.0	7.8	30.8				
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 10/22/19 Updated On:	Q							0-225-276-2019		0.0	0.0	8.6	31.1				
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 10/22/19 Updated On:	Q							0-225-277-2019			0.0	4.8	25.8				
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 01/08/20 Updated On:	Q							0-225-81-2020		22.7	0.0	7.4	29.1				
RECYCLED PCC 55-99-031-QRY Created On: 01/09/20 Updated On:	Q							0-225-96-2020		39.2	0.0	13.1	36.8				
RECYCLED PCC 55-99-031-QRY Created On: 01/09/20 Updated On:	Q							0-225-97-2020		55.8	0.0	12.2	37.7				

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
RECYCLED PCC 55-99-031-QRY Created On: 01/30/20 Updated On:	Q							0-225-103-2020		14.6	0.0	5.6	28.1				
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 01/30/20 Updated On:	Q							0-225-105-2020		36.5	0.0	8.3	32.6				
RECYCLED PCC 55-99-031-QRY Created On: 03/09/20 Updated On:	Q							0-225-125-2020		50.0	0.0	7.5	33.6				
RECYCLED PCC 55-99-031-QRY Created On: 03/30/20 Updated On:	Q							0-225-135-2020		53.3	0.0	10.7	37.2				
RECYCLED PCC 55-99-031-QRY Created On: 04/01/20 Updated On:	Q							0-225-138-2020		49.5	0.0	7.8	33.5				
RECYCLED PCC 55-99-031-QRY Created On: 04/08/20 Updated On:	Q							0-225-147-2020		4.7	0.0	6.9	29.6				
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 04/09/20 Updated On:	Q							0-225-150-2020		31.0	0.0	6.2	29.4				

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
RECYCLED PCC 55-99-031-QRY Created On: 04/09/20 Updated On:	Q							0-225-151-2020		24.4	0.0	6.0	26.9				
RECYCLED PCC 55-99-031-QRY Created On: 05/06/20 Updated On:	Q							0-225-168-2020		16.8	0.0	6.1	27.5				
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 05/19/20 Updated On:	Q							0-225-180-2020		22.5	0.0	7.7	31.5				
RECYCLED PCC 55-99-031-QRY Created On: 07/17/20 Updated On:	Q							0-225-223-2020		40.9	0.0	7.3	30.3				
RECYCLED PCC 55-99-031-QRY Created On: 08/12/20 Updated On:	Q							0-225-232-2020		44.1	0.0	8.4	29.7				
RECYCLED PCC 55-99-031-QRY Created On: 01/06/21 Updated On:	Q							0-225-111-2021		10.7	0.0	8.1	31.3				
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 01/08/21 Updated On:	Q							0-225-119-2021		31.5	0.0	7.5	30.5				

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
RECYCLED PCC 55-99-031-QRY Created On: 04/13/21 Updated On:	Q							0-225-180-2021		41.0	0.0	10.2	35.4				
RECYCLED PCC 55-99-031-QRY Created On: 04/13/21 Updated On:	Q							0-225-181-2021		25.3	0.0	8.2	35.4				
RECYCLED PCC 55-99-031-QRY Created On: 04/30/21 Updated On:	Q							0-225-192-2021		21.1	0.0	9.3	32.5				
RECYCLED PCC 55-99-031-QRY Created On: 07/07/21 Updated On:	Q							0-225-242-2021		30.7	0.0	10.0	35.7				
RECYCLED PCC 55-99-031-QRY Created On: 07/19/21 Updated On:	Q							0-225-248-2021		16.2	0.0	9.1	34.5				
RECYCLED PCC 55-99-031-QRY Created On: 01/04/22 Updated On:	Q							0-225-61-2022		16.5	0.0	7.5	29.3				
RECYCLED PCC 55-99-031-QRY Created On: 01/04/22 Updated On:	Q							0-225-62-2022		24.7	0.0	9.9	35.6				

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
RECYCLED PCC 55-99-031-QRY Created On: 01/04/22 Updated On:	Q							0-225-94-2022	16.7	11.8	0.0	7.0	29.9				
Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																	
RECYCLED PCC 55-99-031-QRY Created On: 03/17/22 Updated On:	Q							0-225-145-2022		25.6	0.0	11.0	33.8				
RECYCLED PCC 55-99-031-QRY Created On: 03/17/22 Updated On:	Q							0-225-151-2022		25.1	0.0	10.7	35.8				
RECYCLED PCC 55-99-031-QRY Created On: 04/19/22 Updated On:	Q							0-225-178-2022		30.1	0.0	10.2	34.7				
RECYCLED PCC 55-99-031-QRY Created On: 04/19/22 Updated On:	Q							0-225-179-2022		44.3	0.0	12.7	37.7				
RECYCLED PCC 55-99-031-QRY Created On: 05/03/22 Updated On:	Q							0-225-199-2022		55.3	0.0	11.6	41.7				
RECYCLED PCC 55-99-031-QRY Created On: 02/06/23 Updated On:	Q							0-225-139-2023		35.3	0.0	7.7	31.0				

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
RECYCLED PCC 55-99-031-QRY Created On: 02/14/23 Updated On:	Q							0-225-143-2023		35.1	0.0	11.6	38.1				
RECYCLED PCC 55-99-031-QRY Created On: 02/14/23 Updated On:	Q							0-225-144-2023		0.0	61.6	12.9	40.9				
RECYCLED PCC 55-99-031-QRY Created On: 02/27/23 Updated On:	Q							0-225-146-2023		41.2	0.0	8.4	28.1				
RECYCLED PCC 55-99-031-QRY Created On: 02/27/23 Updated On:	Q							0-225-149-2023		40.0	0.0	9.0	30.5				
RECYCLED PCC 55-99-031-QRY Created On: 02/28/23 Updated On:	Q							0-225-152-2023		36.3	0.0	9.0	32.8				
RECYCLED PCC 55-99-031-QRY Created On: 03/13/23 Updated On:	Q							0-225-168-2023		18.2	0.0	9.5	32.9				
RECYCLED PCC 55-99-031-QRY Created On: 03/20/23 Updated On:	Q							0-225-169-2023		34.0	0.0	8.0	32.2				

Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
RECYCLED PCC 55-99-031-QRY Created On: 04/04/23 Updated On:	Q							0-225-183-2023		30.5	0.0	10.3	32.7				
RECYCLED PCC 55-99-031-QRY Created On: 04/10/23 Updated On:	Q							0-225-191-2023		49.1	0.0	10.7	37.9				
RECYCLED PCC 55-99-031-QRY Created On: 04/20/23 Updated On:	Q							0-225-201-2023		11.8	0.0	8.1	31.5				
							Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate										
RECYCLED PCC 55-99-031-QRY Created On: 05/01/23 Updated On:	Q							0-225-210-2023	23.3	39.0	0.0	7.7	32.6	2.380	2.464	3.526	
RECYCLED PCC 55-99-031-QRY Created On: 05/01/23 Updated On:	Q							0-225-212-2023		55.7	0.0	8.4	31.2	2.404	2.487	3.462	
RECYCLED PCC 55-99-031-QRY Created On: 05/09/23 Updated On:	Q							0-225-215-2023		33.6	0.0	9.3	35.7				
RECYCLED PCC 55-99-031-QRY Created On: 05/22/23 Updated On:	Q							0-225-222-2023		40.0	0.0	8.8	34.3				

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
RECYCLED PCC 55-99-031-QRY Created On: 05/22/23 Updated On:	Q							0-225-223-2023		43.6	0.0	9.3	33.5				
RECYCLED PCC 55-99-031-QRY Created On: 06/14/23 Updated On:	Q							0-225-232-2023		21.6	0.0	8.5	30.0				
RECYCLED PCC 55-99-031-QRY Created On: 01/02/24 Updated On:	Q							0-225-95-2024		16.0	0.0	6.9	30.2				
							Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate										
RECYCLED PCC 55-99-031-QRY Created On: 01/02/24 Updated On:	Q							0-225-125-2024		19.0	0.0	8.7	33.1				
RECYCLED PCC 55-99-031-QRY Created On: 02/28/24 Updated On:	Q							0-225-169-2024		22.2	0.0	7.5	31.6				
RECYCLED PCC 55-99-031-QRY Created On: 02/28/24 Updated On:	Q							0-225-171-2024		36.6	0.0	10.7	34.0				
RECYCLED PCC 55-99-031-QRY Created On: 03/13/24 Updated On:	Q							0-225-199-2024		19.7	0.0	8.9	30.3				

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
RECYCLED PCC 55-99-031-QRY Created On: 03/27/24 Updated On:	Q							0-225-216-2024		0.7	0.0	4.5	21.9				
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 04/15/24 Updated On:	Q							0-225-220-2024		38.7	0.0	8.3	35.9				
RECYCLED PCC 55-99-031-QRY Created On: 04/15/24 Updated On:	Q							0-225-224-2024		27.0	0.0	9.6	32.5				
RECYCLED PCC 55-99-031-QRY Created On: 04/15/24 Updated On:	Q							0-225-226-2024		9.5	0.0	6.7	28.5				
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 04/30/24 Updated On:	Q							0-225-239-2024		41.8	0.0	9.2	32.2				
RECYCLED PCC 55-99-031-QRY Created On: 05/07/24 Updated On:	Q							0-225-250-2024		58.6	0.0	10.9	43.2				
RECYCLED PCC 55-99-031-QRY Created On: 06/10/24 Updated On:	Q							0-225-270-2024		50.9	0.0	7.0	39.6				

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
RECYCLED PCC 55-99-031-QRY Created On: 06/27/24 Updated On:	Q							0-225-285-2024		27.9	0.0	9.7	32.5				
RECYCLED PCC 55-99-031-QRY Created On: 08/14/24 Updated On:	Q							0-225-299-2024	0.2	2.4	2.8	7.0	31.4	2.692	2.728	1.322	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 08/28/24 Updated On:	Q							0-225-303-2024		22.0	0.0	10.6	33.3				
RECYCLED PCC 55-99-031-QRY Created On: 12/19/24 Updated On:	Q							0-225-316-2024		14.3	0.0	8.1	33.0				
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 01/02/25 Updated On:	Q							0-225-63-2025		16.0	0.0	8.5	34.1				
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 01/02/25 Updated On:	Q							0-225-72-2025		15.3	0.0	7.3	27.8				
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																
RECYCLED PCC 55-99-031-QRY Created On: 01/02/25 Updated On:	Q							0-225-73-2025		20.0	0.0	8.1	29.0				

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
RECYCLED PCC 55-99-031-QRY Created On: 01/15/25 Updated On:	Q							0-225-125-2025		14.4	0.0	8.1	33.0				
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																
* RED ROCK GRANITE 55-37-063-QRY Created On: 07/01/21 Updated On:	Q	N	NW	19	27N	6E	Marathon	0-225-238-2021	0.0	0.0	2.2	10.7	44.0	2.594	2.613	0.722	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
REEDS CORNER 55-20-039-PIT Created On: 01/16/15 Updated On:	P	E	NW	12	15N	14E	Fond Du Lac	0-225-67-2015		0.0	3.0	7.0	30.3	2.751	2.785	1.215	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
REEDS CORNER 55-20-039-PIT Created On: 05/19/20 Updated On:	P	E	NW	12	15N	14E	Fond Du Lac	0-225-181-2020	0.0	0.0	4.3	5.5	25.8	2.774	2.801	0.973	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
REEDS CORNER 55-20-039-PIT Created On: 05/14/25 Updated On:	P	E	NW	12	15N	14E	Fond Du Lac	0-225-204-2025	0.3	0.0	3.4	6.4	29.3	2.742	2.774	1.175	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
REESE 55-36-034-PIT Created On: 06/26/19 Updated On:	P	SW	SW	22	17N	21E	Manitowoc	0-225-228-2019	1.1	2.2	0.8	5.4	29.4	2.753	2.776	0.833	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
REESE 55-36-034-PIT Created On: 05/20/24 Updated On:	P	SW	SW	22	17N	21E	Manitowoc	0-225-255-2024	2.3	3.9	3.6	5.7	29.5	2.734	2.761	0.973	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
Source Name	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
REESMAN CO. - BOLTON 55-64-020-PIT Created On: 02/16/18 Updated On:	P		SW	4	3N	18E	Walworth	0-225-106-2018	1.0	0.0	0.2	5.1	27.2	2.678	2.714	1.341	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
REESMAN CO. - BOLTON 55-64-020-PIT Created On: 01/19/23 Updated On:	P		SW	4	3N	18E	Walworth	0-225-126-2023	0.7	0.0	4.4	5.1	24.9	2.682	2.719	1.366	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
REESMAN-HUGHES PIT 55-51-059-PIT Created On: 06/26/23 Updated On:	P	NW	SW	5	2N	19E	Racine	0-225-235-2023	0.7	17.6	3.0	6.4	23.6	2.629	2.689	2.274	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
REIFF QUARRY 55-10-041-QRY Created On: 01/16/25 Updated On:	Q	NW	NE	22	27N	2W	Clark	0-225-141-2025	0.0	0.0	1.4	4.7	19.7	2.834	2.852	0.646	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
REPROCESSED MATERIAL 55-99-033-PIT Created On: 01/08/20 Updated On:	P							0-225-76-2020		0.0	0.0	6.4	26.1				
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																
REPROCESSED MATERIAL 55-99-033-PIT Created On: 01/08/20 Updated On:	P							0-225-79-2020		0.0	0.0	5.9	24.1				
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																
REPROCESSED MATERIAL 55-99-033-PIT Created On: 01/09/20 Updated On:	P							0-225-82-2020		0.0	0.0	8.0	30.2				
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
REPROCESSED MATERIAL 55-99-033-PIT Created On: 01/30/20 Updated On:	P							0-225-104-2020		0.0	0.0	5.9	26.5				
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																
REPROCESSED MATERIAL 55-99-033-PIT Created On: 04/01/20 Updated On:	P							0-225-137-2020		0.0	0.0	8.2	34.0				
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																
REPROCESSED MATERIAL 55-99-033-PIT Created On: 04/09/20 Updated On:	P							0-225-149-2020			0.0	8.9	32.1				
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																
REPROCESSED MATERIAL 55-99-033-PIT Created On: 04/22/20 Updated On:	P							0-225-155-2020		0.0	0.0	7.5	27.8				
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																
REPROCESSED MATERIAL 55-99-033-PIT Created On: 05/04/20 Updated On:	P							0-225-166-2020		0.0	0.0	5.8	25.1				
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																
REPROCESSED MATERIAL 55-99-033-PIT Created On: 05/06/20 Updated On:	P							0-225-167-2020		18.8	0.0	8.0	30.3				
REPROCESSED MATERIAL 55-99-033-PIT Created On: 05/06/20 Updated On:	P							0-225-169-2020		21.7	0.0	8.6	31.1				

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
REPROCESSED MATERIAL 55-99-033-PIT Created On: 05/06/20 Updated On:	P							0-225-170-2020		11.4	0.0	8.0	31.9				
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																
REPROCESSED MATERIAL 55-99-033-PIT Created On: 05/07/20 Updated On:	P							0-225-173-2020		0.0	0.0	7.3	29.5				
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																
REPROCESSED MATERIAL 55-99-033-PIT Created On: 05/12/20 Updated On:	P							0-225-177-2020		0.0	0.0	9.2	27.8				
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																
REPROCESSED MATERIAL 55-99-033-PIT Created On: 05/21/20 Updated On:	P							0-225-182-2020			0.0	5.5	24.9				
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																
REPROCESSED MATERIAL 55-99-033-PIT Created On: 06/09/20 Updated On:	P							0-225-191-2020		0.0	0.0	6.8	29.2				
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																
REPROCESSED MATERIAL 55-99-033-PIT Created On: 06/22/20 Updated On:	P							0-225-199-2020		0.0	0.0	5.9	27.7				
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																
REPROCESSED MATERIAL 55-99-033-PIT Created On: 07/15/20 Updated On:	P							0-225-215-2020		0.0	0.0	5.2	23.4				
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
REPROCESSED MATERIAL 55-99-033-PIT Created On: 07/23/20 Updated On:	P							0-225-226-2020		0.0	0.0	7.8	30.3				
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																
REPROCESSED MATERIAL 55-99-033-PIT Created On: 07/31/20 Updated On:	P							0-225-228-2020		34.7	0.0	7.9	29.3				
REPROCESSED MATERIAL 55-99-033-PIT Created On: 08/04/20 Updated On:	P							0-225-229-2020		0.0	0.0		30.4				
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																
REPROCESSED MATERIAL 55-99-033-PIT Created On: 08/12/20 Updated On:	P							0-225-233-2020			0.0	6.8	27.1				
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																
REPROCESSED MATERIAL 55-99-033-PIT Created On: 08/27/20 Updated On:	P							0-225-237-2020		0.0	0.0	5.7	25.7				
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																
REPROCESSED MATERIAL 55-99-033-PIT Created On: 08/31/20 Updated On:	P							0-225-238-2020		0.0	0.0	6.0	27.1				
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																
REPROCESSED MATERIAL 55-99-033-PIT Created On: 08/31/20 Updated On:	P							0-225-239-2020		26.6	8.5	7.2	27.4				

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
REPROCESSED MATERIAL 55-99-033-PIT Created On: 01/04/21 Updated On:	P							0-225-7-2021		0.0	0.0	7.4	30.7				
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																
REPROCESSED MATERIAL 55-99-033-PIT Created On: 01/05/21 Updated On:	P							0-225-88-2021		17.8	0.0	11.0	35.2				
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																
REPROCESSED MATERIAL 55-99-033-PIT Created On: 02/08/21 Updated On:	P							0-225-124-2021		15.5	0.0	7.0	27.5				
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																
REPROCESSED MATERIAL 55-99-033-PIT Created On: 02/08/21 Updated On:	P							0-225-125-2021		19.6	0.0	7.4	28.3				
REPROCESSED MATERIAL 55-99-033-PIT Created On: 03/24/21 Updated On:	P							0-225-156-2021			0.0	7.1	29.8				
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																
REPROCESSED MATERIAL 55-99-033-PIT Created On: 04/01/21 Updated On:	P							0-225-168-2021		29.5	0.0	7.5	31.2				
REPROCESSED MATERIAL 55-99-033-PIT Created On: 04/19/21 Updated On:	P							0-225-185-2021		34.5	0.0	7.4	29.4				

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
REPROCESSED MATERIAL 55-99-033-PIT Created On: 04/19/21 Updated On:	P							0-225-186-2021		32.3	0.0	8.3	30.5				
REPROCESSED MATERIAL 55-99-033-PIT Created On: 06/14/21 Updated On:	P							0-225-220-2021		11.1	0.0	6.9	28.7				
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																
REPROCESSED MATERIAL 55-99-033-PIT Created On: 06/14/21 Updated On:	P							0-225-221-2021		15.7	0.0	7.3	27.9				
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																
REPROCESSED MATERIAL 55-99-033-PIT Created On: 06/17/21 Updated On:	P							0-225-225-2021		11.8	0.0	6.9	30.6				
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																
REPROCESSED MATERIAL 55-99-033-PIT Created On: 06/25/21 Updated On:	P							0-225-236-2021		31.9	0.0	6.2	27.2				
REPROCESSED MATERIAL 55-99-033-PIT Created On: 07/01/21 Updated On:	P							0-225-239-2021		9.8	0.0	6.5	29.2				
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																
REPROCESSED MATERIAL 55-99-033-PIT Created On: 07/29/21 Updated On:	P							0-225-255-2021		5.6	0.0	7.1	28.6				
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
REPROCESSED MATERIAL 55-99-033-PIT Created On: 08/11/21 Updated On:	P							0-225-259-2021		10.8	0.0	7.2	28.6				
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																
REPROCESSED MATERIAL 55-99-033-PIT Created On: 01/04/22 Updated On:	P							0-225-53-2022		33.4	0.0	6.6	28.1				
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																
REPROCESSED MATERIAL 55-99-033-PIT Created On: 01/04/22 Updated On:	P							0-225-65-2022		7.5	0.0	6.7	28.3				
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																
REPROCESSED MATERIAL 55-99-033-PIT Created On: 01/04/22 Updated On:	P							0-225-66-2022	18.5	9.2	0.0	7.3	29.7				
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																
REPROCESSED MATERIAL 55-99-033-PIT Created On: 01/10/22 Updated On:	P							0-225-96-2022		26.6	0.0	6.0	25.7				
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																
REPROCESSED MATERIAL 55-99-033-PIT Created On: 02/16/22 Updated On:	P							0-225-124-2022		36.1	3.0	5.2	24.8				
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																
REPROCESSED MATERIAL 55-99-033-PIT Created On: 02/16/22 Updated On:	P							0-225-125-2022		37.5	0.0	7.6	27.6				
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
REPROCESSED MATERIAL 55-99-033-PIT Created On: 02/16/22 Updated On:	P							0-225-127-2022		24.7	0.0	7.8	28.9				
REPROCESSED MATERIAL 55-99-033-PIT Created On: 03/01/22 Updated On:	P							0-225-134-2022		21.3	0.0	10.3	31.0				
REPROCESSED MATERIAL 55-99-033-PIT Created On: 03/17/22 Updated On:	P							0-225-148-2022		37.0	0.0	9.1	33.5				
REPROCESSED MATERIAL 55-99-033-PIT Created On: 03/17/22 Updated On:	P							0-225-149-2022		30.8	0.0	9.1	33.9				
REPROCESSED MATERIAL 55-99-033-PIT Created On: 04/05/22 Updated On:	P							0-225-168-2022		26.0	0.0	6.4	26.7				
REPROCESSED MATERIAL 55-99-033-PIT Created On: 04/05/22 Updated On:	P							0-225-171-2022		36.2	0.0	8.9	32.3				
REPROCESSED MATERIAL 55-99-033-PIT Created On: 04/28/22 Updated On:	P							0-225-188-2022		24.8	0.0	5.7	26.1				

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
REPROCESSED MATERIAL 55-99-033-PIT Created On: 04/28/22 Updated On:	P							0-225-190-2022	7.2	20.1	0.0	6.9	29.9				
REPROCESSED MATERIAL 55-99-033-PIT Created On: 05/03/22 Updated On:	P							0-225-195-2022		32.8	0.0	7.1	27.0				
REPROCESSED MATERIAL 55-99-033-PIT Created On: 05/03/22 Updated On:	P							0-225-196-2022		41.5	0.0	7.3	28.0				
REPROCESSED MATERIAL 55-99-033-PIT Created On: 05/03/22 Updated On:	P							0-225-197-2022		18.0	0.0	7.0	27.8				
REPROCESSED MATERIAL 55-99-033-PIT Created On: 05/17/22 Updated On:	P							0-225-209-2022		15.4	0.0	99.7	99.4				
REPROCESSED MATERIAL 55-99-033-PIT Created On: 06/01/22 Updated On:	P							0-225-212-2022		40.6	0.0	8.6	31.3				
REPROCESSED MATERIAL 55-99-033-PIT Created On: 06/06/22 Updated On:	P							0-225-215-2022		0.0	0.0	6.9	29.5				

Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate

Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
REPROCESSED MATERIAL 55-99-033-PIT Created On: 06/16/22 Updated On:	P							0-225-229-2022		27.7	0.0	7.9	30.9				
REPROCESSED MATERIAL 55-99-033-PIT Created On: 07/26/22 Updated On:	P							0-225-249-2022		27.9	0.0	8.0	31.5				
REPROCESSED MATERIAL 55-99-033-PIT Created On: 08/17/22 Updated On:	P							0-225-252-2022		40.8	0.0	9.2	32.5				
REPROCESSED MATERIAL 55-99-033-PIT Created On: 10/24/22 Updated On:	P							0-225-259-2022		33.3	0.0	13.4	33.0				
REPROCESSED MATERIAL 55-99-033-PIT Created On: 01/03/23 Updated On:	P							0-225-40-2023		15.8	0.0	7.2	29.4				
REPROCESSED MATERIAL 55-99-033-PIT Created On: 01/03/23 Updated On:	P							0-225-77-2023	14.7	8.1	0.0	6.2	29.4				
REPROCESSED MATERIAL 55-99-033-PIT Created On: 02/06/23 Updated On:	P							0-225-136-2023		26.8	0.0	6.6	27.2				

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
REPROCESSED MATERIAL 55-99-033-PIT Created On: 02/06/23 Updated On:	P							0-225-137-2023		30.1	0.0	6.9	28.4				
REPROCESSED MATERIAL 55-99-033-PIT Created On: 02/28/23 Updated On:	P							0-225-153-2023		24.4	0.0	9.6	32.5				
REPROCESSED MATERIAL 55-99-033-PIT Created On: 02/28/23 Updated On:	P							0-225-154-2023		39.7	0.0	8.4	32.0				
REPROCESSED MATERIAL 55-99-033-PIT Created On: 02/28/23 Updated On:	P							0-225-155-2023		38.9	0.0	6.9	30.5				
REPROCESSED MATERIAL 55-99-033-PIT Created On: 02/28/23 Updated On:	P							0-225-156-2023		28.5	0.0	9.0	30.2				
REPROCESSED MATERIAL 55-99-033-PIT Created On: 02/28/23 Updated On:	P							0-225-158-2023		38.3	0.0	7.9	31.8				
REPROCESSED MATERIAL 55-99-033-PIT Created On: 03/06/23 Updated On:	P							0-225-164-2023		37.1	0.0	8.5	33.0				

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
REPROCESSED MATERIAL 55-99-033-PIT Created On: 03/06/23 Updated On:	P							0-225-165-2023		28.7	0.0	6.2	27.4				
REPROCESSED MATERIAL 55-99-033-PIT Created On: 03/06/23 Updated On:	P							0-225-166-2023		29.9	0.0	6.7	26.9				
REPROCESSED MATERIAL 55-99-033-PIT Created On: 04/04/23 Updated On:	P							0-225-179-2023		10.5	0.0	6.9	27.2				
								Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate									
REPROCESSED MATERIAL 55-99-033-PIT Created On: 04/05/23 Updated On:	P							0-225-184-2023		40.5	0.0	6.4	28.0				
REPROCESSED MATERIAL 55-99-033-PIT Created On: 04/05/23 Updated On:	P							0-225-185-2023		51.3	0.0	6.6	28.9				
REPROCESSED MATERIAL 55-99-033-PIT Created On: 04/10/23 Updated On:	P							0-225-194-2023		29.8	0.0	5.5	27.0				
REPROCESSED MATERIAL 55-99-033-PIT Created On: 04/20/23 Updated On:	P							0-225-200-2023		24.7	0.0	7.1	31.5				

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
REPROCESSED MATERIAL 55-99-033-PIT Created On: 04/24/23 Updated On:	P							0-225-204-2023		35.5	0.0	8.7	30.0				
REPROCESSED MATERIAL 55-99-033-PIT Created On: 05/01/23 Updated On:	P							0-225-211-2023		24.3	0.0	6.1	28.2				
REPROCESSED MATERIAL 55-99-033-PIT Created On: 05/01/23 Updated On:	P							0-225-213-2023	9.2	33.5	0.0	8.6	33.5	2.401	2.487	3.588	
REPROCESSED MATERIAL 55-99-033-PIT Created On: 06/12/23 Updated On:	P							0-225-229-2023		38.3	0.5	8.5	32.2				
REPROCESSED MATERIAL 55-99-033-PIT Created On: 06/12/23 Updated On:	P							0-225-230-2023		33.5	0.0	6.1	27.1				
REPROCESSED MATERIAL 55-99-033-PIT Created On: 06/14/23 Updated On:	P							0-225-231-2023		16.3	0.0	7.6	28.6				
REPROCESSED MATERIAL 55-99-033-PIT Created On: 06/26/23 Updated On:	P							0-225-233-2023	14.4	28.9	0.0	10.1	30.9	2.442	2.499	2.354	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
REPROCESSED MATERIAL 55-99-033-PIT Created On: 06/26/23 Updated On:	P							0-225-234-2023		24.1	2.1	6.5	26.8				
REPROCESSED MATERIAL 55-99-033-PIT Created On: 08/22/23 Updated On:	P							0-225-245-2023	4.5	17.0	0.5	6.8	15.3	2.411	2.476	2.706	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
REPROCESSED MATERIAL 55-99-033-PIT Created On: 08/22/23 Updated On:	P							0-225-246-2023	9.1	21.2	0.6	7.1	40.2	2.382	2.457	3.134	
REPROCESSED MATERIAL 55-99-033-PIT Created On: 01/02/24 Updated On:	P							0-225-4-2024		22.3	0.0	6.4	29.4				
REPROCESSED MATERIAL 55-99-033-PIT Created On: 01/02/24 Updated On:	P							0-225-126-2024		19.0	0.0	10.1	30.2				
REPROCESSED MATERIAL 55-99-033-PIT Created On: 01/02/24 Updated On:	P							0-225-127-2024		38.3	0.0	6.2	30.2				
REPROCESSED MATERIAL 55-99-033-PIT Created On: 01/02/24 Updated On:	P							0-225-128-2024		26.5	0.0	5.8	26.8				

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
REPROCESSED MATERIAL 55-99-033-PIT Created On: 01/04/24 Updated On:	P							0-225-138-2024		21.3	0.0	8.5	33.4				
REPROCESSED MATERIAL 55-99-033-PIT Created On: 01/29/24 Updated On:	P							0-225-159-2024		31.0	0.0	10.3	33.9				
REPROCESSED MATERIAL 55-99-033-PIT Created On: 01/29/24 Updated On:	P							0-225-161-2024		24.4	0.0	6.2	26.7				
REPROCESSED MATERIAL 55-99-033-PIT Created On: 01/29/24 Updated On:	P							0-225-167-2024		17.1	0.0	9.8	31.4				
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																
REPROCESSED MATERIAL 55-99-033-PIT Created On: 02/28/24 Updated On:	P							0-225-168-2024		31.0	0.0	9.2	31.8				
REPROCESSED MATERIAL 55-99-033-PIT Created On: 02/28/24 Updated On:	P							0-225-173-2024		34.4	0.0	10.1	35.4				
REPROCESSED MATERIAL 55-99-033-PIT Created On: 02/28/24 Updated On:	P							0-225-174-2024		47.0	0.0	12.0	34.6				

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
REPROCESSED MATERIAL 55-99-033-PIT Created On: 02/28/24 Updated On:	P							0-225-175-2024		31.3	0.0	8.2	30.8				
REPROCESSED MATERIAL 55-99-033-PIT Created On: 02/28/24 Updated On:	P							0-225-176-2024		17.7	0.0	8.2	29.5				
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																
REPROCESSED MATERIAL 55-99-033-PIT Created On: 02/28/24 Updated On:	P							0-225-186-2024		33.9	0.0	6.4	28.1				
REPROCESSED MATERIAL 55-99-033-PIT Created On: 02/28/24 Updated On:	P							0-225-187-2024		28.4	0.0	6.0	25.5				
REPROCESSED MATERIAL 55-99-033-PIT Created On: 03/13/24 Updated On:	P							0-225-203-2024		16.3	0.0	4.9	26.1				
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																
REPROCESSED MATERIAL 55-99-033-PIT Created On: 03/13/24 Updated On:	P							0-225-204-2024		17.9	0.0	5.5	26.2				
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																
REPROCESSED MATERIAL 55-99-033-PIT Created On: 03/13/24 Updated On:	P							0-225-205-2024		30.0	0.0	6.5	27.1				

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
REPROCESSED MATERIAL 55-99-033-PIT Created On: 03/13/24 Updated On:	P							0-225-206-2024		33.7	0.0	8.9	33.0				
REPROCESSED MATERIAL 55-99-033-PIT Created On: 03/27/24 Updated On:	P							0-225-213-2024		33.7	0.0	6.0	26.6				
REPROCESSED MATERIAL 55-99-033-PIT Created On: 03/27/24 Updated On:	P							0-225-215-2024		0.6	0.0	4.4	20.8				
							Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate										
REPROCESSED MATERIAL 55-99-033-PIT Created On: 04/15/24 Updated On:	P							0-225-227-2024		8.4	0.0	5.5	23.8				
							Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate										
REPROCESSED MATERIAL 55-99-033-PIT Created On: 04/15/24 Updated On:	P							0-225-233-2024		37.8	0.0	8.7	34.1				
REPROCESSED MATERIAL 55-99-033-PIT Created On: 04/30/24 Updated On:	P							0-225-238-2024		52.1	0.0	9.8	33.7				
REPROCESSED MATERIAL 55-99-033-PIT Created On: 05/07/24 Updated On:	P							0-225-251-2024	1.3	34.5	0.0	8.0	36.8				

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
REPROCESSED MATERIAL 55-99-033-PIT Created On: 06/10/24 Updated On:	P							0-225-271-2024		24.9	0.0	7.2	29.7				
REPROCESSED MATERIAL 55-99-033-PIT Created On: 06/10/24 Updated On:	P							0-225-272-2024		17.7	2.3	7.1	28.5	2.547	2.610	2.469	
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																
REPROCESSED MATERIAL 55-99-033-PIT Created On: 06/25/24 Updated On:	P							0-225-274-2024		18.0	0.0	7.6	32.0				
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																
REPROCESSED MATERIAL 55-99-033-PIT Created On: 06/27/24 Updated On:	P							0-225-281-2024		24.5	4.3	9.1	35.2				
REPROCESSED MATERIAL 55-99-033-PIT Created On: 06/27/24 Updated On:	P							0-225-286-2024		20.8	0.0	7.6	31.6				
REPROCESSED MATERIAL 55-99-033-PIT Created On: 07/31/24 Updated On:	P							0-225-291-2024		40.3	0.0	8.9	31.2				
REPROCESSED MATERIAL 55-99-033-PIT Created On: 08/14/24 Updated On:	P							0-225-298-2024		27.2	0.0	6.5	26.6				

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
Source Name	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
REPROCESSED MATERIAL 55-99-033-PIT Created On: 08/28/24 Updated On:	P							0-225-306-2024		24.6	0.0	10.6	31.1	2.440	2.498	2.391	
REPROCESSED MATERIAL 55-99-033-PIT Created On: 09/19/24 Updated On:	P							0-225-308-2024		20.3	0.0	6.2	27.7				
REPROCESSED MATERIAL 55-99-033-PIT Created On: 01/02/25 Updated On:	P							0-225-56-2025		26.9	0.0	9.2	31.5				
REPROCESSED MATERIAL 55-99-033-PIT Created On: 01/14/25 Updated On:	P							0-225-99-2025		22.0	0.0	6.7	29.5				
REPROCESSED MATERIAL 55-99-033-PIT Created On: 01/14/25 Updated On:	P							0-225-114-2025		35.6	0.0	6.5	27.5				
REPROCESSED MATERIAL 55-99-033-PIT Created On: 01/14/25 Updated On:	P							0-225-115-2025		33.6	0.0	7.2	27.8				
REPROCESSED MATERIAL 55-99-033-PIT Created On: 01/14/25 Updated On:	P							0-225-116-2025		26.5	0.0	25.3	41.0				

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
REPROCESSED MATERIAL 55-99-033-PIT Created On: 01/14/25 Updated On:	P							0-225-117-2025		45.9	0.0	9.1	32.6				
REPROCESSED MATERIAL 55-99-033-PIT Created On: 01/14/25 Updated On:	P							0-225-118-2025		40.6	0.0	9.3	31.9				
REPROCESSED MATERIAL 55-99-033-PIT Created On: 01/14/25 Updated On:	P							0-225-119-2025		27.3	0.0	8.2	29.5				
REPROCESSED MATERIAL 55-99-033-PIT Created On: 01/14/25 Updated On:	P							0-225-120-2025		47.2	0.0	9.0	31.0				
REPROCESSED MATERIAL 55-99-033-PIT Created On: 01/30/25 Updated On:	P							0-225-145-2025		32.1	0.0	6.5	27.7				
REPROCESSED MATERIAL 55-99-033-PIT Created On: 01/30/25 Updated On:	P							0-225-146-2025		25.6	0.0	5.8	26.4				
REPROCESSED MATERIAL 55-99-033-PIT Created On: 02/20/25 Updated On:	P							0-225-154-2025		23.8	0.0	6.2	26.4				

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
REPROCESSED MATERIAL 55-99-033-PIT Created On: 02/20/25 Updated On:	P							0-225-155-2025		27.7	0.0	8.4	30.1				
REPROCESSED MATERIAL 55-99-033-PIT Created On: 03/04/25 Updated On:	P							0-225-161-2025		28.8	0.0	8.1	28.5				
REPROCESSED MATERIAL 55-99-033-PIT Created On: 03/06/25 Updated On:	P							0-225-163-2025		9.2	0.0	7.1	30.4				
								Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate									
REPROCESSED MATERIAL 55-99-033-PIT Created On: 03/06/25 Updated On:	P							0-225-165-2025		41.2	0.0	10.0	33.4				
REPROCESSED MATERIAL 55-99-033-PIT Created On: 03/24/25 Updated On:	P							0-225-174-2025		25.7	0.0	6.7	27.1				
REPROCESSED MATERIAL 55-99-033-PIT Created On: 03/24/25 Updated On:	P							0-225-177-2025		31.2	0.0	6.4	26.5				
REPROCESSED MATERIAL 55-99-033-PIT Created On: 03/24/25 Updated On:	P							0-225-178-2025		31.1	0.0	6.7	27.7				

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
REPROCESSED MATERIAL 55-99-033-PIT Created On: 03/24/25 Updated On:	P							0-225-179-2025		33.9	0.0	7.6	31.6				
REPROCESSED MATERIAL 55-99-033-PIT Created On: 04/07/25 Updated On:	P							0-225-185-2025		35.6	0.0	5.5	25.5				
REPROCESSED MATERIAL 55-99-033-PIT Created On: 04/15/25 Updated On:	P							0-225-192-2025		24.6	0.0	6.0	32.0				
REPROCESSED MATERIAL 55-99-033-PIT Created On: 04/15/25 Updated On:	P							0-225-193-2025		27.7	0.0	7.0	34.0				
REPROCESSED MATERIAL 55-99-033-PIT Created On: 04/15/25 Updated On:	P							0-225-194-2025		24.7	0.0	7.2	27.3				
REPROCESSED MATERIAL 55-99-033-PIT Created On: 04/15/25 Updated On:	P							0-225-195-2025		27.0	0.0	7.0	27.7				
REPROCESSED MATERIAL 55-99-033-PIT Created On: 06/02/25 Updated On:	P							0-225-214-2025		19.9	0.0	7.6	29.9				

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
REPROCESSED MATERIAL 55-99-033-PIT Created On: 06/12/25 Updated On:	P							0-225-221-2025		17.8	0.0	5.8	25.4				
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																
REPROCESSED MATERIAL 55-99-033-PIT Created On: 07/23/25 Updated On:	P							0-225-224-2025		21.0	0.0	10.8	32.5				
RESCH 55-37-066-PIT Created On: 01/05/17 Updated On:	P	NW	NW	1	29N	10E	Marathon	0-225-16-2017		0.0	2.8	8.3	32.8	2.651	2.672	0.760	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
RESCH 55-37-066-PIT Created On: 05/17/22 Updated On:	P	NW	NW	1	29N	10E	Marathon	0-225-202-2022	0.0	0.0	2.8	8.7	33.5	2.636	2.663	1.047	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
REVELS QUARRY 55-41-018-QRY Created On: 04/25/17 Updated On:	Q	NW	SE	1	16N	3W	Monroe	0-225-155-2017	0.6	0.0	7.0	12.0	42.7	2.547	2.624	3.030	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
REVELS QUARRY 55-41-018-QRY Created On: 02/13/20 Updated On:	Q	NW	SE	1	16N	3W	Monroe	0-225-115-2020	0.0	0.0	3.2	12.9	44.7	2.558	2.631	2.866	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
REVELS QUARRY 55-41-018-QRY Created On: 04/10/23 Updated On:	Q	NW	SE	1	16N	3W	Monroe	0-225-193-2023	2.9	3.5	8.3	11.2	41.9	2.580	2.645	2.540	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
RICHMOND 55-64-035-PIT Created On: 01/12/16 Updated On:	P	NW	NW	15	3N	15E	Walworth	0-225-58-2016	2.4	0.0	1.6	5.2	25.2	2.697	2.736	1.466	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
RICHMOND 55-64-035-PIT Created On: 01/04/21 Updated On:	P	NW	NW	15	3N	15E	Walworth	0-225-10-2021	0.4	3.4	2.3	5.3	26.2	2.696	2.731	1.293	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
RIDGESTONE 55-24-015-QRY Created On: 10/14/16 Updated On:	Q	SW	SE	15	17N	13E	Green Lake	0-225-270-2016	0.9	2.9	1.3	9.5	37.8	2.672	2.719	1.778	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
RIDGESTONE 55-24-015-QRY Created On: 05/24/19 Updated On:	Q	SW	SE	15	17N	13E	Green Lake	0-225-200-2019	0.1	9.3	2.1	10.1	38.9	2.686	2.730	1.634	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
RIDGESTONE 55-24-015-QRY Created On: 03/12/25 Updated On:	Q	SW	SE	15	17N	13E	Green Lake	0-225-173-2025	0.4	2.5	4.4	8.7	36.0	2.695	2.731	1.351	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
* RIGGENBERG 55-13-016-QRY Created On: 10/03/22 Updated On:	Q		NW	23	6N	7E	Dane	0-225-256-2022	0.5	11.6	4.4	7.1	32.4	2.653	2.708	2.068	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
* RIGGENBERG 55-13-016-QRY Created On: 04/07/25 Updated On:	Q		NW	23	6N	7E	Dane	0-225-184-2025	2.8	11.9	11.6	9.9	38.1	2.538	2.655	4.589	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
* RIGGENBERG 55-13-016-QRY Created On: 04/21/25 Updated On:	Q		NW	23	6N	7E	Dane	0-225-198-2025	0.6	14.7	6.6	6.7	29.8	2.651	2.709	2.172	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
RILEY 55-01-007-PIT Created On: 05/01/15 Updated On:	P	NW	SW	19	14N	7E	Adams	0-225-141-2015		0.0	2.8	7.5	28.9	2.819	2.846	0.969	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
RILEY 55-01-007-PIT Created On: 04/28/22 Updated On:	P	NW	SW	19	14N	7E	Adams	0-225-192-2022	0.1	0.0	0.6	6.2	25.7	2.770	2.803	1.188	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
* RIO AGGREGATE PRODUCTS 55-11-020-QRY Created On: 02/09/22 Updated On:	Q	NW	SE	32	12N	11E	Columbia	0-225-118-2022	0.8	2.4	3.1	8.1	35.2	2.617	2.675	2.203	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
* RIPP 55-13-076-QRY Created On: 03/19/15 Updated On:	Q	NW	NW	16	9N	9E	Dane	0-225-99-2015	2.8	3.7	3.2	10.3	36.5	2.555	2.629	2.921	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
* RIPP 55-13-076-QRY Created On: 01/03/18 Updated On:	Q	NW	NW	16	9N	9E	Dane	0-225-23-2018	2.8	2.3	3.1	7.9	31.9	2.575	2.647	2.813	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
* RIPP 55-13-076-QRY Created On: 01/05/21 Updated On:	Q	NW	NW	16	9N	9E	Dane	0-225-98-2021	2.7	3.4	3.7	9.3	36.5	2.543	2.609	2.630	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Coarse Sp. Gravity		Coarse Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
RISNER 55-38-029-PIT Created On: 06/13/22 Updated On:	P	S	SW	16	30N	20E	Marinette	0-225-225-2022	1.2	0.0	0.6	6.0	26.4	2.711	2.741	1.083	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
RIVARD 55-55-012-QRY Created On: 01/12/15 Updated On:	Q	SE	NE	12	30N	20W	St. Croix	0-225-63-2015		0.0	10.9	12.2	39.7	2.522	2.611	3.564	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
RIVARD 55-55-012-QRY Created On: 01/03/18 Updated On:	Q	SE	NE	12	30N	20W	St. Croix	0-225-33-2018	1.2	0.0	4.1	9.9	35.4	2.562	2.639	3.018	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
RIVARD 55-55-012-QRY Created On: 01/05/21 Updated On:	Q	SE	NE	12	30N	20W	St. Croix	0-225-74-2021	1.4	0.0	0.8	7.8	33.9	2.535	2.605	2.738	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
RIVARD 55-55-012-QRY Created On: 01/02/24 Updated On:	Q	SE	NE	12	30N	20W	St. Croix	0-225-78-2024	2.2	5.6	5.1	8.7	29.9	2.607	2.665	2.246	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
RIVER BEND 55-43-020-PIT Created On: 06/13/18 Updated On:	P			22	36N	9E	Oneida	0-225-229-2018	0.0	0.0	1.1	5.1	22.6	2.730	2.749	0.698	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
RIVER BEND 55-43-020-PIT Created On: 01/19/23 Updated On:	P			22	36N	9E	Oneida	0-225-125-2023	0.0	0.0	1.7	4.6	21.4	2.705	2.726	0.774	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
Source Name	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
RIVERVIEW 55-38-046-PIT Created On: 06/13/22 Updated On:	P	SW	SW	18	31N	21E	Marinette	0-225-224-2022	0.5	0.0	2.5	4.6	24.8	2.719	2.743	0.897		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
RLAM (RIPON LIME & MATERIALS) 55-20-035-QRY Created On: 02/06/23 Updated On:	Q	SW	NW	20	16N	14E	Fond Du Lac	0-225-135-2023	0.2	13.7	5.9	7.7	32.3	2.702	2.744	1.525		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
RLAM (RIPON LIME & MATERIALS) 55-20-035-QRY Created On: 01/04/24 Updated On:	Q	SW	NW	20	16N	14E	Fond Du Lac	0-225-145-2024	0.4	2.8	3.3	7.4	32.6	2.710	2.747	1.369		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
ROBERTSON 27-00-014-PIT Created On: 03/16/16 Updated On:	P	NW	SW	11	52N	17W	St Louis	0-225-98-2016		0.6	0.4	2.3	13.4	2.753	2.781	1.035		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
ROBERTSON 27-00-014-PIT Created On: 04/19/21 Updated On:	P	NW	SW	11	52N	17W	St Louis	0-225-184-2021	2.0	1.3	1.6	4.2	19.2	2.797	2.820	0.837		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
ROCK SPRINGS 55-56-024-QRY Created On: 04/17/15 Updated On:	Q		SW	28	12N	5E	Sauk	0-225-127-2015		0.0	0.1	4.0	19.4	2.641	2.649	0.302		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
ROCK SPRINGS 55-56-024-QRY Created On: 02/09/18 Updated On:	Q		SW	28	12N	5E	Sauk	0-225-95-2018	0.2	0.0	0.4	5.6	23.8	2.650	2.658	0.313		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
ROCK SPRINGS 55-56-024-QRY Created On: 01/05/21 Updated On:	Q		SW	28	12N	5E	Sauk	0-225-62-2021	0.1	0.2	0.4	5.1	22.2	2.656	2.666	0.351	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
ROCK SPRINGS 55-56-024-QRY Created On: 01/02/24 Updated On:	Q		SW	28	12N	5E	Sauk	0-225-124-2024	0.0	0.5	0.3	5.2	22.5	2.657	2.664	0.273	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
ROCKLAND QUARRY 55-05-023-QRY Created On: 02/03/17 Updated On:	Q	SE	NE	12	22N	20E	Brown	0-225-61-2017	1.8	5.0	5.6	9.1	33.6	2.680	2.731	1.897	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
ROCKLAND QUARRY 55-05-023-QRY Created On: 01/02/20 Updated On:	Q	SE	NE	12	22N	20E	Brown	0-225-4-2020	0.5	1.9	0.7	5.6	26.9	2.735	2.767	1.163	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
ROCKLAND QUARRY 55-05-023-QRY Created On: 01/03/23 Updated On:	Q	SE	NE	12	22N	20E	Brown	0-225-75-2023	1.5	1.5	1.5	6.3	28.1	2.709	2.747	1.416	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
ROCKWELL LIMESTONE 55-36-035-QRY Created On: 04/13/16 Updated On:	Q			36	20N	23E	Manitowoc	0-225-146-2016		0.0	2.0	12.6	41.7	2.693	2.735	1.577	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
ROCKWELL LIMESTONE 55-36-035-QRY Created On: 04/19/19 Updated On:	Q			36	20N	23E	Manitowoc	0-225-148-2019		0.0	2.9	12.7	42.1	2.692	2.739	1.722	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
ROCKWELL LIMESTONE 55-36-035-QRY Created On: 03/07/22 Updated On:	Q			36	20N	23E	Manitowoc	0-225-137-2022	0.0	0.0	3.0	9.6	32.0	2.728	2.759	1.126	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
ROCKWELL LIMESTONE 55-36-035-QRY Created On: 01/02/25 Updated On:	Q			36	20N	23E	Manitowoc	0-225-62-2025	0.0	3.5	14.5	23.5	56.3	2.658	2.709	1.915	
ROCKY RUN 55-43-024-PIT Created On: 04/11/18 Updated On:	P	SW	14	37N	6E	Oneida		0-225-168-2018	0.5	0.0	0.3	4.3	19.2	2.705	2.727	0.801	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
ROCKY RUN 55-43-024-PIT Created On: 01/03/23 Updated On:	P	SW	14	37N	6E	Oneida		0-225-28-2023	0.5	0.0	1.4	3.9	18.3	2.715	2.740	0.915	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
ROMANOWSKI 55-09-058-PIT Created On: 04/21/17 Updated On:	P	NW	NE	36	31N	5W	Chippewa	0-225-147-2017		0.0	2.1	4.9	21.8	2.667	2.704	1.391	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
ROMANOWSKI 55-09-058-PIT Created On: 01/10/23 Updated On:	P	NW	NE	36	31N	5W	Chippewa	0-225-106-2023	4.1	0.0	2.3	3.8	19.4	2.662	2.693	1.166	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
ROMSKOG 55-32-014-QRY Created On: 04/28/17 Updated On:	Q	NE	SE	18	17N	6W	La Crosse	0-225-162-2017		0.0	5.4	9.8	38.9	2.552	2.636	3.288	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
ROMSKOG 55-32-014-QRY Created On: 01/08/20 Updated On:	Q	NE	SE	18	17N	6W	La Crosse	0-225-64-2020	0.2	0.0	6.3	10.2	37.2	2.567	2.639	2.815	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
ROMSKOG 55-32-014-QRY Created On: 01/03/23 Updated On:	Q	NE	SE	18	17N	6W	La Crosse	0-225-24-2023	0.5	3.8	3.4	12.4	43.5	2.567	2.636	2.683	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
ROSE 55-37-071-QRY Created On: 01/05/17 Updated On:	Q	NE	NW	36	30N	8E	Marathon	0-225-39-2017		0.0	0.2	6.0	26.7	2.615	2.625	0.399	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
ROSE 55-37-071-QRY Created On: 01/03/20 Updated On:	Q	NE	NW	36	30N	8E	Marathon	0-225-14-2020	0.0	0.0	0.5	6.9	32.0	2.598	2.614	0.622	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
ROSE 55-37-071-QRY Created On: 01/03/23 Updated On:	Q	NE	NW	36	30N	8E	Marathon	0-225-19-2023	0.0	0.0	0.3	6.6	29.7	2.605	2.621	0.603	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
ROSE SPUR 19-00-005-QRY Created On: 07/30/15 Updated On:	Q	NE	SE	27	90N	2E	Dubuque	0-225-221-2015	1.9	3.5	3.4	10.5	38.6	2.585	2.651	2.533	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
ROSE SPUR 19-00-005-QRY Created On: 01/04/18 Updated On:	Q	NE	SE	27	90N	2E	Dubuque	0-225-69-2018	2.5	11.3	4.1	9.7	36.4	2.582	2.646	2.493	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
ROSE SPUR 19-00-005-QRY Created On: 01/05/21 Updated On:	Q	NE	SE	27	90N	2E	Dubuque	0-225-58-2021	1.2	5.2	10.0	9.3	35.3	2.567	2.638	2.764		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
ROSE SPUR 19-00-005-QRY Created On: 01/02/24 Updated On:	Q	NE	SE	27	90N	2E	Dubuque	0-225-28-2024	2.0	9.4	3.5	9.8	35.8	2.584	2.652	2.603		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
ROSE STONE 55-03-032-QRY Created On: 01/09/15 Updated On:	Q	SE	SE	30	35N	10W	Barron	0-225-45-2015		0.0	0.7	9.1	41.7	2.553	2.577	0.961		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
ROSE STONE 55-03-032-QRY Created On: 03/23/18 Updated On:	Q	SE	SE	30	35N	10W	Barron	0-225-135-2018		0.0	1.4	7.7	33.7	2.559	2.582	0.885		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
ROSE STONE 55-03-032-QRY Created On: 03/17/21 Updated On:	Q	SE	SE	30	35N	10W	Barron	0-225-152-2021	0.0	0.1	0.3	9.2	38.7	2.565	2.583	0.705		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
ROSE STONE 55-03-032-QRY Created On: 01/04/24 Updated On:	Q	SE	SE	30	35N	10W	Barron	0-225-143-2024	0.0	0.7	1.2	12.6	45.4	2.536	2.567	1.189		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
ROSEMEYER 55-22-045-QRY Created On: 04/07/16 Updated On:	Q	SW	NW	14	3N	1W	Grant	0-225-134-2016	0.7	13.0	8.1	10.9	38.2	2.603	2.672	2.635		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
ROSEMEYER 55-22-045-QRY Created On: 01/04/19 Updated On:	Q	SW	NW	14	3N	1W	Grant	0-225-22-2019	1.8	13.7	4.9	12.2	41.3	2.601	2.667	2.505	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
ROSEMEYER 55-22-045-QRY Created On: 01/04/22 Updated On:	Q	SW	NW	14	3N	1W	Grant	0-225-47-2022	1.3	9.9	0.1	8.5	32.6	2.581	2.651	2.706	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
ROSEMEYER 55-22-045-QRY Created On: 01/02/25 Updated On:	Q	SW	NW	14	3N	1W	Grant	0-225-32-2025	1.4	7.2	4.4	8.8	34.8	2.564	2.642	3.052	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
ROSENBAUM 55-13-078-PIT Created On: 02/17/16 Updated On:	P	SW	NE	18	5N	11E	Dane	0-225-91-2016	7.4	0.0	5.0	8.3	34.0	2.600	2.658	2.249	
	Approved Use : HMA<E-3, HMA>=E-3, Base Aggregate																
ROSENBAUM 55-13-078-PIT Created On: 06/01/22 Updated On:	P	SW	NE	18	5N	11E	Dane	0-225-211-2022	0.3	4.9	6.6	10.0	34.0	2.607	2.661	2.064	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
ROSS 55-63-017-PIT Created On: 01/02/24 Updated On:	P	NE	SW	28	41N	10E	Vilas	0-225-61-2024	1.6	0.0	2.1	4.7	20.5	2.670	2.702	1.179	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
ROUER 55-42-033-QRY Created On: 01/04/22 Updated On:	Q	NW	NE	28	29N	21E	Oconto	0-225-89-2022	0.1	6.3	5.2	6.7	31.5	2.682	2.719	1.359	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
ROUER 55-42-033-QRY Created On: 01/14/25 Updated On:	Q	NW	NE	28	29N	21E	Oconto	0-225-108-2025	1.2	8.8	6.9	7.4	31.8	2.671	2.710	1.466		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
RUBIE 19-00-007-QRY Created On: 01/04/18 Updated On:	Q		SE	6	88N	3E	Dubuque	0-225-66-2018	0.6	4.6	2.5	8.5	35.4	2.578	2.639	2.392		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
RUBIE 19-00-007-QRY Created On: 03/17/21 Updated On:	Q		SE	6	88N	3E	Dubuque	0-225-144-2021	1.1	3.5	3.7	7.6	33.0	2.614	2.670	2.141		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
RUBIE 19-00-007-QRY Created On: 01/02/24 Updated On:	Q		SE	6	88N	3E	Dubuque	0-225-30-2024	0.4	2.9	0.7	8.4	31.8	2.625	2.678	1.997		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
RUBY 55-37-072-QRY Created On: 01/05/17 Updated On:	Q	SE	NW	22	30N	7E	Marathon	0-225-38-2017		0.0	0.8	5.7	26.7	2.598	2.611	0.485		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
RUBY 55-37-072-QRY Created On: 01/03/20 Updated On:	Q	SE	NW	22	30N	7E	Marathon	0-225-13-2020		0.0	1.1	8.0	37.1	2.581	2.602	0.827		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
RUBY 55-37-072-QRY Created On: 01/03/23 Updated On:	Q	SE	NW	22	30N	7E	Marathon	0-225-18-2023	0.0	0.0	0.6	5.8	28.0	2.596	2.613	0.650		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
RUDINGER 55-20-041-QRY Created On: 01/08/15 Updated On:	Q		NW	11	14N	17E	Fond Du Lac	0-225-28-2015		0.4	1.9	8.0	34.1	2.730	2.758	1.030	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
RUDINGER 55-20-041-QRY Created On: 03/07/16 Updated On:	Q		NW	11	14N	17E	Fond Du Lac	0-225-95-2016		1.0	1.3	5.2	25.1	2.762	2.785	0.866	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
RUDINGER 55-20-041-QRY Created On: 01/04/19 Updated On:	Q		NW	11	14N	17E	Fond Du Lac	0-225-20-2019	0.7	1.5	0.9	5.7	27.2	2.760	2.786	0.950	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
RUDINGER 55-20-041-QRY Created On: 01/04/22 Updated On:	Q		NW	11	14N	17E	Fond Du Lac	0-225-21-2022	0.0	0.7	1.5	6.2	28.8	2.727	2.761	1.255	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
RUDINGER 55-20-041-QRY Created On: 01/02/24 Updated On:	Q		NW	11	14N	17E	Fond Du Lac	0-225-101-2024	0.0	0.7	0.8	5.6	27.1	2.775	2.794	0.692	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
RUEF 55-33-024-QRY Created On: 04/06/17 Updated On:	Q	SW	SE	11	2N	3E	Lafayette	0-225-111-2017	1.9	2.4	1.5	10.1	35.5	2.591	2.657	2.532	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
RUEF 55-33-024-QRY Created On: 04/28/20 Updated On:	Q	SW	SE	11	2N	3E	Lafayette	0-225-159-2020	1.1	4.1	1.6	9.3	35.1	2.586	2.665	3.055	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
RUEF 55-33-024-QRY Created On: 01/03/23 Updated On:	Q	SW	SE	11	2N	3E	Lafayette	0-225-8-2023	0.4	4.9	4.3	10.8	38.2	2.551	2.632	3.191	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
RUFERS 55-23-020-QRY Created On: 03/08/17 Updated On:	Q			30	2N	8E	Green	0-225-77-2017	0.4	16.0	5.1	10.6	38.0	2.554	2.639	3.342	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
RUFERS 55-23-020-QRY Created On: 04/17/23 Updated On:	Q			30	2N	8E	Green	0-225-195-2023	0.6	18.1	4.6	6.4	28.8	2.582	2.658	2.934	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
SAFFERT 795 55-03-034-PIT Created On: 01/06/16 Updated On:	P	SW	SW	1	34N	11W	Barron	0-225-27-2016		0.0	5.3	5.7	24.0	2.662	2.703	1.554	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
SAFFERT 795 55-03-034-PIT Created On: 01/05/21 Updated On:	P	SW	SW	1	34N	11W	Barron	0-225-77-2021	0.9	3.8	5.1	4.9	20.8	2.711	2.743	1.184	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
SALZGERBER 55-22-046-QRY Created On: 01/05/17 Updated On:	Q	NE	SW	2	7N	3W	Grant	0-225-34-2017	3.1	4.8	5.6	9.1	37.2	2.619	2.670	1.925	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
SALZGERBER 55-22-046-QRY Created On: 01/09/20 Updated On:	Q	NE	SW	2	7N	3W	Grant	0-225-85-2020	2.8	3.8	7.1	10.2	40.5	2.603	2.659	2.124	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
SALZGERBER 55-22-046-QRY Created On: 01/03/23 Updated On:	Q	NE	SW	2	7N	3W	Grant	0-225-63-2023	1.4	5.6	1.3	11.5	39.5	2.592	2.657	2.498	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
SAMBS STONE 55-34-022-PIT Created On: 03/09/15 Updated On:	P	NW	NW	11	30N	11E	Langlade	0-225-94-2015		0.0	1.6	6.2	26.7	2.675	2.698	0.884	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
SAMBS STONE 55-34-022-PIT Created On: 01/07/20 Updated On:	P	NW	NW	11	30N	11E	Langlade	0-225-46-2020	0.0	1.6	0.5	6.9	29.4	2.687	2.706	0.724	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
SAMBS STONE 55-34-022-PIT Created On: 02/24/25 Updated On:	P	NW	NW	11	30N	11E	Langlade	0-225-156-2025	0.6	3.7	4.2	6.1	25.9	2.671	2.695	0.916	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
SAND LAKE 55-57-023-PIT Created On: 01/25/16 Updated On:	P	NW	NW	15	38N	9W	Sawyer	0-225-78-2016		0.0	1.6	4.2	17.0	2.787	2.816	1.030	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
SAND LAKE 55-57-023-PIT Created On: 05/23/23 Updated On:	P	NW	NW	15	38N	9W	Sawyer	0-225-226-2023	1.4	0.0	0.8	4.5	19.6	2.750	2.773	0.843	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
SANICKI 55-19-012-PIT Created On: 05/13/21 Updated On:	P		SE	31	38N	17E	Florence	0-225-207-2021	0.2	0.4	0.7	4.9	21.1	2.725	2.747	0.805	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
SAXON 55-26-019-PIT Created On: 06/13/18 Updated On:	P	SW	SW	18	46N	1E	Iron	0-225-231-2018		1.0	7.5	5.5	27.2	2.617	2.680	2.440	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
SAXON 55-26-019-PIT Created On: 04/04/23 Updated On:	P	SW	SW	18	46N	1E	Iron	0-225-181-2023		0.0	14.3	5.2	21.7	2.615	2.681	2.528	
	Approved Use : Base Aggregate																
SAXON 55-26-019-PIT Created On: 01/02/25 Updated On:	P	SW	SW	18	46N	1E	Iron	0-225-71-2025	2.5	0.0	11.8	4.1	20.0	2.619	2.678	2.235	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
SCANLON PIT 27-00-029-PIT Created On: 07/31/24 Updated On:	P	NE	NW	36	49N	8W	Statewide	0-225-292-2024	0.9	4.2	1.4	3.4	16.3	2.703	2.729	0.941	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
SCHADLER 55-13-081-PIT Created On: 01/03/18 Updated On:	P	NE	SE	10	8N	6E	Dane	0-225-26-2018	2.9	3.7	3.1	8.8	34.0	2.444	2.512	2.786	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
SCHADLER 55-13-081-PIT Created On: 01/04/23 Updated On:	P	NE	SE	10	8N	6E	Dane	0-225-97-2023	6.9	0.0	3.3	8.8	34.0	2.580	2.629	1.886	
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																
SCHALLOCK 55-21-018-PIT Created On: 08/03/16 Updated On:	P	SE	NE	36	36N	12E	Forest	0-225-234-2016	0.4	0.0	1.5	5.0	21.9	2.695	2.721	0.939	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
SCHALLOCK 55-21-018-PIT Created On: 01/04/21 Updated On:	P	SE	NE	36	36N	12E	Forest	0-225-13-2021	0.0	1.4	0.3	4.8	20.7	2.675	2.707	1.208	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
SCHICK 55-09-060-PIT Created On: 04/21/17 Updated On:	P	SW	NW	2	29N	8W	Chippewa	0-225-143-2017		0.0	2.4	4.9	20.6	2.688	2.720	1.163	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
SCHICK 55-09-060-PIT Created On: 01/04/22 Updated On:	P	SW	NW	2	29N	8W	Chippewa	0-225-80-2022	1.2	0.0	3.2	4.3	20.8	2.688	2.715	1.025	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
SCHILL 55-71-025-QRY Created On: 01/03/17 Updated On:	Q	NW	SW	1	23N	4E	Wood	0-225-4-2017		0.0	0.2	4.9	22.8	2.605	2.617	0.487	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
SCHILL 55-71-025-QRY Created On: 01/02/20 Updated On:	Q	NW	SW	1	23N	4E	Wood	0-225-9-2020	0.9	0.0	0.9	5.1	21.6	2.617	2.629	0.464	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
SCHILL 55-71-025-QRY Created On: 01/03/23 Updated On:	Q	NW	SW	1	23N	4E	Wood	0-225-32-2023	0.2	1.3	1.0	5.7	24.1	2.606	2.619	0.509	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
SCHMITZ 55-41-020-QRY Created On: 08/03/18 Updated On:	Q		SW	18	15N	2W	Monroe	0-225-262-2018	0.7	0.0	5.4	12.4	41.2	2.594	2.657	2.406	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
Source Name	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
SCHMITZ 55-41-020-QRY Created On: 01/05/21 Updated On:	Q		SW	18	15N	2W	Monroe	0-225-65-2021	0.7	0.0	0.3	7.3	30.7	2.634	2.685	1.921		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
SCHMITZ 55-41-020-QRY Created On: 01/02/24 Updated On:	Q		SW	18	15N	2W	Monroe	0-225-26-2024	0.9	2.2	4.2	10.5	39.3	2.599	2.663	2.464		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
SCHMOKER 55-70-029-QRY Created On: 01/09/15 Updated On:	Q		NE	20	19N	16E	Winnebago	0-225-47-2015		3.1	2.0	4.5	20.9	2.773	2.795	0.803		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
SCHMOKER 55-70-029-QRY Created On: 01/04/18 Updated On:	Q		NE	20	19N	16E	Winnebago	0-225-57-2018		4.0	2.1	4.7	21.5	2.771	2.796	0.877		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
SCHMOKER 55-70-029-QRY Created On: 01/05/21 Updated On:	Q		NE	20	19N	16E	Winnebago	0-225-52-2021	0.0	2.9	6.3	6.4	29.9	2.787	2.811	0.841		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
SCHMOKER 55-70-029-QRY Created On: 01/02/24 Updated On:	Q		NE	20	19N	16E	Winnebago	0-225-55-2024	0.2	5.9	7.4	6.1	25.9	2.768	2.793	0.921		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
SCHNEIDER 55-22-048-QRY Created On: 04/16/15 Updated On:	Q	NW	SE	18	4N	3W	Grant	0-225-122-2015	2.2	10.4	6.7	12.8	43.4	2.598	2.665	2.571		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
SCHNEIDER 55-22-048-QRY Created On: 07/28/17 Updated On:	Q	NW	SE	18	4N	3W	Grant	0-225-243-2017	0.3	4.2	8.3	14.4	44.3	2.599	2.667	2.610	
	Approved Use : CONCRETE, OGBC, Base Aggregate																
SCHNEIDER 55-22-048-QRY Created On: 04/28/20 Updated On:	Q	NW	SE	18	4N	3W	Grant	0-225-161-2020	0.1	3.5	2.1	10.8	39.6	2.547	2.631	3.309	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
SCHNEIDER 55-22-048-QRY Created On: 01/03/23 Updated On:	Q	NW	SE	18	4N	3W	Grant	0-225-7-2023	0.4	4.4	7.9	13.0	42.6	2.567	2.640	2.852	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
SCHOEPP 55-13-082-QRY Created On: 03/30/18 Updated On:	Q		NE	9	7N	7E	Dane	0-225-156-2018	1.3	3.5	2.0	9.9	36.8	2.595	2.654	2.262	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
SCHOEPP 55-13-082-QRY Created On: 06/24/19 Updated On:	Q		NE	9	7N	7E	Dane	0-225-225-2019	0.3	2.2	1.8	8.4	35.7	2.592	2.652	2.289	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
SCHOEPP 55-13-082-QRY Created On: 03/21/23 Updated On:	Q		NE	9	7N	7E	Dane	0-225-170-2023	0.3	1.9	3.9	10.2	41.9	2.610	2.664	2.034	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
SCHOOL HILL 55-36-036-PIT Created On: 04/19/19 Updated On:	P	NE	NW	16	17N	22E	Manitowoc	0-225-146-2019	0.6	2.1	0.5	7.2	29.7	2.786	2.807	0.767	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
Source Name	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
SCHOOL HILL 55-36-036-PIT Created On: 01/02/24 Updated On:	P	NE	NW	16	17N	22E	Manitowoc	0-225-130-2024	0.0	2.0	0.7	6.4	30.1	2.785	2.806	0.764		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
SCHREINER 55-60-022-PIT Created On: 01/03/18 Updated On:	P		SE	1	32N	2E	Taylor	0-225-29-2018	0.5	0.0	1.5	4.1	18.3	2.710	2.733	0.825		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
SCHREINER 55-60-022-PIT Created On: 01/10/23 Updated On:	P		SE	1	32N	2E	Taylor	0-225-111-2023	2.1	0.0	2.1	4.1	19.8	2.659	2.688	1.086		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
SCHUCKNECHT 55-56-026-QRY Created On: 01/03/18 Updated On:	Q	SW	SW	25	9N	4E	Sauk	0-225-10-2018	0.1	0.0	1.2	8.1	31.4	2.644	2.696	1.973		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
SCHUCKNECHT 55-56-026-QRY Created On: 01/04/21 Updated On:	Q	SW	SW	25	9N	4E	Sauk	0-225-32-2021	0.5	0.0	0.4	8.9	33.1	2.635	2.690	2.091		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
SCHUCKNECHT 55-56-026-QRY Created On: 01/02/24 Updated On:	Q	SW	SW	25	9N	4E	Sauk	0-225-21-2024	0.4	7.3	1.5	8.8	33.0	2.653	2.703	1.892		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
SCHUETZ 55-13-083-QRY Created On: 04/11/18 Updated On:	Q	SE	SW	26	6N	10E	Dane	0-225-164-2018	4.6	3.8	7.5	10.4	39.4	2.554	2.620	2.605		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Coarse Sp. Gravity		Coarse Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
SCHUETZ 55-13-083-QRY Created On: 01/03/23 Updated On:	Q	SE	SW	26	6N	10E	Dane	0-225-1-2023	1.1	1.6	1.9	5.5	27.4	2.651	2.692	1.521	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
SCHWARZENBERGER 55-23-023-QRY Created On: 05/06/15 Updated On:	Q	NW	NW	5	1N	8E	Green	0-225-146-2015	2.4	7.6	13.7	12.8	44.9	2.541	2.634	3.654	
	Approved Use : Base Aggregate																
SCHWARZENBERGER 55-23-023-QRY Created On: 04/25/17 Updated On:	Q	NW	NW	5	1N	8E	Green	0-225-158-2017	0.4	6.7	10.1	10.7	39.9	2.598	2.674	2.921	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
SCHWARZENBERGER 55-23-023-QRY Created On: 02/12/20 Updated On:	Q	NW	NW	5	1N	8E	Green	0-225-111-2020	0.4	17.9	21.9	9.3	37.7	2.628	2.691	2.410	
SCHWARZENBERGER 55-23-023-QRY Created On: 03/13/24 Updated On:	Q	NW	NW	5	1N	8E	Green	0-225-196-2024	1.1	2.9	5.2	11.6	42.8	2.559	2.645	3.354	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
SCOTT 55-05-027-QRY Created On: 01/02/24 Updated On:	Q	NW	NE	18	24N	22E	Brown	0-225-9-2024	0.2	1.2	0.3	5.4	23.1	2.713	2.751	1.408	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
SCOTT CONSTRUCTION - COOPERSTOWN 55-36-044-QRY Created On: 05/30/17 Updated On:	Q	W	NW	19	21N	22E	Manitowoc	0-225-200-2017	11.6	0.0	6.4	6.1	26.7	2.673	2.722	1.843	
	Approved Use : HMA<MT, HMA>=MT, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
SCOTT CONSTRUCTION - COOPERSTOWN 55-36-044-QRY Created On: 02/28/23 Updated On:	Q	W	NW	19	21N	22E	Manitowoc	0-225-157-2023	9.6	5.6	5.2	5.8	27.5	2.665	2.712	1.737	
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																
SCRAY HILL QUARRY 55-05-003-QRY Created On: 04/05/16 Updated On:	Q	S	NW	5	22N	21E	Brown	0-225-122-2016	3.0	1.4	1.2	6.3	28.9	2.703	2.749	1.717	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
SCRAY HILL QUARRY 55-05-003-QRY Created On: 04/19/19 Updated On:	Q	S	NW	5	22N	21E	Brown	0-225-149-2019	2.0	1.1	2.9	6.2	27.4	2.709	2.748	1.437	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
SCRAY HILL QUARRY 55-05-003-QRY Created On: 01/04/22 Updated On:	Q	S	NW	5	22N	21E	Brown	0-225-72-2022	6.3	10.3	3.4	7.5	29.1	2.656	2.704	1.797	
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																
SCRAY HILL QUARRY 55-05-003-QRY Created On: 01/30/25 Updated On:	Q	S	NW	5	22N	21E	Brown	0-225-144-2025	6.3	5.3	4.1	7.8	31.2	2.677	2.725	1.777	
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																
SEAS BRANCH 55-62-029-QRY Created On: 01/04/23 Updated On:	Q	NE	NW	15	13N	4W	Vernon	0-225-84-2023	0.5	1.5	2.4	9.6	33.9	2.681	2.720	1.471	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
SEVEN SISTERS 55-01-008-QRY Created On: 08/25/16 Updated On:	Q			36	20N	7E	Adams	0-225-248-2016		0.9	0.7	4.6	20.7	2.631	2.646	0.591	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
SEVEN SISTERS 55-01-008-QRY Created On: 01/04/19 Updated On:	Q			36	20N	7E	Adams	0-225-33-2019	0.2	0.0	0.9	4.7	19.6	2.625	2.642	0.666	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
SEVEN SISTERS 55-01-008-QRY Created On: 01/04/22 Updated On:	Q			36	20N	7E	Adams	0-225-36-2022	4.2	12.0	7.8	6.1	22.9	2.543	2.598	2.169	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
SEVEN SISTERS 55-01-008-QRY Created On: 01/02/25 Updated On:	Q			36	20N	7E	Adams	0-225-9-2025	1.1	3.5	1.9	4.3	18.7	2.614	2.637	0.914	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
SEYMOUR 55-44-027-QRY Created On: 05/11/17 Updated On:	Q	SW	SE	31	24N	18E	Outagamie	0-225-180-2017		3.9	1.1	7.5	30.5	2.724	2.761	1.330	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
SEYMOUR 55-44-027-QRY Created On: 04/08/20 Updated On:	Q	SW	SE	31	24N	18E	Outagamie	0-225-146-2020	0.2	12.6	2.4	8.0	30.9	2.758	2.784	0.918	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
SEYMOUR 55-44-027-QRY Created On: 02/28/23 Updated On:	Q	SW	SE	31	24N	18E	Outagamie	0-225-160-2023	1.0	8.8	1.4	6.9	27.6	2.741	2.772	1.124	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
* SHADY NOOK 55-60-032-QRY Created On: 01/05/17 Updated On:	Q	NW	SW	23	30N	2W	Taylor	0-225-17-2017		0.0	0.2	4.7	23.0	2.740	2.754	0.503	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
* SHADY NOOK 55-60-032-QRY Created On: 05/21/21 Updated On:	Q	NW	SW	23	30N	2W	Taylor	0-225-211-2021	0.0	0.0	0.3	4.8	21.9	2.735	2.747	0.467		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
SHAKAL VALLEY 55-09-063-PIT Created On: 03/21/19 Updated On:	P	NW	SW	23	29N	6W	Chippewa	0-225-110-2019	5.5	0.0	6.1	6.3	22.7	2.649	2.686	1.392		
	Approved Use : HMA<MT, HMA>=MT, Base Aggregate																	
SHAKAL VALLEY 55-09-063-PIT Created On: 01/02/24 Updated On:	P	NW	SW	23	29N	6W	Chippewa	0-225-118-2024	2.6	0.0	2.6	4.7	19.4	2.674	2.704	1.127		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
SHANNON 55-52-021-QRY Created On: 05/19/16 Updated On:	Q	NW	SW	32	10N	1W	Richland	0-225-179-2016	1.0	4.2	4.9	8.4	35.3	2.625	2.677	1.988		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
SHANNON 55-52-021-QRY Created On: 07/25/19 Updated On:	Q	NW	SW	32	10N	1W	Richland	0-225-249-2019	0.6	3.2	2.5	7.3	33.2	2.662	2.705	1.623		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
SHANNON 55-52-021-QRY Created On: 04/05/22 Updated On:	Q	NW	SW	32	10N	1W	Richland	0-225-165-2022	0.5	4.5	5.7	8.0	34.4	2.648	2.695	1.803		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
SHANNON 55-52-021-QRY Created On: 01/02/25 Updated On:	Q	NW	SW	32	10N	1W	Richland	0-225-91-2025	0.7	5.7	4.0	8.8	36.7	2.614	2.675	2.311		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
Source Name	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
SHAWANO 55-58-036-QRY Created On: 05/11/15 Updated On:	Q	NE	NW	2	26N	16E	Shawano	0-225-164-2015	0.4	3.1	2.5	8.8	33.8	2.684	2.727	1.613		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
SHAWANO 55-58-036-QRY Created On: 01/04/18 Updated On:	Q	NE	NW	2	26N	16E	Shawano	0-225-61-2018		2.4	2.3	6.7	30.8	2.700	2.734	1.259		
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																	
SHAWANO 55-58-036-QRY Created On: 01/04/21 Updated On:	Q	NE	NW	2	26N	16E	Shawano	0-225-11-2021	0.2	4.1	3.1	5.3	26.5	2.699	2.737	1.410		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
SHAWANO 55-58-036-QRY Created On: 01/02/24 Updated On:	Q	NE	NW	2	26N	16E	Shawano	0-225-8-2024	0.0	2.3	0.3	5.7	26.9	2.722	2.754	1.151		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
SHOCKLEY HILL 55-12-020-QRY Created On: 05/18/17 Updated On:	Q	SW	NE	21	8N	3W	Crawford	0-225-189-2017		2.8	6.6	8.7	33.7	2.632	2.687	2.097		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
SHOCKLEY HILL 55-12-020-QRY Created On: 01/03/20 Updated On:	Q	SW	NE	21	8N	3W	Crawford	0-225-20-2020	0.5	1.1	0.5	7.2	28.3	2.618	2.675	2.193		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
SHOCKLEY HILL 55-12-020-QRY Created On: 01/02/24 Updated On:	Q	SW	NE	21	8N	3W	Crawford	0-225-33-2024	0.8	4.5	2.8	9.2	34.2	2.599	2.662	2.416		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
SIEKIERZYNSKI 55-37-094-PIT Created On: 06/13/22 Updated On:	P	SW	NE	29	27N	9E	Marathon	0-225-216-2022	0.5	0.0	1.0	7.9	32.2	2.614	2.645	1.188	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
SIEKIERZYNSKI 55-37-095-QRY Created On: 06/13/22 Updated On:	Q	SW	NE	29	27N	9E	Marathon	0-225-217-2022	0.1	0.0	0.9	7.6	34.2	2.643	2.659	0.630	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
SIEKIERZYNSKI 55-37-095-QRY Created On: 03/06/25 Updated On:	Q	SW	NE	29	27N	9E	Marathon	0-225-164-2025	0.0	0.0	0.2	4.7	23.1	2.692	2.699	0.275	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
SILHA MH 55-53-012-PIT Created On: 04/16/15 Updated On:	P	SW	NE	2	3N	13E	Rock	0-225-121-2015	0.9	0.0	5.1	6.5	30.2	2.650	2.703	2.026	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
SILHA MH 55-53-014-QRY Created On: 04/12/16 Updated On:	Q	SW	NE	2	3N	13E	Rock	0-225-143-2016	0.2	4.0	8.7	8.5	35.5	2.626	2.687	2.347	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
SILHA MH 55-53-014-QRY Created On: 06/02/17 Updated On:	Q	SW	NE	2	3N	13E	Rock	0-225-203-2017	1.1	2.1	7.9	8.1	34.2	2.603	2.669	2.559	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
SILHA MH 55-53-014-QRY Created On: 09/11/19 Updated On:	Q	SW	NE	2	3N	13E	Rock	0-225-269-2019	1.4	2.6	7.2	8.7	37.7	2.587	2.660	2.819	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
SILHA MH 55-53-014-QRY Created On: 06/23/20 Updated On:	Q	SW	NE	2	3N	13E	Rock	0-225-202-2020	1.8	12.3	13.2	9.8	39.3	2.621	2.672	1.928	
	Approved Use : Base Aggregate																
SILHA MH 55-53-012-PIT Created On: 06/23/20 Updated On:	P	SW	NE	2	3N	13E	Rock	0-225-203-2020	4.3	0.0	5.3	5.4	28.6	2.621	2.672	1.928	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
SILHA MH 55-53-014-QRY Created On: 01/03/23 Updated On:	Q	SW	NE	2	3N	13E	Rock	0-225-14-2023	2.1	6.9	8.7	10.0	39.4	2.553	2.632	3.119	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
SILHA MH 55-53-012-PIT Created On: 01/02/25 Updated On:	P	SW	NE	2	3N	13E	Rock	0-225-7-2025	2.8	0.0	1.9	6.6	30.9	2.650	2.701	1.920	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
SIMMON 55-22-049-QRY Created On: 01/04/18 Updated On:	Q	SW	NW	21	4N	4W	Grant	0-225-71-2018	0.8	10.7	10.0	11.2	40.4	2.575	2.642	2.590	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
SIMMON 55-22-049-QRY Created On: 01/04/22 Updated On:	Q	SW	NW	21	4N	4W	Grant	0-225-45-2022	1.1	10.1	0.7	10.9	39.0	2.559	2.629	2.746	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
SIMMON 55-22-049-QRY Created On: 01/02/25 Updated On:	Q	SW	NW	21	4N	4W	Grant	0-225-26-2025	0.3	2.9	2.7	10.5	36.4	2.567	2.642	2.915	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
SIREN 55-07-018-PIT Created On: 04/17/15 Updated On:	P	NE	SW	32	38N	16W	Burnett	0-225-128-2015		0.0	-7.4	5.1	20.2	2.703	2.740	1.347		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
SIREN 55-07-018-PIT Created On: 04/05/22 Updated On:	P	NE	SW	32	38N	16W	Burnett	0-225-164-2022	6.7	0.0	6.2	4.9	20.0	2.697	2.731	1.272		
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																	
* SITTE 55-15-028-QRY Created On: 03/22/19 Updated On:	Q	S	NE	2	31N	28E	Door	0-225-113-2019	5.5	0.0	5.0	6.1	27.5	2.618	2.674	2.165		
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																	
* SITTE 55-15-028-QRY Created On: 03/07/22 Updated On:	Q	S	NE	2	31N	28E	Door	0-225-138-2022	2.1	0.0	12.0	6.4	29.4	2.620	2.674	2.073		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
SKILLE V 55-57-025-PIT Created On: 05/02/19 Updated On:	P	NW	NE	33	40N	9W	Sawyer	0-225-175-2019	1.1	0.0	1.8	3.4	15.3	2.836	2.858	0.787		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
SKILLE V 55-57-025-PIT Created On: 01/04/24 Updated On:	P	NW	NE	33	40N	9W	Sawyer	0-225-140-2024	1.9	4.4	2.5	4.2	18.1	2.776	2.811	1.259		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
SLAMA 55-12-021-QRY Created On: 07/30/15 Updated On:	Q			18	7N	6W	Crawford	0-225-222-2015	1.1	1.8	2.1	8.7	33.9	2.614	2.675	2.350		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
SLAMA 55-12-021-QRY Created On: 01/04/18 Updated On:	Q			18	7N	6W	Crawford	0-225-73-2018	0.7	1.0	3.2	7.5	37.9	2.636	2.685	1.845	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
SLAMA 55-12-021-QRY Created On: 01/04/21 Updated On:	Q			18	7N	6W	Crawford	0-225-26-2021	1.0	6.6	5.0	7.5	31.7	2.612	2.668	2.167	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
SLAMA 55-12-021-QRY Created On: 01/02/24 Updated On:	Q			18	7N	6W	Crawford	0-225-27-2024	2.0	4.1	1.2	7.0	28.1	2.650	2.696	1.710	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
SMASAL 55-50-028-PIT Created On: 01/09/15 Updated On:	P	SE	25	39N	1W	Price		0-225-50-2015		0.0	1.7	15.5	16.6	2.724	2.751	0.993	
	Approved Use : CONCRETE, OGBC, Base Aggregate																
SMASAL 55-50-028-PIT Created On: 01/07/20 Updated On:	P	SE	25	39N	1W	Price		0-225-45-2020	0.1	0.0	1.8	3.4	16.6	2.733	2.759	0.923	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
SMASAL 55-50-028-PIT Created On: 01/02/25 Updated On:	P	SE	25	39N	1W	Price		0-225-6-2025	0.2	1.1	1.7	3.2	15.0	2.730	2.759	1.048	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
SMITH-PIT 55-21-021-PIT Created On: 02/28/24 Updated On:	P	SE	SW	7	34N	15E	Forest	0-225-195-2024	0.9	0.0	0.3	4.4	20.3	2.731	2.746	0.545	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
SOLON SPRINGS 55-16-024-QRY Created On: 05/09/16 Updated On:	Q	NE	NW	18	45N	11W	Douglas	0-225-167-2016		0.0	4.6	3.8	16.7	2.807	2.839	1.155	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
SOLON SPRINGS 55-16-024-QRY Created On: 01/07/19 Updated On:	Q	NE	NW	18	45N	11W	Douglas	0-225-60-2019	0.3	0.0	8.8	4.6	19.4	2.780	2.824	1.552	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
SOLON SPRINGS 55-16-024-QRY Created On: 07/07/22 Updated On:	Q	NE	NW	18	45N	11W	Douglas	0-225-245-2022	1.4	0.0	4.7	4.8	19.0	2.778	2.807	1.041	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
SOLON SPRINGS 55-16-024-QRY Created On: 01/02/25 Updated On:	Q	NE	NW	18	45N	11W	Douglas	0-225-37-2025	0.0	11.2	11.9	4.5	18.7	2.746	2.802	2.068	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
SPIILDE 55-13-085-PIT Created On: 08/11/15 Updated On:	P		N	17	6N	11E	Dane	0-225-227-2015		7.8	7.4	8.5	34.4	2.631	2.689	2.211	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
SPIILDE 55-13-085-PIT Created On: 01/04/21 Updated On:	P		N	17	6N	11E	Dane	0-225-2-2021	9.4	0.0	12.7	10.7	39.0	2.584	2.647	2.438	
	Approved Use : Base Aggregate																
SPRAGUE 55-42-037-PIT Created On: 01/06/16 Updated On:	P	SE	NE	16	30N	19E	Oconto	0-225-33-2016	1.2	0.0	7.4	8.1	31.2	2.687	2.722	1.305	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
Source Name	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
SPRAGUE 55-42-037-PIT Created On: 02/10/21 Updated On:	P	SE	NE	16	30N	19E	Oconto	0-225-126-2021	2.5	0.0	5.9	6.8	29.5	2.683	2.722	1.449		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
SPREAD EAGLE 55-19-009-QRY Created On: 01/12/16 Updated On:	Q	NW	SE	11	39N	19E	Florence	0-225-50-2016		0.0	0.3	2.9	12.4	2.895	2.903	0.294		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
SPREAD EAGLE 55-19-009-QRY Created On: 01/04/19 Updated On:	Q	NW	SE	11	39N	19E	Florence	0-225-11-2019		0.2	0.1	1.9	9.1	2.951	2.964	0.429		
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																	
SPREAD EAGLE 55-19-009-QRY Created On: 01/04/22 Updated On:	Q	NW	SE	11	39N	19E	Florence	0-225-24-2022	0.0	1.0	0.2	6.1	12.4	2.973	2.982	0.291		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
SPREAD EAGLE 55-19-009-QRY Created On: 01/02/25 Updated On:	Q	NW	SE	11	39N	19E	Florence	0-225-65-2025	0.0	0.0	0.4	2.3	9.9	2.955	2.965	0.361		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
SPRING VALLEY 55-47-026-QRY Created On: 01/05/17 Updated On:	Q	NE	NE	16	27N	15W	Pierce	0-225-44-2017		0.0	0.9	4.4	23.2	2.694	2.725	1.175		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
SPRING VALLEY 55-47-026-QRY Created On: 03/02/20 Updated On:	Q	NE	NE	16	27N	15W	Pierce	0-225-117-2020	0.1	0.0	0.2	6.3	28.5	2.653	2.698	1.693		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
SPRING VALLEY 55-47-026-QRY Created On: 01/10/23 Updated On:	Q	NE	NE	16	27N	15W	Pierce	0-225-104-2023	0.9	7.4	0.2	6.0	30.5	2.634	2.686	1.981	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
SPRINGWATER 55-69-019-PIT Created On: 05/13/21 Updated On:	P	NW	NW	6	20N	11E	Waushara	0-225-206-2021	0.2	2.9	1.3	4.7	21.2	2.700	2.730	1.097	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
ST NAZIANZ 55-36-043-PIT Created On: 01/05/17 Updated On:	P		S	30	18N	22E	Manitowoc	0-225-20-2017	0.5	1.6	2.0	7.8	33.3	2.750	2.778	1.033	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
ST NAZIANZ 55-36-043-PIT Created On: 04/28/22 Updated On:	P		S	30	18N	22E	Manitowoc	0-225-185-2022	1.1	0.0	1.3	7.2	33.0	2.761	2.788	0.983	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
STAG LAKE 55-43-033-PIT Created On: 06/13/18 Updated On:	P	NW	NW	34	36N	7E	Oneida	0-225-226-2018	0.2	0.0	1.9	5.5	24.1	2.682	2.703	0.790	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
STAG LAKE 55-43-033-PIT Created On: 01/19/23 Updated On:	P	NW	NW	34	36N	7E	Oneida	0-225-127-2023	0.4	0.0	2.7	5.3	23.5	2.665	2.695	1.134	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
STAUDENMAIER 55-38-032-QRY Created On: 03/31/17 Updated On:	Q	NW	SW	7	29N	22E	Marinette	0-225-97-2017	0.0	1.9	3.7	5.8	26.2	2.717	2.752	1.294	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
Source Name	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
STAUDENMAIER 55-38-032-QRY Created On: 06/13/22 Updated On:	Q	NW	SW	7	29N	22E	Marinette	0-225-220-2022	0.0	2.6	1.0	7.2	28.8	2.706	2.741	1.263		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
STAUDENMAIER 55-38-032-QRY Created On: 01/02/25 Updated On:	Q	NW	SW	7	29N	22E	Marinette	0-225-61-2025	0.0	2.9	1.5	6.0	26.0	2.728	2.758	1.081		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
STECK BAUER PIT 55-34-027-PIT Created On: 04/15/24 Updated On:	P	SW	NW	30	31N	15E	Langlade	0-225-229-2024	0.8	0.0	0.2	5.3	25.1	2.681	2.698	0.632		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
STEGER 55-20-057-PIT Created On: 03/24/21 Updated On:	P	SW	SW	24	13N	18E	Fond Du Lac	0-225-157-2021	0.1	0.0	3.0	6.4	29.3	2.767	2.790	0.822		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
STELTER 124 PIT 55-09-065-PIT Created On: 05/02/19 Updated On:	P	SW	SW	5	30N	8W	Chippewa	0-225-176-2019	0.0	0.0	2.2	4.5	20.0	2.740	2.765	0.920		
	Approved Use : HMA<MT, HMA>=MT, Base Aggregate																	
STELTER 124 PIT 55-09-065-PIT Created On: 09/19/24 Updated On:	P	SW	SW	5	30N	8W	Chippewa	0-225-309-2024	0.4	0.0	0.4	3.6	18.4	2.739	2.756	0.620		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
STELTER-MORNING WEST PIT 55-09-082-PIT Created On: 09/19/24 Updated On:	P	NE	NE	6	30N	8W	Chippewa	0-225-310-2024	0.0	0.0	1.2	4.0	19.5	2.754	2.773	0.720		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
STEVENSON 55-11-036-QRY Created On: 03/31/15 Updated On:	Q			8	10N	9E	Columbia	0-225-111-2015		1.2	2.2	13.0	45.0	2.524	2.602	3.118	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
STEVENSON 55-11-036-QRY Created On: 01/03/18 Updated On:	Q			8	10N	9E	Columbia	0-225-6-2018	2.5	0.7	3.9	10.4	36.7	2.529	2.615	3.422	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
STEVENSON 55-11-036-QRY Created On: 01/04/21 Updated On:	Q			8	10N	9E	Columbia	0-225-40-2021	2.3	1.2	0.6	8.9	33.9	2.548	2.620	2.799	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
STEVENSON 55-11-036-QRY Created On: 01/02/24 Updated On:	Q			8	10N	9E	Columbia	0-225-18-2024	4.9	5.1	3.1	15.9	45.9	2.512	2.604	3.663	
	Approved Use : CONCRETE, OGBC, Base Aggregate																
STOCKPILE 55-99-042-QRY Created On: 04/22/24 Updated On:	Q							0-225-236-2024		0.0	0.8	5.2	20.5	2.679	2.705	0.973	
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																
STOUGHTON 55-13-001-PIT Created On: 01/04/19 Updated On:	P	E	NW	10	5N	11E	Dane	0-225-10-2019	2.0	9.3	0.9	6.4	30.8	2.664	2.710	1.718	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
STOUGHTON 55-13-001-PIT Created On: 01/02/25 Updated On:	P	E	NW	10	5N	11E	Dane	0-225-2-2025	2.4	6.5	3.2	6.0	27.3	2.673	2.714	1.510	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
* STRAND 55-06-023-QRY Created On: 10/07/20 Updated On:	Q		NE	28	23N	13W	Buffalo	0-225-244-2020	0.3	0.0	12.5	10.3	41.8	2.563	2.655	3.608	
	Approved Use : Base Aggregate																
STRAUB 55-20-006-PIT Created On: 01/04/19 Updated On:	P		W	23	14N	18E	Fond Du Lac	0-225-18-2019		4.9	0.8	7.1	30.0	2.758	2.785	0.984	
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																
STRAUB 55-20-006-PIT Created On: 01/02/24 Updated On:	P		W	23	14N	18E	Fond Du Lac	0-225-100-2024	0.8	2.9	0.2	6.1	26.3	2.772	2.795	0.806	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
* STROETZ 55-37-075-QRY Created On: 03/21/18 Updated On:	Q	SW	NW	10	26N	3E	Marathon	0-225-131-2018		0.0	2.9	6.2	28.0	2.593	2.616	0.874	
	Approved Use : HMA<MT, HMA>=MT, Base Aggregate																
* STROETZ 55-37-075-QRY Created On: 06/28/22 Updated On:	Q	SW	NW	10	26N	3E	Marathon	0-225-241-2022		0.0	1.7	7.6	29.3	2.592	2.620	1.073	
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																
STUCZYNSKI (DUFFEK) 55-49-024-PIT Created On: 07/26/21 Updated On:	P		NE	NW	4	23N	9E	Portage	0-225-250-2021	0.6	0.0	0.6	9.4	34.9	2.603	2.637	1.303
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
STUPAK 55-16-025-QRY Created On: 05/08/15 Updated On:	Q	NW	NW	29	47N	14W	Douglas	0-225-154-2015		0.0	3.2	2.9	15.0	2.791	2.810	0.680	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
Source Name	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
STUPAK 55-16-025-QRY Created On: 01/03/18 Updated On:	Q	NW	NW	29	47N	14W	Douglas	0-225-17-2018		0.0	9.1	3.5	15.5	2.686	2.719	1.235		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
STUPAK 55-16-025-QRY Created On: 01/05/21 Updated On:	Q	NW	NW	29	47N	14W	Douglas	0-225-68-2021	0.0	16.5	10.9	3.5	15.2	2.715	2.749	1.259		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
STUPAK 55-16-025-QRY Created On: 01/02/24 Updated On:	Q	NW	NW	29	47N	14W	Douglas	0-225-92-2024	0.0	0.0	10.6	3.6	17.2	2.633	2.684	1.930		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
STURGEON BAY - MM 55-15-022-QRY Created On: 01/05/17 Updated On:	Q	SE	NW	21	27N	25E	Door	0-225-21-2017		0.0	1.9	7.8	27.6	2.769	2.789	0.736		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
STURGEON BAY - MM 55-15-022-QRY Created On: 01/02/20 Updated On:	Q	SE	NW	21	27N	25E	Door	0-225-7-2020	0.0	0.0	0.5	5.4	25.4	2.779	2.796	0.611		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
STURGEON BAY - MM 55-15-022-QRY Created On: 01/03/23 Updated On:	Q	SE	NW	21	27N	25E	Door	0-225-46-2023		7.2	1.8	5.7	24.0	2.773	2.792	0.688		
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																	
* SUGAR BUSH 55-65-020-PIT Created On: 06/18/20 Updated On:	P		NW	23	37N	10W	Washburn	0-225-198-2020	2.0	0.0	2.1	4.6	20.7	2.753	2.778	0.915		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Coarse Sp. Gravity		Coarse Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
SUPER AGGREGATE - BURGETT LAKES 17-00-007-PIT Created On: 02/16/16 Updated On:	P		SE	1	46N	7E	Mchenry	0-225-88-2016	1.6	3.2	1.7	6.9	34.8	2.677	2.718	1.525	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
SUPER AGGREGATE - BURGETT LAKES 17-00-007-PIT Created On: 01/04/21 Updated On:	P		SE	1	46N	7E	Mchenry	0-225-9-2021	0.7	4.7	0.3	4.5	23.4	2.676	2.708	1.199	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
SUPER AGGREGATE / WATERFORD 55-51-028-PIT Created On: 02/11/19 Updated On:	P	SW	SE	28	4N	19E	Racine	0-225-102-2019	3.1	0.0	7.8	4.6	23.0	2.646	2.692	1.748	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
SUPER AGGREGATE / WATERFORD 55-51-028-PIT Created On: 04/15/24 Updated On:	P	SW	SE	28	4N	19E	Racine	0-225-221-2024	3.9	8.5	1.6	4.3	24.3	2.298	2.335	1.631	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
SUPER AGGREGATE-SUGAR CREEK 55-64-037-PIT Created On: 02/11/19 Updated On:	P	SE	NW	9	3N	16E	Walworth	0-225-106-2019	3.0	0.0	7.0	3.9	24.2	2.651	2.692	1.527	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
SUPER AGGREGATE-SUGAR CREEK 55-64-037-PIT Created On: 04/15/24 Updated On:	P	SE	NW	9	3N	16E	Walworth	0-225-222-2024	2.1	9.3	1.0	4.6	25.2	2.670	2.706	1.367	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
SVEC 55-47-027-QRY Created On: 03/24/16 Updated On:	Q	E	NW	17	26N	18W	Pierce	0-225-115-2016		0.0	7.8	9.9	34.2	2.609	2.674	2.499	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
SVEC 55-47-027-QRY Created On: 01/07/19 Updated On:	Q	E	NW	17	26N	18W	Pierce	0-225-63-2019	0.5	0.0	5.8	9.2	33.8	2.611	2.675	2.469	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
SVEC 55-47-027-QRY Created On: 01/04/22 Updated On:	Q	E	NW	17	26N	18W	Pierce	0-225-77-2022	5.5	16.0	16.4	15.0	45.0	2.551	2.630	3.087	
	Approved Use : Base Aggregate																
SVEC 55-47-027-PIT Created On: 03/15/22 Updated On:	P	E	NW	17	26N	18W	Pierce	0-225-142-2022	2.4	8.7	11.1	10.7	37.6	2.633	2.691	2.177	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
SVEC 55-47-027-QRY Created On: 05/21/24 Updated On:	Q	E	NW	17	26N	18W	Pierce	0-225-261-2024	5.5	16.1	11.1	12.4	41.7	2.568	2.644	2.945	
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																
SWAGEL 55-31-017-PIT Created On: 11/03/17 Updated On:	P		N	29	23N	24E	Kewaunee	0-225-285-2017	1.5	0.0	5.6	7.9	32.9	2.710	2.748	1.420	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
SWAGEL 55-31-017-PIT Created On: 03/07/22 Updated On:	P		N	29	23N	24E	Kewaunee	0-225-140-2022	3.1	0.0	4.2	6.2	30.8	2.693	2.730	1.368	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
SWANSON 55-48-026-PIT Created On: 01/09/15 Updated On:	P	S	SW	30	34N	16W	Polk	0-225-43-2015		0.0	4.0	4.8	19.1	2.758	2.789	1.130	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
Source Name	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
SWANSON 55-48-026-PIT Created On: 04/15/25 Updated On:	P	S	SW	30	34N	16W	Polk	0-225-189-2025	1.6	2.4	3.2	5.1	19.5	2.731	2.770	1.424		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
SWIGGUM 55-25-025-QRY Created On: 04/16/15 Updated On:	Q	NE	NE	30	6N	3E	Iowa	0-225-120-2015	0.5	2.1	3.3	12.6	44.3	2.494	2.587	3.719		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
SWIGGUM 55-12-022-QRY Created On: 07/17/15 Updated On:	Q	SW	NW	29	11N	3W	Crawford	0-225-213-2015		1.1	1.4	9.1	35.6	2.640	2.687	1.764		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
SWIGGUM 55-12-022-QRY Created On: 05/19/16 Updated On:	Q	SW	NW	29	11N	3W	Crawford	0-225-183-2016		1.4	3.9	8.9	34.4	2.661	2.705	1.650		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
SWIGGUM 55-25-025-QRY Created On: 03/23/18 Updated On:	Q	NE	NE	30	6N	3E	Iowa	0-225-144-2018	1.8	1.3	0.5	9.8	37.3	2.506	2.596	3.617		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
SWIGGUM 55-12-022-QRY Created On: 01/07/19 Updated On:	Q	SW	NW	29	11N	3W	Crawford	0-225-55-2019	1.0	2.0	3.5	10.1	36.8	2.602	2.662	2.325		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
SWIGGUM 55-25-025-QRY Created On: 03/17/21 Updated On:	Q	NE	NE	30	6N	3E	Iowa	0-225-146-2021	0.8	1.6	0.9	9.9	38.7	2.491	2.591	4.004		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
SWIGGUM 55-12-022-QRY Created On: 02/16/22 Updated On:	Q	SW	NW	29	11N	3W	Crawford	0-225-123-2022	0.4	5.6	0.3	9.0	35.8	2.642	2.697	2.073	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
SWIGGUM 55-25-025-QRY Created On: 01/02/24 Updated On:	Q	NE	NE	30	6N	3E	Iowa	0-225-2-2024	0.1	1.3	1.5	8.5	36.0	2.537	2.619	3.207	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
SWIGGUM 55-12-022-QRY Created On: 01/02/25 Updated On:	Q	SW	NW	29	11N	3W	Crawford	0-225-29-2025	0.4	3.1	1.8	10.6	36.4	2.625	2.685	2.283	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
SZEWS 55-37-077-PIT Created On: 09/15/16 Updated On:	P	SW	SW	4	28N	10E	Marathon	0-225-257-2016		0.0	0.4	8.2	32.3	2.669	2.689	0.741	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
SZEWS 55-37-077-PIT Created On: 01/04/21 Updated On:	P	SW	SW	4	28N	10E	Marathon	0-225-17-2021	0.0	0.4	0.4	6.9	30.9	2.669	2.691	0.807	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
TAGGE 55-15-023-PIT Created On: 01/05/17 Updated On:	P		NE	31	27N	26E	Door	0-225-22-2017	0.3	0.0	0.3	7.2	30.2	2.726	2.763	1.373	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
TAGGE 55-15-023-PIT Created On: 01/04/22 Updated On:	P		NE	31	27N	26E	Door	0-225-15-2022	0.1	2.2	1.8	6.4	27.5	2.733	2.764	1.151	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
TAMMEC PIT 55-55-016-PIT Created On: 01/05/17 Updated On:	P		SW	16	30N	18W	St. Croix	0-225-45-2017		0.0	3.0	3.6	19.1	2.702	2.735	1.207	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
TAMMEC PIT 55-55-016-PIT Created On: 01/04/22 Updated On:	P		SW	16	30N	18W	St. Croix	0-225-78-2022	3.0	4.1	5.0	4.5	20.3	2.678	2.716	1.393	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
TAMMEC QUARRY 55-55-017-QRY Created On: 01/08/15 Updated On:	Q		SW	16	30N	18W	St. Croix	0-225-39-2015	4.9	0.0	10.3	12.2	41.8	2.497	2.579	3.319	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
TAMMEC QUARRY 55-55-017-QRY Created On: 04/21/17 Updated On:	Q		SW	16	30N	18W	St. Croix	0-225-144-2017	2.8	0.0	6.7	9.2	35.1	2.562	2.626	2.475	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
TAMMEC QUARRY 55-55-017-QRY Created On: 05/04/20 Updated On:	Q		SW	16	30N	18W	St. Croix	0-225-165-2020	2.6	0.0	7.1	9.5	37.0	2.572	2.644	2.800	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
TAMMEC QUARRY 55-55-017-QRY Created On: 01/03/23 Updated On:	Q		SW	16	30N	18W	St. Croix	0-225-53-2023	9.1	14.4	4.2	12.0	43.2	2.481	2.564	3.359	
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																
TAYLOR #1 55-43-028-PIT Created On: 06/13/18 Updated On:	P	NW	NW	16	36N	9E	Oneida	0-225-227-2018	0.2	0.0	0.9	5.1	23.4	2.637	2.655	0.647	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
Source Name	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
TAYLOR #1 55-43-028-PIT Created On: 04/24/23 Updated On:	P	NW	NW	16	36N	9E	Oneida	0-225-206-2023	0.0	0.0	0.8	5.7	25.0	2.742	2.763	0.751		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
TENNYSON 55-22-052-QRY Created On: 04/06/17 Updated On:	Q	NW	NE	36	3N	3W	Grant	0-225-116-2017	2.6	7.7	3.2	11.3	35.1	2.562	2.636	2.888		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
TENNYSON 55-22-052-QRY Created On: 07/28/17 Updated On:	Q	NW	NE	36	3N	3W	Grant	0-225-241-2017	0.3	3.3	1.1	7.5	31.0	2.624	2.678	2.073		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
TENNYSON 55-22-052-QRY Created On: 04/28/20 Updated On:	Q	NW	NE	36	3N	3W	Grant	0-225-160-2020	0.0	3.7	2.2	8.8	33.6	2.642	2.693	1.941		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
TENNYSON 55-22-052-QRY Created On: 01/03/23 Updated On:	Q	NW	NE	36	3N	3W	Grant	0-225-9-2023	0.3	7.0	10.6	10.1	36.8	2.543	2.627	3.277		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
THACKRAY 55-20-048-PIT Created On: 04/10/19 Updated On:	P			13	15N	19E	Fond Du Lac	0-225-129-2019	0.3	0.0	0.9	7.6	33.6	2.748	2.775	0.967		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
THACKRAY 55-20-048-PIT Created On: 01/02/24 Updated On:	P			13	15N	19E	Fond Du Lac	0-225-53-2024	1.1	0.0	1.1	6.0	28.0	2.766	2.787	0.752		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
* THACKRAY SOUTH 55-20-053-PIT Created On: 05/15/20 Updated On:	P	SE	NW	13	15N	19E	Fond Du Lac	0-225-179-2020	0.0	0.0	2.3	7.8	36.0	2.725	2.760	1.289		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
THELEN-ANTIOCH 17-00-002-PIT Created On: 05/09/18 Updated On:	P			9	46N	9E	Lake	0-225-196-2018	0.2	11.9	0.9	5.7	26.1	2.695	2.733	1.439		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
THELEN-ANTIOCH 17-00-002-PIT Created On: 01/03/23 Updated On:	P			9	46N	9E	Lake	0-225-51-2023	1.0	16.2	6.6	4.5	25.1	2.662	2.701	1.465		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
THELEN-LANGE ROAD 55-64-025-PIT Created On: 06/25/15 Updated On:	P	SE	SE	32	1N	18E	Walworth	0-225-202-2015	1.0	0.0	1.1	5.7	33.5	2.674	2.713	1.439		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
THELEN-LANGE ROAD 55-64-025-PIT Created On: 05/09/18 Updated On:	P	SE	SE	32	1N	18E	Walworth	0-225-197-2018	0.3	10.4	0.9	5.5	25.8	2.699	2.737	1.421		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
THELEN-LANGE ROAD 55-64-025-PIT Created On: 01/03/23 Updated On:	P	SE	SE	32	1N	18E	Walworth	0-225-49-2023	0.7	14.4	6.6	5.9	28.4	2.671	2.704	1.241		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
THIEL 55-68-028-PIT Created On: 06/21/16 Updated On:	P	NE	NW	5	22N	13E	Waupaca	0-225-209-2016		0.0	1.1	5.7	27.5	2.691	2.712	0.794		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
THIEL 55-68-028-PIT Created On: 01/04/21 Updated On:	P	NE	NW	5	22N	13E	Waupaca	0-225-21-2021	0.6	3.1	2.0	5.5	26.6	2.703	2.727	0.913	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
THOMAS COBB 55-25-026-QRY Created On: 02/09/18 Updated On:	Q	NE	NE	30	6N	2E	Iowa	0-225-97-2018	2.1	3.9	8.9	10.5	42.6	2.504	2.601	3.891	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
THOMAS COBB 55-25-026-QRY Created On: 03/17/21 Updated On:	Q	NE	NE	30	6N	2E	Iowa	0-225-139-2021	2.6	11.0	9.5	12.7	43.9	2.534	2.625	3.573	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
THOMAS COBB 55-25-026-QRY Created On: 02/28/24 Updated On:	Q	NE	NE	30	6N	2E	Iowa	0-225-181-2024	2.3	12.5	12.4	9.2	38.7	2.526	2.613	3.425	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
THOMAS\RIDGE 55-25-029-QRY Created On: 04/07/16 Updated On:	Q	NW	NE	33	6N	4E	Iowa	0-225-129-2016	5.6	7.4	5.3	12.3	43.2	2.560	2.633	2.859	
	Approved Use : HMA<E-3, HMA>=E-3, Base Aggregate																
THOMAS\RIDGE 55-25-029-QRY Created On: 02/11/19 Updated On:	Q	NW	NE	33	6N	4E	Iowa	0-225-104-2019	1.8	3.0	5.5	10.6	39.8	2.544	2.631	3.408	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
THOMAS\RIDGE 55-25-029-QRY Created On: 03/17/21 Updated On:	Q	NW	NE	33	6N	4E	Iowa	0-225-141-2021	1.5	5.3	2.9	9.2	38.2	2.613	2.676	2.415	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
THOMAS\RIDGE 55-25-029-QRY Created On: 02/28/24 Updated On:	Q	NW	NE	33	6N	4E	Iowa	0-225-183-2024	2.0	5.4	10.5	9.2	37.6	2.542	2.626	3.275	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
THOMPSON 55-57-027-PIT Created On: 01/02/25 Updated On:	P	NW	SW	12	41N	8W	Sawyer	0-225-40-2025	0.2	1.5	1.6	3.7	17.6	2.736	2.763	0.992	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
* THOMSON LIMESTONE 55-42-038-QRY Created On: 01/04/22 Updated On:	Q	SE	SE	20	30N	19E	Oconto	0-225-14-2022	1.4	6.9	6.5	6.0	33.8	2.696	2.736	1.489	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
* THONI 55-25-030-QRY Created On: 03/23/18 Updated On:	Q	SW	SE	3	6N	5E	Iowa	0-225-139-2018	2.7	3.9	1.3	10.9	41.2	2.549	2.632	3.232	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
* THONI 55-25-030-QRY Created On: 03/17/21 Updated On:	Q	SW	SE	3	6N	5E	Iowa	0-225-147-2021	1.9	2.5	0.6	14.9	46.7	2.562	2.632	2.712	
	Approved Use : CONCRETE, OGBC, Base Aggregate																
* THONI 55-25-030-QRY Created On: 05/21/24 Updated On:	Q	SW	SE	3	6N	5E	Iowa	0-225-263-2024	0.2	19.4	9.9	9.9	37.7	2.581	2.656	2.919	
* THONI 55-25-030-QRY Created On: 06/25/24 Updated On:	Q	SW	SE	3	6N	5E	Iowa	0-225-273-2024	0.1	19.3	1.1	14.8	47.4	2.537	2.624	3.428	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
* THONI 55-25-030-QRY Created On: 08/14/24 Updated On:	Q	SW	SE	3	6N	5E	Iowa	0-225-302-2024	0.0	14.1	2.5	14.3	47.5	2.573	2.651	3.026	
	Approved Use : CONCRETE, OGBC, Base Aggregate																
THUNDER HILL AGGREGATE 55-16-026-QRY Created On: 02/09/18 Updated On:	Q		NE	13	47N	14W	Douglas	0-225-98-2018	0.0	0.0	0.4	3.3	11.3	2.837	2.872	1.222	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
THUNDER HILL AGGREGATE 55-16-026-QRY Created On: 05/20/24 Updated On:	Q		NE	13	47N	14W	Douglas	0-225-260-2024	0.0	0.0	5.2	3.3	16.2	2.813	2.835	0.771	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
THURS 55-37-090-QRY Created On: 04/05/19 Updated On:	Q	NE	SW	27	29N	5E	Marathon	0-225-124-2019		0.0	1.4	4.2	18.4	2.715	2.736	0.766	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
THURS 55-37-090-QRY Created On: 04/11/22 Updated On:	Q	NE	SW	27	29N	5E	Marathon	0-225-172-2022	0.0	0.0	0.6	3.2	14.1	2.769	2.780	0.397	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
THURS 55-37-090-QRY Created On: 01/02/25 Updated On:	Q	NE	SW	27	29N	5E	Marathon	0-225-74-2025		0.0	0.3	3.4	15.7	2.797	2.807	0.347	
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																
TIMBERLANE S & G 55-28-015-PIT Created On: 01/04/22 Updated On:	P	NW	SW	19	6N	14E	Jefferson	0-225-88-2022	0.6	6.2	1.8	4.8	25.5	2.677	2.710	1.234	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
TIMM 55-44-029-QRY Created On: 03/17/22 Updated On:	Q	NE	NE	25	22N	16E	Outagamie	0-225-150-2022	0.0	9.0	1.1	5.2	23.6	2.746	2.776	1.083	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
TIMM 55-44-029-QRY Created On: 01/14/25 Updated On:	Q	NE	NE	25	22N	16E	Outagamie	0-225-100-2025		5.7	3.0	5.6	24.2	2.731	2.762	1.146	
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																
TINCHERS QUARRY 55-58-038-QRY Created On: 06/25/24 Updated On:	Q	NE	NE	11	26N	16E	Shawano	0-225-278-2024	0.1	3.0	3.1	7.7	33.6	2.690	2.730	1.481	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
TNT 55-13-094-QRY Created On: 01/30/15 Updated On:	Q		SW	14	6N	12E	Dane	0-225-80-2015		15.5	9.5	8.1	34.5	2.603	2.679	2.917	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
TNT 55-13-094-QRY Created On: 03/22/17 Updated On:	Q		SW	14	6N	12E	Dane	0-225-87-2017	1.6	31.6	19.1	10.5	38.3	2.557	2.644	3.416	
TNT 55-13-094-QRY Created On: 04/12/17 Updated On:	Q		SW	14	6N	12E	Dane	0-225-122-2017		13.2	8.8	8.0	34.9	2.616	2.687	2.679	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
TNT 55-13-094-QRY Created On: 04/12/17 Updated On:	Q		SW	14	6N	12E	Dane	0-225-124-2017	0.5	12.1	6.9	6.5	29.1	2.630	2.692	2.387	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
TNT 55-13-094-QRY Created On: 04/12/17 Updated On:	Q		SW	14	6N	12E	Dane	0-225-125-2017	0.3	10.1	9.5	6.1	28.3	2.630	2.691	2.312	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
TNT 55-13-094-QRY Created On: 02/12/20 Updated On:	Q		SW	14	6N	12E	Dane	0-225-110-2020	0.4	29.8	15.7	7.3	32.8	2.619	2.683	2.461	
TNT 55-13-094-QRY Created On: 04/01/20 Updated On:	Q		SW	14	6N	12E	Dane	0-225-136-2020	0.2	22.0	12.7	6.7	30.8				
TNT 55-13-094-QRY Created On: 08/10/20 Updated On:	Q		SW	14	6N	12E	Dane	0-225-231-2020		17.6	6.7	5.3	26.8	2.662	2.713	1.888	
TNT 55-13-094-QRY Created On: 04/26/21 Updated On:	Q		SW	14	6N	12E	Dane	0-225-189-2021	0.1	16.8	5.8	5.7	27.6	2.622	2.684	2.377	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
TNT 55-13-094-QRY Created On: 01/04/22 Updated On:	Q		SW	14	6N	12E	Dane	0-225-79-2022	0.2	14.2	10.4	5.9	29.5	2.651	2.706	2.058	
	Approved Use : Base Aggregate																
TNT 55-13-094-QRY Created On: 01/14/25 Updated On:	Q		SW	14	6N	12E	Dane	0-225-94-2025	0.2	15.8	2.8	6.6	29.4	2.622	2.686	2.426	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
* TORDEUR 55-05-024-QRY Created On: 01/05/15 Updated On:	Q			18	24N	22E	Brown	0-225-1-2015	0.3	1.3	2.3	5.8	27.2	2.729	2.764	1.285	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
* TORDEUR 55-05-024-QRY Created On: 01/04/18 Updated On:	Q			18	24N	22E	Brown	0-225-52-2018		2.6	2.8	7.2	33.5	2.708	2.748	1.490	
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																
* TORDEUR 55-05-024-QRY Created On: 01/04/21 Updated On:	Q			18	24N	22E	Brown	0-225-8-2021	0.3	0.9	1.5	5.2	24.6	2.703	2.742	1.446	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
TORGERSON 55-32-016-QRY Created On: 03/24/16 Updated On:	Q	SE	SW	31	15N	5W	La Crosse	0-225-113-2016		0.0	3.2	11.1	39.3	2.539	2.612	2.901	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
TORGERSON 55-32-016-QRY Created On: 07/23/25 Updated On:	Q	SE	SW	31	15N	5W	La Crosse	0-225-231-2025	3.1	0.0	9.7	13.2	45.3	2.538	2.614	3.020	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
TORK 55-71-029-QRY Created On: 01/03/17 Updated On:	Q	NE	SW	1	22N	5E	Wood	0-225-2-2017		0.0	0.1	5.8	25.1	2.668	2.682	0.538	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
TORK 55-71-029-QRY Created On: 01/02/20 Updated On:	Q	NE	SW	1	22N	5E	Wood	0-225-1-2020	0.2	0.0	1.6	6.6	27.4	2.664	2.679	0.584	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
TORK 55-71-029-QRY Created On: 01/03/23 Updated On:	Q	NE	SW	1	22N	5E	Wood	0-225-33-2023	0.0	1.0	1.7	6.6	27.6	2.624	2.640	0.608	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
TOWER 55-38-036-PIT Created On: 01/12/16 Updated On:	P	W	NE	34	31N	20E	Marinette	0-225-53-2016		0.0	1.3	4.6	24.4	2.712	2.741	1.081	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
TOWER 55-38-036-PIT Created On: 01/06/21 Updated On:	P	W	NE	34	31N	20E	Marinette	0-225-109-2021	0.3	3.5	1.8	4.6	23.0	2.706	2.737	1.142	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
TOWNLINE 55-53-038-PIT Created On: 04/12/16 Updated On:	P	NE	NE	1	1N	12E	Rock	0-225-142-2016	0.7	3.5	3.1	5.3	24.9	2.646	2.688	1.575	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
TOWNLINE 55-53-038-PIT Created On: 02/06/18 Updated On:	P	NE	NE	1	1N	12E	Rock	0-225-89-2018	2.8	0.0	3.4	5.9	26.5	2.639	2.682	1.629	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
TOWNLINE 55-53-038-PIT Created On: 01/07/19 Updated On:	P	NE	NE	1	1N	12E	Rock	0-225-66-2019	3.1	0.0	3.4	4.5	24.8	2.646	2.689	1.614	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
TOWNLINE 55-53-038-PIT Created On: 03/13/24 Updated On:	P	NE	NE	1	1N	12E	Rock	0-225-198-2024	0.7	8.8	3.0	5.0	24.3	2.689	2.727	1.429	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
TOWNSEND 55-42-039-PIT Created On: 01/05/21 Updated On:	P	SE	SW	15	33N	15E	Oconto	0-225-104-2021	0.0	0.2	0.4	3.9	18.8	2.682	2.697	0.581	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
TRIEMSTRA 55-11-037-QRY Created On: 03/23/16 Updated On:	Q	NE	SW	11	13N	10E	Columbia	0-225-104-2016		0.9	0.5	10.5	39.6	2.599	2.656	2.187	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
TRIEMSTRA 55-11-037-QRY Created On: 04/01/19 Updated On:	Q	NE	SW	11	13N	10E	Columbia	0-225-122-2019	2.6	1.8	1.1	10.4	37.7	2.642	2.689	1.765	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
TRIEMSTRA 55-11-037-QRY Created On: 04/05/22 Updated On:	Q	NE	SW	11	13N	10E	Columbia	0-225-162-2022	4.1	1.5	1.5	10.7	39.1	2.618	2.673	2.086	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
TRIEMSTRA 55-11-037-QRY Created On: 04/15/25 Updated On:	Q	NE	SW	11	13N	10E	Columbia	0-225-186-2025	1.6	0.9	1.3	10.0	37.8	2.618	2.670	1.982	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
TRIMBELLE 55-47-029-QRY Created On: 09/24/20 Updated On:	Q		SW	21	26N	18W	Pierce	0-225-242-2020	3.8	0.0	11.3	12.4	44.8	2.574	2.643	2.668	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
TRIMBELLE 55-47-029-QRY Created On: 10/14/24 Updated On:	Q		SW	21	26N	18W	Pierce	0-225-313-2024	0.4	0.0	5.6	8.6	37.1	2.661	2.707	1.719	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
TUBBS 55-65-017-PIT Created On: 06/09/20 Updated On:	P	NE	SE	18	41N	12W	Washburn	0-225-189-2020	1.7	0.0	2.3	4.0	18.7	2.735	2.771	1.325	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
TUBBS 55-65-017-PIT Created On: 01/16/25 Updated On:	P	NE	SE	18	41N	12W	Washburn	0-225-131-2025	2.9	7.1	7.1	3.9	18.5	2.654	2.711	2.126	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
TWESME 55-61-020-QRY Created On: 01/30/15 Updated On:	Q	SW	SE	34	21N	8W	Trempealeau	0-225-83-2015		0.0	7.1	12.1	41.4	2.590	2.651	2.378	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
TWESME 55-61-020-QRY Created On: 01/04/18 Updated On:	Q	SW	SE	34	21N	8W	Trempealeau	0-225-45-2018	1.4	0.0	6.0	13.1	42.2	2.578	2.646	2.646	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
TWESME 55-61-020-QRY Created On: 01/04/21 Updated On:	Q	SW	SE	34	21N	8W	Trempealeau	0-225-35-2021	1.2	0.0	2.7	10.4	38.7	2.586	2.650	2.496	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
TWESME 55-61-020-QRY Created On: 01/02/24 Updated On:	Q	SW	SE	34	21N	8W	Trempealeau	0-225-120-2024	0.7	6.4	8.8	11.6	40.6	2.584	2.652	2.624	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
UNION 55-15-024-PIT Created On: 07/08/15 Updated On:	P	SW	NW	36	26N	23E	Door	0-225-209-2015	0.1	0.0	7.1	6.0	25.2	2.710	2.748	1.378	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
UNION 55-15-024-PIT Created On: 06/13/22 Updated On:	P	SW	NW	36	26N	23E	Door	0-225-221-2022	0.2	8.9	2.1	5.5	26.8	2.704	2.741	1.368	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
UTECHT 55-55-018-PIT Created On: 01/12/15 Updated On:	P	NE	NE	21	30N	18W	St. Croix	0-225-62-2015		0.0	4.1	5.5	22.4	2.644	2.683	1.496	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
UTECHT 55-55-018-PIT Created On: 01/30/20 Updated On:	P	NE	NE	21	30N	18W	St. Croix	0-225-102-2020	1.1	0.0	5.5	6.0	24.8	2.634	2.678	1.662	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
UTECHT 55-55-018-PIT Created On: 02/20/25 Updated On:	P	NE	NE	21	30N	18W	St. Croix	0-225-153-2025	2.7	0.0	4.8	6.8	26.8	2.631	2.673	1.591	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
UTLEY 55-24-019-QRY Created On: 01/04/16 Updated On:	Q	SE	NW	36	15N	13E	Green Lake	0-225-12-2016		0.2	0.1	4.5	18.8	2.632	2.639	0.240	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
UTLEY 55-24-019-QRY Created On: 06/13/19 Updated On:	Q	SE	NW	36	15N	13E	Green Lake	0-225-221-2019	0.0	0.3	0.5	4.9	20.1	2.620	2.632	0.455	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
UTLEY 55-24-019-QRY Created On: 01/04/22 Updated On:	Q	SE	NW	36	15N	13E	Green Lake	0-225-38-2022	0.0	0.4	0.3	4.9	19.9	2.621	2.631	0.372	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Coarse Sp. Gravity		Coarse Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
UTLEY 55-24-019-QRY Created On: 01/29/24 Updated On:	Q	SE	NW	36	15N	13E	Green Lake	0-225-156-2024	0.0	1.1	0.9	4.9	20.6	2.620	2.630	0.363	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
V.M.I. 55-38-039-PIT Created On: 08/14/17 Updated On:	P	NE	SW	17	31N	21E	Marinette	0-225-250-2017	0.8	6.4	3.9	5.5	25.8	2.730	2.763	1.216	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
V.M.I. 55-38-039-PIT Created On: 04/28/22 Updated On:	P	NE	SW	17	31N	21E	Marinette	0-225-181-2022	0.5	0.0	2.8	5.5	26.9	2.716	2.745	1.046	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
VALDERS 55-36-026-QRY Created On: 01/05/17 Updated On:	Q	SE	NE	32	19N	22E	Manitowoc	0-225-19-2017		0.0	0.8	9.4	39.7	2.730	2.755	0.932	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
VALDERS 55-36-026-QRY Created On: 03/09/20 Updated On:	Q	SE	NE	32	19N	22E	Manitowoc	0-225-122-2020	0.2	0.2	1.9	7.9	36.2	2.745	2.768	0.810	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
VALDERS 55-36-026-QRY Created On: 02/09/23 Updated On:	Q	SE	NE	32	19N	22E	Manitowoc	0-225-142-2023	0.0	0.0	1.5	7.9	35.3	2.740	2.762	0.806	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
* VAN ALLEN 55-53-040-QRY Created On: 03/30/15 Updated On:	Q	SE	SE	15	2N	13E	Rock	0-225-109-2015	3.8	4.1	15.4	12.1	44.3	2.533	2.623	3.539	
	Approved Use : Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
* VAN ALLEN 55-53-040-QRY Created On: 06/02/17 Updated On:	Q	SE	SE	15	2N	13E	Rock	0-225-202-2017	0.2	1.4	8.7	9.3	38.7	2.601	2.669	2.632		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
* VAN ALLEN 55-53-040-QRY Created On: 03/09/20 Updated On:	Q	SE	SE	15	2N	13E	Rock	0-225-126-2020	0.1	2.2	8.2	8.9	36.4	2.576	2.653	3.012		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
VERMILLION 55-03-039-PIT Created On: 01/09/20 Updated On:	P	NW	SW	14	35N	13W	Barron	0-225-88-2020	4.2	0.0	2.6	4.0	19.5	2.711	2.735	0.881		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
VERMILLION 55-03-039-PIT Created On: 01/16/25 Updated On:	P	NW	SW	14	35N	13W	Barron	0-225-136-2025	1.9	0.0	3.4	5.4	20.2	2.681	2.714	1.263		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
VEUM 55-09-068-PIT Created On: 01/08/19 Updated On:	P	NE	NW	35	28N	10W	Chippewa	0-225-82-2019	4.2	0.0	6.7	7.1	26.8	2.593	2.631	1.450		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
VEUM 55-09-068-PIT Created On: 01/02/24 Updated On:	P	NE	NW	35	28N	10W	Chippewa	0-225-79-2024	3.2	0.0	4.6	5.4	22.7	2.677	2.707	1.123		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
* VICTORY 55-62-034-QRY Created On: 08/22/22 Updated On:	Q	NE	NE	34	12N	7W	Vernon	0-225-254-2022	1.2	10.4	7.0	14.5	48.1	2.578	2.646	2.654		
	Approved Use : CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
VIENNA 55-13-099-QRY Created On: 01/05/15 Updated On:	Q	NE	SW	34	9N	9E	Dane	0-225-7-2015	0.7	0.7	2.0	6.8	30.1	2.610	2.670	2.310	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
VIENNA 55-13-099-QRY Created On: 01/03/18 Updated On:	Q	NE	SW	34	9N	9E	Dane	0-225-21-2018	2.1	1.0	3.4	8.3	35.4	2.539	2.619	3.158	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
VIENNA 55-13-099-QRY Created On: 09/17/20 Updated On:	Q	NE	SW	34	9N	9E	Dane	0-225-241-2020	2.0	2.4	3.7	7.8	31.3	2.614	2.667	2.024	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
VIENNA 55-13-099-QRY Created On: 01/03/23 Updated On:	Q	NE	SW	34	9N	9E	Dane	0-225-3-2023	0.6	2.4	8.8	7.2	32.8	2.607	2.662	2.099	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
VINLAND 55-70-032-QRY Created On: 01/02/24 Updated On:	Q	E	NW	21	19N	16E	Winnebago	0-225-99-2024	0.0	2.9	0.5	5.0	22.1	2.785	2.806	0.751	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
VINTON ROCK ROAD 55-44-070-QRY Created On: 02/24/25 Updated On:	Q	SE	SE	17	22N	17E	Outagamie	0-225-158-2025	0.7	0.5	1.1	7.5	30.7	2.716	2.747	1.124	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
VOEGGLI 55-23-027-QRY Created On: 04/11/18 Updated On:	Q	NE	NE	35	4N	7E	Green	0-225-165-2018	0.7	15.6	14.2	13.5	46.4	2.523	2.640	4.674	
	Approved Use : Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
VOEGGLI 55-23-027-QRY Created On: 07/28/21 Updated On:	Q	NE	NE	35	4N	7E	Green	0-225-254-2021	0.9	6.7	2.8	6.1	29.7	2.608	2.668	2.301	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
VOEGGLI 55-23-027-QRY Created On: 01/02/25 Updated On:	Q	NE	NE	35	4N	7E	Green	0-225-1-2025	1.0	6.4	8.2	7.4	33.6	2.612	2.673	2.335	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
VOLENBERG 55-13-100-PIT Created On: 01/05/16 Updated On:	P		NW	19	6N	12E	Dane	0-225-17-2016	6.9	0.0	6.5	6.6	34.2	2.618	2.678	2.294	
	Approved Use : HMA<E-3, HMA>=E-3, Base Aggregate																
VOLENBERG 55-13-100-PIT Created On: 01/04/21 Updated On:	P		NW	19	6N	12E	Dane	0-225-3-2021	4.0	0.0	8.0	8.4	34.5	2.640	2.693	1.982	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
VOLKMAN 55-63-022-PIT Created On: 07/18/19 Updated On:	P	S	NE	17	41N	12E	Vilas	0-225-237-2019	2.4	0.0	0.6	4.8	19.0	2.682	2.709	1.012	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
VOLKMAN 55-63-022-PIT Created On: 01/02/24 Updated On:	P	S	NE	17	41N	12E	Vilas	0-225-56-2024	0.8	0.0	0.3	4.2	18.4	2.701	2.729	1.041	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
W.E. ROCK 55-33-029-QRY Created On: 04/13/21 Updated On:	Q	NE	NE	30	1N	1E	Lafayette	0-225-182-2021	0.0	3.6	1.6	16.1	44.6	2.594	2.664	2.668	
	Approved Use : CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
W.E. ROCK 55-33-029-QRY Created On: 01/29/24 Updated On:	Q	NE	NE	30	1N	1E	Lafayette	0-225-151-2024	0.2	4.1	4.6	8.7	34.9	2.552	2.640	3.426	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
WABASHA SAND & GRAVEL 27-00-020-PIT Created On: 08/12/21 Updated On:	P			32	11N	10W	Wabasha	0-225-263-2021	0.5	1.7	1.4	3.3	17.7	2.685	2.706	0.757	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
WAGNER 55-38-041-QRY Created On: 05/10/18 Updated On:	Q		NW	17	33N	22E	Marinette	0-225-202-2018	0.0	1.8	0.9	7.8	31.9	2.726	2.761	1.250	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
WAGNER 55-38-041-QRY Created On: 04/28/22 Updated On:	Q		NW	17	33N	22E	Marinette	0-225-183-2022	0.3	1.0	1.8	6.3	28.1	2.711	2.750	1.442	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
WAGNER 55-38-041-QRY Created On: 05/14/25 Updated On:	Q		NW	17	33N	22E	Marinette	0-225-205-2025	0.0	1.9	2.0	6.6	31.1	2.705	2.742	1.385	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
WALDENBERGER 55-32-017-QRY Created On: 03/29/17 Updated On:	Q			23	17N	7W	La Crosse	0-225-93-2017	0.3	0.0	3.2	11.8	44.2	2.521	2.610	3.526	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
WALDENBERGER 55-32-017-QRY Created On: 01/03/20 Updated On:	Q			23	17N	7W	La Crosse	0-225-22-2020	1.1	0.0	6.3	10.8	40.5	2.557	2.633	2.981	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
WALDENBERGER 55-32-017-QRY Created On: 01/03/23 Updated On:	Q			23	17N	7W	La Crosse	0-225-22-2023	0.4	6.7	7.8	12.7	45.5	2.529	2.611	3.230	
	Approved Use : HMA<MT, CONCRETE, OGBC, Base Aggregate																
WAMSLEY 55-22-058-QRY Created On: 01/02/25 Updated On:	Q	NE	SW	9	3N	4W	Grant	0-225-90-2025	2.8	4.8	6.7	6.1	30.5	2.618	2.675	2.203	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
* WARMKA 55-14-034-QRY Created On: 01/03/17 Updated On:	Q	NE	NW	9	12N	14E	Dodge	0-225-8-2017		4.0	2.4	5.8	25.1	2.763	2.788	0.904	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
* WARMKA 55-14-034-QRY Created On: 04/01/19 Updated On:	Q	NE	NW	9	12N	14E	Dodge	0-225-118-2019		4.6	2.5	5.2	24.3	2.757	2.785	1.017	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
* WARMKA 55-14-034-QRY Created On: 01/04/22 Updated On:	Q	NE	NW	9	12N	14E	Dodge	0-225-3-2022	0.0	1.8	1.5	5.1	24.5	2.750	2.780	1.070	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
WARTGOW 55-02-019-PIT Created On: 06/11/20 Updated On:	P	NE	NW	4	42N	2W	Ashland	0-225-195-2020		0.0	2.3	4.0	18.4	2.758	2.783	0.913	
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																
WARTGOW 55-02-019-PIT Created On: 01/02/25 Updated On:	P	NE	NW	4	42N	2W	Ashland	0-225-42-2025	0.4	2.0	3.7	3.9	18.3	2.738	2.767	1.072	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
Source Name	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
WAUKESHA LIME & STONE 55-67-042-QRY Created On: 01/04/16 Updated On:	Q	SE	SE	26	7N	19E	Waukesha	0-225-4-2016		9.0	3.0	4.3	20.5	2.712	2.751	1.426		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
WAUKESHA LIME & STONE 55-67-041-PIT Created On: 01/21/16 Updated On:	P	SE	SE	26	7N	8E	Waukesha	0-225-71-2016	1.2	4.7	2.3	4.7	23.4	2.713	2.748	1.311		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
WAUKESHA LIME & STONE 55-67-042-QRY Created On: 02/05/19 Updated On:	Q	SE	SE	26	7N	19E	Waukesha	0-225-98-2019	0.3	1.2	0.2	5.7	27.4	2.682	2.718	1.370		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
WAUKESHA LIME & STONE 55-67-041-PIT Created On: 01/05/21 Updated On:	P	SE	SE	26	7N	8E	Waukesha	0-225-96-2021	0.4	2.2	2.1	5.7	29.2	2.693	2.733	1.502		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
WAUKESHA LIME & STONE 55-67-042-QRY Created On: 01/04/22 Updated On:	Q	SE	SE	26	7N	19E	Waukesha	0-225-54-2022	0.3	0.9	0.5	4.1	20.0	2.776	2.793	0.639		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
WAUKESHA LIME & STONE 55-67-042-QRY Created On: 01/02/25 Updated On:	Q	SE	SE	26	7N	19E	Waukesha	0-225-77-2025	0.0	0.0	3.3	6.2	26.4	2.692	2.733	1.526		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
WEBSTER PIT 55-54-031-PIT Created On: 01/10/23 Updated On:	P	NE	NE	7	34N	4W	Rusk	0-225-116-2023	1.1	0.0	2.2	4.1	18.5	2.768	2.790	0.815		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
WEISENBERGER 55-37-083-QRY Created On: 01/06/16 Updated On:	Q		N	1	28N	5E	Marathon	0-225-32-2016		0.0	0.9	4.5	19.3	2.689	2.720	1.154	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
WEISENBERGER 55-37-083-QRY Created On: 01/04/19 Updated On:	Q		N	1	28N	5E	Marathon	0-225-35-2019		0.0	0.4	4.8	19.6	2.673	2.712	1.471	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
WEISENBERGER 55-37-083-QRY Created On: 01/13/22 Updated On:	Q		N	1	28N	5E	Marathon	0-225-109-2022	0.0	0.3	0.2	4.5	17.7	2.829	2.846	0.615	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
WEISENBERGER 55-37-083-QRY Created On: 01/14/25 Updated On:	Q		N	1	28N	5E	Marathon	0-225-112-2025	1.2	2.6	0.2	3.3	16.4	2.726	2.751	0.941	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
WENDERS 55-06-028-QRY Created On: 05/09/16 Updated On:	Q			10	20N	12W	Buffalo	0-225-163-2016		0.0	11.8	13.7	40.7	2.599	2.660	2.318	
	Approved Use : CONCRETE, Base Aggregate																
WENDERS 55-06-028-QRY Created On: 01/08/19 Updated On:	Q			10	20N	12W	Buffalo	0-225-80-2019	0.7	0.0	2.6	8.8	32.6	2.644	2.691	1.770	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
WENDERS 55-06-028-QRY Created On: 01/04/22 Updated On:	Q			10	20N	12W	Buffalo	0-225-9-2022	0.1	1.7	4.7	9.4	37.1	2.630	2.683	2.015	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse		Absorp. %	
Source Name	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
WENDERS 55-06-028-QRY Created On: 01/02/25 Updated On:	Q			10	20N	12W	Buffalo	0-225-47-2025	0.6	2.1	2.7	8.8	36.2	2.622	2.677	2.083		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
WEST BEND S & G 55-66-020-PIT Created On: 03/22/19 Updated On:	P	SW	SE	8	11N	19E	Washington	0-225-116-2019	0.0	1.1	0.3	4.8	27.3	2.757	2.780	0.819		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
WEST BEND S & G 55-66-020-PIT Created On: 05/20/24 Updated On:	P	SW	SE	8	11N	19E	Washington	0-225-257-2024	2.3	1.5	4.7	5.3	27.1	2.731	2.757	0.964		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
WESTPHAL 55-14-035-QRY Created On: 01/03/18 Updated On:	Q	SE	SE	8	10N	14E	Dodge	0-225-20-2018		13.5	8.9	5.4	25.0	2.689	2.733	1.636		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
WESTPHAL 55-14-035-QRY Created On: 05/17/21 Updated On:	Q	SE	SE	8	10N	14E	Dodge	0-225-209-2021	0.0	8.6	8.2	5.7	25.3	2.689	2.732	1.614		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
WESTPHAL 55-14-035-QRY Created On: 02/06/23 Updated On:	Q	SE	SE	8	10N	14E	Dodge	0-225-141-2023	0.0	17.0	10.1	4.8	30.4	2.703	2.743	1.501		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
WESTRES 55-13-066-QRY Created On: 04/06/17 Updated On:	Q	SW	NE	2	7N	6E	Dane	0-225-110-2017	0.7	1.9	2.2	11.0	37.3	2.613	2.672	2.268		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
Source Name	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
WESTRES 55-13-066-QRY Created On: 03/29/21 Updated On:	Q	SW	NE	2	7N	6E	Dane	0-225-161-2021	0.3	7.5	3.2	9.1	33.6	2.573	2.646	2.848		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
WESTRES 55-13-066-QRY Created On: 01/02/24 Updated On:	Q	SW	NE	2	7N	6E	Dane	0-225-73-2024	0.7	4.8	2.0	11.6	42.5	2.494	2.576	3.284		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
WETZEL 55-12-024-QRY Created On: 01/05/17 Updated On:	Q	NW	SE	31	7N	6W	Crawford	0-225-33-2017		1.2	3.3	6.7	28.7	2.633	2.685	1.977		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
WETZEL 55-12-024-QRY Created On: 01/03/20 Updated On:	Q	NW	SE	31	7N	6W	Crawford	0-225-23-2020	2.3	3.6	2.9	12.1	40.5	2.558	2.633	2.939		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
WETZEL 55-12-024-QRY Created On: 01/03/23 Updated On:	Q	NW	SE	31	7N	6W	Crawford	0-225-71-2023	1.2	4.7	0.6	11.7	39.2	2.604	2.662	2.251		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
WHELAN 55-64-039-PIT Created On: 03/24/16 Updated On:	P	SE	NE	1	1N	15E	Walworth	0-225-110-2016		0.0	2.7	5.6	26.6	2.693	2.726	1.229		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
WHELAN 55-64-039-PIT Created On: 01/05/21 Updated On:	P	SE	NE	1	1N	15E	Walworth	0-225-84-2021	0.0	5.1	3.6	5.2	29.6	2.689	2.727	1.400		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
WHELAN 55-64-039-PIT Created On: 06/02/25 Updated On:	P	SE	NE	1	1N	15E	Walworth	0-225-217-2025	0.5	12.7	0.6	5.4	26.4	2.693	2.732	1.464	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
WHITEWATER LIMESTONE 55-64-052-QRY Created On: 10/03/17 Updated On:	Q	NW	SW	9	4N	15E	Walworth	0-225-277-2017	1.1	2.6	2.1	8.8	34.3	2.618	2.678	2.309	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
WHITEWATER LIMESTONE 55-64-052-QRY Created On: 04/09/20 Updated On:	Q	NW	SW	9	4N	15E	Walworth	0-225-152-2020	0.2	1.8	6.1	8.1	35.2	2.627	2.683	2.152	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
WHITEWATER LIMESTONE 55-64-052-QRY Created On: 02/10/22 Updated On:	Q	NW	SW	9	4N	15E	Walworth	0-225-121-2022	0.6	4.6	7.9	8.1	33.6	2.612	2.675	2.419	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
WHITEWATER LIMESTONE 55-64-052-QRY Created On: 01/02/25 Updated On:	Q	NW	SW	9	4N	15E	Walworth	0-225-3-2025	0.7	2.1	2.5	6.6	29.4	2.604	2.670	2.544	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
WHITSON 55-25-024-QRY Created On: 08/07/18 Updated On:	Q	SE	SE	31	6N	2E	Iowa	0-225-265-2018	1.2	3.8	3.7	12.7	43.7	2.567	2.646	3.066	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
WHITSON 55-25-024-QRY Created On: 01/02/25 Updated On:	Q	SE	SE	31	6N	2E	Iowa	0-225-81-2025	1.3	11.9	10.3	11.3	40.7	2.565	2.648	3.224	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
WIEDL 55-41-024-QRY Created On: 06/10/16 Updated On:	Q	NW	NW	29	16N	2W	Monroe	0-225-195-2016	2.0	0.0	4.6	11.3	39.7	2.547	2.618	2.814		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
WIEDL 55-41-024-QRY Created On: 05/03/18 Updated On:	Q	NW	NW	29	16N	2W	Monroe	0-225-190-2018	0.7	0.0	3.2	8.4	35.2	2.591	2.650	2.294		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
WIEDL 55-41-024-QRY Created On: 08/12/21 Updated On:	Q	NW	NW	29	16N	2W	Monroe	0-225-261-2021	3.4	0.0	8.4	11.4	41.1	2.566	2.633	2.614		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
WIEDL 55-41-024-QRY Created On: 01/02/24 Updated On:	Q	NW	NW	29	16N	2W	Monroe	0-225-23-2024	2.0	2.6	5.0	11.8	40.5	2.576	2.642	2.565		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
WIEMEIR 26-00-005-PIT Created On: 04/23/15 Updated On:	P	SW	NW	33	48N	47W	Gogebic	0-225-130-2015		6.3	13.9	5.4	23.0	2.717	2.760	1.581		
	Approved Use : Base Aggregate																	
WIEMEIR 26-00-005-PIT Created On: 04/30/21 Updated On:	P	SW	NW	33	48N	47W	Gogebic	0-225-193-2021	1.8	11.1	17.7	5.6	24.9	2.715	2.754	1.456		
	Approved Use : Base Aggregate																	
WIESER 55-47-033-QRY Created On: 06/08/17 Updated On:	Q	E	NE	9	25N	16W	Pierce	0-225-206-2017		0.0	3.9	11.8	40.5	2.581	2.644	2.458		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Coarse Sp. Gravity		Coarse Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
WIESER 55-47-033-QRY Created On: 06/06/19 Updated On:	Q	E	NE	9	25N	16W	Pierce	0-225-206-2019	1.9	0.0	7.6	9.7	39.9	2.555	2.626	2.814	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
WIESER 55-47-033-QRY Created On: 04/19/22 Updated On:	Q	E	NE	9	25N	16W	Pierce	0-225-180-2022	2.8	0.0	4.9	12.8	42.9	2.566	2.637	2.779	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
WIESER 55-47-033-QRY Created On: 02/20/25 Updated On:	Q	E	NE	9	25N	16W	Pierce	0-225-152-2025	3.2	0.0	7.2	10.9	38.0	2.596	2.652	2.155	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
WILLIAMS 55-11-039-QRY Created On: 03/30/15 Updated On:	Q	SE	NE	19	12N	8E	Columbia	0-225-103-2015		0.2	0.2	6.0	24.1	2.633	2.646	0.477	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
WILLIAMS 55-11-039-QRY Created On: 01/03/18 Updated On:	Q	SE	NE	19	12N	8E	Columbia	0-225-8-2018	0.0	0.0	0.0	4.4	19.7	2.634	2.644	0.400	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
WILLIAMS 55-11-039-QRY Created On: 01/04/21 Updated On:	Q	SE	NE	19	12N	8E	Columbia	0-225-41-2021	0.0	0.0	0.4	6.1	25.1	2.627	2.639	0.481	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
WILLIAMS 55-11-039-QRY Created On: 01/02/24 Updated On:	Q	SE	NE	19	12N	8E	Columbia	0-225-19-2024	0.1	0.3	0.4	5.3	23.1	2.653	2.659	0.219	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Coarse Sp. Gravity		Coarse Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
WILTON 55-41-027-QRY Created On: 07/25/19 Updated On:	Q		SW	35	16N	1W	Monroe	0-225-250-2019		0.0	4.4	14.1	46.6	2.573	2.637	2.467	
	Approved Use : Base Aggregate																
WILTON 55-41-027-QRY Created On: 01/04/22 Updated On:	Q		SW	35	16N	1W	Monroe	0-225-73-2022		1.2	5.3	13.9	45.7	2.556	2.627	2.796	
	Approved Use : OGBC, Base Aggregate																
WILTON 55-41-027-QRY Created On: 01/02/25 Updated On:	Q		SW	35	16N	1W	Monroe	0-225-28-2025	1.7	0.0	6.4	10.6	40.9	2.547	2.622	2.955	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
WIMMIE 55-49-026-PIT Created On: 01/07/16 Updated On:	P		NW	28	23N	9E	Portage	0-225-43-2016	0.2	0.0	0.8	5.1	24.3	2.705	2.729	0.876	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
WIMMIE 55-49-026-PIT Created On: 01/04/21 Updated On:	P		NW	28	23N	9E	Portage	0-225-22-2021	0.4	2.2	0.4	6.2	26.9	2.726	2.747	0.792	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
WIMMIE #2 55-49-030-PIT Created On: 09/05/23 Updated On:	P		SW	21	23N	9E	Portage	0-225-248-2023	1.0	1.6	1.7	6.1	28.2	2.682	2.709	0.997	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
WISSOTA RUGBY S&G 55-66-021-PIT Created On: 01/07/19 Updated On:	P	SE	NE	34	10N	19E	Washington	0-225-43-2019	0.2	4.6	1.1	5.2	27.4	2.731	2.760	1.095	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
WISSOTA RUGBY S&G 55-66-021-PIT Created On: 01/29/24 Updated On:	P	SE	NE	34	10N	19E	Washington	0-225-160-2024	0.4	9.7	1.1	6.8	31.2	2.725	2.755	1.095	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
WISSOTA RUGBY S&G 55-66-021-PIT Created On: 05/01/24 Updated On:	P	SE	NE	34	10N	19E	Washington	0-225-246-2024	1.3	9.5	1.8	5.6	14.9	2.725	2.755	1.095	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
WITT QUARRY 55-09-084-QRY Created On: 07/23/25 Updated On:	Q	NE	NE	1	28N	5W	Chippewa	0-225-228-2025	1.1	0.0	0.6	4.6	21.1	2.640	2.677	1.390	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
WITTWER 55-04-016-PIT Created On: 05/11/15 Updated On:	P	NE	SE	30	44N	7W	Bayfield	0-225-160-2015		0.0	3.6	4.8	20.5	2.791	2.816	0.923	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
WITTWER 55-04-016-PIT Created On: 01/06/20 Updated On:	P	NE	SE	30	44N	7W	Bayfield	0-225-32-2020	0.8	0.0	4.0	4.0	17.4	2.766	2.803	1.345	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
WITTWER 55-04-016-PIT Created On: 01/16/25 Updated On:	P	NE	SE	30	44N	7W	Bayfield	0-225-130-2025	0.4	0.0	2.9	4.3	17.6	2.816	2.843	0.943	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
* WK 55-13-102-QRY Created On: 03/20/15 Updated On:	Q	SW	SW	8	7N	8E	Dane	0-225-101-2015	1.2	2.3	6.0	7.0	31.3	2.626	2.681	2.081	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
* WK 55-13-102-QRY Created On: 01/03/18 Updated On:	Q	SW	SW	8	7N	8E	Dane	0-225-22-2018	4.6	2.0	11.1	8.7	40.4	2.553	2.633	3.112	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
* WK 55-13-102-QRY Created On: 01/05/21 Updated On:	Q	SW	SW	8	7N	8E	Dane	0-225-93-2021	1.8	3.0	7.4	7.2	31.6	2.612	2.672	2.271	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
WOLF RIVER 55-34-025-PIT Created On: 05/26/16 Updated On:	P	NW	SW	36	31N	14E	Langlade	0-225-189-2016	0.4	0.0	2.1	7.7	26.8	2.635	2.658	0.870	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
WOLF RIVER 55-34-025-PIT Created On: 01/04/21 Updated On:	P	NW	SW	36	31N	14E	Langlade	0-225-14-2021	0.0	0.4	0.3	4.1	23.0	2.664	2.684	0.772	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
WORDEN ENTERPRISES LLC 55-37-097-QRY Created On: 05/09/23 Updated On:	Q	NE	SW	20	27N	6E	Marathon	0-225-216-2023	0.3	0.0	1.8	8.8	37.4	2.554	2.582	1.083	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
WORDEN ENTERPRISES LLC 55-37-097-QRY Created On: 03/13/24 Updated On:	Q	NE	SW	20	27N	6E	Marathon	0-225-201-2024	0.0	0.0	1.1	7.3	28.7	2.571	2.596	0.979	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
WOZNIAK 55-09-074-PIT Created On: 01/07/15 Updated On:	P	SW	NE	1	28N	5W	Chippewa	0-225-11-2015		0.0	1.8	3.6	17.8	2.658	2.689	1.169	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse					
	P/Q	Qrt	Qrt	Sect	Town	Range	County	LA Wear (%)					Sp. Gravity		Absorp. %			
								100					500	OD	SSD	Crse	Fine	
WOZNIAK 55-09-074-QRY Created On: 07/23/15 Updated On:	Q	NW	SE	1	28N	5W	Chippewa	0-225-216-2015		0.0	5.3	5.2	21.3	2.977	3.001	0.808		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
WOZNIAK 55-09-074-PIT Created On: 03/08/18 Updated On:	P	SW	NE	1	28N	5W	Chippewa	0-225-115-2018	0.5	0.0	3.1	3.9	17.4	2.909	2.935	0.866		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
WOZNIAK 55-09-074-PIT Created On: 01/05/21 Updated On:	P	SW	NE	1	28N	5W	Chippewa	0-225-91-2021	0.1	0.0	1.9	4.4	20.1	2.878	2.889	0.374		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
WOZNIAK 55-09-074-QRY Created On: 01/02/24 Updated On:	Q	NW	SE	1	28N	5W	Chippewa	0-225-82-2024	0.0	0.0	1.1	4.2	18.9	2.936	2.946	0.351		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
* WRIGLY 55-13-114-QRY Created On: 06/02/17 Updated On:	Q		NW	29	6N	12E	Dane	0-225-201-2017		3.5	3.8	7.0	28.6					
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
* WRIGLY 55-13-114-QRY Created On: 06/07/18 Updated On:	Q		NW	29	6N	12E	Dane	0-225-220-2018	0.5	11.3	17.2	7.9	33.3	2.619	2.683	2.428		
	Approved Use : Base Aggregate																	
* WRIGLY 55-13-114-QRY Created On: 01/04/22 Updated On:	Q		NW	29	6N	12E	Dane	0-225-55-2022	0.1	17.9	6.2	7.6	30.4	2.615	2.680	2.483		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
ZANDER 55-13-109-PIT Created On: 03/14/18 Updated On:	P	NW	SW	11	7N	7E	Dane	0-225-119-2018	10.1	5.3	16.3	16.4	46.2	2.542	2.621	3.113	
	Approved Use : Base Aggregate																
ZANDER 55-13-109-PIT Created On: 01/07/19 Updated On:	P	NW	SW	11	7N	7E	Dane	0-225-46-2019	4.1	2.2	6.3	9.7	37.0	2.602	2.663	2.362	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
ZANDER 55-13-122-QRY Created On: 06/20/19 Updated On:	Q	NW	SW	11	7N	7E	Dane	0-225-222-2019	0.9	3.3	8.3	8.3	39.0	2.581	2.647	2.581	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
ZANDER 55-13-122-QRY Created On: 04/26/23 Updated On:	Q	NW	SW	11	7N	7E	Dane	0-225-208-2023	1.8	10.9	9.2	11.6	41.5	2.556	2.631	2.938	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
ZANDER 55-13-109-PIT Created On: 01/02/24 Updated On:	P	NW	SW	11	7N	7E	Dane	0-225-129-2024	3.0	0.0	7.8	8.5	34.7	2.619	2.672	2.043	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
ZART 55-22-061-QRY Created On: 04/17/15 Updated On:	Q	SE	SE	7	6N	3W	Grant	0-225-126-2015	2.2	1.3	6.2	9.9	35.6	2.595	2.655	2.302	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
ZART 55-22-061-QRY Created On: 08/15/17 Updated On:	Q	SE	SE	7	6N	3W	Grant	0-225-255-2017	2.4	6.1	2.1	9.4	34.1	2.606	2.663	2.158	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
ZART 55-22-061-QRY Created On: 01/04/18 Updated On:	Q	SE	SE	7	6N	3W	Grant	0-225-67-2018	1.0	5.6	7.7	10.6	38.6	2.620	2.677	2.196	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
ZART 55-22-061-QRY Created On: 01/05/21 Updated On:	Q	SE	SE	7	6N	3W	Grant	0-225-59-2021	1.3	5.7	9.4	13.7	43.9	2.628	2.684	2.135	
	Approved Use : CONCRETE, OGBC, Base Aggregate																
ZART 55-22-061-QRY Created On: 01/02/24 Updated On:	Q	SE	SE	7	6N	3W	Grant	0-225-36-2024	0.3	3.3	2.4	9.2	33.7	2.627	2.684	2.189	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
ZEINERT 55-58-045-PIT Created On: 05/12/16 Updated On:	P	SE	SW	3	28N	12E	Shawano	0-225-170-2016	0.4	0.0	0.9	8.8	34.6	2.631	2.662	1.205	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
ZEINERT 55-58-045-PIT Created On: 01/04/21 Updated On:	P	SE	SW	3	28N	12E	Shawano	0-225-16-2021	0.3	1.4	2.1	9.6	34.0	2.641	2.665	0.920	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
ZIOLKOWSKI 55-37-087-PIT Created On: 01/02/18 Updated On:	P	SW	SE	29	27N	9'E	Marathon	0-225-3-2018	0.6	0.0	1.0	7.0	30.2	2.647	2.672	0.940	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
ZIOLKOWSKI 55-37-087-PIT Created On: 01/02/24 Updated On:	P	SW	SE	29	27N	9'E	Marathon	0-225-44-2024	0.7	1.4	4.8	7.5	32.2	2.645	2.670	0.970	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
ZOBEL 55-56-031-QRY Created On: 06/05/15 Updated On:	Q			21	12N	4E	Sauk	0-225-188-2015		0.0	1.5	10.3	36.7	2.620	2.673	2.006	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
ZOBEL 55-56-031-QRY Created On: 01/04/18 Updated On:	Q			21	12N	4E	Sauk	0-225-51-2018	0.4	0.0	1.7	9.1	35.2	2.631	2.682	1.951	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
ZOBEL 55-56-031-QRY Created On: 01/04/21 Updated On:	Q			21	12N	4E	Sauk	0-225-33-2021	0.6	0.0	0.6	11.4	39.0	2.584	2.644	2.334	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
ZOBEL 55-56-031-QRY Created On: 01/02/24 Updated On:	Q			21	12N	4E	Sauk	0-225-22-2024	0.7	12.9	1.4	8.6	33.4	2.653	2.699	1.758	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
ZOGG 55-62-033-QRY Created On: 07/02/15 Updated On:	Q	SW	SE	27	14N	7W	Vernon	0-225-206-2015		0.0	6.9	11.5	39.7	2.594	2.656	2.412	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
ZOGG 55-62-033-QRY Created On: 01/03/18 Updated On:	Q	SW	SE	27	14N	7W	Vernon	0-225-12-2018	1.0	0.0	3.8	9.9	35.4	2.605	2.667	2.408	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
ZOGG 55-62-033-QRY Created On: 01/04/21 Updated On:	Q	SW	SE	27	14N	7W	Vernon	0-225-29-2021	0.9	0.0	1.2	7.8	32.3	2.600	2.667	2.583	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY SOURCE NAME

Date Printed: 08/06/2025

TEST YEARS BETWEEN 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse LA Wear (%)		Coarse Sp. Gravity		Coarse Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
ZOGG	Q	SW	SE	27	14N	7W	Vernon	0-225-38-2024	0.2	8.9	6.8	9.9	36.6	2.601	2.667	2.529	
55-62-033-QRY	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
Created On: 01/02/24																	
Updated On:																	

Prepared by:

Wisconsin Department of Transportation
Bureau of Highway Construction
Quality Management Section

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
ADAMS -- WI																		
MANTHEY EAST 55-01-004-PIT Created On: 04/07/16 Updated On:	P			26	17N	7E	Adams	0-225-133-2016		0.0	1.9	8.8	32.4	2.697	2.737	1.494		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
MANTHEY EAST 55-01-004-PIT Created On: 01/04/21 Updated On:	P			26	17N	7E	Adams	0-225-23-2021	4.5	2.6	4.3	8.4	34.5	2.702	2.741	1.411		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
RILEY 55-01-007-PIT Created On: 05/01/15 Updated On:	P	NW	SW	19	14N	7E	Adams	0-225-141-2015		0.0	2.8	7.5	28.9	2.819	2.846	0.969		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
RILEY 55-01-007-PIT Created On: 04/28/22 Updated On:	P	NW	SW	19	14N	7E	Adams	0-225-192-2022	0.1	0.0	0.6	6.2	25.7	2.770	2.803	1.188		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
SEVEN SISTERS 55-01-008-QRY Created On: 08/25/16 Updated On:	Q			36	20N	7E	Adams	0-225-248-2016		0.9	0.7	4.6	20.7	2.631	2.646	0.591		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
SEVEN SISTERS 55-01-008-QRY Created On: 01/04/19 Updated On:	Q			36	20N	7E	Adams	0-225-33-2019	0.2	0.0	0.9	4.7	19.6	2.625	2.642	0.666		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
SEVEN SISTERS 55-01-008-QRY Created On: 01/04/22 Updated On:	Q			36	20N	7E	Adams	0-225-36-2022	4.2	12.0	7.8	6.1	22.9	2.543	2.598	2.169		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
ADAMS -- WI																		
SEVEN SISTERS	Q			36	20N	7E	Adams	0-225-9-2025		1.1	3.5	1.9	4.3	18.7	2.614	2.637	0.914	
55-01-008-QRY	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
Created On: 01/02/25																		
Updated On:																		
ASHLAND -- WI																		
HIGHBRIDGE	Q	S	SW	16	45N	3W	Ashland	0-225-91-2023		0.1	0.4	0.3	4.5	21.9	2.588	2.612	0.926	
55-02-005-QRY	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
Created On: 01/04/23																		
Updated On:																		
*HIGHBRIDGE NORTH	Q	S	SW	16	45N	3W	Ashland	0-225-192-2017			0.0	0.7	4.5	21.0	2.615	2.633	0.685	
55-02-005-QRY	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
Created On: 05/19/17																		
Updated On:																		
*HIGHBRIDGE NORTH	Q	S	SW	16	45N	3W	Ashland	0-225-33-2020		0.1	0.0	1.2	5.2	24.3	2.623	2.637	0.549	
55-02-005-QRY	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
Created On: 01/06/20																		
Updated On:																		
PALECEK	P	NW	SW	24	47N	1W	Ashland	0-225-230-2022		0.6	2.1	2.4	4.2	18.9	2.753	2.780	1.004	
55-02-012-PIT	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
Created On: 06/16/22																		
Updated On:																		
PETERSON MARENGO	P	N	SW	18	45N	4W	Ashland	0-225-182-2016			0.0	2.6	5.4	23.1	2.639	2.693	2.050	
55-02-013-PIT	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
Created On: 05/19/16																		
Updated On:																		
PETERSON MARENGO	P	N	SW	18	45N	4W	Ashland	0-225-204-2021		2.5	0.0	14.2	5.8	23.7	2.686	2.741	2.034	
55-02-013-PIT	Approved Use : Base Aggregate																	
Created On: 05/10/21																		
Updated On:																		

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	Sp. Gravity		Absorp. %	
														OD	SSD	Crse	Fine
ASHLAND -- WI																	
WARTGOW 55-02-019-PIT Created On: 06/11/20 Updated On:	P	NE	NW	4	42N	2W	Ashland	0-225-195-2020		0.0	2.3	4.0	18.4	2.758	2.783	0.913	
Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																	
WARTGOW 55-02-019-PIT Created On: 01/02/25 Updated On:	P	NE	NW	4	42N	2W	Ashland	0-225-42-2025	0.4	2.0	3.7	3.9	18.3	2.738	2.767	1.072	
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
BARRON -- WI																	
ADAMS PIT 55-03-044-PIT Created On: 01/08/20 Updated On:	P	NW	NE	12	33N	10W	Barron	0-225-51-2020	0.8	0.0	1.4	4.8	20.9	2.708	2.736	1.032	
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
ADAMS PIT 55-03-044-PIT Created On: 04/29/25 Updated On:	P	NW	NE	12	33N	10W	Barron	0-225-202-2025	0.8	0.0	1.3	5.1	21.2	2.711	2.739	1.031	
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
BOHL #720 55-03-006-PIT Created On: 02/13/17 Updated On:	P	NW	SE	10	32N	11W	Barron	0-225-70-2017		0.0	2.2	4.4	18.9	2.687	2.715	1.015	
Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
BOHL #720 55-03-006-PIT Created On: 03/01/22 Updated On:	P	NW	SE	10	32N	11W	Barron	0-225-135-2022	2.5	2.3	2.3	4.0	18.5	2.685	2.715	1.106	
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
BRUHA 55-03-008-PIT Created On: 01/09/15 Updated On:	P	SW	NE	13	36N	12W	Barron	0-225-44-2015		0.0	2.8	3.5	15.8	2.755	2.789	1.234	
Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
BARRON -- WI																		
BRUHA 55-03-008-PIT Created On: 01/08/20 Updated On:	P	SW	NE	13	36N	12W	Barron	0-225-55-2020	0.7	0.0	2.4	3.6	16.5	2.767	2.794	0.973		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
BRUHA 55-03-008-PIT Created On: 01/02/25 Updated On:	P	SW	NE	13	36N	12W	Barron	0-225-14-2025	1.2	1.1	2.6	3.9	17.9	2.764	2.796	1.145		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
BURIC 55-03-009-PIT Created On: 06/13/16 Updated On:	P	NW	NW	14	33N	10W	Barron	0-225-204-2016		0.0	1.2	5.6	22.0	2.730	2.754	0.876		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
BURIC 55-03-009-PIT Created On: 01/04/22 Updated On:	P	NW	NW	14	33N	10W	Barron	0-225-85-2022	2.7	0.0	1.9	4.6	21.2	2.667	2.689	0.853		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
CAMPIA PIT 55-03-010-PIT Created On: 01/02/24 Updated On:	P	NE	NE	8	35N	10W	Barron	0-225-87-2024	1.3	0.0	0.9	4.2	19.6	2.708	2.734	0.959		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
CEMSTONE CUMBERLAND PIT 55-03-037-PIT Created On: 01/25/16 Updated On:	P	S	SE	35	36N	13W	Barron	0-225-80-2016		0.0	3.2	3.9	18.3	2.726	2.758	1.181		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
CEMSTONE CUMBERLAND PIT 55-03-037-PIT Created On: 01/05/21 Updated On:	P	S	SE	35	36N	13W	Barron	0-225-86-2021	4.1	0.0	2.5	4.0	18.0	2.698	2.731	1.198		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
BARRON -- WI																		
EGSTAD 55-03-014-PIT Created On: 05/18/17 Updated On:	P	S	SW	34	35N	14W	Barron	0-225-188-2017		0.0	4.0	5.3	20.3	2.727	2.766	1.421		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
EGSTAD 55-03-014-PIT Created On: 04/05/22 Updated On:	P	S	SW	34	35N	14W	Barron	0-225-159-2022	1.9	4.8	7.2	5.2	20.0	2.741	2.773	1.151		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
JOHNSON 55-03-024-PIT Created On: 05/23/23 Updated On:	P	NE	NW	5	35N	10W	Barron	0-225-227-2023	3.4	0.0	1.0	4.2	18.8	2.744	2.768	0.869		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
KNUTSON 55-03-026-PIT Created On: 04/07/16 Updated On:	P	SW	SE	22	32N	11W	Barron	0-225-128-2016		0.0	1.7	4.6	20.3	2.698	2.729	1.168		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
KNUTSON 55-03-026-PIT Created On: 07/19/21 Updated On:	P	SW	SE	22	32N	11W	Barron	0-225-247-2021	3.5	0.0	1.3	4.3	20.2	2.677	2.709	1.178		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MCCLAIN 55-03-027-PIT Created On: 05/08/15 Updated On:	P	SW	NE	9	35N	13W	Barron	0-225-159-2015		0.0	2.9	2.8	14.0	2.795	2.817	0.788		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
MCCLAIN 55-03-027-PIT Created On: 04/18/22 Updated On:	P	SW	NE	9	35N	13W	Barron	0-225-177-2022		0.0	2.4	3.4	14.9	2.785	2.811	0.911		
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
BARRON -- WI																		
ROSE STONE 55-03-032-QRY Created On: 01/09/15 Updated On:	Q	SE	SE	30	35N	10W	Barron	0-225-45-2015		0.0	0.7	9.1	41.7	2.553	2.577	0.961		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
ROSE STONE 55-03-032-QRY Created On: 03/23/18 Updated On:	Q	SE	SE	30	35N	10W	Barron	0-225-135-2018		0.0	1.4	7.7	33.7	2.559	2.582	0.885		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
ROSE STONE 55-03-032-QRY Created On: 03/17/21 Updated On:	Q	SE	SE	30	35N	10W	Barron	0-225-152-2021	0.0	0.1	0.3	9.2	38.7	2.565	2.583	0.705		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
ROSE STONE 55-03-032-QRY Created On: 01/04/24 Updated On:	Q	SE	SE	30	35N	10W	Barron	0-225-143-2024	0.0	0.7	1.2	12.6	45.4	2.536	2.567	1.189		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
SAFFERT 795 55-03-034-PIT Created On: 01/06/16 Updated On:	P	SW	SW	1	34N	11W	Barron	0-225-27-2016		0.0	5.3	5.7	24.0	2.662	2.703	1.554		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
SAFFERT 795 55-03-034-PIT Created On: 01/05/21 Updated On:	P	SW	SW	1	34N	11W	Barron	0-225-77-2021	0.9	3.8	5.1	4.9	20.8	2.711	2.743	1.184		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
VERMILLION 55-03-039-PIT Created On: 01/09/20 Updated On:	P	NW	SW	14	35N	13W	Barron	0-225-88-2020	4.2	0.0	2.6	4.0	19.5	2.711	2.735	0.881		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
BARRON -- WI																		
VERMILLION	P	NW	SW	14	35N	13W	Barron	0-225-136-2025	1.9	0.0	3.4	5.4	20.2	2.681	2.714	1.263		
55-03-039-PIT	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
Created On: 01/16/25																		
Updated On:																		
BAYFIELD -- WI																		
BARNES	Q	NW	NE	21	44N	9W	Bayfield	0-225-157-2015		0.0	7.1	3.9	15.4	2.874	2.891	0.570		
55-04-001-QRY	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
Created On: 05/08/15																		
Updated On:																		
BARNES	Q	NW	NE	21	44N	9W	Bayfield	0-225-18-2018	0.2	0.0	3.9	2.8	12.6	2.854	2.881	0.943		
55-04-001-QRY	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
Created On: 01/03/18																		
Updated On:																		
BARNES	Q	NW	NE	21	44N	9W	Bayfield	0-225-203-2021	0.1	1.2	2.9	2.5	11.1	2.884	2.907	0.802		
55-04-001-QRY	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
Created On: 05/06/21																		
Updated On:																		
BARNES	Q	NW	NE	21	44N	9W	Bayfield	0-225-93-2024	0.1	6.2	11.3	4.6	18.3	2.804	2.844	1.422		
55-04-001-QRY	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
Created On: 01/02/24																		
Updated On:																		
CROOKED LAKE	P	SW	NW	36	47N	8W	Bayfield	0-225-58-2019	1.7	0.0	1.9	5.9	22.7	2.814	2.844	1.078		
55-04-003-PIT	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
Created On: 01/07/19																		
Updated On:																		
CROOKED LAKE	P	SW	NW	36	47N	8W	Bayfield	0-225-91-2024	1.4	2.1	2.7	3.4	16.6	2.817	2.843	0.926		
55-04-003-PIT	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
Created On: 01/02/24																		
Updated On:																		

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
BAYFIELD -- WI																	
FROSTMAN 55-04-004-PIT Created On: 01/07/19 Updated On:	P		NW	26	47N	8W	Bayfield	0-225-57-2019	2.3	0.0	2.6	8.8	20.9	2.684	2.715	1.154	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
FROSTMAN 55-04-004-PIT Created On: 01/02/25 Updated On:	P		NW	26	47N	8W	Bayfield	0-225-39-2025	1.1	1.4	1.7	4.5	18.8	2.774	2.803	1.033	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
KELLEY 55-04-019-PIT Created On: 10/04/21 Updated On:	P	SW	NW	25	43N	8W	Bayfield	0-225-266-2021	0.9	0.0	1.6	3.8	17.5	2.811	2.837	0.950	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
WITTWER 55-04-016-PIT Created On: 05/11/15 Updated On:	P	NE	SE	30	44N	7W	Bayfield	0-225-160-2015		0.0	3.6	4.8	20.5	2.791	2.816	0.923	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
WITTWER 55-04-016-PIT Created On: 01/06/20 Updated On:	P	NE	SE	30	44N	7W	Bayfield	0-225-32-2020	0.8	0.0	4.0	4.0	17.4	2.766	2.803	1.345	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
WITTWER 55-04-016-PIT Created On: 01/16/25 Updated On:	P	NE	SE	30	44N	7W	Bayfield	0-225-130-2025	0.4	0.0	2.9	4.3	17.6	2.816	2.843	0.943	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
BROWN -- WI																	
*BAY SETTLEMENT 55-05-012-QRY Created On: 05/17/22 Updated On:	Q			5	24N	22E	Brown	0-225-208-2022	1.8	4.9	1.2	10.5	35.4	2.655	2.711	2.090	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
BROWN -- WI																	
*D AND J SCRAYS HILL 55-05-004-QRY Created On: 04/05/16 Updated On:	Q		NW	6	22N	21E	Brown	0-225-120-2016	0.1	2.9	1.3	9.1	36.3	2.702	2.748	1.721	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
*D AND J SCRAYS HILL 55-05-004-QRY Created On: 02/24/21 Updated On:	Q		NW	6	22N	21E	Brown	0-225-129-2021		2.4	2.4	9.3	37.7	2.681	2.727	1.712	
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																
DENMARK 55-05-005-QRY Created On: 01/05/17 Updated On:	Q		E	36	22N	22E	Brown	0-225-41-2017		2.0	0.4	4.5	21.6	2.792	2.809	0.627	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
DENMARK 55-05-005-QRY Created On: 01/02/20 Updated On:	Q		E	36	22N	22E	Brown	0-225-8-2020		14.4	0.4	6.0	25.9	2.791	2.821	1.089	
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																
DENMARK 55-05-005-QRY Created On: 01/03/23 Updated On:	Q		E	36	22N	22E	Brown	0-225-44-2023	0.0	1.8	0.4	5.5	25.1	2.792	2.809	0.618	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
GLENMORE 55-05-013-QRY Created On: 01/05/15 Updated On:	Q		NE	6	22N	21E	Brown	0-225-5-2015	0.1	0.4	1.2	6.5	30.3	2.730	2.765	1.294	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
GLENMORE 55-05-013-QRY Created On: 01/04/18 Updated On:	Q		NE	6	22N	21E	Brown	0-225-53-2018		1.1	1.8	6.4	30.0	2.725	2.755	1.090	
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
BROWN -- WI																	
GLENMORE 55-05-013-QRY Created On: 01/04/21 Updated On:	Q		NE	6	22N	21E	Brown	0-225-6-2021	1.6	1.6	2.9	6.0	38.7	2.672	2.721	1.807	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
GLENMORE 55-05-013-QRY Created On: 01/02/24 Updated On:	Q		NE	6	22N	21E	Brown	0-225-49-2024	20.7	16.5	6.0	13.7	43.6	2.513	2.597	3.370	
	Approved Use : OGBC, Base Aggregate																
GLENMORE 55-05-013-QRY Created On: 06/25/24 Updated On:	Q		NE	6	22N	21E	Brown	0-225-276-2024	0.2	2.7	3.0	9.3	36.6	2.684	2.731	1.729	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
HOBART QUARRY 55-05-008-QRY Created On: 04/01/16 Updated On:	Q	NE	NE	27	23N	19E	Brown	0-225-119-2016	0.5	5.0	11.3	6.1	26.0	2.739	2.772	1.181	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
HOBART QUARRY 55-05-008-QRY Created On: 04/13/17 Updated On:	Q	NE	NE	27	23N	19E	Brown	0-225-129-2017		7.9	11.1	5.6	24.0	2.759	2.790	1.100	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
HOBART QUARRY 55-05-008-QRY Created On: 03/18/20 Updated On:	Q	NE	NE	27	23N	19E	Brown	0-225-130-2020		20.2	15.7	9.6	27.0	2.733	2.767	1.247	
HOBART QUARRY 55-05-008-QRY Created On: 06/09/20 Updated On:	Q	NE	NE	27	23N	19E	Brown	0-225-190-2020		11.0	4.2	5.4	24.5	2.750	2.779	1.040	
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
BROWN -- WI																		
HOBART QUARRY 55-05-008-QRY Created On: 03/10/21 Updated On:	Q	NE	NE	27	23N	19E	Brown	0-225-134-2021	0.0	1.1	1.0	4.9	22.5	2.791	2.805	0.492		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
HOBART QUARRY 55-05-008-QRY Created On: 01/04/22 Updated On:	Q	NE	NE	27	23N	19E	Brown	0-225-69-2022	0.0	29.3	16.4	5.9	26.6	2.732	2.766	1.248		
HOBART QUARRY 55-05-008-QRY Created On: 02/17/22 Updated On:	Q	NE	NE	27	23N	19E	Brown	0-225-128-2022	0.1	2.1	5.3	4.7	22.5	2.770	2.792	0.811		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
HOBART QUARRY 55-05-008-QRY Created On: 03/21/23 Updated On:	Q	NE	NE	27	23N	19E	Brown	0-225-173-2023	0.0	1.1	0.4	5.3	22.7	2.769	2.789	0.707		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
HOBART QUARRY 55-05-008-QRY Created On: 01/02/24 Updated On:	Q	NE	NE	27	23N	19E	Brown	0-225-14-2024	0.0	2.7	0.4	6.2	27.0	2.765	2.788	0.836		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
HOBART QUARRY 55-05-008-QRY Created On: 01/14/25 Updated On:	Q	NE	NE	27	23N	19E	Brown	0-225-121-2025	0.1	3.7	0.2	5.1	21.7	2.784	2.804	0.726		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
LAWRENCE 55-05-015-QRY Created On: 01/08/16 Updated On:	Q	SW	SW	30	23N	20E	Brown	0-225-46-2016	0.1	12.6	5.1	6.2	26.6	2.725	2.762	1.360		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse					
	P/Q	Qrt	Qrt	Sect	Town	Range	County	LA Wear (%)					Sp. Gravity		Absorp. %			
								100					500	OD	SSD	Crse	Fine	
BROWN -- WI																		
LAWRENCE 55-05-015-QRY Created On: 01/05/17 Updated On:	Q	SW	SW	30	23N	20E	Brown	0-225-36-2017	0.2	22.6	18.9	8.3	29.1	2.740	2.774	1.237		
LAWRENCE 55-05-015-QRY Created On: 03/22/17 Updated On:	Q	SW	SW	30	23N	20E	Brown	0-225-84-2017		5.0	15.9	6.8	24.4	2.745	2.776	1.122		
	Approved Use : Base Aggregate																	
LAWRENCE 55-05-015-QRY Created On: 04/11/18 Updated On:	Q	SW	SW	30	23N	20E	Brown	0-225-167-2018	0.3	16.7	11.1	5.1	23.5	2.747	2.776	1.066		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
LAWRENCE 55-05-015-QRY Created On: 07/18/19 Updated On:	Q	SW	SW	30	23N	20E	Brown	0-225-239-2019	0.2	15.6	20.0	5.2	24.1	2.751	2.779	1.028		
LAWRENCE 55-05-015-QRY Created On: 06/09/20 Updated On:	Q	SW	SW	30	23N	20E	Brown	0-225-192-2020	0.2	8.2	4.0	5.0	21.8	2.778	2.801	0.853		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
LAWRENCE 55-05-015-QRY Created On: 01/10/22 Updated On:	Q	SW	SW	30	23N	20E	Brown	0-225-99-2022	0.6	3.4	4.6	5.0	22.0	2.752	2.779	0.979		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
LAWRENCE 55-05-015-QRY Created On: 01/03/23 Updated On:	Q	SW	SW	30	23N	20E	Brown	0-225-45-2023	0.4	6.2	3.8	6.4	25.9	2.723	2.759	1.313		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
BROWN -- WI																		
ROCKLAND QUARRY 55-05-023-QRY Created On: 02/03/17 Updated On:	Q	SE	NE	12	22N	20E	Brown	0-225-61-2017	1.8	5.0	5.6	9.1	33.6	2.680	2.731	1.897		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
ROCKLAND QUARRY 55-05-023-QRY Created On: 01/02/20 Updated On:	Q	SE	NE	12	22N	20E	Brown	0-225-4-2020	0.5	1.9	0.7	5.6	26.9	2.735	2.767	1.163		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
ROCKLAND QUARRY 55-05-023-QRY Created On: 01/03/23 Updated On:	Q	SE	NE	12	22N	20E	Brown	0-225-75-2023	1.5	1.5	1.5	6.3	28.1	2.709	2.747	1.416		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
SCOTT 55-05-027-QRY Created On: 01/02/24 Updated On:	Q	NW	NE	18	24N	22E	Brown	0-225-9-2024	0.2	1.2	0.3	5.4	23.1	2.713	2.751	1.408		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
SCRAY HILL QUARRY 55-05-003-QRY Created On: 04/05/16 Updated On:	Q	S	NW	5	22N	21E	Brown	0-225-122-2016	3.0	1.4	1.2	6.3	28.9	2.703	2.749	1.717		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
SCRAY HILL QUARRY 55-05-003-QRY Created On: 04/19/19 Updated On:	Q	S	NW	5	22N	21E	Brown	0-225-149-2019	2.0	1.1	2.9	6.2	27.4	2.709	2.748	1.437		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
SCRAY HILL QUARRY 55-05-003-QRY Created On: 01/04/22 Updated On:	Q	S	NW	5	22N	21E	Brown	0-225-72-2022	6.3	10.3	3.4	7.5	29.1	2.656	2.704	1.797		
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
BROWN -- WI																	
SCRAY HILL QUARRY 55-05-003-QRY Created On: 01/30/25 Updated On:	Q	S	NW	5	22N	21E	Brown	0-225-144-2025	6.3	5.3	4.1	7.8	31.2	2.677	2.725	1.777	
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																
*TORDEUR 55-05-024-QRY Created On: 01/05/15 Updated On:	Q			18	24N	22E	Brown	0-225-1-2015	0.3	1.3	2.3	5.8	27.2	2.729	2.764	1.285	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
*TORDEUR 55-05-024-QRY Created On: 01/04/18 Updated On:	Q			18	24N	22E	Brown	0-225-52-2018		2.6	2.8	7.2	33.5	2.708	2.748	1.490	
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																
*TORDEUR 55-05-024-QRY Created On: 01/04/21 Updated On:	Q			18	24N	22E	Brown	0-225-8-2021	0.3	0.9	1.5	5.2	24.6	2.703	2.742	1.446	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
BUFFALO -- WI																	
BORK 55-06-005-QRY Created On: 09/09/16 Updated On:	Q	NW	NE	30	19N	10W	Buffalo	0-225-253-2016		0.0	5.3	8.8	32.6	2.627	2.678	1.932	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
BORK 55-06-005-QRY Created On: 01/08/19 Updated On:	Q	NW	NE	30	19N	10W	Buffalo	0-225-78-2019	0.8	0.0	2.9	10.1	35.8	2.610	2.667	2.156	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
BORK 55-06-005-QRY Created On: 01/04/22 Updated On:	Q	NW	NE	30	19N	10W	Buffalo	0-225-11-2022	0.3	2.4	4.8	9.1	35.3	2.648	2.694	1.717	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
BUFFALO -- WI																		
BORK 55-06-005-QRY Created On: 01/02/25 Updated On:	Q	NW	NE	30	19N	10W	Buffalo	0-225-49-2025	0.7	2.3	5.7	12.0	43.8	2.573	2.642	2.661		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
*BRAGGER 55-06-006-QRY Created On: 04/21/17 Updated On:	Q	W	NW	13	22N	10W	Buffalo	0-225-141-2017	0.4	0.0	7.5	10.3	41.1	2.571	2.646	2.915		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
*BRAGGER 55-06-006-QRY Created On: 06/18/20 Updated On:	Q	W	NW	13	22N	10W	Buffalo	0-225-196-2020	0.0	0.0	5.6	10.2	39.6	2.566	2.641	2.936		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
*BROMMER 55-06-008-QRY Created On: 06/13/16 Updated On:	Q	SW	NE	30	23N	12W	Buffalo	0-225-203-2016		0.0	4.8	8.8	34.7	2.568	2.637	2.681		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
*BROMMER 55-06-008-QRY Created On: 01/05/21 Updated On:	Q	SW	NE	30	23N	12W	Buffalo	0-225-71-2021	2.4	0.0	0.9	8.5	34.4	2.592	2.656	2.470		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
FELTES 55-06-010-QRY Created On: 04/23/15 Updated On:	Q	NE	SE	6	20N	10W	Buffalo	0-225-135-2015		0.0	2.3	10.9	38.7	2.613	2.670	2.180		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
FELTES 55-06-010-QRY Created On: 01/04/18 Updated On:	Q	NE	SE	6	20N	10W	Buffalo	0-225-46-2018	0.7	0.0	1.7	9.2	34.6	2.612	2.672	2.320		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
BUFFALO -- WI																	
FELTES 55-06-010-QRY Created On: 04/17/23 Updated On:	Q	NE	SE	6	20N	10W	Buffalo	0-225-197-2023		0.0	5.2	11.3	41.9	2.613	2.672	2.283	
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																
FELTES 55-06-010-QRY Created On: 05/22/23 Updated On:	Q	NE	SE	6	20N	10W	Buffalo	0-225-219-2023	0.2	0.0	2.9	7.4	33.6	2.647	2.697	1.875	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
*HUBER 55-06-011-QRY Created On: 05/09/16 Updated On:	Q	SE	SE	4	22N	12W	Buffalo	0-225-165-2016		0.0	11.6	13.0	41.2	2.562	2.635	2.833	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
*HUBER 55-06-011-QRY Created On: 08/25/17 Updated On:	Q	SE	SE	4	22N	12W	Buffalo	0-225-263-2017		0.0	3.7	11.2	41.8	2.561	2.640	3.067	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
*HUBER 55-06-011-QRY Created On: 01/06/20 Updated On:	Q	SE	SE	4	22N	12W	Buffalo	0-225-26-2020	0.5	0.0	6.6	11.2	42.0	2.567	2.641	2.888	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
MARSOLEK 55-06-014-QRY Created On: 06/30/16 Updated On:	Q	NW	SE	36	23N	10W	Buffalo	0-225-213-2016		0.0	3.5	8.1	33.4	2.572	2.641	2.694	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
MARSOLEK 55-06-014-QRY Created On: 01/04/19 Updated On:	Q	NW	SE	36	23N	10W	Buffalo	0-225-29-2019	0.9	0.0	7.6	11.5	40.5	2.541	2.623	3.258	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
BUFFALO -- WI																		
MARSOLEK 55-06-014-QRY Created On: 01/04/22 Updated On:	Q	NW	SE	36	23N	10W	Buffalo	0-225-76-2022	4.6	0.0	11.6	12.2	44.5	2.540	2.623	3.280		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MARSOLEK 55-06-014-QRY Created On: 01/02/25 Updated On:	Q	NW	SE	36	23N	10W	Buffalo	0-225-19-2025	1.4	2.7	5.8	8.9	38.9	2.544	2.621	3.058		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MILESTONE-MONDOVI-BUCK RIDGE 55-06-016-QRY Created On: 01/05/17 Updated On:	Q	N	SE	28	24N	11W	Buffalo	0-225-46-2017	0.6	0.0	3.3	8.7	38.7	2.580	2.643	2.445		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
MILESTONE-MONDOVI-BUCK RIDGE 55-06-016-QRY Created On: 06/18/20 Updated On:	Q	N	SE	28	24N	11W	Buffalo	0-225-197-2020	0.6	0.0	6.6	13.3	48.2	2.533	2.615	3.220		
	Approved Use : HMA<MT, CONCRETE, OGBC, Base Aggregate																	
MILESTONE-MONDOVI-BUCK RIDGE 55-06-016-QRY Created On: 01/04/22 Updated On:	Q	N	SE	28	24N	11W	Buffalo	0-225-74-2022	0.6	0.0	40.6	14.7	50.3	2.537	2.622	3.360		
MILESTONE-MONDOVI-BUCK RIDGE 55-06-016-QRY Created On: 08/17/22 Updated On:	Q	N	SE	28	24N	11W	Buffalo	0-225-251-2022	0.1	7.8	12.6	15.3	49.4	2.594	2.660	2.567		
	Approved Use : Base Aggregate																	
MILESTONE-MONDOVI-BUCK RIDGE 55-06-016-QRY Created On: 01/02/25 Updated On:	Q	N	SE	28	24N	11W	Buffalo	0-225-20-2025	0.2	3.9	6.1	12.1	45.2	2.560	2.638	3.030		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
BUFFALO -- WI																	
*O'NEIL 55-06-017-QRY Created On: 05/04/17 Updated On:	Q	SE	NW	36	24N	11W	Buffalo	0-225-167-2017		0.0	14.3	14.1	47.8	2.548	2.639	3.583	
	Approved Use : Base Aggregate																
*O'NEIL 55-06-017-QRY Created On: 01/06/20 Updated On:	Q	SE	NW	36	24N	11W	Buffalo	0-225-28-2020	0.2	0.0	12.8	14.9	46.1	2.553	2.637	3.312	
	Approved Use : Base Aggregate																
RATZ 55-06-020-QRY Created On: 04/23/15 Updated On:	Q	SW	SW	12	20N	11W	Buffalo	0-225-134-2015		0.0	3.2	11.9	41.4	2.595	2.659	2.438	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
RATZ 55-06-020-QRY Created On: 01/04/18 Updated On:	Q	SW	SW	12	20N	11W	Buffalo	0-225-47-2018	0.3	0.0	0.9	9.0	35.1	2.609	2.668	2.269	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
RATZ 55-06-020-QRY Created On: 01/04/21 Updated On:	Q	SW	SW	12	20N	11W	Buffalo	0-225-39-2021	0.9	0.0	0.4	7.8	33.7	2.590	2.650	2.320	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
RATZ 55-06-020-QRY Created On: 01/02/24 Updated On:	Q	SW	SW	12	20N	11W	Buffalo	0-225-117-2024	0.3	3.5	4.3	10.1	39.3	2.607	2.667	2.313	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
*STRAND 55-06-023-QRY Created On: 10/07/20 Updated On:	Q		NE	28	23N	13W	Buffalo	0-225-244-2020	0.3	0.0	12.5	10.3	41.8	2.563	2.655	3.608	
	Approved Use : Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	Sp. Gravity		Absorp. %	
														OD	SSD	Crse	Fine
BUFFALO -- WI																	
WENDERS 55-06-028-QRY Created On: 05/09/16 Updated On:	Q			10	20N	12W	Buffalo	0-225-163-2016		0.0	11.8	13.7	40.7	2.599	2.660	2.318	
Approved Use : CONCRETE, Base Aggregate																	
WENDERS 55-06-028-QRY Created On: 01/08/19 Updated On:	Q			10	20N	12W	Buffalo	0-225-80-2019	0.7	0.0	2.6	8.8	32.6	2.644	2.691	1.770	
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
WENDERS 55-06-028-QRY Created On: 01/04/22 Updated On:	Q			10	20N	12W	Buffalo	0-225-9-2022	0.1	1.7	4.7	9.4	37.1	2.630	2.683	2.015	
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
WENDERS 55-06-028-QRY Created On: 01/02/25 Updated On:	Q			10	20N	12W	Buffalo	0-225-47-2025	0.6	2.1	2.7	8.8	36.2	2.622	2.677	2.083	
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
BURNETT -- WI																	
MILESTONE-DON JOHNSON 55-07-006-PIT Created On: 01/05/16 Updated On:	P	E	SW	21	39N	17W	Burnett	0-225-26-2016		0.0	6.6	3.8	16.9	2.739	2.771	1.148	
Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
MILESTONE-DON JOHNSON 55-07-006-PIT Created On: 10/12/21 Updated On:	P	E	SW	21	39N	17W	Burnett	0-225-267-2021	0.8	3.0	3.7	3.8	16.9	2.778	2.804	0.927	
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MILESTONE-DON JOHNSON 55-07-006-PIT Created On: 01/04/24 Updated On:	P	E	SW	21	39N	17W	Burnett	0-225-144-2024	1.0	4.8	6.4	3.5	16.6	2.747	2.794	1.701	
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse		Absorp. %	
Source Name	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
BURNETT -- WI																	
SIREN	P	NE	SW	32	38N	16W	Burnett	0-225-128-2015		0.0	-7.4	5.1	20.2	2.703	2.740	1.347	
55-07-018-PIT	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
Created On: 04/17/15																	
Updated On:																	
SIREN	P	NE	SW	32	38N	16W	Burnett	0-225-164-2022	6.7	0.0	6.2	4.9	20.0	2.697	2.731	1.272	
55-07-018-PIT	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																
Created On: 04/05/22																	
Updated On:																	
CALUMET -- WI																	
HAYTON	Q		SW	28	18N	20E	Calumet	0-225-206-2016		0.0	1.7	9.5	39.8	2.727	2.757	1.092	
55-08-006-QRY	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
Created On: 06/21/16																	
Updated On:																	
HAYTON	Q		SW	28	18N	20E	Calumet	0-225-72-2019		0.7	0.8	7.8	33.5	2.764	2.787	0.817	
55-08-006-QRY	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
Created On: 01/08/19																	
Updated On:																	
HAYTON	Q		SW	28	18N	20E	Calumet	0-225-29-2022	0.0	0.0	0.5	8.7	36.7	2.758	2.783	0.903	
55-08-006-QRY	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
Created On: 01/04/22																	
Updated On:																	
HAYTON	Q		SW	28	18N	20E	Calumet	0-225-165-2024	0.0	0.6	1.3	8.7	36.9	2.772	2.792	0.713	
55-08-006-QRY	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
Created On: 01/29/24																	
Updated On:																	
JANNETTE CHILTON QUARRY	Q	SW	SW	20	18N	20E	Calumet	0-225-136-2024	0.1	0.0	0.4	5.4	25.3	2.791	2.806	0.552	
55-08-019-QRY	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
Created On: 01/04/24																	
Updated On:																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
CALUMET -- WI																		
KREPLINE 55-08-012-QRY Created On: 05/26/16 Updated On:	Q	NE	NE	34	19N	19E	Calumet	0-225-191-2016		0.0	2.8	8.3	35.1	2.689	2.727	1.415		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
KREPLINE 55-08-012-QRY Created On: 04/24/19 Updated On:	Q	NE	NE	34	19N	19E	Calumet	0-225-167-2019	0.1	0.0	0.5	13.1	49.1	2.671	2.706	1.319		
	Approved Use : HMA<MT, CONCRETE, Base Aggregate																	
KREPLINE 55-08-012-QRY Created On: 04/15/25 Updated On:	Q	NE	NE	34	19N	19E	Calumet	0-225-190-2025	0.0	0.0	1.4	13.4	50.3	2.658	2.697	1.482		
	Approved Use : HMA<MT, CONCRETE, OGBC, Base Aggregate																	
*MICHELS - BRILLION 55-08-014-QRY Created On: 01/07/15 Updated On:	Q		SW	24	20N	20E	Calumet	0-225-22-2015	0.4	0.0	2.6	9.8	39.9	2.627	2.680	2.009		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
*MICHELS - BRILLION 55-08-014-QRY Created On: 03/16/18 Updated On:	Q		SW	24	20N	20E	Calumet	0-225-124-2018		0.0	2.0	9.0	35.7	2.687	2.727	1.498		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
*MICHELS - BRILLION 55-08-014-QRY Created On: 01/05/21 Updated On:	Q		SW	24	20N	20E	Calumet	0-225-48-2021	0.8	0.0	1.2	8.0	34.5	2.661	2.711	1.903		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
*MICHELS BROWN 55-08-015-QRY Created On: 01/04/16 Updated On:	Q	S	SW	32	20N	19E	Calumet	0-225-7-2016	0.1	0.0	1.4	6.0	26.8	2.767	2.789	0.787		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
CALUMET -- WI																		
*MICHELS BROWN 55-08-015-QRY Created On: 01/04/19 Updated On:	Q	S	SW	32	20N	19E	Calumet	0-225-39-2019	0.7	0.0	3.6	8.1	32.6	2.743	2.774	1.131		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
*MICHELS BROWN 55-08-015-QRY Created On: 01/04/22 Updated On:	Q	S	SW	32	20N	19E	Calumet	0-225-32-2022	1.2	0.0	3.2	9.6	37.0	2.713	2.752	1.440		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
CHIPPEWA -- WI																		
29 PINES PIT 55-09-085-PIT Created On: 07/23/25 Updated On:	P	SE	SW	24	28N	10W	Chippewa	0-225-227-2025	1.0	0.0	9.8	8.2	28.0	2.623	2.665	1.591		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
CTH XX PIT 55-09-029-PIT Created On: 07/23/25 Updated On:	P	SW	SW	35	29N	7W	Chippewa	0-225-229-2025	0.2	0.0	0.5	5.2	23.3	2.704	2.720	0.587		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
DUSICK 55-09-024-PIT Created On: 05/17/22 Updated On:	P	SE	NW	17	29N	5W	Chippewa	0-225-205-2022	0.3	0.0	1.0	3.5	17.6	2.763	2.782	0.682		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
GULICH 55-09-079-PIT Created On: 01/30/20 Updated On:	P	NW	SE	10	32N	6W	Chippewa	0-225-101-2020	1.2	0.0	2.4	3.5	17.9	2.675	2.710	1.315		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
GULICH 55-09-079-PIT Created On: 01/16/25 Updated On:	P	NW	SE	10	32N	6W	Chippewa	0-225-134-2025	1.0	0.0	2.3	5.1	21.2	2.650	2.686	1.375		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
CHIPPEWA -- WI																		
HAAS 124 55-09-025-PIT Created On: 06/06/19 Updated On:	P	SE	SE	6	30N	8W	Chippewa	0-225-207-2019	7.8	0.0	3.5	5.3	21.6	2.659	2.687	1.060		
	Approved Use : HMA<MT, HMA>=MT, Base Aggregate																	
HAAS 124 55-09-025-PIT Created On: 06/04/20 Updated On:	P	SE	SE	6	30N	8W	Chippewa	0-225-186-2020	1.1	0.0	0.9	3.7	19.7	2.712	2.745	1.204		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
HAAS 124 55-09-025-PIT Created On: 01/02/25 Updated On:	P	SE	SE	6	30N	8W	Chippewa	0-225-13-2025	0.2	1.8	0.0	5.3	20.0	2.742	2.771	1.075		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
HAAS SPORTS PIT 55-09-081-PIT Created On: 07/27/23 Updated On:	P	NE	NW	25	31N	7W	Chippewa	0-225-241-2023	2.0	0.0	1.0	4.4	20.1	2.723	2.748	0.897		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
HILGER 55-09-031-PIT Created On: 01/08/19 Updated On:	P			8	30N	8W	Chippewa	0-225-75-2019	0.9	0.0	1.5	3.6	17.4	2.702	2.733	1.123		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
HILGER 55-09-031-PIT Created On: 01/02/24 Updated On:	P			8	30N	8W	Chippewa	0-225-84-2024	0.7	0.0	1.6	3.5	17.7	2.708	2.736	1.029		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
JENNEMAN 55-09-032-PIT Created On: 01/08/19 Updated On:	P		NE	6	30N	8W	Chippewa	0-225-77-2019	0.3	0.0	0.9	3.6	17.3	2.726	2.754	1.035		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
CHIPPEWA -- WI																		
JENNEMAN 55-09-032-PIT Created On: 01/02/24 Updated On:	P		NE	6	30N	8W	Chippewa	0-225-85-2024	0.7	0.0	2.0	4.2	20.1	2.708	2.733	0.929		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
LAGESSE 55-09-036-PIT Created On: 08/19/15 Updated On:	P	SE	SE	7	30N	8W	Chippewa	0-225-228-2015		0.0	0.7	4.5	20.3	2.739	2.761	0.799		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
LAGESSE 55-09-036-PIT Created On: 01/09/20 Updated On:	P	SE	SE	7	30N	8W	Chippewa	0-225-86-2020	0.7	0.0	0.9	3.7	17.9	2.717	2.745	1.050		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
LAGESSE 55-09-036-PIT Created On: 01/02/25 Updated On:	P	SE	SE	7	30N	8W	Chippewa	0-225-16-2025	0.7	1.8	2.2	3.4	17.4	2.693	2.724	1.183		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
LAWIN PIT 55-09-039-PIT Created On: 01/07/15 Updated On:	P		NE	18	30N	8W	Chippewa	0-225-12-2015		0.0	2.1	3.9	19.0	2.690	2.715	0.956		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
LAWIN PIT 55-09-039-PIT Created On: 01/08/19 Updated On:	P		NE	18	30N	8W	Chippewa	0-225-74-2019	2.8	0.0	1.9	3.8	19.9	2.706	2.734	1.029		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
LAWIN PIT 55-09-039-PIT Created On: 01/02/24 Updated On:	P		NE	18	30N	8W	Chippewa	0-225-83-2024	1.6	0.0	1.7	4.5	19.7	2.711	2.737	0.970		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
CHIPPEWA -- WI																		
LICHTS 55-09-080-PIT Created On: 04/02/20 Updated On:	P	SE	NW	23	29N	6W	Chippewa	0-225-144-2020	2.2	0.0	2.2	4.8	20.7	2.708	2.735	0.984		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
LICHTS 55-09-080-PIT Created On: 01/16/25 Updated On:	P	SE	NW	23	29N	6W	Chippewa	0-225-133-2025	1.5	0.0	4.5	6.1	22.1	2.705	2.738	1.219		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
*MAHR 55-09-041-PIT Created On: 01/12/15 Updated On:	P	SW	SW	26	29N	5W	Chippewa	0-225-56-2015		0.0	3.2	3.8	18.3	2.733	2.758	0.923		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
*MAHR 55-09-041-PIT Created On: 01/09/20 Updated On:	P	SW	SW	26	29N	5W	Chippewa	0-225-87-2020	1.0	0.0	4.8	5.0	21.7	2.704	2.736	1.183		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
*MAHR 55-09-041-PIT Created On: 01/09/20 Updated On:	P	SW	SW	26	29N	5W	Chippewa	0-225-89-2020	1.7	0.0	3.0	3.9	18.6	2.684	2.719	1.297		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MALLARD RD PIT 55-09-083-PIT Created On: 07/23/25 Updated On:	P	NW	SE	3	29N	8W	Chippewa	0-225-226-2025	0.9	0.0	1.2	5.2	23.0	2.700	2.726	0.978		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MILESTONE-CHARLES OLSEN 55-09-047-PIT Created On: 01/08/15 Updated On:	P	SW	NW	35	30N	8W	Chippewa	0-225-37-2015		0.0	3.3	3.9	17.9	2.704	2.735	1.139		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
CHIPPEWA -- WI																		
MILESTONE-CHARLES OLSEN 55-09-047-PIT Created On: 01/08/20 Updated On:	P	SW	NW	35	30N	8W	Chippewa	0-225-53-2020	1.4	0.0	0.0	4.6	19.6	2.727	2.756	1.068		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MILESTONE-CHARLES OLSEN 55-09-047-PIT Created On: 01/02/25 Updated On:	P	SW	NW	35	30N	8W	Chippewa	0-225-17-2025	1.7	3.0	3.1	3.8	18.2	2.717	2.750	1.216		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MOATS 55-09-044-PIT Created On: 03/08/18 Updated On:	P	SW	NE	15	29N	7W	Chippewa	0-225-114-2018	8.1	0.0	6.5	5.9	20.5	2.630	2.674	1.682		
	Approved Use : HMA<MT, HMA>=MT, Base Aggregate																	
MOATS 55-09-044-PIT Created On: 01/05/21 Updated On:	P	SW	NE	15	29N	7W	Chippewa	0-225-90-2021	2.6	0.0	2.3	5.0	21.7	2.677	2.712	1.298		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
*NELSON MINE 55-09-046-PIT Created On: 01/12/15 Updated On:	P	NW	NW	13	28N	9W	Chippewa	0-225-57-2015		0.0	3.7	5.0	21.5	2.627	2.657	1.113		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
*NELSON MINE 55-09-046-PIT Created On: 04/02/20 Updated On:	P	NW	NW	13	28N	9W	Chippewa	0-225-141-2020	1.5	0.0	1.2	5.1	20.8	2.721	2.739	0.692		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
*OLYNICK - BOHLS 55-09-049-PIT Created On: 06/08/15 Updated On:	P			16	29N	5W	Chippewa	0-225-192-2015		0.0	2.4	5.1	20.3	2.716	2.752	1.321		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
CHIPPEWA -- WI																		
*OLYNICK - BOHLS 55-09-049-PIT Created On: 04/02/20 Updated On:	P			16	29N	5W	Chippewa	0-225-142-2020		0.0	0.0	1.3	4.8	21.7	2.738	2.768	1.106	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
PETERSON 55-09-052-PIT Created On: 10/03/17 Updated On:	P	NE	SW	32	29N	5W	Chippewa	0-225-278-2017		0.0	0.9	4.0	19.1	2.685	2.720	1.273		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
PETERSON 55-09-052-PIT Created On: 01/04/22 Updated On:	P	NE	SW	32	29N	5W	Chippewa	0-225-83-2022		0.8	0.0	1.8	3.3	16.8	2.713	2.744	1.135	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
POTAPENKO 55-09-053-PIT Created On: 03/08/18 Updated On:	P	SE	SW	25	31N	5W	Chippewa	0-225-113-2018		3.3	0.0	1.4	3.9	21.1	2.655	2.691	1.380	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
POTAPENKO 55-09-053-PIT Created On: 01/10/23 Updated On:	P	SE	SW	25	31N	5W	Chippewa	0-225-118-2023		2.3	0.0	2.1	3.7	19.3	2.643	2.685	1.610	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
RANDY MAHR 55-09-055-PIT Created On: 01/07/15 Updated On:	P	NE	SW	23	29N	5W	Chippewa	0-225-10-2015		0.0	1.8	3.7	18.0	2.749	2.774	0.907		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
RANDY MAHR 55-09-055-PIT Created On: 01/05/21 Updated On:	P	NE	SW	23	29N	5W	Chippewa	0-225-92-2021		1.5	0.0	3.4	4.3	20.6	2.714	2.745	1.143	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
CHIPPEWA -- WI																		
ROMANOWSKI 55-09-058-PIT Created On: 04/21/17 Updated On:	P	NW	NE	36	31N	5W	Chippewa	0-225-147-2017		0.0	2.1	4.9	21.8	2.667	2.704	1.391		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
ROMANOWSKI 55-09-058-PIT Created On: 01/10/23 Updated On:	P	NW	NE	36	31N	5W	Chippewa	0-225-106-2023	4.1	0.0	2.3	3.8	19.4	2.662	2.693	1.166		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
SCHICK 55-09-060-PIT Created On: 04/21/17 Updated On:	P	SW	NW	2	29N	8W	Chippewa	0-225-143-2017		0.0	2.4	4.9	20.6	2.688	2.720	1.163		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
SCHICK 55-09-060-PIT Created On: 01/04/22 Updated On:	P	SW	NW	2	29N	8W	Chippewa	0-225-80-2022	1.2	0.0	3.2	4.3	20.8	2.688	2.715	1.025		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
SHAKAL VALLEY 55-09-063-PIT Created On: 03/21/19 Updated On:	P	NW	SW	23	29N	6W	Chippewa	0-225-110-2019	5.5	0.0	6.1	6.3	22.7	2.649	2.686	1.392		
	Approved Use : HMA<MT, HMA>=MT, Base Aggregate																	
SHAKAL VALLEY 55-09-063-PIT Created On: 01/02/24 Updated On:	P	NW	SW	23	29N	6W	Chippewa	0-225-118-2024	2.6	0.0	2.6	4.7	19.4	2.674	2.704	1.127		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
STELTER 124 PIT 55-09-065-PIT Created On: 05/02/19 Updated On:	P	SW	SW	5	30N	8W	Chippewa	0-225-176-2019	0.0	0.0	2.2	4.5	20.0	2.740	2.765	0.920		
	Approved Use : HMA<MT, HMA>=MT, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
CHIPPEWA -- WI																		
STELTER 124 PIT 55-09-065-PIT Created On: 09/19/24 Updated On:	P	SW	SW	5	30N	8W	Chippewa	0-225-309-2024		0.4	0.0	0.4	3.6	18.4	2.739	2.756	0.620	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
STELTER-MORNING WEST PIT 55-09-082-PIT Created On: 09/19/24 Updated On:	P	NE	NE	6	30N	8W	Chippewa	0-225-310-2024		0.0	0.0	1.2	4.0	19.5	2.754	2.773	0.720	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
VEUM 55-09-068-PIT Created On: 01/08/19 Updated On:	P	NE	NW	35	28N	10W	Chippewa	0-225-82-2019		4.2	0.0	6.7	7.1	26.8	2.593	2.631	1.450	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
VEUM 55-09-068-PIT Created On: 01/02/24 Updated On:	P	NE	NW	35	28N	10W	Chippewa	0-225-79-2024		3.2	0.0	4.6	5.4	22.7	2.677	2.707	1.123	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
WITT QUARRY 55-09-084-QRY Created On: 07/23/25 Updated On:	Q	NE	NE	1	28N	5W	Chippewa	0-225-228-2025		1.1	0.0	0.6	4.6	21.1	2.640	2.677	1.390	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
WOZNIAK 55-09-074-PIT Created On: 01/07/15 Updated On:	P	SW	NE	1	28N	5W	Chippewa	0-225-11-2015			0.0	1.8	3.6	17.8	2.658	2.689	1.169	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
WOZNIAK 55-09-074-QRY Created On: 07/23/15 Updated On:	Q	NW	SE	1	28N	5W	Chippewa	0-225-216-2015			0.0	5.3	5.2	21.3	2.977	3.001	0.808	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
CHIPPEWA -- WI																		
WOZNIAK 55-09-074-PIT Created On: 03/08/18 Updated On:	P	SW	NE	1	28N	5W	Chippewa	0-225-115-2018	0.5	0.0	3.1	3.9	17.4	2.909	2.935	0.866		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
WOZNIAK 55-09-074-PIT Created On: 01/05/21 Updated On:	P	SW	NE	1	28N	5W	Chippewa	0-225-91-2021	0.1	0.0	1.9	4.4	20.1	2.878	2.889	0.374		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
WOZNIAK 55-09-074-QRY Created On: 01/02/24 Updated On:	Q	NW	SE	1	28N	5W	Chippewa	0-225-82-2024	0.0	0.0	1.1	4.2	18.9	2.936	2.946	0.351		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
CLARK -- WI																		
EARL'S 55-10-005-QRY Created On: 03/24/16 Updated On:	Q	NE	NE	10	28N	4W	Clark	0-225-116-2016		0.0	2.3	5.4	22.3	2.819	2.833	0.495		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
EARL'S 55-10-005-QRY Created On: 01/08/19 Updated On:	Q	NE	NE	10	28N	4W	Clark	0-225-76-2019		0.0	1.5	4.7	21.8	2.824	2.835	0.380		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
EARL'S 55-10-005-QRY Created On: 05/17/22 Updated On:	Q	NE	NE	10	28N	4W	Clark	0-225-204-2022	0.0	0.0	0.3	3.7	18.2	2.777	2.786	0.322		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
EARL'S 55-10-005-QRY Created On: 01/16/25 Updated On:	Q	NE	NE	10	28N	4W	Clark	0-225-139-2025	0.1	0.0	2.0	4.5	18.9	2.739	2.756	0.598		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
CLARK -- WI																		
GAY 55-10-007-PIT Created On: 04/23/15 Updated On:	P	SE	SE	5	28N	2W	Clark	0-225-136-2015		0.0	1.4	4.1	19.4	2.670	2.698	1.050		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
GAY 55-10-007-PIT Created On: 01/04/23 Updated On:	P	SE	SE	5	28N	2W	Clark	0-225-96-2023	4.3	0.0	6.2	5.1	22.3	2.597	2.645	1.837		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
GOETZ 55-10-039-QRY Created On: 05/17/22 Updated On:	Q	NW	NE	26	24N	2W	Clark	0-225-200-2022	0.5	0.0	0.6	4.0	19.1	2.684	2.694	0.384		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
GOETZ 55-10-039-QRY Created On: 01/16/25 Updated On:	Q	NW	NE	26	24N	2W	Clark	0-225-140-2025	0.3	0.0	1.6	3.2	15.3	2.657	2.677	0.729		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
HUNZICKER 55-10-010-QRY Created On: 07/19/21 Updated On:	Q	SE	NE	16	26N	2W	Clark	0-225-245-2021	0.0	0.0	1.1	7.2	31.3	2.597	2.617	0.772		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
HUNZICKER 55-10-010-QRY Created On: 01/29/24 Updated On:	Q	SE	NE	16	26N	2W	Clark	0-225-162-2024	0.0	1.8	1.2	5.4	25.6	2.594	2.614	0.800		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
ISENBERGER 55-10-011-QRY Created On: 09/28/16 Updated On:	Q	SW	NW	6	28N	4W	Clark	0-225-265-2016		0.0	1.0	4.3	18.6	3.015	3.026	0.342		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
CLARK -- WI																		
ISENBERGER 55-10-011-QRY Created On: 01/08/19 Updated On:	Q	SW	NW	6	28N	4W	Clark	0-225-79-2019		0.0	0.6	3.1	14.9	3.038	3.046	0.289		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
ISENBERGER 55-10-011-QRY Created On: 01/04/22 Updated On:	Q	SW	NW	6	28N	4W	Clark	0-225-82-2022	0.0	0.0	2.0	3.9	17.7	2.785	2.797	0.442		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
ISENBERGER 55-10-011-QRY Created On: 01/16/25 Updated On:	Q	SW	NW	6	28N	4W	Clark	0-225-137-2025	0.0	0.0	2.7	4.6	17.6	2.758	2.778	0.703		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
LONGBRANCH 55-10-015-QRY Created On: 01/29/15 Updated On:	Q	N	SW	34	29N	4W	Clark	0-225-75-2015	0.0	0.9	3.2	14.3	2.720	2.740	0.731			
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
LONGBRANCH 55-10-015-QRY Created On: 03/08/18 Updated On:	Q	N	SW	34	29N	4W	Clark	0-225-112-2018	0.0	0.5	2.6	13.4	2.751	2.764	0.489			
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
LONGBRANCH 55-10-015-QRY Created On: 01/05/21 Updated On:	Q	N	SW	34	29N	4W	Clark	0-225-89-2021	0.3	0.0	0.8	3.4	16.0	2.742	2.755	0.472		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
LONGBRANCH 55-10-015-QRY Created On: 01/02/24 Updated On:	Q	N	SW	34	29N	4W	Clark	0-225-86-2024	0.1	0.0	1.1	3.3	16.2	2.756	2.769	0.465		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
CLARK -- WI																		
MERRILLAN-734 55-10-018-QRY Created On: 07/02/15 Updated On:	Q	NW	SW	13	23N	3W	Clark	0-225-203-2015		0.0	0.5	2.5	15.8	2.635	2.646	0.435		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
MERRILLAN-734 55-10-018-QRY Created On: 01/03/18 Updated On:	Q	NW	SW	13	23N	3W	Clark	0-225-37-2018		0.0	0.4	3.7	20.1	2.622	2.634	0.432		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MERRILLAN-734 55-10-018-QRY Created On: 01/04/21 Updated On:	Q	NW	SW	13	23N	3W	Clark	0-225-19-2021	0.0	0.3	0.4	3.3	16.5	2.694	2.705	0.424		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MERRILLAN-734 55-10-018-QRY Created On: 01/02/24 Updated On:	Q	NW	SW	13	23N	3W	Clark	0-225-110-2024	1.0	3.2	2.2	3.9	19.8	2.658	2.692	1.268		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MERRILLAN-734 55-10-018-QRY Created On: 01/02/24 Updated On:	Q	NW	SW	13	23N	3W	Clark	0-225-111-2024	0.0	0.6	0.6	4.2	19.1	2.705	2.725	0.754		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MILAS 55-10-020-PIT Created On: 03/08/18 Updated On:	P	SE	NW	3	29N	3W	Clark	0-225-116-2018	1.4	0.0	2.5	4.3	19.4	2.686	2.713	1.011		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
MILAS 55-10-020-PIT Created On: 01/04/23 Updated On:	P	SE	NW	3	29N	3W	Clark	0-225-98-2023	1.2	0.0	2.8	3.6	18.0	2.733	2.759	0.969		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
CLARK -- WI																		
NAEDLER 55-10-021-QRY Created On: 06/12/17 Updated On:	Q	SE	NE	35	25N	1W	Clark	0-225-210-2017		0.0	2.2	4.9	23.9	2.632	2.647	0.562		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
NAEDLER 55-10-021-QRY Created On: 01/08/20 Updated On:	Q	SE	NE	35	25N	1W	Clark	0-225-57-2020	0.2	0.0	0.8	5.5	25.2	2.632	2.648	0.598		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
NAEDLER 55-10-021-QRY Created On: 01/03/23 Updated On:	Q	SE	NE	35	25N	1W	Clark	0-225-39-2023	0.3	2.9	3.1	6.4	27.9	2.614	2.634	0.783		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
NEILLSVILLE 55-10-035-QRY Created On: 06/12/17 Updated On:	Q	SE	SW	10	24N	2W	Clark	0-225-208-2017		0.0	0.4	4.7	22.5	2.598	2.611	0.494		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
NEILLSVILLE 55-10-035-QRY Created On: 01/08/20 Updated On:	Q	SE	SW	10	24N	2W	Clark	0-225-61-2020	0.4	0.0	1.5	5.0	23.1	2.609	2.624	0.537		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
NEILLSVILLE 55-10-035-QRY Created On: 01/02/24 Updated On:	Q	SE	SW	10	24N	2W	Clark	0-225-109-2024	1.2	0.4	1.4	5.2	22.9	2.585	2.605	0.767		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
*NERDRUM 55-10-038-PIT Created On: 10/05/20 Updated On:	P	SE	NW	15	29N	2W	Clark	0-225-243-2020	1.5	0.0	1.2	4.9	21.9	2.684	2.717	1.228		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
CLARK -- WI																		
OPELT PIT 55-10-023-PIT Created On: 04/25/17 Updated On:	P	NE	NW	8	23N	2W	Clark	0-225-149-2017		0.0	1.1	3.9	18.9	2.709	2.734	0.920		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
OPELT PIT 55-10-023-PIT Created On: 04/05/22 Updated On:	P	NE	NW	8	23N	2W	Clark	0-225-158-2022	2.0	0.0	0.9	3.9	19.6	2.674	2.703	1.085		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
OPELT QUARRY 55-10-024-QRY Created On: 04/25/17 Updated On:	Q	NE	NW	8	23N	2W	Clark	0-225-148-2017		0.0	0.2	4.2	18.0	2.829	2.839	0.354		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
OPELT QUARRY 55-10-024-QRY Created On: 05/04/20 Updated On:	Q	NE	NW	8	23N	2W	Clark	0-225-164-2020	0.0	0.0	0.4	4.4	21.7	2.745	2.753	0.314		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
OPELT QUARRY 55-10-024-QRY Created On: 01/03/23 Updated On:	Q	NE	NW	8	23N	2W	Clark	0-225-35-2023	0.0	0.2	0.3	3.7	17.6	2.851	2.865	0.492		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
OWEN AVENUE QUARRY 55-10-040-QRY Created On: 08/28/24 Updated On:	Q	SW	SW	31	27N	1W	Clark	0-225-305-2024	0.4	0.0	1.1	6.1	29.9	2.621	2.635	0.549		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
PAUL BUGAR "B" 55-10-026-QRY Created On: 05/21/15 Updated On:	Q	SE	NE	26	25N	1W	Clark	0-225-178-2015		0.0	0.3	6.9	30.5	2.620	2.642	0.831		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
CLARK -- WI																		
PAUL BUGAR "B" 55-10-026-QRY Created On: 04/25/18 Updated On:	Q	SE	NE	26	25N	1W	Clark	0-225-185-2018	0.4	0.0	0.3	5.3	26.4	2.641	2.656	0.597		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
PAUL BUGAR "B" 55-10-026-QRY Created On: 06/17/21 Updated On:	Q	SE	NE	26	25N	1W	Clark	0-225-226-2021	0.1	0.0	2.1	7.2	30.6	2.605	2.626	0.803		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
PAUL BUGAR "B" 55-10-026-QRY Created On: 02/28/24 Updated On:	Q	SE	NE	26	25N	1W	Clark	0-225-192-2024	0.5	0.0	0.5	7.2	32.6	2.615	2.628	0.490		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
PINE VALLEY 55-10-027-QRY Created On: 05/07/15 Updated On:	Q		NW	21	24N	2W	Clark	0-225-152-2015		0.0	0.8	5.9	25.6	2.608	2.621	0.498		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
PINE VALLEY 55-10-027-QRY Created On: 04/19/18 Updated On:	Q		NW	21	24N	2W	Clark	0-225-174-2018	0.8	0.0	1.5	6.7	28.0	2.571	2.596	0.973		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
PINE VALLEY 55-10-027-QRY Created On: 04/08/21 Updated On:	Q		NW	21	24N	2W	Clark	0-225-174-2021	2.4	1.1	3.3	8.8	32.2	2.548	2.579	1.207		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
PINE VALLEY 55-10-027-QRY Created On: 01/29/24 Updated On:	Q		NW	21	24N	2W	Clark	0-225-163-2024	1.0	1.4	0.8	4.1	21.0	2.598	2.613	0.582		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
CLARK -- WI																		
*PRIBBERNOW 55-10-032-QRY Created On: 01/03/17 Updated On:	Q	E	E	13	28N	2W	Clark	0-225-5-2017		0.0	0.8	4.6	21.0	2.626	2.647	0.784		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
*PRIBBERNOW 55-10-032-QRY Created On: 01/07/20 Updated On:	Q	E	E	13	28N	2W	Clark	0-225-41-2020	0.0	0.0	0.6	4.4	19.9	2.707	2.716	0.361		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
REIFF QUARRY 55-10-041-QRY Created On: 01/16/25 Updated On:	Q	NW	NE	22	27N	2W	Clark	0-225-141-2025	0.0	0.0	1.4	4.7	19.7	2.834	2.852	0.646		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
COLUMBIA -- WI																		
ARLINGTON 55-11-002-PIT Created On: 05/04/17 Updated On:	P			23	10N	9E	Columbia	0-225-166-2017	2.4	0.0	4.2	5.7	26.4	2.674	2.724	1.863		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
ARLINGTON 55-11-002-PIT Created On: 06/01/22 Updated On:	P			23	10N	9E	Columbia	0-225-210-2022	1.7	0.0	4.8	5.4	26.5	2.705	2.746	1.502		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
BALLWEG 55-11-003-QRY Created On: 01/21/16 Updated On:	Q		SE	25	10N	7E	Columbia	0-225-63-2016	0.8	1.1	1.0	7.2	30.7	2.590	2.656	2.547		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
BALLWEG 55-11-003-QRY Created On: 04/01/19 Updated On:	Q		SE	25	10N	7E	Columbia	0-225-119-2019	0.9	3.4	5.8	8.7	33.7	2.615	2.669	2.090		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
COLUMBIA -- WI																	
BALLWEG 55-11-003-QRY Created On: 01/04/22 Updated On:	Q		SE	25	10N	7E	Columbia	0-225-57-2022	0.8	1.3	3.0	7.7	30.0	2.618	2.672	2.065	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
BALLWEG 55-11-003-QRY Created On: 02/07/25 Updated On:	Q		SE	25	10N	7E	Columbia	0-225-150-2025	0.1	1.6	2.8	7.4	30.9	2.609	2.670	2.326	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
BECKER 55-11-004-PIT Created On: 01/07/16 Updated On:	P		SW	34	13N	10E	Columbia	0-225-42-2016		0.0	2.0	6.8	29.1	2.658	2.707	1.856	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
BECKER 55-11-004-PIT Created On: 01/05/21 Updated On:	P		SW	34	13N	10E	Columbia	0-225-79-2021	0.0	2.9	2.9	5.6	26.3	2.686	2.732	1.714	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
BLAU (LYCON) 55-11-006-PIT Created On: 01/20/17 Updated On:	P	NE	NW	2	11N	8E	Columbia	0-225-54-2017	1.4	0.0	2.6	7.1	30.0	2.674	2.708	1.266	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
BLAU (LYCON) 55-11-006-PIT Created On: 01/04/22 Updated On:	P	NE	NW	2	11N	8E	Columbia	0-225-42-2022	1.2	0.0	2.8	6.3	28.7	2.692	2.725	1.213	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
BROWN 55-11-010-PIT Created On: 01/03/18 Updated On:	P	NW	SW	18	12N	10E	Columbia	0-225-25-2018	0.3	5.0	1.3	9.8	31.8	2.666	2.718	1.932	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
COLUMBIA -- WI																		
BROWN 55-11-010-PIT Created On: 01/04/23 Updated On:	P	NW	SW	18	12N	10E	Columbia	0-225-93-2023	0.4	0.0	1.8	6.9	30.3	2.691	2.732	1.523		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
ERVIN STIEMKE 55-11-013-QRY Created On: 01/05/17 Updated On:	Q	NW	SW	18	10N	10E	Columbia	0-225-49-2017	1.3	2.5	2.5	11.3	35.5	2.549	2.614	2.559		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
ERVIN STIEMKE 55-11-013-QRY Created On: 01/08/20 Updated On:	Q	NW	SW	18	10N	10E	Columbia	0-225-68-2020	0.1	1.3	3.2	7.9	31.2	2.598	2.658	2.286		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
ERVIN STIEMKE 55-11-013-QRY Created On: 04/04/23 Updated On:	Q	NW	SW	18	10N	10E	Columbia	0-225-177-2023	0.6	1.2	2.2	7.3	29.8	2.556	2.631	2.952		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
ERVIN STIEMKE 55-11-013-QRY Created On: 04/18/24 Updated On:	Q	NW	SW	18	10N	10E	Columbia	0-225-234-2024	0.3	1.1	2.4	7.8	32.9	2.564	2.634	2.741		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
HAHN 55-11-014-QRY Created On: 01/05/17 Updated On:	Q	NW	SE	11	12N	11E	Columbia	0-225-48-2017	0.9	2.6	1.6	13.7	38.3	2.548	2.625	3.010		
	Approved Use : CONCRETE, OGBC, Base Aggregate																	
HAHN 55-11-014-QRY Created On: 01/08/20 Updated On:	Q	NW	SE	11	12N	11E	Columbia	0-225-69-2020	0.7	4.8	8.0	10.0	41.1	2.549	2.625	2.962		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
COLUMBIA -- WI																		
HAHN 55-11-014-QRY Created On: 01/04/23 Updated On:	Q	NW	SE	11	12N	11E	Columbia	0-225-94-2023	0.9	4.9	5.5	11.3	43.4	2.531	2.614	3.289		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
HARTMANN QUARRY 55-11-041-QRY Created On: 01/02/24 Updated On:	Q	NE	NE	36	10N	7E	Columbia	0-225-43-2024	1.6	2.9	9.7	9.0	34.8	2.566	2.633	2.631		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
HOLDER PIT 55-11-017-PIT Created On: 01/03/17 Updated On:	P	NW	SE	30	12N	11E	Columbia	0-225-7-2017	6.6	0.0	7.8	11.5	37.8	2.625	2.680	2.079		
	Approved Use : HMA<E-3, HMA>=E-3, OGBC, Base Aggregate																	
HOLDER PIT 55-11-017-PIT Created On: 01/04/22 Updated On:	P	NW	SE	30	12N	11E	Columbia	0-225-5-2022	6.6	0.0	9.7	11.0	37.6	2.638	2.687	1.882		
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																	
JENKINS 55-11-018-QRY Created On: 05/11/17 Updated On:	Q			11	13N	10E	Columbia	0-225-184-2017		0.9	2.5	11.1	39.9	2.599	2.663	2.473		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
JENKINS 55-11-018-QRY Created On: 01/06/20 Updated On:	Q			11	13N	10E	Columbia	0-225-34-2020	0.2	0.9	2.7	9.9	38.8	2.602	2.663	2.366		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
JENKINS 55-11-018-QRY Created On: 01/03/23 Updated On:	Q			11	13N	10E	Columbia	0-225-69-2023	0.2	1.3	1.8	10.3	38.1	2.607	2.662	2.126		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
COLUMBIA -- WI																		
KETTLESON 55-11-041-PIT Created On: 05/02/17 Updated On:	P	NW	NE	6	13N	7E	Columbia	0-225-163-2017		0.0	3.7	9.4	33.1	2.770	2.803	1.191		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
KETTLESON 55-11-041-PIT Created On: 01/04/22 Updated On:	P	NW	NE	6	13N	7E	Columbia	0-225-12-2022	0.5	0.0	1.5	6.4	27.6	2.773	2.803	1.093		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
KOHN 55-11-019-PIT Created On: 05/03/22 Updated On:	P			30	12N	11E	Columbia	0-225-193-2022	2.7	4.5	3.6	5.9	27.9	2.717	2.754	1.376		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
LINCK #27 55-11-026-QRY Created On: 01/29/15 Updated On:	Q	SW	SW	24	10N	12E	Columbia	0-225-77-2015	0.3	1.4	3.6	5.6	22.9	2.622	2.673	1.954		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
LINCK #27 55-11-026-QRY Created On: 03/01/18 Updated On:	Q	SW	SW	24	10N	12E	Columbia	0-225-108-2018	0.3	3.2	2.5	8.3	35.0	2.577	2.657	3.087		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
LINCK #27 55-11-026-QRY Created On: 03/29/21 Updated On:	Q	SW	SW	24	10N	12E	Columbia	0-225-164-2021	5.0	14.3	1.2	10.5	38.5	2.587	2.654	2.563		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
LINCK #27 55-11-026-QRY Created On: 05/02/24 Updated On:	Q	SW	SW	24	10N	12E	Columbia	0-225-248-2024	4.0	4.6	2.0	9.3	37.0	2.585	2.648	2.432		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
COLUMBIA -- WI																		
MICHELS COLUMBUS 55-11-028-QRY Created On: 01/03/17 Updated On:	Q			11	10N	12E	Columbia	0-225-9-2017	1.9	7.8	7.5	9.8	38.7	2.584	2.647	2.440		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
MICHELS COLUMBUS 55-11-028-QRY Created On: 03/09/20 Updated On:	Q			11	10N	12E	Columbia	0-225-124-2020	2.9	15.0	7.8	10.1	41.5	2.598	2.664	2.568		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MICHELS COLUMBUS 55-11-028-QRY Created On: 01/04/22 Updated On:	Q			11	10N	12E	Columbia	0-225-4-2022	2.7	6.5	9.5	10.0	40.5	2.542	2.616	2.925		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MICHELS COLUMBUS 55-11-028-QRY Created On: 01/02/25 Updated On:	Q			11	10N	12E	Columbia	0-225-24-2025	0.1	10.6	10.5	8.7	37.0	2.582	2.648	2.567		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MILESTONE-DONALD NELSON 55-11-029-PIT Created On: 01/04/19 Updated On:	P	SW	NW	12	13N	6E	Columbia	0-225-21-2019	0.5	0.0	4.1	8.0	31.3	2.693	2.735	1.561		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
MILESTONE-DONALD NELSON 55-11-029-PIT Created On: 01/02/24 Updated On:	P	SW	NW	12	13N	6E	Columbia	0-225-20-2024	1.0	4.2	3.0	7.4	29.3	2.702	2.739	1.355		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MILESTONE-DONALD NELSON 55-11-029-PIT Created On: 05/14/25 Updated On:	P	SW	NW	12	13N	6E	Columbia	0-225-211-2025	0.0	1.1	0.7	6.9	27.7	2.725	2.760	1.291		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
COLUMBIA -- WI																		
*PLENTY 55-11-030-QRY Created On: 05/08/19 Updated On:	Q			16	10N	9E	Columbia	0-225-179-2019		2.8	4.3	3.2	11.0	43.0	2.494	2.596	4.114	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
*PLENTY 55-11-030-QRY Created On: 08/02/22 Updated On:	Q			16	10N	9E	Columbia	0-225-250-2022		3.3	5.4	4.1	9.7	38.5	2.564	2.623	2.291	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
*RIO AGGREGATE PRODUCTS 55-11-020-QRY Created On: 02/09/22 Updated On:	Q	NW	SE	32	12N	11E	Columbia	0-225-118-2022		0.8	2.4	3.1	8.1	35.2	2.617	2.675	2.203	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
STEVENSON 55-11-036-QRY Created On: 03/31/15 Updated On:	Q			8	10N	9E	Columbia	0-225-111-2015			1.2	2.2	13.0	45.0	2.524	2.602	3.118	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
STEVENSON 55-11-036-QRY Created On: 01/03/18 Updated On:	Q			8	10N	9E	Columbia	0-225-6-2018		2.5	0.7	3.9	10.4	36.7	2.529	2.615	3.422	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
STEVENSON 55-11-036-QRY Created On: 01/04/21 Updated On:	Q			8	10N	9E	Columbia	0-225-40-2021		2.3	1.2	0.6	8.9	33.9	2.548	2.620	2.799	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
STEVENSON 55-11-036-QRY Created On: 01/02/24 Updated On:	Q			8	10N	9E	Columbia	0-225-18-2024		4.9	5.1	3.1	15.9	45.9	2.512	2.604	3.663	
	Approved Use : CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
COLUMBIA -- WI																		
TRIEMSTRA 55-11-037-QRY Created On: 03/23/16 Updated On:	Q	NE	SW	11	13N	10E	Columbia	0-225-104-2016		0.9	0.5	10.5	39.6	2.599	2.656	2.187		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
TRIEMSTRA 55-11-037-QRY Created On: 04/01/19 Updated On:	Q	NE	SW	11	13N	10E	Columbia	0-225-122-2019	2.6	1.8	1.1	10.4	37.7	2.642	2.689	1.765		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
TRIEMSTRA 55-11-037-QRY Created On: 04/05/22 Updated On:	Q	NE	SW	11	13N	10E	Columbia	0-225-162-2022	4.1	1.5	1.5	10.7	39.1	2.618	2.673	2.086		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
TRIEMSTRA 55-11-037-QRY Created On: 04/15/25 Updated On:	Q	NE	SW	11	13N	10E	Columbia	0-225-186-2025	1.6	0.9	1.3	10.0	37.8	2.618	2.670	1.982		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
WILLIAMS 55-11-039-QRY Created On: 03/30/15 Updated On:	Q	SE	NE	19	12N	8E	Columbia	0-225-103-2015		0.2	0.2	6.0	24.1	2.633	2.646	0.477		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
WILLIAMS 55-11-039-QRY Created On: 01/03/18 Updated On:	Q	SE	NE	19	12N	8E	Columbia	0-225-8-2018	0.0	0.0	0.0	4.4	19.7	2.634	2.644	0.400		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
WILLIAMS 55-11-039-QRY Created On: 01/04/21 Updated On:	Q	SE	NE	19	12N	8E	Columbia	0-225-41-2021	0.0	0.0	0.4	6.1	25.1	2.627	2.639	0.481		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
COLUMBIA -- WI																	
WILLIAMS 55-11-039-QRY Created On: 01/02/24 Updated On:	Q	SE	NE	19	12N	8E	Columbia	0-225-19-2024	0.1	0.3	0.4	5.3	23.1	2.653	2.659	0.219	
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
CRAWFORD -- WI																	
*BENECKER 55-12-002-QRY Created On: 01/04/21 Updated On:	Q			5	6N	6W	Crawford	0-225-28-2021	11.3	7.8	17.1	18.7	50.3	2.423	2.521	4.012	
Approved Use : Base Aggregate																	
DOSKOCIL QUARRY 55-12-007-QRY Created On: 05/19/17 Updated On:	Q	S	SE	2	9N	5W	Crawford	0-225-191-2017		1.4	5.9	10.4	39.6	2.566	2.637	2.788	
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
DOSKOCIL QUARRY 55-12-007-QRY Created On: 01/09/20 Updated On:	Q	S	SE	2	9N	5W	Crawford	0-225-83-2020	0.4	3.5	2.0	13.1	46.3	2.502	2.569	2.645	
Approved Use : HMA<MT, CONCRETE, Base Aggregate																	
DOSKOCIL QUARRY 55-12-007-QRY Created On: 01/02/24 Updated On:	Q	S	SE	2	9N	5W	Crawford	0-225-37-2024	1.2	3.5	0.5	9.3	39.2	2.606	2.664	2.235	
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
FAIRVIEW QUARRY 55-12-008-QRY Created On: 01/05/17 Updated On:	Q	SW	NE	2	10N	5W	Crawford	0-225-30-2017		2.3	5.1	12.0	41.0	2.557	2.625	2.668	
Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
FAIRVIEW QUARRY 55-12-008-QRY Created On: 01/03/20 Updated On:	Q	SW	NE	2	10N	5W	Crawford	0-225-19-2020	2.6	2.1	1.3	11.1	38.1	2.593	2.653	2.326	
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
CRAWFORD -- WI																		
FAIRVIEW QUARRY 55-12-008-QRY Created On: 01/03/23 Updated On:	Q	SW	NE	2	10N	5W	Crawford	0-225-67-2023	2.3	3.8	1.5	11.6	38.1	2.593	2.658	2.498		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
FORDE 55-12-009-QRY Created On: 01/04/24 Updated On:	Q	SE	NE	5	10N	6W	Crawford	0-225-137-2024	0.2	16.0	4.6	9.5	34.9	2.606	2.672	2.521		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
HAGGERTY 55-12-010-QRY Created On: 07/17/15 Updated On:	Q	SW	SW	10	9N	3W	Crawford	0-225-212-2015		2.6	3.4	8.2	33.6	2.625	2.678	2.011		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
HAGGERTY 55-12-010-QRY Created On: 07/09/20 Updated On:	Q	SW	SW	10	9N	3W	Crawford	0-225-210-2020	0.9	1.5	3.6	9.1	32.3	2.629	2.684	2.072		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
HAGGERTY 55-12-010-QRY Created On: 01/16/25 Updated On:	Q	SW	SW	10	9N	3W	Crawford	0-225-132-2025	2.1	10.2	3.4	13.2	42.7	2.572	2.634	2.388		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
HANSON 55-12-011-QRY Created On: 01/02/24 Updated On:	Q	NW	SW	24	11N	7W	Crawford	0-225-121-2024	0.4	4.1	2.5	11.6	38.9	2.573	2.645	2.788		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
SHOCKLEY HILL 55-12-020-QRY Created On: 05/18/17 Updated On:	Q	SW	NE	21	8N	3W	Crawford	0-225-189-2017		2.8	6.6	8.7	33.7	2.632	2.687	2.097		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
CRAWFORD -- WI																	
SHOCKLEY HILL 55-12-020-QRY Created On: 01/03/20 Updated On:	Q	SW	NE	21	8N	3W	Crawford	0-225-20-2020	0.5	1.1	0.5	7.2	28.3	2.618	2.675	2.193	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
SHOCKLEY HILL 55-12-020-QRY Created On: 01/02/24 Updated On:	Q	SW	NE	21	8N	3W	Crawford	0-225-33-2024	0.8	4.5	2.8	9.2	34.2	2.599	2.662	2.416	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
SLAMA 55-12-021-QRY Created On: 07/30/15 Updated On:	Q			18	7N	6W	Crawford	0-225-222-2015	1.1	1.8	2.1	8.7	33.9	2.614	2.675	2.350	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
SLAMA 55-12-021-QRY Created On: 01/04/18 Updated On:	Q			18	7N	6W	Crawford	0-225-73-2018	0.7	1.0	3.2	7.5	37.9	2.636	2.685	1.845	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
SLAMA 55-12-021-QRY Created On: 01/04/21 Updated On:	Q			18	7N	6W	Crawford	0-225-26-2021	1.0	6.6	5.0	7.5	31.7	2.612	2.668	2.167	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
SLAMA 55-12-021-QRY Created On: 01/02/24 Updated On:	Q			18	7N	6W	Crawford	0-225-27-2024	2.0	4.1	1.2	7.0	28.1	2.650	2.696	1.710	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
SWIGGUM 55-12-022-QRY Created On: 07/17/15 Updated On:	Q	SW	NW	29	11N	3W	Crawford	0-225-213-2015		1.1	1.4	9.1	35.6	2.640	2.687	1.764	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
CRAWFORD -- WI																		
SWIGGUM 55-12-022-QRY Created On: 05/19/16 Updated On:	Q	SW	NW	29	11N	3W	Crawford	0-225-183-2016		1.4	3.9	8.9	34.4	2.661	2.705	1.650		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
SWIGGUM 55-12-022-QRY Created On: 01/07/19 Updated On:	Q	SW	NW	29	11N	3W	Crawford	0-225-55-2019		1.0	2.0	3.5	10.1	36.8	2.602	2.662	2.325	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
SWIGGUM 55-12-022-QRY Created On: 02/16/22 Updated On:	Q	SW	NW	29	11N	3W	Crawford	0-225-123-2022		0.4	5.6	0.3	9.0	35.8	2.642	2.697	2.073	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
SWIGGUM 55-12-022-QRY Created On: 01/02/25 Updated On:	Q	SW	NW	29	11N	3W	Crawford	0-225-29-2025		0.4	3.1	1.8	10.6	36.4	2.625	2.685	2.283	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
WETZEL 55-12-024-QRY Created On: 01/05/17 Updated On:	Q	NW	SE	31	7N	6W	Crawford	0-225-33-2017		1.2	3.3	6.7	28.7	2.633	2.685	1.977		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
WETZEL 55-12-024-QRY Created On: 01/03/20 Updated On:	Q	NW	SE	31	7N	6W	Crawford	0-225-23-2020		2.3	3.6	2.9	12.1	40.5	2.558	2.633	2.939	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
WETZEL 55-12-024-QRY Created On: 01/03/23 Updated On:	Q	NW	SE	31	7N	6W	Crawford	0-225-71-2023		1.2	4.7	0.6	11.7	39.2	2.604	2.662	2.251	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
DANE -- WI																	
ANDERSON 55-13-001-PIT Created On: 01/05/17 Updated On:	P	E	NW	10	5N	11E	Dane	0-225-51-2017	1.7	16.3	16.8	11.2	42.5	2.545	2.630	3.316	
	Approved Use : Base Aggregate																
ANDERSON 55-13-001-PIT Created On: 01/03/23 Updated On:	P	E	NW	10	5N	11E	Dane	0-225-4-2023	0.3	3.2	13.1	8.1	35.2	2.586	2.655	2.679	
	Approved Use : Base Aggregate																
ANDERSON 55-13-001-PIT Created On: 07/31/24 Updated On:	P	E	NW	10	5N	11E	Dane	0-225-288-2024	4.0	13.6	7.0	11.2	41.1	2.574	2.649	2.935	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
BONG 55-13-004-QRY Created On: 05/11/18 Updated On:	Q	SW	SE	11	8N	9E	Dane	0-225-210-2018	4.1	1.9	3.7	11.9	39.2	2.537	2.611	2.930	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
BONG 55-13-004-QRY Created On: 02/15/21 Updated On:	Q	SW	SE	11	8N	9E	Dane	0-225-127-2021	5.2	3.4	3.4	9.2	36.4	2.570	2.638	2.624	
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																
BONG 55-13-004-QRY Created On: 01/04/24 Updated On:	Q	SW	SE	11	8N	9E	Dane	0-225-148-2024	3.2	5.5	2.5	9.8	40.1	2.560	2.625	2.530	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
BONG (YAHARA) 55-13-004-QRY Created On: 04/18/24 Updated On:	Q	SW	SE	11	8N	9E	Dane	0-225-235-2024	0.6	7.4	5.3	12.0	46.5	2.489	2.579	3.606	
	Approved Use : HMA<MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
DANE -- WI																		
BREUNIG 55-13-006-PIT Created On: 01/20/17 Updated On:	P	NE	NW	7	9N	7E	Dane	0-225-55-2017	1.5	0.0	5.2	7.6	30.6	2.677	2.724	1.745		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
BREUNIG 55-13-006-PIT Created On: 01/04/22 Updated On:	P	NE	NW	7	9N	7E	Dane	0-225-43-2022	2.1	0.0	6.8	7.2	31.4	2.671	2.720	1.819		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
BUCKEYE 55-13-008-QRY Created On: 01/21/15 Updated On:	Q	SW	NE	14	7N	10E	Dane	0-225-74-2015		6.1	4.4	9.7	38.9	2.563	2.636	2.824		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
BUCKEYE 55-13-008-QRY Created On: 01/05/17 Updated On:	Q	SW	NE	14	7N	10E	Dane	0-225-35-2017	1.1	3.7	2.1	6.2	27.2	2.603	2.667	2.481		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
BUCKEYE 55-13-008-QRY Created On: 05/13/19 Updated On:	Q	SW	NE	14	7N	10E	Dane	0-225-186-2019	0.3	1.1	0.9	6.9	28.7	2.619	2.678	2.260		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
BUCKEYE 55-13-008-QRY Created On: 03/09/20 Updated On:	Q	SW	NE	14	7N	10E	Dane	0-225-121-2020	0.1	1.6	4.7	6.3	25.1	2.644	2.695	1.895		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
BUCKEYE 55-13-008-QRY Created On: 03/16/21 Updated On:	Q	SW	NE	14	7N	10E	Dane	0-225-136-2021	0.8	1.6	3.4	6.4	26.8	2.634	2.689	2.079		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
DANE -- WI																	
BUCKEYE 55-13-008-QRY Created On: 01/02/24 Updated On:	Q	SW	NE	14	7N	10E	Dane	0-225-88-2024	0.2	3.0	2.4	10.1	35.4	2.583	2.646	2.430	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
BUCKEYE 55-13-008-QRY Created On: 01/02/25 Updated On:	Q	SW	NE	14	7N	10E	Dane	0-225-80-2025	1.2	15.9	7.9	10.9	42.0	2.507	2.595	3.518	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
C6 QUARRY 55-13-126-QRY Created On: 09/05/23 Updated On:	Q	NE	NW	17	6N	8E	Dane	0-225-250-2023	0.7	2.8	0.5	5.4	23.9	2.680	2.720	1.486	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
CAPITOL SAND & GRAVEL 55-13-010-PIT Created On: 09/26/18 Updated On:	P			11	7N	7E	Dane	0-225-283-2018	9.2	5.8	3.1	8.1	32.1	2.587	2.639	1.997	
	Approved Use : HMA<MT, HMA>=MT, Base Aggregate																
CAPITOL SAND & GRAVEL 55-13-010-PIT Created On: 01/09/20 Updated On:	P			11	7N	7E	Dane	0-225-92-2020	4.2	9.1	0.9	11.0	38.5	2.635	2.681	1.729	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
CAPITOL SAND & GRAVEL 55-13-010-PIT Created On: 01/02/24 Updated On:	P			11	7N	7E	Dane	0-225-41-2024	1.7	2.8	5.7	11.0	38.2	2.649	2.691	1.584	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
EVANS 55-13-017-QRY Created On: 01/06/20 Updated On:	Q	NW	SW	24	9N	9E	Dane	0-225-29-2020	0.8	1.4	1.9	7.6	31.7	2.614	2.660	1.742	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
DANE -- WI																	
EVANS 55-13-017-QRY Created On: 01/04/23 Updated On:	Q	NW	SW	24	9N	9E	Dane	0-225-92-2023	0.7	1.1	1.4	8.8	34.9	2.602	2.661	2.297	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
FINK 55-13-020-QRY Created On: 01/04/22 Updated On:	Q	NW	NW	14	6N	6E	Dane	0-225-44-2022	0.8	7.7	11.0	11.7	43.2	2.552	2.628	2.944	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
FINK 55-13-020-QRY Created On: 01/02/25 Updated On:	Q	NW	NW	14	6N	6E	Dane	0-225-53-2025	3.9	7.1	6.7	12.1	44.0	2.580	2.653	2.794	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
*FINK (YAHARA) 55-13-021-QRY Created On: 03/19/15 Updated On:	Q	SE	NW	14	6N	6E	Dane	0-225-98-2015		8.2	4.0	10.4	38.4	2.563	2.635	2.807	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
*FINK (YAHARA) 55-13-021-QRY Created On: 01/03/18 Updated On:	Q	SE	NW	14	6N	6E	Dane	0-225-27-2018	1.0	10.3	8.2	10.5	40.7	2.506	2.599	3.703	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
*FINK (YAHARA) 55-13-021-QRY Created On: 06/20/22 Updated On:	Q	SE	NW	14	6N	6E	Dane	0-225-234-2022	0.6	0.8	2.1	7.7	33.0	2.679	2.719	1.507	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
FITCHBURG HILLS QUARRY 55-13-127-QRY Created On: 03/27/24 Updated On:	Q	NE	NE	18	6N	9E	Dane	0-225-217-2024	0.2	9.2	4.7	8.9	37.8	2.602	2.672	2.669	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
DANE -- WI																		
FITCHBURG MINERALS 55-13-121-QRY Created On: 01/14/25 Updated On:	Q	SE	SW	7	6N	9E	Dane	0-225-123-2025	1.6	2.8	5.7	9.0	34.8	2.586	2.649	2.419		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
GILLES (DANE) 55-13-024-QRY Created On: 01/24/22 Updated On:	Q	NW	NW	4	9N	9E	Dane	0-225-117-2022	0.7	1.2	1.1	9.5	34.9	2.602	2.658	2.140		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
GILLES (DANE) 55-13-024-QRY Created On: 01/23/23 Updated On:	Q	NW	NW	4	9N	9E	Dane	0-225-131-2023	0.3	1.2	1.0	8.6	35.3	2.560	2.628	2.681		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
GILLES (DANE) 55-13-024-QRY Created On: 04/15/24 Updated On:	Q	NW	NW	4	9N	9E	Dane	0-225-225-2024	0.7	0.9	1.7	9.5	37.8	2.602	2.665	2.409		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
GILLES (DANE) 55-13-024-QRY Created On: 01/02/25 Updated On:	Q	NW	NW	4	9N	9E	Dane	0-225-38-2025	1.5	1.6	3.1	10.0	36.5	2.642	2.687	1.702		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
HARVEST HAVEN / O'BRIAN 55-13-030-QRY Created On: 01/07/15 Updated On:	Q		SE	7	6N	9E	Dane	0-225-8-2015		21.1	10.1	6.0	28.1	2.614	2.680	2.509		
HARVEST HAVEN / O'BRIAN 55-13-030-QRY Created On: 06/03/15 Updated On:	Q		SE	7	6N	9E	Dane	0-225-181-2015		16.0	7.4	6.4	30.3	2.608	2.683	2.892		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
DANE -- WI																		
HARVEST HAVEN / O'BRIAN 55-13-030-QRY Created On: 09/15/16 Updated On:	Q		SE	7	6N	9E	Dane	0-225-256-2016	0.5	15.9	9.8	7.2	32.5	2.596	2.666	2.711		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
HARVEST HAVEN / O'BRIAN 55-13-030-QRY Created On: 01/02/18 Updated On:	Q		SE	7	6N	9E	Dane	0-225-1-2018	0.8	8.7	13.9	6.1	30.7	2.597	2.665	2.601		
	Approved Use : Base Aggregate																	
HARVEST HAVEN / O'BRIAN 55-13-030-QRY Created On: 03/18/21 Updated On:	Q		SE	7	6N	9E	Dane	0-225-154-2021	0.4	4.0	7.1	8.1	34.2	2.597	2.657	2.288		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
HARVEST HAVEN / O'BRIAN 55-13-030-QRY Created On: 01/04/24 Updated On:	Q		SE	7	6N	9E	Dane	0-225-146-2024	0.7	7.4	6.2	9.8	40.1	2.580	2.649	2.667		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
HAWKINSON 55-13-123-PIT Created On: 01/09/20 Updated On:	P	SE	SE	34	6N	10E	Dane	0-225-90-2020	3.9	0.0	4.1	5.7	31.2	2.634	2.687	1.999		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
HAWKINSON 55-13-123-PIT Created On: 01/02/25 Updated On:	P	SE	SE	34	6N	10E	Dane	0-225-52-2025	3.0	0.0	10.3	8.1	33.8	2.614	2.678	2.438		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
HELLICKSON 55-13-031-PIT Created On: 04/12/17 Updated On:	P	SE	NW	34	7N	11E	Dane	0-225-123-2017	2.7	0.0	3.9	7.1	31.6	2.635	2.687	1.966		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
DANE -- WI																		
HELLICKSON 55-13-031-PIT Created On: 04/18/22 Updated On:	P	SE	NW	34	7N	11E	Dane	0-225-175-2022	3.4	4.5	6.2	7.0	31.4	2.642	2.692	1.910		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
HERFEL 55-13-033-PIT Created On: 04/21/17 Updated On:	P	S	SE	28	6N	8E	Dane	0-225-139-2017	5.0	2.8	4.0	7.2	30.0	2.565	2.627	2.421		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
HERFEL 55-13-033-PIT Created On: 06/27/24 Updated On:	P	S	SE	28	6N	8E	Dane	0-225-284-2024	4.8	0.0	5.6	9.2	35.9	2.609	2.662	2.045		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
HWY 51 55-13-042-QRY Created On: 01/21/15 Updated On:	Q	SW	NE	17	8N	10E	Dane	0-225-73-2015	0.8	1.6	2.7	7.9	32.6	2.609	2.666	2.187		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
HWY 51 55-13-042-QRY Created On: 05/08/17 Updated On:	Q	SW	NE	17	8N	10E	Dane	0-225-176-2017	1.1	0.7	2.6	7.3	31.9	2.610	2.669	2.267		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
HWY 51 55-13-042-QRY Created On: 04/10/18 Updated On:	Q	SW	NE	17	8N	10E	Dane	0-225-162-2018	1.9	3.5	2.9	7.6	32.3	2.586	2.647	2.375		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
HWY 51 55-13-042-QRY Created On: 03/27/19 Updated On:	Q	SW	NE	17	8N	10E	Dane	0-225-117-2019	0.8	2.2	3.0	7.4	31.4	2.647	2.687	1.511		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
DANE -- WI																	
HWY 51 55-13-042-QRY Created On: 03/09/20 Updated On:	Q	SW	NE	17	8N	10E	Dane	0-225-120-2020	0.2	1.5	2.8	7.3	30.8	2.613	2.664	1.961	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
HWY 51 55-13-042-QRY Created On: 03/29/21 Updated On:	Q	SW	NE	17	8N	10E	Dane	0-225-159-2021	0.4	1.9	1.6	7.8	30.5	2.607	2.662	2.141	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
HWY 51 55-13-042-QRY Created On: 01/04/22 Updated On:	Q	SW	NE	17	8N	10E	Dane	0-225-6-2022	1.8	5.3	2.3	6.9	30.3	2.579	2.644	2.541	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
HWY 51 55-13-042-QRY Created On: 01/23/23 Updated On:	Q	SW	NE	17	8N	10E	Dane	0-225-130-2023	0.5	2.1	1.3	7.0	30.9	2.588	2.650	2.406	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
HWY 51 55-13-042-QRY Created On: 01/02/24 Updated On:	Q	SW	NE	17	8N	10E	Dane	0-225-74-2024	0.4	2.3	3.0	6.7	30.2	2.567	2.635	2.653	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
HWY 51 55-13-042-QRY Created On: 01/02/25 Updated On:	Q	SW	NE	17	8N	10E	Dane	0-225-78-2025	1.7	2.4	1.3	7.0	29.9	2.605	2.660	2.105	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
KAMPMEIER 55-13-045-QRY Created On: 04/09/15 Updated On:	Q	SW	SW	26	7N	10E	Dane	0-225-119-2015	7.0	16.1	17.1	12.4	44.0	2.493	2.591	3.926	
	Approved Use : Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
DANE -- WI																		
KAMPMEIER 55-13-045-QRY Created On: 01/04/22 Updated On:	Q	SW	SW	26	7N	10E	Dane	0-225-58-2022	3.1	6.8	5.2	10.1	37.7	2.574	2.641	2.610		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
KAMPMEIER 55-13-045-QRY Created On: 01/02/25 Updated On:	Q	SW	SW	26	7N	10E	Dane	0-225-54-2025	3.4	2.8	7.8	8.3	34.0	2.575	2.641	2.577		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
KELLY 55-13-047-QRY Created On: 04/06/16 Updated On:	Q	SW	SW	14	6N	7E	Dane	0-225-125-2016	0.2	15.7	7.7	9.7	36.0	2.582	2.655	2.854		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
KELLY 55-13-047-QRY Created On: 06/03/19 Updated On:	Q	SW	SW	14	6N	7E	Dane	0-225-203-2019	0.7	5.3	0.5	8.1	33.6	2.583	2.656	2.826		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
KELLY 55-13-047-QRY Created On: 01/04/22 Updated On:	Q	SW	SW	14	6N	7E	Dane	0-225-56-2022	0.7	5.0	2.4	6.7	28.9	2.581	2.648	2.573		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
KELLY 55-13-047-QRY Created On: 02/07/25 Updated On:	Q	SW	SW	14	6N	7E	Dane	0-225-151-2025	0.5	5.3	1.7	7.1	29.0	2.581	2.647	2.543		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
KIPPLEY 55-13-048-QRY Created On: 05/26/16 Updated On:	Q	NW	NE	11	8N	9E	Dane	0-225-186-2016	1.0	2.8	1.4	10.0	37.1	2.548	2.619	2.798		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
DANE -- WI																		
KIPPLEY 55-13-048-QRY Created On: 01/04/23 Updated On:	Q	NW	NE	11	8N	9E	Dane	0-225-99-2023	1.9	2.5	3.0	12.0	41.6	2.510	2.590	3.200		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
*KREUGER 55-13-050-QRY Created On: 06/10/15 Updated On:	Q	SW	SW	3	6N	11E	Dane	0-225-194-2015		24.6	6.9	6.0	30.0	2.641	2.699	2.220		
*KREUGER 55-13-050-QRY Created On: 08/05/15 Updated On:	Q	SW	SW	3	6N	11E	Dane	0-225-224-2015		9.1	11.1	7.1	31.7	2.641	2.701	2.300		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
*KREUGER 55-13-050-QRY Created On: 01/04/18 Updated On:	Q	SW	SW	3	6N	11E	Dane	0-225-65-2018	0.3	1.7	8.1	5.6	27.7	2.657	2.707	1.912		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
*KREUGER 55-13-050-QRY Created On: 06/14/21 Updated On:	Q	SW	SW	3	6N	11E	Dane	0-225-223-2021	0.6	7.9	7.2	5.4	26.7	2.679	2.730	1.906		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
KRUEGER 55-13-051-QRY Created On: 04/04/23 Updated On:	Q	SE	SW	32	5N	8E	Dane	0-225-180-2023	0.6	14.7	10.1	10.1	39.8	2.523	2.614	3.604		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MAIER 55-13-124-QRY Created On: 01/05/21 Updated On:	Q		NW	21	9N	9E	Dane	0-225-99-2021	3.4	4.0	10.0	10.2	37.4	2.553	2.623	2.714		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
DANE -- WI																	
MAIER 55-13-124-QRY Created On: 02/28/24 Updated On:	Q		NW 21	9N	9E	Dane		0-225-190-2024	2.5	4.5	4.3	7.5	32.2	2.602	2.665	2.428	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
MEINHOLZ 55-13-064-QRY Created On: 01/20/16 Updated On:	Q			35	8N	8E	Dane	0-225-62-2016	1.0	1.4	0.8	7.6	33.0	2.563	2.627	2.493	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
MEINHOLZ 55-13-064-QRY Created On: 04/01/19 Updated On:	Q			35	8N	8E	Dane	0-225-120-2019	0.8	1.5	2.8	9.3	35.2	2.565	2.636	2.748	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
MEINHOLZ 55-13-064-QRY Created On: 03/29/21 Updated On:	Q			35	8N	8E	Dane	0-225-160-2021	0.8	2.4	2.5	7.7	30.4	2.593	2.656	2.426	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
MEINHOLZ 55-13-064-QRY Created On: 01/04/22 Updated On:	Q			35	8N	8E	Dane	0-225-40-2022	1.3	4.5	5.1	9.4	31.3	2.578	2.643	2.515	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
MEINHOLZ 55-13-064-QRY Created On: 01/23/23 Updated On:	Q			35	8N	8E	Dane	0-225-132-2023	0.6	2.3	2.3	9.4	37.8	2.533	2.602	2.715	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
MEINHOLZ 55-13-064-QRY Created On: 01/02/24 Updated On:	Q			35	8N	8E	Dane	0-225-72-2024	0.8	1.7	1.3	7.2	30.4	2.540	2.619	3.106	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
DANE -- WI																	
MEINHOLZ 55-13-064-QRY Created On: 01/02/25 Updated On:	Q			35	8N	8E	Dane	0-225-79-2025	1.4	2.2	1.5	7.9	32.1	2.562	2.631	2.684	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
MILE ROAD 55-13-007-QRY Created On: 03/07/16 Updated On:	Q	NE	NE	13	9N	10E	Dane	0-225-97-2016	1.1	2.6	8.9	6.5	29.4	2.640	2.693	2.030	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
MILE ROAD 55-13-007-QRY Created On: 01/04/19 Updated On:	Q	NE	NE	13	9N	10E	Dane	0-225-9-2019	1.7	7.0	7.4	10.1	28.7	2.536	2.616	3.134	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
MILE ROAD 55-13-007-QRY Created On: 01/02/24 Updated On:	Q	NE	NE	13	9N	10E	Dane	0-225-42-2024	0.7	14.1	12.6	9.8	43.1	2.545	2.623	3.066	
	Approved Use : Base Aggregate																
NORWAY GROVE 55-13-068-PIT Created On: 10/27/22 Updated On:	P	NW	SW	14	9N	9E	Dane	0-225-260-2022	6.8	0.0	3.8	8.4	32.9	2.656	2.698	1.587	
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																
OAK PARK 55-13-069-QRY Created On: 01/02/24 Updated On:	Q	NE	SW	29	7N	12E	Dane	0-225-89-2024	0.1	16.0	8.1	6.6	28.8	2.578	2.656	3.038	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
OREGON 55-13-112-PIT Created On: 01/05/17 Updated On:	P	NW	SE	36	5N	9E	Dane	0-225-50-2017	2.5	4.1	1.4	11.2	39.0	2.561	2.630	2.668	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
DANE -- WI																	
OREGON 55-13-112-PIT Created On: 01/04/22 Updated On:	P	NW	SE	36	5N	9E	Dane	0-225-59-2022	5.2	5.2	2.9	7.0	30.4	2.591	2.645	2.068	
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																
*RIGGENBERG 55-13-016-QRY Created On: 10/03/22 Updated On:	Q		NW	23	6N	7E	Dane	0-225-256-2022	0.5	11.6	4.4	7.1	32.4	2.653	2.708	2.068	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
*RIGGENBERG 55-13-016-QRY Created On: 04/07/25 Updated On:	Q		NW	23	6N	7E	Dane	0-225-184-2025	2.8	11.9	11.6	9.9	38.1	2.538	2.655	4.589	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
*RIGGENBERG 55-13-016-QRY Created On: 04/21/25 Updated On:	Q		NW	23	6N	7E	Dane	0-225-198-2025	0.6	14.7	6.6	6.7	29.8	2.651	2.709	2.172	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
*RIPP 55-13-076-QRY Created On: 03/19/15 Updated On:	Q	NW	NW	16	9N	9E	Dane	0-225-99-2015	2.8	3.7	3.2	10.3	36.5	2.555	2.629	2.921	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
*RIPP 55-13-076-QRY Created On: 01/03/18 Updated On:	Q	NW	NW	16	9N	9E	Dane	0-225-23-2018	2.8	2.3	3.1	7.9	31.9	2.575	2.647	2.813	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
*RIPP 55-13-076-QRY Created On: 01/05/21 Updated On:	Q	NW	NW	16	9N	9E	Dane	0-225-98-2021	2.7	3.4	3.7	9.3	36.5	2.543	2.609	2.630	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
DANE -- WI																		
ROSENBAUM 55-13-078-PIT Created On: 02/17/16 Updated On:	P	SW	NE	18	5N	11E	Dane	0-225-91-2016	7.4	0.0	5.0	8.3	34.0	2.600	2.658	2.249		
	Approved Use : HMA<E-3, HMA>=E-3, Base Aggregate																	
ROSENBAUM 55-13-078-PIT Created On: 06/01/22 Updated On:	P	SW	NE	18	5N	11E	Dane	0-225-211-2022	0.3	4.9	6.6	10.0	34.0	2.607	2.661	2.064		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
SCHADLER 55-13-081-PIT Created On: 01/03/18 Updated On:	P	NE	SE	10	8N	6E	Dane	0-225-26-2018	2.9	3.7	3.1	8.8	34.0	2.444	2.512	2.786		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
SCHADLER 55-13-081-PIT Created On: 01/04/23 Updated On:	P	NE	SE	10	8N	6E	Dane	0-225-97-2023	6.9	0.0	3.3	8.8	34.0	2.580	2.629	1.886		
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																	
SCHOEPP 55-13-082-QRY Created On: 03/30/18 Updated On:	Q		NE	9	7N	7E	Dane	0-225-156-2018	1.3	3.5	2.0	9.9	36.8	2.595	2.654	2.262		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
SCHOEPP 55-13-082-QRY Created On: 06/24/19 Updated On:	Q		NE	9	7N	7E	Dane	0-225-225-2019	0.3	2.2	1.8	8.4	35.7	2.592	2.652	2.289		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
SCHOEPP 55-13-082-QRY Created On: 03/21/23 Updated On:	Q		NE	9	7N	7E	Dane	0-225-170-2023	0.3	1.9	3.9	10.2	41.9	2.610	2.664	2.034		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
DANE -- WI																		
SCHUETZ 55-13-083-QRY Created On: 04/11/18 Updated On:	Q	SE	SW	26	6N	10E	Dane	0-225-164-2018	4.6	3.8	7.5	10.4	39.4	2.554	2.620	2.605		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
SCHUETZ 55-13-083-QRY Created On: 01/03/23 Updated On:	Q	SE	SW	26	6N	10E	Dane	0-225-1-2023	1.1	1.6	1.9	5.5	27.4	2.651	2.692	1.521		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
SPILE 55-13-085-PIT Created On: 08/11/15 Updated On:	P		N	17	6N	11E	Dane	0-225-227-2015		7.8	7.4	8.5	34.4	2.631	2.689	2.211		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
SPILE 55-13-085-PIT Created On: 01/04/21 Updated On:	P		N	17	6N	11E	Dane	0-225-2-2021	9.4	0.0	12.7	10.7	39.0	2.584	2.647	2.438		
	Approved Use : Base Aggregate																	
STOUGHTON 55-13-001-PIT Created On: 01/04/19 Updated On:	P	E	NW	10	5N	11E	Dane	0-225-10-2019	2.0	9.3	0.9	6.4	30.8	2.664	2.710	1.718		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
STOUGHTON 55-13-001-PIT Created On: 01/02/25 Updated On:	P	E	NW	10	5N	11E	Dane	0-225-2-2025	2.4	6.5	3.2	6.0	27.3	2.673	2.714	1.510		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
TNT 55-13-094-QRY Created On: 01/30/15 Updated On:	Q		SW	14	6N	12E	Dane	0-225-80-2015		15.5	9.5	8.1	34.5	2.603	2.679	2.917		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
DANE -- WI																	
TNT 55-13-094-QRY Created On: 03/22/17 Updated On:	Q		SW	14	6N	12E	Dane	0-225-87-2017	1.6	31.6	19.1	10.5	38.3	2.557	2.644	3.416	
TNT 55-13-094-QRY Created On: 04/12/17 Updated On:	Q		SW	14	6N	12E	Dane	0-225-122-2017		13.2	8.8	8.0	34.9	2.616	2.687	2.679	
Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
TNT 55-13-094-QRY Created On: 04/12/17 Updated On:	Q		SW	14	6N	12E	Dane	0-225-124-2017	0.5	12.1	6.9	6.5	29.1	2.630	2.692	2.387	
Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
TNT 55-13-094-QRY Created On: 04/12/17 Updated On:	Q		SW	14	6N	12E	Dane	0-225-125-2017	0.3	10.1	9.5	6.1	28.3	2.630	2.691	2.312	
Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
TNT 55-13-094-QRY Created On: 02/12/20 Updated On:	Q		SW	14	6N	12E	Dane	0-225-110-2020	0.4	29.8	15.7	7.3	32.8	2.619	2.683	2.461	
TNT 55-13-094-QRY Created On: 04/01/20 Updated On:	Q		SW	14	6N	12E	Dane	0-225-136-2020	0.2	22.0	12.7	6.7	30.8				
TNT 55-13-094-QRY Created On: 08/10/20 Updated On:	Q		SW	14	6N	12E	Dane	0-225-231-2020		17.6	6.7	5.3	26.8	2.662	2.713	1.888	
Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
DANE -- WI																	
TNT 55-13-094-QRY Created On: 04/26/21 Updated On:	Q		SW	14	6N	12E	Dane	0-225-189-2021	0.1	16.8	5.8	5.7	27.6	2.622	2.684	2.377	
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
TNT 55-13-094-QRY Created On: 01/04/22 Updated On:	Q		SW	14	6N	12E	Dane	0-225-79-2022	0.2	14.2	10.4	5.9	29.5	2.651	2.706	2.058	
Approved Use : Base Aggregate																	
TNT 55-13-094-QRY Created On: 01/14/25 Updated On:	Q		SW	14	6N	12E	Dane	0-225-94-2025	0.2	15.8	2.8	6.6	29.4	2.622	2.686	2.426	
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
VIENNA 55-13-099-QRY Created On: 01/05/15 Updated On:	Q	NE	SW	34	9N	9E	Dane	0-225-7-2015	0.7	0.7	2.0	6.8	30.1	2.610	2.670	2.310	
Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
VIENNA 55-13-099-QRY Created On: 01/03/18 Updated On:	Q	NE	SW	34	9N	9E	Dane	0-225-21-2018	2.1	1.0	3.4	8.3	35.4	2.539	2.619	3.158	
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
VIENNA 55-13-099-QRY Created On: 09/17/20 Updated On:	Q	NE	SW	34	9N	9E	Dane	0-225-241-2020	2.0	2.4	3.7	7.8	31.3	2.614	2.667	2.024	
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
VIENNA 55-13-099-QRY Created On: 01/03/23 Updated On:	Q	NE	SW	34	9N	9E	Dane	0-225-3-2023	0.6	2.4	8.8	7.2	32.8	2.607	2.662	2.099	
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
DANE -- WI																	
VOLENBERG 55-13-100-PIT Created On: 01/05/16 Updated On:	P		NW	19	6N	12E	Dane	0-225-17-2016	6.9	0.0	6.5	6.6	34.2	2.618	2.678	2.294	
	Approved Use : HMA<E-3, HMA>=E-3, Base Aggregate																
VOLENBERG 55-13-100-PIT Created On: 01/04/21 Updated On:	P		NW	19	6N	12E	Dane	0-225-3-2021	4.0	0.0	8.0	8.4	34.5	2.640	2.693	1.982	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
WESTRES 55-13-066-QRY Created On: 04/06/17 Updated On:	Q	SW	NE	2	7N	6E	Dane	0-225-110-2017	0.7	1.9	2.2	11.0	37.3	2.613	2.672	2.268	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
WESTRES 55-13-066-QRY Created On: 03/29/21 Updated On:	Q	SW	NE	2	7N	6E	Dane	0-225-161-2021	0.3	7.5	3.2	9.1	33.6	2.573	2.646	2.848	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
WESTRES 55-13-066-QRY Created On: 01/02/24 Updated On:	Q	SW	NE	2	7N	6E	Dane	0-225-73-2024	0.7	4.8	2.0	11.6	42.5	2.494	2.576	3.284	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
*WK 55-13-102-QRY Created On: 03/20/15 Updated On:	Q	SW	SW	8	7N	8E	Dane	0-225-101-2015	1.2	2.3	6.0	7.0	31.3	2.626	2.681	2.081	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
*WK 55-13-102-QRY Created On: 01/03/18 Updated On:	Q	SW	SW	8	7N	8E	Dane	0-225-22-2018	4.6	2.0	11.1	8.7	40.4	2.553	2.633	3.112	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
DANE -- WI																		
*WK 55-13-102-QRY Created On: 01/05/21 Updated On:	Q	SW	SW	8	7N	8E	Dane	0-225-93-2021	1.8	3.0	7.4	7.2	31.6	2.612	2.672	2.271		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
*WRIGLY 55-13-114-QRY Created On: 06/02/17 Updated On:	Q		NW	29	6N	12E	Dane	0-225-201-2017		3.5	3.8	7.0	28.6					
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
*WRIGLY 55-13-114-QRY Created On: 06/07/18 Updated On:	Q		NW	29	6N	12E	Dane	0-225-220-2018	0.5	11.3	17.2	7.9	33.3	2.619	2.683	2.428		
	Approved Use : Base Aggregate																	
*WRIGLY 55-13-114-QRY Created On: 01/04/22 Updated On:	Q		NW	29	6N	12E	Dane	0-225-55-2022	0.1	17.9	6.2	7.6	30.4	2.615	2.680	2.483		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
ZANDER 55-13-109-PIT Created On: 03/14/18 Updated On:	P	NW	SW	11	7N	7E	Dane	0-225-119-2018	10.1	5.3	16.3	16.4	46.2	2.542	2.621	3.113		
	Approved Use : Base Aggregate																	
ZANDER 55-13-109-PIT Created On: 01/07/19 Updated On:	P	NW	SW	11	7N	7E	Dane	0-225-46-2019	4.1	2.2	6.3	9.7	37.0	2.602	2.663	2.362		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
ZANDER 55-13-122-QRY Created On: 06/20/19 Updated On:	Q	NW	SW	11	7N	7E	Dane	0-225-222-2019	0.9	3.3	8.3	8.3	39.0	2.581	2.647	2.581		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse					
	P/Q	Qrt	Qrt	Sect	Town	Range	County	LA Wear (%)					Sp. Gravity		Absorp. %			
								100					500	OD	SSD	Crse	Fine	
DANE -- WI																		
ZANDER 55-13-122-QRY Created On: 04/26/23 Updated On:	Q	NW	SW	11	7N	7E	Dane	0-225-208-2023	1.8	10.9	9.2	11.6	41.5	2.556	2.631	2.938		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
ZANDER 55-13-109-PIT Created On: 01/02/24 Updated On:	P	NW	SW	11	7N	7E	Dane	0-225-129-2024	3.0	0.0	7.8	8.5	34.7	2.619	2.672	2.043		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
DODGE -- WI																		
BUCHDA 55-14-004-QRY Created On: 01/04/16 Updated On:	Q	NE	NW	5	12N	14E	Dodge	0-225-3-2016	0.5	2.2	1.4	6.8	27.7	2.745	2.779	1.209		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
BUCHDA 55-14-004-QRY Created On: 06/06/19 Updated On:	Q	NE	NW	5	12N	14E	Dodge	0-225-204-2019		2.1	1.0	7.6	29.5	2.752	2.779	0.973		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
BUCHDA 55-14-004-QRY Created On: 01/04/22 Updated On:	Q	NE	NW	5	12N	14E	Dodge	0-225-95-2022	0.0	2.4	2.5	8.0	27.1	2.738	2.772	1.252		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
BUCHDA 55-14-004-QRY Created On: 02/07/25 Updated On:	Q	NE	NW	5	12N	14E	Dodge	0-225-149-2025	0.0	2.8	1.9	6.9	25.7	2.760	2.786	0.955		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
CHRISTIAN - GADE 55-14-006-PIT Created On: 01/07/16 Updated On:	P	W	SW	33	12N	15E	Dodge	0-225-41-2016		11.7	2.6	5.4	25.5	2.743	2.779	1.332		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
DODGE -- WI																		
CHRISTIAN - GADE 55-14-006-PIT Created On: 01/04/21 Updated On:	P	W	SW	33	12N	15E	Dodge	0-225-5-2021	0.0	14.4	2.5	5.7	25.9	2.728	2.772	1.598		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
*FARMERSVILLE 55-14-007-QRY Created On: 04/18/22 Updated On:	Q	S	SW	30	13N	17E	Dodge	0-225-176-2022	0.0	0.8	1.5	9.1	37.5	2.690	2.725	1.322		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
*FRENS 55-14-038-QRY Created On: 04/05/21 Updated On:	Q		NW	3	13N	14E	Dodge	0-225-169-2021	0.6	3.0	2.9	5.9	25.8	2.770	2.795	0.906		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
HERMAN 55-14-011-QRY Created On: 04/06/17 Updated On:	Q	SW	NW	6	11N	17E	Dodge	0-225-105-2017		1.1	1.3	6.9	29.6	2.733	2.764	1.114		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
HERMAN 55-14-011-QRY Created On: 06/04/20 Updated On:	Q	SW	NW	6	11N	17E	Dodge	0-225-187-2020		4.5	0.1	5.0	26.7	2.773	2.789	0.577		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
HERMAN 55-14-011-QRY Created On: 02/27/23 Updated On:	Q	SW	NW	6	11N	17E	Dodge	0-225-147-2023	0.4	6.2	3.1	10.4	33.0	2.734	2.764	1.085		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
HUSTISFORD 55-14-012-QRY Created On: 01/21/16 Updated On:	Q	SE	SW	33	10N	16E	Dodge	0-225-69-2016		4.4	5.3	5.1	24.4	2.669	2.718	1.859		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
DODGE -- WI																		
HUSTISFORD 55-14-012-QRY Created On: 02/05/19 Updated On:	Q	SE	SW	33	10N	16E	Dodge	0-225-97-2019		3.7	1.2	5.5	25.9	2.697	2.737	1.487		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
HUSTISFORD 55-14-012-QRY Created On: 01/04/22 Updated On:	Q	SE	SW	33	10N	16E	Dodge	0-225-87-2022	0.0	3.5	1.2	5.5	28.1	2.680	2.723	1.620		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
HUSTISFORD 55-14-012-QRY Created On: 01/02/25 Updated On:	Q	SE	SW	33	10N	16E	Dodge	0-225-4-2025	0.0	4.1	4.0	6.3	27.7	2.711	2.744	1.206		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
LINCK #22 55-14-019-QRY Created On: 01/29/15 Updated On:	Q	SW	SW	9	12N	14E	Dodge	0-225-79-2015		2.4	0.9	6.3	29.1	2.764	2.786	0.794		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
LINCK #22 55-14-019-QRY Created On: 03/01/18 Updated On:	Q	SW	SW	9	12N	14E	Dodge	0-225-107-2018	0.3	3.8	2.2	6.9	28.9	2.743	2.777	1.239		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
LINCK #22 55-14-019-QRY Created On: 03/29/21 Updated On:	Q	SW	SW	9	12N	14E	Dodge	0-225-162-2021	0.0	10.4	0.5	6.8	27.2	2.768	2.794	0.938		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
LINCK #22 55-14-019-QRY Created On: 02/28/24 Updated On:	Q	SW	SW	9	12N	14E	Dodge	0-225-189-2024	0.0	5.0	0.3	5.3	24.0	2.778	2.799	0.762		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
DODGE -- WI																		
LINCK #24 55-14-020-QRY Created On: 01/29/15 Updated On:	Q	SW	SW	16	9N	15E	Dodge	0-225-78-2015	0.6	18.4	10.7	6.4	29.7	2.669	2.718	1.840		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
LINCK #24 55-14-020-QRY Created On: 03/01/18 Updated On:	Q	SW	SW	16	9N	15E	Dodge	0-225-109-2018	0.3	20.5	8.1	8.3	32.3	2.651	2.709	2.191		
LINCK #24 55-14-020-QRY Created On: 10/01/18 Updated On:	Q	SW	SW	16	9N	15E	Dodge	0-225-286-2018	0.2	10.0	6.8	7.1	29.6	2.646	2.705	2.219		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
LINCK #24 55-14-020-QRY Created On: 08/17/22 Updated On:	Q	SW	SW	16	9N	15E	Dodge	0-225-253-2022		22.4	2.5	7.2	29.5					
LINCK #24 55-14-020-QRY Created On: 04/15/25 Updated On:	Q	SW	SW	16	9N	15E	Dodge	0-225-187-2025	0.8	14.8	3.4	8.2	32.4	2.665	2.713	1.809		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MAYVILLE WHITELIME 55-14-023-QRY Created On: 08/08/17 Updated On:	Q			1	11N	16E	Dodge	0-225-248-2017	2.3	1.5	0.2	6.6	29.0	2.704	2.748	1.628		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MAYVILLE WHITELIME 55-14-023-QRY Created On: 08/24/20 Updated On:	Q			1	11N	16E	Dodge	0-225-235-2020	1.8	3.3	0.2	6.8	30.1	2.725	2.764	1.419		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
DODGE -- WI																		
MAYVILLE WHITELIME 55-14-023-QRY Created On: 02/27/23 Updated On:	Q			1	11N	16E	Dodge	0-225-151-2023	2.1	7.5	5.1	6.0	29.7	2.712	2.754	1.530		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MICHEL'S NASBRO 55-14-025-QRY Created On: 01/04/16 Updated On:	Q	W	SE	18	13N	17E	Dodge	0-225-1-2016		0.4	1.3	7.5	32.2	2.714	2.746	1.179		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
MICHEL'S NASBRO 55-14-025-QRY Created On: 01/04/19 Updated On:	Q	W	SE	18	13N	17E	Dodge	0-225-1-2019	0.1	0.9	1.4	9.1	35.7	2.710	2.744	1.269		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
MICHEL'S NASBRO 55-14-025-QRY Created On: 01/04/22 Updated On:	Q	W	SE	18	13N	17E	Dodge	0-225-2-2022	0.0	0.5	1.0	7.2	30.8	2.731	2.763	1.155		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MICHEL'S NASBRO 55-14-025-QRY Created On: 01/02/25 Updated On:	Q	W	SE	18	13N	17E	Dodge	0-225-22-2025	0.0	0.5	1.2	8.5	34.4	2.714	2.748	1.240		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MICHEL'S WARMKA 55-14-034-QRY Created On: 01/02/25 Updated On:	Q	NE	NW	9	12N	14E	Dodge	0-225-23-2025	0.0	2.2	1.7	5.3	24.3	2.755	2.781	0.937		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MICHEL'S-WATERLOO 55-14-028-QRY Created On: 01/04/16 Updated On:	Q	NW	NW	34	9N	13E	Dodge	0-225-2-2016		0.4	0.5	4.1	21.8	2.655	2.667	0.461		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
DODGE -- WI																		
MICHEL'S-WATERLOO 55-14-028-QRY Created On: 01/04/19 Updated On:	Q	NW	NW	34	9N	13E	Dodge	0-225-2-2019		0.8	0.3	4.1	22.0	2.651	2.667	0.604		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MICHEL'S-WATERLOO 55-14-028-QRY Created On: 01/04/22 Updated On:	Q	NW	NW	34	9N	13E	Dodge	0-225-1-2022	0.0	0.1	0.2	5.2	26.1	2.662	2.673	0.397		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MICHEL'S-WATERLOO 55-14-028-QRY Created On: 01/02/25 Updated On:	Q	NW	NW	34	9N	13E	Dodge	0-225-25-2025	0.0	0.6	0.4	4.9	24.2	2.649	2.667	0.673		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
*WARMKA 55-14-034-QRY Created On: 01/03/17 Updated On:	Q	NE	NW	9	12N	14E	Dodge	0-225-8-2017		4.0	2.4	5.8	25.1	2.763	2.788	0.904		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
*WARMKA 55-14-034-QRY Created On: 04/01/19 Updated On:	Q	NE	NW	9	12N	14E	Dodge	0-225-118-2019		4.6	2.5	5.2	24.3	2.757	2.785	1.017		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
*WARMKA 55-14-034-QRY Created On: 01/04/22 Updated On:	Q	NE	NW	9	12N	14E	Dodge	0-225-3-2022	0.0	1.8	1.5	5.1	24.5	2.750	2.780	1.070		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
WESTPHAL 55-14-035-QRY Created On: 01/03/18 Updated On:	Q	SE	SE	8	10N	14E	Dodge	0-225-20-2018		13.5	8.9	5.4	25.0	2.689	2.733	1.636		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
DODGE -- WI																		
WESTPHAL 55-14-035-QRY Created On: 05/17/21 Updated On:	Q	SE	SE	8	10N	14E	Dodge	0-225-209-2021	0.0	8.6	8.2	5.7	25.3	2.689	2.732	1.614		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
WESTPHAL 55-14-035-QRY Created On: 02/06/23 Updated On:	Q	SE	SE	8	10N	14E	Dodge	0-225-141-2023	0.0	17.0	10.1	4.8	30.4	2.703	2.743	1.501		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
DOOR -- WI																		
BAILEYS HARBOR 55-15-001-QRY Created On: 01/21/16 Updated On:	Q	SW	NW	17	30N	28E	Door	0-225-73-2016	4.5	0.0	4.4	7.7	33.0	2.631	2.687	2.132		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
BAILEYS HARBOR 55-15-001-QRY Created On: 04/13/17 Updated On:	Q	SW	NW	17	30N	28E	Door	0-225-130-2017	1.3	0.0	2.9	7.6	32.6	2.637	2.692	2.074		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
BAILEYS HARBOR 55-15-001-QRY Created On: 01/02/20 Updated On:	Q	SW	NW	17	30N	28E	Door	0-225-6-2020		0.0	1.4	6.6	30.3	2.548	2.605	2.233		
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																	
BAILEYS HARBOR 55-15-001-QRY Created On: 01/03/23 Updated On:	Q	SW	NW	17	30N	28E	Door	0-225-38-2023	0.2	3.9	1.3	6.0	26.9	2.742	2.773	1.137		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
BIWERS 55-15-002-QRY Created On: 04/27/15 Updated On:	Q	NW	SE	10	30N	27E	Door	0-225-139-2015		0.0	1.0	6.4	24.1	2.760	2.783	0.829		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
DOOR -- WI																		
BIWERS 55-15-002-QRY Created On: 02/15/18 Updated On:	Q	NW	SE	10	30N	27E	Door	0-225-102-2018	0.1	1.0	1.0	6.3	25.9	2.759	2.783	0.876		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
BIWERS 55-15-002-QRY Created On: 01/06/21 Updated On:	Q	NW	SE	10	30N	27E	Door	0-225-113-2021	0.0	0.5	0.7	5.5	23.3	2.760	2.784	0.886		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
BIWERS 55-15-002-QRY Created On: 01/29/24 Updated On:	Q	NW	SE	10	30N	27E	Door	0-225-157-2024	0.1	0.8	0.4	5.4	22.7	2.760	2.783	0.837		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
CAREW - BRUSSELS 55-15-004-QRY Created On: 01/16/15 Updated On:	Q	NW	NW	21	26N	24E	Door	0-225-69-2015		0.0	3.3	7.2	27.5	2.749	2.778	1.052		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
CAREW - BRUSSELS 55-15-004-QRY Created On: 03/01/18 Updated On:	Q	NW	NW	21	26N	24E	Door	0-225-111-2018		0.0	5.2	6.0	26.6	2.773	2.793	0.717		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
CAREW - BRUSSELS 55-15-004-QRY Created On: 01/14/21 Updated On:	Q	NW	NW	21	26N	24E	Door	0-225-120-2021	0.0	0.0	0.9	5.4	24.8	2.780	2.798	0.655		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
CAREW - BRUSSELS 55-15-004-QRY Created On: 02/28/24 Updated On:	Q	NW	NW	21	26N	24E	Door	0-225-177-2024	0.0	0.0	1.7	6.4	27.4	2.772	2.790	0.650		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
DOOR -- WI																		
CLOVERLEAF QUARRY 55-15-032-QRY Created On: 03/13/24 Updated On:	Q	NW	SE	19	27N	25E	Door	0-225-202-2024	0.0	0.0	0.7	6.5	30.6	2.754	2.775	0.759		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
HIGH ROAD QUARRY 55-15-015-QRY Created On: 01/03/23 Updated On:	Q		NW	4	26N	24E	Door	0-225-42-2023	0.0	2.3	5.4	6.7	29.6	2.705	2.747	1.553		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
*ISLAND STONE 55-15-030-QRY Created On: 06/28/22 Updated On:	Q	SW	SW	32	34N	30E	Door	0-225-237-2022	1.4	0.0	7.7	5.6	26.8	2.658	2.705	1.777		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
JADIN #2 55-15-009-QRY Created On: 06/27/18 Updated On:	Q	SW	NE	33	26N	24E	Door	0-225-242-2018		0.0	1.4	7.2	30.8	2.740	2.769	1.054		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
JADIN #2 55-15-009-QRY Created On: 01/14/21 Updated On:	Q	SW	NE	33	26N	24E	Door	0-225-122-2021	0.0	0.0	0.3	6.9	31.1	2.709	2.742	1.219		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
JADIN #2 55-15-009-QRY Created On: 04/15/24 Updated On:	Q	SW	NE	33	26N	24E	Door	0-225-232-2024	0.0	0.0	2.5	6.8	31.7	2.708	2.743	1.286		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
KISSER 55-15-013-QRY Created On: 01/04/16 Updated On:	Q	NW	NW	20	27N	25E	Door	0-225-9-2016		3.0	2.5	6.4	26.3	2.762	2.788	0.957		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
DOOR -- WI																		
KISSER 55-15-013-QRY Created On: 01/08/19 Updated On:	Q	NW	NW	20	27N	25E	Door	0-225-73-2019		0.0	3.0	7.8	32.2	2.790	2.817	0.997		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
KISSER 55-15-013-QRY Created On: 01/10/22 Updated On:	Q	NW	NW	20	27N	25E	Door	0-225-97-2022	0.0	1.7	1.7	6.5	29.2	2.750	2.778	0.995		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
KISSER 55-15-013-QRY Created On: 01/02/25 Updated On:	Q	NW	NW	20	27N	25E	Door	0-225-60-2025	0.0	2.3	2.0	6.2	26.3	2.763	2.788	0.880		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MATHEY 55-15-014-QRY Created On: 07/08/15 Updated On:	Q	E	SE	22	28N	26E	Door	0-225-208-2015	0.1	0.0	0.6	5.7	25.8	2.793	2.811	0.616		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
MATHEY 55-15-014-QRY Created On: 01/04/18 Updated On:	Q	E	SE	22	28N	26E	Door	0-225-84-2018	1.0	3.3	1.7	8.0	30.8	2.748	2.780	1.144		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MATHEY 55-15-014-QRY Created On: 01/05/21 Updated On:	Q	E	SE	22	28N	26E	Door	0-225-107-2021	0.0	1.5	0.7	5.7	24.7	2.778	2.802	0.831		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MATHEY 55-15-014-QRY Created On: 01/02/24 Updated On:	Q	E	SE	22	28N	26E	Door	0-225-48-2024	0.1	0.0	0.6	0.9	29.5	2.778	2.797	0.705		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
DOOR -- WI																		
*MURRAY 55-15-017-PIT Created On: 07/30/15 Updated On:	P	NE	SE	26	26N	23E	Door	0-225-220-2015	0.1	0.0	9.3	8.2	36.1	2.638	2.697	2.256		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
*MURRAY 55-15-017-PIT Created On: 08/25/20 Updated On:	P	NE	SE	26	26N	23E	Door	0-225-236-2020	1.5	0.0	3.4	6.5	30.2	2.693	2.736	1.598		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
NEBEL 55-15-003-QRY Created On: 08/19/15 Updated On:	Q	NE	SW	20	26N	24E	Door	0-225-231-2015		0.0	8.1	4.9	22.7	2.780	2.807	0.971		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
NEBEL 55-15-003-QRY Created On: 04/01/25 Updated On:	Q	NE	SW	20	26N	24E	Door	0-225-181-2025	0.0	0.0	2.2	5.0	24.2	2.784	2.804	0.744		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
PETERS-BRUSSELS 55-15-003-PIT Created On: 04/14/16 Updated On:	P	SE	NW	26	26N	23E	Door	0-225-148-2016	0.4	0.0	9.4	8.0	25.5	2.691	2.736	1.676		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
PETERS-BRUSSELS 55-15-003-PIT Created On: 05/30/17 Updated On:	P	SE	NW	26	26N	23E	Door	0-225-195-2017	0.4	0.0	6.3	8.2	33.5	2.714	2.763	1.795		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
PETERS-BRUSSELS 55-15-003-PIT Created On: 04/20/23 Updated On:	P	SE	NW	26	26N	23E	Door	0-225-203-2023	0.2	0.0	6.9	6.1	28.5	2.719	2.757	1.393		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
DOOR -- WI																		
*SITTE 55-15-028-QRY Created On: 03/22/19 Updated On:	Q	S	NE	2	31N	28E	Door	0-225-113-2019	5.5	0.0	5.0	6.1	27.5	2.618	2.674	2.165		
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																	
*SITTE 55-15-028-QRY Created On: 03/07/22 Updated On:	Q	S	NE	2	31N	28E	Door	0-225-138-2022	2.1	0.0	12.0	6.4	29.4	2.620	2.674	2.073		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
STURGEON BAY - MM 55-15-022-QRY Created On: 01/05/17 Updated On:	Q	SE	NW	21	27N	25E	Door	0-225-21-2017		0.0	1.9	7.8	27.6	2.769	2.789	0.736		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
STURGEON BAY - MM 55-15-022-QRY Created On: 01/02/20 Updated On:	Q	SE	NW	21	27N	25E	Door	0-225-7-2020	0.0	0.0	0.5	5.4	25.4	2.779	2.796	0.611		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
STURGEON BAY - MM 55-15-022-QRY Created On: 01/03/23 Updated On:	Q	SE	NW	21	27N	25E	Door	0-225-46-2023		7.2	1.8	5.7	24.0	2.773	2.792	0.688		
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																	
TAGGE 55-15-023-PIT Created On: 01/05/17 Updated On:	P		NE	31	27N	26E	Door	0-225-22-2017	0.3	0.0	0.3	7.2	30.2	2.726	2.763	1.373		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
TAGGE 55-15-023-PIT Created On: 01/04/22 Updated On:	P		NE	31	27N	26E	Door	0-225-15-2022	0.1	2.2	1.8	6.4	27.5	2.733	2.764	1.151		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
DOOR -- WI																		
UNION	P	SW	NW	36	26N	23E	Door	0-225-209-2015	0.1	0.0	7.1	6.0	25.2	2.710	2.748	1.378		
55-15-024-PIT	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
Created On: 07/08/15																		
Updated On:																		
UNION	P	SW	NW	36	26N	23E	Door	0-225-221-2022	0.2	8.9	2.1	5.5	26.8	2.704	2.741	1.368		
55-15-024-PIT	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
Created On: 06/13/22																		
Updated On:																		
DOUGLAS -- WI																		
COLBY	Q	NE	SW	25	48N	11W	Douglas	0-225-66-2017		0.0	14.4	4.5	20.3	2.798	2.834	1.297		
55-16-005-QRY	Approved Use : Base Aggregate																	
Created On: 02/13/17																		
Updated On:																		
COLBY	Q	NE	SW	25	48N	11W	Douglas	0-225-59-2020	0.4	0.0	15.5	5.4	21.6	2.818	2.857	1.368		
55-16-005-QRY	Approved Use : Base Aggregate																	
Created On: 01/08/20																		
Updated On:																		
COLBY	Q	NE	SW	25	48N	11W	Douglas	0-225-90-2023	0.0	7.7	13.7	4.7	19.0	2.801	2.841	1.421		
55-16-005-QRY	Approved Use : Base Aggregate																	
Created On: 01/04/23																		
Updated On:																		
HOME RUN	Q	NE	SE	21	48N	10W	Douglas	0-225-193-2017		18.3	7.3	4.0	32.4	2.753	2.789	1.311		
55-16-008-QRY	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
Created On: 05/19/17																		
Updated On:																		
HOME RUN	Q	NE	SE	21	48N	10W	Douglas	0-225-153-2020		0.0	2.4	2.5	10.8	2.852	2.886	1.191		
55-16-008-QRY	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																	
Created On: 04/16/20																		
Updated On:																		

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
DOUGLAS -- WI																		
HOME RUN 55-16-008-QRY Created On: 01/04/23 Updated On:	Q	NE	SE	21	48N	10W	Douglas	0-225-88-2023	0.0	0.0	2.1	2.7	13.4	2.837	2.869	1.105		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
HOME RUN 55-16-008-QRY Created On: 03/04/25 Updated On:	Q	NE	SE	21	48N	10W	Douglas	0-225-159-2025	0.5	7.0	4.8	3.7	15.9	2.767	2.802	1.275		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
KIMMES 55-16-011-QRY Created On: 02/13/17 Updated On:	Q	SW	NW	14	47N	14W	Douglas	0-225-67-2017		0.0	10.0	4.9	20.6	2.692	2.731	1.468		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
KIMMES 55-16-011-QRY Created On: 01/08/20 Updated On:	Q	SW	NW	14	47N	14W	Douglas	0-225-56-2020	0.0	0.0	4.2	2.8	13.6	2.756	2.786	1.086		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
KIMMES 55-16-011-QRY Created On: 01/03/23 Updated On:	Q	SW	NW	14	47N	14W	Douglas	0-225-56-2023	0.0	4.8	1.6	3.3	13.3	2.771	2.800	1.051		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MIKKOLA QUARRY 55-16-014-QRY Created On: 08/15/17 Updated On:	Q	NE	NE	35	48N	11W	Douglas	0-225-254-2017		0.0	0.9	3.1	13.9	2.620	2.643	0.891		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MIKKOLA QUARRY 55-16-014-QRY Created On: 01/06/20 Updated On:	Q	NE	NE	35	48N	11W	Douglas	0-225-30-2020	0.1	0.0	4.9	3.1	13.9	2.582	2.615	1.247		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
DOUGLAS -- WI																		
MIKKOLA QUARRY 55-16-014-QRY Created On: 01/04/23 Updated On:	Q	NE	NE	35	48N	11W	Douglas	0-225-89-2023	0.6	2.4	2.9	3.4	15.0	2.645	2.682	1.392		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MILESTONE-BUCKLEY 55-16-002-QRY Created On: 02/13/17 Updated On:	Q	NW	NW	32	48N	12W	Douglas	0-225-69-2017		0.0	9.5	4.8	21.2	2.880	2.910	1.027		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
MILESTONE-BUCKLEY 55-16-002-QRY Created On: 08/15/17 Updated On:	Q	NW	NW	32	48N	12W	Douglas	0-225-253-2017	0.1	0.0	6.7	5.6	22.4	2.870	2.887	0.584		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
MILESTONE-BUCKLEY 55-16-002-QRY Created On: 01/08/20 Updated On:	Q	NW	NW	32	48N	12W	Douglas	0-225-58-2020	0.0	0.0	5.6	5.3	22.3	2.816	2.841	0.882		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MILESTONE-BUCKLEY 55-16-002-QRY Created On: 01/03/23 Updated On:	Q	NW	NW	32	48N	12W	Douglas	0-225-59-2023	0.0	1.5	2.3	3.5	17.3	2.817	2.845	1.009		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
OLSON 55-16-017-QRY Created On: 06/13/16 Updated On:	Q	NW	NW	24	48N	10W	Douglas	0-225-198-2016		1.7	0.2	2.4	11.9	2.853	2.885	1.121		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
OLSON 55-16-017-QRY Created On: 06/03/21 Updated On:	Q	NW	NW	24	48N	10W	Douglas	0-225-218-2021	0.7	0.0	4.0	4.4	18.7	2.844	2.872	1.016		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
DOUGLAS -- WI																		
OLSON 55-16-017-QRY Created On: 04/15/24 Updated On:	Q	NW	NW	24	48N	10W	Douglas	0-225-228-2024	0.5	0.0	2.3	3.5	14.7	2.844	2.880	1.285		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
SOLON SPRINGS 55-16-024-QRY Created On: 05/09/16 Updated On:	Q	NE	NW	18	45N	11W	Douglas	0-225-167-2016		0.0	4.6	3.8	16.7	2.807	2.839	1.155		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
SOLON SPRINGS 55-16-024-QRY Created On: 01/07/19 Updated On:	Q	NE	NW	18	45N	11W	Douglas	0-225-60-2019	0.3	0.0	8.8	4.6	19.4	2.780	2.824	1.552		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
SOLON SPRINGS 55-16-024-QRY Created On: 07/07/22 Updated On:	Q	NE	NW	18	45N	11W	Douglas	0-225-245-2022	1.4	0.0	4.7	4.8	19.0	2.778	2.807	1.041		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
SOLON SPRINGS 55-16-024-QRY Created On: 01/02/25 Updated On:	Q	NE	NW	18	45N	11W	Douglas	0-225-37-2025	0.0	11.2	11.9	4.5	18.7	2.746	2.802	2.068		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
STUPAK 55-16-025-QRY Created On: 05/08/15 Updated On:	Q	NW	NW	29	47N	14W	Douglas	0-225-154-2015		0.0	3.2	2.9	15.0	2.791	2.810	0.680		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
STUPAK 55-16-025-QRY Created On: 01/03/18 Updated On:	Q	NW	NW	29	47N	14W	Douglas	0-225-17-2018		0.0	9.1	3.5	15.5	2.686	2.719	1.235		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
DOUGLAS -- WI																		
STUPAK 55-16-025-QRY Created On: 01/05/21 Updated On:	Q	NW	NW	29	47N	14W	Douglas	0-225-68-2021	0.0	16.5	10.9	3.5	15.2	2.715	2.749	1.259		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
STUPAK 55-16-025-QRY Created On: 01/02/24 Updated On:	Q	NW	NW	29	47N	14W	Douglas	0-225-92-2024	0.0	0.0	10.6	3.6	17.2	2.633	2.684	1.930		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
THUNDER HILL AGGREGATE 55-16-026-QRY Created On: 02/09/18 Updated On:	Q		NE	13	47N	14W	Douglas	0-225-98-2018	0.0	0.0	0.4	3.3	11.3	2.837	2.872	1.222		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
THUNDER HILL AGGREGATE 55-16-026-QRY Created On: 05/20/24 Updated On:	Q		NE	13	47N	14W	Douglas	0-225-260-2024	0.0	0.0	5.2	3.3	16.2	2.813	2.835	0.771		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
DUNN -- WI																		
GATES #238 55-17-011-QRY Created On: 01/08/15 Updated On:	Q	S	NW	17	28N	14W	Dunn	0-225-36-2015	0.7	0.0	4.5	7.3	32.3	2.629	2.688	2.238		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
GATES #238 55-17-011-QRY Created On: 07/17/15 Updated On:	Q	S	NW	17	28N	14W	Dunn	0-225-215-2015		0.0	1.9	7.5	31.3	2.608	2.669	2.323		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
GATES #238 55-17-011-QRY Created On: 04/21/17 Updated On:	Q	S	NW	17	28N	14W	Dunn	0-225-142-2017	1.3	0.0	2.0	7.7	31.1	2.610	2.672	2.371		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
DUNN -- WI																		
GATES #238 55-17-011-QRY Created On: 08/09/19 Updated On:	Q	S	NW	17	28N	14W	Dunn	0-225-259-2019	2.9	0.0	5.3	11.3	39.7	2.558	2.641	3.218		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
GATES #238 55-17-011-QRY Created On: 04/05/22 Updated On:	Q	S	NW	17	28N	14W	Dunn	0-225-157-2022	6.5	1.8	10.6	11.6	43.4	2.537	2.614	3.053		
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																	
GATES #238 55-17-011-QRY Created On: 01/02/25 Updated On:	Q	S	NW	17	28N	14W	Dunn	0-225-43-2025	2.0	1.7	6.7	10.8	41.2	2.568	2.640	2.794		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
HAFFELDER 55-17-013-QRY Created On: 06/08/15 Updated On:	Q	NE	NE	23	28N	14W	Dunn	0-225-189-2015		0.0	4.4	7.5	39.1	2.571	2.641	2.714		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
HAFFELDER 55-17-013-QRY Created On: 01/03/18 Updated On:	Q	NE	NE	23	28N	14W	Dunn	0-225-32-2018	2.0	0.0	6.3	10.5	36.9	2.531	2.616	3.356		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
HAFFELDER 55-17-013-QRY Created On: 01/05/21 Updated On:	Q	NE	NE	23	28N	14W	Dunn	0-225-75-2021	1.4	0.0	0.8	9.7	35.3	2.559	2.641	3.186		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
HAFFELDER 55-17-013-QRY Created On: 01/02/24 Updated On:	Q	NE	NE	23	28N	14W	Dunn	0-225-75-2024	1.7	6.7	6.7	12.2	43.3	2.548	2.629	3.169		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
DUNN -- WI																	
HUGHES 55-17-015-QRY Created On: 01/05/17 Updated On:	Q		SW	15	28N	14W	Dunn	0-225-47-2017		0.0	5.4	9.0	35.8	2.594	2.661	2.585	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
HUGHES 55-17-015-QRY Created On: 08/15/19 Updated On:	Q		SW	15	28N	14W	Dunn	0-225-261-2019	0.9	0.0	5.5	7.9	33.5	2.601	2.668	2.584	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
HUGHES 55-17-015-QRY Created On: 04/05/22 Updated On:	Q		SW	15	28N	14W	Dunn	0-225-161-2022	2.3	1.4	5.0	11.4	41.0	2.586	2.650	2.464	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
HUGHES 55-17-015-QRY Created On: 01/02/25 Updated On:	Q		SW	15	28N	14W	Dunn	0-225-36-2025	1.0	0.9	10.8	9.7	40.4	2.579	2.650	2.727	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
EAU CLAIRE -- WI																	
AMERICAN MATERIALS #31 55-18-003-PIT Created On: 01/05/17 Updated On:	P	N	NE	2	26N	10W	Eau Claire	0-225-32-2017		0.0	2.9	4.4	20.9	2.635	2.666	1.171	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
AMERICAN MATERIALS #31 55-18-003-PIT Created On: 01/04/21 Updated On:	P	N	NE	2	26N	10W	Eau Claire	0-225-36-2021	1.1	5.4	5.7	4.1	20.2	2.638	2.668	1.166	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
MILESTONE RIEKEMANN PIT #222 55-18-011-PIT Created On: 01/03/18 Updated On:	P	SE	SW	4	26N	10W	Eau Claire	0-225-41-2018	1.7	0.0	2.0	3.8	19.4	2.641	2.670	1.078	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
EAU CLAIRE -- WI																		
MILESTONE RIEKEMANN PIT #222 55-18-011-PIT Created On: 01/03/23 Updated On:	P	SE	SW	4	26N	10W	Eau Claire	0-225-52-2023	0.7	4.4	3.1	4.2	20.9	2.632	2.665	1.261		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
FLORENCE -- WI																		
DELARULLE 55-19-003-PIT Created On: 01/04/19 Updated On:	P	SE	SW	12	39N	17E	Florence	0-225-12-2019	0.0	0.0	3.2	6.2	29.1	2.619	2.664	1.744		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
DELARULLE 55-19-003-PIT Created On: 01/02/24 Updated On:	P	SE	SW	12	39N	17E	Florence	0-225-12-2024	1.1	0.0	0.5	5.9	26.0	2.641	2.682	1.551		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
SANICKI 55-19-012-PIT Created On: 05/13/21 Updated On:	P		SE	31	38N	17E	Florence	0-225-207-2021	0.2	0.4	0.7	4.9	21.1	2.725	2.747	0.805		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
SPREAD EAGLE 55-19-009-QRY Created On: 01/12/16 Updated On:	Q	NW	SE	11	39N	19E	Florence	0-225-50-2016		0.0	0.3	2.9	12.4	2.895	2.903	0.294		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
SPREAD EAGLE 55-19-009-QRY Created On: 01/04/19 Updated On:	Q	NW	SE	11	39N	19E	Florence	0-225-11-2019		0.2	0.1	1.9	9.1	2.951	2.964	0.429		
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																	
SPREAD EAGLE 55-19-009-QRY Created On: 01/04/22 Updated On:	Q	NW	SE	11	39N	19E	Florence	0-225-24-2022	0.0	1.0	0.2	6.1	12.4	2.973	2.982	0.291		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
Source Name	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
FLORENCE -- WI																		
SPREAD EAGLE	Q	NW	SE	11	39N	19E	Florence	0-225-65-2025	0.0	0.0	0.4	2.3	9.9	2.955	2.965	0.361		
55-19-009-QRY	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
Created On: 01/02/25																		
Updated On:																		
FOND DU LAC -- WI																		
*175 WEST	Q	NE	SW	10	14N	17E	Fond Du Lac	0-225-214-2020	0.0	4.9	1.4	7.7	32.8	2.724	2.757	1.200		
55-20-054-QRY	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
Created On: 07/15/20																		
Updated On:																		
BATTERMAN	Q	SW	SW	11	14N	17E	Fond Du Lac	0-225-60-2017		0.6	1.4	9.1	40.8	2.696	2.725	1.060		
55-20-050-QRY	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
Created On: 02/03/17																		
Updated On:																		
BATTERMAN	Q	SW	SW	11	14N	17E	Fond Du Lac	0-225-116-2020	0.2	0.5	2.1	8.2	34.7	2.753	2.775	0.821		
55-20-050-QRY	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
Created On: 03/02/20																		
Updated On:																		
BATTERMAN	Q	SW	SW	11	14N	17E	Fond Du Lac	0-225-101-2023	0.0	3.0	1.2	6.5	28.9	2.794	2.808	0.508		
55-20-050-QRY	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
Created On: 01/04/23																		
Updated On:																		
BREAKNECK ROAD	Q	NE	NW	34	14N	16E	Fond Du Lac	0-225-121-2021	0.0	0.7	0.6	5.8	25.8	2.773	2.792	0.676		
55-20-055-QRY	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
Created On: 01/14/21																		
Updated On:																		
BREAKNECK ROAD	Q	NE	NW	34	14N	16E	Fond Du Lac	0-225-50-2024	0.1	1.3	1.0	5.9	26.7	2.772	2.790	0.646		
55-20-055-QRY	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
Created On: 01/02/24																		
Updated On:																		

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
FOND DU LAC -- WI																		
*BUECHEL STONE OAKFIELD 55-20-056-QRY Created On: 03/24/21 Updated On:	Q	NE	NE	34	14N	16E	Fond Du Lac	0-225-158-2021		0.0	1.0	2.7	5.5	26.0	2.738	2.766	1.007	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
*BYRON 55-20-012-QRY Created On: 01/08/15 Updated On:	Q	N	SE	10	14N	17E	Fond Du Lac	0-225-29-2015			0.5	1.5	5.5	26.4	2.735	2.765	1.106	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
*BYRON 55-20-012-QRY Created On: 03/16/18 Updated On:	Q	N	SE	10	14N	17E	Fond Du Lac	0-225-122-2018			0.6	0.7	5.5	27.8	2.725	2.758	1.203	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
*BYRON 55-20-012-QRY Created On: 01/05/21 Updated On:	Q	N	SE	10	14N	17E	Fond Du Lac	0-225-49-2021		0.0	1.2	0.9	5.8	28.1	2.738	2.767	1.045	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
CAREW - EDEN 55-20-058-PIT Created On: 01/25/16 Updated On:	P	W	SE	23	14N	18E	Fond Du Lac	0-225-81-2016		0.3	0.0	2.9	8.0	33.0	2.742	2.772	1.093	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
CAREW - EDEN 55-20-058-PIT Created On: 02/08/21 Updated On:	P	W	SE	23	14N	18E	Fond Du Lac	0-225-123-2021		0.5	2.9	3.6	7.6	33.2	2.752	2.783	1.128	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
CAREW ALTO/WAUPUN 55-20-008-QRY Created On: 03/08/17 Updated On:	Q	S	NE	36	14N	14E	Fond Du Lac	0-225-78-2017			6.0	4.4	6.3	27.9	2.767	2.790	0.826	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
FOND DU LAC -- WI																		
CAREW ALTO/WAUPUN 55-20-008-QRY Created On: 01/30/20 Updated On:	Q	S	NE	36	14N	14E	Fond Du Lac	0-225-99-2020	0.0	4.0	3.5	6.2	27.1	2.764	2.791	0.974		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
CAREW ALTO/WAUPUN 55-20-008-QRY Created On: 01/04/23 Updated On:	Q	S	NE	36	14N	14E	Fond Du Lac	0-225-100-2023	0.0	3.9	1.6	6.3	28.2	2.771	2.794	0.821		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
EVENSON - BERTRAM 55-20-011-QRY Created On: 01/08/15 Updated On:	Q	NE	NW	15	16N	18E	Fond Du Lac	0-225-26-2015		0.2	3.1	11.2	41.8	2.715	2.748	1.245		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
EVENSON - BERTRAM 55-20-011-QRY Created On: 04/13/17 Updated On:	Q	NE	NW	15	16N	18E	Fond Du Lac	0-225-128-2017		1.0	1.2	12.9	44.2	2.714	2.750	1.348		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
EVENSON - BERTRAM 55-20-011-QRY Created On: 01/30/20 Updated On:	Q	NE	NW	15	16N	18E	Fond Du Lac	0-225-106-2020	0.0	0.6	1.1	11.0	42.5	2.720	2.758	1.424		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
EVENSON - BERTRAM 55-20-011-QRY Created On: 01/04/24 Updated On:	Q	NE	NW	15	16N	18E	Fond Du Lac	0-225-149-2024	0.3	0.6	1.0	8.7	36.6	2.759	2.783	0.870		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
GRAHL-EMPIRE 55-20-014-PIT Created On: 05/12/16 Updated On:	P	S	SE	36	15N	18E	Fond Du Lac	0-225-173-2016	0.1	0.0	2.2	6.5	29.8	2.740	2.768	1.052		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
FOND DU LAC -- WI																		
GRAHL-EMPIRE 55-20-014-PIT Created On: 04/13/21 Updated On:	P	S	SE	36	15N	18E	Fond Du Lac	0-225-178-2021		1.0	4.9	3.2	5.7	28.7	2.734	2.765	1.105	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
GUELIG 55-20-015-PIT Created On: 01/21/16 Updated On:	P	NW	SE	9	16N	19E	Fond Du Lac	0-225-66-2016		0.0	3.3	4.7	7.4	31.7	2.739	2.774	1.295	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
GUELIG 55-20-015-PIT Created On: 01/05/21 Updated On:	P	NW	SE	9	16N	19E	Fond Du Lac	0-225-102-2021		0.0	3.6	1.1	7.5	31.4	2.738	2.771	1.206	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
GUELIG NORTH 55-20-059-PIT Created On: 10/21/21 Updated On:	P	NW	NE	9	16N	19E	Fond Du Lac	0-225-270-2021		0.3	0.0	4.6	7.5	32.3	2.761	2.789	1.047	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
HOLLATZ 55-20-017-PIT Created On: 01/12/16 Updated On:	P	NE	NW	17	16N	14E	Fond Du Lac	0-225-51-2016			0.0	1.4	5.0	24.2	2.729	2.760	1.132	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
HOLLATZ 55-20-017-PIT Created On: 01/04/21 Updated On:	P	NE	NW	17	16N	14E	Fond Du Lac	0-225-45-2021		0.0	3.7	2.4	4.7	23.3	2.718	2.754	1.341	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
LINCK #26 55-20-028-QRY Created On: 05/09/19 Updated On:	Q	NW	SE	36	14N	14E	Fond Du Lac	0-225-183-2019		0.0	0.9	0.9	6.3	26.4	2.778	2.800	0.809	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
FOND DU LAC -- WI																		
LINCK #26 55-20-028-QRY Created On: 06/28/22 Updated On:	Q	NW	SE	36	14N	14E	Fond Du Lac	0-225-236-2022	0.0	4.4	0.5	6.4	25.6	2.780	2.802	0.798		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
LINCK #26 55-20-028-QRY Created On: 07/23/25 Updated On:	Q	NW	SE	36	14N	14E	Fond Du Lac	0-225-225-2025	0.2	2.7	0.4	6.6	26.9	2.770	2.793	0.824		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MICHELS - TAYCHEEDAH 55-20-021-QRY Created On: 01/04/17 Updated On:	Q	SW	NE	16	16N	18E	Fond Du Lac	0-225-11-2017	1.3	0.6	1.4	7.6	33.4	2.749	2.777	1.027		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
MICHELS - TAYCHEEDAH 55-20-021-QRY Created On: 01/08/20 Updated On:	Q	SW	NE	16	16N	18E	Fond Du Lac	0-225-70-2020	0.2	0.9	1.4	9.2	38.3	2.740	2.770	1.088		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MICHELS - TAYCHEEDAH 55-20-021-QRY Created On: 01/03/23 Updated On:	Q	SW	NE	16	16N	18E	Fond Du Lac	0-225-43-2023	0.2	0.7	2.1	7.3	33.5	2.742	2.774	1.175		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
*MICHELS HAMILTON HILL 55-20-024-QRY Created On: 07/07/21 Updated On:	Q		NW	10	14N	17E	Fond Du Lac	0-225-243-2021	1.6	7.4	7.9	12.7	41.3	2.697	2.742	1.665		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
*MICHELS KETTER 55-20-025-PIT Created On: 03/19/15 Updated On:	P		SW	4	13N	19E	Fond Du Lac	0-225-100-2015	1.1	0.0	4.1	7.9	32.8	2.725	2.758	1.180		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
FOND DU LAC -- WI																		
*MICHELS KETTER 55-20-025-PIT Created On: 01/08/20 Updated On:	P		SW	4	13N	19E	Fond Du Lac	0-225-74-2020		2.0	8.5	4.0	8.5	34.3	2.715	2.755	1.466	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MICHELS MARBLEHEAD 55-20-026-QRY Created On: 01/04/16 Updated On:	Q	NE	NE	7	14N	18E	Fond Du Lac	0-225-13-2016			2.3	1.1	8.4	34.6	2.760	2.782	0.806	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
MICHELS MARBLEHEAD 55-20-026-QRY Created On: 01/04/19 Updated On:	Q	NE	NE	7	14N	18E	Fond Du Lac	0-225-19-2019			5.0	2.7	9.3	36.0	2.739	2.766	0.981	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MICHELS MARBLEHEAD 55-20-026-QRY Created On: 01/04/22 Updated On:	Q	NE	NE	7	14N	18E	Fond Du Lac	0-225-23-2022		0.0	2.6	1.6	8.8	35.3	2.739	2.770	1.140	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MICHELS MARBLEHEAD 55-20-026-QRY Created On: 01/02/25 Updated On:	Q	NE	NE	7	14N	18E	Fond Du Lac	0-225-57-2025		0.0	2.2	2.7	8.3	34.9	2.739	2.765	0.925	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
*MICHELS-WAUPUN 55-20-031-QRY Created On: 01/04/16 Updated On:	Q	S	NW	36	14N	14E	Fond Du Lac	0-225-8-2016			4.5	4.2	6.5	27.5	2.778	2.801	0.828	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
*MICHELS-WAUPUN 55-20-031-QRY Created On: 01/08/19 Updated On:	Q	S	NW	36	14N	14E	Fond Du Lac	0-225-71-2019		0.0	9.5	6.0	6.7	30.9	2.798	2.822	0.865	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
FOND DU LAC -- WI																		
*MICHEL'S-WAUPUN 55-20-031-QRY Created On: 01/04/22 Updated On:	Q	S	NW	36	14N	14E	Fond Du Lac	0-225-19-2022	0.0	5.6	2.8	6.0	28.6	2.764	2.791	0.973		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MICHEL'S/BERRES 55-20-004-PIT Created On: 01/04/19 Updated On:	P	SW	SE	32	14N	19E	Fond Du Lac	0-225-17-2019	0.8	0.0	2.2	8.9	34.6	2.728	2.764	1.316		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
MICHEL'S/BERRES 55-20-004-PIT Created On: 01/02/24 Updated On:	P	SW	SE	32	14N	19E	Fond Du Lac	0-225-52-2024	1.0	0.0	2.9	8.6	34.2	2.735	2.764	1.025		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MICHEL'S/BERRES 55-20-058-QRY Created On: 05/20/24 Updated On:	Q	SW	SE	32	14N	19E	Fond Du Lac	0-225-259-2024	6.6	10.0	4.7	7.9	32.2	2.655	2.703	1.820		
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																	
*OAKFIELD STONE FOND DU LAC 55-20-033-QRY Created On: 04/22/20 Updated On:	Q	SE	SE	10	14N	17E	Fond Du Lac	0-225-154-2020	0.0	2.2	1.7	5.7	26.5	2.771	2.796	0.879		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
R & R WASH 55-20-035-PIT Created On: 04/24/19 Updated On:	P	E	SW	7	16N	14E	Fond Du Lac	0-225-164-2019	1.9	4.4	4.0	7.8	31.5	2.704	2.743	1.446		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
R & R WASH 55-20-035-PIT Created On: 01/02/24 Updated On:	P	E	SW	7	16N	14E	Fond Du Lac	0-225-132-2024	7.6	2.0	8.4	10.6	37.8	2.642	2.693	1.903		
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
FOND DU LAC -- WI																		
RADEMANN STONE 55-20-036-QRY Created On: 05/08/15 Updated On:	Q	NE	SW	11	14N	17E	Fond Du Lac	0-225-156-2015		1.2	0.4	6.9	29.4	2.778	2.795	0.615		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
RADEMANN STONE 55-20-036-QRY Created On: 06/27/18 Updated On:	Q	NE	SW	11	14N	17E	Fond Du Lac	0-225-241-2018		1.0	1.0	6.3	30.2	2.759	2.781	0.797		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
RADEMANN STONE 55-20-036-QRY Created On: 04/30/21 Updated On:	Q	NE	SW	11	14N	17E	Fond Du Lac	0-225-197-2021	0.7	1.1	0.5	7.7	31.5	2.739	2.763	0.867		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
RADEMANN STONE 55-20-036-QRY Created On: 01/02/24 Updated On:	Q	NE	SW	11	14N	17E	Fond Du Lac	0-225-108-2024	0.0	0.7	0.7	6.2	28.4	2.770	2.790	0.719		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
REEDS CORNER 55-20-039-PIT Created On: 01/16/15 Updated On:	P	E	NW	12	15N	14E	Fond Du Lac	0-225-67-2015		0.0	3.0	7.0	30.3	2.751	2.785	1.215		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
REEDS CORNER 55-20-039-PIT Created On: 05/19/20 Updated On:	P	E	NW	12	15N	14E	Fond Du Lac	0-225-181-2020	0.0	0.0	4.3	5.5	25.8	2.774	2.801	0.973		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
REEDS CORNER 55-20-039-PIT Created On: 05/14/25 Updated On:	P	E	NW	12	15N	14E	Fond Du Lac	0-225-204-2025	0.3	0.0	3.4	6.4	29.3	2.742	2.774	1.175		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
FOND DU LAC -- WI																		
RLAM (RIPON LIME & MATERIALS) 55-20-035-QRY Created On: 02/06/23 Updated On:	Q	SW	NW	20	16N	14E	Fond Du Lac	0-225-135-2023	0.2	13.7	5.9	7.7	32.3	2.702	2.744	1.525		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
RLAM (RIPON LIME & MATERIALS) 55-20-035-QRY Created On: 01/04/24 Updated On:	Q	SW	NW	20	16N	14E	Fond Du Lac	0-225-145-2024	0.4	2.8	3.3	7.4	32.6	2.710	2.747	1.369		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
RUDINGER 55-20-041-QRY Created On: 01/08/15 Updated On:	Q		NW	11	14N	17E	Fond Du Lac	0-225-28-2015		0.4	1.9	8.0	34.1	2.730	2.758	1.030		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
RUDINGER 55-20-041-QRY Created On: 03/07/16 Updated On:	Q		NW	11	14N	17E	Fond Du Lac	0-225-95-2016		1.0	1.3	5.2	25.1	2.762	2.785	0.866		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
RUDINGER 55-20-041-QRY Created On: 01/04/19 Updated On:	Q		NW	11	14N	17E	Fond Du Lac	0-225-20-2019	0.7	1.5	0.9	5.7	27.2	2.760	2.786	0.950		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
RUDINGER 55-20-041-QRY Created On: 01/04/22 Updated On:	Q		NW	11	14N	17E	Fond Du Lac	0-225-21-2022	0.0	0.7	1.5	6.2	28.8	2.727	2.761	1.255		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
RUDINGER 55-20-041-QRY Created On: 01/02/24 Updated On:	Q		NW	11	14N	17E	Fond Du Lac	0-225-101-2024	0.0	0.7	0.8	5.6	27.1	2.775	2.794	0.692		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
FOND DU LAC -- WI																		
STEGER 55-20-057-PIT Created On: 03/24/21 Updated On:	P	SW	SW	24	13N	18E	Fond Du Lac	0-225-157-2021		0.1	0.0	3.0	6.4	29.3	2.767	2.790	0.822	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
STRAUB 55-20-006-PIT Created On: 01/04/19 Updated On:	P		W	23	14N	18E	Fond Du Lac	0-225-18-2019			4.9	0.8	7.1	30.0	2.758	2.785	0.984	
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																	
STRAUB 55-20-006-PIT Created On: 01/02/24 Updated On:	P		W	23	14N	18E	Fond Du Lac	0-225-100-2024		0.8	2.9	0.2	6.1	26.3	2.772	2.795	0.806	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
THACKRAY 55-20-048-PIT Created On: 04/10/19 Updated On:	P			13	15N	19E	Fond Du Lac	0-225-129-2019		0.3	0.0	0.9	7.6	33.6	2.748	2.775	0.967	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
THACKRAY 55-20-048-PIT Created On: 01/02/24 Updated On:	P			13	15N	19E	Fond Du Lac	0-225-53-2024		1.1	0.0	1.1	6.0	28.0	2.766	2.787	0.752	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
*THACKRAY SOUTH 55-20-053-PIT Created On: 05/15/20 Updated On:	P	SE	NW	13	15N	19E	Fond Du Lac	0-225-179-2020		0.0	0.0	2.3	7.8	36.0	2.725	2.760	1.289	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
FOREST -- WI																		
FLANNERY 55-21-004-PIT Created On: 05/11/15 Updated On:	P	SW	SE	33	36N	13E	Forest	0-225-165-2015			0.0	0.5	5.4	23.3	2.701	2.729	1.042	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
FOREST -- WI																		
FLANNERY 55-21-004-PIT Created On: 07/16/20 Updated On:	P	SW	SE	33	36N	13E	Forest	0-225-221-2020	0.0	0.0	0.4	5.2	23.5	2.743	2.762	0.685		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
FLANNERY 55-21-004-PIT Created On: 02/24/25 Updated On:	P	SW	SE	33	36N	13E	Forest	0-225-157-2025	0.8	0.0	1.1	4.6	21.3	2.731	2.756	0.901		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
HAGENY 55-21-008-PIT Created On: 08/14/24 Updated On:	P	NE	SE	2	35N	12E	Forest	0-225-296-2024	0.3	0.0	2.7	6.2	25.6	2.704	2.731	0.997		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
ISON 55-21-011-PIT Created On: 08/16/16 Updated On:	P	SE	NW	19	37N	13E	Forest	0-225-240-2016		0.0	0.6	6.5	26.2	2.696	2.713	0.646		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
ISON 55-21-011-PIT Created On: 01/04/21 Updated On:	P	SE	NW	19	37N	13E	Forest	0-225-12-2021	0.0	1.6	0.8	4.8	21.3	2.673	2.695	0.795		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
LABINE 55-21-21-PIT Created On: 08/22/17 Updated On:	P	S	SW	12	37N	16E	Forest	0-225-258-2017	0.8	0.0	0.5	5.1	19.9	2.741	2.762	0.732		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
LABINE 55-21-21-PIT Created On: 06/13/22 Updated On:	P	S	SW	12	37N	16E	Forest	0-225-227-2022	0.0	0.6	0.8	4.0	18.0	2.724	2.743	0.691		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
FOREST -- WI																		
POPPLE RIVER 55-21-016-PIT Created On: 07/01/21 Updated On:	P	SW	NW	12	38N	14E	Forest	0-225-240-2021	0.0	0.2	0.2	3.6	17.1	2.734	2.749	0.556		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
SCHALLOCK 55-21-018-PIT Created On: 08/03/16 Updated On:	P	SE	NE	36	36N	12E	Forest	0-225-234-2016	0.4	0.0	1.5	5.0	21.9	2.695	2.721	0.939		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
SCHALLOCK 55-21-018-PIT Created On: 01/04/21 Updated On:	P	SE	NE	36	36N	12E	Forest	0-225-13-2021	0.0	1.4	0.3	4.8	20.7	2.675	2.707	1.208		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
SMITH-PIT 55-21-021-PIT Created On: 02/28/24 Updated On:	P	SE	SW	7	34N	15E	Forest	0-225-195-2024	0.9	0.0	0.3	4.4	20.3	2.731	2.746	0.545		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
GRANT -- WI																		
ADAMETZ 55-22-001-QRY Created On: 01/05/17 Updated On:	Q	SE	SE	11	6N	1W	Grant	0-225-29-2017	0.3	5.4	4.1	8.5	34.9	2.631	2.680	1.878		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
ADAMETZ 55-22-001-QRY Created On: 01/04/19 Updated On:	Q	SE	SE	11	6N	1W	Grant	0-225-27-2019	1.2	7.9	7.2	12.6	40.8	2.608	2.665	2.185		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
ADAMETZ 55-22-001-QRY Created On: 01/04/22 Updated On:	Q	SE	SE	11	6N	1W	Grant	0-225-52-2022	1.1	5.0	2.7	8.0	29.5	2.644	2.693	1.825		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
GRANT -- WI																	
ADAMETZ 55-22-001-QRY Created On: 01/02/25 Updated On:	Q	SE	SE	11	6N	1W	Grant	0-225-31-2025	0.9	3.3	1.2	8.4	31.0	2.637	2.690	1.977	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
ASHTON 55-22-003-QRY Created On: 06/30/16 Updated On:	Q	SW	SW	26	4N	3W	Grant	0-225-218-2016		3.6	1.1	12.3	42.2	2.588	2.663	2.893	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
ASHTON 55-22-003-QRY Created On: 01/07/19 Updated On:	Q	SW	SW	26	4N	3W	Grant	0-225-52-2019	0.4	9.8	2.8	14.0	45.7	2.570	2.646	2.946	
	Approved Use : CONCRETE, Base Aggregate																
ASHTON 55-22-003-QRY Created On: 04/05/23 Updated On:	Q	SW	SW	26	4N	3W	Grant	0-225-189-2023	0.4	9.2	9.4	12.3	42.9	2.591	2.662	2.716	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
*BAKER 55-22-065-QRY Created On: 06/17/21 Updated On:	Q	NE	NE	35	4N	2W	Grant	0-225-224-2021	0.5	8.2	11.6	15.3	48.3	2.557	2.638	3.177	
	Approved Use : CONCRETE, OGBC, Base Aggregate																
BOSCOBEL 55-22-060-QRY Created On: 01/05/17 Updated On:	Q	NE	SE	14	7N	3W	Grant	0-225-25-2017	0.7	5.6	2.2	7.5	29.9	2.611	2.674	2.416	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
BOSCOBEL 55-22-060-QRY Created On: 08/03/18 Updated On:	Q	NE	SE	14	7N	3W	Grant	0-225-263-2018	0.8	4.1	6.1	7.5	30.8	2.625	2.678	2.014	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
GRANT -- WI																	
BOSCOBEL 55-22-060-QRY Created On: 04/07/21 Updated On:	Q	NE	SE	14	7N	3W	Grant	0-225-172-2021	0.0	1.9	6.8	8.1	31.0	2.621	2.680	2.252	
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
BOSCOBEL 55-22-060-QRY Created On: 01/02/24 Updated On:	Q	NE	SE	14	7N	3W	Grant	0-225-3-2024	0.2	1.9	1.1	5.8	25.7	2.662	2.707	1.683	
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
CASSVILLE 55-22-009-QRY Created On: 06/30/16 Updated On:	Q	NW	SW	27	3N	5W	Grant	0-225-214-2016	1.2	1.9	0.8	8.8	36.7	2.592	2.659	2.573	
Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
CASSVILLE 55-22-009-QRY Created On: 01/07/19 Updated On:	Q	NW	SW	27	3N	5W	Grant	0-225-47-2019	0.4	5.2	3.1	8.3	34.7	2.590	2.656	2.564	
Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
CASSVILLE 55-22-009-QRY Created On: 01/10/22 Updated On:	Q	NW	SW	27	3N	5W	Grant	0-225-104-2022	2.3	5.0	8.0	8.4	36.4	2.594	2.658	2.469	
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
CASSVILLE 55-22-009-QRY Created On: 01/02/25 Updated On:	Q	NW	SW	27	3N	5W	Grant	0-225-84-2025	1.6	15.6	5.5	9.3	35.1	2.556	2.630	2.913	
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
CROFT 55-22-010-QRY Created On: 04/07/16 Updated On:	Q	NW	SE	24	6N	3W	Grant	0-225-132-2016	0.8	24.3	17.5	12.0	41.8	2.577	2.651	2.876	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
GRANT -- WI																		
CROFT 55-22-010-QRY Created On: 01/05/17 Updated On:	Q	NW	SE	24	6N	3W	Grant	0-225-23-2017	0.4	16.9	9.9	16.7	49.6	2.554	2.632	3.042		
	Approved Use : CONCRETE, Base Aggregate																	
CROFT 55-22-010-QRY Created On: 04/25/17 Updated On:	Q	NW	SE	24	6N	3W	Grant	0-225-153-2017	0.2	17.2	12.9	11.8	41.4	2.579	2.651	2.777		
	Approved Use : Base Aggregate																	
CROFT 55-22-010-QRY Created On: 05/21/18 Updated On:	Q	NW	SE	24	6N	3W	Grant	0-225-216-2018	0.3	14.9	10.3	13.4	44.3	2.561	2.639	3.057		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
CROFT 55-22-010-QRY Created On: 01/05/21 Updated On:	Q	NW	SE	24	6N	3W	Grant	0-225-56-2021	2.7	15.3	17.5	15.9	48.0	2.515	2.606	3.633		
	Approved Use : Base Aggregate																	
CROFT 55-22-010-QRY Created On: 01/02/24 Updated On:	Q	NW	SE	24	6N	3W	Grant	0-225-39-2024	1.4	11.8	5.2	12.8	39.8	2.530	2.617	3.433		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
DEITER 55-22-013-QRY Created On: 04/06/17 Updated On:	Q	NW	NW	29	2N	1W	Grant	0-225-112-2017	0.7	1.4	1.4	10.0	38.1	2.573	2.644	2.760		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
DEITER 55-22-013-QRY Created On: 07/28/17 Updated On:	Q	NW	NW	29	2N	1W	Grant	0-225-242-2017	0.4	2.1	2.1	12.5	43.6	2.554	2.630	2.995		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
GRANT -- WI																		
DEITER 55-22-013-QRY Created On: 04/28/20 Updated On:	Q	NW	NW	29	2N	1W	Grant	0-225-158-2020	2.1	1.7	2.6	12.9	42.2	2.548	2.627	3.105		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
DEITER 55-22-013-QRY Created On: 01/03/23 Updated On:	Q	NW	NW	29	2N	1W	Grant	0-225-6-2023	0.1	2.0	3.6	11.7	42.0	2.536	2.625	3.500		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
FREY 55-22-017-QRY Created On: 06/30/16 Updated On:	Q	NW	SE	15	7N	3W	Grant	0-225-216-2016		3.9	4.5	12.0	39.2	2.605	2.668	2.431		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
FREY 55-22-017-QRY Created On: 05/12/20 Updated On:	Q	NW	SE	15	7N	3W	Grant	0-225-175-2020	0.7	4.6	3.7	10.5	37.5	2.577	2.646	2.654		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
FREY 55-22-017-QRY Created On: 01/10/23 Updated On:	Q	NW	SE	15	7N	3W	Grant	0-225-117-2023	0.4	5.1	4.0	11.0	38.6	2.544	2.631	3.430		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
HAMPTON 55-22-021-QRY Created On: 04/07/16 Updated On:	Q			21	4N	5W	Grant	0-225-136-2016	1.2	8.5	6.9	9.4	36.5	2.576	2.646	2.698		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
HAMPTON 55-22-021-QRY Created On: 04/19/19 Updated On:	Q			21	4N	5W	Grant	0-225-156-2019	1.5	7.6	5.4	10.0	38.0	2.594	2.656	2.424		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
GRANT -- WI																	
HAMPTON 55-22-021-QRY Created On: 01/04/22 Updated On:	Q			21	4N	5W	Grant	0-225-46-2022	0.9	14.6	1.1	10.6	36.4	2.569	2.638	2.693	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
HAMPTON 55-22-021-QRY Created On: 01/02/25 Updated On:	Q			21	4N	5W	Grant	0-225-27-2025	0.7	2.2	0.4	9.7	33.2	2.592	2.656	2.478	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
*HAVERLAND 55-22-023-QRY Created On: 04/06/17 Updated On:	Q	NE	NW	26	2N	2W	Grant	0-225-106-2017	1.0	2.4	2.5	12.7	39.1	2.528	2.616	3.516	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
*HAVERLAND 55-22-023-QRY Created On: 03/23/18 Updated On:	Q	NE	NW	26	2N	2W	Grant	0-225-137-2018	1.0	2.9	2.5	13.4	41.0	2.552	2.627	2.962	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
*HAVERLAND 55-22-023-QRY Created On: 03/17/21 Updated On:	Q	NE	NW	26	2N	2W	Grant	0-225-150-2021	0.1	3.9	4.1	18.0	49.1	2.507	2.598	3.604	
	Approved Use : Base Aggregate																
HWY-11 55-22-025-QRY Created On: 06/01/21 Updated On:	Q	SE	NW	26	1N	2W	Grant	0-225-217-2021	0.8	2.9	3.4	9.4	37.2	2.608	2.667	2.256	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
HWY-11 55-22-025-QRY Created On: 01/02/24 Updated On:	Q	SE	NW	26	1N	2W	Grant	0-225-32-2024	0.7	3.4	4.9	10.7	36.8	2.561	2.636	2.904	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
GRANT -- WI																	
JULIUS WIEST 55-22-028-QRY Created On: 04/25/17 Updated On:	Q	NE	NW	26	3N	5W	Grant	0-225-152-2017	0.2	15.9	7.0	10.9	41.3	2.562	2.639	2.987	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
JULIUS WIEST 55-22-028-QRY Created On: 04/19/19 Updated On:	Q	NE	NW	26	3N	5W	Grant	0-225-158-2019	0.8	11.1	10.9	12.4	42.9	2.584	2.652	2.647	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
JULIUS WIEST 55-22-028-QRY Created On: 01/04/22 Updated On:	Q	NE	NW	26	3N	5W	Grant	0-225-48-2022	0.9	15.9	0.8	9.7	36.0	2.578	2.651	2.840	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
JULIUS WIEST 55-22-028-QRY Created On: 01/02/25 Updated On:	Q	NE	NW	26	3N	5W	Grant	0-225-30-2025	0.2	3.4	0.5	11.2	38.2	2.571	2.645	2.874	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
KEILER 55-22-068-QRY Created On: 01/02/25 Updated On:	Q	NW	SW	4	1N	2W	Grant	0-225-88-2025	15.4	8.5	16.2	7.1	35.6	2.497	2.587	3.576	
	Approved Use : Base Aggregate																
KLAR 55-22-031-QRY Created On: 06/30/16 Updated On:	Q	NW	NW	33	3N	2W	Grant	0-225-217-2016		5.4	4.3	11.7	40.9	2.580	2.653	2.810	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
KLAR 55-22-031-QRY Created On: 07/28/17 Updated On:	Q	NW	NW	33	3N	2W	Grant	0-225-244-2017	2.3	6.0	2.2	11.1	40.3	2.575	2.649	2.872	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
GRANT -- WI																		
KLAR 55-22-031-QRY Created On: 04/28/20 Updated On:	Q	NW	NW	33	3N	2W	Grant	0-225-157-2020	0.7	3.3	1.8	9.8	36.6	2.604	2.667	2.432		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
KLAR 55-22-031-QRY Created On: 01/03/23 Updated On:	Q	NW	NW	33	3N	2W	Grant	0-225-11-2023	1.0	2.8	4.2	9.3	35.6	2.575	2.646	2.751		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
KUNKEL QUARRY 55-22-066-QRY Created On: 05/22/23 Updated On:	Q	SE	NE	15	1N	2W	Grant	0-225-220-2023	2.0	2.8	2.7	13.2	42.6	2.529	2.615	3.406		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
LM WIEST 55-22-067-QRY Created On: 01/02/25 Updated On:	Q	NE	SE	10	3N	5W	Grant	0-225-87-2025	1.7	4.4	6.7	7.4	37.1	2.592	2.658	2.565		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MILESTONE-ARNOLD ANDERSON 55-22-002-QRY Created On: 04/07/16 Updated On:	Q	SW	SE	34	3N	1W	Grant	0-225-131-2016	1.5	6.1	7.6	12.8	44.0	2.549	2.631	3.202		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
MILESTONE-ARNOLD ANDERSON 55-22-002-QRY Created On: 01/04/19 Updated On:	Q	SW	SE	34	3N	1W	Grant	0-225-25-2019	3.4	9.9	9.4	15.0	48.1	2.537	2.618	3.195		
	Approved Use : CONCRETE, Base Aggregate																	
MILESTONE-ARNOLD ANDERSON 55-22-002-QRY Created On: 05/01/23 Updated On:	Q	SW	SE	34	3N	1W	Grant	0-225-214-2023	1.9	7.0	12.0	12.8	44.9	2.546	2.628	3.224		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
GRANT -- WI																		
MORRIS 55-22-040-QRY Created On: 04/09/15 Updated On:	Q	NW	NW	3	5N	3W	Grant	0-225-116-2015	1.3	2.4	3.9	11.4	39.8	2.671	2.733	2.297		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
MORRIS 55-22-040-QRY Created On: 04/05/23 Updated On:	Q	NW	NW	3	5N	3W	Grant	0-225-188-2023		17.6	2.7	9.5	37.8	2.657	2.685	1.057		
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																	
RAISBECK QUARRY 55-22-042-QRY Created On: 04/06/17 Updated On:	Q	SE	NE	12	4N	5W	Grant	0-225-113-2017	1.8	3.4	5.5	8.8	39.3	2.588	2.652	2.494		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
RAISBECK QUARRY 55-22-042-QRY Created On: 01/02/25 Updated On:	Q	SE	NE	12	4N	5W	Grant	0-225-86-2025	1.7	6.6	7.3	6.9	34.6	2.625	2.683	2.230		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
ROSEMEYER 55-22-045-QRY Created On: 04/07/16 Updated On:	Q	SW	NW	14	3N	1W	Grant	0-225-134-2016	0.7	13.0	8.1	10.9	38.2	2.603	2.672	2.635		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
ROSEMEYER 55-22-045-QRY Created On: 01/04/19 Updated On:	Q	SW	NW	14	3N	1W	Grant	0-225-22-2019	1.8	13.7	4.9	12.2	41.3	2.601	2.667	2.505		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
ROSEMEYER 55-22-045-QRY Created On: 01/04/22 Updated On:	Q	SW	NW	14	3N	1W	Grant	0-225-47-2022	1.3	9.9	0.1	8.5	32.6	2.581	2.651	2.706		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
GRANT -- WI																		
ROSEMEYER 55-22-045-QRY Created On: 01/02/25 Updated On:	Q	SW	NW	14	3N	1W	Grant	0-225-32-2025	1.4	7.2	4.4	8.8	34.8	2.564	2.642	3.052		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
SALZGERBER 55-22-046-QRY Created On: 01/05/17 Updated On:	Q	NE	SW	2	7N	3W	Grant	0-225-34-2017	3.1	4.8	5.6	9.1	37.2	2.619	2.670	1.925		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
SALZGERBER 55-22-046-QRY Created On: 01/09/20 Updated On:	Q	NE	SW	2	7N	3W	Grant	0-225-85-2020	2.8	3.8	7.1	10.2	40.5	2.603	2.659	2.124		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
SALZGERBER 55-22-046-QRY Created On: 01/03/23 Updated On:	Q	NE	SW	2	7N	3W	Grant	0-225-63-2023	1.4	5.6	1.3	11.5	39.5	2.592	2.657	2.498		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
SCHNEIDER 55-22-048-QRY Created On: 04/16/15 Updated On:	Q	NW	SE	18	4N	3W	Grant	0-225-122-2015	2.2	10.4	6.7	12.8	43.4	2.598	2.665	2.571		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
SCHNEIDER 55-22-048-QRY Created On: 07/28/17 Updated On:	Q	NW	SE	18	4N	3W	Grant	0-225-243-2017	0.3	4.2	8.3	14.4	44.3	2.599	2.667	2.610		
	Approved Use : CONCRETE, OGBC, Base Aggregate																	
SCHNEIDER 55-22-048-QRY Created On: 04/28/20 Updated On:	Q	NW	SE	18	4N	3W	Grant	0-225-161-2020	0.1	3.5	2.1	10.8	39.6	2.547	2.631	3.309		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
GRANT -- WI																	
SCHNEIDER 55-22-048-QRY Created On: 01/03/23 Updated On:	Q	NW	SE	18	4N	3W	Grant	0-225-7-2023	0.4	4.4	7.9	13.0	42.6	2.567	2.640	2.852	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
SIMMON 55-22-049-QRY Created On: 01/04/18 Updated On:	Q	SW	NW	21	4N	4W	Grant	0-225-71-2018	0.8	10.7	10.0	11.2	40.4	2.575	2.642	2.590	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
SIMMON 55-22-049-QRY Created On: 01/04/22 Updated On:	Q	SW	NW	21	4N	4W	Grant	0-225-45-2022	1.1	10.1	0.7	10.9	39.0	2.559	2.629	2.746	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
SIMMON 55-22-049-QRY Created On: 01/02/25 Updated On:	Q	SW	NW	21	4N	4W	Grant	0-225-26-2025	0.3	2.9	2.7	10.5	36.4	2.567	2.642	2.915	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
TENNYSON 55-22-052-QRY Created On: 04/06/17 Updated On:	Q	NW	NE	36	3N	3W	Grant	0-225-116-2017	2.6	7.7	3.2	11.3	35.1	2.562	2.636	2.888	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
TENNYSON 55-22-052-QRY Created On: 07/28/17 Updated On:	Q	NW	NE	36	3N	3W	Grant	0-225-241-2017	0.3	3.3	1.1	7.5	31.0	2.624	2.678	2.073	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
TENNYSON 55-22-052-QRY Created On: 04/28/20 Updated On:	Q	NW	NE	36	3N	3W	Grant	0-225-160-2020	0.0	3.7	2.2	8.8	33.6	2.642	2.693	1.941	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
GRANT -- WI																		
TENNYSON 55-22-052-QRY Created On: 01/03/23 Updated On:	Q	NW	NE	36	3N	3W	Grant	0-225-9-2023	0.3	7.0	10.6	10.1	36.8	2.543	2.627	3.277		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
WAMSLEY 55-22-058-QRY Created On: 01/02/25 Updated On:	Q	NE	SW	9	3N	4W	Grant	0-225-90-2025	2.8	4.8	6.7	6.1	30.5	2.618	2.675	2.203		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
ZART 55-22-061-QRY Created On: 04/17/15 Updated On:	Q	SE	SE	7	6N	3W	Grant	0-225-126-2015	2.2	1.3	6.2	9.9	35.6	2.595	2.655	2.302		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
ZART 55-22-061-QRY Created On: 08/15/17 Updated On:	Q	SE	SE	7	6N	3W	Grant	0-225-255-2017	2.4	6.1	2.1	9.4	34.1	2.606	2.663	2.158		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
ZART 55-22-061-QRY Created On: 01/04/18 Updated On:	Q	SE	SE	7	6N	3W	Grant	0-225-67-2018	1.0	5.6	7.7	10.6	38.6	2.620	2.677	2.196		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
ZART 55-22-061-QRY Created On: 01/05/21 Updated On:	Q	SE	SE	7	6N	3W	Grant	0-225-59-2021	1.3	5.7	9.4	13.7	43.9	2.628	2.684	2.135		
	Approved Use : CONCRETE, OGBC, Base Aggregate																	
ZART 55-22-061-QRY Created On: 01/02/24 Updated On:	Q	SE	SE	7	6N	3W	Grant	0-225-36-2024	0.3	3.3	2.4	9.2	33.7	2.627	2.684	2.189		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
GREEN -- WI																	
*BLACKHAWK 55-23-003-QRY Created On: 05/11/15 Updated On:	Q	SW	NE	20	1N	6E	Green	0-225-162-2015		11.7	9.3	11.0	32.8	2.622	2.676	2.068	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
*BLACKHAWK 55-23-003-QRY Created On: 03/23/18 Updated On:	Q	SW	NE	20	1N	6E	Green	0-225-142-2018	0.1	13.5	1.6	8.1	29.9	2.601	2.668	2.568	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
*BLACKHAWK 55-23-003-QRY Created On: 03/17/21 Updated On:	Q	SW	NE	20	1N	6E	Green	0-225-151-2021	1.6	7.8	2.3	8.1	26.9	2.578	2.652	2.885	
	Approved Use : Base Aggregate																
DISCH-WAELCHLI 55-23-028-QRY Created On: 01/02/25 Updated On:	Q	NW	NE	16	3N	8E	Green	0-225-51-2025	0.0	17.9	9.0	10.1	37.1	2.591	2.668	2.965	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
INDERGAND 55-23-007-QRY Created On: 07/16/15 Updated On:	Q	SE	SE	20	2N	7E	Green	0-225-210-2015		10.9	6.6	5.5	27.0	2.637	2.698	2.309	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
INDERGAND 55-23-007-QRY Created On: 04/12/16 Updated On:	Q	SE	SE	20	2N	7E	Green	0-225-140-2016		9.3	7.7	5.0	28.1	2.632	2.689	2.175	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
INDERGAND 55-23-007-QRY Created On: 05/16/19 Updated On:	Q	SE	SE	20	2N	7E	Green	0-225-190-2019	0.0	7.5	10.2	5.6	25.2	2.637	2.697	2.259	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
GREEN -- WI																	
INDERGAND 55-23-007-QRY Created On: 04/05/22 Updated On:	Q	SE	SE	20	2N	7E	Green	0-225-155-2022	0.5	8.6	7.6	5.3	26.5	2.607	2.676	2.659	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
INDERGAND 55-23-007-QRY Created On: 01/14/25 Updated On:	Q	SE	SE	20	2N	7E	Green	0-225-96-2025	0.1	12.5	4.8	5.5	29.7	2.656	2.713	2.129	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
*KLITZKE 55-23-009-QRY Created On: 03/19/15 Updated On:	Q			16	4N	7E	Green	0-225-97-2015		5.6	6.7	14.1	46.7	2.510	2.611	4.014	
	Approved Use : CONCRETE, Base Aggregate																
*KLITZKE 55-23-009-QRY Created On: 05/11/18 Updated On:	Q			16	4N	7E	Green	0-225-211-2018	1.7	6.8	7.7	12.3	41.5	2.546	2.634	3.485	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
*KLITZKE 55-23-009-QRY Created On: 04/30/21 Updated On:	Q			16	4N	7E	Green	0-225-195-2021	0.1	22.4	3.8	10.4	38.2	2.582	2.655	2.836	
*KLITZKE 55-23-009-QRY Created On: 08/11/21 Updated On:	Q			16	4N	7E	Green	0-225-258-2021	0.1	5.0	7.4	10.8	37.5	2.595	2.654	2.282	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
MONROE CONSTRUCTION 55-23-014-QRY Created On: 03/08/17 Updated On:	Q	SE	NE	32	2N	7E	Green	0-225-76-2017	0.2	11.2	2.6	11.5	40.7	2.573	2.650	2.974	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse						
	P/Q	Qrt	Qrt	Sect	Town	Range	County					LA Wear (%)		Sp. Gravity		Absorp. %		
												100	500	OD	SSD	Crse	Fine	
GREEN -- WI																		
MONROE CONSTRUCTION 55-23-014-QRY Created On: 04/17/23 Updated On:	Q	SE	NE	32	2N	7E	Green	0-225-196-2023	0.9	4.2	6.3	12.0	43.5	2.514	2.611	3.860		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
RUFERS 55-23-020-QRY Created On: 03/08/17 Updated On:	Q			30	2N	8E	Green	0-225-77-2017	0.4	16.0	5.1	10.6	38.0	2.554	2.639	3.342		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
RUFERS 55-23-020-QRY Created On: 04/17/23 Updated On:	Q			30	2N	8E	Green	0-225-195-2023	0.6	18.1	4.6	6.4	28.8	2.582	2.658	2.934		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
SCHWARZENBERGER 55-23-023-QRY Created On: 05/06/15 Updated On:	Q	NW	NW	5	1N	8E	Green	0-225-146-2015	2.4	7.6	13.7	12.8	44.9	2.541	2.634	3.654		
	Approved Use : Base Aggregate																	
SCHWARZENBERGER 55-23-023-QRY Created On: 04/25/17 Updated On:	Q	NW	NW	5	1N	8E	Green	0-225-158-2017	0.4	6.7	10.1	10.7	39.9	2.598	2.674	2.921		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
SCHWARZENBERGER 55-23-023-QRY Created On: 02/12/20 Updated On:	Q	NW	NW	5	1N	8E	Green	0-225-111-2020	0.4	17.9	21.9	9.3	37.7	2.628	2.691	2.410		
SCHWARZENBERGER 55-23-023-QRY Created On: 03/13/24 Updated On:	Q	NW	NW	5	1N	8E	Green	0-225-196-2024	1.1	2.9	5.2	11.6	42.8	2.559	2.645	3.354		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
GREEN -- WI																		
VOEGGLI 55-23-027-QRY Created On: 04/11/18 Updated On:	Q	NE	NE	35	4N	7E	Green	0-225-165-2018	0.7	15.6	14.2	13.5	46.4	2.523	2.640	4.674		
	Approved Use : Base Aggregate																	
VOEGGLI 55-23-027-QRY Created On: 07/28/21 Updated On:	Q	NE	NE	35	4N	7E	Green	0-225-254-2021	0.9	6.7	2.8	6.1	29.7	2.608	2.668	2.301		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
VOEGGLI 55-23-027-QRY Created On: 01/02/25 Updated On:	Q	NE	NE	35	4N	7E	Green	0-225-1-2025	1.0	6.4	8.2	7.4	33.6	2.612	2.673	2.335		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
GREEN LAKE -- WI																		
MARKESAN 55-24-007-QRY Created On: 01/16/15 Updated On:	Q		NE	3	14N	13E	Green Lake	0-225-70-2015	0.1	0.9	7.9	6.3	28.2	2.693	2.741	1.785		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
MARKESAN 55-24-007-QRY Created On: 04/11/18 Updated On:	Q		NE	3	14N	13E	Green Lake	0-225-166-2018	0.3	15.1	10.2	7.5	31.5	2.671	2.722	1.926		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
MARKESAN 55-24-007-QRY Created On: 01/10/19 Updated On:	Q		NE	3	14N	13E	Green Lake	0-225-83-2019		12.5	8.9	7.6	31.8	2.681	2.733	1.931		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MARKESAN 55-24-007-QRY Created On: 03/07/22 Updated On:	Q		NE	3	14N	13E	Green Lake	0-225-139-2022	0.0	10.9	6.7	6.2	28.0	2.703	2.744	1.507		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
GREEN LAKE -- WI																		
MARKESAN 55-24-007-QRY Created On: 03/24/25 Updated On:	Q		NE	3	14N	13E	Green Lake	0-225-176-2025		0.0	8.1	5.5	6.6	29.5	2.695	2.742	1.740	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MASHUDA UPPER 55-24-008-QRY Created On: 03/31/17 Updated On:	Q	NE	NW	28	16N	12E	Green Lake	0-225-95-2017		0.4	1.7	2.6	10.7	38.6	2.640	2.701	2.315	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
MASHUDA UPPER 55-24-008-QRY Created On: 05/07/20 Updated On:	Q	NE	NW	28	16N	12E	Green Lake	0-225-172-2020		0.6	1.8	2.2	8.5	37.7				
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MASHUDA UPPER 55-24-008-QRY Created On: 04/04/23 Updated On:	Q	NE	NW	28	16N	12E	Green Lake	0-225-176-2023		0.5	1.6	1.8	10.9	37.5	2.665	2.718	1.975	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
*MICHELS MANCHESTER 55-24-010-PIT Created On: 07/08/15 Updated On:	P	SW	SE	16	14N	12E	Green Lake	0-225-207-2015		7.7	0.0	7.3	7.3	33.6	2.573	2.632	2.258	
	Approved Use : HMA<E-3, HMA>=E-3, Base Aggregate																	
*MICHELS MANCHESTER 55-24-010-PIT Created On: 01/07/20 Updated On:	P	SW	SE	16	14N	12E	Green Lake	0-225-40-2020		1.7	14.5	9.5	6.5	32.3	2.570	2.630	2.356	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MICHELS MARKESAN 55-24-011-QRY Created On: 01/04/16 Updated On:	Q	SW	SW	9	14N	13E	Green Lake	0-225-14-2016			13.7	6.0	6.1	27.0	2.678	2.724	1.714	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
GREEN LAKE -- WI																		
MICHEL'S MARKESAN 55-24-011-QRY Created On: 01/03/23 Updated On:	Q	SW	SW	9	14N	13E	Green Lake	0-225-41-2023		0.0	14.9	9.3	6.6	29.0	2.673	2.724	1.902	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MORRIS 55-24-012-QRY Created On: 04/03/17 Updated On:	Q	SE	SW	3	16N	13E	Green Lake	0-225-99-2017		0.7	6.4	5.3	12.7	37.1	2.648	2.698	1.874	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MORRIS 55-24-012-QRY Created On: 05/07/20 Updated On:	Q	SE	SW	3	16N	13E	Green Lake	0-225-171-2020		3.2	22.9	3.8	10.4	38.1	2.648	2.703	2.072	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MORRIS 55-24-012-QRY Created On: 05/27/21 Updated On:	Q	SE	SW	3	16N	13E	Green Lake	0-225-216-2021		2.1	5.7	3.6	7.7	29.8	2.682	2.722	1.487	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MORRIS 55-24-012-QRY Created On: 05/20/24 Updated On:	Q	SE	SW	3	16N	13E	Green Lake	0-225-254-2024		0.7	0.7	1.4	6.7	29.0	2.704	2.742	1.428	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
NESHKORO 55-24-013-PIT Created On: 05/14/25 Updated On:	P	NW	SW	23	17N	11E	Green Lake	0-225-210-2025		0.3	3.6	5.2	8.2	33.3	2.698	2.736	1.412	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
RIDGESTONE 55-24-015-QRY Created On: 10/14/16 Updated On:	Q	SW	SE	15	17N	13E	Green Lake	0-225-270-2016		0.9	2.9	1.3	9.5	37.8	2.672	2.719	1.778	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
GREEN LAKE -- WI																		
RIDGESTONE 55-24-015-QRY Created On: 05/24/19 Updated On:	Q	SW	SE	15	17N	13E	Green Lake	0-225-200-2019		0.1	9.3	2.1	10.1	38.9	2.686	2.730	1.634	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
RIDGESTONE 55-24-015-QRY Created On: 03/12/25 Updated On:	Q	SW	SE	15	17N	13E	Green Lake	0-225-173-2025		0.4	2.5	4.4	8.7	36.0	2.695	2.731	1.351	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
UTLEY 55-24-019-QRY Created On: 01/04/16 Updated On:	Q	SE	NW	36	15N	13E	Green Lake	0-225-12-2016			0.2	0.1	4.5	18.8	2.632	2.639	0.240	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
UTLEY 55-24-019-QRY Created On: 06/13/19 Updated On:	Q	SE	NW	36	15N	13E	Green Lake	0-225-221-2019		0.0	0.3	0.5	4.9	20.1	2.620	2.632	0.455	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
UTLEY 55-24-019-QRY Created On: 01/04/22 Updated On:	Q	SE	NW	36	15N	13E	Green Lake	0-225-38-2022		0.0	0.4	0.3	4.9	19.9	2.621	2.631	0.372	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
UTLEY 55-24-019-QRY Created On: 01/29/24 Updated On:	Q	SE	NW	36	15N	13E	Green Lake	0-225-156-2024		0.0	1.1	0.9	4.9	20.6	2.620	2.630	0.363	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
IOWA -- WI																		
19TH HOLE (BURGESS) 55-25-001-QRY Created On: 03/23/17 Updated On:	Q	SE	SW	15	5N	3E	Iowa	0-225-88-2017		1.7	6.2	9.7	10.0	36.9	2.536	2.629	3.681	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
IOWA -- WI																	
19TH HOLE (BURGESS) 55-25-001-QRY Created On: 07/15/20 Updated On:	Q	SE	SW	15	5N	3E	Iowa	0-225-217-2020	1.3	4.7	10.0	8.0	32.9	2.543	2.628	3.350	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
19TH HOLE (BURGESS) 55-25-001-QRY Created On: 02/28/24 Updated On:	Q	SE	SW	15	5N	3E	Iowa	0-225-185-2024	1.8	8.1	11.7	9.8	37.4	2.487	2.588	4.051	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
BERNING 55-25-005-QRY Created On: 08/08/16 Updated On:	Q	NE	SW	26	5N	3E	Iowa	0-225-237-2016	1.1	6.2	7.1	8.1	35.0	2.582	2.664	3.184	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
BERNING 55-25-005-QRY Created On: 02/11/19 Updated On:	Q	NE	SW	26	5N	3E	Iowa	0-225-103-2019	1.1	10.8	12.5	8.8	35.3	2.560	2.645	3.316	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
BERNING 55-25-005-QRY Created On: 03/17/21 Updated On:	Q	NE	SW	26	5N	3E	Iowa	0-225-143-2021	1.3	14.6	6.1	6.0	30.6	2.642	2.706	2.400	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
BERNING 55-25-005-QRY Created On: 02/28/24 Updated On:	Q	NE	SW	26	5N	3E	Iowa	0-225-184-2024	1.2	13.1	9.3	7.2	32.5	2.616	2.686	2.682	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
EHLER-COBB 55-25-008-QRY Created On: 04/06/17 Updated On:	Q	SE	SE	14	6N	1E	Iowa	0-225-114-2017	1.1	6.2	4.5	14.4	40.1	2.531	2.607	3.013	
	Approved Use : CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
IOWA -- WI																		
EHLER-COBB 55-25-008-QRY Created On: 04/28/20 Updated On:	Q	SE	SE	14	6N	1E	Iowa	0-225-162-2020	0.7	5.4	5.1	15.0	46.7	2.554	2.633	3.079		
Approved Use : CONCRETE, OGBC, Base Aggregate																		
EHLER-COBB 55-25-008-QRY Created On: 01/03/23 Updated On:	Q	SE	SE	14	6N	1E	Iowa	0-225-10-2023	0.7	7.0	9.0	12.5	44.2	2.551	2.631	3.167		
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
*GOLD THORPE 55-25-032-QRY Created On: 06/13/19 Updated On:	Q	SE	SW	15	5N	3E	Iowa	0-225-214-2019	0.1	1.6	3.4	7.6	30.1	2.601	2.669	2.626		
Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																		
*GOLD THORPE 55-25-032-QRY Created On: 01/10/22 Updated On:	Q	SE	SW	15	5N	3E	Iowa	0-225-100-2022	0.8	3.4	6.9	7.4	35.1	2.573	2.643	2.721		
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
HACKL 55-25-010-QRY Created On: 01/05/17 Updated On:	Q	SW	SW	21	8N	1E	Iowa	0-225-24-2017	6.9	4.5	4.6	8.9	34.3	2.645	2.696	1.917		
Approved Use : HMA<E-3, HMA>=E-3, Base Aggregate																		
HACKL 55-25-010-QRY Created On: 01/04/19 Updated On:	Q	SW	SW	21	8N	1E	Iowa	0-225-23-2019	0.9	7.7	2.9	8.3	32.4	2.662	2.707	1.711		
Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																		
HACKL 55-25-010-QRY Created On: 01/04/22 Updated On:	Q	SW	SW	21	8N	1E	Iowa	0-225-49-2022	0.2	6.2	0.4	10.3	34.8	2.648	2.698	1.890		
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse					
	P/Q	Qrt	Qrt	Sect	Town	Range	County	LA Wear (%)					Sp. Gravity		Absorp. %			
								100					500	OD	SSD	Crse	Fine	
IOWA -- WI																		
HACKL 55-25-010-QRY Created On: 01/02/25 Updated On:	Q	SW	SW	21	8N	1E	Iowa	0-225-33-2025	0.5	2.8	0.3	6.4	26.4	2.664	2.709	1.684		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
HYDE 55-25-014-QRY Created On: 06/25/24 Updated On:	Q	NW	NE	26	6N	4E	Iowa	0-225-280-2024	0.8	17.6	3.3	10.1	38.6	2.580	2.657	2.974		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
HYDE 55-25-014-QRY Created On: 06/27/24 Updated On:	Q	NW	NE	26	6N	4E	Iowa	0-225-282-2024	0.9	8.5	3.6	10.9	38.2	2.584	2.655	2.744		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
*JONES 55-25-016-QRY Created On: 05/08/15 Updated On:	Q	SE	NE	22	5N	1E	Iowa	0-225-158-2015	0.6	3.4	6.9	14.6	48.5	2.522	2.616	3.719		
	Approved Use : CONCRETE, Base Aggregate																	
*JONES 55-25-016-QRY Created On: 03/23/18 Updated On:	Q	SE	NE	22	5N	1E	Iowa	0-225-140-2018	2.0	5.7	1.9	13.5	45.8	2.529	2.615	3.401		
	Approved Use : CONCRETE, Base Aggregate																	
*JONES 55-25-016-QRY Created On: 03/17/21 Updated On:	Q	SE	NE	22	5N	1E	Iowa	0-225-145-2021	1.0	7.6	2.1	15.8	48.7	2.489	2.591	4.117		
	Approved Use : CONCRETE, OGBC, Base Aggregate																	
LEIGHTY 55-25-017-QRY Created On: 02/09/18 Updated On:	Q	N	NE	4	4N	1E	Iowa	0-225-93-2018	0.9	1.6	6.7	10.6	39.6	2.556	2.628	2.822		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
IOWA -- WI																		
LEIGHTY 55-25-017-QRY Created On: 03/17/21 Updated On:	Q	N	NE	4	4N	1E	Iowa	0-225-140-2021	1.6	12.7	4.0	8.2	34.8	2.539	2.621	3.259		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
LEIGHTY 55-25-017-QRY Created On: 02/28/24 Updated On:	Q	N	NE	4	4N	1E	Iowa	0-225-180-2024	1.7	8.3	6.3	8.1	33.7	2.591	2.658	2.562		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
LINDEN 55-25-018-QRY Created On: 06/30/16 Updated On:	Q	SW	SW	14	5N	2E	Iowa	0-225-215-2016		0.8	0.5	10.7	39.8	2.676	2.720	1.661		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
LINDEN 55-25-018-QRY Created On: 01/07/19 Updated On:	Q	SW	SW	14	5N	2E	Iowa	0-225-54-2019	0.2	1.8	4.1	10.8	35.9	2.603	2.669	2.522		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
LINDEN 55-25-018-QRY Created On: 01/10/22 Updated On:	Q	SW	SW	14	5N	2E	Iowa	0-225-103-2022	0.4	3.0	4.2	11.0	37.1	2.602	2.670	2.617		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
LINDEN 55-25-018-QRY Created On: 01/02/25 Updated On:	Q	SW	SW	14	5N	2E	Iowa	0-225-83-2025	0.0	3.5	2.5	8.8	34.5	2.616	2.678	2.386		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MILLER 55-25-019-QRY Created On: 04/16/15 Updated On:	Q	NW	NW	31	6N	3E	Iowa	0-225-124-2015		4.7	7.2	6.9	30.0	2.588	2.661	2.840		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
IOWA -- WI																		
MILLER 55-25-019-QRY Created On: 03/28/17 Updated On:	Q	NW	NW	31	6N	3E	Iowa	0-225-91-2017	0.0	4.6	9.2	6.9	30.1	2.594	2.666	2.762		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MILLER 55-25-019-QRY Created On: 02/09/18 Updated On:	Q	NW	NW	31	6N	3E	Iowa	0-225-96-2018	3.0	4.0	6.8	10.8	42.3	2.580	2.650	2.707		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
MILLER 55-25-019-QRY Created On: 03/17/21 Updated On:	Q	NW	NW	31	6N	3E	Iowa	0-225-142-2021	0.1	5.9	3.6	7.7	33.2	2.579	2.651	2.796		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MILLER 55-25-019-QRY Created On: 02/28/24 Updated On:	Q	NW	NW	31	6N	3E	Iowa	0-225-179-2024	0.8	8.1	10.1	10.2	38.4	2.537	2.627	3.577		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
NANKEY 55-25-020-QRY Created On: 01/05/17 Updated On:	Q	SE	NE	14	7N	1E	Iowa	0-225-26-2017	0.9	3.4	5.2	7.2	30.2	2.634	2.685	1.932		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
NANKEY 55-25-020-QRY Created On: 01/04/19 Updated On:	Q	SE	NE	14	7N	1E	Iowa	0-225-28-2019	0.6	6.4	4.8	6.7	28.9	2.645	2.692	1.786		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
NANKEY 55-25-020-QRY Created On: 01/02/24 Updated On:	Q	SE	NE	14	7N	1E	Iowa	0-225-40-2024	0.2	5.1	2.3	9.2	32.6	2.621	2.677	2.131		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
IOWA -- WI																		
SWIGGUM 55-25-025-QRY Created On: 04/16/15 Updated On:	Q	NE	NE	30	6N	3E	Iowa	0-225-120-2015	0.5	2.1	3.3	12.6	44.3	2.494	2.587	3.719		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
SWIGGUM 55-25-025-QRY Created On: 03/23/18 Updated On:	Q	NE	NE	30	6N	3E	Iowa	0-225-144-2018	1.8	1.3	0.5	9.8	37.3	2.506	2.596	3.617		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
SWIGGUM 55-25-025-QRY Created On: 03/17/21 Updated On:	Q	NE	NE	30	6N	3E	Iowa	0-225-146-2021	0.8	1.6	0.9	9.9	38.7	2.491	2.591	4.004		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
SWIGGUM 55-25-025-QRY Created On: 01/02/24 Updated On:	Q	NE	NE	30	6N	3E	Iowa	0-225-2-2024	0.1	1.3	1.5	8.5	36.0	2.537	2.619	3.207		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
THOMAS COBB 55-25-026-QRY Created On: 02/09/18 Updated On:	Q	NE	NE	30	6N	2E	Iowa	0-225-97-2018	2.1	3.9	8.9	10.5	42.6	2.504	2.601	3.891		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
THOMAS COBB 55-25-026-QRY Created On: 03/17/21 Updated On:	Q	NE	NE	30	6N	2E	Iowa	0-225-139-2021	2.6	11.0	9.5	12.7	43.9	2.534	2.625	3.573		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
THOMAS COBB 55-25-026-QRY Created On: 02/28/24 Updated On:	Q	NE	NE	30	6N	2E	Iowa	0-225-181-2024	2.3	12.5	12.4	9.2	38.7	2.526	2.613	3.425		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
IOWA -- WI																		
THOMAS\RIDGE 55-25-029-QRY Created On: 04/07/16 Updated On:	Q	NW	NE	33	6N	4E	Iowa	0-225-129-2016	5.6	7.4	5.3	12.3	43.2	2.560	2.633	2.859		
	Approved Use : HMA<E-3, HMA>=E-3, Base Aggregate																	
THOMAS\RIDGE 55-25-029-QRY Created On: 02/11/19 Updated On:	Q	NW	NE	33	6N	4E	Iowa	0-225-104-2019	1.8	3.0	5.5	10.6	39.8	2.544	2.631	3.408		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
THOMAS\RIDGE 55-25-029-QRY Created On: 03/17/21 Updated On:	Q	NW	NE	33	6N	4E	Iowa	0-225-141-2021	1.5	5.3	2.9	9.2	38.2	2.613	2.676	2.415		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
THOMAS\RIDGE 55-25-029-QRY Created On: 02/28/24 Updated On:	Q	NW	NE	33	6N	4E	Iowa	0-225-183-2024	2.0	5.4	10.5	9.2	37.6	2.542	2.626	3.275		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
*THONI 55-25-030-QRY Created On: 03/23/18 Updated On:	Q	SW	SE	3	6N	5E	Iowa	0-225-139-2018	2.7	3.9	1.3	10.9	41.2	2.549	2.632	3.232		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
*THONI 55-25-030-QRY Created On: 03/17/21 Updated On:	Q	SW	SE	3	6N	5E	Iowa	0-225-147-2021	1.9	2.5	0.6	14.9	46.7	2.562	2.632	2.712		
	Approved Use : CONCRETE, OGBC, Base Aggregate																	
*THONI 55-25-030-QRY Created On: 05/21/24 Updated On:	Q	SW	SE	3	6N	5E	Iowa	0-225-263-2024	0.2	19.4	9.9	9.9	37.7	2.581	2.656	2.919		

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
IOWA -- WI																		
*THONI 55-25-030-QRY Created On: 06/25/24 Updated On:	Q	SW	SE	3	6N	5E	Iowa	0-225-273-2024	0.1	19.3	1.1	14.8	47.4	2.537	2.624	3.428		
*THONI 55-25-030-QRY Created On: 08/14/24 Updated On:	Q	SW	SE	3	6N	5E	Iowa	0-225-302-2024 Approved Use : CONCRETE, OGBC, Base Aggregate	0.0	14.1	2.5	14.3	47.5	2.573	2.651	3.026		
WHITSON 55-25-024-QRY Created On: 08/07/18 Updated On:	Q	SE	SE	31	6N	2E	Iowa	0-225-265-2018 Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate	1.2	3.8	3.7	12.7	43.7	2.567	2.646	3.066		
WHITSON 55-25-024-QRY Created On: 01/02/25 Updated On:	Q	SE	SE	31	6N	2E	Iowa	0-225-81-2025 Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate	1.3	11.9	10.3	11.3	40.7	2.565	2.648	3.224		
IRON -- WI																		
BRACKETT QUARRY 55-26-002-QRY Created On: 07/21/17 Updated On:	Q	NE	NW	31	46N	2E	Iron	0-225-239-2017 Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate	0.1	0.0	0.5	2.6	11.9	2.697	2.710	0.487		
BRACKETT QUARRY 55-26-002-QRY Created On: 01/06/20 Updated On:	Q	NE	NW	31	46N	2E	Iron	0-225-31-2020 Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate	0.0	0.0	9.1	3.8	16.2	2.683	2.705	0.816		
BRACKETT QUARRY 55-26-002-QRY Created On: 01/04/23 Updated On:	Q	NE	NW	31	46N	2E	Iron	0-225-95-2023 Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate	0.1	2.9	1.6	3.0	13.4	2.662	2.682	0.759		

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
IRON -- WI																		
JOE KOHEGYI 55-26-012-PIT Created On: 07/21/17 Updated On:	P	NE	SW	31	43N	4E	Iron	0-225-238-2017		0.0	1.5	3.9	19.0	2.745	2.765	0.734		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
JOE KOHEGYI 55-26-012-PIT Created On: 04/15/24 Updated On:	P	NE	SW	31	43N	4E	Iron	0-225-231-2024	0.3	0.0	2.0	3.0	14.8	2.749	2.776	0.970		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
KIMBALL 55-26-013-QRY Created On: 04/23/15 Updated On:	Q		S	1	46N	1E	Iron	0-225-129-2015		0.0	1.6	2.6	12.0	2.733	2.764	1.142		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
KIMBALL 55-26-013-QRY Created On: 01/04/18 Updated On:	Q		S	1	46N	1E	Iron	0-225-60-2018	0.3	0.0	2.3	2.6	12.2	2.685	2.719	1.274		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
KIMBALL 55-26-013-QRY Created On: 04/30/21 Updated On:	Q		S	1	46N	1E	Iron	0-225-194-2021	0.3	0.0	2.4	2.6	12.3	2.700	2.736	1.344		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
KIMBALL 55-26-013-QRY Created On: 11/25/24 Updated On:	Q		S	1	46N	1E	Iron	0-225-315-2024	0.0	0.0	0.8	2.5	12.1	2.642	2.676	1.278		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
LUPPINO KIMBALL 55-26-030-QRY Created On: 06/13/18 Updated On:	Q		NW	4	46N	2E	Iron	0-225-230-2018		0.0	9.2	5.0	27.1	2.826	2.890	2.262		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
IRON -- WI																		
LUPPINO KIMBALL 55-26-030-QRY Created On: 04/01/21 Updated On:	Q		NW	4	46N	2E	Iron	0-225-165-2021		0.0	1.7	2.9	12.4	2.796	2.832	1.285		
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																	
LUPPINO KIMBALL 55-26-030-QRY Created On: 01/02/24 Updated On:	Q		NW	4	46N	2E	Iron	0-225-62-2024	0.1	0.0	9.4	3.5	15.9	2.608	2.671	2.430		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
LUPPINO MERCER 55-26-029-PIT Created On: 01/05/17 Updated On:	P	NW	NE	1	42N	3E	Iron	0-225-37-2017		0.0	2.8	3.9	18.8	2.710	2.740	1.085		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
LUPPINO MERCER 55-26-029-PIT Created On: 04/04/23 Updated On:	P	NW	NE	1	42N	3E	Iron	0-225-182-2023		0.0	2.7	4.3	18.7	2.721	2.753	1.167		
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																	
NLC MERCER 55-26-024-PIT Created On: 05/02/16 Updated On:	P	S	NW	6	42N	4E	Iron	0-225-159-2016		0.0	0.5	3.7	18.2	2.734	2.760	0.963		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
NLC MERCER 55-26-024-PIT Created On: 01/05/21 Updated On:	P	S	NW	6	42N	4E	Iron	0-225-55-2021	1.1	0.0	1.7	3.4	17.9	2.731	2.756	0.924		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
SAXON 55-26-019-PIT Created On: 06/13/18 Updated On:	P	SW	SW	18	46N	1E	Iron	0-225-231-2018		1.0	7.5	5.5	27.2	2.617	2.680	2.440		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
IRON -- WI																		
SAXON	P	SW	SW	18	46N	1E	Iron	0-225-181-2023		0.0	14.3	5.2	21.7	2.615	2.681	2.528		
55-26-019-PIT	Approved Use : Base Aggregate																	
Created On: 04/04/23																		
Updated On:																		
SAXON	P	SW	SW	18	46N	1E	Iron	0-225-71-2025	2.5	0.0	11.8	4.1	20.0	2.619	2.678	2.235		
55-26-019-PIT	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
Created On: 01/02/25																		
Updated On:																		
JACKSON -- WI																		
JACKSON COUNTY IRON MINE	Q	SE	SE	22	21N	3W	Jackson	0-225-120-2017		0.0	0.7	6.2	24.1	2.812	2.850	1.356		
55-27-004-QRY	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
Created On: 04/10/17																		
Updated On:																		
JACKSON COUNTY IRON MINE	Q	SE	SE	22	21N	3W	Jackson	0-225-62-2020		0.0	1.5	6.1	23.6	2.871	2.897	0.882		
55-27-004-QRY	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																	
Created On: 01/08/20																		
Updated On:																		
JACKSON COUNTY IRON MINE	Q	SE	SE	22	21N	3W	Jackson	0-225-60-2023	0.5	5.5	5.7	6.6	25.0	2.785	2.832	1.679		
55-27-004-QRY	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
Created On: 01/03/23																		
Updated On:																		
JACKSON COUNTY IRON MINE	Q	SE	SE	22	21N	3W	Jackson	0-225-251-2023	1.2	2.9	2.5	6.7	24.3	2.805	2.837	1.125		
55-27-004-QRY	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
Created On: 11/29/23																		
Updated On:																		
JACKSON COUNTY IRON MINE	Q	SE	SE	22	21N	3W	Jackson	0-225-82-2025	1.6	8.3	5.6	7.6	27.0	2.758	2.808	1.840		
55-27-004-QRY	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
Created On: 01/02/25																		
Updated On:																		

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	Sp. Gravity		Absorp. %	
														OD	SSD	Crse	Fine
JEFFERSON -- WI																	
ASPHALT CONTRACTORS JEFFERSON 55-28-019-PIT Created On: 01/08/21 Updated On:	P		NE	3	6N	13E	Jefferson	0-225-117-2021	2.3	3.8	0.8	8.6	35.4	2.634	2.681	1.789	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
BRATTSET 55-28-020-PIT Created On: 01/04/22 Updated On:	P	NW	NW	5	5N	16E	Jefferson	0-225-41-2022	1.6	5.2	1.1	4.3	22.8	2.694	2.732	1.401	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
*HAUSZ BROS. 55-28-021-QRY Created On: 04/05/22 Updated On:	Q	S	SW	11	5N	14E	Jefferson	0-225-154-2022	1.0	7.1	16.6	17.7	43.4	2.523	2.614	3.645	
	Approved Use : Base Aggregate																
NABER 55-28-009-PIT Created On: 03/20/20 Updated On:	P	NE	NW	31	5N	14E	Jefferson	0-225-133-2020	0.7	0.0	1.7	6.3	30.2	2.654	2.697	1.606	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
NABER 55-28-009-PIT Created On: 01/14/25 Updated On:	P	NE	NW	31	5N	14E	Jefferson	0-225-95-2025	1.0	10.1	3.2	5.4	26.7	2.684	2.726	1.556	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
NABER QUARRY 55-28-022-QRY Created On: 09/06/22 Updated On:	Q	NE	NW	31	5N	14E	Jefferson	0-225-255-2022	2.2	15.6	10.6	9.7	39.0	2.633	2.694	2.328	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
NABER QUARRY 55-28-022-QRY Created On: 11/07/22 Updated On:	Q	NE	NW	31	5N	14E	Jefferson	0-225-261-2022	0.2	10.9	6.1	4.9	26.5	2.693	2.736	1.614	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
JEFFERSON -- WI																		
NABER QUARRY 55-28-022-QRY Created On: 01/14/25 Updated On:	Q	NE	NW	31	5N	14E	Jefferson	0-225-97-2025	0.1	13.9	5.7	12.5	39.4	2.643	2.706	2.403		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
TIMBERLANE S & G 55-28-015-PIT Created On: 01/04/22 Updated On:	P	NW	SW	19	6N	14E	Jefferson	0-225-88-2022	0.6	6.2	1.8	4.8	25.5	2.677	2.710	1.234		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
JUNEAU -- WI																		
GEIER ROAD 55-29-009-QRY Created On: 05/18/18 Updated On:	Q			27	14N	3E	Juneau	0-225-213-2018	0.6	0.0	4.4	12.3	45.7	2.608	2.672	2.457		
	Approved Use : HMA<MT, CONCRETE, OGBC, Base Aggregate																	
GEIER ROAD 55-29-009-QRY Created On: 01/05/21 Updated On:	Q			27	14N	3E	Juneau	0-225-64-2021	0.8	6.2	8.4	10.9	42.9	2.645	2.697	1.973		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
GEIER ROAD 55-29-009-QRY Created On: 01/02/24 Updated On:	Q			27	14N	3E	Juneau	0-225-116-2024	1.8	4.2	1.6	8.4	34.6	2.577	2.634	2.197		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
KENOSHA -- WI																		
AMRIZE-DYER LAKE 55-30-004-PIT Created On: 05/11/18 Updated On:	P		W	29	2N	19E	Kenosha	0-225-209-2018	2.4	10.7	6.7	5.2	25.1	2.673	2.713	1.500		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
KENOSHA -- WI																		
AMRIZE-DYER LAKE 55-30-004-PIT Created On: 01/03/23 Updated On:	P		W	29	2N	19E	Kenosha	0-225-31-2023		0.0	12.3	1.3	6.6	28.2	2.628	2.683	2.079	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
KEWAUNEE -- WI																		
*BOULANGER 55-31-002-QRY Created On: 07/31/18 Updated On:	Q	NE	SE	15	22N	23E	Kewaunee	0-225-261-2018		1.9	0.0	2.1	6.7	31.1	2.769	2.794	0.885	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
*BOULANGER 55-31-002-QRY Created On: 01/06/21 Updated On:	Q	NE	SE	15	22N	23E	Kewaunee	0-225-112-2021		1.2	0.0	0.6	7.2	31.5	2.781	2.800	0.657	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
JADIN 55-31-006-PIT Created On: 07/31/18 Updated On:	P	NE	SE	31	25N	25E	Kewaunee	0-225-260-2018		4.5	0.0	3.0	7.2	30.8	2.667	2.697	1.107	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
JADIN 55-31-006-PIT Created On: 05/09/23 Updated On:	P	NE	SE	31	25N	25E	Kewaunee	0-225-217-2023		1.4	0.0	3.1	5.8	28.8	2.691	2.733	1.554	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
*KROPP AB 55-31-020-QRY Created On: 02/11/19 Updated On:	Q	NE	SE	15	22N	23E	Kewaunee	0-225-105-2019			0.0	1.7	7.9	34.6	2.810	2.823	0.456	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
*KROPP AB 55-31-020-QRY Created On: 04/28/22 Updated On:	Q	NE	SE	15	22N	23E	Kewaunee	0-225-187-2022		0.2	0.0	3.4	8.1	35.0	2.780	2.801	0.737	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
KEWAUNEE -- WI																		
PETERS ELLISVILLE PIT 55-31-005-PIT Created On: 06/25/24 Updated On:	P	NW	NW	13	23N	23E	Kewaunee	0-225-275-2024	0.6	0.0	1.6	7.7	32.6	2.712	2.747	1.287		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
SWAGEL 55-31-017-PIT Created On: 11/03/17 Updated On:	P		N	29	23N	24E	Kewaunee	0-225-285-2017	1.5	0.0	5.6	7.9	32.9	2.710	2.748	1.420		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
SWAGEL 55-31-017-PIT Created On: 03/07/22 Updated On:	P		N	29	23N	24E	Kewaunee	0-225-140-2022	3.1	0.0	4.2	6.2	30.8	2.693	2.730	1.368		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
LA CROSSE -- WI																		
KINGS BLUFF 55-32-010-QRY Created On: 09/02/15 Updated On:	Q	W	NE	25	18N	8W	La Crosse	0-225-235-2015	1.6	0.0	3.6	10.9	40.9	2.580	2.649	2.670		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
KINGS BLUFF 55-32-010-QRY Created On: 04/25/17 Updated On:	Q	W	NE	25	18N	8W	La Crosse	0-225-156-2017		0.0	3.0	12.0	44.3	2.584	2.650	2.532		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
KINGS BLUFF 55-32-010-QRY Created On: 03/23/18 Updated On:	Q	W	NE	25	18N	8W	La Crosse	0-225-145-2018	0.9	0.0	9.9	13.7	45.3	2.572	2.644	2.793		
	Approved Use : CONCRETE, Base Aggregate																	
KINGS BLUFF 55-32-010-QRY Created On: 01/07/19 Updated On:	Q	W	NE	25	18N	8W	La Crosse	0-225-48-2019	1.9	0.0	3.2	11.0	42.9	2.593	2.654	2.373		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
LA CROSSE -- WI																		
KINGS BLUFF 55-32-010-QRY Created On: 01/04/22 Updated On:	Q	W	NE	25	18N	8W	La Crosse	0-225-10-2022	1.1	3.0	6.6	11.0	42.6	2.589	2.655	2.544		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
KINGS BLUFF 55-32-010-QRY Created On: 01/14/25 Updated On:	Q	W	NE	25	18N	8W	La Crosse	0-225-101-2025	0.6	1.8	4.8	9.7	40.8	2.591	2.656	2.512		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MILESTONE-ANDERSON EE 55-32-001-QRY Created On: 07/15/20 Updated On:	Q	SE	NW	33	18N	5W	La Crosse	0-225-216-2020	0.8	0.0	2.6	8.9	38.5	2.606	2.666	2.278		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MILESTONE-ANDERSON EE 55-32-001-QRY Created On: 01/04/23 Updated On:	Q	SE	NW	33	18N	5W	La Crosse	0-225-85-2023	0.2	1.0	0.9	8.1	35.4	2.628	2.678	1.910		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MILESTONE-CLEMENTS 33 55-32-003-QRY Created On: 04/06/17 Updated On:	Q	NW	NE	7	15N	5W	La Crosse	0-225-109-2017	1.3	0.0	1.6	10.0	41.0	2.529	2.607	3.051		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
MILESTONE-CLEMENTS 33 55-32-003-QRY Created On: 01/03/20 Updated On:	Q	NW	NE	7	15N	5W	La Crosse	0-225-17-2020	1.8	0.0	5.1	11.2	41.6	2.539	2.618	3.141		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MILESTONE-CLEMENTS 33 55-32-003-QRY Created On: 01/04/23 Updated On:	Q	NW	NE	7	15N	5W	La Crosse	0-225-86-2023	2.1	3.4	3.8	11.4	41.8	2.544	2.621	3.050		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
LA CROSSE -- WI																		
MILESTONE-CLEMENTS YY 55-32-004-QRY Created On: 06/05/15 Updated On:	Q	SW	NE	3	15N	6W	La Crosse	0-225-186-2015		0.0	2.3	10.4	36.9	2.597	2.656	2.237		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
MILESTONE-CLEMENTS YY 55-32-004-QRY Created On: 01/03/18 Updated On:	Q	SW	NE	3	15N	6W	La Crosse	0-225-11-2018	3.0	0.0	2.6	12.2	41.9	2.551	2.620	2.700		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
MILESTONE-CLEMENTS YY 55-32-004-QRY Created On: 01/04/21 Updated On:	Q	SW	NE	3	15N	6W	La Crosse	0-225-30-2021	2.9	0.0	0.0	10.7	38.2	2.536	2.612	3.006		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MILESTONE-CLEMENTS YY 55-32-004-QRY Created On: 01/02/24 Updated On:	Q	SW	NE	3	15N	6W	La Crosse	0-225-25-2024	2.5	6.8	2.3	10.4	39.4	2.568	2.636	2.657		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MINDORO 55-32-012-QRY Created On: 05/04/17 Updated On:	Q	SW	SW	33	18N	6W	La Crosse	0-225-174-2017		0.0	2.7	10.2	32.7	2.611	2.669	2.187		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
MINDORO 55-32-012-QRY Created On: 01/08/20 Updated On:	Q	SW	SW	33	18N	6W	La Crosse	0-225-67-2020	0.7	0.0	7.4	10.3	38.6	2.584	2.650	2.549		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MINDORO 55-32-012-QRY Created On: 01/04/23 Updated On:	Q	SW	SW	33	18N	6W	La Crosse	0-225-87-2023	0.6	3.5	1.5	9.7	38.3	2.596	2.659	2.442		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
LA CROSSE -- WI																		
ROMSKOG 55-32-014-QRY Created On: 04/28/17 Updated On:	Q	NE	SE	18	17N	6W	La Crosse	0-225-162-2017		0.0	5.4	9.8	38.9	2.552	2.636	3.288		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
ROMSKOG 55-32-014-QRY Created On: 01/08/20 Updated On:	Q	NE	SE	18	17N	6W	La Crosse	0-225-64-2020	0.2	0.0	6.3	10.2	37.2	2.567	2.639	2.815		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
ROMSKOG 55-32-014-QRY Created On: 01/03/23 Updated On:	Q	NE	SE	18	17N	6W	La Crosse	0-225-24-2023	0.5	3.8	3.4	12.4	43.5	2.567	2.636	2.683		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
TORGERSON 55-32-016-QRY Created On: 03/24/16 Updated On:	Q	SE	SW	31	15N	5W	La Crosse	0-225-113-2016		0.0	3.2	11.1	39.3	2.539	2.612	2.901		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
TORGERSON 55-32-016-QRY Created On: 07/23/25 Updated On:	Q	SE	SW	31	15N	5W	La Crosse	0-225-231-2025	3.1	0.0	9.7	13.2	45.3	2.538	2.614	3.020		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
WALDENBERGER 55-32-017-QRY Created On: 03/29/17 Updated On:	Q			23	17N	7W	La Crosse	0-225-93-2017	0.3	0.0	3.2	11.8	44.2	2.521	2.610	3.526		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
WALDENBERGER 55-32-017-QRY Created On: 01/03/20 Updated On:	Q			23	17N	7W	La Crosse	0-225-22-2020	1.1	0.0	6.3	10.8	40.5	2.557	2.633	2.981		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
LA CROSSE -- WI																	
WALDENBERGER 55-32-017-QRY Created On: 01/03/23 Updated On:	Q			23	17N	7W	La Crosse	0-225-22-2023	0.4	6.7	7.8	12.7	45.5	2.529	2.611	3.230	
Approved Use : HMA<MT, CONCRETE, OGBC, Base Aggregate																	
LAFAYETTE -- WI																	
APPEL 55-33-002-QRY Created On: 04/23/15 Updated On:	Q	NW	SW	11	1N	3E	Lafayette	0-225-132-2015	0.2	0.4	3.5	10.1	38.7	2.635	2.686	1.954	
Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
APPEL 55-33-002-QRY Created On: 01/04/18 Updated On:	Q	NW	SW	11	1N	3E	Lafayette	0-225-70-2018	0.5	8.4	4.5	12.6	42.9	2.575	2.643	2.644	
Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
APPEL 55-33-002-QRY Created On: 01/05/21 Updated On:	Q	NW	SW	11	1N	3E	Lafayette	0-225-61-2021	0.8	3.1	5.0	11.2	39.6	2.619	2.677	2.213	
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
APPEL 55-33-002-QRY Created On: 06/12/25 Updated On:	Q	NW	SW	11	1N	3E	Lafayette	0-225-222-2025	1.0	10.0	5.1	9.5	37.6	2.608	2.671	2.411	
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
BLACKHAWK QUARRY PRODUCTS 55-33-017-QRY Created On: 02/13/20 Updated On:	Q	NE	NE	15	1N	5E	Lafayette	0-225-112-2020	0.5	4.2	5.6	11.6	42.5	2.538	2.627	3.508	
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
BLACKHAWK QUARRY PRODUCTS 55-33-017-QRY Created On: 01/02/24 Updated On:	Q	NE	NE	15	1N	5E	Lafayette	0-225-71-2024	0.1	4.6	2.6	9.9	36.0	2.609	2.676	2.559	
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
LAFAYETTE -- WI																	
DUNN 55-33-008-QRY Created On: 03/23/17 Updated On:	Q		SW	22	2N	3E	Lafayette	0-225-89-2017	1.8	5.3	7.4	10.5	38.9	2.584	2.654	2.710	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
DUNN 55-33-008-QRY Created On: 02/09/18 Updated On:	Q		SW	22	2N	3E	Lafayette	0-225-92-2018	1.1	3.0	9.0	7.5	33.8	2.563	2.639	2.964	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
DUNN 55-33-008-QRY Created On: 03/17/21 Updated On:	Q		SW	22	2N	3E	Lafayette	0-225-138-2021	0.7	14.2	2.4	9.1	36.3	2.581	2.650	2.678	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
DUNN 55-33-008-QRY Created On: 02/28/24 Updated On:	Q		SW	22	2N	3E	Lafayette	0-225-182-2024	1.6	12.4	8.3	9.5	38.3	2.578	2.649	2.754	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
FLANNERY 55-33-009-QRY Created On: 04/16/15 Updated On:	Q	NW	SW	6	2N	5E	Lafayette	0-225-125-2015	1.3	8.1	2.4	7.7	31.6	2.643	2.692	1.852	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
FLANNERY 55-33-009-QRY Created On: 03/23/18 Updated On:	Q	NW	SW	6	2N	5E	Lafayette	0-225-141-2018	2.4	17.0	4.0	7.4	28.8	2.597	2.658	2.340	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
FLANNERY 55-33-009-QRY Created On: 01/07/19 Updated On:	Q	NW	SW	6	2N	5E	Lafayette	0-225-53-2019	1.5	9.5	5.4	7.5	29.9	2.603	2.660	2.196	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
LAFAYETTE -- WI																		
FLANNERY 55-33-009-QRY Created On: 04/28/20 Updated On:	Q	NW	SW	6	2N	5E	Lafayette	0-225-163-2020	0.9	6.5	3.5	9.8	34.6	2.599	2.662	2.392		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
FLANNERY 55-33-009-QRY Created On: 03/17/21 Updated On:	Q	NW	SW	6	2N	5E	Lafayette	0-225-148-2021	3.0	8.3	3.4	9.8	35.3	2.560	2.634	2.864		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
FLANNERY 55-33-009-QRY Created On: 03/15/22 Updated On:	Q	NW	SW	6	2N	5E	Lafayette	0-225-143-2022	1.3	5.4	7.0	10.0	35.1	2.635	2.688	1.987		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
FLANNERY 55-33-009-QRY Created On: 01/03/23 Updated On:	Q	NW	SW	6	2N	5E	Lafayette	0-225-5-2023	1.2	4.1	3.8	6.9	29.0	2.609	2.669	2.290		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
FLANNERY 55-33-009-QRY Created On: 01/04/24 Updated On:	Q	NW	SW	6	2N	5E	Lafayette	0-225-139-2024	0.8	6.9	8.1	8.8	36.9	2.610	2.671	2.312		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
LANGE (CAREY) 55-33-013-QRY Created On: 10/10/16 Updated On:	Q	NE	SE	6	2N	3E	Lafayette	0-225-266-2016	3.3	2.6	1.6	8.3	33.3	2.545	2.620	2.968		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
LANGE (CAREY) 55-33-013-QRY Created On: 01/07/19 Updated On:	Q	NE	SE	6	2N	3E	Lafayette	0-225-56-2019	3.2	6.2	3.8	10.9	38.1	2.530	2.609	3.125		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
LAFAYETTE -- WI																		
LANGE (CAREY) 55-33-013-QRY Created On: 01/10/22 Updated On:	Q	NE	SE	6	2N	3E	Lafayette	0-225-106-2022	2.2	8.1	8.8	10.4	39.6	2.502	2.594	3.681		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
LANGE (CAREY) 55-33-013-QRY Created On: 01/02/25 Updated On:	Q	NE	SE	6	2N	3E	Lafayette	0-225-85-2025	2.0	12.7	3.4	9.8	34.8	2.569	2.640	2.747		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MOUNDS BRANCH 55-33-018-QRY Created On: 01/29/24 Updated On:	Q	NW	NE	33	4N	1E	Lafayette	0-225-150-2024	1.0	5.8	3.2	9.2	34.9	2.574	2.645	2.755		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
RUEF 55-33-024-QRY Created On: 04/06/17 Updated On:	Q	SW	SE	11	2N	3E	Lafayette	0-225-111-2017	1.9	2.4	1.5	10.1	35.5	2.591	2.657	2.532		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
RUEF 55-33-024-QRY Created On: 04/28/20 Updated On:	Q	SW	SE	11	2N	3E	Lafayette	0-225-159-2020	1.1	4.1	1.6	9.3	35.1	2.586	2.665	3.055		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
RUEF 55-33-024-QRY Created On: 01/03/23 Updated On:	Q	SW	SE	11	2N	3E	Lafayette	0-225-8-2023	0.4	4.9	4.3	10.8	38.2	2.551	2.632	3.191		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
W.E. ROCK 55-33-029-QRY Created On: 04/13/21 Updated On:	Q	NE	NE	30	1N	1E	Lafayette	0-225-182-2021	0.0	3.6	1.6	16.1	44.6	2.594	2.664	2.668		
	Approved Use : CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	Sp. Gravity		Absorp. %		
														OD	SSD	Crse	Fine	
LAFAYETTE -- WI																		
W.E. ROCK 55-33-029-QRY Created On: 01/29/24 Updated On:	Q	NE	NE	30	1N	1E	Lafayette	0-225-151-2024	0.2	4.1	4.6	8.7	34.9	2.552	2.640	3.426		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
LANGLADE -- WI																		
AINSWORTH 55-34-001-PIT Created On: 01/04/19 Updated On:	P	SW	SW	1	33N	12E	Langlade	0-225-13-2019	0.0	0.0	0.2	5.3	22.9	2.693	2.709	0.613		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
AINSWORTH 55-34-001-PIT Created On: 08/14/24 Updated On:	P	SW	SW	1	33N	12E	Langlade	0-225-295-2024	0.9	1.0	0.6	5.1	21.5	2.703	2.719	0.615		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
ANTIGO 55-34-002-PIT Created On: 01/04/19 Updated On:	P	SE	NE	13	31N	11E	Langlade	0-225-15-2019	0.0	0.7	1.4	7.8	32.6	2.650	2.672	0.802		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
ANTIGO 55-34-002-PIT Created On: 01/02/24 Updated On:	P	SE	NE	13	31N	11E	Langlade	0-225-11-2024	0.2	0.0	0.2	6.6	27.5	2.676	2.695	0.719		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
BENES 55-34-004-PIT Created On: 07/18/19 Updated On:	P	SW	NE	8	32N	11E	Langlade	0-225-241-2019	0.1	0.0	0.5	4.6	20.5	2.709	2.735	0.935		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
BENES 55-34-004-PIT Created On: 01/02/24 Updated On:	P	SW	NE	8	32N	11E	Langlade	0-225-63-2024	0.1	0.0	2.0	5.2	22.0	2.719	2.747	1.035		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
LANGLADE -- WI																		
BRIGGS PIT 55-34-008-PIT Created On: 08/20/19 Updated On:	P	SW	NE	1	34N	10E	Langlade	0-225-263-2019		0.6	0.0	1.1	4.3	19.0	2.680	2.703	0.860	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
BRIGGS PIT 55-34-008-PIT Created On: 04/24/23 Updated On:	P	SW	NE	1	34N	10E	Langlade	0-225-207-2023		0.2	0.0	0.7	4.8	22.0	2.691	2.711	0.762	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
HESS 55-34-014-PIT Created On: 01/08/16 Updated On:	P	SW	SW	2	30N	11E	Langlade	0-225-45-2016			0.0	1.8	5.8	27.2	2.677	2.695	0.664	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
HESS 55-34-014-PIT Created On: 01/04/21 Updated On:	P	SW	SW	2	30N	11E	Langlade	0-225-15-2021		0.0	0.6	0.8	5.6	25.3	2.680	2.711	1.180	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
KOEPPPEL 55-34-015-PIT Created On: 06/13/22 Updated On:	P		NW	12	30N	12E	Langlade	0-225-228-2022		0.0	0.5	0.3	6.6	29.3	2.671	2.691	0.743	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
OLDENBURG 55-34-028-PIT Created On: 01/30/25 Updated On:	P	NE	SW	19	34N	9E	Langlade	0-225-147-2025		0.7	0.0	1.6	4.9	22.5	2.693	2.724	1.158	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
SAMBS STONE 55-34-022-PIT Created On: 03/09/15 Updated On:	P	NW	NW	11	30N	11E	Langlade	0-225-94-2015			0.0	1.6	6.2	26.7	2.675	2.698	0.884	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
LANGLADE -- WI																		
SAMBS STONE 55-34-022-PIT Created On: 01/07/20 Updated On:	P	NW	NW	11	30N	11E	Langlade	0-225-46-2020	0.0	1.6	0.5	6.9	29.4	2.687	2.706	0.724		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
SAMBS STONE 55-34-022-PIT Created On: 02/24/25 Updated On:	P	NW	NW	11	30N	11E	Langlade	0-225-156-2025	0.6	3.7	4.2	6.1	25.9	2.671	2.695	0.916		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
STECK BAUER PIT 55-34-027-PIT Created On: 04/15/24 Updated On:	P	SW	NW	30	31N	15E	Langlade	0-225-229-2024	0.8	0.0	0.2	5.3	25.1	2.681	2.698	0.632		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
WOLF RIVER 55-34-025-PIT Created On: 05/26/16 Updated On:	P	NW	SW	36	31N	14E	Langlade	0-225-189-2016	0.4	0.0	2.1	7.7	26.8	2.635	2.658	0.870		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
WOLF RIVER 55-34-025-PIT Created On: 01/04/21 Updated On:	P	NW	SW	36	31N	14E	Langlade	0-225-14-2021	0.0	0.4	0.3	4.1	23.0	2.664	2.684	0.772		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
LINCOLN -- WI																		
BROCK 55-35-003-PIT Created On: 03/09/15 Updated On:	P		NE	29	31N	7E	Lincoln	0-225-93-2015		0.0	3.2	4.1	19.0	2.685	2.714	1.094		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
BROCK 55-35-003-PIT Created On: 01/08/20 Updated On:	P		NE	29	31N	7E	Lincoln	0-225-47-2020	0.0	2.0	0.5	6.0	24.4	2.690	2.715	0.948		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
LINCOLN -- WI																	
BROCK 55-35-003-PIT Created On: 01/14/25 Updated On:	P		NE	29	31N	7E	Lincoln	0-225-111-2025	2.2	8.0	0.9	4.1	18.2	2.672	2.708	1.315	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
COOMBS 55-35-004-PIT Created On: 01/03/18 Updated On:	P			16	34N	7E	Lincoln	0-225-4-2018	0.2	0.0	1.2	4.3	21.1	2.724	2.745	0.766	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
COOMBS 55-35-004-PIT Created On: 05/22/23 Updated On:	P			16	34N	7E	Lincoln	0-225-224-2023	0.3	0.0	2.8	4.5	20.3	2.749	2.773	0.858	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
COOMBS SOUTH 55-35-005-PIT Created On: 05/10/18 Updated On:	P		NW	21	34N	7E	Lincoln	0-225-204-2018	1.3	0.0	1.4	4.7	22.9	2.709	2.732	0.819	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
COOMBS SOUTH 55-35-005-PIT Created On: 01/02/24 Updated On:	P		NW	21	34N	7E	Lincoln	0-225-67-2024	0.3	2.9	3.2	4.2	20.5	2.683	2.714	1.138	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
CTH R 55-35-009-PIT Created On: 07/26/21 Updated On:	P	SE	NE	7	32N	7E	Lincoln	0-225-251-2021	0.4	0.0	5.1	4.7	21.3	2.715	2.748	1.217	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
DALKA 55-35-043-PIT Created On: 04/24/19 Updated On:	P	SW	SW	3	35N	8E	Lincoln	0-225-170-2019	0.6	0.0	0.3	4.6	21.5	2.671	2.694	0.868	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
LINCOLN -- WI																		
DALKA 55-35-043-PIT Created On: 01/02/24 Updated On:	P	SW	SW	3	35N	8E	Lincoln	0-225-66-2024	0.0	0.0	1.3	4.3	18.7	2.699	2.724	0.917		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
EVERSON PIT 55-35-044-PIT Created On: 01/02/24 Updated On:	P	SE	SW	2	35N	8E	Lincoln	0-225-58-2024	0.3	0.0	0.2	3.4	16.1	2.735	2.753	0.641		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
*JAECKS 55-35-027-PIT Created On: 06/25/20 Updated On:	P	SE	SW	1	34N	6E	Lincoln	0-225-208-2020	0.3	0.0	0.5	4.6	21.3	2.689	2.718	1.096		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
LINCOLN CTH W 55-35-041-PIT Created On: 01/02/20 Updated On:	P	E	SW	33	31N	7E	Lincoln	0-225-11-2020	3.2	0.0	6.2	5.1	22.7	2.613	2.655	1.617		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
LINCOLN CTH W 55-35-041-PIT Created On: 01/02/25 Updated On:	P	E	SW	33	31N	7E	Lincoln	0-225-11-2025	0.1	4.5	7.7	4.8	21.9	2.630	2.668	1.443		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
*PETERSON 55-35-029-PIT Created On: 07/16/20 Updated On:	P	NW	SE	30	32N	6E	Lincoln	0-225-218-2020	1.4	0.0	0.8	4.2	20.6	2.688	2.717	1.087		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
*PINE RIDGE 55-35-030-PIT Created On: 05/11/15 Updated On:	P	NW	SW	8	31N	7E	Lincoln	0-225-168-2015		0.0	0.9	4.5	19.8	2.675	2.708	1.256		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
LINCOLN -- WI																		
*PINE RIDGE 55-35-030-PIT Created On: 05/12/20 Updated On:	P	NW	SW	8	31N	7E	Lincoln	0-225-176-2020	1.9	0.0	2.3	4.4	20.6	2.679	2.708	1.085		
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
MANITOWOC -- WI																		
AGGRECON 55-36-001-QRY Created On: 06/03/15 Updated On:	Q		SE	33	17N	21E	Manitowoc	0-225-182-2015	1.5	0.0	1.4	7.6	32.9	2.719	2.751	1.152		
Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																		
AGGRECON 55-36-001-QRY Created On: 02/15/18 Updated On:	Q		SE	33	17N	21E	Manitowoc	0-225-99-2018	0.9	3.3	2.7	6.6	32.2	2.745	2.770	0.917		
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
AGGRECON 55-36-001-QRY Created On: 01/04/21 Updated On:	Q		SE	33	17N	21E	Manitowoc	0-225-43-2021	0.3	1.2	0.3	5.3	25.5	2.764	2.785	0.755		
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
AGGRECON 55-36-001-QRY Created On: 01/29/24 Updated On:	Q		SE	33	17N	21E	Manitowoc	0-225-166-2024	0.0	0.9	1.2	6.4	29.4	2.780	2.799	0.659		
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
BADGERLAND 55-36-031-PIT Created On: 01/25/19 Updated On:	P			33	21N	23E	Manitowoc	0-225-93-2019	1.8	0.0	3.5	5.9	29.5	2.697	2.738	1.535		
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
BADGERLAND 55-36-031-PIT Created On: 02/28/24 Updated On:	P			33	21N	23E	Manitowoc	0-225-170-2024	4.2	0.0	2.5	6.5	30.4	2.719	2.753	1.245		
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
MANITOWOC -- WI																		
BADGERLAND - LARABEE 55-36-033-QRY Created On: 04/24/19 Updated On:	Q			33	21N	23E	Manitowoc	0-225-166-2019		0.0	0.0	3.7	6.5	29.6	2.743	2.764	0.768	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
BADGERLAND - LARABEE 55-36-033-QRY Created On: 01/04/22 Updated On:	Q			33	21N	23E	Manitowoc	0-225-63-2022		3.7	0.0	5.3	8.1	34.8	2.661	2.711	1.890	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
BADGERLAND - LARABEE 55-36-033-QRY Created On: 04/15/24 Updated On:	Q			33	21N	23E	Manitowoc	0-225-230-2024		0.0	0.0	0.9	9.0	38.7	2.794	2.811	0.625	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
BADGERLAND X PIT 55-36-039-PIT Created On: 08/28/18 Updated On:	P	SW	9		17N	22E	Manitowoc	0-225-278-2018		0.1	0.0	1.3	6.0	27.5	2.774	2.799	0.870	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
BADGERLAND X PIT 55-36-039-PIT Created On: 03/21/23 Updated On:	P	SW	9		17N	22E	Manitowoc	0-225-172-2023		0.8	0.0	2.9	6.3	30.2	2.763	2.790	0.948	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
BADGERLAND-SHOTO 55-36-005-QRY Created On: 01/21/16 Updated On:	Q	SE	SW	20	20N	24E	Manitowoc	0-225-67-2016		0.8	1.1	1.2	8.0	32.1	2.798	2.817	0.704	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
BADGERLAND-SHOTO 55-36-005-QRY Created On: 01/25/19 Updated On:	Q	SE	SW	20	20N	24E	Manitowoc	0-225-92-2019			0.0	4.1	8.5	32.5	2.746	2.781	1.284	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
MANITOWOC -- WI																		
BADGERLAND-SHOTO 55-36-005-QRY Created On: 01/04/22 Updated On:	Q	SE	SW	20	20N	24E	Manitowoc	0-225-67-2022	0.0	0.0	8.5	7.9	32.3	2.785	2.806	0.771		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
BADGERLAND-SHOTO 55-36-005-QRY Created On: 04/07/25 Updated On:	Q	SE	SW	20	20N	24E	Manitowoc	0-225-183-2025	0.0	1.0	0.5	7.4	29.9	2.813	2.825	0.437		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
BIESE 55-36-006-PIT Created On: 01/04/18 Updated On:	P	SW	NE	34	18N	21E	Manitowoc	0-225-83-2018	0.3	1.3	2.7	6.4	30.5	2.752	2.780	1.013		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
BIESE 55-36-006-PIT Created On: 01/02/24 Updated On:	P	SW	NE	34	18N	21E	Manitowoc	0-225-131-2024	2.2	4.7	3.6	9.5	34.1	2.730	2.764	1.220		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
BLATZ - QRY 55-36-047-QRY Created On: 01/07/20 Updated On:	Q	SW	NE	35	17N	21E	Manitowoc	0-225-37-2020	0.1	0.0	2.4	6.3	28.3	2.769	2.792	0.815		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
BLATZ - QRY 55-36-047-QRY Created On: 05/20/24 Updated On:	Q	SW	NE	35	17N	21E	Manitowoc	0-225-256-2024	1.4	0.9	2.3	8.9	35.8	2.746	2.771	0.889		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
BONDE 55-36-008-PIT Created On: 01/05/17 Updated On:	P		NE	5	17N	22E	Manitowoc	0-225-18-2017	0.9	1.9	2.2	8.0	33.1	2.768	2.790	0.797		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
MANITOWOC -- WI																		
BONDE 55-36-008-PIT Created On: 04/28/22 Updated On:	P		NE	5	17N	22E	Manitowoc	0-225-184-2022	2.1	0.0	0.4	7.8	34.3	2.766	2.790	0.873		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
BROCKER 55-36-009-PIT Created On: 04/19/19 Updated On:	P	NW	SW	20	18N	21E	Manitowoc	0-225-147-2019	0.8	0.0	1.3	6.5	29.2	2.764	2.789	0.902		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
BROCKER 55-36-009-PIT Created On: 01/02/24 Updated On:	P	NW	SW	20	18N	21E	Manitowoc	0-225-51-2024	1.1	0.0	2.2	7.9	33.4	2.749	2.777	1.001		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
CAREW-MARIBEL 55-36-013-PIT Created On: 08/09/18 Updated On:	P	NE	NW	19	21N	22E	Manitowoc	0-225-267-2018	1.2	0.0	2.9	7.6	34.2	2.707	2.748	1.491		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
CAREW-MARIBEL 55-36-013-PIT Created On: 01/04/23 Updated On:	P	NE	NW	19	21N	22E	Manitowoc	0-225-102-2023	0.8	0.0	3.7	8.2	34.9	2.691	2.731	1.486		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
GRIMMS 55-36-015-QRY Created On: 01/04/16 Updated On:	Q	NE	SE	6	19N	22E	Manitowoc	0-225-6-2016		0.2	1.4	7.8	30.5	2.690	2.727	1.362		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
GRIMMS 55-36-015-QRY Created On: 05/09/19 Updated On:	Q	NE	SE	6	19N	22E	Manitowoc	0-225-182-2019	0.0	0.0	0.7	8.0	32.0	2.693	2.731	1.426		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
MANITOWOC -- WI																		
GRIMMS 55-36-015-QRY Created On: 01/04/22 Updated On:	Q	NE	SE	6	19N	22E	Manitowoc	0-225-33-2022	0.0	0.0	1.6	9.6	38.6	2.727	2.758	1.133		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
GRIMMS 55-36-015-QRY Created On: 01/02/24 Updated On:	Q	NE	SE	6	19N	22E	Manitowoc	0-225-102-2024	0.0	0.5	1.2	8.9	36.6	2.712	2.744	1.200		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
KOSSUTH QUARRY 55-36-048-QRY Created On: 03/28/18 Updated On:	Q	W	SE	36	20N	23E	Manitowoc	0-225-151-2018	0.0	0.8	0.4	7.4	33.2	2.794	2.811	0.633		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
KOSSUTH QUARRY 55-36-048-QRY Created On: 01/05/21 Updated On:	Q	W	SE	36	20N	23E	Manitowoc	0-225-106-2021	0.0	1.0	2.2	8.1	33.3	2.752	2.780	1.045		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
KOSSUTH QUARRY 55-36-048-QRY Created On: 01/04/24 Updated On:	Q	W	SE	36	20N	23E	Manitowoc	0-225-135-2024	0.0	0.0	0.8	10.1	37.8	2.766	2.790	0.852		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
LEMBERGER QUARRY 55-36-049-QRY Created On: 01/29/24 Updated On:	Q	SE	NE	34	20N	22E	Manitowoc	0-225-164-2024	0.2	0.0	0.6	9.6	34.6	2.716	2.747	1.116		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
LUTZKE 55-36-022-PIT Created On: 10/05/18 Updated On:	P	SE	SE	20	18N	22E	Manitowoc	0-225-288-2018	1.2	0.0	1.0	6.7	31.6	2.766	2.789	0.835		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
MANITOWOC -- WI																		
LUTZKE 55-36-022-PIT Created On: 04/28/22 Updated On:	P	SE	SE	20	18N	22E	Manitowoc	0-225-189-2022	1.5	0.0	0.4	6.9	32.4	2.769	2.792	0.819		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
*MANITOWOC CO. STH 310 55-36-023-QRY Created On: 01/12/16 Updated On:	Q	E	SW	36	20N	23E	Manitowoc	0-225-49-2016		0.0	0.7	6.8	30.0	2.779	2.799	0.741		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
*MANITOWOC CO. STH 310 55-36-023-QRY Created On: 01/04/19 Updated On:	Q	E	SW	36	20N	23E	Manitowoc	0-225-16-2019		1.3	9.6	8.1	34.3	2.764	2.790	0.950		
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																	
*MANITOWOC CO. STH 310 55-36-023-QRY Created On: 01/10/22 Updated On:	Q	E	SW	36	20N	23E	Manitowoc	0-225-98-2022	0.2	2.8	2.8	10.0	37.7	2.738	2.766	1.014		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MICHELS - MISHICOT 55-36-025-PIT Created On: 01/08/15 Updated On:	P	SE	SE	27	21N	23E	Manitowoc	0-225-27-2015	0.5	0.0	3.7	7.1	32.4	2.679	2.720	1.537		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
MICHELS - MISHICOT 55-36-025-PIT Created On: 01/05/21 Updated On:	P	SE	SE	27	21N	23E	Manitowoc	0-225-46-2021	0.8	0.0	3.6	6.0	29.8	2.698	2.741	1.612		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MISHICOT 55-36-027-PIT Created On: 01/12/16 Updated On:	P	NE	SE	27	21N	23E	Manitowoc	0-225-55-2016		0.0	1.3	6.1	28.9	2.727	2.757	1.109		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
MANITOWOC -- WI																		
MISHICOT 55-36-027-PIT Created On: 01/05/21 Updated On:	P	NE	SE	27	21N	23E	Manitowoc	0-225-105-2021	0.0	3.7	0.9	5.7	27.3	2.675	2.721	1.710		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
REESE 55-36-034-PIT Created On: 06/26/19 Updated On:	P	SW	SW	22	17N	21E	Manitowoc	0-225-228-2019	1.1	2.2	0.8	5.4	29.4	2.753	2.776	0.833		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
REESE 55-36-034-PIT Created On: 05/20/24 Updated On:	P	SW	SW	22	17N	21E	Manitowoc	0-225-255-2024	2.3	3.9	3.6	5.7	29.5	2.734	2.761	0.973		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
ROCKWELL LESTONE 55-36-035-QRY Created On: 04/13/16 Updated On:	Q			36	20N	23E	Manitowoc	0-225-146-2016		0.0	2.0	12.6	41.7	2.693	2.735	1.577		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
ROCKWELL LESTONE 55-36-035-QRY Created On: 04/19/19 Updated On:	Q			36	20N	23E	Manitowoc	0-225-148-2019		0.0	2.9	12.7	42.1	2.692	2.739	1.722		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
ROCKWELL LESTONE 55-36-035-QRY Created On: 03/07/22 Updated On:	Q			36	20N	23E	Manitowoc	0-225-137-2022	0.0	0.0	3.0	9.6	32.0	2.728	2.759	1.126		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
ROCKWELL LESTONE 55-36-035-QRY Created On: 01/02/25 Updated On:	Q			36	20N	23E	Manitowoc	0-225-62-2025	0.0	3.5	14.5	23.5	56.3	2.658	2.709	1.915		

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	LA Wear (%)					OD		SSD			
								100					500	OD	SSD	Crse	Fine	
MANITOWOC -- WI																		
SCHOOL HILL 55-36-036-PIT Created On: 04/19/19 Updated On:	P	NE	NW	16	17N	22E	Manitowoc	0-225-146-2019	0.6	2.1	0.5	7.2	29.7	2.786	2.807	0.767		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
SCHOOL HILL 55-36-036-PIT Created On: 01/02/24 Updated On:	P	NE	NW	16	17N	22E	Manitowoc	0-225-130-2024	0.0	2.0	0.7	6.4	30.1	2.785	2.806	0.764		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
SCOTT CONSTRUCTION - COOPERSTOWN 55-36-044-QRY Created On: 05/30/17 Updated On:	Q	W	NW	19	21N	22E	Manitowoc	0-225-200-2017	11.6	0.0	6.4	6.1	26.7	2.673	2.722	1.843		
	Approved Use : HMA<MT, HMA>=MT, Base Aggregate																	
SCOTT CONSTRUCTION - COOPERSTOWN 55-36-044-QRY Created On: 02/28/23 Updated On:	Q	W	NW	19	21N	22E	Manitowoc	0-225-157-2023	9.6	5.6	5.2	5.8	27.5	2.665	2.712	1.737		
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																	
ST NAZIANZ 55-36-043-PIT Created On: 01/05/17 Updated On:	P		S	30	18N	22E	Manitowoc	0-225-20-2017	0.5	1.6	2.0	7.8	33.3	2.750	2.778	1.033		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
ST NAZIANZ 55-36-043-PIT Created On: 04/28/22 Updated On:	P		S	30	18N	22E	Manitowoc	0-225-185-2022	1.1	0.0	1.3	7.2	33.0	2.761	2.788	0.983		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
VALDERS 55-36-026-QRY Created On: 01/05/17 Updated On:	Q	SE	NE	32	19N	22E	Manitowoc	0-225-19-2017		0.0	0.8	9.4	39.7	2.730	2.755	0.932		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
MANITOWOC -- WI																		
VALDERS 55-36-026-QRY Created On: 03/09/20 Updated On:	Q	SE	NE	32	19N	22E	Manitowoc	0-225-122-2020	0.2	0.2	1.9	7.9	36.2	2.745	2.768	0.810		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
VALDERS 55-36-026-QRY Created On: 02/09/23 Updated On:	Q	SE	NE	32	19N	22E	Manitowoc	0-225-142-2023	0.0	0.0	1.5	7.9	35.3	2.740	2.762	0.806		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MARATHON -- WI																		
ATHENS 55-37-005-QRY Created On: 08/16/16 Updated On:	Q	S	SE	24	30N	4E	Marathon	0-225-243-2016		0.0	0.2	5.1	24.8	2.695	2.710	0.573		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
ATHENS 55-37-005-QRY Created On: 05/10/18 Updated On:	Q	S	SE	24	30N	4E	Marathon	0-225-203-2018		0.0	0.2	3.0	16.1	2.837	2.845	0.255		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
ATHENS 55-37-005-QRY Created On: 01/05/21 Updated On:	Q	S	SE	24	30N	4E	Marathon	0-225-87-2021	0.0	0.0	0.6	4.8	23.1	2.711	2.724	0.492		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
ATHENS 55-37-005-QRY Created On: 01/02/24 Updated On:	Q	S	SE	24	30N	4E	Marathon	0-225-81-2024	0.0	0.0	0.3	5.4	25.3	2.708	2.718	0.397		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
BEVENT 55-37-008-PIT Created On: 04/30/21 Updated On:	P	SW	NW	5	26N	9E	Marathon	0-225-196-2021	2.0	0.0	0.6	5.8	26.5	2.654	2.675	0.771		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
MARATHON -- WI																	
BOHLMON 55-37-009-PIT Created On: 05/01/18 Updated On:	P		SE	36	28N	10E	Marathon	0-225-187-2018		0.6	2.1	7.5	30.8	2.653	2.682	1.105	
	Approved Use : HMA<MT, HMA>=MT, Base Aggregate																
BOHLMON 55-37-009-PIT Created On: 01/03/23 Updated On:	P		SE	36	28N	10E	Marathon	0-225-16-2023		0.0	0.4	8.6	33.4	2.646	2.673	1.028	
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																
CISLER 55-37-016-QRY Created On: 01/06/16 Updated On:	Q	NW	NW	5	26N	7E	Marathon	0-225-29-2016		0.0	0.5	3.9	17.2	2.680	2.691	0.411	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
CISLER 55-37-016-QRY Created On: 01/04/19 Updated On:	Q	NW	NW	5	26N	7E	Marathon	0-225-32-2019		0.0	0.2	2.6	13.6	2.683	2.691	0.319	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
CISLER 55-37-016-QRY Created On: 04/01/19 Updated On:	Q	NW	NW	5	26N	7E	Marathon	0-225-121-2019	0.0	0.0	0.4	4.3	18.4	2.678	2.688	0.350	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
CISLER 55-37-016-QRY Created On: 01/04/22 Updated On:	Q	NW	NW	5	26N	7E	Marathon	0-225-37-2022	0.0	1.3	1.9	4.2	18.7	2.660	2.677	0.650	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
CISLER 55-37-016-QRY Created On: 01/02/25 Updated On:	Q	NW	NW	5	26N	7E	Marathon	0-225-10-2025	0.0	0.3	0.2	2.6	13.3	2.670	2.681	0.425	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
MARATHON -- WI																		
COLDSRING QUARRY 55-37-099-QRY Created On: 01/29/24 Updated On:	Q	SW	SE	34	30N	8E	Marathon	0-225-154-2024	0.2	0.0	1.2	7.1	32.9	2.597	2.612	0.590		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
CTH "N" / MILESTONE 345 55-37-021-QRY Created On: 01/06/16 Updated On:	Q	NW	NE	19	28N	7E	Marathon	0-225-30-2016	0.0	0.0	0.5	11.3	45.4	2.579	2.600	0.795		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
CTH "N" / MILESTONE 345 55-37-021-QRY Created On: 01/04/19 Updated On:	Q	NW	NE	19	28N	7E	Marathon	0-225-34-2019	0.0	0.0	0.7	9.8	42.2	2.276	2.286	0.431		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
CTH "N" / MILESTONE 345 55-37-021-QRY Created On: 01/04/22 Updated On:	Q	NW	NE	19	28N	7E	Marathon	0-225-25-2022	0.0	0.2	0.6	7.6	36.6	2.603	2.617	0.563		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
CTH "N" / MILESTONE 345 55-37-021-QRY Created On: 01/02/25 Updated On:	Q	NW	NE	19	28N	7E	Marathon	0-225-5-2025	0.0	0.3	0.8	7.7	37.7	2.598	2.613	0.605		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
EASTON 55-37-026-PIT Created On: 01/05/17 Updated On:	P		SW	23	29N	9E	Marathon	0-225-43-2017	0.0	0.0	2.1	6.1	25.3	2.670	2.695	0.921		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
EASTON 55-37-026-PIT Created On: 01/14/25 Updated On:	P		SW	23	29N	9E	Marathon	0-225-113-2025	0.8	7.1	3.3	3.6	17.6	2.729	2.752	0.860		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
MARATHON -- WI																		
GRANITE HEIGHTS 55-37-100-QRY Created On: 07/31/24 Updated On:	Q	NE	NE	35	30N	7E	Marathon	0-225-289-2024		0.0	0.7	0.8	4.2	21.2	2.605	2.626	0.807	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
H&H 55-37-096-QRY Created On: 01/19/23 Updated On:	Q	NW	SW	5	28N	6E	Marathon	0-225-124-2023		0.2	2.6	1.0	4.7	19.0	2.627	2.670	1.619	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
KAFKA QUARRY 55-37-039-QRY Created On: 01/03/17 Updated On:	Q	NE	NW	3	27N	3E	Marathon	0-225-6-2017			0.0	0.5	2.0	10.6	2.776	2.785	0.325	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
KAFKA QUARRY 55-37-039-QRY Created On: 01/07/20 Updated On:	Q	NE	NW	3	27N	3E	Marathon	0-225-42-2020		0.0	0.0	0.1	2.5	10.8	2.800	2.805	0.201	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
KAFKA QUARRY 55-37-039-QRY Created On: 01/03/23 Updated On:	Q	NE	NW	3	27N	3E	Marathon	0-225-37-2023		0.0	0.8	0.6	3.5	14.6	2.749	2.766	0.638	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MARTIN ROAD 55-37-091-QRY Created On: 06/26/19 Updated On:	Q	SE	SE	6	27N	9E	Marathon	0-225-232-2019		1.3	0.0	1.3	9.6	38.3	2.591	2.609	0.713	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
MARTIN ROAD 55-37-091-QRY Created On: 02/17/22 Updated On:	Q	SE	SE	6	27N	9E	Marathon	0-225-132-2022		0.0	0.0	0.5	6.8	33.7	2.610	2.623	0.500	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
MARATHON -- WI																		
MARTIN ROAD 55-37-091-QRY Created On: 03/06/25 Updated On:	Q	SE	SE	6	27N	9E	Marathon	0-225-166-2025		0.0	0.0	0.2	6.1	29.4	2.610	2.621	0.389	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MATTHIAE 55-37-047-PIT Created On: 03/13/23 Updated On:	P	SE	SE	35	29N	5E	Marathon	0-225-167-2023		0.3	0.0	1.8	3.3	15.5	2.764	2.786	0.796	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MEVERDEN MATERIALS 55-37-048-QRY Created On: 01/22/16 Updated On:	Q	NE	SW	19	28N	7E	Marathon	0-225-76-2016			0.0	0.5	8.1	36.7	2.594	2.622	1.074	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
MEVERDEN MATERIALS 55-37-048-QRY Created On: 05/09/19 Updated On:	Q	NE	SW	19	28N	7E	Marathon	0-225-185-2019		0.0	0.0	0.6	9.4	40.9	2.616	2.635	0.702	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
MEVERDEN MATERIALS 55-37-048-QRY Created On: 04/30/24 Updated On:	Q	NE	SW	19	28N	7E	Marathon	0-225-241-2024		0.0	0.0	0.4	9.2	38.6	2.617	2.634	0.663	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MICHELS-RIB 55-37-093-QRY Created On: 01/04/22 Updated On:	Q	SW	SE	9	30N	7E	Marathon	0-225-16-2022		0.0	0.0	0.8	7.7	32.4	2.579	2.597	0.687	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MICHELS-RIB 55-37-093-QRY Created On: 01/02/25 Updated On:	Q	SW	SE	9	30N	7E	Marathon	0-225-12-2025		0.0	0.1	0.7	5.9	27.1	2.597	2.610	0.519	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
MARATHON -- WI																		
MITCH KING 55-37-051-PIT Created On: 01/03/17 Updated On:	P	SW	NE	6	26N	9E	Marathon	0-225-3-2017		0.0	2.2	8.2	33.4	2.619	2.650	1.173		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
MITCH KING 55-37-051-PIT Created On: 02/17/22 Updated On:	P	SW	NE	6	26N	9E	Marathon	0-225-133-2022	1.3	0.0	2.5	9.0	34.2	2.628	2.655	1.035		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MORGAN 55-37-052-PIT Created On: 04/05/19 Updated On:	P	SE	SW	35	29N	5E	Marathon	0-225-123-2019	0.6	0.0	0.8	5.1	21.5	2.642	2.673	1.161		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
MORGAN 55-37-052-PIT Created On: 01/02/24 Updated On:	P	SE	SW	35	29N	5E	Marathon	0-225-57-2024	0.6	0.0	1.6	3.8	20.9	2.615	2.650	1.356		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MROCZINSKI 55-37-054-PIT Created On: 04/24/19 Updated On:	P	SW	NW	16	29N	5E	Marathon	0-225-169-2019	0.0	0.0	0.2	3.5	17.8	2.638	2.656	0.675		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
MROCZINSKI 55-37-054-PIT Created On: 01/02/24 Updated On:	P	SW	NW	16	29N	5E	Marathon	0-225-60-2024	0.0	0.0	6.9	6.3	25.7	2.637	2.673	1.372		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
PAUL BUGAR "N" 55-37-057-QRY Created On: 05/21/15 Updated On:	Q	N	NE	2	27N	2E	Marathon	0-225-176-2015		0.0	1.2	4.5	22.0	2.573	2.603	1.159		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
MARATHON -- WI																		
PAUL BUGAR "N" 55-37-057-QRY Created On: 04/25/18 Updated On:	Q	N	NE	2	27N	2E	Marathon	0-225-184-2018		0.0	0.2	5.0	23.3	2.617	2.631	0.534		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
PAUL BUGAR "N" 55-37-057-QRY Created On: 06/17/21 Updated On:	Q	N	NE	2	27N	2E	Marathon	0-225-228-2021	0.3	0.0	0.7	6.7	30.4	2.597	2.616	0.747		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
PAUL BUGAR "N" 55-37-057-QRY Created On: 02/28/24 Updated On:	Q	N	NE	2	27N	2E	Marathon	0-225-193-2024	0.1	0.0	0.6	5.3	24.7	2.607	2.621	0.550		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
PAUL BUGAR "R" 55-37-058-QRY Created On: 05/21/15 Updated On:	Q	NE	NW	1	27N	2E	Marathon	0-225-177-2015		0.0	0.9	4.7	23.1	2.626	2.654	1.037		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
PAUL BUGAR "R" 55-37-058-QRY Created On: 04/25/18 Updated On:	Q	NE	NW	1	27N	2E	Marathon	0-225-183-2018	0.1	0.0	0.6	5.2	25.9	2.593	2.610	0.655		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
PAUL BUGAR "R" 55-37-058-QRY Created On: 06/17/21 Updated On:	Q	NE	NW	1	27N	2E	Marathon	0-225-227-2021	0.0	0.0	0.3	5.5	26.8	2.607	2.618	0.450		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
PAUL BUGAR "R" 55-37-058-QRY Created On: 02/28/24 Updated On:	Q	NE	NW	1	27N	2E	Marathon	0-225-194-2024	0.0	0.0	0.3	7.3	32.2	2.601	2.618	0.644		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
MARATHON -- WI																		
RC HOGARTY 55-37-092-QRY Created On: 07/01/21 Updated On:	Q	SW	SE	32	30N	10E	Marathon	0-225-241-2021	0.1	0.0	1.0	6.7	34.0	2.656	2.673	0.648		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
RC HOGARTY 55-37-092-QRY Created On: 01/29/24 Updated On:	Q	SW	SE	32	30N	10E	Marathon	0-225-155-2024	0.0	0.0	0.6	11.8	38.5	2.676	2.685	0.360		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
*RED ROCK GRANITE 55-37-063-QRY Created On: 07/01/21 Updated On:	Q	N	NW	19	27N	6E	Marathon	0-225-238-2021	0.0	0.0	2.2	10.7	44.0	2.594	2.613	0.722		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
RESCH 55-37-066-PIT Created On: 01/05/17 Updated On:	P	NW	NW	1	29N	10E	Marathon	0-225-16-2017		0.0	2.8	8.3	32.8	2.651	2.672	0.760		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
RESCH 55-37-066-PIT Created On: 05/17/22 Updated On:	P	NW	NW	1	29N	10E	Marathon	0-225-202-2022	0.0	0.0	2.8	8.7	33.5	2.636	2.663	1.047		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
ROSE 55-37-071-QRY Created On: 01/05/17 Updated On:	Q	NE	NW	36	30N	8E	Marathon	0-225-39-2017		0.0	0.2	6.0	26.7	2.615	2.625	0.399		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
ROSE 55-37-071-QRY Created On: 01/03/20 Updated On:	Q	NE	NW	36	30N	8E	Marathon	0-225-14-2020	0.0	0.0	0.5	6.9	32.0	2.598	2.614	0.622		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
MARATHON -- WI																		
ROSE 55-37-071-QRY Created On: 01/03/23 Updated On:	Q	NE	NW	36	30N	8E	Marathon	0-225-19-2023	0.0	0.0	0.3	6.6	29.7	2.605	2.621	0.603		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
RUBY 55-37-072-QRY Created On: 01/05/17 Updated On:	Q	SE	NW	22	30N	7E	Marathon	0-225-38-2017		0.0	0.8	5.7	26.7	2.598	2.611	0.485		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
RUBY 55-37-072-QRY Created On: 01/03/20 Updated On:	Q	SE	NW	22	30N	7E	Marathon	0-225-13-2020		0.0	1.1	8.0	37.1	2.581	2.602	0.827		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
RUBY 55-37-072-QRY Created On: 01/03/23 Updated On:	Q	SE	NW	22	30N	7E	Marathon	0-225-18-2023	0.0	0.0	0.6	5.8	28.0	2.596	2.613	0.650		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
SIEKIERZYNSKI 55-37-094-PIT Created On: 06/13/22 Updated On:	P	SW	NE	29	27N	9E	Marathon	0-225-216-2022	0.5	0.0	1.0	7.9	32.2	2.614	2.645	1.188		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
SIEKIERZYNSKI 55-37-095-QRY Created On: 06/13/22 Updated On:	Q	SW	NE	29	27N	9E	Marathon	0-225-217-2022	0.1	0.0	0.9	7.6	34.2	2.643	2.659	0.630		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
SIEKIERZYNSKI 55-37-095-QRY Created On: 03/06/25 Updated On:	Q	SW	NE	29	27N	9E	Marathon	0-225-164-2025	0.0	0.0	0.2	4.7	23.1	2.692	2.699	0.275		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
MARATHON -- WI																		
*STROETZ 55-37-075-QRY Created On: 03/21/18 Updated On:	Q	SW	NW	10	26N	3E	Marathon	0-225-131-2018		0.0	2.9	6.2	28.0	2.593	2.616	0.874		
	Approved Use : HMA<MT, HMA>=MT, Base Aggregate																	
*STROETZ 55-37-075-QRY Created On: 06/28/22 Updated On:	Q	SW	NW	10	26N	3E	Marathon	0-225-241-2022		0.0	1.7	7.6	29.3	2.592	2.620	1.073		
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																	
SZEWS 55-37-077-PIT Created On: 09/15/16 Updated On:	P	SW	SW	4	28N	10E	Marathon	0-225-257-2016		0.0	0.4	8.2	32.3	2.669	2.689	0.741		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
SZEWS 55-37-077-PIT Created On: 01/04/21 Updated On:	P	SW	SW	4	28N	10E	Marathon	0-225-17-2021	0.0	0.4	0.4	6.9	30.9	2.669	2.691	0.807		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
THURS 55-37-090-QRY Created On: 04/05/19 Updated On:	Q	NE	SW	27	29N	5E	Marathon	0-225-124-2019		0.0	1.4	4.2	18.4	2.715	2.736	0.766		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
THURS 55-37-090-QRY Created On: 04/11/22 Updated On:	Q	NE	SW	27	29N	5E	Marathon	0-225-172-2022	0.0	0.0	0.6	3.2	14.1	2.769	2.780	0.397		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
THURS 55-37-090-QRY Created On: 01/02/25 Updated On:	Q	NE	SW	27	29N	5E	Marathon	0-225-74-2025		0.0	0.3	3.4	15.7	2.797	2.807	0.347		
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
MARATHON -- WI																		
WEISENBERGER 55-37-083-QRY Created On: 01/06/16 Updated On:	Q		N	1	28N	5E	Marathon	0-225-32-2016		0.0	0.9	4.5	19.3	2.689	2.720	1.154		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
WEISENBERGER 55-37-083-QRY Created On: 01/04/19 Updated On:	Q		N	1	28N	5E	Marathon	0-225-35-2019		0.0	0.4	4.8	19.6	2.673	2.712	1.471		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
WEISENBERGER 55-37-083-QRY Created On: 01/13/22 Updated On:	Q		N	1	28N	5E	Marathon	0-225-109-2022		0.0	0.3	0.2	4.5	17.7	2.829	2.846	0.615	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
WEISENBERGER 55-37-083-QRY Created On: 01/14/25 Updated On:	Q		N	1	28N	5E	Marathon	0-225-112-2025		1.2	2.6	0.2	3.3	16.4	2.726	2.751	0.941	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
WORDEN ENTERPRISES LLC 55-37-097-QRY Created On: 05/09/23 Updated On:	Q	NE	SW	20	27N	6E	Marathon	0-225-216-2023		0.3	0.0	1.8	8.8	37.4	2.554	2.582	1.083	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
WORDEN ENTERPRISES LLC 55-37-097-QRY Created On: 03/13/24 Updated On:	Q	NE	SW	20	27N	6E	Marathon	0-225-201-2024		0.0	0.0	1.1	7.3	28.7	2.571	2.596	0.979	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
ZIOLKOWSKI 55-37-087-PIT Created On: 01/02/18 Updated On:	P	SW	SE	29	27N	9'E	Marathon	0-225-3-2018		0.6	0.0	1.0	7.0	30.2	2.647	2.672	0.940	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
MARATHON -- WI																		
ZIOLKOWSKI 55-37-087-PIT Created On: 01/02/24 Updated On:	P	SW	SE	29	27N	9'E	Marathon	0-225-44-2024	0.7	1.4	4.8	7.5	32.2	2.645	2.670	0.970		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MARINETTE -- WI																		
*BEAVER 55-38-003-QRY Created On: 06/13/22 Updated On:	Q	NE	NE	26	31N	20E	Marinette	0-225-223-2022	5.6	10.7	5.8	10.6	37.9	2.627	2.679	1.973		
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																	
BEECHER 55-38-004-PIT Created On: 07/26/23 Updated On:	P	NW	NE	20	36N	21E	Marinette	0-225-239-2023		1.1	0.0	6.2	27.3	2.716	2.745	1.072		
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																	
BIEHL 55-38-007-QRY Created On: 01/08/16 Updated On:	Q		SE	4	31N	22E	Marinette	0-225-44-2016		7.6	4.9	7.9	34.4	2.675	2.711	1.343		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
BIEHL 55-38-007-QRY Created On: 05/24/19 Updated On:	Q		SE	4	31N	22E	Marinette	0-225-197-2019	0.0	12.3	2.3	9.0	35.0	2.684	2.720	1.314		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
BIEHL 55-38-007-QRY Created On: 05/17/22 Updated On:	Q		SE	4	31N	22E	Marinette	0-225-206-2022	0.0	8.4	2.3	9.5	37.4	2.654	2.704	1.876		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
BIEHL 55-38-007-QRY Created On: 01/02/25 Updated On:	Q		SE	4	31N	22E	Marinette	0-225-64-2025	0.0	10.2	3.0	7.9	34.4	2.677	2.712	1.309		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
MARINETTE -- WI																		
BIEHL 11TH ROAD 55-38-008-QRY Created On: 01/05/17 Updated On:	Q	NW	NW	19	30N	21E	Marinette	0-225-53-2017		1.0	0.9	5.9	25.9	2.726	2.762	1.322		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
BIEHL 11TH ROAD 55-38-008-QRY Created On: 07/15/20 Updated On:	Q	NW	NW	19	30N	21E	Marinette	0-225-213-2020	0.0	0.9	1.3	4.1	25.9	2.723	2.754	1.157		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
BIEHL 11TH ROAD 55-38-008-QRY Created On: 01/03/23 Updated On:	Q	NW	NW	19	30N	21E	Marinette	0-225-48-2023	0.1	2.3	1.3	7.7	30.3	2.717	2.750	1.219		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
BIEHL 9TH ROAD 55-38-007-PIT Created On: 01/04/18 Updated On:	P	S	NW	18	30N	21E	Marinette	0-225-85-2018	0.9	0.0	3.5	5.1	26.3	2.711	2.741	1.131		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
BIEHL 9TH ROAD 55-38-007-PIT Created On: 01/03/23 Updated On:	P	S	NW	18	30N	21E	Marinette	0-225-34-2023		4.7	1.9	5.9	25.7	2.686	2.720	1.250		
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																	
DE LAET 55-38-012-PIT Created On: 06/13/22 Updated On:	P	SE	SE	14	34N	20E	Marinette	0-225-222-2022	3.0	0.0	1.8	6.6	31.8	2.718	2.745	0.977		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
NOLL 55-38-022-PIT Created On: 03/02/15 Updated On:	P	NW	SW	8	30N	21E	Marinette	0-225-85-2015	0.5	0.0	3.4	5.0	29.2	2.716	2.746	1.104		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
MARINETTE -- WI																		
NOLL 55-38-022-PIT Created On: 01/02/20 Updated On:	P	NW	SW	8	30N	21E	Marinette	0-225-2-2020	0.5	0.0	5.7	5.5	27.2	2.713	2.745	1.177		
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
NOLL 55-38-022-PIT Created On: 01/14/25 Updated On:	P	NW	SW	8	30N	21E	Marinette	0-225-106-2025	1.8	0.0	2.1	5.9	29.6	2.684	2.719	1.330		
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
NORROK 55-38-023-QRY Created On: 05/10/18 Updated On:	Q	NE	SE	30	31N	22E	Marinette	0-225-199-2018	0.3	7.9	1.2	7.1	30.1	2.689	2.735	1.729		
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
NORROK 55-38-023-QRY Created On: 04/28/22 Updated On:	Q	NE	SE	30	31N	22E	Marinette	0-225-182-2022	0.0	13.4	11.7	6.6	30.1	2.681	2.720	1.459		
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
NORROK 55-38-023-QRY Created On: 05/14/25 Updated On:	Q	NE	SE	30	31N	22E	Marinette	0-225-207-2025	0.0	13.1	7.7	7.9	33.4	2.676	2.716	1.499		
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
PETERS - PESHTIGO QUARRY 55-38-026-QRY Created On: 01/05/17 Updated On:	Q	SE	NW	33	30N	22E	Marinette	0-225-52-2017	1.8	4.4	3.7	8.9	33.7	2.663	2.715	1.953		
Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																		
PETERS - PESHTIGO QUARRY 55-38-026-QRY Created On: 01/02/20 Updated On:	Q	SE	NW	33	30N	22E	Marinette	0-225-5-2020	0.1	3.7	4.0	5.3	24.7	2.737	2.766	1.056		
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
MARINETTE -- WI																		
PETERS - PESHTIGO QUARRY 55-38-026-QRY Created On: 01/12/23 Updated On:	Q	SE	NW	33	30N	22E	Marinette	0-225-119-2023	0.1	3.8	4.0	7.0	31.0	2.676	2.730	2.000		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
PETERS PORTERFIELD QRY 55-38-015-QRY Created On: 01/04/22 Updated On:	Q	SE	SE	19	31N	22E	Marinette	0-225-91-2022	0.0	7.3	6.6	6.9	32.0	2.696	2.731	1.314		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
PETERS PORTERFIELD QRY 55-38-015-QRY Created On: 01/14/25 Updated On:	Q	SE	SE	19	31N	22E	Marinette	0-225-104-2025	0.0	7.8	5.5	6.3	28.8	2.727	2.753	0.944		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
PETERS-CRIVITZ QUARRY 55-38-018-QRY Created On: 06/12/25 Updated On:	Q	SW	NW	30	32N	21E	Marinette	0-225-220-2025	0.8	8.0	8.4	8.4	35.7	2.624	2.682	2.237		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
RISNER 55-38-029-PIT Created On: 06/13/22 Updated On:	P	S	SW	16	30N	20E	Marinette	0-225-225-2022	1.2	0.0	0.6	6.0	26.4	2.711	2.741	1.083		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
RIVERVIEW 55-38-046-PIT Created On: 06/13/22 Updated On:	P	SW	SW	18	31N	21E	Marinette	0-225-224-2022	0.5	0.0	2.5	4.6	24.8	2.719	2.743	0.897		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
STAUDENMAIER 55-38-032-QRY Created On: 03/31/17 Updated On:	Q	NW	SW	7	29N	22E	Marinette	0-225-97-2017	0.0	1.9	3.7	5.8	26.2	2.717	2.752	1.294		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
MARINETTE -- WI																		
STAUDENMAIER 55-38-032-QRY Created On: 06/13/22 Updated On:	Q	NW	SW	7	29N	22E	Marinette	0-225-220-2022		0.0	2.6	1.0	7.2	28.8	2.706	2.741	1.263	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
STAUDENMAIER 55-38-032-QRY Created On: 01/02/25 Updated On:	Q	NW	SW	7	29N	22E	Marinette	0-225-61-2025		0.0	2.9	1.5	6.0	26.0	2.728	2.758	1.081	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
TOWER 55-38-036-PIT Created On: 01/12/16 Updated On:	P	W	NE	34	31N	20E	Marinette	0-225-53-2016			0.0	1.3	4.6	24.4	2.712	2.741	1.081	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
TOWER 55-38-036-PIT Created On: 01/06/21 Updated On:	P	W	NE	34	31N	20E	Marinette	0-225-109-2021		0.3	3.5	1.8	4.6	23.0	2.706	2.737	1.142	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
V.M.I. 55-38-039-PIT Created On: 08/14/17 Updated On:	P	NE	SW	17	31N	21E	Marinette	0-225-250-2017		0.8	6.4	3.9	5.5	25.8	2.730	2.763	1.216	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
V.M.I. 55-38-039-PIT Created On: 04/28/22 Updated On:	P	NE	SW	17	31N	21E	Marinette	0-225-181-2022		0.5	0.0	2.8	5.5	26.9	2.716	2.745	1.046	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
WAGNER 55-38-041-QRY Created On: 05/10/18 Updated On:	Q		NW	17	33N	22E	Marinette	0-225-202-2018		0.0	1.8	0.9	7.8	31.9	2.726	2.761	1.250	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
MARINETTE -- WI																	
WAGNER 55-38-041-QRY Created On: 04/28/22 Updated On:	Q		NW	17	33N	22E	Marinette	0-225-183-2022	0.3	1.0	1.8	6.3	28.1	2.711	2.750	1.442	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
WAGNER 55-38-041-QRY Created On: 05/14/25 Updated On:	Q		NW	17	33N	22E	Marinette	0-225-205-2025	0.0	1.9	2.0	6.6	31.1	2.705	2.742	1.385	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
MILWAUKEE -- WI																	
FRANKLIN 55-40-008-QRY Created On: 01/21/16 Updated On:	Q		NE	10	5N	21E	Milwaukee	0-225-70-2016	3.5	15.1	2.8	4.4	21.7	2.636	2.695	2.235	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
FRANKLIN 55-40-008-QRY Created On: 05/26/16 Updated On:	Q		NE	10	5N	21E	Milwaukee	0-225-188-2016	0.3	1.3	1.1	5.6	26.0	2.639	2.677	1.453	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
FRANKLIN 55-40-008-QRY Created On: 08/25/17 Updated On:	Q		NE	10	5N	21E	Milwaukee	0-225-266-2017		0.0	1.0	7.9	29.7	2.649	2.704	2.074	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
FRANKLIN 55-40-008-QRY Created On: 01/09/20 Updated On:	Q		NE	10	5N	21E	Milwaukee	0-225-95-2020	1.5	0.0	3.0	4.5	21.8	2.730	2.760	1.098	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
FRANKLIN 55-40-008-QRY Created On: 01/03/23 Updated On:	Q		NE	10	5N	21E	Milwaukee	0-225-82-2023	1.0	3.3	0.3	6.2	29.0	2.578	2.634	2.163	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
MONROE -- WI																		
BJORNSTAD 55-41-001-QRY Created On: 01/09/15 Updated On:	Q	NE	SW	35	15N	4W	Monroe	0-225-52-2015		0.0	6.3	12.9	41.3	2.562	2.632	2.743		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
BJORNSTAD 55-41-001-QRY Created On: 01/03/18 Updated On:	Q	NE	SW	35	15N	4W	Monroe	0-225-14-2018	1.2	0.0	1.9	10.4	38.2	2.615	2.671	2.140		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
BJORNSTAD 55-41-001-QRY Created On: 01/04/21 Updated On:	Q	NE	SW	35	15N	4W	Monroe	0-225-27-2021	1.2	0.0	0.9	9.3	34.7	2.620	2.671	1.962		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
BJORNSTAD 55-41-001-QRY Created On: 06/05/24 Updated On:	Q	NE	SW	35	15N	4W	Monroe	0-225-264-2024	1.2	2.1	1.3	9.1	38.2	2.602	2.664	2.376		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
BRUEGGEMAN 55-41-003-QRY Created On: 04/06/17 Updated On:	Q	NE	NW	29	15N	2W	Monroe	0-225-115-2017	0.3	0.0	1.5	9.8	37.6	2.618	2.673	2.081		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
BRUEGGEMAN 55-41-003-QRY Created On: 04/02/20 Updated On:	Q	NE	NW	29	15N	2W	Monroe	0-225-139-2020	0.0	0.0	2.6	10.7	38.1	2.610	2.671	2.342		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
BRUEGGEMAN 55-41-003-QRY Created On: 01/04/24 Updated On:	Q	NE	NW	29	15N	2W	Monroe	0-225-134-2024	1.0	2.7	3.6	8.8	35.6	2.631	2.682	1.936		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
MONROE -- WI																		
DONSKEY 55-41-004-QRY Created On: 04/08/15 Updated On:	Q	NW	SE	11	16N	3W	Monroe	0-225-112-2015		0.0	2.4	9.2	37.6	2.625	2.677	1.979		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
DONSKEY 55-41-004-QRY Created On: 05/04/17 Updated On:	Q	NW	SE	11	16N	3W	Monroe	0-225-169-2017	1.6	0.0	3.3	10.0	38.4	2.622	2.674	1.956		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
DONSKEY 55-41-004-QRY Created On: 03/23/18 Updated On:	Q	NW	SE	11	16N	3W	Monroe	0-225-146-2018	0.5	0.0	7.9	11.2	41.2	2.589	2.653	2.482		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
DONSKEY 55-41-004-QRY Created On: 01/03/20 Updated On:	Q	NW	SE	11	16N	3W	Monroe	0-225-18-2020	1.2	0.0	3.7	9.7	38.3	2.608	2.670	2.375		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
DONSKEY 55-41-004-QRY Created On: 01/03/23 Updated On:	Q	NW	SE	11	16N	3W	Monroe	0-225-65-2023	2.3	1.8	6.3	11.9	44.4	2.567	2.635	2.661		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
ENDRES 55-41-006-QRY Created On: 07/26/16 Updated On:	Q	NE	SW	22	18N	4W	Monroe	0-225-229-2016	3.2	0.0	5.0	17.2	56.1	2.548	2.623	2.945		
ENDRES 55-41-006-QRY Created On: 08/03/16 Updated On:	Q	NE	SW	22	18N	4W	Monroe	0-225-235-2016	0.4	0.0	4.0	11.4	41.7	2.637	2.687	1.913		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
MONROE -- WI																		
ENDRES 55-41-006-QRY Created On: 05/13/20 Updated On:	Q	NE	SW	22	18N	4W	Monroe	0-225-178-2020	0.8	0.0	4.6	10.7	39.7	2.629	2.684	2.110		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
ENDRES 55-41-006-QRY Created On: 01/03/23 Updated On:	Q	NE	SW	22	18N	4W	Monroe	0-225-70-2023	0.5	3.9	1.6	11.3	42.2	2.589	2.658	2.665		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
*GERKE 55-41-009-QRY Created On: 04/25/17 Updated On:	Q	NE	SE	36	17N	1W	Monroe	0-225-157-2017	0.2	0.0	11.8	13.1	48.9	2.523	2.606	3.298		
	Approved Use : HMA<E-3, CONCRETE, Base Aggregate																	
*GERKE 55-41-009-QRY Created On: 01/24/22 Updated On:	Q	NE	SE	36	17N	1W	Monroe	0-225-116-2022	0.0	0.0	4.8	12.8	45.8	2.541	2.619	3.035		
	Approved Use : HMA<MT, CONCRETE, OGBC, Base Aggregate																	
KING 55-41-011-QRY Created On: 04/07/16 Updated On:	Q	SE	SE	1	16N	1W	Monroe	0-225-130-2016		0.0	3.0	8.1	34.4	2.637	2.690	1.999		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
KING 55-41-011-QRY Created On: 05/04/17 Updated On:	Q	SE	SE	1	16N	1W	Monroe	0-225-172-2017		0.0	11.7	8.3	36.6	2.621	2.680	2.244		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
KING 55-41-011-QRY Created On: 04/02/20 Updated On:	Q	SE	SE	1	16N	1W	Monroe	0-225-140-2020	0.0	0.0	4.4	8.6	34.7	2.616	2.675	2.257		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
MONROE -- WI																		
KING 55-41-011-QRY Created On: 05/22/23 Updated On:	Q	SE	SE	1	16N	1W	Monroe	0-225-221-2023	0.8	10.5	6.1	10.3	39.6	2.593	2.661	2.622		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MENN 55-41-013-QRY Created On: 03/07/16 Updated On:	Q	SW	NW	2	15N	2W	Monroe	0-225-92-2016	0.4	0.0	3.4	19.1	45.9	2.532	2.614	3.242		
	Approved Use : CONCRETE, Base Aggregate																	
MENN 55-41-013-QRY Created On: 04/19/18 Updated On:	Q	SW	NW	2	15N	2W	Monroe	0-225-176-2018	0.3	0.0	1.7	10.1	37.5	2.598	2.659	2.360		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
MENN 55-41-013-QRY Created On: 03/12/20 Updated On:	Q	SW	NW	2	15N	2W	Monroe	0-225-127-2020	0.0	0.0	3.7	11.8	40.5	2.551	2.626	2.945		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MENN 55-41-013-QRY Created On: 04/10/23 Updated On:	Q	SW	NW	2	15N	2W	Monroe	0-225-192-2023	1.3	3.6	5.5	10.8	40.1	2.608	2.663	2.102		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
REVELS QUARRY 55-41-018-QRY Created On: 04/25/17 Updated On:	Q	NW	SE	1	16N	3W	Monroe	0-225-155-2017	0.6	0.0	7.0	12.0	42.7	2.547	2.624	3.030		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
REVELS QUARRY 55-41-018-QRY Created On: 02/13/20 Updated On:	Q	NW	SE	1	16N	3W	Monroe	0-225-115-2020	0.0	0.0	3.2	12.9	44.7	2.558	2.631	2.866		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
MONROE -- WI																		
REVELS QUARRY 55-41-018-QRY Created On: 04/10/23 Updated On:	Q	NW	SE	1	16N	3W	Monroe	0-225-193-2023	2.9	3.5	8.3	11.2	41.9	2.580	2.645	2.540		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
SCHMITZ 55-41-020-QRY Created On: 08/03/18 Updated On:	Q		SW	18	15N	2W	Monroe	0-225-262-2018	0.7	0.0	5.4	12.4	41.2	2.594	2.657	2.406		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
SCHMITZ 55-41-020-QRY Created On: 01/05/21 Updated On:	Q		SW	18	15N	2W	Monroe	0-225-65-2021	0.7	0.0	0.3	7.3	30.7	2.634	2.685	1.921		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
SCHMITZ 55-41-020-QRY Created On: 01/02/24 Updated On:	Q		SW	18	15N	2W	Monroe	0-225-26-2024	0.9	2.2	4.2	10.5	39.3	2.599	2.663	2.464		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
WIEDL 55-41-024-QRY Created On: 06/10/16 Updated On:	Q	NW	NW	29	16N	2W	Monroe	0-225-195-2016	2.0	0.0	4.6	11.3	39.7	2.547	2.618	2.814		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
WIEDL 55-41-024-QRY Created On: 05/03/18 Updated On:	Q	NW	NW	29	16N	2W	Monroe	0-225-190-2018	0.7	0.0	3.2	8.4	35.2	2.591	2.650	2.294		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
WIEDL 55-41-024-QRY Created On: 08/12/21 Updated On:	Q	NW	NW	29	16N	2W	Monroe	0-225-261-2021	3.4	0.0	8.4	11.4	41.1	2.566	2.633	2.614		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
MONROE -- WI																		
WIEDL 55-41-024-QRY Created On: 01/02/24 Updated On:	Q	NW	NW	29	16N	2W	Monroe	0-225-23-2024	2.0	2.6	5.0	11.8	40.5	2.576	2.642	2.565		
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
WILTON 55-41-027-QRY Created On: 07/25/19 Updated On:	Q		SW	35	16N	1W	Monroe	0-225-250-2019		0.0	4.4	14.1	46.6	2.573	2.637	2.467		
Approved Use : Base Aggregate																		
WILTON 55-41-027-QRY Created On: 01/04/22 Updated On:	Q		SW	35	16N	1W	Monroe	0-225-73-2022		1.2	5.3	13.9	45.7	2.556	2.627	2.796		
Approved Use : OGBC, Base Aggregate																		
WILTON 55-41-027-QRY Created On: 01/02/25 Updated On:	Q		SW	35	16N	1W	Monroe	0-225-28-2025	1.7	0.0	6.4	10.6	40.9	2.547	2.622	2.955		
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
OCONTO -- WI																		
CAELWAERTS 55-42-002-QRY Created On: 08/16/16 Updated On:	Q	NE	SE	31	29N	22E	Oconto	0-225-241-2016		7.7	2.6	4.6	25.7	2.721	2.753	1.160		
Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																		
CAELWAERTS 55-42-002-QRY Created On: 04/24/19 Updated On:	Q	NE	SE	31	29N	22E	Oconto	0-225-165-2019		7.7	1.3	5.5	25.2	2.707	2.741	1.245		
Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																		
CAELWAERTS 55-42-002-QRY Created On: 01/04/22 Updated On:	Q	NE	SE	31	29N	22E	Oconto	0-225-92-2022	0.0	4.5	4.7	6.2	28.2	2.709	2.739	1.115		
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
OCONTO -- WI																		
CAELWAERTS 55-42-002-QRY Created On: 01/14/25 Updated On:	Q	NE	SE	31	29N	22E	Oconto	0-225-107-2025	0.0	4.7	3.7	7.2	30.5	2.698	2.734	1.342		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
CHASE (NEA) 55-42-003-QRY Created On: 01/12/16 Updated On:	Q	NW	NE	17	26N	19E	Oconto	0-225-48-2016		0.2	1.2	3.9	20.7	2.759	2.782	0.821		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
CHASE (NEA) 55-42-003-QRY Created On: 05/12/21 Updated On:	Q	NW	NE	17	26N	19E	Oconto	0-225-205-2021	0.0	0.9	0.2	4.7	20.7	2.776	2.795	0.714		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
CHASE (NEA) 55-42-003-QRY Created On: 01/02/24 Updated On:	Q	NW	NE	17	26N	19E	Oconto	0-225-10-2024	0.6	3.6	0.2	6.2	25.9	2.765	2.788	0.815		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
*D and J CHASE 55-42-006-QRY Created On: 04/01/16 Updated On:	Q	E	NE	17	26N	19E	Oconto	0-225-118-2016	0.4	8.3	1.3	6.2	26.8	2.718	2.753	1.279		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
*D and J CHASE 55-42-006-QRY Created On: 04/24/19 Updated On:	Q	E	NE	17	26N	19E	Oconto	0-225-163-2019	0.0	0.8	1.2	5.1	22.9	2.858	2.879	0.705		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
*D and J CHASE 55-42-006-QRY Created On: 01/04/22 Updated On:	Q	E	NE	17	26N	19E	Oconto	0-225-70-2022	1.1	3.7	3.0	5.2	24.6	2.749	2.770	0.762		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
OCONTO -- WI																		
DUAME #1 55-42-001-QRY Created On: 04/27/17 Updated On:	Q	SE	SE	31	29N	21E	Oconto	0-225-160-2017	0.7	5.9	8.7	10.1	36.8	2.683	2.722	1.456		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
DUAME #1 55-42-001-QRY Created On: 02/24/21 Updated On:	Q	SE	SE	31	29N	21E	Oconto	0-225-130-2021	0.1	1.8	4.3	8.8	36.6	2.705	2.746	1.532		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
DUAME #1 55-42-001-QRY Created On: 06/25/24 Updated On:	Q	SE	SE	31	29N	21E	Oconto	0-225-277-2024	0.0	9.2	2.9	6.5	29.9	2.713	2.742	1.050		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
GOHR 55-42-011-QRY Created On: 05/30/17 Updated On:	Q	SW	NE	4	26N	19E	Oconto	0-225-196-2017		1.2	1.2	5.7	26.2	2.772	2.793	0.751		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
GOHR 55-42-011-QRY Created On: 01/02/20 Updated On:	Q	SW	NE	4	26N	19E	Oconto	0-225-3-2020	0.0	2.9	2.4	5.7	25.5	2.748	2.771	0.823		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
GOHR 55-42-011-QRY Created On: 01/12/23 Updated On:	Q	SW	NE	4	26N	19E	Oconto	0-225-121-2023	0.0	2.1	1.9	6.8	23.7	2.755	2.780	0.884		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
HODGE PIT 55-42-046-PIT Created On: 01/02/24 Updated On:	P	SE	SE	8	29N	20E	Oconto	0-225-96-2024	0.1	0.0	4.0	5.8	27.9	2.709	2.741	1.198		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
OCONTO -- WI																		
KRUEGER 55-42-017-QRY Created On: 01/07/16 Updated On:	Q	SE	SE	6	27N	21E	Oconto	0-225-35-2016	0.0	1.2	2.5	6.3	29.1	2.693	2.728	1.313		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
KRUEGER 55-42-017-QRY Created On: 01/25/19 Updated On:	Q	SE	SE	6	27N	21E	Oconto	0-225-91-2019	0.3	13.2	4.0	6.4	29.0	2.668	2.708	1.509		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
KRUEGER 55-42-017-QRY Created On: 01/04/22 Updated On:	Q	SE	SE	6	27N	21E	Oconto	0-225-93-2022	0.1	2.4	3.4	5.7	27.8	2.710	2.740	1.084		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
KRUEGER 55-42-017-QRY Created On: 01/14/25 Updated On:	Q	SE	SE	6	27N	21E	Oconto	0-225-105-2025	0.6	9.4	6.3	6.2	29.0	2.657	2.698	1.530		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
LAUERSDORF 55-42-019-QRY Created On: 03/17/16 Updated On:	Q	NE	SW	35	29N	18E	Oconto	0-225-99-2016	0.9	1.4	0.7	8.5	35.6	2.700	2.738	1.396		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
LAUERSDORF 55-42-019-QRY Created On: 01/08/20 Updated On:	Q	NE	SW	35	29N	18E	Oconto	0-225-71-2020	0.1	0.9	3.0	8.7	35.9	2.728	2.756	1.027		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
LAUERSDORF 55-42-019-QRY Created On: 01/12/23 Updated On:	Q	NE	SW	35	29N	18E	Oconto	0-225-120-2023	0.0	4.8	4.8	10.1	41.3	2.648	2.700	1.964		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
OCONTO -- WI																		
MCKEEFRY - CHASE 55-42-023-PIT Created On: 08/16/16 Updated On:	P	NW	SE	3	26N	19E	Oconto	0-225-242-2016	0.8	1.3	0.4	6.5	29.0	2.743	2.769	0.970		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
MCKEEFRY - CHASE 55-42-023-PIT Created On: 04/13/21 Updated On:	P	NW	SE	3	26N	19E	Oconto	0-225-179-2021	0.4	3.3	5.2	8.5	36.8	2.710	2.745	1.303		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
*MICHELS CHASE 55-42-024-QRY Created On: 01/07/15 Updated On:	Q	NE	SW	17	26N	19E	Oconto	0-225-21-2015		2.0	2.4	4.8	22.1	2.733	2.759	0.924		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
*MICHELS CHASE 55-42-024-QRY Created On: 01/04/19 Updated On:	Q	NE	SW	17	26N	19E	Oconto	0-225-40-2019		5.7	3.2	5.9	25.8	2.738	2.764	0.975		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
*MICHELS CHASE 55-42-024-QRY Created On: 04/11/22 Updated On:	Q	NE	SW	17	26N	19E	Oconto	0-225-174-2022	0.1	3.4	3.4	5.8	24.7	2.730	2.760	1.129		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MOUNTAIN STONeworks INC. 55-42-027-PIT Created On: 07/11/18 Updated On:	P		NW	3	31N	16E	Oconto	0-225-250-2018	0.5	0.0	1.4	5.2	23.8	2.706	2.727	0.754		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MOUNTAIN STONeworks INC. 55-42-027-PIT Created On: 05/01/24 Updated On:	P		NW	3	31N	16E	Oconto	0-225-244-2024	0.1	0.0	2.3	4.9	22.5	2.687	2.706	0.712		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
OCONTO -- WI																		
PETERS CHASE #5 55-42-030-QRY Created On: 01/30/15 Updated On:	Q		NW	17	26N	19E	Oconto	0-225-81-2015	0.7	4.2	3.9	5.6	24.9	2.731	2.759	0.995		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
PETERS CHASE #5 55-42-030-QRY Created On: 01/07/16 Updated On:	Q		NW	17	26N	19E	Oconto	0-225-39-2016		1.8	2.6	5.3	24.4	2.720	2.748	1.033		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
PETERS CHASE #5 55-42-030-QRY Created On: 01/25/19 Updated On:	Q		NW	17	26N	19E	Oconto	0-225-90-2019	0.1	6.5	1.7	5.2	23.6	2.756	2.780	0.879		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
PETERS CHASE #5 55-42-030-QRY Created On: 01/04/22 Updated On:	Q		NW	17	26N	19E	Oconto	0-225-90-2022	0.0	2.7	1.9	5.0	23.5	2.736	2.760	0.876		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
PETERS CHASE #5 55-42-030-QRY Created On: 03/06/25 Updated On:	Q		NW	17	26N	19E	Oconto	0-225-162-2025	0.0	2.9	1.3	4.9	22.0	2.746	2.771	0.899		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
PETERSON "CC" 55-42-032-PIT Created On: 03/30/15 Updated On:	P	S	NW	32	28N	19E	Oconto	0-225-102-2015	0.2	0.0	3.3	6.8	30.5	2.734	2.765	1.134		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
PETERSON "CC" 55-42-032-PIT Created On: 01/08/20 Updated On:	P	S	NW	32	28N	19E	Oconto	0-225-75-2020	0.2	0.0	2.8	6.1	29.9	2.732	2.759	0.996		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
OCONTO -- WI																		
PETERSON "CC" 55-42-032-PIT Created On: 05/14/25 Updated On:	P	S	NW	32	28N	19E	Oconto	0-225-206-2025	0.4	0.0	1.7	6.3	29.0	2.711	2.746	1.302		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
ROUER 55-42-033-QRY Created On: 01/04/22 Updated On:	Q	NW	NE	28	29N	21E	Oconto	0-225-89-2022	0.1	6.3	5.2	6.7	31.5	2.682	2.719	1.359		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
ROUER 55-42-033-QRY Created On: 01/14/25 Updated On:	Q	NW	NE	28	29N	21E	Oconto	0-225-108-2025	1.2	8.8	6.9	7.4	31.8	2.671	2.710	1.466		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
SPRAGUE 55-42-037-PIT Created On: 01/06/16 Updated On:	P	SE	NE	16	30N	19E	Oconto	0-225-33-2016	1.2	0.0	7.4	8.1	31.2	2.687	2.722	1.305		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
SPRAGUE 55-42-037-PIT Created On: 02/10/21 Updated On:	P	SE	NE	16	30N	19E	Oconto	0-225-126-2021	2.5	0.0	5.9	6.8	29.5	2.683	2.722	1.449		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
*THOMSON LIMESTONE 55-42-038-QRY Created On: 01/04/22 Updated On:	Q	SE	SE	20	30N	19E	Oconto	0-225-14-2022	1.4	6.9	6.5	6.0	33.8	2.696	2.736	1.489		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
TOWNSEND 55-42-039-PIT Created On: 01/05/21 Updated On:	P	SE	SW	15	33N	15E	Oconto	0-225-104-2021	0.0	0.2	0.4	3.9	18.8	2.682	2.697	0.581		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
ONEIDA -- WI																		
A-FRAME 55-43-001-PIT Created On: 05/12/16 Updated On:	P	NE	NE	22	37N	6E	Oneida	0-225-169-2016		0.0	0.3	4.6	20.3	2.681	2.712	1.169		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
A-FRAME 55-43-001-PIT Created On: 01/08/20 Updated On:	P	NE	NE	22	37N	6E	Oneida	0-225-49-2020	1.5	0.0	1.9	4.0	18.6	2.724	2.737	0.483		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
A-FRAME 55-43-001-PIT Created On: 01/02/25 Updated On:	P	NE	NE	22	37N	6E	Oneida	0-225-67-2025	1.7	0.0	2.1	4.7	20.7	2.674	2.698	0.878		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
BLUE LAKE 55-43-002-PIT Created On: 05/10/18 Updated On:	P	SW	SE	27	39N	6E	Oneida	0-225-205-2018	0.8	0.0	1.4	4.2	18.7	2.701	2.723	0.811		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
BLUE LAKE 55-43-002-PIT Created On: 01/03/23 Updated On:	P	SW	SE	27	39N	6E	Oneida	0-225-29-2023	2.4	0.0	2.5	4.9	20.8	2.670	2.698	1.026		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
FLANNERY MATERIALS LAKE TOMAHAWK 55-43-010-PIT Created On: 04/18/19 Updated On:	P	SW	NW	36	39N	7E	Oneida	0-225-139-2019	0.3	0.0	0.1	5.5	26.2	2.655	2.673	0.680		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
FLANNERY MATERIALS LAKE TOMAHAWK 55-43-010-PIT Created On: 07/31/24 Updated On:	P	SW	NW	36	39N	7E	Oneida	0-225-290-2024	0.7	0.0	1.4	6.2	27.2	2.636	2.666	1.148		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
ONEIDA -- WI																		
HAZELHURST 55-43-005-PIT Created On: 06/01/18 Updated On:	P	NE	SE	15	37N	6E	Oneida	0-225-218-2018		0.0	0.5	4.3	20.6	2.689	2.713	0.896		
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																	
HAZELHURST 55-43-005-PIT Created On: 01/03/23 Updated On:	P	NE	SE	15	37N	6E	Oneida	0-225-17-2023		0.0	0.3	3.1	16.4	2.713	2.734	0.773		
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																	
*INDIAN LAKE 55-43-006-PIT Created On: 07/16/20 Updated On:	P	E	NE	6	38N	10E	Oneida	0-225-222-2020		0.1	0.0	1.2	4.5	20.1	2.688	2.711	0.856	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
K-PIT ONEIDA 55-43-011-PIT Created On: 06/13/18 Updated On:	P	NW	NW	6	36N	8E	Oneida	0-225-228-2018		1.8	0.0	1.8	7.3	28.2	2.690	2.715	0.914	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
K-PIT ONEIDA 55-43-011-PIT Created On: 01/19/23 Updated On:	P	NW	NW	6	36N	8E	Oneida	0-225-129-2023		1.0	0.0	3.5	5.7	24.7	2.664	2.698	1.299	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
*KELLY 55-43-007-PIT Created On: 04/19/19 Updated On:	P	NE	SE	32	38N	11E	Oneida	0-225-151-2019		1.1	0.0	0.4	5.3	22.9	2.689	2.714	0.954	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
*KELLY 55-43-007-PIT Created On: 07/30/20 Updated On:	P	NE	SE	32	38N	11E	Oneida	0-225-227-2020		0.0	0.0	0.2	4.1	22.0	2.751	2.767	0.581	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
ONEIDA -- WI																		
KELLY QUARRY 55-43-034-QRY Created On: 01/03/23 Updated On:	Q	NE	SE	32	38N	11E	Oneida	0-225-25-2023	0.0	0.0	0.5	7.6	30.4	2.751	2.767	0.581		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
KING 55-43-008-QRY Created On: 04/05/16 Updated On:	Q	NW	NW	19	38N	10E	Oneida	0-225-121-2016		0.0	0.3	9.5	40.2	2.608	2.623	0.586		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
KING 55-43-008-QRY Created On: 01/07/19 Updated On:	Q	NW	NW	19	38N	10E	Oneida	0-225-69-2019		0.0	0.2	6.3	29.5	2.616	2.628	0.479		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
KING 55-43-008-QRY Created On: 07/16/20 Updated On:	Q	NW	NW	19	38N	10E	Oneida	0-225-219-2020	0.0	0.0	0.2	7.6	36.4	2.608	2.622	0.563		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
KING 55-43-008-QRY Created On: 01/03/23 Updated On:	Q	NW	NW	19	38N	10E	Oneida	0-225-20-2023	0.7	0.0	0.7	5.8	28.8	2.622	2.639	0.652		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
*KLAVER 55-43-009-PIT Created On: 06/25/20 Updated On:	P	NW	SE	4	36N	8E	Oneida	0-225-209-2020	0.1	0.0	0.6	5.1	23.4	2.737	2.759	0.791		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
KUCZMARSKI 55-43-037-PIT Created On: 01/02/24 Updated On:	P	W	SE	26	37N	10E	Oneida	0-225-64-2024	0.2	0.0	1.1	4.3	20.6	2.716	2.736	0.722		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
ONEIDA -- WI																		
LASSIG PIT 55-43-036-PIT Created On: 09/05/23 Updated On:	P	NW	NE	29	36N	9E	Oneida	0-225-249-2023	0.1	0.0	3.5	6.8	27.4	2.726	2.748	0.838		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
LUND / RIOPEL 55-43-013-PIT Created On: 01/04/18 Updated On:	P	SW	SW	6	36N	8E	Oneida	0-225-59-2018		0.0	1.5	4.2	20.2	2.674	2.702	1.027		
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																	
LUND / RIOPEL 55-43-013-PIT Created On: 01/03/23 Updated On:	P	SW	SW	6	36N	8E	Oneida	0-225-15-2023		0.0	0.6	3.3	17.6	2.696	2.721	0.933		
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																	
MILITARY 55-43-015-PIT Created On: 01/05/21 Updated On:	P	NE	SE	2	39N	11E	Oneida	0-225-53-2021	0.9	0.0	0.6	3.0	15.7	2.702	2.725	0.847		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MONICO 55-43-016-PIT Created On: 07/16/20 Updated On:	P	NW	SE	26	36N	11E	Oneida	0-225-220-2020	0.0	1.3	0.4	3.2	13.4	2.699	2.715	0.615		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MONICO 55-43-016-PIT Created On: 01/02/25 Updated On:	P	NW	SE	26	36N	11E	Oneida	0-225-70-2025	0.2	1.8	0.6	3.0	14.1	2.729	2.748	0.688		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
RIVER BEND 55-43-020-PIT Created On: 06/13/18 Updated On:	P			22	36N	9E	Oneida	0-225-229-2018	0.0	0.0	1.1	5.1	22.6	2.730	2.749	0.698		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
ONEIDA -- WI																		
RIVER BEND 55-43-020-PIT Created On: 01/19/23 Updated On:	P			22	36N	9E	Oneida	0-225-125-2023	0.0	0.0	1.7	4.6	21.4	2.705	2.726	0.774		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
ROCKY RUN 55-43-024-PIT Created On: 04/11/18 Updated On:	P	SW	14		37N	6E	Oneida	0-225-168-2018	0.5	0.0	0.3	4.3	19.2	2.705	2.727	0.801		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
ROCKY RUN 55-43-024-PIT Created On: 01/03/23 Updated On:	P	SW	14		37N	6E	Oneida	0-225-28-2023	0.5	0.0	1.4	3.9	18.3	2.715	2.740	0.915		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
STAG LAKE 55-43-033-PIT Created On: 06/13/18 Updated On:	P	NW	NW	34	36N	7E	Oneida	0-225-226-2018	0.2	0.0	1.9	5.5	24.1	2.682	2.703	0.790		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
STAG LAKE 55-43-033-PIT Created On: 01/19/23 Updated On:	P	NW	NW	34	36N	7E	Oneida	0-225-127-2023	0.4	0.0	2.7	5.3	23.5	2.665	2.695	1.134		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
TAYLOR #1 55-43-028-PIT Created On: 06/13/18 Updated On:	P	NW	NW	16	36N	9E	Oneida	0-225-227-2018	0.2	0.0	0.9	5.1	23.4	2.637	2.655	0.647		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
TAYLOR #1 55-43-028-PIT Created On: 04/24/23 Updated On:	P	NW	NW	16	36N	9E	Oneida	0-225-206-2023	0.0	0.0	0.8	5.7	25.0	2.742	2.763	0.751		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
OUTAGAMIE -- WI																		
CAREW - FREEDOM 55-44-006-QRY Created On: 01/16/15 Updated On:	Q	SW	NE	10	22N	18E	Outagamie	0-225-68-2015		0.8	0.8	1.0	4.6	20.6	2.791	2.808	0.616	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
CAREW - FREEDOM 55-44-006-QRY Created On: 03/06/17 Updated On:	Q	SW	NE	10	22N	18E	Outagamie	0-225-75-2017			2.8	1.5	4.6	21.2	2.774	2.796	0.794	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
CAREW - FREEDOM 55-44-006-QRY Created On: 01/30/20 Updated On:	Q	SW	NE	10	22N	18E	Outagamie	0-225-100-2020		0.0	2.4	1.2	4.0	18.3	2.796	2.812	0.572	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
CAREW - FREEDOM 55-44-006-QRY Created On: 01/04/23 Updated On:	Q	SW	NE	10	22N	18E	Outagamie	0-225-103-2023		0.0	1.2	1.2	4.4	19.9	2.788	2.804	0.572	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
CAREW - FREEDOM 55-44-006-QRY Created On: 02/28/24 Updated On:	Q	SW	NE	10	22N	18E	Outagamie	0-225-178-2024		0.0	1.2	1.3	4.8	21.3	2.771	2.791	0.732	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
*CAREW - ROCK RD 55-44-007-QRY Created On: 01/25/16 Updated On:	Q	NE	NW	20	22N	17E	Outagamie	0-225-82-2016			0.7	3.7	5.6	27.6	2.701	2.738	1.363	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
*CAREW - ROCK RD 55-44-007-QRY Created On: 01/10/19 Updated On:	Q	NE	NW	20	22N	17E	Outagamie	0-225-84-2019		0.1	4.1	3.0	6.1	27.9	2.746	2.775	1.045	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
OUTAGAMIE -- WI																		
*CAREW - ROCK RD 55-44-007-QRY Created On: 03/17/22 Updated On:	Q	NE	NW	20	22N	17E	Outagamie	0-225-152-2022	0.2	2.7	3.6	5.9	27.4	2.725	2.756	1.124		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
DREPHALS 55-44-011-QRY Created On: 05/11/17 Updated On:	Q		E	17	24N	17E	Outagamie	0-225-181-2017		3.9	2.5	7.1	30.0	2.717	2.753	1.342		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
DREPHALS 55-44-011-QRY Created On: 03/17/22 Updated On:	Q		E	17	24N	17E	Outagamie	0-225-144-2022	0.5	1.0	1.2	10.2	36.8	2.727	2.762	1.293		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
DREPHALS 55-44-011-QRY Created On: 01/30/25 Updated On:	Q		E	17	24N	17E	Outagamie	0-225-143-2025	0.0	1.1	5.7	11.8	40.8	2.683	2.732	1.802		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
FREEDOM - N.E.A. 55-44-012-QRY Created On: 01/04/22 Updated On:	Q	NE	NW	10	22N	18E	Outagamie	0-225-13-2022	0.0	2.5	0.3	4.6	21.2	2.757	2.783	0.941		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
FREEDOM - N.E.A. 55-44-012-QRY Created On: 01/02/25 Updated On:	Q	NE	NW	10	22N	18E	Outagamie	0-225-58-2025	0.0	4.0	1.1	4.7	21.4	2.775	2.799	0.869		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
KAUKAUNA 55-44-017-QRY Created On: 05/26/16 Updated On:	Q			18	21N	19E	Outagamie	0-225-190-2016	0.2	23.1	17.0	5.3	24.3	2.732	2.766	1.242		

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
OUTAGAMIE -- WI																		
KAUKAUNA 55-44-017-QRY Created On: 02/03/17 Updated On:	Q			18	21N	19E	Outagamie	0-225-62-2017		23.5	16.7	4.8	21.2	2.766	2.789	0.824		
KAUKAUNA 55-44-017-QRY Created On: 01/15/25 Updated On:	Q			18	21N	19E	Outagamie	0-225-128-2025	0.3	25.2	14.6	5.6	24.6	2.719	2.753	1.272		
KAUKAUNA 55-44-017-QRY Created On: 04/21/25 Updated On:	Q			18	21N	19E	Outagamie	0-225-196-2025		11.2	8.0	4.9	20.8	2.756	2.783	0.987		
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																	
KAUKAUNA 55-44-017-QRY Created On: 05/14/25 Updated On:	Q			18	21N	19E	Outagamie	0-225-213-2025		12.8	3.7	5.2	22.6	2.742	2.777	1.301		
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																	
MACKVILLE 55-44-019-QRY Created On: 03/30/15 Updated On:	Q	SW	NE	33	22N	17E	Outagamie	0-225-105-2015	0.1	0.5	2.4	4.3	18.8	2.767	2.789	0.789		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
MACKVILLE 55-44-019-QRY Created On: 02/16/16 Updated On:	Q	SW	NE	33	22N	17E	Outagamie	0-225-84-2016	0.4	2.7	0.8	4.7	21.5	2.751	2.777	0.940		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
MACKVILLE 55-44-019-QRY Created On: 02/03/17 Updated On:	Q	SW	NE	33	22N	17E	Outagamie	0-225-58-2017	0.2	3.7	1.5	6.1	24.5	2.724	2.759	1.284		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
OUTAGAMIE -- WI																		
MACKVILLE 55-44-019-QRY Created On: 03/16/18 Updated On:	Q	SW	NE	33	22N	17E	Outagamie	0-225-123-2018	0.5	3.0	1.0	4.2	19.6	2.765	2.788	0.856		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
MACKVILLE 55-44-019-QRY Created On: 04/24/19 Updated On:	Q	SW	NE	33	22N	17E	Outagamie	0-225-168-2019	0.6	2.5	0.4	5.2	21.5	2.771	2.795	0.870		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MACKVILLE 55-44-019-QRY Created On: 06/24/20 Updated On:	Q	SW	NE	33	22N	17E	Outagamie	0-225-205-2020	0.2	8.5	1.7	4.4	22.2	2.773	2.795	0.800		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MACKVILLE 55-44-019-QRY Created On: 01/17/23 Updated On:	Q	SW	NE	33	22N	17E	Outagamie	0-225-122-2023	0.1	4.7	1.2	4.6	20.4	2.762	2.788	0.923		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MACKVILLE 55-44-019-QRY Created On: 01/02/24 Updated On:	Q	SW	NE	33	22N	17E	Outagamie	0-225-105-2024	0.3	6.4	1.0	5.0	21.7	2.764	2.788	0.882		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MCC FREEDOM EAST QUARRY 55-44-028-QRY Created On: 01/14/25 Updated On:	Q			16	22N	18E	Outagamie	0-225-122-2025	1.3	7.2	5.7	6.7	30.6	2.682	2.722	1.511		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MCC ROCK ROAD 55-44-031-QRY Created On: 01/05/21 Updated On:	Q	SE	SW	17	22N	17E	Outagamie	0-225-100-2021	0.2	0.8	3.2	6.7	30.2	2.716	2.756	1.469		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse					
	P/Q	Qrt	Qrt	Sect	Town	Range	County	LA Wear (%)					Sp. Gravity		Absorp. %			
								100					500	OD	SSD	Crse	Fine	
OUTAGAMIE -- WI																		
MCC ROCK ROAD 55-44-031-QRY Created On: 01/02/24 Updated On:	Q	SE	SW	17	22N	17E	Outagamie	0-225-6-2024	0.6	1.5	0.4	7.3	31.6	2.712	2.743	1.120		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MCC- FREEDOM WEST 55-44-020-QRY Created On: 05/02/16 Updated On:	Q	NE	SE	17	22N	18E	Outagamie	0-225-160-2016	0.4	12.0	0.2	5.6	23.7	2.768	2.790	0.823		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
MCC- FREEDOM WEST 55-44-020-QRY Created On: 04/19/19 Updated On:	Q	NE	SE	17	22N	18E	Outagamie	0-225-150-2019	0.3	3.8	2.5	4.8	21.6	2.768	2.793	0.907		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
MCC- FREEDOM WEST 55-44-020-QRY Created On: 06/24/20 Updated On:	Q	NE	SE	17	22N	18E	Outagamie	0-225-206-2020	0.6	7.9	2.2	5.2	21.5	2.769	2.792	0.841		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MCC- FREEDOM WEST 55-44-020-QRY Created On: 01/05/21 Updated On:	Q	NE	SE	17	22N	18E	Outagamie	0-225-101-2021	0.1	2.2	2.4	5.2	22.4	2.762	2.787	0.909		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MCC- FREEDOM WEST 55-44-020-QRY Created On: 01/02/24 Updated On:	Q	NE	SE	17	22N	18E	Outagamie	0-225-5-2024	0.0	5.9	1.7	5.0	22.2	2.763	2.789	0.919		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MEDINA 55-44-016-PIT Created On: 03/17/22 Updated On:	P		SW	19	21N	16E	Outagamie	0-225-146-2022	0.5	0.0	0.3	5.2	25.2	2.754	2.780	0.924		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
OUTAGAMIE -- WI																		
MICHEL'S GARVEY 55-44-021-QRY Created On: 01/07/16 Updated On:	Q	SE	SE	17	22N	17E	Outagamie	0-225-36-2016		0.6	1.9	7.0	31.4	2.682	2.720	1.428		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
MICHEL'S GARVEY 55-44-021-QRY Created On: 01/07/19 Updated On:	Q	SE	SE	17	22N	17E	Outagamie	0-225-42-2019	0.2	3.9	5.1	6.9	31.6	2.741	2.769	1.022		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MICHEL'S GARVEY 55-44-021-QRY Created On: 01/04/22 Updated On:	Q	SE	SE	17	22N	17E	Outagamie	0-225-34-2022	0.2	0.8	1.7	5.8	27.9	2.720	2.753	1.221		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MICHEL'S GARVEY 55-44-021-QRY Created On: 01/02/24 Updated On:	Q	SE	SE	17	22N	17E	Outagamie	0-225-106-2024	1.2	3.9	4.1	7.8	32.4	2.688	2.728	1.509		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
NEW LONDON 55-44-025-QRY Created On: 05/26/16 Updated On:	Q			30	22N	15E	Outagamie	0-225-192-2016		8.3	8.8	7.4	31.7	2.691	2.731	1.467		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
NEW LONDON 55-44-025-QRY Created On: 01/25/19 Updated On:	Q			30	22N	15E	Outagamie	0-225-89-2019	0.4	2.6	1.1	8.0	31.3	2.731	2.759	1.005		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
NEW LONDON 55-44-025-QRY Created On: 04/28/22 Updated On:	Q			30	22N	15E	Outagamie	0-225-186-2022	0.4	7.3	2.1	6.3	29.8	2.722	2.754	1.193		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
OUTAGAMIE -- WI																		
NEW LONDON 55-44-025-QRY Created On: 01/14/25 Updated On:	Q			30	22N	15E	Outagamie	0-225-103-2025		0.0	3.0	3.3	6.9	29.3	2.709	2.743	1.248	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
PEARL 55-44-014-QRY Created On: 01/02/25 Updated On:	Q	SW	SE	25	24N	18E	Outagamie	0-225-59-2025		0.0	4.9	1.4	4.9	21.2	2.794	2.811	0.641	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
SEYMOUR 55-44-027-QRY Created On: 05/11/17 Updated On:	Q	SW	SE	31	24N	18E	Outagamie	0-225-180-2017			3.9	1.1	7.5	30.5	2.724	2.761	1.330	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
SEYMOUR 55-44-027-QRY Created On: 04/08/20 Updated On:	Q	SW	SE	31	24N	18E	Outagamie	0-225-146-2020		0.2	12.6	2.4	8.0	30.9	2.758	2.784	0.918	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
SEYMOUR 55-44-027-QRY Created On: 02/28/23 Updated On:	Q	SW	SE	31	24N	18E	Outagamie	0-225-160-2023		1.0	8.8	1.4	6.9	27.6	2.741	2.772	1.124	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
TIMM 55-44-029-QRY Created On: 03/17/22 Updated On:	Q	NE	NE	25	22N	16E	Outagamie	0-225-150-2022		0.0	9.0	1.1	5.2	23.6	2.746	2.776	1.083	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
TIMM 55-44-029-QRY Created On: 01/14/25 Updated On:	Q	NE	NE	25	22N	16E	Outagamie	0-225-100-2025			5.7	3.0	5.6	24.2	2.731	2.762	1.146	
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																	

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
OUTAGAMIE -- WI																		
VINTON ROCK ROAD 55-44-070-QRY Created On: 02/24/25 Updated On:	Q	SE	SE	17	22N	17E	Outagamie	0-225-158-2025		0.7	0.5	1.1	7.5	30.7	2.716	2.747	1.124	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
OZAUKEE -- WI																		
HARTMAN SPRING LAKE 55-45-004-PIT Created On: 04/26/19 Updated On:	P	SE	NE	3	12N	21E	Ozaukee	0-225-171-2019		0.4	1.5	0.6	8.4	35.2	2.717	2.746	1.084	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
HARTMAN SPRING LAKE 55-45-004-PIT Created On: 05/20/24 Updated On:	P	SE	NE	3	12N	21E	Ozaukee	0-225-258-2024		0.2	3.3	0.4	6.2	30.1	2.724	2.750	0.951	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
PEPIN -- WI																		
DURAND 55-46-002-QRY Created On: 06/08/15 Updated On:	Q	SW	SW	33	25N	13W	Pepin	0-225-190-2015			0.0	3.0	10.4	37.9	2.586	2.654	2.632	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
DURAND 55-46-002-QRY Created On: 01/03/18 Updated On:	Q	SW	SW	33	25N	13W	Pepin	0-225-28-2018		1.0	0.0	1.8	9.1	34.5	2.588	2.656	2.604	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
DURAND 55-46-002-QRY Created On: 01/05/21 Updated On:	Q	SW	SW	33	25N	13W	Pepin	0-225-69-2021		1.3	0.0	0.5	8.2	33.0	2.596	2.666	2.675	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
PEPIN -- WI																		
DURAND	Q	SW	SW	33	25N	13W	Pepin	0-225-76-2024	0.8	1.4	4.9	9.8	37.9	2.592	2.660	2.613		
55-46-002-QRY	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
Created On: 01/02/24																		
Updated On:																		
PIERCE -- WI																		
DON MILLER	Q	N	NE	10	27N	15W	Pierce	0-225-191-2015		0.0	6.3	10.3	36.1	2.555	2.625	2.717		
55-47-006-QRY	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
Created On: 06/08/15																		
Updated On:																		
DON MILLER	Q	N	NE	10	27N	15W	Pierce	0-225-34-2018	3.2	0.0	1.1	9.4	34.4	2.559	2.628	2.668		
55-47-006-QRY	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
Created On: 01/03/18																		
Updated On:																		
DON MILLER	Q	N	NE	10	27N	15W	Pierce	0-225-73-2021	2.2	0.0	0.1	8.3	31.8	2.603	2.659	2.146		
55-47-006-QRY	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
Created On: 01/05/21																		
Updated On:																		
DON MILLER	Q	N	NE	10	27N	15W	Pierce	0-225-77-2024	4.1	0.0	5.8	11.0	39.4	2.550	2.624	2.893		
55-47-006-QRY	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
Created On: 01/02/24																		
Updated On:																		
EL PASO	Q	NE	SE	5	26N	16W	Pierce	0-225-45-2025	0.8	6.8	4.8	9.0	36.2	2.612	2.671	2.243		
55-47-007-QRY	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
Created On: 01/02/25																		
Updated On:																		
ELMWOOD	Q	SE	SE	36	27N	15W	Pierce	0-225-164-2016		0.0	3.9	8.3	30.5	2.666	2.708	1.573		
55-47-008-QRY	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
Created On: 05/09/16																		
Updated On:																		

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
PIERCE -- WI																		
ELMWOOD 55-47-008-QRY Created On: 01/07/19 Updated On:	Q	SE	SE	36	27N	15W	Pierce	0-225-64-2019	2.5	0.0	7.8	14.1	45.8	2.493	2.588	3.836		
	Approved Use : CONCRETE, Base Aggregate																	
ELMWOOD 55-47-008-QRY Created On: 04/05/22 Updated On:	Q	SE	SE	36	27N	15W	Pierce	0-225-160-2022	0.5	0.0	8.2	12.4	44.9	2.555	2.627	2.821		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
ELMWOOD 55-47-008-QRY Created On: 01/02/25 Updated On:	Q	SE	SE	36	27N	15W	Pierce	0-225-41-2025	0.8	1.4	8.5	10.7	42.2	2.547	2.629	3.221		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
ELMWOOD CTH G QUARRY 55-47-036-QRY Created On: 03/27/24 Updated On:	Q	SE	SE	34	27N	15W	Pierce	0-225-208-2024	4.1	0.0	6.1	12.9	41.6	2.562	2.631	2.703		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
ELMWOOD CTH S QUARRY 55-47-037-QRY Created On: 03/27/24 Updated On:	Q	SE	SW	15	26N	15W	Pierce	0-225-209-2024	7.2	0.0	5.8	7.7	32.7	2.618	2.668	1.893		
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																	
ELMWOOD CTH S QUARRY 55-47-037-QRY Created On: 10/15/24 Updated On:	Q	SE	SW	15	26N	15W	Pierce	0-225-314-2024	1.0	0.0	3.2	5.8	26.1	2.666	2.704	1.424		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
HOLST 55-47-010-PIT Created On: 01/03/18 Updated On:	P		W	33	25N	18W	Pierce	0-225-40-2018	1.5	0.0	1.9	5.5	24.5	2.660	2.699	1.455		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
PIERCE -- WI																	
HOLST 55-47-010-PIT Created On: 08/22/23 Updated On:	P		W	33	25N	18W	Pierce	0-225-247-2023	1.5	0.0	0.6	6.2	25.1	2.645	2.675	1.167	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
*KAASA 55-47-015-QRY Created On: 01/12/15 Updated On:	Q			15	24N	16W	Pierce	0-225-61-2015		0.0	5.4	11.6	42.0	2.551	2.623	2.801	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
*KAASA 55-47-015-QRY Created On: 01/03/18 Updated On:	Q			15	24N	16W	Pierce	0-225-35-2018	1.4	0.0	5.1	8.3	30.5	2.637	2.683	1.757	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
*KAASA 55-47-015-QRY Created On: 01/05/21 Updated On:	Q			15	24N	16W	Pierce	0-225-72-2021	1.8	0.0	0.6	9.0	32.3	2.660	2.701	1.557	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
*MILESTONE-WAYNE ANDERSON 55-47-030-QRY Created On: 01/03/18 Updated On:	Q	NW	NE	9	25N	18W	Pierce	0-225-39-2018	2.1	0.0	4.2	8.7	33.4	2.615	2.674	2.258	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
*MILESTONE-WAYNE ANDERSON 55-47-030-QRY Created On: 01/05/21 Updated On:	Q	NW	NE	9	25N	18W	Pierce	0-225-76-2021	1.9	0.0	0.4	7.7	31.3	2.605	2.667	2.360	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
MORRISON 55-47-018-QRY Created On: 06/10/16 Updated On:	Q	SE	NW	35	25N	18W	Pierce	0-225-196-2016	2.1	0.0	2.1	7.3	31.2	2.665	2.709	1.622	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
PIERCE -- WI																		
MORRISON 55-47-018-QRY Created On: 01/07/19 Updated On:	Q	SE	NW	35	25N	18W	Pierce	0-225-62-2019	2.2	0.0	5.7	9.5	38.5	2.614	2.669	2.125		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MORRISON 55-47-018-QRY Created On: 03/07/22 Updated On:	Q	SE	NW	35	25N	18W	Pierce	0-225-141-2022		3.2	5.1	8.5	34.9	2.640	2.690	1.900		
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																	
MORRISON 55-47-018-QRY Created On: 01/02/25 Updated On:	Q	SE	NW	35	25N	18W	Pierce	0-225-21-2025	1.1	4.5	7.9	9.6	38.4	2.618	2.678	2.308		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
PRESCOTT 55-47-020-QRY Created On: 09/02/16 Updated On:	Q	NW	NW	12	26N	20W	Pierce	0-225-252-2016		0.0	3.5	8.6	34.8	2.604	2.664	2.321		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
PRESCOTT 55-47-020-QRY Created On: 01/07/19 Updated On:	Q	NW	NW	12	26N	20W	Pierce	0-225-61-2019	1.2	0.0	7.4	8.4	34.6	2.622	2.679	2.160		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
PRESCOTT 55-47-020-QRY Created On: 01/04/22 Updated On:	Q	NW	NW	12	26N	20W	Pierce	0-225-75-2022	4.6	7.0	5.2	7.8	33.1	2.635	2.685	1.901		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
PRESCOTT 55-47-020-QRY Created On: 01/02/25 Updated On:	Q	NW	NW	12	26N	20W	Pierce	0-225-34-2025	2.6	0.0	3.3	7.8	34.5	2.605	2.660	2.120		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
PIERCE -- WI																		
SPRING VALLEY 55-47-026-QRY Created On: 01/05/17 Updated On:	Q	NE	NE	16	27N	15W	Pierce	0-225-44-2017		0.0	0.9	4.4	23.2	2.694	2.725	1.175		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
SPRING VALLEY 55-47-026-QRY Created On: 03/02/20 Updated On:	Q	NE	NE	16	27N	15W	Pierce	0-225-117-2020	0.1	0.0	0.2	6.3	28.5	2.653	2.698	1.693		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
SPRING VALLEY 55-47-026-QRY Created On: 01/10/23 Updated On:	Q	NE	NE	16	27N	15W	Pierce	0-225-104-2023	0.9	7.4	0.2	6.0	30.5	2.634	2.686	1.981		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
SVEC 55-47-027-QRY Created On: 03/24/16 Updated On:	Q	E	NW	17	26N	18W	Pierce	0-225-115-2016		0.0	7.8	9.9	34.2	2.609	2.674	2.499		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
SVEC 55-47-027-QRY Created On: 01/07/19 Updated On:	Q	E	NW	17	26N	18W	Pierce	0-225-63-2019	0.5	0.0	5.8	9.2	33.8	2.611	2.675	2.469		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
SVEC 55-47-027-QRY Created On: 01/04/22 Updated On:	Q	E	NW	17	26N	18W	Pierce	0-225-77-2022	5.5	16.0	16.4	15.0	45.0	2.551	2.630	3.087		
	Approved Use : Base Aggregate																	
SVEC 55-47-027-PIT Created On: 03/15/22 Updated On:	P	E	NW	17	26N	18W	Pierce	0-225-142-2022	2.4	8.7	11.1	10.7	37.6	2.633	2.691	2.177		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
PIERCE -- WI																	
SVEC 55-47-027-QRY Created On: 05/21/24 Updated On:	Q	E	NW	17	26N	18W	Pierce	0-225-261-2024	5.5	16.1	11.1	12.4	41.7	2.568	2.644	2.945	
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																
TRIMBELLE 55-47-029-QRY Created On: 09/24/20 Updated On:	Q		SW	21	26N	18W	Pierce	0-225-242-2020	3.8	0.0	11.3	12.4	44.8	2.574	2.643	2.668	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
TRIMBELLE 55-47-029-QRY Created On: 10/14/24 Updated On:	Q		SW	21	26N	18W	Pierce	0-225-313-2024	0.4	0.0	5.6	8.6	37.1	2.661	2.707	1.719	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
WIESER 55-47-033-QRY Created On: 06/08/17 Updated On:	Q	E	NE	9	25N	16W	Pierce	0-225-206-2017		0.0	3.9	11.8	40.5	2.581	2.644	2.458	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
WIESER 55-47-033-QRY Created On: 06/06/19 Updated On:	Q	E	NE	9	25N	16W	Pierce	0-225-206-2019	1.9	0.0	7.6	9.7	39.9	2.555	2.626	2.814	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
WIESER 55-47-033-QRY Created On: 04/19/22 Updated On:	Q	E	NE	9	25N	16W	Pierce	0-225-180-2022	2.8	0.0	4.9	12.8	42.9	2.566	2.637	2.779	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
WIESER 55-47-033-QRY Created On: 02/20/25 Updated On:	Q	E	NE	9	25N	16W	Pierce	0-225-152-2025	3.2	0.0	7.2	10.9	38.0	2.596	2.652	2.155	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
POLK -- WI																	
DRESSER TRAP 55-48-007-QRY Created On: 01/05/16 Updated On:	Q			5	33N	18W	Polk	0-225-25-2016		0.0	3.6	4.6	16.8	2.880	2.903	0.792	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
DRESSER TRAP 55-48-007-QRY Created On: 01/10/22 Updated On:	Q			5	33N	18W	Polk	0-225-108-2022	0.0	1.4	1.2	2.1	9.2	2.933	2.948	0.522	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
DRESSER TRAP 55-48-007-QRY Created On: 01/02/25 Updated On:	Q			5	33N	18W	Polk	0-225-48-2025	0.0	0.0	1.7	2.6	11.6	2.925	2.942	0.595	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
LAKETOWN 55-48-015-QRY Created On: 05/07/15 Updated On:	Q	SW	SE	12	36N	18W	Polk	0-225-149-2015		0.0	0.5	0.9	9.3	2.993	3.000	0.243	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
LAKETOWN 55-48-015-QRY Created On: 05/21/18 Updated On:	Q	SW	SE	12	36N	18W	Polk	0-225-215-2018	0.0	0.0	1.4	2.5	11.3	2.967	2.979	0.405	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
LAKETOWN 55-48-015-QRY Created On: 01/04/21 Updated On:	Q	SW	SE	12	36N	18W	Polk	0-225-38-2021	0.0	0.3	0.2	1.7	8.0	2.998	3.009	0.384	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
LAKETOWN 55-48-015-QRY Created On: 01/04/24 Updated On:	Q	SW	SE	12	36N	18W	Polk	0-225-142-2024	0.0	0.1	0.2	1.9	9.2	2.989	3.001	0.384	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
POLK -- WI																		
MILESTONE-ANSEL JOHNSON 55-48-013-PIT Created On: 01/05/16 Updated On:	P	NW	SW	35	34N	16W	Polk	0-225-22-2016		0.0	1.6	2.9	14.7	2.744	2.773	1.035		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
MILESTONE-ANSEL JOHNSON 55-48-013-PIT Created On: 01/04/21 Updated On:	P	NW	SW	35	34N	16W	Polk	0-225-37-2021	0.7	1.2	2.3	2.7	14.1	2.747	2.779	1.159		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MILESTONE-WALKER 8 55-48-030-PIT Created On: 06/21/18 Updated On:	P	SE	SE	23	34N	17W	Polk	0-225-238-2018	0.3	0.0	1.6	4.8	17.4	2.823	2.853	1.051		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MILESTONE-WALKER 8 55-48-030-PIT Created On: 05/01/23 Updated On:	P	SE	SE	23	34N	17W	Polk	0-225-209-2023	0.1	0.0	1.1	2.6	13.1	2.854	2.880	0.911		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
NYRENE 55-48-017-PIT Created On: 01/02/25 Updated On:	P	SW	NE	23	36N	18W	Polk	0-225-46-2025	1.9	0.0	2.8	5.3	19.5	2.742	2.769	1.005		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
OSCEOLA 55-48-018-PIT Created On: 01/09/15 Updated On:	P	NW	SE	16	33N	18W	Polk	0-225-42-2015		0.0	3.4	5.8	18.3	2.780	2.809	1.068		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
OSCEOLA 55-48-018-PIT Created On: 01/02/24 Updated On:	P	NW	SE	16	33N	18W	Polk	0-225-80-2024	4.0	0.0	2.4	5.3	19.9	2.737	2.772	1.263		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
POLK -- WI																		
POLK LIME QUARRY 55-48-034-QRY Created On: 03/17/21 Updated On:	Q	NW	NE	10	32N	18W	Polk	0-225-153-2021	2.3	0.0	6.4	9.7	36.0	2.552	2.637	3.334		
Approved Use : Base Aggregate																		
POLK LIME QUARRY 55-48-034-QRY Created On: 10/14/21 Updated On:	Q	NW	NE	10	32N	18W	Polk	0-225-269-2021	5.3	0.0	15.1	12.3	44.9	2.509	2.604	3.803		
Approved Use : Base Aggregate																		
POLK LIME QUARRY 55-48-034-QRY Created On: 01/13/22 Updated On:	Q	NW	NE	10	32N	18W	Polk	0-225-113-2022	2.4	0.0	8.8	9.2	38.0	2.529	2.621	3.641		
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
POLK LIME QUARRY 55-48-034-QRY Created On: 04/01/25 Updated On:	Q	NW	NE	10	32N	18W	Polk	0-225-180-2025	0.7	0.0	12.4	8.3	34.9	2.540	2.628	3.466		
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
SWANSON 55-48-026-PIT Created On: 01/09/15 Updated On:	P	S	SW	30	34N	16W	Polk	0-225-43-2015		0.0	4.0	4.8	19.1	2.758	2.789	1.130		
Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																		
SWANSON 55-48-026-PIT Created On: 04/15/25 Updated On:	P	S	SW	30	34N	16W	Polk	0-225-189-2025	1.6	2.4	3.2	5.1	19.5	2.731	2.770	1.424		
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
PORTAGE -- WI																		
BIBBY 55-49-028-PIT Created On: 01/02/24 Updated On:	P	NE	NW	8	22N	9E	Portage	0-225-65-2024	0.2	6.0	0.1	6.7	27.7	2.672	2.698	0.982		
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
PORTAGE -- WI																		
BOULDER HILL 55-49-003-PIT Created On: 01/04/18 Updated On:	P	SW	NE	22	22N	9E	Portage	0-225-86-2018	0.9	0.0	4.2	8.7	31.8	2.678	2.707	1.106		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
BOULDER HILL 55-49-003-PIT Created On: 01/03/23 Updated On:	P	SW	NE	22	22N	9E	Portage	0-225-12-2023	0.4	3.5	3.3	7.9	31.2	2.667	2.700	1.234		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
BUENA VISTA RIDGE 55-49-032-PIT Created On: 06/10/24 Updated On:	P	SW	NW	33	22N	9E	Portage	0-225-268-2024	0.7	0.0	1.6	5.5	24.9	2.705	2.735	1.138		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
CUSTER 55-49-004-PIT Created On: 01/06/16 Updated On:	P		E	4	23N	9E	Portage	0-225-31-2016		0.0	1.9	7.1	27.6	2.680	2.703	0.868		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
CUSTER 55-49-004-PIT Created On: 01/04/21 Updated On:	P		E	4	23N	9E	Portage	0-225-20-2021	0.0	0.0	0.7	7.3	29.0	2.650	2.683	1.214		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
*DB 55-49-007-QRY Created On: 03/21/18 Updated On:	Q	SW	SW	1	25N	7E	Portage	0-225-133-2018		0.0	2.1	5.7	22.6	2.647	2.666	0.741		
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																	
*DB 55-49-007-QRY Created On: 06/28/22 Updated On:	Q	SW	SW	1	25N	7E	Portage	0-225-240-2022		0.0	1.3	5.2	21.1	2.680	2.699	0.713		
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse		Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
PORTAGE -- WI																		
JET BLACK QUARRY 55-49-031-QRY Created On: 03/13/24 Updated On:	Q	NE	SW	25	25N	7E	Portage	0-225-200-2024	0.0	0.0	0.7	4.5	18.3	2.971	2.993	0.733		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MILESTONE SOMERS 55-49-015-PIT Created On: 01/07/15 Updated On:	P	NE	NE	29	23N	9E	Portage	0-225-18-2015		0.0	2.5	6.9	28.8	2.685	2.718	1.206		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
MILESTONE SOMERS 55-49-015-PIT Created On: 01/07/20 Updated On:	P	NE	NE	29	23N	9E	Portage	0-225-43-2020	2.6	0.0	3.9	9.4	33.4	2.663	2.698	1.321		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MILESTONE SOMERS 55-49-015-PIT Created On: 01/02/24 Updated On:	P	NE	NE	29	23N	9E	Portage	0-225-45-2024	0.4	3.9	2.0	7.1	29.2	2.683	2.715	1.188		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
PERZINSKI 55-49-018-PIT Created On: 04/15/24 Updated On:	P	SE	SE	20	23N	9E	Portage	0-225-218-2024	1.9	2.2	2.3	6.1	29.3	2.659	2.693	1.263		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
PLOVER 55-49-019-PIT Created On: 03/06/17 Updated On:	P	SW	SW	5	22N	9E	Portage	0-225-74-2017	0.2	0.0	1.8	7.1	29.0	2.661	2.691	1.110		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
PLOVER 55-49-019-PIT Created On: 02/17/22 Updated On:	P	SW	SW	5	22N	9E	Portage	0-225-131-2022	0.9	0.0	3.2	6.3	27.2	2.652	2.681	1.107		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
PORTAGE -- WI																		
STUCZYNSKI (DUFFEK) 55-49-024-PIT Created On: 07/26/21 Updated On:	P	NE	NW	4	23N	9E	Portage	0-225-250-2021	0.6	0.0	0.6	9.4	34.9	2.603	2.637	1.303		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
WIMMIE 55-49-026-PIT Created On: 01/07/16 Updated On:	P		NW	28	23N	9E	Portage	0-225-43-2016	0.2	0.0	0.8	5.1	24.3	2.705	2.729	0.876		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
WIMMIE 55-49-026-PIT Created On: 01/04/21 Updated On:	P		NW	28	23N	9E	Portage	0-225-22-2021	0.4	2.2	0.4	6.2	26.9	2.726	2.747	0.792		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
WIMMIE #2 55-49-030-PIT Created On: 09/05/23 Updated On:	P		SW	21	23N	9E	Portage	0-225-248-2023	1.0	1.6	1.7	6.1	28.2	2.682	2.709	0.997		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
PRICE -- WI																		
HAAS RW PIT 55-50-029-PIT Created On: 07/27/23 Updated On:	P	NE	SW	36	35N	1E	Price	0-225-242-2023	1.1	0.0	0.7	4.0	18.8	2.717	2.737	0.754		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
HAY CREEK (PRICE) 55-50-008-PIT Created On: 04/23/20 Updated On:	P		SE	4	35N	1E	Price	0-225-156-2020	1.1	0.0	3.9	4.8	20.3	2.707	2.740	1.226		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
HAY CREEK (PRICE) 55-50-008-PIT Created On: 01/02/25 Updated On:	P		SE	4	35N	1E	Price	0-225-66-2025	0.9	0.0	4.7	4.3	19.4	2.668	2.696	1.034		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
PRICE -- WI																		
KRAUS 55-50-011-PIT Created On: 06/26/19 Updated On:	P	E	NE	7	34N	3E	Price	0-225-231-2019	2.0	0.0	2.0	4.6	20.0	2.691	2.725	1.263		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
KRAUS 55-50-011-PIT Created On: 01/02/24 Updated On:	P	E	NE	7	34N	3E	Price	0-225-113-2024	7.1	0.0	5.9	6.4	24.0	2.674	2.714	1.513		
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																	
MILLER 55-50-014-PIT Created On: 05/11/17 Updated On:	P		NE	4	35N	1E	Price	0-225-179-2017		0.0	1.5	4.0	18.7	2.717	2.742	0.913		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MILLER 55-50-014-PIT Created On: 05/17/22 Updated On:	P		NE	4	35N	1E	Price	0-225-201-2022	0.0	0.0	4.2	4.1	19.2	2.724	2.752	1.063		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
NEECK READY MIX 55-50-016-PIT Created On: 01/04/19 Updated On:	P	NW	NW	31	39N	1E	Price	0-225-3-2019	1.0	0.0	2.0	4.1	19.0	2.738	2.764	0.924		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
NEECK READY MIX 55-50-016-PIT Created On: 01/02/24 Updated On:	P	NW	NW	31	39N	1E	Price	0-225-90-2024	0.3	2.6	2.8	3.6	17.5	2.722	2.750	1.034		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
PHILLIPS 55-50-019-PIT Created On: 01/05/21 Updated On:	P	SW	SW	5	37N	1E	Price	0-225-54-2021	0.8	0.0	1.5	4.0	19.3	2.691	2.720	1.042		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
PRICE -- WI																		
PROHASKA 55-50-024-PIT Created On: 06/26/17 Updated On:	P	SW	SW	10	36N	1W	Price	0-225-220-2017		0.0	1.9	4.7	21.5	2.736	2.758	0.829		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
PROHASKA 55-50-024-PIT Created On: 01/04/22 Updated On:	P	SW	SW	10	36N	1W	Price	0-225-86-2022	1.5	0.0	1.7	4.9	22.5	2.742	2.768	0.933		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
RATKOWSKI PIT 55-50-030-PIT Created On: 01/02/25 Updated On:	P			30	39N	1E	Price	0-225-68-2025	0.0	0.0	1.8	4.2	19.1	2.746	2.767	0.757		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
SMASAL 55-50-028-PIT Created On: 01/09/15 Updated On:	P		SE	25	39N	1W	Price	0-225-50-2015		0.0	1.7	15.5	16.6	2.724	2.751	0.993		
	Approved Use : CONCRETE, OGBC, Base Aggregate																	
SMASAL 55-50-028-PIT Created On: 01/07/20 Updated On:	P		SE	25	39N	1W	Price	0-225-45-2020	0.1	0.0	1.8	3.4	16.6	2.733	2.759	0.923		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
SMASAL 55-50-028-PIT Created On: 01/02/25 Updated On:	P		SE	25	39N	1W	Price	0-225-6-2025	0.2	1.1	1.7	3.2	15.0	2.730	2.759	1.048		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
RACINE -- WI																		
A TO Z AGGREGATE SOLUTIONS 55-31-001-PIT Created On: 01/23/17 Updated On:	P		SW	3	3N	19E	Racine	0-225-56-2017	1.9	2.4	1.7	7.0	35.6	2.694	2.732	1.394		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
RACINE -- WI																	
A TO Z AGGREGATE SOLUTIONS 55-51-001-PIT Created On: 01/05/21 Updated On:	P		SW	3	3N	19E	Racine	0-225-80-2021	0.0	8.4	5.3	4.4	23.6	2.680	2.720	1.503	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
BAUMEISTER 55-51-005-PIT Created On: 03/24/16 Updated On:	P		NW	19	2N	19E	Racine	0-225-112-2016		0.0	3.2	5.7	25.5	2.632	2.672	1.516	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
BAUMEISTER 55-51-005-PIT Created On: 01/05/21 Updated On:	P		NW	19	2N	19E	Racine	0-225-83-2021	0.0	0.0	5.1	4.8	25.6	2.671	2.712	1.544	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
BAUMEISTER 55-51-005-PIT Created On: 06/02/25 Updated On:	P		NW	19	2N	19E	Racine	0-225-215-2025	1.5	0.0	0.8	5.0	24.4	2.676	2.721	1.664	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
BURLINGTON SPRING VALLEY 55-51-006-PIT Created On: 03/24/16 Updated On:	P			6	2N	19E	Racine	0-225-114-2016	2.0	8.5	3.3	7.2	31.9	2.646	2.696	1.913	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
BURLINGTON SPRING VALLEY 55-51-006-PIT Created On: 01/05/21 Updated On:	P			6	2N	19E	Racine	0-225-81-2021	0.0	0.0	5.4	4.9	26.3	2.655	2.702	1.768	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
CLEARWATER ACRES LLP 55-51-056-PIT Created On: 01/09/20 Updated On:	P		NE	17	4N	19E	Racine	0-225-94-2020		0.0	4.6	5.6	28.7	2.625	2.673	1.797	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
RACINE -- WI																	
CLEARWATER ACRES LLP 55-51-056-PIT Created On: 04/01/25 Updated On:	P		NE	17	4N	19E	Racine	0-225-182-2025	2.5	0.0	1.8	7.1	30.3	2.641	2.691	1.878	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
CRETEX-MAIN 55-51-015-PIT Created On: 05/21/18 Updated On:	P		NW	6	2N	19E	Racine	0-225-214-2018	1.8	13.1	7.1	5.5	26.6	2.667	2.708	1.560	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
CRETEX-MAIN 55-51-015-PIT Created On: 04/05/23 Updated On:	P		NW	6	2N	19E	Racine	0-225-186-2023	1.4	16.2	11.6	7.4	36.9	2.557	2.612	2.148	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
CRETEX-WARREN 55-51-007-QRY Created On: 03/24/16 Updated On:	Q		NE	4	2N	19E	Racine	0-225-108-2016		0.0	11.1	7.6	27.3	2.615	2.668	2.026	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
CRETEX-WARREN 55-51-007-QRY Created On: 06/18/21 Updated On:	Q		NE	4	2N	19E	Racine	0-225-229-2021	0.0	18.0	10.3	6.1	26.3	2.549	2.630	3.176	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
CRETEX-WARREN 55-51-007-QRY Created On: 05/21/24 Updated On:	Q		NE	4	2N	19E	Racine	0-225-262-2024		21.9	11.9	7.6	27.8	2.602	2.669	2.560	
HIGH VIEW-SAND & GRAVEL 55-51-058-PIT Created On: 01/14/25 Updated On:	P	SE	NE	34	4N	19E	Racine	0-225-124-2025	3.9	9.1	4.7	4.0	24.1	2.674	2.706	1.200	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
RACINE -- WI																	
HILLSIDE 55-51-010-PIT Created On: 02/20/19 Updated On:	P		SE	7	2N	19E	Racine	0-225-107-2019	0.7	7.1	1.8	5.4	26.0	2.663	2.712	1.877	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
HILLSIDE 55-51-010-PIT Created On: 02/28/24 Updated On:	P		SE	7	2N	19E	Racine	0-225-188-2024	2.0	11.7	7.6	5.6	25.7	2.670	2.712	1.603	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
KORDUS AGGREGATES 55-51-057-PIT Created On: 06/25/21 Updated On:	P	S	SW	7	2N	19E	Racine	0-225-235-2021	1.2	10.9	5.3	7.4	31.0	2.656	2.708	1.942	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
P&D HONEY CREEK 55-51-020-PIT Created On: 01/04/18 Updated On:	P		NW	6	3N	19E	Racine	0-225-78-2018	0.5	5.8	1.8	4.1	26.4	2.675	2.720	1.666	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
P&D HONEY CREEK 55-51-020-PIT Created On: 01/03/23 Updated On:	P		NW	6	3N	19E	Racine	0-225-74-2023	0.2	11.5	1.3	5.3	24.4	2.673	2.719	1.722	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
PAYNE AND DOLAN / RACINE 55-51-022-QRY Created On: 02/03/17 Updated On:	Q		S	29	4N	23E	Racine	0-225-57-2017	1.2	0.0	0.9	6.4	27.3	2.633	2.685	1.970	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
PAYNE AND DOLAN / RACINE 55-51-022-QRY Created On: 01/08/20 Updated On:	Q		S	29	4N	23E	Racine	0-225-78-2020	3.2	0.0	4.1	6.3	27.8	2.638	2.693	2.102	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
RACINE -- WI																	
PAYNE AND DOLAN / RACINE 55-51-022-QRY Created On: 01/03/23 Updated On:	Q		S	29	4N	23E	Racine	0-225-50-2023	0.0	0.4	0.1	5.9	26.0	2.665	2.691	0.999	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
PINE LAKE MATERIALS 55-51-025-PIT Created On: 03/24/16 Updated On:	P		NE	35	3N	19E	Racine	0-225-117-2016	0.6	7.3	2.3	5.7	29.6	2.676	2.724	1.793	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
PINE LAKE MATERIALS 55-51-025-PIT Created On: 01/05/21 Updated On:	P		NE	35	3N	19E	Racine	0-225-82-2021	0.0	14.4	4.8	5.0	25.0	2.654	2.703	1.880	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
REESMAN-HUGHES PIT 55-51-059-PIT Created On: 06/26/23 Updated On:	P	NW	SW	5	2N	19E	Racine	0-225-235-2023	0.7	17.6	3.0	6.4	23.6	2.629	2.689	2.274	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
SUPER AGGREGATE / WATERFORD 55-51-028-PIT Created On: 02/11/19 Updated On:	P	SW	SE	28	4N	19E	Racine	0-225-102-2019	3.1	0.0	7.8	4.6	23.0	2.646	2.692	1.748	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
SUPER AGGREGATE / WATERFORD 55-51-028-PIT Created On: 04/15/24 Updated On:	P	SW	SE	28	4N	19E	Racine	0-225-221-2024	3.9	8.5	1.6	4.3	24.3	2.298	2.335	1.631	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
RICHLAND -- WI																	
*ALVA MILLER 55-52-001-QRY Created On: 06/30/16 Updated On:	Q			17	9N	2W	Richland	0-225-219-2016		0.0	2.2	7.3	30.3	2.692	2.727	1.299	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
RICHLAND -- WI																	
*ALVA MILLER 55-52-001-QRY Created On: 06/20/22 Updated On:	Q			17	9N	2W	Richland	0-225-232-2022	1.2	1.6	1.1	7.9	32.9	2.680	2.718	1.430	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
*BROWN 55-52-027-QRY Created On: 06/02/20 Updated On:	Q			4	11N	1W	Richland	0-225-184-2020	1.3	0.0	0.5	10.0	34.5	2.603	2.661	2.216	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
DOOLEY 55-52-008-QRY Created On: 06/05/15 Updated On:	Q			9	12N	2E	Richland	0-225-187-2015		0.0	1.7	9.2	35.8	2.637	2.685	1.851	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
DOOLEY 55-52-008-QRY Created On: 01/04/18 Updated On:	Q			9	12N	2E	Richland	0-225-50-2018	0.5	0.0	3.1	9.1	36.1	2.628	2.683	2.076	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
DOOLEY 55-52-008-QRY Created On: 01/04/21 Updated On:	Q			9	12N	2E	Richland	0-225-31-2021	0.4	0.0	2.2	9.2	35.8	2.615	2.673	2.222	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
DOOLEY 55-52-008-QRY Created On: 01/02/24 Updated On:	Q			9	12N	2E	Richland	0-225-122-2024	0.8	4.6	1.2	9.5	35.6	2.631	2.691	2.285	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
*FRAWLEY 55-52-010-QRY Created On: 06/21/18 Updated On:	Q			9	10N	2W	Richland	0-225-237-2018	0.8	6.3	9.4	10.2	30.6	2.669	2.716	1.752	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
RICHLAND -- WI																		
*FRAWLEY 55-52-010-QRY Created On: 03/17/21 Updated On:	Q			9	10N	2W	Richland	0-225-149-2021	1.2	11.2	8.6	12.0	38.9	2.593	2.664	2.737		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
HOUSEHOLDER 55-52-014-QRY Created On: 05/09/17 Updated On:	Q	NW	SE	15	10N	1E	Richland	0-225-178-2017		0.0	7.0	9.9	37.3	2.569	2.649	3.125		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
HOUSEHOLDER 55-52-014-QRY Created On: 03/12/20 Updated On:	Q	NW	SE	15	10N	1E	Richland	0-225-128-2020	1.9	0.0	2.8	10.6	36.4	2.517	2.600	3.306		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
HOUSEHOLDER 55-52-014-QRY Created On: 01/03/23 Updated On:	Q	NW	SE	15	10N	1E	Richland	0-225-21-2023	0.3	8.4	0.7	9.4	36.8	2.596	2.660	2.456		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
*KOCH QUARRY 55-52-028-QRY Created On: 05/03/22 Updated On:	Q	SE	NE	18	11N	2E	Richland	0-225-198-2022	0.7	7.5	9.3	11.3	42.4	2.588	2.661	2.816		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
SHANNON 55-52-021-QRY Created On: 05/19/16 Updated On:	Q	NW	SW	32	10N	1W	Richland	0-225-179-2016	1.0	4.2	4.9	8.4	35.3	2.625	2.677	1.988		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
SHANNON 55-52-021-QRY Created On: 07/25/19 Updated On:	Q	NW	SW	32	10N	1W	Richland	0-225-249-2019	0.6	3.2	2.5	7.3	33.2	2.662	2.705	1.623		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
Source Name	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
RICHLAND -- WI																		
SHANNON	Q	NW	SW	32	10N	1W	Richland	0-225-165-2022	0.5	4.5	5.7	8.0	34.4	2.648	2.695	1.803		
55-52-021-QRY	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
Created On: 04/05/22																		
Updated On:																		
SHANNON	Q	NW	SW	32	10N	1W	Richland	0-225-91-2025	0.7	5.7	4.0	8.8	36.7	2.614	2.675	2.311		
55-52-021-QRY	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
Created On: 01/02/25																		
Updated On:																		
ROCK -- WI																		
BJOIN	Q	SW	SW	36	3N	11E	Rock	0-225-86-2017	0.6	2.6	8.0	7.2	31.1	2.622	2.690	2.597		
55-53-003-QRY	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
Created On: 03/22/17																		
Updated On:																		
BJOIN	Q	SW	SW	36	3N	11E	Rock	0-225-118-2020	0.6	12.3	10.5	7.3	32.1	2.626	2.689	2.400		
55-53-003-QRY	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
Created On: 03/02/20																		
Updated On:																		
BJOIN	Q	SW	SW	36	3N	11E	Rock	0-225-133-2023	0.6	26.4	10.2	8.1	34.8	2.624	2.696	2.733		
55-53-003-QRY																		
Created On: 01/30/23																		
Updated On:																		
BJOIN	Q	SW	SW	36	3N	11E	Rock	0-225-174-2023	0.4	15.0	4.4	5.4	26.7	2.678	2.735	2.129		
55-53-003-QRY	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
Created On: 03/21/23																		
Updated On:																		
BRAUKHOFF	Q	S	SW	26	2N	14E	Rock	0-225-203-2022	0.4	6.5	2.7	7.7	34.7	2.652	2.707	2.091		
55-53-004-QRY	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
Created On: 05/17/22																		
Updated On:																		

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
ROCK -- WI																	
BRAUKHOFF 55-53-004-QRY Created On: 01/14/25 Updated On:	Q	S	SW	26	2N	14E	Rock	0-225-98-2025	0.0	7.4	2.4	9.0	37.2	2.603	2.672	2.628	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
*CCI BELOIT QUARRY 55-53-42-QRY Created On: 08/08/17 Updated On:	Q		NW	22	1N	13E	Rock	0-225-246-2017	1.8	1.8	1.3	7.8	35.1	2.480	2.584	4.225	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
*CCI BELOIT QUARRY 55-53-42-QRY Created On: 07/09/20 Updated On:	Q		NW	22	1N	13E	Rock	0-225-211-2020	2.1	9.2	14.6	9.2	36.6	2.571	2.653	3.188	
	Approved Use : Base Aggregate																
CRONIN 55-53-006-PIT Created On: 05/18/18 Updated On:	P	S	SE	5	2N	13E	Rock	0-225-212-2018	1.1	0.0	4.2	5.6	27.8	2.663	2.702	1.458	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
CRONIN 55-53-006-PIT Created On: 01/03/23 Updated On:	P	S	SE	5	2N	13E	Rock	0-225-13-2023		0.0	1.4	4.8	25.3	2.637	2.679	1.577	
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																
DW 55-53-043-PIT Created On: 05/02/19 Updated On:	P		SW	7	3N	13E	Rock	0-225-174-2019	2.7	0.0	6.2	7.5	33.2	2.608	2.677	2.644	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
DW 55-53-043-PIT Created On: 02/10/22 Updated On:	P		SW	7	3N	13E	Rock	0-225-122-2022	5.5	4.3	1.6	8.1	29.0	2.651	2.692	1.551	
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
ROCK -- WI																	
EMPIRE LIME 55-53-010-QRY Created On: 08/08/16 Updated On:	Q	SW	NE	21	1N	12E	Rock	0-225-239-2016	1.5	6.3	12.6	11.8	41.4	2.564	2.649	3.333	
	Approved Use : Base Aggregate																
EMPIRE LIME 55-53-010-QRY Created On: 03/21/23 Updated On:	Q	SW	NE	21	1N	12E	Rock	0-225-175-2023	0.4	12.2	12.9	11.9	42.0	2.566	2.650	3.286	
	Approved Use : Base Aggregate																
FOOTVILLE ROCK & LIME 55-53-011-QRY Created On: 03/22/19 Updated On:	Q	SE	NW	2	2N	10E	Rock	0-225-115-2019	0.1	5.8	10.5	6.0	28.3	2.648	2.703	2.051	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
FOOTVILLE ROCK & LIME 55-53-011-QRY Created On: 01/03/23 Updated On:	Q	SE	NW	2	2N	10E	Rock	0-225-61-2023	1.0	16.2	17.4	11.1	40.6	2.570	2.654	3.255	
	Approved Use : Base Aggregate																
FOOTVILLE ROCK & LIME 55-53-011-QRY Created On: 03/27/24 Updated On:	Q	SE	NW	2	2N	10E	Rock	0-225-212-2024	0.6	17.6	15.6	8.7	37.0	2.582	2.667	3.288	
	Approved Use : Base Aggregate																
HURD PIT 55-53-017-PIT Created On: 03/30/15 Updated On:	P	NW	SW	15	4N	12E	Rock	0-225-108-2015	4.2	0.0	2.2	5.7	27.5	2.645	2.691	1.736	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
HURD PIT 55-53-017-PIT Created On: 04/20/23 Updated On:	P	NW	SW	15	4N	12E	Rock	0-225-202-2023	4.9	8.0	2.3	5.9	27.1	2.673	2.721	1.814	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
ROCK -- WI																	
*HURD QUARRY 55-53-044-QRY Created On: 07/02/19 Updated On:	Q	NW	SW	15	4N	12E	Rock	0-225-233-2019		5.1	9.9	7.3	35.1	2.630	2.691	2.326	
	Approved Use : HMA<MT, HMA>=MT, Base Aggregate																
*HURD QUARRY 55-53-044-QRY Created On: 01/05/21 Updated On:	Q	NW	SW	15	4N	12E	Rock	0-225-78-2021		9.1	6.0	4.8	30.0	2.659	2.712	1.997	
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																
JANESVILLE SAND & GRAVEL 55-53-018-PIT Created On: 03/02/15 Updated On:	P	SE	SW	24	3N	12E	Rock	0-225-84-2015	2.0	6.2	2.1	6.7	30.0	2.628	2.679	1.925	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
JANESVILLE SAND & GRAVEL 55-53-018-PIT Created On: 01/08/20 Updated On:	P	SE	SW	24	3N	12E	Rock	0-225-50-2020	2.8	0.0	2.7	6.3	29.9	2.624	2.676	1.986	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
JANESVILLE SAND & GRAVEL 55-53-018-PIT Created On: 01/14/25 Updated On:	P	SE	SW	24	3N	12E	Rock	0-225-110-2025	4.0	0.0	3.5	6.2	29.1	2.622	2.669	1.794	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
LATHER 55-53-022-PIT Created On: 04/12/16 Updated On:	P	NW	NW	16	1N	13E	Rock	0-225-141-2016	0.9	3.6	4.1	4.7	25.0	2.638	2.679	1.560	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
LATHER 55-53-022-PIT Created On: 02/06/18 Updated On:	P	NW	NW	16	1N	13E	Rock	0-225-88-2018	3.0	0.0	2.2	4.7	23.8	2.640	2.683	1.638	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
ROCK -- WI																		
LATHER 55-53-022-PIT Created On: 01/07/19 Updated On:	P	NW	NW	16	1N	13E	Rock	0-225-67-2019	3.8	0.0	5.1	5.1	26.9	2.632	2.676	1.690		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
LATHER 55-53-022-PIT Created On: 03/13/24 Updated On:	P	NW	NW	16	1N	13E	Rock	0-225-197-2024	4.9	6.0	1.8	4.4	23.9	2.637	2.677	1.504		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
LITTLE LIMESTONE 55-53-023-QRY Created On: 03/29/17 Updated On:	Q	SW	NE	6	1N	14E	Rock	0-225-92-2017	2.2	3.4	14.9	10.8	39.0	2.547	2.634	3.414		
	Approved Use : Base Aggregate																	
LITTLE LIMESTONE 55-53-023-QRY Created On: 03/19/20 Updated On:	Q	SW	NE	6	1N	14E	Rock	0-225-132-2020	3.1	10.1	16.8	10.4	39.8	2.536	2.624	3.457		
	Approved Use : Base Aggregate																	
LITTLE LIMESTONE 55-53-023-QRY Created On: 01/03/23 Updated On:	Q	SW	NE	6	1N	14E	Rock	0-225-2-2023	3.1	13.3	18.0	99.7	46.6	2.484	2.585	4.090		
	Approved Use : Base Aggregate																	
LITTLE LIMESTONE 55-53-023-QRY Created On: 04/05/23 Updated On:	Q	SW	NE	6	1N	14E	Rock	0-225-190-2023	4.0	9.2	8.8	10.5	39.3	2.640	2.702	2.352		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
PRAIRIE AVE S&G 55-53-030-PIT Created On: 02/16/16 Updated On:	P		SW	6	1N	13E	Rock	0-225-87-2016	0.4	2.2	0.8	8.1	39.5	2.669	2.708	1.481		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
ROCK -- WI																	
PRAIRIE AVE S&G 55-53-030-PIT Created On: 02/06/18 Updated On:	P		SW	6	1N	13E	Rock	0-225-87-2018	4.5	0.0	2.4	5.5	26.7	2.672	2.709	1.399	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
PRAIRIE AVE S&G 55-53-030-PIT Created On: 01/07/19 Updated On:	P		SW	6	1N	13E	Rock	0-225-68-2019	4.6	0.0	4.7	5.3	26.2	2.654	2.694	1.490	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
PRAIRIE AVE S&G 55-53-030-PIT Created On: 01/02/24 Updated On:	P		SW	6	1N	13E	Rock	0-225-1-2024	4.5	0.0	4.1	5.0	25.8	2.662	2.701	1.464	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
SILHA MH 55-53-012-PIT Created On: 04/16/15 Updated On:	P	SW	NE	2	3N	13E	Rock	0-225-121-2015	0.9	0.0	5.1	6.5	30.2	2.650	2.703	2.026	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
SILHA MH 55-53-014-QRY Created On: 04/12/16 Updated On:	Q	SW	NE	2	3N	13E	Rock	0-225-143-2016	0.2	4.0	8.7	8.5	35.5	2.626	2.687	2.347	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
SILHA MH 55-53-014-QRY Created On: 06/02/17 Updated On:	Q	SW	NE	2	3N	13E	Rock	0-225-203-2017	1.1	2.1	7.9	8.1	34.2	2.603	2.669	2.559	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
SILHA MH 55-53-014-QRY Created On: 09/11/19 Updated On:	Q	SW	NE	2	3N	13E	Rock	0-225-269-2019	1.4	2.6	7.2	8.7	37.7	2.587	2.660	2.819	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
ROCK -- WI																		
SILHA MH 55-53-014-QRY Created On: 06/23/20 Updated On:	Q	SW	NE	2	3N	13E	Rock	0-225-202-2020	1.8	12.3	13.2	9.8	39.3	2.621	2.672	1.928		
	Approved Use : Base Aggregate																	
SILHA MH 55-53-012-PIT Created On: 06/23/20 Updated On:	P	SW	NE	2	3N	13E	Rock	0-225-203-2020	4.3	0.0	5.3	5.4	28.6	2.621	2.672	1.928		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
SILHA MH 55-53-014-QRY Created On: 01/03/23 Updated On:	Q	SW	NE	2	3N	13E	Rock	0-225-14-2023	2.1	6.9	8.7	10.0	39.4	2.553	2.632	3.119		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
SILHA MH 55-53-012-PIT Created On: 01/02/25 Updated On:	P	SW	NE	2	3N	13E	Rock	0-225-7-2025	2.8	0.0	1.9	6.6	30.9	2.650	2.701	1.920		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
TOWNLINE 55-53-038-PIT Created On: 04/12/16 Updated On:	P	NE	NE	1	1N	12E	Rock	0-225-142-2016	0.7	3.5	3.1	5.3	24.9	2.646	2.688	1.575		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
TOWNLINE 55-53-038-PIT Created On: 02/06/18 Updated On:	P	NE	NE	1	1N	12E	Rock	0-225-89-2018	2.8	0.0	3.4	5.9	26.5	2.639	2.682	1.629		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
TOWNLINE 55-53-038-PIT Created On: 01/07/19 Updated On:	P	NE	NE	1	1N	12E	Rock	0-225-66-2019	3.1	0.0	3.4	4.5	24.8	2.646	2.689	1.614		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
ROCK -- WI																		
TOWNLIN 55-53-038-PIT Created On: 03/13/24 Updated On:	P	NE	NE	1	1N	12E	Rock	0-225-198-2024	0.7	8.8	3.0	5.0	24.3	2.689	2.727	1.429		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
*VAN ALLEN 55-53-040-QRY Created On: 03/30/15 Updated On:	Q	SE	SE	15	2N	13E	Rock	0-225-109-2015	3.8	4.1	15.4	12.1	44.3	2.533	2.623	3.539		
	Approved Use : Base Aggregate																	
*VAN ALLEN 55-53-040-QRY Created On: 06/02/17 Updated On:	Q	SE	SE	15	2N	13E	Rock	0-225-202-2017	0.2	1.4	8.7	9.3	38.7	2.601	2.669	2.632		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
*VAN ALLEN 55-53-040-QRY Created On: 03/09/20 Updated On:	Q	SE	SE	15	2N	13E	Rock	0-225-126-2020	0.1	2.2	8.2	8.9	36.4	2.576	2.653	3.012		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
RUSK -- WI																		
BESTWAY 55-54-002-PIT Created On: 01/09/15 Updated On:	P		NW	18	33N	9W	Rusk	0-225-40-2015		0.0	4.8	4.8	20.3	2.724	2.756	1.187		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
BESTWAY 55-54-002-PIT Created On: 01/08/20 Updated On:	P		NW	18	33N	9W	Rusk	0-225-52-2020	0.4	0.0	1.2	4.0	18.8	2.760	2.783	0.837		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
BESTWAY 55-54-002-PIT Created On: 01/02/25 Updated On:	P		NW	18	33N	9W	Rusk	0-225-15-2025	0.9	3.7	3.6	4.3	18.6	2.676	2.719	1.609		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
RUSK -- WI																		
BURMEISTER 55-54-029-QRY Created On: 08/20/20 Updated On:	Q	NE	SW	33	33N	5W	Rusk	0-225-234-2020	0.3	0.0	0.4	3.3	14.9	2.814	2.830	0.569		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
BURMEISTER 55-54-030-PIT Created On: 01/04/22 Updated On:	P	NE	SW	33	33N	5W	Rusk	0-225-84-2022	0.4	0.0	1.5	3.6	17.6	2.708	2.736	1.037		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
BURMEISTER 55-54-029-QRY Created On: 01/10/23 Updated On:	Q	NE	SW	33	33N	5W	Rusk	0-225-108-2023	0.0	0.0	0.2	2.1	9.6	2.878	2.887	0.328		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
GLEN FLORA PETERSON 55-54-020-PIT Created On: 06/24/21 Updated On:	P		NE	30	35N	4W	Rusk	0-225-232-2021	1.3	0.0	1.2	4.7	20.5	2.751	2.777	0.939		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
HAAS 0-M PIT 55-54-032-PIT Created On: 07/27/23 Updated On:	P	NW	SE	19	33N	9W	Rusk	0-225-240-2023	1.9	0.0	1.0	5.1	22.5	2.685	2.712	1.002		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
HAAS LEHMAN PIT 55-54-033-PIT Created On: 07/27/23 Updated On:	P	SE	NE	3	33N	7W	Rusk	0-225-244-2023	0.5	0.0	0.5	3.7	18.1	2.688	2.715	1.000		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
HAWKINS 286 55-54-008-PIT Created On: 01/05/16 Updated On:	P	S	NW	15	35N	3W	Rusk	0-225-24-2016		0.0	1.4	4.3	19.4	2.731	2.751	0.758		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
RUSK -- WI																		
HAWKINS 286 55-54-008-PIT Created On: 10/12/21 Updated On:	P	S	NW	15	35N	3W	Rusk	0-225-268-2021	0.4	1.2	1.5	3.5	17.4	2.755	2.770	0.579		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
HAWKINS 286 55-54-008-PIT Created On: 01/10/23 Updated On:	P	S	NW	15	35N	3W	Rusk	0-225-115-2023	0.5	0.0	1.3	3.9	20.0	2.718	2.741	0.826		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
HEATH 55-54-009-PIT Created On: 04/11/18 Updated On:	P	NW	NW	30	35N	4W	Rusk	0-225-163-2018	0.5	0.0	2.4	3.8	17.9	2.760	2.785	0.898		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
HEATH 55-54-009-PIT Created On: 01/10/23 Updated On:	P	NW	NW	30	35N	4W	Rusk	0-225-113-2023	0.7	0.0	1.6	3.5	17.4	2.763	2.782	0.705		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
KAZMIERKOWSKI PIT 55-54-011-PIT Created On: 07/12/23 Updated On:	P	SW	SE	9	34N	8W	Rusk	0-225-237-2023	1.3	0.0	0.7	5.4	23.8	2.677	2.697	0.724		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
LADYSMITH EAST 55-54-012-PIT Created On: 01/03/18 Updated On:	P	S	NW	15	35N	6W	Rusk	0-225-30-2018	1.0	0.0	1.3	4.2	19.1	2.727	2.752	0.906		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
LADYSMITH EAST 55-54-012-PIT Created On: 01/10/23 Updated On:	P	S	NW	15	35N	6W	Rusk	0-225-109-2023	1.1	0.0	2.6	3.8	19.1	2.687	2.718	1.173		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
RUSK -- WI																		
LADYSMITH WEST 55-54-022-PIT Created On: 03/08/18 Updated On:	P	SE	NW	16	35N	6W	Rusk	0-225-117-2018	1.8	0.0	2.4	4.0	18.9	2.688	2.721	1.225		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
LADYSMITH WEST 55-54-022-PIT Created On: 03/06/23 Updated On:	P	SE	NW	16	35N	6W	Rusk	0-225-163-2023	0.0	0.0	1.0	4.4	19.1	2.733	2.761	1.051		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
NOVAK 55-54-016-PIT Created On: 08/24/17 Updated On:	P	SE	NE	32	34N	9W	Rusk	0-225-261-2017		0.0	2.9	5.1	21.4	2.734	2.764	1.081		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
NOVAK 55-54-016-PIT Created On: 07/19/21 Updated On:	P	SE	NE	32	34N	9W	Rusk	0-225-246-2021	1.1	0.0	0.7	4.0	20.2	2.754	2.774	0.726		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
WEBSTER PIT 55-54-031-PIT Created On: 01/10/23 Updated On:	P	NE	NE	7	34N	4W	Rusk	0-225-116-2023	1.1	0.0	2.2	4.1	18.5	2.768	2.790	0.815		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
SAUK -- WI																		
ALT 55-56-033-QRY Created On: 06/02/20 Updated On:	Q			12	9N	3E	Sauk	0-225-183-2020	1.2	0.0	8.5	10.9	37.6	2.574	2.644	2.715		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
ALT 55-56-033-QRY Created On: 01/02/24 Updated On:	Q			12	9N	3E	Sauk	0-225-119-2024	0.9	5.9	1.3	9.3	34.1	2.600	2.662	2.370		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	Coarse					
	P/Q	Qrt	Qrt	Sect	Town	Range	County	LA Wear (%)					Sp. Gravity		Absorp. %			
								100					500	OD	SSD	Crse	Fine	
SAUK -- WI																		
BALFANZ 55-56-001-QRY Created On: 07/16/15 Updated On:	Q	NE	NE	14	10N	5E	Sauk	0-225-211-2015		0.0	3.8	9.0	42.8	2.557	2.628	2.758		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
BALFANZ 55-56-001-QRY Created On: 01/03/18 Updated On:	Q	NE	NE	14	10N	5E	Sauk	0-225-24-2018	0.7	6.7	8.1	12.8	45.6	2.527	2.607	3.151		
	Approved Use : HMA<MT, CONCRETE, Base Aggregate																	
BALFANZ 55-56-001-QRY Created On: 04/06/21 Updated On:	Q	NE	NE	14	10N	5E	Sauk	0-225-171-2021	0.6	1.4	1.3	10.9	41.1	2.597	2.655	2.257		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
BALFANZ 55-56-001-QRY Created On: 01/02/24 Updated On:	Q	NE	NE	14	10N	5E	Sauk	0-225-70-2024	0.3	1.7	2.0	11.6	42.5	2.574	2.635	2.381		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
CHARLIE MILLER 55-56-005-QRY Created On: 01/09/15 Updated On:	Q			17	13N	2E	Sauk	0-225-53-2015		0.0	4.6	10.2	36.6	2.615	2.668	2.057		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
CHARLIE MILLER 55-56-005-QRY Created On: 01/03/18 Updated On:	Q			17	13N	2E	Sauk	0-225-13-2018	1.0	0.0	1.9	8.5	34.8	2.626	2.676	1.939		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
CHARLIE MILLER 55-56-005-QRY Created On: 01/04/21 Updated On:	Q			17	13N	2E	Sauk	0-225-24-2021	1.2	0.0	1.7	7.6	32.3	2.626	2.681	2.083		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
SAUK -- WI																	
CHARLIE MILLER 55-56-005-QRY Created On: 01/02/24 Updated On:	Q			17	13N	2E	Sauk	0-225-123-2024	2.4	6.3	1.5	10.7	38.5	2.599	2.656	2.198	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
FOX RIDGE 55-56-008-PIT Created On: 04/29/25 Updated On:	P		NE	22	12N	6E	Sauk	0-225-199-2025	0.4	0.7	2.2	8.5	28.7	2.662	2.692	1.132	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
HILLPOINT 55-56-010-QRY Created On: 05/14/15 Updated On:	Q		SW	22	11N	3E	Sauk	0-225-175-2015	0.3	1.2	2.5	10.5	41.7	2.629	2.682	2.011	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
HILLPOINT 55-56-010-QRY Created On: 04/10/18 Updated On:	Q		SW	22	11N	3E	Sauk	0-225-158-2018	0.3	0.0	7.6	12.1	44.8	2.609	2.670	2.362	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
HILLPOINT 55-56-010-QRY Created On: 01/29/24 Updated On:	Q		SW	22	11N	3E	Sauk	0-225-152-2024	0.9	7.9	10.9	13.2	45.9	2.575	2.644	2.665	
	Approved Use : HMA<MT, CONCRETE, OGBC, Base Aggregate																
HWY 154 QUARRY 55-56-034-QRY Created On: 05/04/21 Updated On:	Q	SW	SW	30	11N	3E	Sauk	0-225-200-2021	3.1	9.8	4.1	11.7	41.4	2.606	2.657	1.943	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
HWY 154 QUARRY 55-56-034-QRY Created On: 03/12/25 Updated On:	Q	SW	SW	30	11N	3E	Sauk	0-225-172-2025	3.2	6.5	5.2	9.3	37.2	2.599	2.667	2.615	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
SAUK -- WI																		
JACKSON 55-56-011-QRY Created On: 01/09/15 Updated On:	Q	SW	SW	6	10N	4E	Sauk	0-225-54-2015		0.0	4.0	11.9	40.5	2.561	2.632	2.764		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
JACKSON 55-56-011-QRY Created On: 01/03/18 Updated On:	Q	SW	SW	6	10N	4E	Sauk	0-225-9-2018	1.0	0.0	2.1	8.8	33.8	2.610	2.668	2.230		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
JACKSON 55-56-011-QRY Created On: 01/04/21 Updated On:	Q	SW	SW	6	10N	4E	Sauk	0-225-34-2021	0.5	0.0	0.4	7.9	32.5	2.635	2.685	1.882		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
JACKSON 55-56-011-QRY Created On: 01/29/24 Updated On:	Q	SW	SW	6	10N	4E	Sauk	0-225-153-2024	1.5	5.1	7.7	11.8	42.9	2.577	2.643	2.571		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
KLINGAMEYER-LARUE 55-56-015-QRY Created On: 08/16/16 Updated On:	Q		NW	22	11N	5E	Sauk	0-225-245-2016		0.0	0.2	5.5	24.1	2.619	2.632	0.495		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
KLINGAMEYER-LARUE 55-56-015-QRY Created On: 04/06/21 Updated On:	Q		NW	22	11N	5E	Sauk	0-225-170-2021	1.3	0.4	0.5	6.5	26.6	2.599	2.621	0.843		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
KLINGAMEYER-LARUE 55-56-015-QRY Created On: 01/02/24 Updated On:	Q		NW	22	11N	5E	Sauk	0-225-69-2024	0.5	0.2	0.4	6.0	23.8	2.603	2.627	0.914		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
SAUK -- WI																		
*LEATHERBERRY 55-56-017-PIT Created On: 01/08/20 Updated On:	P	E	NW	26	12N	6E	Sauk	0-225-66-2020		0.0	2.1	8.8	29.4	2.649	2.681	1.198		
Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																		
LINS 55-56-019-QRY Created On: 09/21/15 Updated On:	Q	NW	NE	22	9N	3E	Sauk	0-225-238-2015	3.5	2.7	5.9	10.6	40.5	2.568	2.643	2.897		
Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																		
LINS 55-56-019-QRY Created On: 07/24/18 Updated On:	Q	NW	NE	22	9N	3E	Sauk	0-225-257-2018	2.7	3.8	6.5	9.9	38.5	2.587	2.656	2.656		
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
LINS 55-56-019-QRY Created On: 04/07/21 Updated On:	Q	NW	NE	22	9N	3E	Sauk	0-225-173-2021	2.6	8.3	7.1	8.5	35.6	2.600	2.665	2.493		
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
LINS 55-56-019-QRY Created On: 03/27/24 Updated On:	Q	NW	NE	22	9N	3E	Sauk	0-225-210-2024	1.3	5.8	5.6	8.1	30.0	2.601	2.660	2.259		
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
*MATOUSHEK 55-56-021-QRY Created On: 05/11/17 Updated On:	Q			28	10N	6E	Sauk	0-225-185-2017		0.0	4.1	10.7	37.6	2.598	2.661	2.459		
Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																		
*MATOUSHEK 55-56-021-QRY Created On: 01/06/20 Updated On:	Q			28	10N	6E	Sauk	0-225-25-2020	0.9	0.0	0.2	8.5	33.6	2.619	2.677	2.204		
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
SAUK -- WI																	
MYKLEBUST 55-56-023-PIT Created On: 01/03/18 Updated On:	P		NE	26	13N	6E	Sauk	0-225-7-2018	1.5	0.0	1.5	6.5	26.3	2.720	2.753	1.219	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
MYKLEBUST 55-56-023-PIT Created On: 04/17/23 Updated On:	P		NE	26	13N	6E	Sauk	0-225-199-2023	0.4	0.0	2.6	5.4	24.8	2.697	2.720	0.856	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
ROCK SPRINGS 55-56-024-QRY Created On: 04/17/15 Updated On:	Q		SW	28	12N	5E	Sauk	0-225-127-2015		0.0	0.1	4.0	19.4	2.641	2.649	0.302	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
ROCK SPRINGS 55-56-024-QRY Created On: 02/09/18 Updated On:	Q		SW	28	12N	5E	Sauk	0-225-95-2018	0.2	0.0	0.4	5.6	23.8	2.650	2.658	0.313	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
ROCK SPRINGS 55-56-024-QRY Created On: 01/05/21 Updated On:	Q		SW	28	12N	5E	Sauk	0-225-62-2021	0.1	0.2	0.4	5.1	22.2	2.656	2.666	0.351	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
ROCK SPRINGS 55-56-024-QRY Created On: 01/02/24 Updated On:	Q		SW	28	12N	5E	Sauk	0-225-124-2024	0.0	0.5	0.3	5.2	22.5	2.657	2.664	0.273	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
SCHUCKNECHT 55-56-026-QRY Created On: 01/03/18 Updated On:	Q	SW	SW	25	9N	4E	Sauk	0-225-10-2018	0.1	0.0	1.2	8.1	31.4	2.644	2.696	1.973	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
SAUK -- WI																		
SCHUCKNECHT 55-56-026-QRY Created On: 01/04/21 Updated On:	Q	SW	SW	25	9N	4E	Sauk	0-225-32-2021	0.5	0.0	0.4	8.9	33.1	2.635	2.690	2.091		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
SCHUCKNECHT 55-56-026-QRY Created On: 01/02/24 Updated On:	Q	SW	SW	25	9N	4E	Sauk	0-225-21-2024	0.4	7.3	1.5	8.8	33.0	2.653	2.703	1.892		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
ZOBEL 55-56-031-QRY Created On: 06/05/15 Updated On:	Q			21	12N	4E	Sauk	0-225-188-2015		0.0	1.5	10.3	36.7	2.620	2.673	2.006		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
ZOBEL 55-56-031-QRY Created On: 01/04/18 Updated On:	Q			21	12N	4E	Sauk	0-225-51-2018	0.4	0.0	1.7	9.1	35.2	2.631	2.682	1.951		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
ZOBEL 55-56-031-QRY Created On: 01/04/21 Updated On:	Q			21	12N	4E	Sauk	0-225-33-2021	0.6	0.0	0.6	11.4	39.0	2.584	2.644	2.334		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
ZOBEL 55-56-031-QRY Created On: 01/02/24 Updated On:	Q			21	12N	4E	Sauk	0-225-22-2024	0.7	12.9	1.4	8.6	33.4	2.653	2.699	1.758		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
SAWYER -- WI																		
MROTEK 55-57-013-PIT Created On: 01/03/18 Updated On:	P		SW	1	41N	8W	Sawyer	0-225-16-2018	0.8	0.0	2.2	3.6	15.8	2.810	2.837	0.969		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
SAWYER -- WI																		
MROTEK 55-57-013-PIT Created On: 01/03/23 Updated On:	P		SW	1	41N	8W	Sawyer	0-225-57-2023	1.9	1.5	1.1	3.8	16.1	2.769	2.800	1.122		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
OLSON 55-57-017-PIT Created On: 02/13/17 Updated On:	P	NW	SW	14	41N	9W	Sawyer	0-225-71-2017		0.0	4.6	3.1	15.6	2.815	2.840	0.882		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
OLSON 55-57-017-PIT Created On: 01/10/22 Updated On:	P	NW	SW	14	41N	9W	Sawyer	0-225-105-2022	1.7	3.7	4.9	3.6	16.3	2.778	2.808	1.089		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
POINT SPORT 55-57-020-PIT Created On: 01/03/18 Updated On:	P		NE	2	41N	7W	Sawyer	0-225-19-2018	0.9	0.0	1.5	4.1	18.3	2.763	2.788	0.877		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
POINT SPORT 55-57-020-PIT Created On: 01/03/23 Updated On:	P		NE	2	41N	7W	Sawyer	0-225-58-2023	0.2	0.9	1.5	3.5	16.4	2.756	2.787	1.133		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
SAND LAKE 55-57-023-PIT Created On: 01/25/16 Updated On:	P	NW	NW	15	38N	9W	Sawyer	0-225-78-2016		0.0	1.6	4.2	17.0	2.787	2.816	1.030		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
SAND LAKE 55-57-023-PIT Created On: 05/23/23 Updated On:	P	NW	NW	15	38N	9W	Sawyer	0-225-226-2023	1.4	0.0	0.8	4.5	19.6	2.750	2.773	0.843		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
SAWYER -- WI																		
SKILLE V 55-57-025-PIT Created On: 05/02/19 Updated On:	P	NW	NE	33	40N	9W	Sawyer	0-225-175-2019	1.1	0.0	1.8	3.4	15.3	2.836	2.858	0.787		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
SKILLE V 55-57-025-PIT Created On: 01/04/24 Updated On:	P	NW	NE	33	40N	9W	Sawyer	0-225-140-2024	1.9	4.4	2.5	4.2	18.1	2.776	2.811	1.259		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
THOMPSON 55-57-027-PIT Created On: 01/02/25 Updated On:	P	NW	SW	12	41N	8W	Sawyer	0-225-40-2025	0.2	1.5	1.6	3.7	17.6	2.736	2.763	0.992		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
SHAWANO -- WI																		
BONDUEL 55-58-002-QRY Created On: 01/20/16 Updated On:	Q		NE	29	25N	17E	Shawano	0-225-60-2016		1.1	0.9	7.2	30.9	2.719	2.749	1.102		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
BONDUEL 55-58-002-QRY Created On: 01/04/19 Updated On:	Q		NE	29	25N	17E	Shawano	0-225-14-2019		4.3	0.7	6.3	31.0	2.721	2.752	1.162		
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																	
BONDUEL 55-58-002-QRY Created On: 01/04/22 Updated On:	Q		NE	29	25N	17E	Shawano	0-225-35-2022	0.0	2.9	1.8	6.3	28.3	2.717	2.747	1.083		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
BONDUEL 55-58-002-QRY Created On: 01/02/25 Updated On:	Q		NE	29	25N	17E	Shawano	0-225-55-2025	0.0	1.5	1.2	6.2	27.4	2.738	2.765	0.955		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
SHAWANO -- WI																	
GRUNEWALD 55-58-009-QRY Created On: 05/10/18 Updated On:	Q			33	27N	17E	Shawano	0-225-206-2018	0.0	6.2	3.4	7.8	32.4	2.715	2.753	1.389	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
GRUNEWALD 55-58-009-QRY Created On: 04/30/21 Updated On:	Q			33	27N	17E	Shawano	0-225-198-2021	0.9	2.3	6.4	8.1	34.6	2.687	2.733	1.703	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
GRUNEWALD 55-58-009-QRY Created On: 01/02/24 Updated On:	Q			33	27N	17E	Shawano	0-225-68-2024	0.0	3.9	3.7	8.2	35.1	2.676	2.719	1.606	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
KROENING 55-58-014-QRY Created On: 01/07/15 Updated On:	Q			24	26N	17E	Shawano	0-225-16-2015		11.1	12.8	7.5	28.7	2.674	2.721	1.762	
	Approved Use : Base Aggregate																
KROENING 55-58-014-QRY Created On: 01/04/18 Updated On:	Q			24	26N	17E	Shawano	0-225-58-2018	0.6	11.6	15.2	8.8	32.3	2.640	2.696	2.126	
	Approved Use : Base Aggregate																
KROENING 55-58-014-QRY Created On: 01/04/19 Updated On:	Q			24	26N	17E	Shawano	0-225-38-2019	1.4	20.7	15.4	7.2	28.0	2.638	2.698	2.278	
KROENING 55-58-014-QRY Created On: 01/02/20 Updated On:	Q			24	26N	17E	Shawano	0-225-10-2020	1.6	14.3	13.1	7.0	28.2	2.662	2.713	1.937	
	Approved Use : Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
SHAWANO -- WI																	
KROENING 55-58-014-QRY Created On: 01/03/23 Updated On:	Q			24	26N	17E	Shawano	0-225-78-2023	1.8	8.0	7.0	6.0	25.7	2.715	2.748	1.198	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
*MCKEEFRY 55-58-021-QRY Created On: 03/30/15 Updated On:	Q		NW	23	25N	18E	Shawano	0-225-106-2015	0.9	2.2	2.2	4.9	21.5	2.776	2.796	0.723	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
*MCKEEFRY 55-58-021-QRY Created On: 02/16/16 Updated On:	Q		NW	23	25N	18E	Shawano	0-225-85-2016	0.1	2.4	0.4	5.2	22.6	2.765	2.786	0.749	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
*MCKEEFRY 55-58-021-QRY Created On: 05/24/19 Updated On:	Q		NW	23	25N	18E	Shawano	0-225-196-2019	0.7	9.6	3.1	5.7	25.1	2.746	2.773	1.014	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
*MCKEEFRY 55-58-021-QRY Created On: 05/17/22 Updated On:	Q		NW	23	25N	18E	Shawano	0-225-207-2022	0.3	7.7	0.6	6.2	30.0	2.747	2.772	0.921	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
MCKEEFRY #3 55-58-049-QRY Created On: 10/19/17 Updated On:	Q	N	SW	14	25N	18E	Shawano	0-225-282-2017	0.2	5.2	2.7	6.1	25.7	2.748	2.779	1.112	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
MCKEEFRY #3 55-58-049-QRY Created On: 04/08/20 Updated On:	Q	N	SW	14	25N	18E	Shawano	0-225-145-2020	0.5	2.2	3.4	5.5	23.9	2.767	2.790	0.861	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
SHAWANO -- WI																		
MCKEEFRY #3 55-58-049-QRY Created On: 06/12/23 Updated On:	Q	N	SW	14	25N	18E	Shawano	0-225-228-2023		0.0	17.0	10.1	4.8	30.4	2.703	2.743	1.501	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
PETERS-BONDUEL 55-58-050-PIT Created On: 01/06/21 Updated On:	P	NW	NE	30	26N	17E	Shawano	0-225-110-2021		3.4	4.9	4.9	9.7	35.2	2.645	2.694	1.844	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
SHAWANO 55-58-036-QRY Created On: 05/11/15 Updated On:	Q	NE	NW	2	26N	16E	Shawano	0-225-164-2015		0.4	3.1	2.5	8.8	33.8	2.684	2.727	1.613	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
SHAWANO 55-58-036-QRY Created On: 01/04/18 Updated On:	Q	NE	NW	2	26N	16E	Shawano	0-225-61-2018			2.4	2.3	6.7	30.8	2.700	2.734	1.259	
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																	
SHAWANO 55-58-036-QRY Created On: 01/04/21 Updated On:	Q	NE	NW	2	26N	16E	Shawano	0-225-11-2021		0.2	4.1	3.1	5.3	26.5	2.699	2.737	1.410	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
SHAWANO 55-58-036-QRY Created On: 01/02/24 Updated On:	Q	NE	NW	2	26N	16E	Shawano	0-225-8-2024		0.0	2.3	0.3	5.7	26.9	2.722	2.754	1.151	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
TINCHERS QUARRY 55-58-038-QRY Created On: 06/25/24 Updated On:	Q	NE	NE	11	26N	16E	Shawano	0-225-278-2024		0.1	3.0	3.1	7.7	33.6	2.690	2.730	1.481	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

Date Printed: 08/06/2025

* = Not Certified
Source Name

SHAWANO -- WI

ZEINERT	P	SE	SW	3	28N	12E	Shawano	0-225-16-2021	0.3	1.4	2.1	9.6	34.0	2.641	2.665	0.920
55-58-045-PIT	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC,															
Created On: 01/04/21	Base Aggregate															
Updated On:																

BADGERLAND BISON	P	SW	NE	19	15N	20E	Sheboygan	0-225-5-2016	2.0	0.7	0.9	5.9	29.2	2.744	2.770	0.961
55-59-003-PIT	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC,															
Created On: 01/04/16	Base Aggregate															
Updated On:																

BADGERLAND BISON	P	SW	NE	19	15N	20E	Sheboygan	0-225-132-2021	2.0	2.8	2.8	6.5	31.6	2.735	2.765	1.079
55-59-003-PIT	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC,															
Created On: 03/10/21	Base Aggregate															
Updated On:																

BATES RD PIT	P	E	SE	33	14N	21E	Sheboygan	0-225-129-2022	0.1	2.5	3.2	10.0	38.5	2.715	2.749	1.239
55-59-024-PIT	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC,															
Created On: 02/17/22	Base Aggregate															
Updated On:																

DIPPEL	P	NE	SE	32	15N	20E	Sheboygan	0-225-100-2018	1.8	1.3	6.6	30.2	2.728	2.760	1.155
55-59-005-PIT	Approved Use : HMA<MT, HMA>=MT, OGBC, Base														
Created On: 02/15/18	Aggregate														
Updated On:															

DIPPEL	P	NE	SE	32	15N	20E	Sheboygan	0-225-47-2023	1.4	0.0	0.7	7.2	32.5	2.720	2.754	1.254
55-59-005-PIT	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC,															
Created On: 01/03/23	Base Aggregate															
Updated On:																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
SHEBOYGAN -- WI																		
KRAEMER 55-59-008-PIT Created On: 01/21/16 Updated On:	P	SW	NE	13	14N	20E	Sheboygan	0-225-64-2016	0.5	0.0	0.8	6.0	28.8	2.752	2.778	0.927		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
KRAEMER 55-59-008-PIT Created On: 01/05/21 Updated On:	P	SW	NE	13	14N	20E	Sheboygan	0-225-108-2021	0.5	2.2	0.7	5.6	26.9	2.740	2.767	0.981		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MICHEL'S BEECHWOOD 55-59-023-PIT Created On: 01/05/21 Updated On:	P	W	NE	4	13N	20E	Sheboygan	0-225-85-2021	0.6	0.0	3.7	9.5	35.9	2.715	2.753	1.391		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
ST. CROIX -- WI																		
DOWNING (RIEMANN) 55-55-004-QRY Created On: 06/20/22 Updated On:	Q	E	SE	1	29N	15W	St. Croix	0-225-231-2022	2.2	1.2	5.8	11.2	46.6	2.542	2.623	3.188		
	Approved Use : HMA<MT, CONCRETE, OGBC, Base Aggregate																	
DOWNING (RIEMANN) 55-55-004-QRY Created On: 01/02/25 Updated On:	Q	E	SE	1	29N	15W	St. Croix	0-225-35-2025		3.5	9.9	24.2	67.3	2.417	2.532	4.755		
DOWNING (RIEMANN) 55-55-004-QRY Created On: 06/12/25 Updated On:	Q	E	SE	1	29N	15W	St. Croix	0-225-223-2025	1.9	1.1	4.1	9.5	39.2	2.601	2.666	2.506		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
GILLEN 55-55-006-QRY Created On: 04/06/17 Updated On:	Q	E	NW	10	30N	17W	St. Croix	0-225-117-2017		0.0	1.1	10.9	39.7	2.605	2.666	2.322		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
ST. CROIX -- WI																		
GILLEN 55-55-006-QRY Created On: 01/08/20 Updated On:	Q	E	NW	10	30N	17W	St. Croix	0-225-54-2020	1.6	0.0	17.0	12.5	42.2	2.599	2.663	2.479		
Approved Use : Base Aggregate																		
GILLEN 55-55-006-QRY Created On: 01/03/23 Updated On:	Q	E	NW	10	30N	17W	St. Croix	0-225-54-2023	0.5	0.0	10.4	11.7	39.3	2.579	2.656	2.966		
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
MCNAMARA 55-55-007-QRY Created On: 04/21/17 Updated On:	Q	SE	NW	25	31N	15W	St. Croix	0-225-145-2017		0.0	5.2	10.4	38.0	2.558	2.633	2.956		
Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																		
MCNAMARA 55-55-007-QRY Created On: 01/06/20 Updated On:	Q	SE	NW	25	31N	15W	St. Croix	0-225-27-2020	1.8	0.0	7.5	10.2	34.7	2.533	2.620	3.440		
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
MCNAMARA 55-55-007-QRY Created On: 04/05/23 Updated On:	Q	SE	NW	25	31N	15W	St. Croix	0-225-187-2023	6.2	0.0	10.0	11.8	40.8	2.511	2.598	3.462		
Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																		
MIMBACH 55-55-008-QRY Created On: 01/08/15 Updated On:	Q	SW	NW	5	28N	19W	St. Croix	0-225-38-2015		0.0	6.4	7.6	29.5	2.694	2.735	1.497		
Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																		
MIMBACH 55-55-008-QRY Created On: 04/21/17 Updated On:	Q	SW	NW	5	28N	19W	St. Croix	0-225-140-2017	0.1	0.0	2.7	6.7	28.5	2.675	2.720	1.702		
Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																		

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
ST. CROIX -- WI																		
MIMBACH 55-55-008-QRY Created On: 01/08/20 Updated On:	Q	SW	NW	5	28N	19W	St. Croix	0-225-60-2020	2.2	0.0	8.1	10.0	37.8	2.562	2.639	2.990		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MIMBACH 55-55-008-QRY Created On: 01/03/23 Updated On:	Q	SW	NW	5	28N	19W	St. Croix	0-225-55-2023	0.7	7.7	12.4	13.9	44.8	2.559	2.642	3.214		
	Approved Use : CONCRETE, OGBC, Base Aggregate																	
MIMBACH 55-55-008-QRY Created On: 03/01/23 Updated On:	Q	SW	NW	5	28N	19W	St. Croix	0-225-161-2023	0.3	2.6	2.3	8.2	32.7	2.643	2.700	2.160		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
RIVARD 55-55-012-QRY Created On: 01/12/15 Updated On:	Q	SE	NE	12	30N	20W	St. Croix	0-225-63-2015		0.0	10.9	12.2	39.7	2.522	2.611	3.564		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
RIVARD 55-55-012-QRY Created On: 01/03/18 Updated On:	Q	SE	NE	12	30N	20W	St. Croix	0-225-33-2018	1.2	0.0	4.1	9.9	35.4	2.562	2.639	3.018		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
RIVARD 55-55-012-QRY Created On: 01/05/21 Updated On:	Q	SE	NE	12	30N	20W	St. Croix	0-225-74-2021	1.4	0.0	0.8	7.8	33.9	2.535	2.605	2.738		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
RIVARD 55-55-012-QRY Created On: 01/02/24 Updated On:	Q	SE	NE	12	30N	20W	St. Croix	0-225-78-2024	2.2	5.6	5.1	8.7	29.9	2.607	2.665	2.246		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
ST. CROIX -- WI																		
TAMMEC PIT 55-55-016-PIT Created On: 01/05/17 Updated On:	P		SW	16	30N	18W	St. Croix	0-225-45-2017		0.0	3.0	3.6	19.1	2.702	2.735	1.207		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
TAMMEC PIT 55-55-016-PIT Created On: 01/04/22 Updated On:	P		SW	16	30N	18W	St. Croix	0-225-78-2022	3.0	4.1	5.0	4.5	20.3	2.678	2.716	1.393		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
TAMMEC QUARRY 55-55-017-QRY Created On: 01/08/15 Updated On:	Q		SW	16	30N	18W	St. Croix	0-225-39-2015	4.9	0.0	10.3	12.2	41.8	2.497	2.579	3.319		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
TAMMEC QUARRY 55-55-017-QRY Created On: 04/21/17 Updated On:	Q		SW	16	30N	18W	St. Croix	0-225-144-2017	2.8	0.0	6.7	9.2	35.1	2.562	2.626	2.475		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
TAMMEC QUARRY 55-55-017-QRY Created On: 05/04/20 Updated On:	Q		SW	16	30N	18W	St. Croix	0-225-165-2020	2.6	0.0	7.1	9.5	37.0	2.572	2.644	2.800		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
TAMMEC QUARRY 55-55-017-QRY Created On: 01/03/23 Updated On:	Q		SW	16	30N	18W	St. Croix	0-225-53-2023	9.1	14.4	4.2	12.0	43.2	2.481	2.564	3.359		
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																	
UTECHT 55-55-018-PIT Created On: 01/12/15 Updated On:	P	NE	NE	21	30N	18W	St. Croix	0-225-62-2015		0.0	4.1	5.5	22.4	2.644	2.683	1.496		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
ST. CROIX -- WI																		
UTECHT 55-55-018-PIT Created On: 01/30/20 Updated On:	P	NE	NE	21	30N	18W	St. Croix	0-225-102-2020	1.1	0.0	5.5	6.0	24.8	2.634	2.678	1.662		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
UTECHT 55-55-018-PIT Created On: 02/20/25 Updated On:	P	NE	NE	21	30N	18W	St. Croix	0-225-153-2025	2.7	0.0	4.8	6.8	26.8	2.631	2.673	1.591		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
TAYLOR -- WI																		
BROOKS 55-60-003-PIT Created On: 08/08/17 Updated On:	P	SW	SE	7	33N	3W	Taylor	0-225-247-2017		0.0	2.2	5.3	21.5	2.734	2.765	1.125		
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																	
BROOKS 55-60-003-PIT Created On: 01/04/22 Updated On:	P	SW	SE	7	33N	3W	Taylor	0-225-81-2022	1.1	0.0	3.8	3.9	19.8	2.697	2.731	1.242		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
CHELSEA 55-60-036-PIT Created On: 01/02/24 Updated On:	P	N	SE	10	32N	1E	Taylor	0-225-114-2024	0.5	0.0	3.4	3.1	17.2	2.688	2.716	1.029		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
DUESSING 55-60-007-PIT Created On: 06/26/17 Updated On:	P	N	SW	33	32N	1E	Taylor	0-225-221-2017		0.0	0.6	3.5	17.4	2.743	2.769	0.947		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
DUESSING 55-60-007-PIT Created On: 06/28/22 Updated On:	P	N	SW	33	32N	1E	Taylor	0-225-238-2022	0.7	0.0	2.0	4.1	18.4	2.742	2.768	0.948		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
TAYLOR -- WI																		
FOSTERS 55-60-008-PIT Created On: 07/07/22 Updated On:	P	NW	SE	20	33N	3W	Taylor	0-225-244-2022	1.9	0.0	3.3	4.5	21.1	2.711	2.739	1.036		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
GOSBEE 55-60-009-PIT Created On: 06/26/17 Updated On:	P	SE	NE	28	32N	1E	Taylor	0-225-219-2017		0.0	0.6	4.2	19.4	2.697	2.733	1.354		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
GOSBEE 55-60-009-PIT Created On: 06/28/22 Updated On:	P	SE	NE	28	32N	1E	Taylor	0-225-242-2022	0.6	0.0	2.7	4.1	18.0	2.728	2.753	0.921		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
HAAS EMSTROM PIT 55-60-035-PIT Created On: 07/27/23 Updated On:	P	NE	NW	3	31N	2W	Taylor	0-225-243-2023	1.8	0.0	1.5	4.5	21.2	2.742	2.762	0.718		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
*JUMP RIVER 55-60-015-QRY Created On: 07/07/22 Updated On:	Q	NE	SE	14	33N	4W	Taylor	0-225-247-2022	0.0	0.0	0.5	4.7	21.6	2.662	2.676	0.519		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
JUMP RIVER PIT 55-60-037-PIT Created On: 01/02/24 Updated On:	P	SW	NE	13	33N	4W	Taylor	0-225-115-2024	0.2	0.0	5.5	4.3	19.9	2.732	2.770	1.387		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
KRUG 55-60-012-PIT Created On: 05/24/19 Updated On:	P			28	32N	1E	Taylor	0-225-201-2019	0.1	0.0	1.7	3.9	17.5	2.723	2.750	0.972		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
TAYLOR -- WI																		
KRUG 55-60-012-PIT Created On: 01/02/24 Updated On:	P			28	32N	1E	Taylor	0-225-112-2024	0.1	0.0	4.2	3.8	17.9	2.717	2.751	1.222		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
LARSON 55-60-013-PIT Created On: 10/28/16 Updated On:	P	SE	SW	13	33N	1E	Taylor	0-225-272-2016		0.0	2.2	4.1	18.9	2.727	2.759	1.162		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
LARSON 55-60-013-PIT Created On: 09/30/24 Updated On:	P	SE	SW	13	33N	1E	Taylor	0-225-312-2024	0.1	0.0	1.7	4.1	19.5	2.700	2.736	1.319		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
LISSNER 55-60-014-PIT Created On: 01/09/15 Updated On:	P		SW	27	32N	1E	Taylor	0-225-46-2015		0.0	2.7	3.7	17.7	2.718	2.749	1.133		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
LISSNER 55-60-014-PIT Created On: 01/08/20 Updated On:	P		SW	27	32N	1E	Taylor	0-225-48-2020	1.0	0.0	2.6	4.2	18.8	2.760	2.781	0.771		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
LISSNER 55-60-014-PIT Created On: 01/02/25 Updated On:	P		SW	27	32N	1E	Taylor	0-225-69-2025	0.5	0.0	2.5	3.6	18.5	2.736	2.754	0.680		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MAIN PIT 55-60-016-PIT Created On: 01/10/23 Updated On:	P	NE	SE	14	33N	4W	Taylor	0-225-114-2023	0.4	0.0	1.9	4.2	20.3	2.727	2.751	0.902		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
TAYLOR -- WI																		
MAIN QUARRY 55-60-039-QRY Created On: 01/16/25 Updated On:	Q	NE	SE	14	33N	4W	Taylor	0-225-138-2025	0.0	0.0	1.9	5.4	20.2	2.657	2.676	0.726		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MAYER 55-60-017-PIT Created On: 06/26/17 Updated On:	P	SE	SW	2	32N	1E	Taylor	0-225-218-2017		0.0	2.5	4.9	21.9	2.739	2.766	1.004		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MAYER 55-60-017-PIT Created On: 01/10/23 Updated On:	P	SE	SW	2	32N	1E	Taylor	0-225-112-2023	0.2	0.0	4.0	5.2	23.7	2.762	2.792	1.080		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
NEUMAN 55-60-018-PIT Created On: 06/26/17 Updated On:	P	NE	SE	28	32N	1E	Taylor	0-225-222-2017		0.0	0.6	3.5	17.8	2.729	2.758	1.052		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
NEUMAN 55-60-018-PIT Created On: 06/28/22 Updated On:	P	NE	SE	28	32N	1E	Taylor	0-225-239-2022	1.1	0.0	2.4	3.6	17.3	2.751	2.778	0.995		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
OVYN 55-60-020-QRY Created On: 02/14/17 Updated On:	Q	NE	SW	28	30N	2W	Taylor	0-225-72-2017		0.0	0.2	3.2	15.2	3.004	3.024	0.683		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
OVYN 55-60-030-PIT Created On: 02/14/17 Updated On:	P	NE	SW	28	30N	2W	Taylor	0-225-73-2017		0.0	1.4	4.2	20.3	2.659	2.700	1.526		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
TAYLOR -- WI																		
OVYN 55-60-030-PIT Created On: 04/22/21 Updated On:	P	NE	SW	28	30N	2W	Taylor	0-225-187-2021	2.3	0.0	2.8	5.0	20.9	2.671	2.704	1.199		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
OVYN 55-60-020-QRY Created On: 04/22/21 Updated On:	Q	NE	SW	28	30N	2W	Taylor	0-225-188-2021	0.0	0.0	0.3	3.8	16.9	2.865	2.878	0.436		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
OVYN 55-60-020-QRY Created On: 04/15/24 Updated On:	Q	NE	SW	28	30N	2W	Taylor	0-225-219-2024	0.0	0.0	0.3	3.8	17.2	2.825	2.842	0.615		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
SCHREINER 55-60-022-PIT Created On: 01/03/18 Updated On:	P		SE	1	32N	2E	Taylor	0-225-29-2018	0.5	0.0	1.5	4.1	18.3	2.710	2.733	0.825		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
SCHREINER 55-60-022-PIT Created On: 01/10/23 Updated On:	P		SE	1	32N	2E	Taylor	0-225-111-2023	2.1	0.0	2.1	4.1	19.8	2.659	2.688	1.086		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
*SHADY NOOK 55-60-032-QRY Created On: 01/05/17 Updated On:	Q	NW	SW	23	30N	2W	Taylor	0-225-17-2017		0.0	0.2	4.7	23.0	2.740	2.754	0.503		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
*SHADY NOOK 55-60-032-QRY Created On: 05/21/21 Updated On:	Q	NW	SW	23	30N	2W	Taylor	0-225-211-2021	0.0	0.0	0.3	4.8	21.9	2.735	2.747	0.467		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
TREMPEALEAU -- WI																		
ARCADIA 55-61-003-QRY Created On: 04/25/17 Updated On:	Q	NW	SE	16	20N	9W	Trempealeau	0-225-150-2017		0.0	2.3	12.5	43.4	2.536	2.613	3.068		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
ARCADIA 55-61-003-QRY Created On: 06/02/20 Updated On:	Q	NW	SE	16	20N	9W	Trempealeau	0-225-185-2020	0.8	0.0	4.5	8.6	37.7	2.554	2.635	3.170		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
ARCADIA 55-61-003-QRY Created On: 01/03/23 Updated On:	Q	NW	SE	16	20N	9W	Trempealeau	0-225-64-2023	1.8	0.8	3.6	10.6	42.9	2.548	2.614	2.607		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
BONDLEI 55-61-004-QRY Created On: 03/13/17 Updated On:	Q	NE	SW	20	20N	8W	Trempealeau	0-225-81-2017	0.5	0.0	4.5	8.8	34.8	2.612	2.668	2.142		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
BONDLEI 55-61-004-QRY Created On: 03/12/20 Updated On:	Q	NE	SW	20	20N	8W	Trempealeau	0-225-129-2020	0.0	0.0	9.4	12.7	40.5	2.544	2.623	3.084		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
BONDLEI 55-61-004-QRY Created On: 04/04/23 Updated On:	Q	NE	SW	20	20N	8W	Trempealeau	0-225-178-2023	0.0	0.0	5.5	8.4	34.2	2.595	2.658	2.396		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
HAEF 55-61-007-PIT Created On: 03/28/17 Updated On:	P	SW	NE	19	18N	8W	Trempealeau	0-225-90-2017		0.0	0.3	4.3	19.1	2.630	2.664	1.291		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
TREMPEALEAU -- WI																		
HAEF 55-61-007-PIT Created On: 01/04/22 Updated On:	P	SW	NE	19	18N	8W	Trempealeau	0-225-50-2022		0.0	0.3	0.5	3.2	14.5	2.635	2.674	1.478	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
IRVINE 55-61-009-QRY Created On: 07/02/15 Updated On:	Q	SW	NE	18	19N	7W	Trempealeau	0-225-205-2015			0.0	2.5	10.4	38.3	2.591	2.648	2.208	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
IRVINE 55-61-009-QRY Created On: 01/04/18 Updated On:	Q	SW	NE	18	19N	7W	Trempealeau	0-225-48-2018		0.7	0.0	5.8	9.3	36.2	2.603	2.667	2.483	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
IRVINE 55-61-009-QRY Created On: 01/04/21 Updated On:	Q	SW	NE	18	19N	7W	Trempealeau	0-225-4-2021		1.3	0.0	2.8	9.6	35.9	2.610	2.666	2.135	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
IRVINE 55-61-009-QRY Created On: 01/02/24 Updated On:	Q	SW	NE	18	19N	7W	Trempealeau	0-225-24-2024		0.6	7.8	10.6	13.5	46.5	2.572	2.645	2.820	
	Approved Use : CONCRETE, OGBC, Base Aggregate																	
TWESME 55-61-020-QRY Created On: 01/30/15 Updated On:	Q	SW	SE	34	21N	8W	Trempealeau	0-225-83-2015			0.0	7.1	12.1	41.4	2.590	2.651	2.378	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
TWESME 55-61-020-QRY Created On: 01/04/18 Updated On:	Q	SW	SE	34	21N	8W	Trempealeau	0-225-45-2018		1.4	0.0	6.0	13.1	42.2	2.578	2.646	2.646	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
TREMPEALEAU -- WI																		
TWESME	Q	SW	SE	34	21N	8W	Trempealeau	0-225-35-2021		1.2	0.0	2.7	10.4	38.7	2.586	2.650	2.496	
55-61-020-QRY	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC,																	
Created On: 01/04/21	Base Aggregate																	
Updated On:																		
TWESME	Q	SW	SE	34	21N	8W	Trempealeau	0-225-120-2024		0.7	6.4	8.8	11.6	40.6	2.584	2.652	2.624	
55-61-020-QRY	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC,																	
Created On: 01/02/24	Base Aggregate																	
Updated On:																		
VERNON -- WI																		
*BAKKESTUEN / COON VALLEY	Q	NW	NW	22	14N	5W	Vernon	0-225-211-2017			0.0	1.7	9.7	36.4	2.646	2.694	1.843	
55-62-002-PIT	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC,																	
Created On: 06/12/17	Base Aggregate																	
Updated On:																		
*BAKKESTUEN / COON VALLEY	Q	NW	NW	22	14N	5W	Vernon	0-225-107-2022		0.7	1.3	0.3	11.4	35.8	2.639	2.687	1.788	
55-62-002-PIT	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC,																	
Created On: 01/10/22	Base Aggregate																	
Updated On:																		
BROOKVILLE	Q			22	12N	4W	Vernon	0-225-184-2016			0.0	4.0	11.0	38.1	2.637	2.689	1.954	
55-62-004-QRY	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base																	
Created On: 05/19/16	Aggregate																	
Updated On:																		
BROOKVILLE	Q			22	12N	4W	Vernon	0-225-44-2018		0.4	0.0	2.1	9.8	37.3	2.636	2.685	1.861	
55-62-004-QRY	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base																	
Created On: 01/04/18	Aggregate																	
Updated On:																		
BROOKVILLE	Q			22	12N	4W	Vernon	0-225-63-2021		0.4	0.0	0.4	8.1	33.7	2.634	2.687	1.993	
55-62-004-QRY	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC,																	
Created On: 01/05/21	Base Aggregate																	
Updated On:																		

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
VERNON -- WI																	
BROOKVILLE 55-62-004-QRY Created On: 01/02/24 Updated On:	Q			22	12N	4W	Vernon	0-225-35-2024	1.7	0.8	5.1	11.6	42.3	2.617	2.677	2.278	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
BUGBEE QUARRY 55-62-035-QRY Created On: 02/28/24 Updated On:	Q	SE	SW	21	14N	1W	Vernon	0-225-191-2024	1.2	3.7	6.4	8.5	36.8	2.608	2.667	2.226	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
BURT(MUELLER) 55-62-005-QRY Created On: 05/18/17 Updated On:	Q	NW	SW	33	13N	2W	Vernon	0-225-190-2017		0.0	2.1	8.7	33.2	2.626	2.681	2.133	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
BURT(MUELLER) 55-62-005-QRY Created On: 01/08/20 Updated On:	Q	NW	SW	33	13N	2W	Vernon	0-225-65-2020	0.5	0.0	5.6	8.2	32.2	2.650	2.696	1.760	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
BURT(MUELLER) 55-62-005-QRY Created On: 01/30/23 Updated On:	Q	NW	SW	33	13N	2W	Vernon	0-225-134-2023	1.5	1.6	1.7	8.5	33.4	2.654	2.703	1.858	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
CLARK 55-62-006-QRY Created On: 05/19/16 Updated On:	Q	SE	SW	28	13N	1E	Vernon	0-225-181-2016	1.0	5.4	6.6	8.5	37.3	2.615	2.673	2.211	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
CLARK 55-62-006-QRY Created On: 07/25/19 Updated On:	Q	SE	SW	28	13N	1E	Vernon	0-225-251-2019	0.8	5.4	4.8	8.2	37.1	2.639	2.693	2.033	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
VERNON -- WI																		
CLARK 55-62-006-QRY Created On: 04/05/22 Updated On:	Q	SE	SW	28	13N	1E	Vernon	0-225-167-2022	0.7	9.7	6.6	8.3	36.1	2.625	2.683	2.213		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
CLARK 55-62-006-QRY Created On: 01/02/25 Updated On:	Q	SE	SW	28	13N	1E	Vernon	0-225-89-2025	0.5	8.4	8.4	8.9	37.2	2.630	2.683	2.021		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
CLOCKMAKER 55-62-007-QRY Created On: 01/05/17 Updated On:	Q	SE	NW	26	14N	4W	Vernon	0-225-31-2017		0.0	5.1	10.0	38.3	2.585	2.650	2.489		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
CLOCKMAKER 55-62-007-QRY Created On: 01/08/20 Updated On:	Q	SE	NW	26	14N	4W	Vernon	0-225-63-2020	0.6	0.0	1.5	7.6	33.1	2.644	2.692	1.815		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
CLOCKMAKER 55-62-007-QRY Created On: 01/03/23 Updated On:	Q	SE	NW	26	14N	4W	Vernon	0-225-68-2023	0.7	3.0	1.6	9.8	31.8	2.646	2.694	1.833		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
GUDGEON 55-62-012-QRY Created On: 01/09/20 Updated On:	Q	NW	NE	27	13N	4E	Vernon	0-225-84-2020	0.0	1.9	3.3	10.5	41.7	2.589	2.655	2.518		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
GUDGEON 55-62-012-QRY Created On: 01/10/23 Updated On:	Q	NW	NE	27	13N	4E	Vernon	0-225-107-2023	0.5	3.6	3.0	11.2	40.6	2.580	2.653	2.842		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
VERNON -- WI																		
*HOHFELD 55-62-015-QRY Created On: 02/03/20 Updated On:	Q	NE	NE	8	14N	6W	Vernon	0-225-109-2020	2.7	0.0	8.2	12.8	46.2	2.550	2.627	3.035		
	Approved Use : HMA<MT, CONCRETE, OGBC, Base Aggregate																	
LIBERTY 55-62-019-QRY Created On: 05/07/24 Updated On:	Q			15	12N	3W	Vernon	0-225-249-2024	0.5	3.2	3.0	12.6	45.3	2.593	2.660	2.583		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MILESTONE-THOMPSON F 55-62-030-QRY Created On: 05/04/17 Updated On:	Q	SE	SW	8	14N	1E	Vernon	0-225-171-2017		0.0	3.2	8.8	36.4	2.615	2.669	2.066		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
MILESTONE-THOMPSON F 55-62-030-QRY Created On: 01/03/20 Updated On:	Q	SE	SW	8	14N	1E	Vernon	0-225-24-2020	1.2	0.0	5.1	9.7	34.7	2.597	2.661	2.461		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
MILESTONE-THOMPSON F 55-62-030-QRY Created On: 01/03/23 Updated On:	Q	SE	SW	8	14N	1E	Vernon	0-225-30-2023	1.0	3.6	0.6	9.7	35.5	2.623	2.674	1.940		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MOLLETT 55-62-022-QRY Created On: 05/19/16 Updated On:	Q	NE	SE	4	12N	4W	Vernon	0-225-180-2016		0.0	4.6	9.4	35.5	2.636	2.686	1.903		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
MOLLETT 55-62-022-QRY Created On: 01/07/19 Updated On:	Q	NE	SE	4	12N	4W	Vernon	0-225-51-2019	0.5	0.0	2.0	8.1	33.7	2.632	2.683	1.931		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
VERNON -- WI																		
MOLLETT 55-62-022-QRY Created On: 01/10/22 Updated On:	Q	NE	SE	4	12N	4W	Vernon	0-225-101-2022	0.2	6.0	0.5	9.4	35.2	2.635	2.690	2.091		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MOLLETT 55-62-022-QRY Created On: 01/02/25 Updated On:	Q	NE	SE	4	12N	4W	Vernon	0-225-92-2025	0.5	2.1	0.4	9.7	36.0	2.631	2.688	2.147		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
PEDRETTI 55-62-028-QRY Created On: 01/09/15 Updated On:	Q	SW	NW	27	13N	7W	Vernon	0-225-51-2015		0.0	9.2	10.8	40.0	2.575	2.641	2.576		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
PEDRETTI 55-62-028-QRY Created On: 01/03/18 Updated On:	Q	SW	NW	27	13N	7W	Vernon	0-225-15-2018	0.5	0.0	2.1	8.5	32.3	2.594	2.659	2.520		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
PEDRETTI 55-62-028-QRY Created On: 01/04/21 Updated On:	Q	SW	NW	27	13N	7W	Vernon	0-225-25-2021	0.4	0.0	0.9	10.0	34.8	2.573	2.646	2.835		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
PEDRETTI 55-62-028-QRY Created On: 01/02/24 Updated On:	Q	SW	NW	27	13N	7W	Vernon	0-225-29-2024	2.1	9.0	11.7	13.4	45.6	2.538	2.619	3.220		
	Approved Use : HMA<MT, CONCRETE, OGBC, Base Aggregate																	
SEAS BRANCH 55-62-029-QRY Created On: 01/04/23 Updated On:	Q	NE	NW	15	13N	4W	Vernon	0-225-84-2023	0.5	1.5	2.4	9.6	33.9	2.681	2.720	1.471		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
VERNON -- WI																		
*VICTORY 55-62-034-QRY Created On: 08/22/22 Updated On:	Q	NE	NE	34	12N	7W	Vernon	0-225-254-2022	1.2	10.4	7.0	14.5	48.1	2.578	2.646	2.654		
Approved Use : CONCRETE, OGBC, Base Aggregate																		
ZOGG 55-62-033-QRY Created On: 07/02/15 Updated On:	Q	SW	SE	27	14N	7W	Vernon	0-225-206-2015		0.0	6.9	11.5	39.7	2.594	2.656	2.412		
Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																		
ZOGG 55-62-033-QRY Created On: 01/03/18 Updated On:	Q	SW	SE	27	14N	7W	Vernon	0-225-12-2018	1.0	0.0	3.8	9.9	35.4	2.605	2.667	2.408		
Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																		
ZOGG 55-62-033-QRY Created On: 01/04/21 Updated On:	Q	SW	SE	27	14N	7W	Vernon	0-225-29-2021	0.9	0.0	1.2	7.8	32.3	2.600	2.667	2.583		
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
ZOGG 55-62-033-QRY Created On: 01/02/24 Updated On:	Q	SW	SE	27	14N	7W	Vernon	0-225-38-2024	0.2	8.9	6.8	9.9	36.6	2.601	2.667	2.529		
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
VILAS -- WI																		
BIRCHWOOD 55-63-024-PIT Created On: 05/20/24 Updated On:	P	NW	NE	27	40N	8E	Vilas	0-225-253-2024	0.7	0.0	0.4	3.2	15.9	2.730	2.754	0.868		
Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																		
GATEWAY 55-63-023-PIT Created On: 07/18/19 Updated On:	P	SE	NE	11	42N	10E	Vilas	0-225-236-2019	0.3	0.0	0.6	3.5	16.4	2.744	2.763	0.689		
Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																		

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
VILAS -- WI																		
GATEWAY 55-63-023-PIT Created On: 01/02/24 Updated On:	P	SE	NE	11	42N	10E	Vilas	0-225-59-2024	0.7	0.0	0.5	3.9	18.0	2.727	2.749	0.824		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
*HARRY'S 55-63-006-PIT Created On: 05/08/15 Updated On:	P	SE	SE	14	40N	6E	Vilas	0-225-153-2015		0.0	0.5	4.4	20.0	2.692	2.717	0.937		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
*HARRY'S 55-63-006-PIT Created On: 01/08/20 Updated On:	P	SE	SE	14	40N	6E	Vilas	0-225-72-2020	0.8	0.0	0.9	3.4	16.6	2.702	2.728	0.958		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
HOLTAN 55-63-007-PIT Created On: 06/13/19 Updated On:	P	NW	NW	33	43N	8E	Vilas	0-225-220-2019	0.3	0.0	1.8	3.9	19.2	2.742	2.767	0.888		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
HOLTAN 55-63-007-PIT Created On: 01/03/23 Updated On:	P	NW	NW	33	43N	8E	Vilas	0-225-27-2023	1.5	0.0	1.0	4.6	20.4	2.720	2.756	1.307		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
NLC WOODRUFF 55-63-013-PIT Created On: 04/11/18 Updated On:	P	NW	SE	14	40N	6E	Vilas	0-225-169-2018	0.6	0.0	0.6	3.6	18.2	2.691	2.713	0.818		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
NLC WOODRUFF 55-63-013-PIT Created On: 01/03/23 Updated On:	P	NW	SE	14	40N	6E	Vilas	0-225-23-2023	1.2	0.0	1.0	4.5	20.2	2.701	2.722	0.812		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
VILAS -- WI																		
ROSS	P	NE	SW	28	41N	10E	Vilas	0-225-61-2024	1.6	0.0	2.1	4.7	20.5	2.670	2.702	1.179		
55-63-017-PIT	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
Created On: 01/02/24																		
Updated On:																		
VOLKMAN	P	S	NE	17	41N	12E	Vilas	0-225-237-2019	2.4	0.0	0.6	4.8	19.0	2.682	2.709	1.012		
55-63-022-PIT	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
Created On: 07/18/19																		
Updated On:																		
VOLKMAN	P	S	NE	17	41N	12E	Vilas	0-225-56-2024	0.8	0.0	0.3	4.2	18.4	2.701	2.729	1.041		
55-63-022-PIT	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
Created On: 01/02/24																		
Updated On:																		
WALWORTH -- WI																		
AMON / WILSON	P	NE	SE	25	3N	18E	Walworth	0-225-226-2017		0.0	0.9	7.4	37.2	2.669	2.708	1.467		
55-64-002-PIT	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
Created On: 06/30/17																		
Updated On:																		
AMON / WILSON	P	NE	SE	25	3N	18E	Walworth	0-225-169-2022	0.9	0.0	4.5	4.8	26.5	2.680	2.720	1.491		
55-64-002-PIT	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
Created On: 04/05/22																		
Updated On:																		
ATKINSON	P	NE	SW	6	3N	18E	Walworth	0-225-87-2019	4.6	4.2	0.7	5.1	26.3	2.681	2.717	1.342		
55-64-005-PIT	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
Created On: 01/18/19																		
Updated On:																		
ATKINSON	P	NE	SW	6	3N	18E	Walworth	0-225-15-2024	0.4	4.9	2.9	5.0	25.8	2.668	2.704	1.323		
55-64-005-PIT	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
Created On: 01/02/24																		
Updated On:																		

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
WALWORTH -- WI																		
BLOOMFIELD 55-64-008-PIT Created On: 01/18/19 Updated On:	P	E	SW	1	1N	19E	Walworth	0-225-86-2019	1.5	7.4	0.9	4.0	21.5	2.669	2.711	1.566		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
BLOOMFIELD 55-64-008-PIT Created On: 04/15/24 Updated On:	P	E	SW	1	1N	19E	Walworth	0-225-223-2024	4.3	17.4	0.1	4.4	24.1	2.164	2.201	1.737		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
COUNTRY SIDE WOODS 55-64-054-PIT Created On: 05/13/19 Updated On:	P		SW	20	3N	16E	Walworth	0-225-187-2019	1.7	2.8	0.8	6.3	26.9	2.649	2.689	1.508		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
COUNTRY SIDE WOODS 55-64-054-PIT Created On: 02/10/22 Updated On:	P		SW	20	3N	16E	Walworth	0-225-120-2022	3.3	6.8	1.6	5.1	26.1	2.676	2.714	1.430		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
DARIEN 55-64-055-PIT Created On: 06/25/21 Updated On:	P	W	NW	7	2N	15E	Walworth	0-225-234-2021	0.1	5.3	6.7	6.2	25.6	2.662	2.706	1.648		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
JOHNSON S&G BOWERS ROAD 55-64-015-PIT Created On: 04/24/19 Updated On:	P		NE	2	3N	17E	Walworth	0-225-159-2019	2.1	0.0	3.8	4.0	26.4	2.678	2.713	1.293		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
JOHNSON S&G BOWERS ROAD 55-64-015-PIT Created On: 03/27/24 Updated On:	P		NE	2	3N	17E	Walworth	0-225-214-2024	0.8	9.2	0.8	4.2	25.8	2.711	2.748	1.365		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
WALWORTH -- WI																		
LAGRANGE 55-64-024-PIT Created On: 02/05/19 Updated On:	P	W	SE	20	4N	16E	Walworth	0-225-94-2019	0.9	7.0	0.5	4.3	22.4	2.695	2.731	1.337		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
LAGRANGE 55-64-024-PIT Created On: 01/02/24 Updated On:	P	W	SE	20	4N	16E	Walworth	0-225-17-2024	0.0	4.5	2.9	4.8	23.2	2.705	2.738	1.224		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
ODLING 55-64-013-PIT Created On: 01/19/23 Updated On:	P	NW	SE	36	2N	16E	Walworth	0-225-123-2023	1.9	2.6	2.4	4.7	30.5	2.664	2.704	1.503		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
PADDOCK 55-64-028-PIT Created On: 04/10/18 Updated On:	P	E	SE	1	3N	16E	Walworth	0-225-161-2018	1.4	0.0	1.3	5.3	25.7	2.670	2.709	1.457		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
PADDOCK 55-64-028-PIT Created On: 05/14/21 Updated On:	P	E	SE	1	3N	16E	Walworth	0-225-208-2021	4.9	7.2	3.0	4.6	29.8	2.696	2.732	1.316		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
REESMAN CO. - BOLTON 55-64-020-PIT Created On: 02/16/18 Updated On:	P		SW	4	3N	18E	Walworth	0-225-106-2018	1.0	0.0	0.2	5.1	27.2	2.678	2.714	1.341		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
REESMAN CO. - BOLTON 55-64-020-PIT Created On: 01/19/23 Updated On:	P		SW	4	3N	18E	Walworth	0-225-126-2023	0.7	0.0	4.4	5.1	24.9	2.682	2.719	1.366		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
WALWORTH -- WI																		
RICHMOND 55-64-035-PIT Created On: 01/12/16 Updated On:	P	NW	NW	15	3N	15E	Walworth	0-225-58-2016	2.4	0.0	1.6	5.2	25.2	2.697	2.736	1.466		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
RICHMOND 55-64-035-PIT Created On: 01/04/21 Updated On:	P	NW	NW	15	3N	15E	Walworth	0-225-10-2021	0.4	3.4	2.3	5.3	26.2	2.696	2.731	1.293		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
SUPER AGGREGATE-SUGAR CREEK 55-64-037-PIT Created On: 02/11/19 Updated On:	P	SE	NW	9	3N	16E	Walworth	0-225-106-2019	3.0	0.0	7.0	3.9	24.2	2.651	2.692	1.527		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
SUPER AGGREGATE-SUGAR CREEK 55-64-037-PIT Created On: 04/15/24 Updated On:	P	SE	NW	9	3N	16E	Walworth	0-225-222-2024	2.1	9.3	1.0	4.6	25.2	2.670	2.706	1.367		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
THELEN-LANGE ROAD 55-64-025-PIT Created On: 06/25/15 Updated On:	P	SE	SE	32	1N	18E	Walworth	0-225-202-2015	1.0	0.0	1.1	5.7	33.5	2.674	2.713	1.439		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
THELEN-LANGE ROAD 55-64-025-PIT Created On: 05/09/18 Updated On:	P	SE	SE	32	1N	18E	Walworth	0-225-197-2018	0.3	10.4	0.9	5.5	25.8	2.699	2.737	1.421		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
THELEN-LANGE ROAD 55-64-025-PIT Created On: 01/03/23 Updated On:	P	SE	SE	32	1N	18E	Walworth	0-225-49-2023	0.7	14.4	6.6	5.9	28.4	2.671	2.704	1.241		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
WALWORTH -- WI																		
WHELAN 55-64-039-PIT Created On: 03/24/16 Updated On:	P	SE	NE	1	1N	15E	Walworth	0-225-110-2016		0.0	2.7	5.6	26.6	2.693	2.726	1.229		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
WHELAN 55-64-039-PIT Created On: 01/05/21 Updated On:	P	SE	NE	1	1N	15E	Walworth	0-225-84-2021		0.0	5.1	3.6	5.2	29.6	2.689	2.727	1.400	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
WHELAN 55-64-039-PIT Created On: 06/02/25 Updated On:	P	SE	NE	1	1N	15E	Walworth	0-225-217-2025		0.5	12.7	0.6	5.4	26.4	2.693	2.732	1.464	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
WHITEWATER LIMESTONE 55-64-052-QRY Created On: 10/03/17 Updated On:	Q	NW	SW	9	4N	15E	Walworth	0-225-277-2017		1.1	2.6	2.1	8.8	34.3	2.618	2.678	2.309	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
WHITEWATER LIMESTONE 55-64-052-QRY Created On: 04/09/20 Updated On:	Q	NW	SW	9	4N	15E	Walworth	0-225-152-2020		0.2	1.8	6.1	8.1	35.2	2.627	2.683	2.152	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
WHITEWATER LIMESTONE 55-64-052-QRY Created On: 02/10/22 Updated On:	Q	NW	SW	9	4N	15E	Walworth	0-225-121-2022		0.6	4.6	7.9	8.1	33.6	2.612	2.675	2.419	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
WHITEWATER LIMESTONE 55-64-052-QRY Created On: 01/02/25 Updated On:	Q	NW	SW	9	4N	15E	Walworth	0-225-3-2025		0.7	2.1	2.5	6.6	29.4	2.604	2.670	2.544	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
WASHBURN -- WI																	
FRAATZ 55-65-006-PIT Created On: 06/08/17 Updated On:	P		SW	18	41N	12W	Washburn	0-225-207-2017		0.0	3.8	6.0	24.3	2.629	2.682	2.020	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
FRAATZ 55-65-006-PIT Created On: 03/01/23 Updated On:	P		SW	18	41N	12W	Washburn	0-225-162-2023	4.4	0.0	6.9	5.0	22.5	2.661	2.707	1.738	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
MINONG 55-65-009-QRY Created On: 10/08/15 Updated On:	Q	NE	NW	27	42N	11W	Washburn	0-225-241-2015		0.0	0.4	2.9	11.8	2.903	2.915	0.400	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
MINONG 55-65-009-QRY Created On: 06/07/18 Updated On:	Q	NE	NW	27	42N	11W	Washburn	0-225-219-2018		0.0	0.5	2.3	10.1	2.930	2.940	0.320	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
MINONG 55-65-009-QRY Created On: 07/07/22 Updated On:	Q	NE	NW	27	42N	11W	Washburn	0-225-246-2022	0.0	0.5	0.3	2.0	10.7	2.914	2.924	0.339	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
MINONG 55-65-009-QRY Created On: 01/02/25 Updated On:	Q	NE	NW	27	42N	11W	Washburn	0-225-18-2025	0.0	0.2	0.2	3.1	13.8	2.907	2.922	0.512	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
PAFFEL 55-65-010-PIT Created On: 01/07/19 Updated On:	P	NE	NE	21	39N	12W	Washburn	0-225-59-2019	0.3	0.0	2.3	3.8	17.3	2.708	2.743	1.323	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
WASHBURN -- WI																		
PAFFEL 55-65-010-PIT Created On: 01/02/24 Updated On:	P	NE	NE	21	39N	12W	Washburn	0-225-94-2024	0.9	3.3	2.0	3.9	18.6	2.706	2.742	1.313		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
PINE BROOK 55-65-012-PIT Created On: 05/14/15 Updated On:	P		N	21	38N	11W	Washburn	0-225-174-2015		0.0	3.1	4.1	18.5	2.788	2.815	0.978		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
PINE BROOK 55-65-012-PIT Created On: 01/08/21 Updated On:	P		N	21	38N	11W	Washburn	0-225-118-2021	0.3	0.0	4.3	4.9	20.4	2.736	2.776	1.464		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
*SUGAR BUSH 55-65-020-PIT Created On: 06/18/20 Updated On:	P		NW	23	37N	10W	Washburn	0-225-198-2020	2.0	0.0	2.1	4.6	20.7	2.753	2.778	0.915		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
TUBBS 55-65-017-PIT Created On: 06/09/20 Updated On:	P	NE	SE	18	41N	12W	Washburn	0-225-189-2020	1.7	0.0	2.3	4.0	18.7	2.735	2.771	1.325		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
TUBBS 55-65-017-PIT Created On: 01/16/25 Updated On:	P	NE	SE	18	41N	12W	Washburn	0-225-131-2025	2.9	7.1	7.1	3.9	18.5	2.654	2.711	2.126		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
WASHINGTON -- WI																		
CEDAR LAKE 55-66-004-PIT Created On: 01/04/16 Updated On:	P	N	SW	35	11N	18E	Washington	0-225-15-2016	1.9	1.3	2.1	5.7	26.4	2.712	2.743	1.165		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
WASHINGTON -- WI																		
CEDAR LAKE 55-66-004-PIT Created On: 01/08/21 Updated On:	P	N	SW	35	11N	18E	Washington	0-225-116-2021		0.8	8.7	1.1	5.9	32.1	2.749	2.772	0.830	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
LANNON STONE - JACKSON 55-66-012-QRY Created On: 01/22/16 Updated On:	Q		NE	12	10N	20E	Washington	0-225-75-2016			0.3	0.2	9.4	34.0	2.705	2.734	1.068	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
LANNON STONE - JACKSON 55-66-012-QRY Created On: 01/18/19 Updated On:	Q		NE	12	10N	20E	Washington	0-225-88-2019			0.9	0.2	8.9	34.4	2.658	2.697	1.478	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
LANNON STONE - JACKSON 55-66-012-QRY Created On: 01/13/22 Updated On:	Q		NE	12	10N	20E	Washington	0-225-111-2022		0.0	0.7	0.6	8.1	36.5	2.608	2.648	1.554	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
LANNON STONE - JACKSON 55-66-012-QRY Created On: 01/03/23 Updated On:	Q		NE	12	10N	20E	Washington	0-225-80-2023		1.6	1.6	0.6	7.4	31.6	2.620	2.670	1.914	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
LANNON STONE - RICHFIELD 55-66-013-PIT Created On: 02/16/16 Updated On:	P		SE	24	9N	19E	Washington	0-225-89-2016			2.6	1.1	8.2	35.1				
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
LANNON STONE - RICHFIELD 55-66-013-PIT Created On: 01/08/21 Updated On:	P		SE	24	9N	19E	Washington	0-225-114-2021		0.0	2.2	2.3	6.9	28.6	2.710	2.740	1.116	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
WASHINGTON -- WI																		
MICHEL'S BECKER 55-66-016-PIT Created On: 01/08/15 Updated On:	P	SW	SW	27	11N	18E	Washington	0-225-32-2015	0.2	3.6	3.7	6.6	29.1	2.704	2.738	1.262		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
MICHEL'S BECKER 55-66-016-PIT Created On: 01/08/20 Updated On:	P	SW	SW	27	11N	18E	Washington	0-225-77-2020	2.2	10.5	2.7	6.1	28.8	2.678	2.718	1.499		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MICHEL'S BECKER 55-66-016-PIT Created On: 01/02/25 Updated On:	P	SW	SW	27	11N	18E	Washington	0-225-76-2025	0.1	4.3	3.2	5.6	27.7	2.670	2.708	1.400		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
WEST BEND S & G 55-66-020-PIT Created On: 03/22/19 Updated On:	P	SW	SE	8	11N	19E	Washington	0-225-116-2019	0.0	1.1	0.3	4.8	27.3	2.757	2.780	0.819		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
WEST BEND S & G 55-66-020-PIT Created On: 05/20/24 Updated On:	P	SW	SE	8	11N	19E	Washington	0-225-257-2024	2.3	1.5	4.7	5.3	27.1	2.731	2.757	0.964		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
WISSOTA RUGBY S&G 55-66-021-PIT Created On: 01/07/19 Updated On:	P	SE	NE	34	10N	19E	Washington	0-225-43-2019	0.2	4.6	1.1	5.2	27.4	2.731	2.760	1.095		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
WISSOTA RUGBY S&G 55-66-021-PIT Created On: 01/29/24 Updated On:	P	SE	NE	34	10N	19E	Washington	0-225-160-2024	0.4	9.7	1.1	6.8	31.2	2.725	2.755	1.095		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
WASHINGTON -- WI																		
WISSOTA RUGBY S&G 55-66-021-PIT Created On: 05/01/24 Updated On:	P	SE	NE	34	10N	19E	Washington	0-225-246-2024	1.3	9.5	1.8	5.6	14.9	2.725	2.755	1.095		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
WAUKESHA -- WI																		
AMRIZE-COLGATE 55-67-021-PIT Created On: 01/08/15 Updated On:	P	S	NW	3	8N	19E	Waukesha	0-225-35-2015	0.9	2.5	2.4	4.5	23.9	2.736	2.759	0.827		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
AMRIZE-COLGATE 55-67-021-PIT Created On: 03/16/18 Updated On:	P	S	NW	3	8N	19E	Waukesha	0-225-129-2018		3.7	3.6	5.6	25.7	2.742	2.765	0.840		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
AMRIZE-COLGATE 55-67-021-PIT Created On: 01/03/23 Updated On:	P	S	NW	3	8N	19E	Waukesha	0-225-26-2023	0.0	5.6	1.0	6.0	27.6	2.691	2.728	1.408		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
GENESEE 55-67-007-PIT Created On: 01/05/16 Updated On:	P	NE	SE	29	6N	18E	Waukesha	0-225-21-2016	0.2	1.9	2.4	8.0	34.9	2.708	2.745	1.346		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
GENESEE 55-67-007-PIT Created On: 01/05/21 Updated On:	P	NE	SE	29	6N	18E	Waukesha	0-225-95-2021	0.0	6.1	2.8	6.1	27.5	2.727	2.759	1.189		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
GENESEE / HILLVIEW 55-67-005-PIT Created On: 01/08/15 Updated On:	P		SE	8	8N	19E	Waukesha	0-225-30-2015	0.5	4.6	3.9	5.9	28.1	2.686	2.725	1.439		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
WAUKESHA -- WI																		
GENESEE / HILLVIEW 55-67-005-PIT Created On: 02/16/16 Updated On:	P		SE	8	8N	19E	Waukesha	0-225-90-2016		1.6	1.6	7.6	34.6	2.711	2.743	1.180		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
GENESEE / HILLVIEW 55-67-005-PIT Created On: 01/05/21 Updated On:	P		SE	8	8N	19E	Waukesha	0-225-97-2021	0.4	6.1	3.8	7.4	31.0	2.578	2.643	2.498		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
GENESEE/OTTAWA PIT 55-67-006-PIT Created On: 01/05/16 Updated On:	P		SW	1	6N	17E	Waukesha	0-225-19-2016	0.0	3.0	4.9	8.4	37.1	2.688	2.723	1.324		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
GENESEE/OTTAWA PIT 55-67-006-PIT Created On: 01/05/21 Updated On:	P		SW	1	6N	17E	Waukesha	0-225-94-2021	0.0	5.2	6.8	5.5	26.7	2.677	2.716	1.452		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
HALQUIST 55-67-048-QRY Created On: 04/29/25 Updated On:	Q	SE	SW	17	8N	20E	Waukesha	0-225-203-2025		3.6	0.1	4.6	22.7	2.755	2.778	0.840		
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																	
HALQUIST NORTH LAKE 55-67-032-PIT Created On: 06/27/18 Updated On:	P		SE	9	8N	18E	Waukesha	0-225-239-2018	1.1	0.8	1.0	5.6	27.3	2.721	2.749	1.042		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
HALQUIST NORTH LAKE 55-67-032-PIT Created On: 03/21/23 Updated On:	P		SE	9	8N	18E	Waukesha	0-225-171-2023	0.6	17.3	0.0	5.3	25.1	2.720	2.744	0.900		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
WAUKESHA -- WI																	
HALQUIST NORTH LAKE 55-67-032-PIT Created On: 06/27/24 Updated On:	P		SE	9	8N	18E	Waukesha	0-225-283-2024	1.2	9.1	2.2	5.4	26.1	2.708	2.736	1.062	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
JOHNSON S&G - CROWBAR 55-67-016-PIT Created On: 03/06/25 Updated On:	P		NW	6	5N	20E	Waukesha	0-225-171-2025	1.9	12.3	3.1	4.3	22.5	2.683	2.721	1.429	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
K & N 55-67-019-PIT Created On: 02/05/19 Updated On:	P		S	9	8N	19E	Waukesha	0-225-96-2019		4.0	1.1	4.5	23.4	2.733	2.758	0.908	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
K & N 55-67-019-PIT Created On: 01/02/24 Updated On:	P		S	9	8N	19E	Waukesha	0-225-16-2024	0.1	2.3	1.8	5.2	23.9	2.730	2.756	0.960	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
LANNON LISBON PIT 55-67-024-PIT Created On: 01/08/15 Updated On:	P		SW	24	8N	19E	Waukesha	0-225-31-2015	0.8	2.9	4.9	6.4	29.2	2.729	2.758	1.039	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
LANNON LISBON PIT 55-67-024-PIT Created On: 01/09/20 Updated On:	P		SW	24	8N	19E	Waukesha	0-225-93-2020	0.0	2.7	1.1	4.3	22.9	2.736	2.764	1.041	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
LANNON LISBON PIT 55-67-024-PIT Created On: 01/14/25 Updated On:	P		SW	24	8N	19E	Waukesha	0-225-93-2025	0.3	9.2	2.7	4.0	22.5	2.746	2.778	1.172	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
WAUKESHA -- WI																	
LANNON STONE - LANNON 55-67-026-QRY Created On: 01/08/15 Updated On:	Q		E	20	8N	20E	Waukesha	0-225-34-2015		0.9	4.6	6.1	28.5	2.720	2.748	1.026	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
LANNON STONE - LANNON 55-67-026-QRY Created On: 02/09/18 Updated On:	Q		E	20	8N	20E	Waukesha	0-225-91-2018		3.8	2.3	5.5	24.0	2.729	2.759	1.110	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
LANNON STONE - LANNON 55-67-026-QRY Created On: 01/08/21 Updated On:	Q		E	20	8N	20E	Waukesha	0-225-115-2021	0.0	2.7	4.1	4.8	21.8	2.746	2.772	0.936	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
LANNON STONE - LANNON 55-67-026-QRY Created On: 04/22/24 Updated On:	Q		E	20	8N	20E	Waukesha	0-225-237-2024	0.0	1.8	1.4	4.8	23.5	2.751	2.778	0.984	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
LANNON STONE - SUSSEX 55-67-025-QRY Created On: 04/04/17 Updated On:	Q		NE	35	8N	19E	Waukesha	0-225-103-2017		1.5	1.2	5.7	25.8	2.721	2.748	0.980	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
LANNON STONE - SUSSEX 55-67-025-QRY Created On: 01/08/20 Updated On:	Q		NE	35	8N	19E	Waukesha	0-225-80-2020	0.0	0.9	0.6	5.0	24.9	2.715	2.747	1.167	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
LANNON STONE - SUSSEX 55-67-025-QRY Created On: 02/27/23 Updated On:	Q		NE	35	8N	19E	Waukesha	0-225-145-2023	3.7	3.1	0.9	5.3	24.7	2.735	2.767	1.176	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
WAUKESHA -- WI																	
LANNON STONE - WEST QUARRY 55-67-008-QRY Created On: 01/08/15 Updated On:	Q		NW	35	8N	19E	Waukesha	0-225-33-2015		0.8	1.3	5.8	26.1	2.738	2.766	1.027	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
LANNON STONE - WEST QUARRY 55-67-008-QRY Created On: 01/12/16 Updated On:	Q		NW	35	8N	19E	Waukesha	0-225-57-2016		0.6	0.4	8.2	39.7	2.716	2.743	0.974	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
LANNON STONE - WEST QUARRY 55-67-008-QRY Created On: 02/11/19 Updated On:	Q		NW	35	8N	19E	Waukesha	0-225-101-2019	6.2	5.1	1.2	4.1	22.4	2.715	2.750	1.282	
	Approved Use : HMA<MT, HMA>=MT, Base Aggregate																
LANNON STONE - WEST QUARRY 55-67-008-QRY Created On: 01/13/22 Updated On:	Q		NW	35	8N	19E	Waukesha	0-225-110-2022	0.0	11.1	4.1	5.3	25.5	2.684	2.725	1.512	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
LANNON STONE - WEST QUARRY 55-67-008-QRY Created On: 01/03/23 Updated On:	Q		NW	35	8N	19E	Waukesha	0-225-81-2023	2.7	12.1	0.5	5.5	25.4	2.718	2.748	1.109	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
LANNON STONE-DOUSMAN 55-67-043-PIT Created On: 04/03/17 Updated On:	P		E	6	6N	18E	Waukesha	0-225-102-2017		2.8	2.7	5.2	24.9	2.723	2.750	1.000	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
LANNON STONE-DOUSMAN 55-67-043-PIT Created On: 08/03/21 Updated On:	P		E	6	6N	18E	Waukesha	0-225-257-2021	0.8	1.3	2.4	4.1	23.0	2.736	2.766	1.064	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
WAUKESHA -- WI																	
LANNON STONE-DOUSMAN 55-67-043-PIT Created On: 01/14/25 Updated On:	P		E	6	6N	18E	Waukesha	0-225-109-2025		2.0	7.6	2.2	5.3	27.2	2.718	2.750	1.170
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
LEMKE STONE 55-67-046-QRY Created On: 05/07/20 Updated On:	Q	NE	NW	19	8N	20E	Waukesha	0-225-174-2020		0.0	2.1	3.1	5.3	25.3	2.755	2.792	1.319
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
LEMKE STONE 55-67-046-QRY Created On: 05/14/25 Updated On:	Q	NE	NW	19	8N	20E	Waukesha	0-225-212-2025		0.0	0.9	1.0	5.2	24.6	2.690	2.733	1.618
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
MUSKEGO 55-67-029-PIT Created On: 01/04/18 Updated On:	P	SW	SW	18	5N	20E	Waukesha	0-225-76-2018		0.3	2.9	1.8	3.8	24.9	2.676	2.723	1.774
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
MUSKEGO 55-67-029-PIT Created On: 01/03/23 Updated On:	P	SW	SW	18	5N	20E	Waukesha	0-225-73-2023		0.1	3.6	0.9	4.7	22.7	2.700	2.735	1.314
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
WAUKESHA LIME & STONE 55-67-042-QRY Created On: 01/04/16 Updated On:	Q	SE	SE	26	7N	19E	Waukesha	0-225-4-2016			9.0	3.0	4.3	20.5	2.712	2.751	1.426
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																
WAUKESHA LIME & STONE 55-67-041-PIT Created On: 01/21/16 Updated On:	P	SE	SE	26	7N	8E	Waukesha	0-225-71-2016		1.2	4.7	2.3	4.7	23.4	2.713	2.748	1.311
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
WAUKESHA -- WI																		
WAUKESHA LIME & STONE 55-67-042-QRY Created On: 02/05/19 Updated On:	Q	SE	SE	26	7N	19E	Waukesha	0-225-98-2019	0.3	1.2	0.2	5.7	27.4	2.682	2.718	1.370		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
WAUKESHA LIME & STONE 55-67-041-PIT Created On: 01/05/21 Updated On:	P	SE	SE	26	7N	8E	Waukesha	0-225-96-2021	0.4	2.2	2.1	5.7	29.2	2.693	2.733	1.502		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
WAUKESHA LIME & STONE 55-67-042-QRY Created On: 01/04/22 Updated On:	Q	SE	SE	26	7N	19E	Waukesha	0-225-54-2022	0.3	0.9	0.5	4.1	20.0	2.776	2.793	0.639		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
WAUKESHA LIME & STONE 55-67-042-QRY Created On: 01/02/25 Updated On:	Q	SE	SE	26	7N	19E	Waukesha	0-225-77-2025	0.0	0.0	3.3	6.2	26.4	2.692	2.733	1.526		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
WAUPACA -- WI																		
COLRUE 55-68-033-PIT Created On: 03/01/18 Updated On:	P	SW	NE	31	23N	12E	Waupaca	0-225-110-2018	0.3	0.0	1.3	6.0	27.0	2.680	2.705	0.935		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
COLRUE 55-68-033-PIT Created On: 04/17/23 Updated On:	P	SW	NE	31	23N	12E	Waupaca	0-225-198-2023	1.1	1.6	2.6	5.9	26.9	2.612	2.646	1.298		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
FAULKS Q-PIT 55-68-010-PIT Created On: 08/03/16 Updated On:	P	SW	SE	17	22N	11E	Waupaca	0-225-232-2016	0.8	0.0	1.9	9.0	24.8	2.601	2.634	1.287		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
WAUPACA -- WI																		
FAULKS Q-PIT 55-68-010-PIT Created On: 06/10/24 Updated On:	P	SW	SE	17	22N	11E	Waupaca	0-225-267-2024	0.1	12.6	3.8	8.7	36.9	2.685	2.731	1.719		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
GO GREEN 55-68-019-QRY Created On: 09/02/15 Updated On:	Q		NW	13	21N	14E	Waupaca	0-225-236-2015		0.0	11.3	8.4	34.6	2.701	2.745	1.654		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
GO GREEN 55-68-019-QRY Created On: 02/15/18 Updated On:	Q		NW	13	21N	14E	Waupaca	0-225-101-2018		0.0	2.6	5.9	27.4	2.698	2.738	1.490		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
GO GREEN 55-68-019-QRY Created On: 02/28/23 Updated On:	Q		NW	13	21N	14E	Waupaca	0-225-159-2023	1.3	5.4	2.3	8.5	32.7	2.699	2.739	1.476		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MARION AGGREGATES 55-68-022-PIT Created On: 06/30/17 Updated On:	P	SW	NW	5	25N	13E	Waupaca	0-225-223-2017		0.0	0.3	4.8	24.9	2.701	2.722	0.801		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MARION AGGREGATES 55-68-022-PIT Created On: 01/04/22 Updated On:	P	SW	NW	5	25N	13E	Waupaca	0-225-71-2022	0.0	0.9	0.6	5.0	23.6	2.700	2.724	0.904		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
READFIELD 55-68-025-QRY Created On: 08/03/16 Updated On:	Q	NE	SW	26	21N	14E	Waupaca	0-225-231-2016		0.0	2.0	7.2	31.5	2.645	2.702	2.155		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
WAUPACA -- WI																		
READFIELD 55-68-025-QRY Created On: 01/10/19 Updated On:	Q	NE	SW	26	21N	14E	Waupaca	0-225-85-2019	0.3	0.0	2.4	6.1	29.8	2.712	2.752	1.453		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
READFIELD 55-68-025-QRY Created On: 03/17/22 Updated On:	Q	NE	SW	26	21N	14E	Waupaca	0-225-147-2022	0.9	0.0	1.2	9.2	39.7	2.635	2.686	1.905		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
READFIELD 55-68-025-QRY Created On: 01/14/25 Updated On:	Q	NE	SW	26	21N	14E	Waupaca	0-225-102-2025		2.1	6.3	11.3	41.5	2.631	2.681	1.902		
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																	
THIEL 55-68-028-PIT Created On: 06/21/16 Updated On:	P	NE	NW	5	22N	13E	Waupaca	0-225-209-2016		0.0	1.1	5.7	27.5	2.691	2.712	0.794		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
THIEL 55-68-028-PIT Created On: 01/04/21 Updated On:	P	NE	NW	5	22N	13E	Waupaca	0-225-21-2021	0.6	3.1	2.0	5.5	26.6	2.703	2.727	0.913		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
WAUSHARA -- WI																		
HEYN 55-69-006-PIT Created On: 04/13/17 Updated On:	P	W	NE	22	19N	8E	Waushara	0-225-131-2017		0.0	2.8	6.7	25.8	2.737	2.775	1.388		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
HEYN 55-69-006-PIT Created On: 04/30/21 Updated On:	P	W	NE	22	19N	8E	Waushara	0-225-191-2021	3.3	2.5	4.9	7.6	31.0	2.705	2.741	1.330		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
WAUSHARA -- WI																		
KELLEY 55-69-018-PIT Created On: 11/12/18 Updated On:	P	NE	NE	22	19N	3E	Waushara	0-225-291-2018	1.5	0.0	1.7	6.9	27.9	2.730	2.756	0.975		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
KELLEY 55-69-018-PIT Created On: 06/26/23 Updated On:	P	NE	NE	22	19N	3E	Waushara	0-225-236-2023		0.0	0.1	5.6	25.5	2.739	2.766	0.991		
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																	
MEYER 55-69-012-PIT Created On: 01/04/22 Updated On:	P	NW	NW	36	20N	9E	Waushara	0-225-39-2022	1.0	0.0	6.4	6.9	29.2	2.699	2.733	1.256		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
SPRINGWATER 55-69-019-PIT Created On: 05/13/21 Updated On:	P	NW	NW	6	20N	11E	Waushara	0-225-206-2021	0.2	2.9	1.3	4.7	21.2	2.700	2.730	1.097		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
WINNEBAGO -- WI																		
BEN CARRIE 55-70-001-QRY Created On: 01/09/15 Updated On:	Q	NW	SW	29	20N	17E	Winnebago	0-225-49-2015	0.1	2.1	1.4	5.6	24.3	2.768	2.792	0.891		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
BEN CARRIE 55-70-001-QRY Created On: 05/12/16 Updated On:	Q	NW	SW	29	20N	17E	Winnebago	0-225-171-2016		0.9	1.3	4.5	21.5	2.780	2.803	0.825		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
BEN CARRIE 55-70-001-QRY Created On: 03/13/17 Updated On:	Q	NW	SW	29	20N	17E	Winnebago	0-225-79-2017	0.2	1.8	4.6	5.0	23.4	2.768	2.792	0.846		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
WINNEBAGO -- WI																		
BEN CARRIE 55-70-001-QRY Created On: 03/28/18 Updated On:	Q	NW	SW	29	20N	17E	Winnebago	0-225-150-2018	0.1	2.1	1.4	4.3	20.6	2.773	2.799	0.919		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
BEN CARRIE 55-70-001-QRY Created On: 04/10/19 Updated On:	Q	NW	SW	29	20N	17E	Winnebago	0-225-128-2019		5.6	2.9	4.6	22.2	2.761	2.788	0.978		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
BEN CARRIE 55-70-001-QRY Created On: 04/08/20 Updated On:	Q	NW	SW	29	20N	17E	Winnebago	0-225-148-2020	0.0	6.3	3.2	4.9	22.4	2.765	2.794	1.042		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
BEN CARRIE 55-70-001-QRY Created On: 01/03/23 Updated On:	Q	NW	SW	29	20N	17E	Winnebago	0-225-76-2023	0.0	6.0	3.2	6.6	29.7	2.717	2.753	1.322		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
CURTIS QUARRY 55-70-040-QRY Created On: 07/02/24 Updated On:	Q	SW	NW	4	20N	17E	Winnebago	0-225-287-2024		10.6	1.8	8.1	33.4	2.729	2.759	1.092		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
JORGENSEN 55-70-004-QRY Created On: 01/09/15 Updated On:	Q		NE	5	20N	17E	Winnebago	0-225-48-2015	0.1	9.2	4.4	6.2	28.8	2.729	2.761	1.149		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
JORGENSEN 55-70-004-QRY Created On: 01/04/18 Updated On:	Q		NE	5	20N	17E	Winnebago	0-225-55-2018		13.2	6.0	5.8	28.4	2.749	2.778	1.060		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine	
WINNEBAGO -- WI																		
JORGENSEN 55-70-004-QRY Created On: 01/05/21 Updated On:	Q		NE	5	20N	17E	Winnebago	0-225-51-2021	0.0	10.5	2.0	6.4	30.2	2.729	2.761	1.202		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
JORGENSEN 55-70-004-QRY Created On: 01/02/24 Updated On:	Q		NE	5	20N	17E	Winnebago	0-225-54-2024	0.0	14.4	10.1	9.0	34.9	2.695	2.734	1.468		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
KALATA 55-70-005-QRY Created On: 01/12/16 Updated On:	Q	NE	NE	27	19N	14E	Winnebago	0-225-52-2016	0.2	1.7	3.3	9.1	36.0	2.692	2.731	1.436		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
KALATA 55-70-005-QRY Created On: 05/24/19 Updated On:	Q	NE	NE	27	19N	14E	Winnebago	0-225-198-2019	0.9	0.8	1.9	8.0	33.5	2.701	2.739	1.422		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
KALATA 55-70-005-QRY Created On: 01/04/22 Updated On:	Q	NE	NE	27	19N	14E	Winnebago	0-225-17-2022	1.8	2.0	4.5	9.9	37.6	2.656	2.703	1.751		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
KALATA 55-70-005-QRY Created On: 01/02/24 Updated On:	Q	NE	NE	27	19N	14E	Winnebago	0-225-107-2024	0.3	1.2	3.9	8.0	35.0	2.679	2.720	1.510		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
LARSEN 55-70-007-QRY Created On: 01/05/15 Updated On:	Q	N	NE	19	20N	16E	Winnebago	0-225-2-2015	1.6	0.7	1.9	5.0	23.1	2.725	2.755	1.102		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
WINNEBAGO -- WI																		
LARSEN 55-70-007-QRY Created On: 01/04/18 Updated On:	Q	N	NE	19	20N	16E	Winnebago	0-225-54-2018		0.7	0.7	4.8	22.8	2.716	2.749	1.211		
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																	
LARSEN 55-70-007-QRY Created On: 01/05/21 Updated On:	Q	N	NE	19	20N	16E	Winnebago	0-225-47-2021	0.0	1.6	2.1	6.8	27.4	2.713	2.750	1.340		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
LARSEN 55-70-007-QRY Created On: 01/02/24 Updated On:	Q	N	NE	19	20N	16E	Winnebago	0-225-97-2024	0.5	0.7	0.2	4.8	21.3	2.756	2.779	0.800		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MCC - LARSEN 55-70-010-QRY Created On: 05/26/16 Updated On:	Q	NE	NW	19	20N	16E	Winnebago	0-225-193-2016	2.8	1.4	1.2	5.3	24.4	2.737	2.761	0.873		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
MCC - LARSEN 55-70-010-QRY Created On: 03/16/18 Updated On:	Q	NE	NW	19	20N	16E	Winnebago	0-225-125-2018	0.3	3.3	1.4	5.6	24.2	2.729	2.756	1.003		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
MCC - LARSEN 55-70-010-QRY Created On: 01/05/21 Updated On:	Q	NE	NW	19	20N	16E	Winnebago	0-225-103-2021	0.2	10.0	11.3	6.8	28.9	2.708	2.750	1.553		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MCC - LARSEN 55-70-010-QRY Created On: 01/02/24 Updated On:	Q	NE	NW	19	20N	16E	Winnebago	0-225-7-2024	0.0	13.8	3.9	7.5	32.3	2.723	2.757	1.260		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
WINNEBAGO -- WI																		
MICHEL'S ALLEN 55-70-011-QRY Created On: 01/21/16 Updated On:	Q	NE	SW	9	18N	14E	Winnebago	0-225-68-2016	0.5	1.4	6.8	11.6	39.5	2.645	2.700	2.056		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
MICHEL'S ALLEN 55-70-011-QRY Created On: 01/07/19 Updated On:	Q	NE	SW	9	18N	14E	Winnebago	0-225-70-2019	0.0	1.7	2.3	7.2	32.0	2.753	2.785	1.180		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
MICHEL'S ALLEN 55-70-011-QRY Created On: 01/04/22 Updated On:	Q	NE	SW	9	18N	14E	Winnebago	0-225-18-2022	0.0	1.1	1.2	7.9	33.9	2.738	2.769	1.142		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MICHEL'S ALLEN 55-70-011-QRY Created On: 01/02/24 Updated On:	Q	NE	SW	9	18N	14E	Winnebago	0-225-104-2024	0.8	2.2	2.8	9.3	36.2	2.693	2.734	1.512		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MICHEL'S DEVENS 55-70-013-QRY Created On: 01/07/16 Updated On:	Q	NW	NW	21	19N	16E	Winnebago	0-225-40-2016		2.8	2.3	4.5	20.4	2.767	2.791	0.876		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
MICHEL'S DEVENS 55-70-013-QRY Created On: 01/07/20 Updated On:	Q	NW	NW	21	19N	16E	Winnebago	0-225-36-2020	0.2	9.9	2.0	6.1	26.0	2.736	2.772	1.323		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MICHEL'S DEVENS 55-70-013-QRY Created On: 01/02/24 Updated On:	Q	NW	NW	21	19N	16E	Winnebago	0-225-47-2024	0.1	5.1	3.8	6.1	26.0	2.763	2.791	0.999		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
WINNEBAGO -- WI																		
MICHEL'S DIETZ 55-70-014-QRY Created On: 03/31/17 Updated On:	Q			8	20N	17E	Winnebago	0-225-96-2017	0.1	3.8	5.4	6.9	30.5	2.741	2.770	1.060		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
MICHEL'S DIETZ 55-70-014-QRY Created On: 01/07/20 Updated On:	Q			8	20N	17E	Winnebago	0-225-39-2020	0.1	12.5	2.1	5.5	26.0	2.742	2.777	1.297		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MICHEL'S DIETZ 55-70-014-QRY Created On: 01/03/23 Updated On:	Q			8	20N	17E	Winnebago	0-225-79-2023	0.1	13.6	10.6	6.6	28.8	2.717	2.760	1.576		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MICHEL'S DIETZ 55-70-014-QRY Created On: 04/15/25 Updated On:	Q			8	20N	17E	Winnebago	0-225-191-2025	0.1	13.3	10.7	6.9	29.2	2.740	2.773	1.206		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MICHEL'S GRUNSKA 55-70-016-QRY Created On: 05/10/18 Updated On:	Q	SE	SE	8	20N	16E	Winnebago	0-225-201-2018	1.4	10.5	3.9	6.9	30.0	2.695	2.730	1.298		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MICHEL'S GRUNSKA 55-70-016-QRY Created On: 01/05/21 Updated On:	Q	SE	SE	8	20N	16E	Winnebago	0-225-50-2021	1.5	5.7	4.8	7.0	30.6	2.705	2.743	1.392		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MICHEL'S GRUNSKA 55-70-016-QRY Created On: 01/02/24 Updated On:	Q	SE	SE	8	20N	16E	Winnebago	0-225-46-2024	1.3	7.9	5.8	6.8	28.5	2.705	2.740	1.265		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
WINNEBAGO -- WI																		
MICHEL'S KOCH 55-70-017-QRY Created On: 01/04/22 Updated On:	Q	NW	NE	29	20N	17E	Winnebago	0-225-20-2022	0.2	1.7	2.0	5.2	23.9	2.758	2.787	1.050		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MICHEL'S KOCH 55-70-017-QRY Created On: 01/04/24 Updated On:	Q	NW	NE	29	20N	17E	Winnebago	0-225-147-2024	0.0	2.9	2.4	5.4	25.6	2.759	2.788	1.039		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MICHEL'S OSHKOSH 55-70-018-QRY Created On: 01/04/16 Updated On:	Q		NE	27	18N	16E	Winnebago	0-225-11-2016		3.1	2.8	5.0	22.1	2.755	2.782	0.992		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
MICHEL'S OSHKOSH 55-70-018-QRY Created On: 01/04/19 Updated On:	Q		NE	27	18N	16E	Winnebago	0-225-6-2019		8.9	2.1	4.1	19.8	2.766	2.792	0.929		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
MICHEL'S OSHKOSH 55-70-018-QRY Created On: 01/04/22 Updated On:	Q		NE	27	18N	16E	Winnebago	0-225-22-2022	0.1	7.3	5.0	4.9	22.8	2.730	2.766	1.321		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MICHEL'S OSHKOSH 55-70-018-QRY Created On: 01/02/24 Updated On:	Q		NE	27	18N	16E	Winnebago	0-225-103-2024	0.0	6.3	2.3	4.8	22.8	2.753	2.781	1.035		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
*MICHEL'S-HUGHES 55-70-019-QRY Created On: 01/05/17 Updated On:	Q	SW	NW	32	17N	16E	Winnebago	0-225-13-2017	0.3	11.7	9.9	6.6	28.9	2.731	2.765	1.269		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
WINNEBAGO -- WI																		
*MICHEL'S-HUGHES 55-70-019-QRY Created On: 01/04/19 Updated On:	Q	SW	NW	32	17N	16E	Winnebago	0-225-7-2019		0.5	22.5	8.7	7.3	30.2	2.708	2.752	1.629	
*MICHEL'S-HUGHES 55-70-019-QRY Created On: 05/09/19 Updated On:	Q	SW	NW	32	17N	16E	Winnebago	0-225-181-2019		0.5	10.8	10.4	6.9	30.8	2.735	2.770	1.282	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
*MICHEL'S-HUGHES 55-70-019-QRY Created On: 01/04/22 Updated On:	Q	SW	NW	32	17N	16E	Winnebago	0-225-31-2022		0.3	9.9	9.2	6.9	30.2	2.720	2.756	1.340	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
NEA MENASHA 55-70-024-QRY Created On: 01/05/15 Updated On:	Q		NW	4	20N	17E	Winnebago	0-225-3-2015			4.8	2.8	3.9	19.1	2.733	2.765	1.159	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
NEA MENASHA 55-70-024-QRY Created On: 01/04/18 Updated On:	Q		NW	4	20N	17E	Winnebago	0-225-56-2018			11.5	3.0	4.7	25.5	2.717	2.751	1.240	
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																	
NEA MENASHA 55-70-024-QRY Created On: 01/04/21 Updated On:	Q		NW	4	20N	17E	Winnebago	0-225-44-2021		0.0	10.6	3.6	5.5	26.9	2.722	2.757	1.272	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
NEA MENASHA 55-70-024-QRY Created On: 01/02/24 Updated On:	Q		NW	4	20N	17E	Winnebago	0-225-98-2024		0.1	12.7	0.3	5.0	25.1	2.747	2.771	0.846	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
WINNEBAGO -- WI																		
NEKIMI QUARRY 55-70-041-QRY Created On: 08/14/24 Updated On:	Q	NE	NW	14	17N	16E	Winnebago	0-225-300-2024	0.0	2.9	2.3	6.2	26.6	2.753	2.782	1.050		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
SCHMOKER 55-70-029-QRY Created On: 01/09/15 Updated On:	Q		NE	20	19N	16E	Winnebago	0-225-47-2015		3.1	2.0	4.5	20.9	2.773	2.795	0.803		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
SCHMOKER 55-70-029-QRY Created On: 01/04/18 Updated On:	Q		NE	20	19N	16E	Winnebago	0-225-57-2018		4.0	2.1	4.7	21.5	2.771	2.796	0.877		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
SCHMOKER 55-70-029-QRY Created On: 01/05/21 Updated On:	Q		NE	20	19N	16E	Winnebago	0-225-52-2021	0.0	2.9	6.3	6.4	29.9	2.787	2.811	0.841		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
SCHMOKER 55-70-029-QRY Created On: 01/02/24 Updated On:	Q		NE	20	19N	16E	Winnebago	0-225-55-2024	0.2	5.9	7.4	6.1	25.9	2.768	2.793	0.921		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
VINLAND 55-70-032-QRY Created On: 01/02/24 Updated On:	Q	E	NW	21	19N	16E	Winnebago	0-225-99-2024	0.0	2.9	0.5	5.0	22.1	2.785	2.806	0.751		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
WOOD -- WI																		
BIG RACK (VENDEN) 55-71-004-QRY Created On: 10/19/17 Updated On:	Q	S	SW	31	24N	3E	Wood	0-225-283-2017		0.0	0.4	4.0	18.2	2.606	2.617	0.389		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
WOOD -- WI																		
BIG RACK (VENDEN) 55-71-004-QRY Created On: 01/08/20 Updated On:	Q	S	SW	31	24N	3E	Wood	0-225-73-2020	0.0	0.0	0.3	3.6	16.9	2.603	2.616	0.495		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
BIG RACK (VENDEN) 55-71-004-QRY Created On: 01/10/23 Updated On:	Q	S	SW	31	24N	3E	Wood	0-225-105-2023	0.2	0.0	0.3	3.2	16.1	2.615	2.625	0.377		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
*CEPRESS 55-71-010-QRY Created On: 03/21/18 Updated On:	Q	SE	NE	2	23N	2E	Wood	0-225-132-2018		0.0	1.3	2.4	12.3	2.723	2.734	0.403		
	Approved Use : HMA<MT, HMA>=MT, Base Aggregate																	
*CEPRESS 55-71-010-QRY Created On: 06/28/22 Updated On:	Q	SE	NE	2	23N	2E	Wood	0-225-243-2022		0.0	1.0	3.5	14.4	2.706	2.722	0.602		
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																	
HASKE 55-71-017-QRY Created On: 01/07/15 Updated On:	Q	SW	SE	24	24N	2E	Wood	0-225-17-2015		0.0	0.5	5.0	20.6	2.619	2.629	0.374		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
HASKE 55-71-017-QRY Created On: 01/02/18 Updated On:	Q	SW	SE	24	24N	2E	Wood	0-225-2-2018		0.0	0.3	3.6	17.7	2.620	2.628	0.308		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
HASKE 55-71-017-QRY Created On: 01/04/21 Updated On:	Q	SW	SE	24	24N	2E	Wood	0-225-18-2021	0.0	0.1	0.1	5.2	22.0	2.622	2.633	0.416		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
WOOD -- WI																		
HASKE 55-71-017-QRY Created On: 05/01/24 Updated On:	Q	SW	SE	24	24N	2E	Wood	0-225-245-2024	0.0	0.0	0.1	5.1	22.0	2.616	2.627	0.407		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
K QUARRY 55-71-018-QRY Created On: 04/14/16 Updated On:	Q	SW	SW	13	24N	4E	Wood	0-225-147-2016		0.0	0.7	4.0	17.1	2.701	2.728	1.012		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
K QUARRY 55-71-018-QRY Created On: 01/04/21 Updated On:	Q	SW	SW	13	24N	4E	Wood	0-225-1-2021	0.5	0.0	2.9	3.4	15.5	2.699	2.718	0.710		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
K QUARRY 55-71-018-QRY Created On: 02/28/24 Updated On:	Q	SW	SW	13	24N	4E	Wood	0-225-172-2024	0.2	0.0	1.9	2.9	17.0	2.755	2.775	0.739		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MAPLE RIDGE #2 55-71-020-QRY Created On: 05/11/17 Updated On:	Q	NW	NW	17	22N	3E	Wood	0-225-182-2017		0.0	1.3	6.8	25.7	2.707	2.728	0.774		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
MAPLE RIDGE #2 55-71-020-QRY Created On: 01/07/20 Updated On:	Q	NW	NW	17	22N	3E	Wood	0-225-44-2020	0.4	0.0	0.5	4.0	17.2	2.734	2.744	0.353		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MAPLE RIDGE #2 55-71-020-QRY Created On: 05/22/23 Updated On:	Q	NW	NW	17	22N	3E	Wood	0-225-225-2023	0.4	0.0	1.0	4.0	17.5	2.759	2.772	0.473		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
WOOD -- WI																		
MARSHFIELD 55-71-021-QRY Created On: 01/03/17 Updated On:	Q	SE	NW	2	25N	3E	Wood	0-225-1-2017		0.0	0.3	5.1	23.8	2.676	2.690	0.520		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
MARSHFIELD 55-71-021-QRY Created On: 01/03/20 Updated On:	Q	SE	NW	2	25N	3E	Wood	0-225-12-2020	0.0	0.0	0.3	5.0	22.6	2.719	2.731	0.460		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MARSHFIELD 55-71-021-QRY Created On: 01/03/23 Updated On:	Q	SE	NW	2	25N	3E	Wood	0-225-36-2023	0.0	1.2	3.0	5.5	24.2	2.763	2.783	0.708		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
SCHILL 55-71-025-QRY Created On: 01/03/17 Updated On:	Q	NW	SW	1	23N	4E	Wood	0-225-4-2017		0.0	0.2	4.9	22.8	2.605	2.617	0.487		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
SCHILL 55-71-025-QRY Created On: 01/02/20 Updated On:	Q	NW	SW	1	23N	4E	Wood	0-225-9-2020	0.9	0.0	0.9	5.1	21.6	2.617	2.629	0.464		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
SCHILL 55-71-025-QRY Created On: 01/03/23 Updated On:	Q	NW	SW	1	23N	4E	Wood	0-225-32-2023	0.2	1.3	1.0	5.7	24.1	2.606	2.619	0.509		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
TORK 55-71-029-QRY Created On: 01/03/17 Updated On:	Q	NE	SW	1	22N	5E	Wood	0-225-2-2017		0.0	0.1	5.8	25.1	2.668	2.682	0.538		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
WOOD -- WI																		
TORK	Q	NE	SW	1	22N	5E	Wood	0-225-1-2020	0.2	0.0	1.6	6.6	27.4	2.664	2.679	0.584		
55-71-029-QRY	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
Created On: 01/02/20																		
Updated On:																		
TORK	Q	NE	SW	1	22N	5E	Wood	0-225-33-2023	0.0	1.0	1.7	6.6	27.6	2.624	2.640	0.608		
55-71-029-QRY	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
Created On: 01/03/23																		
Updated On:																		
HOUSTON -- MN																		
ABNET	Q			2	104N	5W	Houston	0-225-170-2017	0.8	2.2	4.8	8.1	32.9	2.644	2.690	1.769		
27-00-008-QRY	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
Created On: 05/04/17																		
Updated On:																		
ABNET	Q			2	104N	5W	Houston	0-225-108-2020	2.4	1.0	4.1	8.0	33.1	2.617	2.672	2.083		
27-00-008-QRY	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
Created On: 02/03/20																		
Updated On:																		
ABNET	Q			2	104N	5W	Houston	0-225-66-2023	0.9	1.3	3.2	9.8	37.1	2.599	2.658	2.268		
27-00-008-QRY	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
Created On: 01/03/23																		
Updated On:																		
LAKELAND -- MN																		
GREY CLOUD NELSON	P	S	NW	31	27N	21W	Lakeland	0-225-127-2016	0.1	1.9	3.9	4.2	24.0	2.674	2.712	1.422		
27-00-010-PIT	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
Created On: 04/07/16																		
Updated On:																		

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
LAKELAND -- MN																		
GREY CLOUD NELSON 27-00-010-PIT Created On: 08/12/21 Updated On:	P	S	NW	31	27N	21W	Lakeland	0-225-262-2021	1.5	4.4	1.6	5.2	24.1	2.694	2.722	1.023		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
PINE -- MN																		
CLARK 27-00-013-PIT Created On: 05/09/16 Updated On:	P	NW	SW	26	41N	17W	Pine	0-225-166-2016		3.9	3.1	3.1	15.9	2.781	2.820	1.402		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
CLARK 27-00-013-PIT Created On: 06/10/21 Updated On:	P	NW	SW	26	41N	17W	Pine	0-225-219-2021	2.0	2.9	1.6	4.2	19.2	2.797	2.820	0.837		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
ST LOUIS -- MN																		
ROBERTSON 27-00-014-PIT Created On: 03/16/16 Updated On:	P	NW	SW	11	52N	17W	St Louis	0-225-98-2016		0.6	0.4	2.3	13.4	2.753	2.781	1.035		
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																	
ROBERTSON 27-00-014-PIT Created On: 04/19/21 Updated On:	P	NW	SW	11	52N	17W	St Louis	0-225-184-2021	2.0	1.3	1.6	4.2	19.2	2.797	2.820	0.837		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
STATEWIDE -- MN																		
BECKS QUARRY 27-00-028-QRY Created On: 07/31/24 Updated On:	Q	N	SE	4	48N	15W	Statewide	0-225-294-2024	0.0	1.8	0.7	4.0	11.3	2.786	2.807	0.767		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
STATEWIDE -- MN																		
DAMMER 27-00-032-PIT Created On: 03/04/25 Updated On:	P	NE	NE	10	52N	17W	Statewide	0-225-160-2025		0.6	1.3	1.5	2.9	14.7	2.709	2.733	0.872	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
ELK RIVER PIT 27-00-034-PIT Created On: 04/29/25 Updated On:	P	SE	SE	9	33N	26W	Statewide	0-225-201-2025		1.3	2.0	1.4	2.3	15.0	2.690	2.718	1.047	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
EMPIRE PIT 27-00-031-PIT Created On: 08/14/24 Updated On:	P	NE	SE	5	114N	19W	Statewide	0-225-301-2024			3.0	1.5	4.5	20.6	2.692	2.720	1.057	
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																	
GREY CLOUD PIT 27-00-033-PIT Created On: 04/29/25 Updated On:	P	NW	NW	31	27N	21W	Statewide	0-225-200-2025		2.2	4.9	2.4	4.5	21.1	2.651	2.684	1.246	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
OSCAR 27-00-030-PIT Created On: 07/31/24 Updated On:	P	NW	NW	29	52N	14W	Statewide	0-225-293-2024		1.1	3.7	3.2	3.1	15.2	2.720	2.757	1.353	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
SCANLON PIT 27-00-029-PIT Created On: 07/31/24 Updated On:	P	NE	NW	36	49N	8W	Statewide	0-225-292-2024		0.9	4.2	1.4	3.4	16.3	2.703	2.729	0.941	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
WABASHA -- MN																		
WABASHA SAND & GRAVEL 27-00-020-PIT Created On: 08/12/21 Updated On:	P			32	11N	10W	Wabasha	0-225-263-2021		0.5	1.7	1.4	3.3	17.7	2.685	2.706	0.757	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
WINONA -- MN																		
MILESTONE #43	Q			16	106N	7W	Winona	0-225-49-2019	0.6	2.0	2.5	8.7	34.9	2.619	2.676	2.192		
27-00-024-QRY	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
Created On: 01/07/19																		
Updated On:																		
MILESTONE #43	Q			16	106N	7W	Winona	0-225-72-2023	0.8	1.1	3.8	10.1	39.4	2.614	2.672	2.223		
27-00-024-QRY	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
Created On: 01/03/23																		
Updated On:																		
GOGEBIC -- MI																		
MARHAR - MICHIGAN	P	S	NW	34	45N	35E	Gogebic	0-225-28-2022	0.0	1.4	1.4	3.0	14.2	2.769	2.783	0.519		
26-00-003-PIT	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
Created On: 01/04/22																		
Updated On:																		
WIEMEIR	P	SW	NW	33	48N	47W	Gogebic	0-225-130-2015		6.3	13.9	5.4	23.0	2.717	2.760	1.581		
26-00-005-PIT	Approved Use : Base Aggregate																	
Created On: 04/23/15																		
Updated On:																		
WIEMEIR	P	SW	NW	33	48N	47W	Gogebic	0-225-193-2021	1.8	11.1	17.7	5.6	24.9	2.715	2.754	1.456		
26-00-005-PIT	Approved Use : Base Aggregate																	
Created On: 04/30/21																		
Updated On:																		
IRON -- MI																		
*BEECHWOOD	P	NE	NW	1	43N	36W	Iron	0-225-193-2020	0.0	2.0	0.3	3.0	15.8	2.734	2.752	0.676		
26-00-013-PIT	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
Created On: 06/11/20																		
Updated On:																		

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
IRON -- MI																		
*CZAPIGA 55-26-005-PIT Created On: 06/11/20 Updated On:	P	NE	SE	26	42N	35W	Iron	0-225-194-2020		1.6	0.9	3.2	16.6	2.736	2.754	0.681		
	Approved Use : HMA<MT, HMA>=MT, OGBC, Base Aggregate																	
IRON RIVER 26-00-008-PIT Created On: 01/05/17 Updated On:	P	SW	NW	22	43N	35W	Iron	0-225-40-2017		0.8	0.5	0.5	3.6	14.8	2.712	2.740	1.030	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
IRON RIVER 26-00-008-PIT Created On: 01/04/22 Updated On:	P	SW	NW	22	43N	35W	Iron	0-225-27-2022		0.0	0.5	0.6	3.4	15.1	2.715	2.736	0.752	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
IRON, MI -- MI																		
FA 26-00-014-PIT Created On: 04/19/21 Updated On:	P			8	43N	35W	Iron, Mi	0-225-183-2021		0.0	1.0	0.8	4.4	19.1	2.694	2.716	0.810	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
STATEWIDE -- MI																		
LUPPINO BLACK RIVER PIT 26-00-015-PIT Created On: 09/30/24 Updated On:	P	NW	SW	19	49N	46W	Statewide	0-225-311-2024		4.8	0.0	15.1	6.9	26.9	2.581	2.640	2.268	
	Approved Use : Base Aggregate																	
DUNDEE -- IL																		
BEVERLY MATERIALS 17-00-018-PIT Created On: 01/24/22 Updated On:	P	NE	SE	36	42N	8E	Dundee	0-225-115-2022		2.4	12.9	2.8	5.2	26.5	2.674	2.713	1.458	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
KENDALL, IL -- IL																		
*LAFARGE KENDALL 17-00-017-QRY Created On: 04/30/21 Updated On:	Q		W	29	35N	7E	Kendall, Il	0-225-199-2021		0.6	1.9	0.4	6.8	29.0	2.695	2.727	1.213	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
LAKE -- IL																		
THELEN-ANTIOCH 17-00-002-PIT Created On: 05/09/18 Updated On:	P			9	46N	9E	Lake	0-225-196-2018		0.2	11.9	0.9	5.7	26.1	2.695	2.733	1.439	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
THELEN-ANTIOCH 17-00-002-PIT Created On: 01/03/23 Updated On:	P			9	46N	9E	Lake	0-225-51-2023		1.0	16.2	6.6	4.5	25.1	2.662	2.701	1.465	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
MCHENRY -- IL																		
AMRIZE-MCHENRY 17-00-011-PIT Created On: 04/24/23 Updated On:	P	NE	NE	29	45N	8E	Mchenry	0-225-205-2023		0.5	7.9	5.2	4.6	24.9	2.631	2.678	1.807	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
SUPER AGGREGATE - BURGETT LAKES 17-00-007-PIT Created On: 02/16/16 Updated On:	P		SE	1	46N	7E	Mchenry	0-225-88-2016		1.6	3.2	1.7	6.9	34.8	2.677	2.718	1.525	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, OGBC, Base Aggregate																	
SUPER AGGREGATE - BURGETT LAKES 17-00-007-PIT Created On: 01/04/21 Updated On:	P		SE	1	46N	7E	Mchenry	0-225-9-2021		0.7	4.7	0.3	4.5	23.4	2.676	2.708	1.199	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County	100					500	OD	SSD	Crse	Fine	
STATEWIDE -- IL																		
AMRIZE - CONCO 17-00-023-QRY Created On: 03/06/25 Updated On:	Q	SE	SE	3	38N	7E	Statewide	0-225-170-2025	0.2	2.4	2.6	6.0	27.1	2.635	2.683	1.786		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
AMRIZE-ELBURN 17-00-024-PIT Created On: 03/24/25 Updated On:	P			20	39N	7E	Statewide	0-225-175-2025	0.0	10.6	10.0	5.8	29.0	2.646	2.697	1.932		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
AMRIZE-JOLIET 17-00-022-QRY Created On: 03/06/25 Updated On:	Q			20	39N	7E	Statewide	0-225-169-2025	0.0	0.8	1.1	6.0	27.6	2.660	2.702	1.568		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
AMRIZE-KENDALL, ILL 17-00-021-QRY Created On: 04/30/24 Updated On:	Q	NW	SE	29	35N	7E	Statewide	0-225-242-2024	0.3	5.9	0.9	7.7	31.3	2.683	2.724	1.513		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
*IRENE 17-01-010-QRY Created On: 05/01/18 Updated On:	Q		NW	9	43N	3E	Statewide	0-225-188-2018	0.2	4.8	4.8	7.6	37.9	2.599	2.662	2.393		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																	
*IRENE 17-01-010-QRY Created On: 08/10/20 Updated On:	Q		NW	9	43N	3E	Statewide	0-225-230-2020	0.2	10.2	3.9	8.5	35.5	2.603	2.665	2.378		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	
OZINGA-CHANNAHON, IL 17-00-020-PIT Created On: 05/01/24 Updated On:	P	NE	E	17	34N	9E	Statewide	0-225-243-2024	2.0	15.0	2.8	5.1	25.3	2.638	2.688	1.905		
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																	

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
CLAYTON -- IA																	
FRENCHTOWN 19-00-008-QRY Created On: 05/22/19 Updated On:	Q			18	93N	2W	Clayton	0-225-191-2019	0.4	1.4	0.2	5.9	26.6	2.647	2.685	1.444	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
FRENCHTOWN 19-00-008-QRY Created On: 05/22/19 Updated On:	Q			18	93N	2W	Clayton	0-225-192-2019	0.1	4.3	0.7	6.2	27.7	2.661	2.703	1.558	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
FRENCHTOWN 19-00-008-QRY Created On: 01/13/22 Updated On:	Q			18	93N	2W	Clayton	0-225-112-2022	1.8	3.6	2.8	7.5	32.1	2.606	2.660	2.069	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
FRENCHTOWN 19-00-008-QRY Created On: 03/27/24 Updated On:	Q			18	93N	2W	Clayton	0-225-207-2024	1.4	14.4	3.9	9.5	36.7	2.580	2.650	2.724	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
DUBUQUE -- IA																	
BROWNS BOTTOM 19-00-002-QRY Created On: 04/23/15 Updated On:	Q		NW	33	89N	2E	Dubuque	0-225-131-2015		0.2	0.8	7.0	28.0	2.670	2.706	1.367	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
BROWNS BOTTOM 19-00-002-QRY Created On: 01/04/18 Updated On:	Q		NW	33	89N	2E	Dubuque	0-225-72-2018	0.2	1.3	1.1	6.4	27.3	2.661	2.701	1.506	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
BROWNS BOTTOM 19-00-002-QRY Created On: 01/05/21 Updated On:	Q		NW	33	89N	2E	Dubuque	0-225-57-2021	0.2	0.5	0.6	7.3	29.1	2.676	2.715	1.430	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

APPROVED AGGREGATE SOURCES INFORMATION SORTED BY COUNTY & SOURCE NAME

Date Printed: 08/06/2025

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
DUBUQUE -- IA																	
BROWNS BOTTOM 19-00-002-QRY Created On: 01/02/24 Updated On:	Q		NW	33	89N	2E	Dubuque	0-225-34-2024	0.3	3.1	1.0	8.4	32.0	2.620	2.673	2.026	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
ROSE SPUR 19-00-005-QRY Created On: 07/30/15 Updated On:	Q	NE	SE	27	90N	2E	Dubuque	0-225-221-2015	1.9	3.5	3.4	10.5	38.6	2.585	2.651	2.533	
	Approved Use : HMA<E-3, HMA>=E-3, CONCRETE, Base Aggregate																
ROSE SPUR 19-00-005-QRY Created On: 01/04/18 Updated On:	Q	NE	SE	27	90N	2E	Dubuque	0-225-69-2018	2.5	11.3	4.1	9.7	36.4	2.582	2.646	2.493	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
ROSE SPUR 19-00-005-QRY Created On: 01/05/21 Updated On:	Q	NE	SE	27	90N	2E	Dubuque	0-225-58-2021	1.2	5.2	10.0	9.3	35.3	2.567	2.638	2.764	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
ROSE SPUR 19-00-005-QRY Created On: 01/02/24 Updated On:	Q	NE	SE	27	90N	2E	Dubuque	0-225-28-2024	2.0	9.4	3.5	9.8	35.8	2.584	2.652	2.603	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																
RUBIE 19-00-007-QRY Created On: 01/04/18 Updated On:	Q		SE	6	88N	3E	Dubuque	0-225-66-2018	0.6	4.6	2.5	8.5	35.4	2.578	2.639	2.392	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, Base Aggregate																
RUBIE 19-00-007-QRY Created On: 03/17/21 Updated On:	Q		SE	6	88N	3E	Dubuque	0-225-144-2021	1.1	3.5	3.7	7.6	33.0	2.614	2.670	2.141	
	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC, Base Aggregate																

Report Date Range 2015 AND 2025

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	% SDS	LA Wear (%)		Coarse Sp. Gravity		Absorp. %	
	P/Q	Qrt	Qrt	Sect	Town	Range	County					100	500	OD	SSD	Crse	Fine
DUBUQUE -- IA																	
RUBIE	Q		SE	6	88N	3E	Dubuque	0-225-30-2024	0.4	2.9	0.7	8.4	31.8	2.625	2.678	1.997	
19-00-007-QRY	Approved Use : HMA<MT, HMA>=MT, CONCRETE, OGBC,																
Created On: 01/02/24	Base Aggregate																
Updated On:																	

Prepared by:
Wisconsin Department of Transportation
Bureau of Highway Construction
Quality Management Section