# **Vertical and Overhead Repair Material**

#### Date last edited: 04/29/2025

In accordance with 509.2, contractor may use an engineer-approved commercial grout, however, products below have been prequalified by BTS in accordance with the APL approval process for vertical and overhead repair.

Manufacturer	Product Name	Approval Date
Sika Corporation	SikaQuick VOH	3/6/2025
SpecChem	RepCon V/O	3/7/2025
Mapei Corporation	Planitop X	4/29/2025
Mapei Corporation	Planitop XS	4/29/2025

\*WisDOT evaluates submittals in accordance with the application process for Vertical and Overhead Repair Material. To apply, see WisDOT policy beginning on page 2 for additional information. Products from this list should only be used for applications within the manufacturer's intended purpose.

#### Contact:

DOTProductSubmittal@dot.wi.gov



### **Wisconsin Department of Transportation**

Division of Transportation System Development Bureau of Technical Services 3502 Kinsman Boulevard Madison, WI 53704

# Approved Product List Application Process for Vertical and Overhead Repair Material

Wisconsin Department of Transportation (WisDOT) requires pre-packaged vertical and overhead repair materials used in concrete projects from the approved product list (APL).

#### **Approval Process**

- To apply for WisDOT's APL process for pre-packaged vertical and overhead repair material, the manufacturer/supplier must submit the required information listed below for WisDOT's review:
  - Safety Data Sheet
  - Technical Data Sheet
  - American Association of State Highway and Transportation Officials (AASHTO) Product Evaluation & Audit Solutions (formerly NTPEP) or any accredited (AASHTO or Cement and Concrete Reference Laboratory (CCRL)) independent laboratory test data showing the vertical and overhead repair material has met or exceeded the requirements in outlined in the material property requirements section.
    - If submitting an independent laboratory test data, include the AASHTO/CCRL certification of the testing laboratory.
  - Manufacturer's installation instructions including surface preparation, bonding, and curing requirements for the product seeking approval.
  - Primary point of contact for the submitted product including name, email address, phone number, and mailing address.
- The submitted test data must be less than five years old. Submit the above required information to <a href="mailto:DOTProductSubmittal@dot.wi.gov">DOTProductSubmittal@dot.wi.gov</a>.
- By applying, the manufacturer/supplier certifies that they have reviewed the standards/requirements, and their product meets the requirements. WisDOT may reject an APL submittal without further review if WisDOT determines that the product does not meet standards/requirements.
- <u>Applications will be reviewed within 4 weeks of submittal</u> and when the review is completed, manufacturers/suppliers will be notified. Approved products will be listed on the department's APL.

## **Material Property Requirements**

- Vertical and overhead repair materials must be able to counteract the effects of gravity and must be suitable for exterior application demonstrating resistance to corrosion, freezethaw, and deicing salts.
- The vertical and overhead repair material must meet the testing requirements as specified in Table 1.

**Table 1.** Vertical and Overhead Repair Material Test Requirements

Test	ASTM/AASHTO Standard	Age/Procedure	Minimum Requirements
Compressive	ASTM C109/	1 days	≥ 2,000
Strength (psi)	AASHTO T106/	7 days	≥ 4,000
Strength (psi)	ASTM C928	28 days	≥ 4,000
Freeze-Thaw Durability	ASTM C666/ AASHTO T161	Procedure A, Durability Factor	90% at 300 cycles
Length Change (%)	ASTM C157/ AASHTO T160/ ASTM C928	Water and air, 28 days	Maximum +/- 0.15
Bond Strength in Direct Tension (psi)	ASTM C1583	28 days	≥ 200
Slant Shear Bond	ASTM	1 day	≥ 1,000
Strength (psi)	C882/ASTM C928	7 days	≥ 1,500
Rapid Chloride Permeability (Coulombs)	ASTM C1202	28 days	≤ 2,000

#### **Compliance**

- To remain on the WisDOT APL, the manufacturer/supplier must reapply every 5 years.
- The department may request re-compliance at any time. WisDOT may request a sample of the material to test for conformance and compare the results with the vendor test data. The verification testing sample will be taken by a WisDOT project engineer.
- The manufacturer/supplier shall be responsible for quality control of the product. The manufacturer/supplier shall also sample and test the material as necessary during production to ensure that all material conforms to the specifications as listed above and is consistent with the sample of material that was tested and approved. When requested by the Department, the manufacturer/supplier will submit the quality control data within 30 days. Any change in the product will require a requalification at the manufacturer's/supplier's expense.

#### **Non-Compliance**

- WisDOT will continue to regard this approval valid for 5 years unless/until any of the following conditions arise:
  - If the manufacturer/supplier changes the product physical or chemical properties without notifying WisDOT.
  - The product samples audited/tested by WisDOT do not meet the requirements as specified in this document.
- Manufacturers/suppliers are required as a condition of approval to inform WisDOT of any of the above conditions as soon as they become aware of them.

#### Correspondence

If the name and/or address of the contact person in your company for this correspondence have changed, or if you have questions or need further information, please contact us via email <a href="mailto:DOTProductSubmittal@dot.wi.gov">DOTProductSubmittal@dot.wi.gov</a>.