



Wisconsin Department of Transportation

October 24, 2016

Division of Transportation Systems Development

Bureau of Project Development
4802 Sheboygan Avenue, Rm 601
P O Box 7916
Madison, WI 53707-7916

Telephone: (608) 266-1631
Facsimile (FAX): (608) 266-8459

NOTICE TO ALL CONTRACTORS:

Proposal #13: 1185-02-61, WISC 2016 348
Ashland - Hurley
Ashland County Line to CTH B
USH 2
Iron County

Letting of November 8, 2016

This is Addendum No.01, which provides for the following:

Special Provisions

Revised Special Provisions	
Article No.	Description
14	Seal Coat Special, Item SPV.0180.01

The responsibility for notifying potential subcontractors and suppliers of these changes remains with the prime contractor.

Sincerely,

Mike Coleman

Proposal Development Specialist
Proposal Management Section

ADDENDUM NO. 01

1185-02-61

October 24, 2016

Special Provisions

14. Seal Coat Special, Item SPV.0180.01.

Replace entire article language with the following:

A Description

Construct a seal coat with an applied fog seal as described in standard spec 475 and as hereinafter provided.

B Materials

Furnish polymer-modified asphaltic materials for seal coat conforming to standard spec 455.

Furnish cationic emulsified asphaltic material for fog seal conforming to standard spec 455.

Furnish emulsions diluted during manufacture. Field dilution is not allowed.

Furnish aggregate conforming to standard spec 460 except as follows:

1. Aggregate retained on the No. 8 sieve shall have 5%, by weight, or less flat and elongated pieces based on a 5:1 ratio.
2. The percent wear, measured according to AASHTO T96, shall not exceed 30 after 500 revolutions.
3. At least 70 percent, by count of the aggregate retained on the No. 8 sieve shall have 2 or more fractured faces.
4. Conform to the following gradation:

SIEVE SIZE	PERCENT PASSING BY WEIGHT
3/8 inch (9.51 mm)	100%
No. 4 (4.75 mm)	85-100%
No. 8 (2.38 mm)	5-15%
No. 30 (.595 mm)	0-5%
No. 200 (.074 mm)	0-1.5%

Take all precautions to minimize contamination of the aggregate.

C Construction

Prepare pavement surface to ensure the Seal Coat Special effectively bonds to the pavement.

Select and apply an asphaltic emulsion at a rate and formulation to ensure an adequate bond between the existing roadway surface and the aggregate.

Apply the aggregates at a rate to ensure complete and uniform coverage of the roadway.

Apply adequate aggregate coverage at all intersections and at commercial and private entrances to prevent tracking of the asphalt.

Broom all seal coated pavements in the rural area prior to opening to through traffic, including paved shoulders, paved private entrances, and intersecting highways.

Damage to the Seal Coat Special caused by construction equipment and traffic shall be corrected at the contractor's expense.

Select and apply a cationic emulsion as fog seal over the completed and broomed seal coat at a residual rate of 0.05 to 0.20 gallons/square yard providing a uniform application of asphalt emulsion. Minimize the amount of overspray during the fog seal operation.

Do not allow traffic on the fog sealed surface until the asphalt material has set and will not track on vehicle tires.

Reestablish pavement markings lost due to maintenance for the paving period.

C.1 Acceptance

All work will be inspected by the department before opening the completed Seal Coat Special to traffic, 1 month after opening to traffic, and after the first winter following construction. Any area exhibiting loss of aggregate will be repaired as directed under the Maintenance section of this provision, once weather conditions specified in standard spec 475 permit.

C.2 Maintenance

Maintain the work until the final inspection. Repair damage and correct areas with loss of asphaltic material or aggregate. Removal of substandard Seal Coat Special and reapplication of Seal Coat Special if required is considered maintenance. Snow plow damage to the Seal Coat Special at tented transverse joints is not the responsibility of the contractor.

D Measurement

The department will measure Seal Coat Special by the square yard, acceptably completed.

E Payment

The department will pay for measured quantities at the contract unit price under the following bid item:

ITEM NUMBER	DESCRIPTION	UNIT
SPV.0180.01	Seal Coat Special	SY

Payment is full compensation for providing aggregate and emulsified asphaltic materials for seal coat and fog seal; for preparing, and applying all materials; and for furnishing all maintenance including traffic control, and for the reestablishment of pavement markings lost due to maintenance for the proving period.

END OF ADDENDUM